Martijn Tibbe

Improving organ on-chip physiology

*Exploring the barrier in **blood**-brain
barrier on-chip systems*

Improving Organ on-Chip Physiology

Exploring the barrier in blood-brain barrier on-chip
systems

Martijn Tibbe

Improving Organ on-Chip Physiology

Exploring the barrier in blood-brain barrier on-chip
systems

DISSERTATION

to obtain
the degree of doctor at the University of Twente,
on the authority of the rector magnificus,
Prof. dr. T. T. M. Palstra,
on account of the decision of the Doctorate Board,
to be publicly defended
on Friday the 31st of January 2020 at 14:45

by

Martijn Peter Tibbe
born on the 4th of August 1988
in Hengelo, The Netherlands

This dissertation has been approved by:

Prof. dr. ir. A. van den Berg
Prof. dr. ir. L.I. Segerink
Dr. ir. A.M. Leferink

Promotor
Promotor
Co-promotor

Cover design: Annemarie Tibbe and Nienke van Dongen

Printed by: Gildeprint, Enschede, the Netherlands

ISBN: 978-90-365-4930-1

DOI: 10.3990/1.9789036549301

URL: <https://doi.org/10.3990/10.3990/1.9789036549301>

© 2020 Enschede, The Netherlands. All rights reserved. No parts of this thesis may be reproduced, stored in a retrieval system or transmitted in any form or by any means without permission of the author. Alle rechten voorbehouden. Niets uit deze uitgave mag worden vermenigvuldigd, in enige vorm of op enige wijze, zonder voorafgaande schriftelijke toestemming van de auteur.

Graduation Committee:

Chairman:

Prof. dr. J. N. Kok

University of Twente

Promoters:

Prof. dr. ir. A. van den Berg

University of Twente

Prof. dr. ir. L.I. Segerink

University of Twente

Co-promotor:

Dr. ir. A.M. Leferink

University of Twente

Committee Members:

Dr. B.M. Maoz

Tel Aviv University

Prof. dr. ir. P.M. Sarro

Technical University Delft

Dr. G. Luurtsema

University of Groningen

Prof. dr. D. Stamatialis

University of Twente

Prof. dr. ir. R.G.H. Lammertink

University of Twente

Dr. A.D. van der Meer

University of Twente

The research described in this thesis was conducted at the BIOS Lab-on-a-Chip Group of the MESA+ Institute for Nanotechnology, Max Planck Center for Complex Fluid Dynamics, University of Twente, Enschede, The Netherlands. The research was supported by the ERC advanced grant VESCEL (grant no. 669768) of Albert van den Berg.

Table of contents

Chapter 1: Introduction and outline	11
1.1 Membranes in organ on-chip systems	13
1.2 Thesis outline	16
1.3 ERC advanced VESCEL	17
1.4 References	17
Chapter 2: Membranes for organs-on-chips	21
2.1 Organs-on-chips	23
2.1.1 Lung on-chip	23
2.1.2 Gut on-chip	25
2.1.3 Blood-brain barrier on-chip	26
2.2 Membrane properties	30
2.3 Reflection and Outlook	32
2.3.1 Membrane morphology: 2D vs. 3D.	32
2.3.2 Membrane topography	34
2.3.3 Biochemical functionalization	34
2.3.4 Temporary membranes	36
2.3.5 The future of OOC research	37
2.4 References	37
Chapter 3: Transwell integrated porous, thin PDMS membranes as alternative cell culture platform	41
3.1 Introduction	43
3.2 Materials and Methods	46
3.2.1 Membrane fabrication	46
3.2.2 Cell seeding and staining	47
3.2.3 Scanning electron microscopy of cell samples	49
3.2.4 Permeability measurement	49
3.3 Results and Discussion	51
3.4 Conclusion and Outlook	58
3.5 References	60
Chapter 4: Three-dimensional semi-circular microvascular blood-brain barriers on-chip using hyaluronic acid based hydrogels	63
4.1 Introduction	65
4.2 Materials and Methods	67
4.2.1 Device design and fabrication	67
4.2.2 Hydrogel chip fabrication	68
4.2.3 Hydrogel chip validation	69
4.2.4 Cell viability and morphology on HA-based hydrogels	71
4.3 Results and Discussion	72
4.3.1 Hydrogel chip optimization	72
4.3.2 Cell culture on HA-based hydrogels	76
4.4 Conclusion and Outlook	78

4.5 References	80
Chapter 5: Impedance spectroscopy in a semi-circular blood-brain barrier on-chip to assess barrier properties	83
5.1 Introduction	85
5.2 Materials and Methods	87
5.2.1 Device design and fabrication	87
5.2.2 Electrical simulations	89
5.2.3 Impedance spectroscopy measurements	90
5.2.4 Cell culture and immunofluorescence	91
5.3 Results and Discussion	93
5.3.1 Electrical simulations	93
5.3.2 Impedance spectroscopy	95
5.3.3 Varying extracellular and intracellular calcium concentration	98
5.3.4 The effect of vitamin C on the endothelium	100
5.3.5 The effect of astrocyte-conditioned medium on the endothelium	102
5.3.6 Endothelial exhibits <i>in vivo</i> -like TEER values	102
5.3.7 General considerations	103
5.4 Conclusion and Outlook	104
5.5 References	105
Chapter 6: Microfluidic gel patterning by use of a temporary membrane	109
6.1 Introduction	111
6.2 Materials and Methods	113
6.2.1 Device design and fabrication	113
6.2.2 Chitosan preparation	113
6.2.3 Cell seeding and staining	114
6.3 Results and Discussion	115
6.4 Conclusion and Outlook	123
6.5 References	124
Chapter 7: Endothelial cell-sheets as a replacement for non-physiological membranes in organs-on-chips	127
7.1 Introduction	129
7.2 Materials and Methods	131
7.2.1 Cell sheet formation	131
7.2.2 Cell sheet transfer	132
7.2.3 Cell sheet analysis	134
7.3 Results and Discussion	136
7.4 Conclusion and Outlook	140
7.5 References	141
Chapter 8: Summary and outlook	143
8.1 Summary	145
8.2 Outlook	148
8.2.1 Material choice	148
8.2.2 Readout methods	149

8.2.3 Membrane: yes or no?	150
8.3 References	151
Appendix: Supplementary information and figures	153
Appendix A: Supplementary information Chapter 3	155
Appendix B: Supplementary information Chapter 5	158
Appendix C: Supplementary information Chapter 6	164
Appendix D: Supplementary information Chapter 7	165
Scientific output	166
Journal articles	166
Conference contributions	166
Samenvatting	168
Funding and Contributions	172
Dankwoord	174
Biography	177

1

Introduction and outline

In this introduction, the importance of recreating organ tissues on microfluidic chips is described followed by an explanation of the essence of this thesis being the improvement of current organ on-chip (OOC) systems. Although membranes are considered a crucial element in in vivo barriers, in OOC systems they have not been given a lot of attention in previous work. Therefore, several approaches to replace or remove these membranes to create more physiological relevant OOC systems are explored and described in this thesis.

1.1 Membranes in organ on-chip systems

Over the last decades, animal models are considered the gold standard when it comes to disease modelling and drug testing. However, since these models are ethically questionable and they do not provide a proper physiological representation of the human body, a vast body of research has been conducted on *in vitro* cell culture systems to study specific tissues of the human body^{1,2}. The first systems used were traditional two-dimensional (2D) mono- and co-cultures in cell culture dishes and in Transwell systems³. These 2D systems evolved into three-dimensional systems such as organoids and tissue constructs^{4,5}. With the development of microfluidic systems, the field of *in vitro* cell culture took a turn towards so-called organ on-chip (OOC) systems⁶⁻⁹. Cells are cultured inside microchannels under realistic flow conditions, which ensures nutrient supply, waste removal and mechanical forces such as shear stress to the cells. OOC systems are portable, cheap to fabricate, reproducible and due to the small sample volumes, very cost effective and present an interesting alternative to animal testing which explains the growing interest for such systems from various industries. So far, multiple organs such as the lung^{10,11}, the gut^{12,13} and the blood-brain barrier (BBB)¹⁴⁻¹⁸ have been recreated on-chip. A large class of these OOC barrier systems consist of two channels separated by a porous membrane. One channel represents the luminal side of an organ, whereas the other channel represents the basolateral side. The goal of these systems is to study the interaction between both sides and transport from one side to the other. The used polymer membranes¹⁹⁻²³ are often relatively thick compared to the thin barrier that separates cells *in vivo* (Figure 1)^{24,25}. As can be seen in Figure 1, the membrane is visualized schematically as a thin layer in between two cell types, whereas it is actually a few micrometer thick barrier between the cells.

FIGURE 1 SCHEMATIC IMAGE OF HOW THE BARRIER IN AN ORGAN ON-CHIP IS OFTEN REPRESENTED IN LITERATURE COMPARED TO THE REALISTIC DIMENSIONS AND THE *IN VIVO* SITUATION.

Introducing a large distance between adjacent channels in a co-culture situation increases the diffusion distance and time as well as the ability of cells to physically and mechanically interact with each other through direct cell-cell contact. Furthermore, these membranes often do not have the optimal mechanical properties that match the tissue to be replicated. Therefore, a membrane-free, physiologically relevant system that resembles the shape and structure of vasculature, would be preferable and has thus far been developed by several people ^{15, 18, 26-28}. However, in their OOC systems, due to design limitations it has not been possible to monitor the state of the cell layer in real-time by use of, for example, trans-endothelial electrical resistance (TEER) which is an indicator of cell layer integrity ^{29, 30}. Systems that contain a membrane allow for the integration of electrodes inside the system to be able to measure TEER in real-time. As reported so far, membrane-free systems make use of a hydrogel barrier to create a cell-gel interface. Although such an approach could be considered 'elegant' with respect to physiological representation of the extracellular matrix (ECM), so far this approach did not allow for the measurement of the electrical resistance over the cellular layer from the basal to luminal side.

In this thesis we focus on the BBB, which acts as a gatekeeper for the brain where it prevents harmful substances from entering ³¹. The barrier consists of a luminal side; formed by brain endothelial cells, tightly packed together by interconnecting tight junctions; and a basolateral side, which consists of multiple cells such as astrocytes, pericytes and other glial cells. The luminal side is separated from the basolateral side by a basement membrane which is only a few (~20-200) nanometres thin. As drugs do not pass the barrier easily *in vivo*, understanding its functionality is crucial. Therefore, attempts have been made to recreate this complex barrier *in vitro* ^{17, 18, 32, 33}. Comparable to other OOC systems, BBB on-chip systems are often two-channel systems which contain a relatively thick (10 μm) polymer membrane for cell separation. However, the cell-cell interaction between brain endothelial cells and astrocytes is thought to be crucial for the development of a tight BBB ^{26, 34, 35}.

To enable cell-cell contact between the basal and luminal side of the barrier two different approaches of recreating a BBB on-chip are being described in this thesis. The first being the replacement of the currently used, 10 μm thick, Transwell membranes with a random pore distribution by a thinner membrane with controlled pore dimensions and organization. The second

approach is to entirely remove the membrane to create a cell-gel interface. For both approaches, one or more systems were developed to see whether these systems are suitable for the desired application.

1.2 Thesis outline

The importance of membranes in OOC systems is being described in **Chapter 2**. This review chapter gives an overview of the currently used membranes with their benefits and shortcomings. In **Chapter 3**, the application of an alternative membrane in a Transwell-like cell culture set-up is reported. The alternative in-house developed porous polydimethylsiloxane (PDMS) membrane is almost a 5-fold thinner compared to the traditional polycarbonate (PC) and polyethylene Transwell membranes. During the cell culture experiments, the effect of the PDMS membranes on brain endothelial cell culture is studied and compared to culture on PC membranes. In **Chapter 4**, the development of a hydrogel chip is described as an approach to obtain a membrane-free OOC systems that allows for more realistic cell-cell contact. To increase the physiological relevance of the chip for BBB research, a hyaluronic acid hydrogel is applied. To study the integrity of a cell layer inside a semi-circular hydrogel chip, a measurement set-up is developed in **Chapter 5**. This impedance measurement set-up allows for real-time measurement of resistance of the cells cultured inside a semi-circular channel. Preliminary impedance measurements were conducted, these were however not trustworthy and have to be repeated. To show the applicability of the impedance measurement set-up, cells were seeded into the channel to form a vessel. Dose response experiments were conducted using vitamin-C and astrocyte conditioned media to study the influence on the tightness of the brain endothelial cells. Adding a calcium chelator to the endothelial cells led to a decrease in ZO-1 localization as a result of a decreased amount of tight junctions. Another membrane-free BBB on-chip system was developed by making use of laminar flow in a microfluidic chip to initiate a chemical reaction on-chip which is described in **Chapter 6**. This chemical reaction leads to the formation of a temporary membrane on-chip. As the reaction is reversible, the membrane can be removed easily after patterning a gel inside one of the two used channels. An interesting tissue engineering technique, cell sheet engineering, is reported in **Chapter 7**. This technique makes use of the thermoresponsive polymer poly-N(isopropyl acrylamide) to harvest intact cell sheets. As a proof of concept we applied this technique to transfer a sheet of

brain endothelial cells from one system to another. In the future, this method might be used to replace the polymer membrane in an OOC system with an intact cell sheet. Finally, in **Chapter 8**, a general discussion of the results from this thesis and future perspectives are given.

1.3 ERC advanced VESCEL

This research was financed by the ERC advanced grant “VESCEL” (Grant no. 669768) which was granted to prof. dr. ir. Albert van den Berg. The VESCEL project has the goal to develop and improve the growth of vascular tissue on-chip. Therefore, six separate projects were initiated which all have their own contribution towards a better, more physiologically relevant representation of on-chip vasculature. This specific project, which focused on the membrane in an OOC system, contributes to the improvement of the physiological character of the luminal-basolateral barrier in a BBB on-chip. We are very grateful to the European Research Council for providing us with the opportunity to conduct this research.

1.4 References

1. M. E. Furth and A. Atala, in *Principles of Tissue Engineering (Fourth Edition)*, eds. R. Lanza, R. Langer and J. Vacanti, Academic Press, Boston, 2014, pp. 83-123.
2. K. Duval, H. Grover, L.-H. Han, Y. Mou, A. F. Pegoraro, J. Fredberg and Z. Chen, *Physiology (Bethesda)*, 2017, **32**, 266-277.
3. K. Hatherell, P.-O. Couraud, I. A. Romero, B. Weksler and G. J. Pilkington, *Journal of Neuroscience Methods*, 2011, **199**, 223-229.
4. M. A. Lancaster and J. A. Knoblich, *Science*, 2014, **345**, 1247125.
5. D. Dutta, I. Heo and H. Clevers, *Trends in Molecular Medicine*, 2017, **23**, 393-410.
6. S. N. Bhatia and D. E. Ingber, *Nature Biotechnology*, 2014, **32**, 760-772.
7. E. W. Esch, A. Bahinski and D. Huh, *Nature Reviews Drug Discovery*, 2015, **14**, 248-260.
8. D. Huh, H. J. Kim, J. P. Fraser, D. E. Shea, M. Khan, A. Bahinski, G. A. Hamilton and D. E. Ingber, *Nature Protocols*, 2013, **8**, 2135.
9. D. Huh, G. A. Hamilton and D. E. Ingber, *Trends in Cell Biology*, 2011, **21**, 745-754.
10. D. Huh, B. D. Matthews, A. Mammoto, M. Montoya-Zavala, H. Y. Hsin and D. E. Ingber, *Science*, 2010, **328**, 1662-1668.
11. D. D. Huh, *Annals of the American Thoracic Society*, 2015, **12 Suppl 1**, S42-S44.
12. H. J. Kim, D. Huh, G. Hamilton and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2165-2174.

13. H. J. Kim and D. E. Ingber, *Integrative Biology*, 2013, **5**, 1130-1140.
14. L. M. Griep, F. Wolbers, B. Wagenaar, P. M. Braak, B. B. Weksler, I. A. Romero, P. O. Couraud, I. Vermes, A. D. Meer and A. Berg, *Biomedical Microdevices*, 2012, **15**, 145-150.
15. H. Cho, J. H. Seo, K. H. K. Wong, Y. Terasaki, J. Park, K. Bong, K. Arai, E. H. Lo and D. Irimia, *Scientific Reports*, 2015, **5**, 15222.
16. R. Booth and H. Kim, *Lab on a Chip*, 2012, **12**, 1784-1792.
17. J. H. Yeon, D. Na, K. Choi, S.-W. Ryu, C. Choi and J.-K. Park, *Biomedical Microdevices*, 2012, **14**, 1141-1148.
18. J. A. Kim, H. N. Kim, S.-K. Im, S. Chung, J. Y. Kang and N. Choi, *Biomicrofluidics*, 2015, **9**, 024115-024115.
19. D. Huh, Y.-s. Torisawa, G. A. Hamilton, H. J. Kim and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2156-2164.
20. A. O. Stucki, J. D. Stucki, S. R. R. Hall, M. Felder, Y. Mermoud, R. A. Schmid, T. Geiser and O. T. Guenat, *Lab on a Chip*, 2015, **15**, 1302-1310.
21. J. A. Brown, S. G. Codreanu, M. Shi, S. D. Sherrod, D. A. Markov, M. D. Neely, C. M. Britt, O. S. Hoilett, R. S. Reiserer, P. C. Samson, L. J. McCawley, D. J. Webb, A. B. Bowman, J. A. McLean and J. P. Wikswo, *J Neuroinflammation*, 2016, **13**, 306-306.
22. D. Gao, H. Liu, J.-M. Lin, Y. Wang and Y. Jiang, *Lab on a Chip*, 2013, **13**, 978-985.
23. B. M. Maoz, A. Herland, O. Y. F. Henry, W. D. Leineweber, M. Yadid, J. Doyle, R. Mannix, V. J. Kujala, E. A. FitzGerald, K. K. Parker and D. E. Ingber, *Lab on a Chip*, 2017, **17**, 2294-2302.
24. M. S. Thomsen, L. J. Routhe and T. Moos, *J Cereb Blood Flow Metab*, 2017, **37**, 3300-3317.
25. R. Jayadev and D. R. Sherwood, *Current Biology*, 2017, **27**, R207-R211.
26. A. Herland, A. D. van der Meer, E. A. FitzGerald, T.-E. Park, J. J. F. Sleeboom and D. E. Ingber, *PLOS ONE*, 2016, **11**, e0150360.
27. J. Nie, Q. Gao, Y. Wang, J. Zeng, H. Zhao, Y. Sun, J. Shen, H. Ramezani, Z. Fu, Z. Liu, M. Xiang, J. Fu, P. Zhao, W. Chen and Y. He, *Small*, 2018, **14**, 1802368.
28. L.-Y. Jiang and Y. Luo, *Soft Matter*, 2013, **9**, 1113-1121.
29. O. Y. F. Henry, R. Villenave, M. J. Cronce, W. D. Leineweber, M. A. Benz and D. E. Ingber, *Lab on a Chip*, 2017, **17**, 2264-2271.
30. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
31. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
32. D. T. Phan, R. H. F. Bender, J. W. Andrejcsk, A. Sobrino, S. J. Hachey, S. C. George and C. C. Hughes, *Experimental biology and medicine (Maywood, N.J.)*, 2017, **242**, 1669-1678.
33. R. Booth and H. Kim, *Annals of Biomedical Engineering*, 2014, **42**, 2379-2391.
34. N. J. Abbott, L. Rönnbäck and E. Hansson, *Nature Reviews Neuroscience*, 2006, **7**, 41.

35. J. A. Holash, D. M. Noden and P. A. Stewart, *Developmental Dynamics*, 1993, **197**, 14-25.

Membranes for organs-on-chips

In the field of organs-on-chips, “barrier-type” systems form an important class. In these “barrier-type” systems, membranes are applied to separate adjacent cell culture compartments. Besides separation of different cell types, this physical layer also supports cell adherence and separates different cell types from each other. In this chapter, the role of the membrane in current organ-on-chip systems is discussed. Furthermore, an overview of membrane fabrication methods and membrane characteristics is given.

This chapter is adapted from:

Membranes for organs-on-chips

M. P. Tibbe, A. D. v. d. Meer, A. v. d. Berg, D. Stamatialis and L. I. Segerink

Biomedical Membranes and (Bio)Artificial Organs, WORLD SCIENTIFIC, 2017, pp. 295-321.

2.1 Organs-on-chips

The first organ-on-chip (OOC) models were only comprised of one cell type cultured in a microfluidic channel. By introducing a porous membrane that separates two parallel placed microchannels, it is possible to culture multiple tissue types, simultaneously, in one compartmentalized chip. Current OOC models are compartmentalized systems containing microfluidic channels, often separated by a (porous) membrane, with on either side a cell layer of different cell types. Sensors can be included in these chips for *in situ* measurements. The compartments can be individually addressed to regulate fluid flow resulting in physiological relevant shear stresses to which the tissues are exposed. In the following sections, the function of the membrane in a number of OOC systems is described in more detail, highlighting the benefits and crucial role that membranes have in this technology ¹.

2.1.1 Lung on-chip

The lung consists of millions of alveoli surrounded by capillaries. Transporting oxygen from inhaled air to the blood stream is, together with the removal of carbon-dioxide, one of the main functions of the lung carried out by these alveoli-capillary interfaces. When engineering the capillary oxygen uptake from air on- chip, recreating this interface is crucial. Huh *et al.* developed a compartmentalized system comprised of two parallel polydimethylsiloxane (PDMS) channels separated by a porous, 10 μm thick PDMS membrane (pore size 0.4 μm) in which both human pulmonary microvascular endothelial and human alveolar epithelial cell lines can be cultured simultaneously to mimic the interface. Microdevices were made by soft lithography. Prior to cell culture, the PDMS microchannels were coated with an extra-cellular matrix (ECM) based coating to promote cell attachment. ²

Besides mimicking the cell-cell interface, a lung on-chip system has to very well mimic the mechanical forces present in the organ. When a lung inhales, alveoli expand, increasing the surface area over which oxygen can pass the interface. During this mechanical stretching and relaxing, epithelial and endothelial cells undergo mechanical stress which induces changes to the paracellular transport, resulting in a change of permeability of the endothelial cell layer. In the system of Huh *et al.*, this movement is mimicked by adding, parallel to the microfluidics channels and separated by a 10 μm thin PDMS layer, two air filled chambers (Figure 1).

FIGURE 1 LUNG ON-CHIP MODEL BY HUH *ET AL.* (A) CHIP DESIGN IN WHICH TWO CELL TYPES, NAMELY ENDOTHELIAL CELLS AND EPITHELIUM CELLS, ARE CO-CULTURED ONTO A POROUS PDMS MEMBRANE. BY APPLYING A VACUUM IN THE SIDE CHAMBERS, THE MEMBRANE IS STRETCHED, CAUSING A STRETCHING MOVEMENT IN THE ATTACHING CELLS. (B) INHALATION IN AN *IN VIVO* LUNG BY EXPANSION OF THE ALVEOLI. (C) CONSTRUCTION OF THE DEVICE BY IRREVERSIBLE BINDING A PDMS MEMBRANE BETWEEN TWO PIECES OF PDMS (SCALE BAR IS 200 μM) (FROM ². REPRINTED WITH PERMISSION FROM AAAS.)

By applying a vacuum in these chambers, both adherent cell layers are stretched as they do during *in vivo* inspiration. By introducing mechanical stress, together with controlled fluid flow, Huh *et al.* were able to study the whole-organ response of a lung. In the lung on-chip system by Huh *et al.*, the porous PDMS membrane does not only function as a barrier between two tissue types, but it also functions as a flexible substrate through which mechanical strain is transferred to the attached tissue ². Stretching of the membrane induces mechanotransduction in the attached cells, leading to cytoskeletal reorganization which influences the behavior of the cells. By looking at the pulmonary inflammation reaction caused by immune cells, which can be introduced into the vascular channel, they concluded that the cells function as they would do *in vivo*. Studying such immune response *in vitro* is not possible in multi tissue set-ups, such as the Transwell® systems, since those are static. When using a porous membrane, there is a possibility to study the permeability of the cell-layers, this is however limited by the pore size of the membrane. Results show that the cellular oxidative stress response,

induced by nanoparticles, is increased by a factor of more than four when strain is applied to the cells ^{2,3}.

2.1.2 Gut on-chip

Chronic intestinal disorders such as ulcerative colitis and Crohn's disease are lacking proper medicinal treatment. To test new drugs, a physiological relevant intestinal system has to be created. The difficulty of recreating such a system lies with culturing living microbes on the luminal side of the epithelium. These, so called microbial symbionts, have a major contribution to the barrier function of the intestinal epithelium layer ^{4, 5}. To study these microbial symbionts and the influence of drugs on the intestinal system, *in vitro* systems are being developed. Simple two-dimensional (2D) and three-dimensional (3D) studies, such as Transwell® and polymeric scaffold systems, cannot mimic the physiological relevant shear stress and stretch that the cells experience in the gut as a result of fluid flow and peristalsis ⁶⁻⁸. In these systems it is also challenging to keep the microbes alive for longer periods of time. By using OOC technology, researchers have tried to recreate the intestinal microenvironment on a microfluidic chip. Such a system provides a platform for tissue culture, as well, as for the introduction of the proper mechanical cues to the tissue.

Kim *et al.* developed a gut on-chip system by culturing gut epithelium cells under physiological relevant conditions. Similar to the chip designed by Huh *et al.* (Figure 1), this PDMS chip consists of two microfluidic channels separated by a porous, 30 µm thin, PDMS membrane (pore size 10 µm). On both sides of the channels, vacuum chambers were used to create peristaltic movement of the membrane. When cells were attached to the membrane, a 10% width increase was achieved mimicking the mechanical microenvironment in a more realistic matter. For this gut on-chip system, cells of the human colorectal carcinoma line (Caco-2) were used to recreate the epithelial cell layer present in the intestinal tract ⁹. Cells became larger in size when a mechanical strain, which increases the membrane width by 30%, was applied. The cells produced a similar amount of strain compared to the membrane as a function of the pressure applied in the vacuum chambers. Further research on this gut on-chip system shows that gut epithelial cells that are continuously exposed to mechanical cues such as shear stress and mechanical strain form villi that express organ specific characteristics ¹⁰.

Whereas Kim *et al.* used a two-channel microfluidic device to recreate a gut on-chip ⁹, Gümüşcü *et al.* developed a microfluidic chip in which hydrogel arrays were patterned in closed microchips (Figure 2). By using these, so called hydrogel pockets as 3D scaffolds for culturing intestinal epithelium, a multiplexed platform was created in which each pocket resembles a part of the intestinal lumen. The use of hydrogels allows for co-culturing multiple cell types without the need of a physical membrane. The 3D architecture of the hydrogel guides the cells towards the formation of distinct intestinal morphologies such as villi and tube structures, similar to physiological structure formation observed by Kim *et al.* ^{10, 11}.

FIGURE 2 GUT ON-CHIP SYSTEM BY GÜMÜSCÜ *ET AL.* USING CAPILLARY PINNING TO OBTAIN HYDROGEL POCKETS IN WHICH CELLS CAN BE CULTURED. (A) PHOTOGRAPH OF THE USED MICROFLUIDIC CHIP. (B) OPTICAL MICROSCOPY IMAGE OF THE CHIP, SHOWING THE PDMS PILLARS IN GREY AND THE CAPTURED HYDROGEL IN BLUE. (C) CACO-2 CELLS ARE CULTURED WITHIN THE HYDROGEL, WHEREAS CULTURE MEDIUM IS FLUSHED THROUGH THE MICROCHANNELS TO SUPPLY THE CELLS WITH NUTRIENTS. (D) SCHEMATIC OVERVIEW OF THE MICROFLUIDIC CHIP. (E) SCHEMATIC ILLUSTRATION OF THE CHIP SHOWING THE PDMS PILLARS AND THE PDMS CAPILLARY BARRIERS THAT PIN THE HYDROGEL. (ADAPTED FROM ¹¹.)

2.1.3 Blood-brain barrier on-chip

In the mammalian body, there is a barrier between the central nervous system (CNS) and the circulatory system. This barrier present in the brain is called the blood-brain barrier (BBB) and was first discovered by Paul Ehrlich in 1885 ¹². There are a few barrier functions for which the BBB is responsible, such as the protection of the brain from the extracellular environment and the blockage

and diffusion of specific nutrients. Besides, it also maintains the homeostasis of the CNS ¹³. The BBB is formed by the interactions of multiple cell types and membranes in the context of the neurovascular unit (NVU). One NVU consists of a monolayer of brain microvascular endothelial cells (BMVEC) which are surrounded by a basement membrane and glial cells. The inner endothelial cell layer is surrounded by a basement membrane, which anchors the endothelial cells and pericytes and forms a connection between these cells and the glial cells. Structural and specialized proteins such as collagen, elastin, fibronectin and laminin form, together with proteoglycans, the basement membrane. These ECM proteins are generated and maintained by BMVECs, astrocytes and pericytes within the NVU ¹⁴.

Multiple research institutes have attempted to recreate this complex organ *in vitro*. Standard co-cultures using BMVECs and glial cells were carried out in Transwell® systems. These systems were also used to study passive drug transportation through the endothelial layer ¹⁵. Since flow is necessary to increase the physiological behavior of the endothelial cell layer ¹⁶, OOC technology is used to recreate the BBB on-chip. Most of these systems are comprised again of two parallel microchannels separated by a porous membrane on which different cell types can be cultured. By measuring trans-endothelial electrical resistance (TEER), the tightness of the BMVEC layer can be quantified ¹⁷. Since the resistance can be influenced by the membrane porosity, it is important to have a quantitative control study on the barrier. This can for example be done by staining the tight junction complexes formed between endothelial cells. One of the most abundantly studied tight junction proteins is zonula occludens-1 (ZO-1), which stabilizes tight junction complexes ¹⁸. Therefore, most BBB studies use ZO-1 visualization to quantify the barrier integrity.

One of the first BBB models was produced by Booth and Kim in 2012 ¹⁹. Their model consists of two pieces of PDMS containing microfluidic channels separated by a polycarbonate (PC) membrane (10 μm thick, 0.4 μm pores). They were able to seed a layer of endothelial cells in the top channel, while simultaneously a murine astrocyte cell line was cultured in the other channel. A TEER of 180-280 $\Omega\cdot\text{cm}^2$ was measured, for the endothelial cell layer on the membrane which indicates that the barrier functions as it should. However, note that there is yet no actual TEER value that defines a successful barrier. The measured TEER inside a microfluidic chip depends on multiple factors

such as material properties and the consistence of the used liquids. In 2014 the same research group improved their first model and tested it again for TEER and permeability. This time they found a TEER value of $150 \Omega \cdot \text{cm}^2$ and a permeability coefficient which could be correlated to physiological brain/plasma permeability coefficients ²⁰.

In 2016, van der Helm *et al.* developed a similar system in which two channels, microfabricated in PDMS, are placed perpendicularly on top of each other and the channels are separated by a PC membrane similar to that of Booth and Kim. Due to this smart chip design (Figure 3), it is possible to perform a 4-point TEER measurement, which is much more accurate compared to the traditional 2-point measurement ¹⁷.

Both van der Helm *et al.* and Booth *et al.* use the same PC membrane which is placed horizontally in the chip ^{17, 20}. These membranes are opaque, which makes visual inspection of both channels at the same time very difficult if not impossible when using a bright field microscope. Live cell imaging without having to introduce fluorophores is not possible when using these membranes. TEER and permeability measurements show that the membrane does not have a significant influence on the resistance of the BBB-chip. However, the fact that the chip resembles the function of the BBB, the question rises whether the endothelial cells would form an even better, compacter, barrier if direct contact with astrocytes is initialized. This direct contact can, for example, be achieved by using an alternative membrane or by using a cell-hydrogel system.

FIGURE 3 SCHEMATIC OF THE CHIP DESIGN BY VAN DER HELM *ET AL.* (A) EXPLODED VIEW OF THE CHIP SHOWING ALL THE COMPONENTS WITH IN THE MIDDLE THE POROUS PC MEMBRANE (M) THE TOTAL CULTURE AREA OF THE MEMBRANE SUSPENDED BETWEEN THE TWO CHANNELS IS 0.25 mm^2 . (B) PHOTOGRAPHIC IMAGE OF THE ACTUAL CHIP. (C) SCHEMATIC TOP VIEW OF THE CHIP. (D) SCHEMATIC CROSS-SECTION VIEW OF THE CHIP SHOWING ENDOTHELIAL CELLS (EC) IN THE TOP CHANNEL (TC). NO CELLS ARE PRESENT IN THE BOTTOM CHANNEL (BC). (E) ELECTRODE CIRCUIT OF THE CHIP, WITH ELECTRODES E1 AND E3 IN THE TC AND E2 AND E4 IN THE BC, TOP CHANNEL REPRESENTED BY RESISTORS R1 AND R3, AND THE BOTTOM CHANNEL REPRESENTED BY RESISTORS R2 AND R4. RESISTOR R_m REPRESENTS THE MEMBRANE AND POSSIBLE EC BARRIER. (REPRINTED FROM ¹⁷ WITH PERMISSION FROM ELSEVIER.)

2.2 Membrane properties

Most well-known OOC systems make use of a membrane. The type of material used for the membrane determines its properties such as: elasticity, transparency, biocompatibility and cytocompatibility.

Elasticity is the ability of a material body, deformed by an outer force, to return to its original shape and size when the forces causing the deformation are removed. A body with this ability is said to behave (or respond) elastically. The Young's modulus (E), describes the elastic properties of a material that is deformed in one direction. Soft materials have a low Young's modulus whereas stiff materials have a higher one. Huh *et al.* used an elastic PDMS membrane ($E \approx 5 \text{ MPa}$ ²¹) in their lung on-chip systems. Due to an applied vacuum, the PDMS membrane is stretched and when the vacuum is released, the material returns to its original state ². Stiffer materials such as PC ($E \approx 2 \text{ GPa}$ ²²) are not able to deform equally when exposed to similar forces. Instead of returning to their original state, stiffer materials can break or tear easier upon a certain amount of strain.

Different structural factors influence the transparency of the membrane, such as the thickness, the degree of crosslinking and the porosity. Thicker membranes are less transparent compared to thinner ones of the same material and consistence. When the crosslinking density is high, the opacity of the membrane also increases. To be able to visualize both channels in a two-channel OOC system, the membrane in between the channels should be as transparent as possible to see the cells on both sides of the interface. This is only necessary when the membrane is placed horizontally with respect to the focal plane of the microscope. When used vertically relative to the focal plane, membrane transparency is not necessary and therefore, crosslinking density can be higher to improve the strength of the membrane.

Traditionally, biocompatibility has been related to the effect of the membrane material on the biological system it is in contact with ²³. There should be no adverse biological response resulting from contact of the material with the tissue. In OOC research, membranes are used to separate channels in which multiple cell types can be cultured. As these cells are grown directly onto the membranes, it is necessary that they are made of biocompatible materials. It is

also possible to apply a surface treatment to the membranes so that they become biocompatible.

Apart from the biocompatibility of a material, anchorage dependent cells and tissues need a mechanical interaction with the material surface. Integrins on the cell surface can bind to proteins located at the surface of the membrane. This integrin binding triggers an internal process in the cell, called mechanotransduction. Cells attach to the surface, 'pulling' on it with a certain force which deforms the internal cytoskeletal structure. Deformation leads to phenotypic change, influencing the state of the cells ²⁴. Stiffer materials are more suitable to culture cells from stiff tissues compared to more elastic or softer materials ¹⁶. To keep a cell in its differentiated state, the material stiffness should not induce a change in phenotype with regard to the cell's original phenotype. Therefore, it is necessary to identify the ideal material stiffness for a specific cell type prior to the experiment. In a co-culture system such as an OOC where multiple tissues are involved, it is important to find a balance between the material properties that are suitable for both tissue types. When anchorage dependent cells are used, it is often crucial to apply the proper surface treatment to the membrane material. To culture endothelial cells on a hydrophilic surface, attachment can be induced by applying an ECM-protein coating prior to cell seeding. This coating can, for example, be fibronectin, collagen, laminin or Matrigel™ ^{25, 26}. Furthermore, by applying an O₂ plasma treatment to the chip, the channels and the membrane become hydrophilic, which improves fluid inflow into the channels. Such treatment is especially useful when a viscous hydrogel has to be injected into a chip. Due to hydrophobic recovery, the material should be subjected to plasma treatment within a short period prior to fluid inflow. Cells, however, do not attach well to hydrophilic surfaces. So, when an O₂ plasma treatment is used prior to cell seeding, the channels and the membrane should be coated with the appropriate coating to promote cell attachment.

Surface porosity is a measure for the total pore area of a membrane, thus the total amount of pores per surface area multiplied by the size of a single pore ²⁷. When increasing membrane porosity, the amount of light that can pass the membrane increases too. In OOC systems, having a membrane with a high porosity and a good transparency allows for inspection of both channels at the same time without having to turn the chip over or having to apply fluorophores. Increasing the porosity will also have an influence on the

membrane's electrical resistance. Besides, depending on the pore size, cells might be able to penetrate the membrane pores, blocking electrical signal propagation. However, when the porosity is high, but the pore size small, cell penetration can be avoided and electrical signals can pass easily. In OOC systems, flow of nutrients and cell signaling molecules through the membrane is crucial. Nutrients and small molecules are able to pass membranes with very small pores down to a few nanometers. For some tissue types, communication between tissues separated by a membrane is crucial to function properly. This communication can happen through paracrine signaling, or even through cell-cell contact. For example, in the BBB direct cell-cell contact between brain-endothelial cells and surrounding cells (astrocytes, pericytes, microglia and neurons) is thought to be essential for maintenance of the barrier ²⁸. To achieve this cell-cell contact, the pores of the used membrane should be large enough for cells to contact the opposite site directly.

Casillo *et al.* showed that pore size and spacing have an influence on cell-substrate and cell-cell interactions. Human umbilical vein endothelial cells (HUVECs) were cultured on silicon dioxide (SiO₂) membranes with different pore sizes (0.5 μm and 3 μm). Cells grown on membranes with small pore sizes express a similar behavior compared to cells cultured on soft PDMS surfaces. The amount of focal adhesions on membranes with 0.5 μm pores was significantly lower than for cells cultured on membranes with 3 μm pores. When the cells were not able to form proper cell-substrate interactions, the cell-cell interactions increased ²⁹.

2.3 Reflection and Outlook

Although the so far developed OOC systems function properly, the rapidly emerging field of OOC still holds a lot of room for improvement. Making these systems more physiologically relevant will improve experimental output for which these systems are intended. To achieve more realistic systems, structural and mechanical adjustments have to be made to the chips and especially to the membranes.

2.3.1 Membrane morphology: 2D vs. 3D

All organs have specific morphologies, from the macroscale to the microscale, all the way down to the nanoscale. When recreating the tissue microenvironment in an OOC, the organ morphology plays a crucial role in the

functionality of the system. All systems described here, consist of a planar membrane on which tissues and cells are cultured. Such a planar interface is almost nowhere to be found in the human body. Lungs consist of alveoli, which are spherical shaped balloon-like structures that regulate, among others, the uptake of O_2 into the bloodstream. In their model, Huh *et al.* did not recreate the curvature to which lung endothelial cells are exposed in actual alveoli. This curvature can influence the compactness and the permeability of the lung epithelial cell layer and thus the uptake of factors, such as CO_2 , O_2 or medication, from the blood side.

The influence of cellular compactness is highly relevant for the endothelial cells used to recreate the BBB on-chip as it is known that the BBB contains a higher degree of tight junctions compared to other cell barriers. When recreating a brain capillary on-chip, the curvature of the membrane on which endothelial cells are cultured should, in the ideal case, be mimicking the curvature of a brain capillary. As is the case for the BBB and the lung on-chip, as it exists now, the gut on-chip also contains a planar membrane. However as mentioned previously, Kim *et al.* managed to create a gut on-chip in which epithelial cells form their own specific villi structures due to peristalsis and the shear stress caused by fluid flow ¹⁰.

Creation of 3D membranes can be done using various methods including hot embossing ³⁰, thermoforming ^{31, 32} and/or phase separation micromolding ³³. Using hot embossing, it is challenging to obtain membranes that are thin enough ($< 10 \mu m$) to allow for cell-cell contact. There, the polymer is heated up to its glass transition temperature which allows for the material to be molded into the desired shape. Depending on the original pore size and porosity of the membrane, it is possible that the pores become larger or smaller during the embossing process ³⁰. Similar to hot embossing, thermoforming makes use of the thermoresponsive behavior of the used material. The thermoplastic polymer can be shaped by 3D-stretching into the desired shape ³². Depending on the microfabrication method the choice of materials may be limited as a limited amount of materials is suitable to be molded into the desired shape. Technologies such as etching and lithography mostly use silicon-like materials, whereas polymers are being used in soft lithography processes ³⁴.

Another method to create a surface topography in a controlled way is phase separation micromolding ³⁴. A dissolved polymer film is casted onto a mold

after which phase separation takes place, solidifying the polymer (Figure 4). This can either be liquid- or thermally induced phase separation. Phase separation micromolding allows for molding of a variety of polymers including block copolymers and biodegradable polymers. When the features of the mold are high enough to perforate the polymer film, it is possible to create an open structure which has potential to be applied as a membrane in OOC systems ^{35, 36}.

2.3.2 Membrane topography

Apart from the microstructure of the membrane, surface texture can also be adjusted. This texture can vary from a nanometer size roughness up to patterned microstructures. By patterning of the membrane surface with micrometer sized features, cells can reorganize their cytoskeleton upon cell attachment. It has been shown that this rearrangement as a consequence of cells attaching to nano- and microtopographical patterned surfaces, influences stem cell differentiation and cell fate ³⁷. Cell lines can be kept in their differentiated state more easily when the surface directs the cells to adapt a certain phenotype ³⁸. Cell patterning has been used to create aligned and higher-order tissues in for example heart-on-chip devices. For example, in the heart-on-chip model of Zhang *et al.* a PDMS mold is made by lithography after which a gel is imprinted transferring micrometer sized features onto the surface ³⁹. Just like membrane morphology, thermoforming or hot embossing can be used to pattern a surface. The “topochip”, developed by Unadkat *et al.*, is made by hot embossing a poly-lactic acid (PLA) film. A mathematical algorithm was developed to create random surface topographies on a polymer sheet to study the cellular interaction with these topographies ⁴⁰. Differences in cell morphology and mechanics are a result of surface stiffness in combination with the area, and thus the topography, to which a cell is constrained ⁴¹. Therefore, designing the used membrane in such a way that the cells keep their organ specific phenotype is highly preferable.

2.3.3 Biochemical functionalization

There are multiple cell adhesive polymers, such as PLA, polytrimethyl carbonate (PTMC) and polycaprolactone (PCL) that are used for biomedical applications ^{42,43}. Although these materials are presently not being used in OOC systems, they offer the opportunity to be used as membrane materials in the future as they are suitable for membrane production processes such as

thermoforming and phase separation micromolding. Currently used materials for membranes have to undergo biochemical functionalization to become bioactive. Membranes can, for example, be functionalized by covalently binding cell adhesive groups to the chemical structure. Arginyglycylaspartic acid (RGD) is a peptide that is often incorporated into the polymer structure to induce cell attachment by offering a recognition sequence for integrins ⁴⁴.

Phase Separation Micro Molding (PS_μM)

FIGURE 4 SCHEMATIC OF LIQUID INDUCED PHASE SEPARATION MICROMOLDING PROCESS. (1) FIRST, A DISSOLVED POLYMER IS CASTED ONTO A STRUCTURED MOLD. (2) BY PLACING THE POLYMER INTO A NON-SOLVENT SOLUTION, PHASE INVERSION TAKES PLACE. (3) THE POLYMER PRECIPITATES, REPLICATING THE MOLDS STRUCTURE. (4) DUE TO SHRINKAGE OF THE CREATED POLYMER FILM, IT IS RELEASED FROM THE MOULD. (REPRODUCED FROM ³⁵ WITH PERMISSION OF THE ROYAL SOCIETY OF CHEMISTRY.)

Commercially available membranes are often not chemically modified and only support cell attachment after surface treatment. An ECM-coating, which provides cell-attachment factors, can be self-assembled onto the membrane and on the surface of the microfluidic channels inside the chip. ECM factors that induce ECM production can also be included into the membrane as factors that are secreted over time.

2.3.4 Temporary membranes

To be able to create a system without any additional factors that may influence the possible outcome of the cell culture process, temporary membranes should be used. There is a wide range of polymers that hydrolytically degrade over time. A commonly used material in tissue engineering, PLA, has a degradation time of weeks up to months under cell culture conditions ^{45,46}, which is too long for OOC research. PC is another frequently used membrane material which does not degrade at all. Till date, it seems challenging to keep tissue cultures alive for longer periods in a microfluidic system and therefore, OOC systems are used for short term experiments and drug testing. The process of creating a membrane-free system by degradation of the polymer membrane can be time consuming and therefore, fully or partially removable membranes are preferred. Some polymers possess the ability to be degraded enzymatically. By flowing an enzyme solution over the membrane, it can be degraded faster ⁴⁷. This way, a co-culture of different cells can be made by first seeding the first cell type in a supporting matrix, such as a hydrogel, at the membrane interface, secondly removing the membrane enzymatically and thirdly adding another cell type at the newly formed hydrogel interface. If the cells produce enough ECM, they are able to form their own basal membrane on the interface between two channels after which other cell types can be added into the other channel. Another option would be the on-chip fabrication of a temporary membrane instead of placing the membrane in the chip during chip fabrication. This could be done by applying a polysaccharide that precipitates at an interface where deprotonation takes place ⁴⁸. Upon protonation of such a material, the material will become soluble again. These so called reversible membranes can be used as temporal phase guides. Recent research has led to the development of a membrane free BBB on-chip system using chitosan ⁴⁹ (**Chapter 6**).

It is thought that in the ideal case, cells should be able to form their own ECM and thus their own basal membrane. This basal membrane provides the basic mechanical stability that organ tissues need. As mentioned above, the membrane surface can be used to induce ECM formation in cells. However, to be able to get the best results from an OOC system, the system should be as realistic as possible. Therefore, membrane free systems are being studied recently. Without a membrane, cells are in direct contact with each other as they would be in the physiological *in vivo* situation.

Hydrogels have already been mentioned in this chapter and can be considered membrane free systems. Two types of hydrogels can be distinguished, being synthetic and natural hydrogels. The structure of synthetic hydrogels, such as polyethylene glycol (PEG), can easily be modified. The porosity can be tuned by altering the molecular weight of the polymer. The disadvantage of most synthetic hydrogels is poor cell attachment, which can be improved by costly synthesis of additional functional groups. The majority of natural hydrogels are derived from ECM and are therefore very suitable to be used as cell culture material. Natural hydrogels are for example, alginate, collagen or fibrin. Collagen is often used in cell culture because of its excellent cell adhesion properties. The stiffness and cross-linking time can easily be adjusted by changing the protein concentration. Cells are able to migrate through the cell-gel interface and reach the other cell layer. Using a hydrogel, both a horizontal and a vertical interface between two channels can be created. Horizontally, the hydrogel can be injected into the channels, if this is done to create a vertical membrane, there is a possibility that the gel does not have enough time to set at the interface and it will fill both channels. To solve this problem, the company MIMETAS, developed OrganoPlates® which contain phase guides that guide two liquids exactly along the middle axis of the chip⁵⁰.

2.3.5 The future of OOC research

OOC research can be considered an exciting field of *in vitro* research in which there is still a lot of room for improvement. Considering membrane containing systems, more research is required to improve the structural, mechanical and chemical structure of the membranes to make the system more physiologically relevant. The latest idea to create membrane free OOC systems can be of great importance for the development of new lab-on-chip applications. Therefore, other techniques, such as interfacial polymerization or deprotonation of polysaccharides should be studied more extensively^{48,49,51}.

2.4 References

1. E. W. Esch, A. Bahinski and D. Huh, *Nature Reviews Drug Discovery*, 2015, **14**, 248-260.
2. D. Huh, B. D. Matthews, A. Mammoto, M. Montoya-Zavala, H. Y. Hsin and D. E. Ingber, *Science*, 2010, **328**, 1662-1668.
3. D. D. Huh, *Annals of the American Thoracic Society*, 2015, S42-S44.
4. J. C. Arthur and C. Jobin, *Inflammatory Bowel Diseases*, 2011, **17**, 396-409.

5. H. Sokol and P. Seksik, *Current Opinion in Gastroenterology*, 2010, **26**, 327-331.
6. B. P. Hurley, W. Pirzai, A. D. Eaton, M. Harper, J. Roper, C. Zimmermann, G. S. Ladics, R. J. Layton and B. Delaney, *Food and Chemical Toxicology*, 2016, **92**, 75-87.
7. J. H. Sung, J. Yu, D. Luo, M. L. Shuler and J. C. March, *Lab on a Chip*, 2011, **11**, 389-392.
8. C. Pereira, J. Costa, B. Sarmento and F. Araújo, in *Concepts and Models for Drug Permeability Studies*, ed. B. Sarmento, Woodhead Publishing, 2016, pp. 57-81.
9. H. J. Kim, D. Huh, G. Hamilton and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2165-2174.
10. H. J. Kim and D. E. Ingber, *Integrative Biology*, 2013, **5**, 1130-1140.
11. B. Gumuscu, H. J. Albers, A. van den Berg, J. C. T. Eijkel and A. D. van der Meer, *Scientific Reports*, 2017, **7**, 3381.
12. P. Ehrlich, *Hirschwald*, 1885.
13. N. J. Abbott, L. Rönnbäck and E. Hansson, *Nature Reviews Neuroscience*, 2006, **7**, 41.
14. N. J. Abbott and A. Friedman, *Epilepsia*, 2012, 1-6.
15. D. J. Mc Carthy, M. Malhotra, A. M. O'Mahony, J. F. Cryan and C. M. O'Driscoll, *Pharmaceutical Research*, 2015, **32**, 1161-1185.
16. C. R. White and J. A. Frangos, *Philosophical Transactions of the Royal Society B: Biological Sciences*, 2007, **362**, 1459-1467.
17. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
18. A.-C. Luissint, C. Artus, F. Glacial, K. Ganeshamoorthy and P.-O. Couraud, *Fluids and Barriers of the CNS*, 2012, **9**, 23.
19. R. Booth and H. Kim, *Lab on a Chip*, 2012, **12**, 1784-1792.
20. R. Booth and H. Kim, *Annals of Biomedical Engineering*, 2014, **42**, 2379-2391.
21. J. Gao, D. Guo, S. Santhanam and G. K. Fedder, *Journal of Microelectromechanical Systems*, 2015, **24**, 2170-2177.
22. V. A. Soloukhin, J. C. M. Brokken-Zijp, O. L. J. van Asselen and G. de With, *Macromolecules*, 2003, **36**, 7585-7597.
23. D. F. Stamatialis, B. J. Papenburg, M. Gironés, S. Saiful, S. N. M. Bettahalli, S. Schmitmeier and M. Wessling, *Journal of Membrane Science*, 2008, **308**, 1-34.
24. M. J. Bissell and M. H. Barcellos-Hoff, *Journal of Cell Science*, 1987, **1987**, 327.
25. M. J. Cooke, S. R. Phillips, D. S. Shah, D. Athey, J. H. Lakey and S. A. Przyborski, *Cytotechnology*, 2008, **56**, 71-79.
26. K. C. Chaw, M. Manimaran, F. E. H. Tay and S. Swaminathan, *Biomedical Microdevices*, 2007, **9**, 597-602.
27. M. Mulder, in *Basic Principles of Membrane Technology*, Kluwer Academic Publishers, Dordrecht, The Netherlands, 1996, ch. 5, pp. 210-230.

28. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
29. S. M. Casillo, A. P. Peredo, S. J. Perry, H. H. Chung and T. R. Gaborski, *ACS Biomaterials Science & Engineering*, 2017, **3**, 243-248.
30. H. Becker and U. Heim, *Sensors and Actuators A: Physical*, 2000, **83**, 130-135.
31. R. Truckenmuller, S. Giselbrecht, C. van Blitterswijk, N. Dambrowsky, E. Gottwald, T. Mappes, A. Rolletschek, V. Saile, C. Trautmann, K. F. Weibezahn and A. Welle, *Lab on a Chip*, 2008, **8**, 1570-1579.
32. R. Truckenmüller, S. Giselbrecht, N. Rivron, E. Gottwald, V. Saile, A. van den Berg, M. Wessling and C. van Blitterswijk, *Advanced Materials*, 2011, **23**, 1311-1329.
33. B. J. Papenburg, L. Vogelaar, L. A. M. Bolhuis-Versteeg, R. G. H. Lammertink, D. Stamatialis and M. Wessling, *Biomaterials*, 2007, **28**, 1998-2009.
34. L. Vogelaar, R. G. H. Lammertink, J. N. Barsema, W. Nijdam, L. A. M. Bolhuis-Versteeg, C. J. M. van Rijn and M. Wessling, *Small*, 2005, **1**, 645-655.
35. J. de Jong, B. Ankoné, R. G. H. Lammertink and M. Wessling, *Lab on a Chip*, 2005, **5**, 1240-1247.
36. M. Gironès, I. J. Akbarsyah, W. Nijdam, C. J. M. van Rijn, H. V. Jansen, R. G. H. Lammertink and M. Wessling, *Journal of Membrane Science*, 2006, **283**, 411-424.
37. M. F. Griffin, P. E. Butler, A. M. Seifalian and D. M. Kalaskar, *World Journal of Stem Cells*, 2015, **7**, 37-50.
38. G. F. B. Hulshof, University of Twente, 2016.
39. Y. S. Zhang, J. Aleman, A. Arneri, S. Bersini, F. Piraino, S. R. Shin, M. R. Dokmeci and A. Khademhosseini, *Biomedical Materials*, 2015, **10**, 034006-034006.
40. H. V. Unadkat, M. Hulsman, K. Cornelissen, B. J. Papenburg, R. K. Truckenmüller, A. E. Carpenter, M. Wessling, G. F. Post, M. Uetz, M. J. T. Reinders, D. Stamatialis, C. A. van Blitterswijk and J. de Boer, *Proceedings of the National Academy of Sciences*, 2011, **108**, 16565-16570.
41. S.-Y. Tee, J. Fu, Christopher S. Chen and Paul A. Janmey, *Biophysical Journal*, 2011, **100**, L25-L27.
42. B. D. Ulery, L. S. Nair and C. T. Laurencin, *Journal of Polymer Science. Part B, Polymer Physics*, 2011, **49**, 832-864.
43. R. van Dijkhuizen-Radersma, L. Moroni, A. v. Apeldoorn, Z. Zhang and D. Grijpma, in *Tissue Engineering*, ed. P. T. Clemens van Blitterswijk, Anders Lindahl, Jeffrey Hubbell, David F. Williams, Ranieri Cancedda, Joost D. de Bruijn and Jérôme Sohier Academic Press, Burlington, 2008, pp. 193-221.
44. J. D. Humphries, A. Byron and M. J. Humphries, *Journal of Cell Science*, 2006, **119**, 3901-3903.
45. Z. Zhang, R. Kuijer, S. K. Bulstra, D. W. Grijpma and J. Feijen, *Biomaterials*, 2006, **27**, 1741-1748.
46. L. Xu, K. Crawford and C. B. Gorman, *Macromolecules*, 2011, **44**, 4777-4782.
47. A. Banerjee, K. Chatterjee and G. Madras, *Materials Science and Technology*, 2014, **30**, 567-573.

- 48. X. Luo, D. L. Berlin, J. Betz, G. F. Payne, W. E. Bentley and G. W. Rubloff, *Lab on a Chip*, 2010, **10**, 59-65.
- 49. M. P. Tibbe, A. M. Leferink, A. van den Berg, J. C. T. Eijkel and L. I. Segerink, *Advanced Materials Technologies*, 2018, **3**, 1700200.
- 50. M. Jang, P. Neuzil, T. Volk, A. Manz and A. Kleber, *Biomicrofluidics*, 2015, **9**, 034113.
- 51. Y. Zhang, N. E. Benes and R. G. H. Lammertink, *Lab on a Chip*, 2015, **15**, 575-580.

3

Transwell integrated porous, thin PDMS membranes as alternative cell culture platform

Traditional Transwell cell culture systems contain track-etched, 10 μm thick polymer membranes. In some systems, these membranes have a crucial role and can therefore not be removed entirely. However, removing or replacing this membrane by a thinner one will decrease the distance between adjacent cell types resulting in an increased cell-cell contact possibility. In this chapter the use of a new porous 5-fold thinner (2 μm) PDMS membrane in co-culture experiments is shown.

Some parts of this work were published in:

Large-scale fabrication of free-standing and sub- μm PDMS through-hole membranes

H. Le-The, M.P. Tibbe, J.T. Loessberg-Zahl, M. Palma do Carmo, M.W. van der Helm, J.G. Bomer, A. van den Berg, A.M. Leferink, L.I. Segerink and J.C.T. Eijkel

*Nanoscale, 2018, **10**, 7711*

3.1 Introduction

Porous membranes have multidisciplinary applications such as filtration, separation and recently, they are used as a physical barrier in organ on chip (OOC) systems ¹⁻⁶. These OOC systems are of great interest due to their potential as a replacement for unethical *in vivo* studies. By recreating organ function and/or organ structure with patient specific tissue on a microfluidic chip, a realistic simulation of the *in vivo* situation can be made *in vitro* ⁷. The aim of OOC technology is to mimic the organ tissue as realistic as possible. Often this is achieved by recreating the connection between a blood vessel (lumen) and an organ tissue. One organ that attracts a lot of attention in OOC research due to its complex structure is the blood-brain barrier (BBB) ⁸. This barrier is comprised of tightly connected endothelial cells that form the blood vessels in the brain. Due to its tight structure, only paracellular transport of molecules through the barrier is possible as intercellular transport is hindered to protect the brain from harmful unwanted substances. Failure of the BBB contributes to the pathogenesis of neurodegenerative disorders such as Alzheimer's and Parkinson's disease ⁹. The protective function also prevents drugs from passing the barrier and entering the brain ^{8, 10, 11}. Recreating such a barrier *in vitro* on a microfluidic chip makes drug research and disease modelling cheaper and more reproducible compared to *in vivo* experiments. Eventually, patient specific materials can be used in these studies to facilitate personalized medicine ¹².

In most OOC systems developed so far, the separation between the luminal side and the apical (tissue) side of the chip is achieved by the incorporation of thick polymer membranes made from materials such as polycarbonate (PC) ^{13, 14}, and polyethylene terephthalate (PET) ¹⁵⁻¹⁷. Apart from separating the compartments, this membrane also acts as structural support for the cells to attach to. It is possible to obtain membranes with different pore sizes ranging from 0.4 μm to 8 μm . In general, these pores are created by track etching of the material ^{18, 19}. A big disadvantage of this fabrication method is the random distribution of the pores, which sometimes results in interconnecting pores which can be a lot bigger than the expected pore size. Another big disadvantage of these membranes is their thickness, which is at least 10 μm , whereas the *in vivo* membrane between tissues is in the order of nanometers ²⁰. So far, little attention has gone towards the non-physiological structure of these commercially available membranes. When used in an OOC, these membranes

form a physiologically irrelevant big barrier between adjacent cell culture channels. Furthermore, when culturing cells on PC and PET membranes, live cell imaging using bright field or phase contrast microscopy is not possible. Due to the material structure, thickness and random pore tortuosity, they are only fluorescently transparent. Live cell labelling with fluorescent markers has shown to be feasible. However, using a fluorescence-based imaging modality does not allow for the analysis of the cell layer which is cultured on top of the membrane. Nevertheless, it has been shown that the porosity of these commercial membranes allows for paracrine signalling; and if the pores are at least 3 μm wide, cell migration through the pores is possible ²¹.

Recently, other types of membranes are being developed and integrated into OOC systems. Das *et al.* developed a polymeric blend membrane using phase inversion technology. The physico-chemical characteristics of the membrane are fully tuneable by the production method and the polymer preparations. This way a more physiologically relevant membrane for implementation in an OOC system can be obtained ²². To decrease the distance between two microfluidic compartments in an OOC system, a thinner membrane can be introduced. Ma *et al.* developed a thin (~ 500 nm) silicon nitride membrane on which endothelial cells and astrocytes were cultured ²³. Normal tissue culture plastic has an elastic modulus of approximately 10 MPa ²⁴ which is already much higher compared to brain tissue which has an elastic modulus of 0.5 – 1 kPa ²⁵. The elastic modulus of silicon nitride is in the GPa range ²⁶ which might have an influence on the cultured cell layer. Quirós-Solano *et al.* and Le-The *et al.* both developed a porous poly dimethyl siloxane (PDMS) membrane with tunable pore structure that can be used in cell culture and OOC research ^{27, 28}. The thin, porous PDMS membrane of Le-The *et al.* was developed within our research group ²⁸. This fabrication method is adjustable such that membranes with different thicknesses, down to 1 μm , can be fabricated (Figure 1). Apart from the easily tuneable membrane morphology, these membranes are also fully optically transparent which makes live cell imaging without having to use fluorescent markers possible. Contradictory to the PC and PE membranes, these PDMS membranes are thin and have straight pores perpendicular to the membrane surface which makes observation of the cell layer integrity optically possible through bright field and phase contrast microscopy. As the pore distribution and size is well controlled by the photolithography process, the cultured cells experience a regular cell culture surface whereas track etched

membranes have a random pore structure with interconnecting pores. The distance between the cells can be ten times smaller when using our PDMS membrane compared to using PC or PE membranes. The separation distance between cells in opposite channels is therefore small enough to allow for direct cell-cell contact without the cells having to fully migrate through the membrane. PDMS thin films have a lower elastic modulus ($\sim 8 \text{ MPa}$ ²⁹) compared to PC ($\sim 2 - 2.4 \text{ GPa}$ ³⁰) and PE ($\sim 2 - 3 \text{ GPa}$ ³⁰), which makes the membranes more elastic. Combined with the small thickness, mechanotransduction between cells on adjacent sides of the membrane should be possible.

To test whether the developed PDMS membranes are suitable for cell culture applications, human cerebral microvascular endothelial cells (hCMEC/D3) were cultured inside adapted Transwell inserts. Prior to cell culture, the membranes were sterilized using ethanol as other sterilization methods might change the membrane structure. HCMEC/D3 cells showed a high viability after seven days of culture (Figure 5). As mentioned earlier in this chapter, the BBB is an interesting organ in which multiple cell types such as endothelial cells and astrocytes are influenced by each other to maintain a good barrier integrity. Having direct cell-cell contact seems essential for proper functioning of the brain endothelial cells. Therefore, to study whether our PDMS membranes allow for an improved cell-cell interaction, hCMEC/D3 cells were also co-cultured with human astrocytes in a Transwell-like set-up. Validating the integrity of the barrier can be done by looking at the expression of the tight junction proteins which are present in hCMEC/D3 cells that form a proper, closed, monolayer of cells. Zonula Occludens 1 (ZO-1) is such a tight junction protein that is present in abundance in a good brain endothelial cell monolayer ^{31 32}.

In this chapter we studied the interaction between hCMEC/D3 cells and human astrocytes on our newly developed PDMS membranes and as a comparison we co-cultured these cells on PC membranes with similar pore sizes to see whether a decrease in distance between two cell types improves the barrier structure. We will validate the barrier formation by immunostaining of the ZO-1 protein in the hCMEC/D3 cells.

3.2 Materials and Methods

3.2.1 Membrane fabrication

Prior to spinning the photoresist (PR) layer, a thin hexamethyldisilazane (HMDS) was spun onto the 4" silicon wafer (525 μm thick, Okmetic, Finland) to increase the adhesion of the PR to the wafer. A 4.80 μm thin layer of positive PR (AZ®9260, MicroChemicals, Germany) was spun at 2000 rpm for 60 s onto the HMDS coated wafer. The PR was baked for 2 min at 110 °C on a hotplate. The PR was exposed for 17 s with an intensity of 12 mW cm^{-2} using a mask alignment system (EVG620, EV Group, Austria), while covering the PR with a quartz photo mask containing chromium structures of 3 and 5 μm . The exposed PR was post baked on a hotplate for 1 min at 110 °C prior to developing the PR using an OPD4246 developer for 5 min followed by rinsing with de-ionized (DI) water. The development results in PR column arrays.

A degassed solution of PDMS prepolymer with curing agent ((wt. ratio 10:1) Sylgard 184 Silicone elastomer kit, Dow Corning, MI, USA) was mixed with hexane at a 4:10 (PDMS : hexane) wt. ratio to make the solution suitable for spin coating. The PDMS and hexane solution was spun onto the PR column array at 4000 rpm for 1 min. After spinning, the PDMS membrane was cured at 60 °C for at least 12 h to remove all the hexane. Due to the spin coating process, a thin residual layer of PDMS remains on the column array resulting in a non-porous membrane. Therefore, this layer was plasma etched using a parallel plate reactive ion etching system (in-house built TEske system, Nanolab University of Twente, the Netherlands) at 47 sccm SF_6 , 17 sccm O_2 , 50 mTorr and 100 W. This etching process decreases the thickness of the entire PDMS membrane and opens the pores. The amount of gas and power determines the etch rate and therefore the final membrane thickness. Longer etching results in membranes with a thickness down to 900 nm. The etch rate could easily be determined by measuring the membrane thickness before and after etching. Membrane thickness was determined from images that are being made by a scanning electron microscope ((SEM) HR-SEM, FEI Sirion microscope). Images were taken at a 5 kV acceleration voltage and a spot size of 3.

FIGURE 1 SCHEMATIC IMAGE OF POROUS PDMS MEMBRANE FABRICATION METHOD. A LAYER OF PR IS COATED ONTO A HMDS COATED 4" SILICON WAFER (A). THE PR LAYER IS PATTERNED USING PHOTOLITHOGRAPHY RESULTING IN A PR COLUMN ARRAY (B). A MIXTURE OF PDMS AND HEXANE (4:10 WT. RATIO) IS SPUN ONTO THE PILLAR ARRAY (C). THE RESIDUAL PDMS LAYER IS ETCHED USING REACTIVE ION ETCHING (D). THE PDMS MEMBRANE IS RELEASED BY DISSOLVING THE PR LAYER AND ATTACHED TO A TRANSWELL INSERT (F AND G).

To be able to use these membranes for cell culture, a Transwell insert from which the original membrane was removed was attached to the membrane by use of an uncured PDMS (pre-polymer : curing agent, wt. ratio 10:1) glue. After attaching the insert to the membrane, the glue was cured at 60°C for 3 hours. The membranes were released from the silicon substrate by dissolving both the PR columns as well as the PR sacrificial layer in a mixture of acetone and ethanol (100%) at a 70:30 v/v ratio. Released membranes were sterilized by immersing them in ethanol (70%) for 24 h. Prior to cell culture, the membranes were washed (3x) with 1 x phosphate buffered saline (PBS, Merck, Germany).

3.2.2 Cell seeding and staining

To assess the biocompatibility of the produced porous PDMS membranes, human cerebral microvascular endothelial cells (hCMEC/D3, passage 30-34, Merck Millipore, the Netherlands) were seeded on top of the Transwell-mounted PDMS membranes. Commercially available Transwell systems with PC membranes (Corning, NY, USA) are included in the experiment to compare cell culture results. Membranes were prepared for cell seeding by coating them for 1 h with a 40 $\mu\text{g mL}^{-1}$ fibronectin (YoProteins, Sweden) in PBS solution.

hCMEC/D3 cells were resuspended in a 15×10^4 cells mL^{-1} concentration in endothelial cell growth medium (ECGM, Sigma-Aldrich Chemie GmbH, Steinheim, Germany). Prior to cell seeding, 600 μL ECGM was pipetted in the lower compartment of the 24-wells Transwell system. 100 μL hCMEC/D3 cell suspension is pipetted on top of the collagen coated PDMS and PC membranes and cultured statically. The cell morphology was observed daily using phase contrast microscopy (EVOS®, PA, USA). Cell viability was assessed 4 and 7 days after seeding by use of a live/dead viability assay (LIVE/DEAD™ Viability/Cytotoxicity Kit for mammalian cells, Thermo Fisher Scientific, MA, USA) according to the manufacturers protocol. Results were analysed using the “find maxima” method on separate RFP and GFP channels in ImageJ (Supplementary Figure A1 and Supplementary Figure A4).

The influence of astrocytes on the endothelial cell layer was assessed by co-culturing astrocytes and hCMEC/D3 cells (passage 30-34) on adjacent sides of the Transwell membrane. For these experiments, the Transwell inserts were prepared similarly as mentioned above. The bottom of the membrane was coated with a layer of poly-L-lysine (PLL, 2 $\mu\text{g mL}^{-1}$ in PBS, Sigma-Aldrich Chemie GmbH, Germany) for 1 h at 37°C. After removing excess PLL solution, 50 μL human astrocyte (passage 6-10, ScienCell Research Laboratories, CA, USA) cell suspension ($2 \times 10^5 \text{ mL}^{-1}$ in serum-free astrocyte medium (AM, ScienCell Research Laboratories, CA, USA)) was pipetted onto the PLL coated side of the membranes. Astrocytes were incubated for 8 h at 37°C, 5% CO_2 . Once the astrocytes attached properly, the inserts were flipped over to coat the top of the membrane with a 100 $\mu\text{g mL}^{-1}$ collagen (Corning, MA, USA) coating for 1 h at 37°C, 5% CO_2 . A volume of 100 μL hCMEC/D3 suspension was added on top of the collagen coated membranes to seed a final concentration of 2×10^5 cells mL^{-1} in ECGM (Sigma-Aldrich Chemie GmbH, Germany). 500 μL ECGM was added to the endothelial cells in the bottom compartment of the mono-culture samples. The serum-free AM in the bottom compartment of the co-culture samples was replaced with 500 μL serum-rich medium (2% v/v fetal bovine serum (FBS), 1% astrocyte growth supplement (AGS, 100x) and 1% penicillin/streptomycin solution (P/S, 10,000 units mL^{-1} of Penicillin and 10,000 $\mu\text{g mL}^{-1}$ of Streptomycin) all from ScienCell, CA, USA). Medium was refreshed every day. Tight junctions and cell morphology were analysed using immunofluorescence imaging. Prior to immunostaining, astrocytes and hCMEC/D3 were fixed on ice using ice-cold methanol (100%) for 15 min. After

fixation, membranes were washed 3x with 1x PBS supplied with 1% BSA. Cells were permeated using Triton-X (0.1% in 5% BSA solution) for 30 min at room temperature. Fixed samples were incubated overnight (ON) at 4°C with 5 $\mu\text{g mL}^{-1}$ primary antibody (AB) in 0.5% BSA, anti ZO-1 rabbit polyclonal (Thermo Fisher Scientific, MA, USA). The medium in the bottom compartment was replaced by 0.5% BSA in PBS solution. After primary AB incubation, samples were washed 3x with 1% BSA in PBS solution. Washed samples were incubated for 1 h at room temperature with Alexa fluor 647 donkey anti-rabbit ((5 $\mu\text{g mL}^{-1}$) Thermo Fisher Scientific, MA, USA) diluted together with NucBlue™ and ActinGreen™ (both Thermo Fisher Scientific, MA, USA) in DI-water. After incubation, samples were washed 2x with 1x PBS. Cells were imaged by fluorescence microscopy (EVOS®, PA, USA) and by confocal microscopy (Nikon A1). Z-stacks were made using confocal microscopy with a step size of 0.1 μm .

3.2.3 Scanning electron microscopy of cell samples

Cell distribution on the membranes was visualized through SEM. Samples were fixed by incubation in 100% ice-cold methanol for 15 min followed by washing 2x using 1x PBS. After fixation, the samples were dehydrated by use of an ethanol gradient (60%, 70%, 80%, 90%, 96% and 100% (2x) v/v ethanol in milliQ). Samples are dehydrated further using critical point drying (Blazers CPD 030) by liquid carbon dioxide exchange. Prior to SEM, the samples were gold-coated using a Cressington sputter coater. SEM images were made at a 10 kV acceleration voltage with a JEOL JSM-IT 100 SEM.

3.2.4 Permeability measurement

The integrity of the endothelial cell layer was assessed by studying the paracellular transport of fluorescently labelled dextran from the top compartment of the Transwell to the well plate (Figure 2). Cells were seeded as co- and monoculture in Transwell inserts with PDMS and PC membranes (5 μm pore size) as mentioned before (Section 3.2.2). Cells were cultured for 4 days to obtain a proper monolayer. Prior to the experiment, 600 μL assay buffer containing 5% v/v FBS, 2% v/v l-glutamine and 2,5% v/v HEPES in DMEM was added to each well of a new 24-wells plate. Medium was removed from the cell coated Transwell inserts and 100 μL FITC-Dextran (20 mM in assay buffer, 4 kDa, Sigma Aldrich, Germany) was added on top of the endothelial cell layer. The Transwell inserts were placed into the assay buffer

and incubated for 15 minutes. After 15 minutes, the inserts were placed into a new well plate containing fresh assay buffer.

FIGURE 2 SCHEMATIC OF THE PERMEABILITY MEASUREMENT. (A) FIRST A CELL COATED TRANSWELL INSERT CONTAINING A DEXTRAN SOLUTION IS PLACED INTO AN ASSAY BUFFER SOLUTION. (B) AFTER 15 MINUTES OF INCUBATION (C) THE TRANSWELL INSERT IS TRANSFERRED TO A FRESH ASSAY BUFFER SOLUTION FOLLOWED BY AGAIN 15 MINUTES INCUBATION. STEP B IS REPEATED 2X UNTIL 4 TIME-POINTS HAVE BEEN GATHERED. (D) THE FLUORESCENT EMISSION OF THE ASSAY BUFFER SOLUTIONS IS BEING DETERMINED USING A PLATE READER.

Inserts were transferred every 15 minutes into a new solution. Per time-point and per sample (n=4), 3 x 50 μ L was pipetted into a black (clear bottom) 96-well plate. As a control, the starting solution and an empty assay buffer solution were included in the measurement. Fluorescent intensity was measured using a Victor3 plate reader (PerkinElmer, Ma, USA) with excitation at 485 nm and emission at 528 nm. Results were normalized to the lowest measured fluorescence intensity which is a monoculture on a PDMS membrane. Significance was determined by one-way ANOVA with a post-hoc Tukey test using SPSS (IBM SPSS Statistics, Version 26 for Windows), n=4 per condition at each time-point. Data was compared between both types of membranes at the same time point and between mono- and co-cultures at the same time point.

3.3 Results and Discussion

Membranes with different pore sizes can be created using the reported membrane fabrication method²⁸. Here we used membranes with a pore size of 5 μ m (Figure 3). Changing the PDMS : hexane ratio as well as changing the speed of spin coating and the etching time determine the final membrane thickness²⁸. The thickness of the PDMS should be chosen such that the residual layer of PDMS on top of the pillars is relatively thin (nanometre range), resulting in a minimal time of dry etching. Analysis of the PDMS surface after etching showed some traces of sulphur, which should be kept minimal by reducing the etching time. In this research, membranes with a thickness of approximately 2 μ m were used (Figure 3). As can be seen in Figure 3B, when a mask with 5 μ m pore size is used, the actual pore size turns out to be approximately 3-4 μ m. This size is dependent on the thickness on the membrane as the used pillars are slightly tapered. In this case, a thinner membrane results in larger pores.

FIGURE 3 SEM IMAGES OF THE PDMS MEMBRANE. CROSS SECTIONAL VIEW OF MEMBRANES WITH 5 μm PORE SIZE. THE MEMBRANE ITSELF HAS A THICKNESS OF 2 μm AFTER ETCHING. AFTER ETCHING THE PR COLUMN IS EXPOSED RESULTING IN AN POROUS MEMBRANE STRUCTURE UPON PR REMOVAL.

FIGURE 4 PHASE CONTRAST IMAGES OF hCMEC/D3 CULTURED ON PDMS MEMBRANES WITH 3 μm PORES. CELLS WERE SEEDD IN A CONCENTRATION OF 1.5×10^4 CELLS/INSERT AND FORM A MONOLAYER AFTER 5 DAYS OF CULTURE. A MORE COMPACT COBBLESTONE CELL STRUCTURE IS FORMED AFTER 7 DAYS. SCALEBARS REPRESENT 100 μm.

To validate whether etching PDMS using sulphur hexafluoride (SF_6) and oxygen has a toxic influence on cells cultured on these membranes, hCMEC/D3 are cultured for up to 7 days on the membrane. The monolayer formation of the cells was analysed over time (Figure 4) as well as an end point measurement of the cell viability after 4 and 7 days of culture (Figure 5).

FIGURE 5 LIVE DEAD VIABILITY ASSAY AFTER 4 AND 7 DAYS OF CO-CULTURE (hCMEC/D3 & HUMAN ASTROCYTES). hCMEC/D3 CELLS AND HUMAN ASTROCYTES CULTURED ON A PDMS MEMBRANE (A & B) AND ON A PC MEMBRANE (C & D), BOTH WITH 5 μm PORES. VIABLE CELLS ARE STAINED WITH CALCEIN AM (GREEN), WHEREAS NECROTIC CELLS ARE STAINED USING ETHIDIUM HOMODIMER (RED). (A & C) AFTER 4 DAYS OF CULTURE, THE CELLS HAVE FORMED A VIABLE MONOLAYER WITH AN ACCEPTABLE AMOUNT OF NECROTIC CELLS ON BOTH MEMBRANES. (B & D) AFTER 7 DAYS OF CULTURE, THE CELL LAYER IS STILL VIABLE WITH A SIMILAR AMOUNT OF NECROTIC CELLS COMPARED TO THE PREVIOUS TIME POINT. SCALEBARS REPRESENT 250 μm

Le-The *et al.* have shown that etching PDMS with SF_6 results in approximately 1.5% wt. sulphur residues on the membrane surface²⁸. After 7 days of culture, hCMEC/D3 cultured on the PDMS membranes form a proper monolayer (Figure 4D). Results from the live/dead viability assay show that after 4 and after 7 days of culture, a percentage of approximately 80% of cells on the PDMS

membranes as well as on the PC membrane are viable (Figure 5 & Supplementary Figure A4). There was no significant difference detected in viability between the two membranes at both time points (one-way ANOVA, $p > 0.05$, $n=3$). Analysis of the phase contrast image of hCMEC/D3 on PDMS and the viability assay on day 7 shows a proper monolayer and good viability of the cells (Figure 4). As the viability of the cells is not negatively influenced by the PDMS membrane, another co-culture of hCMEC/D3 and human astrocytes is conducted to study the interaction between these cell types. In previous experiments, membranes were coated with collagen prior to cell seeding to provide better attachment for the brain endothelial cells. As the astrocytes are seeded 24 h before the endothelial cells are seeded, serum-free medium must be used to prevent proteins from the astrocyte medium precipitating on the membrane prior to collagen coating, occupying the available binding sites for collagen on the membrane surface. The influence of membrane thickness on cell-cell interactions is studied by comparing the cell morphology and ZO-1 expression in co-cultures on PDMS membranes with the result of cells cultured on PC membranes. As can be seen in Figure 6B and Figure 6E, the hCMEC/D3 cells cultured on the PDMS membrane show a lower fluorescent intensity of tight junction protein ZO-1 compared to the cells cultured on the PC membrane. Furthermore, in both conditions the ZO-1 staining is not localized at the borders of the cells. As reported by Gottardi *et al.*, ZO-1 localizes towards the nucleus when the cell-cell contacts are remodelling or not present at all³¹. Both the hCMEC/D3 cultured on the PDMS as the cells cultured on the PC show similar, randomly distributed, ZO-1 expression profiles. The fact that there is a higher expression of ZO-1 protein by the endothelial cells cultured on the PC membranes can be the result of a higher number of astrocytes, due to lack of attachment in the beginning of the experiment. Most astrocytes seeded on the PDMS membranes detached after flipping the membrane and seeding the endothelial cells. However, after 7 days of culture, the remaining astrocytes have formed a proper monolayer on the bottom of the membrane (Figure 7B).

It was expected that the endothelial cells would be able to migrate through the membrane to the side of the astrocytes, due to the chosen pore size. However, Figure 6C and Figure 6F do not show ZO-1 staining, indicating that there are no or little hCMEC/D3 cells on the other side of the membrane. In the SEM images in Figure 7, a clear difference in morphology and organization between

astrocytes on the bottom of the membrane and endothelial cells on top of the membrane can be seen.

FIGURE 6 IMMUNOSTAINING OF TIGHT JUNCTION PROTEIN ZO-1 (ALEXA FLUOR 647, RED), CELL NUCLEI (NUCBLUE®, BLUE) AND ACTIN (ACTINGREEN®, GREEN) AFTER 7 DAYS OF COCULTURING ASTROCYTES AND HCMEC/D3. ASTROCYTES ON THE BOTTOM OF THE MEMBRANE SHOW AN ELONGATED MORPHOLOGY AND NO ZO-1 EXPRESSION (A & D). HCMEC/D3 CELLS SEEDED ON TOP OF THE MEMBRANE SHOW A CHARACTERISTIC COBBLESTONE MORPHOLOGY AND EXPRESS ZO-1 ON BOTH MEMBRANES (B & E). THE ENDOTHELIAL CELLS CULTURED ON THE PC MEMBRANE EXPRESS A HIGHER AMOUNT OF ZO-1, HOWEVER, NO LOCALIZATION AT THE CELL BORDERS IS FOUND (E). A CROSS-SECTION OF BOTH MEMBRANES SHOWS THE DIFFERENCE IN THICKNESS BETWEEN THE PDMS AND PC MEMBRANE (C & F). THE PDMS MEMBRANE IS BARELY VISIBLE (C) WHEREAS THE PC MEMBRANE CLEARLY SEPARATES THE TWO CELL LAYERS FROM EACH OTHER (F). SCALEBARS REPRESENT 50 μm.

When we look at a monoculture, an endothelial cell protrusion going through a 5 μm pore can be seen (Figure 7C). From this observation it can be concluded that cells are able to have direct cell-cell contact without having to migrate to the other side of the membrane. Once the monolayer of endothelial cells starts to overgrow, they will look for empty cell culture surfaces leading to migration to the other side (Supplementary Figure A2). A good monolayer of astrocytes on the other side of the membrane prevents this migration and facilitates

direct cell-cell contact. HCMEC/D3 and astrocytes, grown on PC membranes with a comparable pore size of 5 μm show a similar morphology compared to the same cells grown on the newly developed PDMS membrane Supplementary Figure A3. From Supplementary Figure A3D it can be concluded that endothelial cell protrusions are able to penetrate through the pores of the PC membrane.

FIGURE 7 SEM IMAGES OF HCMEC AND HUMAN ASTROCYTES CULTURED FOR 7 DAYS ON PDMS MEMBRANES WITH 5 μm PORE SIZES. A MONOLAYER OF HCMEC/D3 CELLS IS FOUND AT THE MONO- AND CO-CULTURE CONDITION (A & C). ON THE OPPOSITE SIDE OF THE ENDOTHELIAL CELLS IN THE CO-CULTURE CONDITION, A MONOLAYER OF ASTROCYTES WITH THEIR CHARACTERISTIC ELONGATED SHAPE IS FOUND (B). A ZOOM IN OF THE ENDOTHELIAL CELL LAYER SHOWS THAT PROTRUSIONS OF THE CELLS ARE ABLE TO REACH THROUGH THE 5 μm LARGE PORES TOWARDS THE OTHER SIDE OF THE MEMBRANE (D).

An indication of cell layer integrity is the permeability to certain substances. Here we used fluorescently labeled dextran (4 kDa) which was added to the top compartment of the Transwell inserts after which the intensity of fluorescence in the bottom compartment was measured after 15 minutes of incubation. The Transwell was then transferred to a fresh buffer solution from

which the fluorescent intensity was measured again after 15 minutes of incubation.

FIGURE 8 BOXPLOT REPRESENTATION OF RELATIVE FLUORESCENCE OF FITC-DEXTRAN AFTER PASSIVE DIFFUSION THROUGH CO- AND MONOCULTURES OF hCMEC/D3 WITH AND WITHOUT HUMAN ASTROCYTES ON BOTH PDMS AND PC MEMBRANES WITH 5 μ m PORE SIZE. MEASUREMENTS WERE TAKEN 4 TIMES, EACH AFTER 15 MINUTES (T1-T4). EVERY WELL (N=4 FOR EACH CONDITION) IS MEASURED 3 TIMES AT EACH TIME POINT. SIGNIFICANCE: ** REPRESENTS P-VALUE < 0.01, "ns" REPRESENTS NOT SIGNIFICANT

Because of the extremely high amount of dextran in the top compartment and the low permeability of the cell layer, we assume that the decrease of dextran concentration can be neglected. Note that due to this assumption, the permeability of especially the PC membrane (it has a significantly higher permeability compared to PDMS) over time is slightly underestimated which might explain the insignificant difference appearing at $T = 4$. As can be seen in Figure 8, the PDMS membranes allow for approximately 6x less transfer of dextran to the bottom compartment compared to the PC membranes. There is no significant difference in relative fluorescence between the samples that were taken from the FITC-dextran that passively diffused through the coculture and the monoculture on PDMS membranes. This might indicate that only having a monoculture of hCMEC/D3 cells is already enough to form a proper cellular barrier on PDMS membranes. This is in accordance with results from Cucullo *et al.* who showed that there is no difference in trans-endothelial electrical resistance (TEER), a measure for barrier integrity, between a coculture of hCMEC and astrocytes and a monoculture of hCMEC³³. Contradictory, our results show that the measured samples from the coculture on PC membranes show a significantly lower relative fluorescence of diffused FITC-dextran, compared to the monoculture of hCMEC/D3 cells. The latter indicates that the interaction between the astrocytes and endothelial cells has an influence on the barrier integrity on thick porous PC membranes. However, Odijk *et al.* showed that there is a significant variability in TEER measurements along different systems³⁴ which might be caused by several factors such as environmental conditions and cell layer continuity. A similar variability can occur in these permeability measurements as a result of, for example, gaps in the cell layer.

3.4 Conclusion and Outlook

In this chapter we show the implementation of a porous PDMS membrane for cell culture. The fabrication method of this membrane allows for precise control of pore size, pore distribution, pore density and membrane thickness. These are parameters that cannot be easily adjusted when using traditional Transwell membranes³⁵⁻³⁷. Traditional Transwell membranes are often non-transparent which makes live cell imaging a challenge. The low thickness and straight pore morphology make the reported PDMS membranes transparent and suitable for live cell imaging without the need for fluorescent tracers. Cell

culture results have shown that the used fabrication method is not toxic to the cultured cells. HCMEC/D3 cells were grown successfully for up to 7 days onto the PDMS membranes. Although PDMS has proven to be a suitable material for cell culture^{38, 39}, cell culture conditions still have to be optimized. We found that using membranes with pore sizes of 5 μm results in cell migration to the other side of the membrane leading to gaps in the cell layer directly after seeding. Culturing the endothelial cells for prolonged time might solve the problem of a discontinuous cell layer. However, prolonged cell culture can lead to the formation of an endothelial cell monolayer on both sides of the membrane. Cell migration can be averted by co-culturing a second cell type on the opposite side of the membrane. An unexpected result was the increase in ZO-1 expression in hCMEC/D3 cells cultured on the PC membranes compared to the cells cultured on the PDMS membranes. As these PDMS membranes are a 5-fold thinner compared to traditional PC membranes, it was expected that thinner membranes allow for direct cross-talk between endothelial cells and astrocytes resulting in an increased expression of tight junction proteins. We confirmed this direct contact by SEM, showing cell protrusions going through the pores of the PDMS membrane. Closer contact might lead to symbiotic signalling between endothelial cells and astrocytes resulting in further reduction of paracellular permeability⁴⁰. The increase in ZO-1 expression in the cells cultured on PC membranes is assumed to not be a result of the distance between cell types. However, good attachment of endothelial cells to the PC surface is the expected reason for an increased tight junction expression. Permeability measurements show that PC membranes allow for more transport of fluorescently labelled dextran compared to PDMS membranes. When comparing the porosity of both membranes, an increased permeability of PC membranes is expected. Initially, a Lucifer yellow permeability assay was proposed, however due to circumstances, fluorescently labelled dextran was chosen. The size of the dextran allows for transcellular and paracellular transport of the molecules, this way the transport is dependent on the tightness of the cellular barrier. It is seen that there is little influence of astrocytes in close proximity to the endothelial cells on the PDMS membranes. When astrocytes are cocultured with hCMEC/D3 on PC membranes, the permeability decreases, indicating a better cellular barrier. Results show that the permeability of the cell layers cultured on PC membranes is 6x higher compared to PDMS membranes. The fact that the porosity of PC

membranes is only 4x higher suggests that endothelial cells form a tighter barrier on PDMS membranes.

Ultimately, these membranes are meant to be used as barriers in an OOC system. Therefore, the inclusion of PDMS membranes inside a microfluidic chip has to be optimized. Preliminary tests have shown that it is possible to insert a porous PDMS membrane inside a PDMS microfluidic chip by use of surface optimization using O₂ plasma²⁸. This method, also reported by Quiros-Solano *et al.*, results in leak free microfluidic chips²⁷. These microfluidic chips allow for continuously perfused cell culture conditions.

The co-culture system reported in this chapter can be made even more physiologically relevant by including pericytes in the system. Pericytes are thought to have an activating influence on astrocytes, improving the barrier function of the endothelial cells⁴¹⁻⁴³.

3.5 References

1. Z. Yan, Nan, K. and Rogers, J. A., in *Silicon Nanomembranes*, ed. J. A. R. a. J. Ahn, 2016.
2. S. P. Adiga, C. Jin, L. A. Curtiss, N. A. Monteiro-Riviere and R. J. Narayan, *Wiley Interdisciplinary Reviews: Nanomedicine and Nanobiotechnology*, 2009, **1**, 568-581.
3. M. M. Pérez-Madriral, M. I. Giannotti, L. J. del Valle, L. Franco, E. Armelin, J. Puiggali, F. Sanz and C. Alemán, *ACS Applied Materials & Interfaces*, 2014, **6**, 9719-9732.
4. D. Huh, H. J. Kim, J. P. Fraser, D. E. Shea, M. Khan, A. Bahinski, G. A. Hamilton and D. E. Ingber, *Nature Protocols*, 2013, **8**, 2135.
5. D. D. Huh, *Annals of the American Thoracic Society*, 2015, S42-S44.
6. H. J. Kim, D. Huh, G. Hamilton and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2165-2174.
7. S. N. Bhatia and D. E. Ingber, *Nature Biotechnology*, 2014, **32**, 760-772.
8. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
9. M. D. Sweeney, A. P. Sagare and B. V. Zlokovic, *Nat Rev Neurol*, 2018, **14**, 133-150.
10. N. J. Abbott and A. Friedman, *Epilepsia*, 2012, 1-6.
11. B. T. Hawkins and T. P. Davis, *Pharmacological Reviews*, 2005, **57**, 173-185.
12. L. M. Griep, F. Wolbers, B. Wagenaar, P. M. Braak, B. B. Weksler, I. A. Romero, P. O. Couraud, I. Vermes, A. D. Meer and A. Berg, *Biomedical Microdevices*, 2012, **15**, 145-150.

13. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
14. D. Gao, H. Liu, J.-M. Lin, Y. Wang and Y. Jiang, *Lab on a Chip*, 2013, **13**, 978-985.
15. T.-E. Park, N. Mustafaoglu, A. Herland, R. Hasselkus, R. Mannix, E. A. FitzGerald, R. Prantil-Baun, A. Watters, O. Henry, M. Benz, H. Sanchez, H. J. McCrea, L. C. Goumnerova, H. W. Song, S. P. Palecek, E. Shusta and D. E. Ingber, *Nature Communications*, 2019, **10**, 2621.
16. F. R. Walter, S. Valkai, A. Kincses, A. Petnehazi, T. Czeller, S. Veszelka, P. Ormos, M. A. Deli and A. Der, *Sensors and Actuators B-Chemical*, 2016, **222**, 1209-1219.
17. O. Y. F. Henry, R. Villenave, M. J. Cronce, W. D. Leineweber, M. A. Benz and D. E. Ingber, *Lab on a chip*, 2017, **17**, 2264-2271.
18. P. Y. Apel, I. V. Blonskaya, S. N. Dmitriev, O. L. Orelovitch and B. Sartowska, *Journal of Membrane Science*, 2006, **282**, 393-400.
19. M. Y. Kim, D. J. Li, L. K. Pham, B. G. Wong and E. E. Hui, *Journal of Membrane Science*, 2014, **452**, 460-469.
20. R. Jayadev and D. R. Sherwood, *Current Biology*, 2017, **27**, R207-R211.
21. C. R. Justus, N. Leffler, M. Ruiz-Echevarria and L. V. Yang, *Journal of visualized experiments : JoVE*, 2014, 51046.
22. D. P. Das, D. A. v. d. Meer, M. A. Vivas, M. Y. B. Arik, P. J.-C. Remigy, D. J.-F. Lahitte, P. R. G. H. Lammertink and P. P. Bacchin, *Tissue Engineering Part A*, 2019, **0**, null.
23. S. H. Ma, L. A. Lepak, R. J. Hussain, W. Shain and M. L. Shuler, *Lab on a Chip*, 2005, **5**, 74-85.
24. D. E. Discher, P. Janmey and Y.-l. Wang, *Science*, 2005, **310**, 1139-1143.
25. M. Akhmanova, E. Osidak, S. Domogatsky, S. Rodin and A. Domogatskaya, *Stem Cells Int*, 2015, **2015**, 167025-167025.
26. Z. Gan, C. Wang and Z. Chen, *Surfaces*, 2018, **1**, 59-72.
27. W. F. Quirós-Solano, N. Gaio, C. Silvestri, Y. B. Arik, O. M. J. A. Stassen, A. D. v. d. Meer, C. V. C. Bouten, A. v. d. Berg, R. Dekker and P. M. Sarro, 2018.
28. H. Le-The, M. Tibbe, J. Loessberg-Zahl, M. Palma do Carmo, M. van der Helm, J. Bomer, A. van den Berg, A. Leferink, L. Segerink and J. Eijkel, *Nanoscale*, 2018, **10**, 7711-7718.
29. J. Gao, D. Guo, S. Santhanam and G. K. Fedder, *Journal of Microelectromechanical Systems*, 2015, **24**, 2170-2177.
30. T. Pasman, D. Grijpma, D. Stamatialis and A. Poot, *Journal of The Royal Society Interface*, 2018, **15**, 20180351.
31. C. J. Gottardi, M. Arpin, A. S. Fanning and D. Louvard, *Proceedings of the National Academy of Sciences of the United States of America*, 1996, **93**, 10779-10784.
32. A.-C. Luissint, C. Artus, F. Glacial, K. Ganeshamoorthy and P.-O. Couraud, *Fluids and Barriers of the CNS*, 2012, **9**, 23.
33. L. Cucullo, P.-O. Couraud, B. Weksler, I.-A. Romero, M. Hossain, E. Rapp and D. Janigro, *Journal of Cerebral Blood Flow & Metabolism*, 2008, **28**, 312-328.

34. M. Odijk, A. D. van der Meer, D. Levner, H. J. Kim, M. W. van der Helm, L. I. Segerink, J.-P. Frimat, G. A. Hamilton, D. E. Ingber and A. van den Berg, *Lab on a Chip*, 2015, **15**, 745-752.
35. N. L. Stone, T. J. England and S. E. O'Sullivan, *Frontiers in Cellular Neuroscience*, 2019, **13**.
36. A. Appelt-Menzel, A. Cubukova, K. Günther, F. Edenhofer, J. Piontek, G. Krause, T. Stüber, H. Walles, W. Neuhaus and M. Metzger, *Stem Cell Reports*, 2017, **8**, 894-906.
37. Y. Wang, N. Wang, B. Cai, G.-Y. Wang, J. Li and X.-X. Piao, *Neural regeneration research*, 2015, **10**, 2011-2017.
38. S. Halldorsson, E. Lucumi, R. Gómez-Sjöberg and R. M. T. Fleming, *Biosensors and Bioelectronics*, 2015, **63**, 218-231.
39. M. Tanyeri and S. Tay, in *Methods in Cell Biology*, eds. D. A. Fletcher, J. Doh and M. Piel, Academic Press, 2018, vol. 148, pp. 3-33.
40. K. Chris, L. K. E., L. Sylvia, M. D. W. and K. G. T., *Journal of Pharmacy and Pharmacology*, 2017, **69**, 1684-1696.
41. A. Al Ahmad, C. B. Taboada, M. Gassmann and O. O. Ogunshola, *Journal of Cerebral Blood Flow & Metabolism*, 2011, **31**, 693-705.
42. C.-H. Lai and K.-H. Kuo, *Brain Research Reviews*, 2005, **50**, 258-265.
43. A. Herland, A. D. van der Meer, E. A. FitzGerald, T.-E. Park, J. J. F. Sleeboom and D. E. Ingber, *PLOS ONE*, 2016, **11**, e0150360.

Three-dimensional semi-circular microvascular blood-brain barriers on-chip using hyaluronic acid based hydrogels

Most of the transport to the brain happens through the capillaries. Attempts have been made to recreate these microvessels on-chip. However, recently used methods do not allow for the controlled formation of small microvessels in a physiological relevant size range. A promising method for creating microvessels on-chip is the use of a hydrogel to create a cell-gel interface. These so-called lumens-in-a-gel allow for the formation of blood vessels in a biomimicking extra cellular matrix environment. In this chapter we show the formation of a small ($<50\text{ }\mu\text{m}$) lumen inside a hyaluronic acid based environment which eventually allows for direct electrical validation of the cell layer.

4.1 Introduction

Recreating vascular structures *in vitro* for endothelial cell culture ^{1,2}, disease modelling ^{3,4}, drug studies ⁵ and understanding complex cellular pathways ^{6,7}, has gained a lot of attention over the last decades. Several systems such as organ-on-chip (OOC) devices and Transwell based systems are often used to recreate structures that mimic vascular tissue. In both systems cells are cultured on a two-dimensional (2D) membrane, which serves as barrier between multiple cell types as well as providing a cell culture surface.

Despite the ability of OOC systems to mimic physiological factors such as fluid flow and shear stress which are necessary for cell mechanotransduction ⁶, most fail to recreate the physiological relevant three-dimensional (3D) structure of the desired tissue. Recently, more physiologically relevant *in vitro* models of microvasculature have been developed by the use of hydrogels ^{8,9}. Campisi *et al.* has been developing a system in which endothelial cells are seeded in a hydrogel matrix which leads to the spontaneous formation of a perfusable microvascular network having vessels with a diameter ranging from 10 to 100 μm ¹⁰. This bottom-up approach results in random formation of the vessel structure. A more controlled way of forming a vessel inside a hydrogel is by use of viscous finger patterning as reported by Herland *et al.* in 2016 ¹¹. Using this method, a hollow lumen (diameter around 600-800 μm) is created inside a collagen gel due to a difference in viscosity between the gel and the liquid that is used to form the lumen. Endothelial cells can be seeded inside this pre-engineered lumen after which a cell solution can be flown through the lumen to create a vessel-like structure. Another method that yields a similar lumen is microneedling ^{12, 13}, where a gel is cast around a thin (diameter; 160 μm) microneedle ¹⁴. After removing the needle, endothelial cells can be seeded inside the formed lumen. These methods are very robust and reproducible; however, they have the disadvantage that the final lumen size is always quite large ($> 100 \mu\text{m}$). Within the human brain, the capillaries form the BBB that separates the brain tissue from the blood stream ¹⁵. These capillaries have an average diameter of approximately 10 μm ¹⁶ and therefore our aim is to develop a method to make microvascular with a comparable size range on a microfluidic chip.

Hydrogels that are used for these methods are often easy to use gels such as collagen and fibrinogen, which have great cell culture possibilities. Yet, these

gels are not always able to resemble the physiological environment in the best possible way. During this study we try to fabricate a lumen inside a hydrogel which will be used for BBB research purposes. To increase the physiological relevance of the system, the used gel should resemble the extra cellular matrix (ECM) of the neurovascular unit (NVU). Fibrinogen and collagen are barely present in the brain, but hyaluronic acid (HA) is present in abundance¹⁷. For this reason, we chose to use a HA-based hydrogel to create a hydrogel chip. HA is a polysaccharide that is used extensively in biomedical applications because of its biocompatibility and biodegradability¹⁸. In the natural ECM, HA plays a role in cellular signalling, matrix organization and wound repair. To our knowledge, HA is a material that has not been used before in OOC systems.

Another advantage of using a hydrogel to form a channel is the possibility to create a cell-gel interface. Most ECM-like hydrogels are suitable for cell culture inside and on top of the gel. In the brain microenvironment, astrocytes play an important role in maintaining a proper barrier. By encapsulating astrocytes inside the hydrogel and growing endothelial cells on the outside of the gel, the physiology of the BBB can be recreated. Placone *et al.* showed that a gel mixture of HA, collagen and Matrigel is the ideal combination for a co-culture of endothelial cells on top and astrocytes embedded inside a gel matrix¹⁹. In a mixture of HA, collagen and Matrigel cells will be able to migrate through the gel to form direct cell-cell contacts.

In this chapter, we describe a fabrication method for the formation of lumens inside a HA-based hydrogel which potentially can be used to mimic the BBB to study its function and drug response. By altering the molecular weight of HA, mechanical properties can be changed such that gels with a proper stiffness to be used for our application can be designed. Here, we make use of a soft lithography approach to create a semi-circular channel inside a HA-based hydrogel. Microchannels have been made before using similar methods such as micromoulding, casting or imprinting. Zheng *et al.* and Ling *et al.* both describe a method in which a gel is made by casting an uncured gel over a surface containing a microstructure^{20,21}. To seal these channels, a second layer of hydrogel was used. As the channel diameter is determined by the microstructured surface, channel diameters smaller than 50 μm can be made. The method we propose here does not include a second layer of hydrogel to seal the channel, but instead the gel is attached directly onto a glass slide to

allow for better channel visualization and characterization of the created lumen. Using a glass slide, it becomes possible to validate the tightness of the cell layer by use of trans endothelial electrical measurements (TEER) inside a similar chip, which will be discussed in Chapter 5. In the current chapter, the placement of the channel directly on an empty glass slide is described, which allows for good real-time visualization of the cells that form the lumen using bright field microscopy.

4.2 Materials and Methods

4.2.1 Device design and fabrication

First a Delrin mould holder, which contains a lowered plateau used for placing an interchangeable silicon chip with channel features, was made using a micromilling machine (Datron NEO, NH, US). In this mould holder, there is space for a poly-methyl methacrylate (PMMA) support structure containing rectangular open channels, created by micromilling. The open channels can be addressed from the top through two shafts on each side of the open channels, the outer ones for hydrogel injection and the inner ones for addressing the imprinted channel structure. Additional shafts were created on the outside of the PMMA support to fixate the support into the mould holder using fixation plates and screws. The complete gel injection set-up is shown in Figure 1. Prior to hydrogel injection, the silicon chip must be placed in the lowered plateau of the mould holder and fixed with a small piece of double-sided tape to prevent movement during soft lithography.

The silicon chip with positive photoresist features was made by standard photolithography. A 4" silicon wafer was primed with hexamethyldisilazane (HMDS) prior to spin coating a layer of positive photoresist AZ®40XT (Microchemicals GmbH, Germany) (Step 1: 800 rpm, 100 r s⁻², 15 s; Step 2: 2500 rpm, 400 r s⁻², 30 s; Step 3: 3500 rpm, 1200 r s⁻², 1 s) to obtain a 30 µm thick layer. The resist was soft baked for 7 minutes at 126 °C. Using a mask alignment system (EVG620, EV Group, Austria), a channel pattern was transferred into the AZ®40XT resist for 40 seconds with a power of 12 mW cm⁻². After exposure the resist was baked for 100 seconds at 105 °C. The resist was developed using an OPD4246 developer for 3 minutes. To create semi-circular structures, the AZ®40XT was reflowed for 60 seconds at 140 °C. Prior to using the moulds, chips were diced and coated with perfluorodecyltrichlorosilane

(FDTs, abcr GmbH, Germany) by evaporation, each chip containing two channels that align perfectly with the PMMA support structure (Figure 2A).

FIGURE 1 EXPLODED VIEW OF THE HYDROGEL INJECTION SET-UP

4.2.2 Hydrogel chip fabrication

The hydrogel used in these experiments has to meet two crucial requirements. The first, being able to replicate the AZ®40XT channel structure. Secondly, the gel has to be able to bind to the glass substrate after channel formation. As successful experiments were already reported with agarose (3%), we used this gel as a positive comparison^{21, 22}. The elastic modulus of agarose (3%) is relatively high (19-32 kPa) compared to the elastic modulus of brain tissue, which is approximately 1.0 kPa²³. HA-based hydrogels more closely resemble multiple properties of the brain tissue including the brain tissue modulus. Therefore, not only agarose, but also HA-based hydrogels were used. These gels were made by the reaction between tyramine (TA) coupled HA and TA coupled dextran (Dex-TA). To ensure endothelial cell adhesion, gelatin was

added to the hydrogels prior to gelation. HA-TA/Dex-TA hydrogels with a final polymer concentration of 10% have a reported elastic modulus of approximately 10 kPa²⁴. Lower concentrations of 2.5% and 5.0% HA-TA/Dex-TA hydrogel with estimated moduli of approximately 7 kPa and 3 kPa respectively were included in these experiments.

Prior to hydrogel injection, the silicon chip was placed in the chip holder and the PMMA gel support was secured on the chip holder using fixation plates and screws. Agarose gels (1%, 2% and 3%) were prepared by dissolving agarose powder (low electroendosmosis (EEO), Sigma Aldrich, St. Louis, USA) in 1x phosphate buffered saline (PBS, Thermo Fisher Scientific, MA USA). Dissolution was initiated by heating up the mixture in a microwave according to manufacturer's protocol. HA-TA/Dex-TA hydrogels do not allow for endothelial cells attachment, therefore TA coupled gelatin (Gel-TA) was added to the HA-TA/Dex-TA mixture prior to injection. To create the HA-based hydrogel, HA-TA, Dex-TA and Gel-TA (all generously provided by the Developmental Bio Engineering group, University of Twente, the Netherlands) were mixed in a 1:1:0.05, 1:1:0.1 and 1:1:0.2 ratio to obtain polymer solutions of 3.1%, 6.2% and 12.5% w/v in 1x PBS respectively. The enzyme horse radish peroxidase (HRP, 311 U mL⁻¹ stock in PBS) was added to the gel solution to a final concentration of 5 U mL⁻¹. The mixture was shaken gently prior to overnight incubation at 4 °C to allow for equal distribution of components. To initiate gelation, freshly made hydrogen peroxide (H₂O₂ 30% w/v stock concentration, Sigma Aldrich, St. Louis, USA) with a final concentration of 0.015% w/v was added to the previously made gel. After proper mixing of the gel mixture, 30 µL gel per channel was injected into the PMMA holder using a 200 µL pipette tip (Figure 2B). Gels were incubated 10 minutes at room temperature (RT) after which the PMMA holder was transferred onto a glass slide for further analysis (Figure 2C).

4.2.3 Hydrogel chip validation

Once a successful channel had been formed inside the HA-TA/Dex-TA hydrogel, it should be sealed onto a glass slide to ensure that no liquid is able to migrate underneath the gel. To prepare the glass slide, it was pre-treated with oxygen plasma followed by a 30 minutes submersion in 3% (3-Aminopropyl)triethoxysilane (APTES, Sigma Aldrich, St. Louis, USA). The glass slides were washed with 70% ethanol followed by milliQ washing and air

drying. The TA-NHS used to functionalize the APTES coated glass surface was prepared by dissolving TA-NHS in dimethyl sulfoxide (DMSO, Sigma Aldrich, St. Louis, USA) and bicarbonate buffer (pH 8.6) to obtain a final concentration of 0.5 mg mL^{-1} . The APTES coated glass slides were incubated for 30 minutes at RT with the TA-NHS solution. HA-TA/Dex-TA pre-gels were prepared as reported in the previous section (4.2.2). To test attachment of the hydrogel to a TA-coated surface, two experiments were conducted. In the first experiment, the gelation process was initialized by adding H_2O_2 after which it was solidified for 10 minutes on a non-treated glass slide. After solidification, the hydrogel was transferred to a TA-coated glass slide. During the second experiment, a droplet of gel to which H_2O_2 was added was placed directly onto the TA-coated surface to allow crosslinking for 10 minutes.

Channel features could not be transferred successfully to HA-TA/Dex-TA hydrogels with a concentration of 2.5%. Therefore, the experiments described here were conducted with 1% agarose, 2% agarose, 5% HA-TA/Dex-TA and 10% HA-TA/Dex-TA. Channel formation was validated by measuring the width of the created channels and comparing this width with the feature dimensions from the used AZ®40XT mould. For these measurements, channels with a width of 40, 50 and 60 μm and a height of 22 μm were used ($n = 4$). Widths were measured using an EVOS FL cell imaging system (Thermo Fischer Scientific, MA, USA) and images were analysed using Leica Application Suite software (Leica Microsystems).

To validate whether the produced hydrogel chips were applicable for cell culture experiments, the sealing on the glass surface after crosslinking had to be studied. To assess the channel inside the hydrogel, a glass capillary (inner diameter: 250 μm , outer diameter: 380 μm , Postnova analytics) was punched through the gel into the open channel. To allow swelling of the hydrogel, distilled water (dH_2O) was flushed through the channel. A solution of 10 μm microbeads (Polysciences Inc., Germany) was flushed through the channel after swelling to assess the sealing of the gel to the glass surface (Figure 2C). The dispersion of the microbeads through the channel and the rest of the system was analysed optically using an EVOS FL cell imaging system.

4.2.4 Cell viability and morphology on HA-based hydrogels

As these hydrogel chips will be used for the *in vitro* formation of vasculature, the viability of human cerebral microvascular endothelial cells (hCMEC/D3) on the HA-based gels was assessed using a PrestoBlue™ viability assay. The 5.0% HA-TA/Dex-TA gel was most suitable for replicating the channel structure due to its stiffness and its ability to replicate the mould; therefore, this hydrogel composition was used to study biocompatibility. A pre-gel containing HA-TA, Dex-TA and Gel-TA was made according to reported protocol. The gel was finalized by adding H₂O₂. Plugs of gel were pipetted into a 96-wells plate where gels could solidify for 10 minutes at RT. To prevent gel dehydration, 200 µL endothelial cell growth medium (ECGM, Sigma Aldrich, St. Louis, USA) was placed on top of the gel. As a control, empty wells were coated with collagen-1 (50 µg mL⁻¹, rat-tail, Corning, NY, USA). HCMEC/D3 (Merck Millipore, MA, USA) were trypsinized and diluted to seeding concentrations of 7.5×10^4 cells cm⁻² and 15×10^4 cells cm⁻². A presto blue assay was conducted on day 1, 3, 5 and 7. Presto blue solution in cell culture medium (ratio 1:10) was added to the samples (n=3 per seeding density; n=2 for the gel only samples) and incubated for 4 hours at 37°C. From each well, 3 samples of 90 µL are taken to correct for pipetting errors. Samples were placed in a black 96-well plate after which they were analysed using a VICTOR³ plate reader (PerkinElmer, MA, USA). Statistical analysis was done by conducting two-way ANOVA tests using GraphPad Prism software (GraphPad Software, Inc., version 6.07 for Windows). Data was compared between time points for each substrate and seeding density, between different substrates per seeding density on the same time point and between the two cell seeding densities for each substrate on the same time point.

Cell morphology was analysed by immunofluorescent staining of actin filaments. HCMEC/D3 cells (same conditions as described for the viability assay) were grown for 24 hours on 5% HA-TA/Dex-TA/Gel-TA hydrogels after which they were fixed using 4% formaldehyde (Sigma Aldrich, St. Louis, USA) for 15 minutes at RT. Fixed samples were permeabilized using 0.1% Tween (Sigma Aldrich, St. Louis, USA) in 1.0% w/v BSA (in PBS 1x) for 10 minutes. Staining solution containing NucBlue® and ActinRed® (Thermo Fisher Scientific, MA, USA) was added to the samples followed by 15 minutes incubation at RT. Cells were imaged using an EVOS FL cell imaging system.

FIGURE 2 CROSS-SECTIONAL PROCESS FLOW OF HYDROGEL CHANNEL FORMATION. FIRST THE PMMA SUPPORT STRUCTURE IS PLACED INTO THE DELRIN MOULD HOLDER, RESULTING IN EXACT ALIGNMENT OF THE HYDROGEL INJECTION CAVITY ABOVE THE AZ@40XT PATTERNED SILICON CHIP (A). NOW THE HYDROGEL IS INJECTED INTO THE CAVITIES USING 200 μ L PIPETTE TIPS (B). ONCE THE GEL IS SOLIDIFIED, THE PMMA SUPPORT STRUCTURE FILLED WITH HYDROGEL IS TRANSFERRED ONTO A GLASS SLIDE. THE CREATED LUMEN INSIDE THE HYDROGELS CAN NOW BE ACCESSED THROUGH CAPILLARIES (C).

4.3 Results and Discussion

4.3.1 Hydrogel chip optimization

Prior to hydrogel chip transfer, the AZ@40XT channel transfer was assessed for all hydrogels. Except for the 2.5% HA-based hydrogel, all could be imprinted successfully. To assess reproducibility of the soft lithography, imprinting was repeated multiple times and analysed by bright field microscopy. In some cases, the imprinted channels show abnormalities. One type of abnormality is caused by impairments of the AZ@40XT photoresist which is mechanically influenced after many imprint replicates. The second abnormality is not caused by physical alteration of the mould. However, the chemical structure of the hydrogel seems to be altered locally resulting in a wavy structure of the gel.

The first impairment can be overcome by using the AZ®40XT mould a maximum of 20 times. The second impairment is solved by making fresh hydrogel solutions prior to each experiment.

The attachment of HA-based hydrogels to a TA-coated surface before and after crosslinking was tested by mechanical manipulation of the gels. In case that gels can crosslink on the TA-coated surface covalently, gel rupture should take place upon mechanical stress. However, when crosslinked gels were transferred to a TA-treated glass slide, the gel can be moved around freely, indicating no covalent binding. According to Wennink *et al.*, a decrease in gel concentration results in a shorter gelation time²⁴. HA-TA/Dex-TA hydrogels with a gel percentage of 10% form a hydrogel in approximately 10 seconds, meaning that a 5% gel will gelate within 10 seconds. As we were not able to inject and transfer the gel within 10 seconds, it is necessary to find a bonding method that seals the gel sufficiently to the glass surface even after full gelation has occurred. Although the gels did not attach covalently to the glass surface, the mechanical sealing of imprinted hydrogels on glass surfaces was assessed by flowing beads through the channel. As can be seen in Figure 3A the beads flow through the imprinted channel and do not migrate underneath the gel. However, in some cases, beads were able to escape the channel and end up underneath the gel (Figure 3B). It is hypothesized that isotropic shrinkage of the gel results in detachment from the surface. Shrinkage as a result from hydrogel dehydration can be prevented by adding a droplet of PBS to the glass surface prior to hydrogel transfer.

Another channel characteristic that was analysed is the replication quality of the AZ®40XT mould. Replication quality is measured by measuring the width of the imprinted channel on a glass slide and comparing this with the actual width of the photoresist channel feature. Results show that successful replication of channel features is possible. However, the actual measured channel width deviates from the width on the silicon chip (see Figure 4) for both agarose and HA-based gels. This can be the result of multiple factors such as hydrogel swelling²⁵ and the previously mentioned adherence of the gel to the support structure and to the glass. During this experiment, two different channel geometries were compared, being semi-circular channels (width 40 and 60 μm) and square channels (width 50 μm). It is hypothesized that the hydrostatic force distribution on top of the channel has an influence on how the gel can deform at the glass/gel interface. Semi-circular channels are

therefore able to deform differently due to the horizontal load distribution. The force distribution on a square channel is perpendicular to the top of the channel and equal along the surface whereas the force on top of the semi-circular channel is not perpendicular.

FIGURE 3 IMPRINTED CHANNELS IN 5% HA-TA/Dex-TA/Gel-TA HYDROGEL. 10 μM BEADS WERE INJECTED IN THE CHANNEL. SOME PARTS OF THE CHANNEL ARE PROPERLY SEALED ONTO THE GLASS SLIDE, PREVENTING THE BEADS FROM LEAVING THE CHANNEL (A). SOME PARTS ARE NOT SEALED PROPERLY, LEADING TO MIGRATION OF BEADS OUT OF THE CHANNEL, UNDERNEATH THE HYDROGEL (B). THE RED DASHED LINES INDICATE THE BORDERS OF THE IMPRINTED CHANNEL. SCALEBARS REPRESENT 200 μM .

The most consistent replication of channel features was achieved by the 2% agarose gel and the 10% Ha-TA/Dex-TA/Gel-TA gel, whereas they both show a good final channel width in correspondence with the silicon chip that was used. Note that we observe an increased hydrogel channel width for the stiffest agarose gel which is often used in literature ^{21, 22}. As there is no logical chemical explanation for this increase, it is thought that the gel is not able to attach properly to the glass slide, causing an observation in a wrong focus plane leading to an increased estimation of the channel width. This can be checked by adding a visible structure to the glass slide. This might also be the case for the 5% Ha-TA/Dex-TA/Gel-TA gel as we have shown for this mixed gel that attachment to the glass is not optimal (Figure 3B).

FIGURE 4 DIAMETER OF THE CREATED CHANNELS AS A RESULT OF THE MOULD DIMENSION. IN TOTAL, 3 DIFFERENT SIZE MOULDS WERE USED BEING; $D=40\ \mu\text{m}$ (SEMI-CIRCULAR), $D=50\ \mu\text{m}$ (SQUARE) AND $D=60\ \mu\text{m}$ (SEMI-CIRCULAR). THE USED SILICON CHIPS WERE MEASURED AND PLOTTED TO VALIDATE THE SUCCESS OF THE PHOTOLITHOGRAPHY PROCESS (GREEN CUBES). THE TOP GRAPH SHOWS THE RESULT OF AGAROSE GELS WITH DIFFERENT GEL CONCENTRATIONS (1%, 2% AND 3%). THE BOTTOM GRAPH SHOWS THE CREATED CHANNEL DIAMETERS IN HA-BASED GELS (HA-TA/Dex-TA/Gel-TA 5% AND 10%) ($N=3$ FOR EACH GEL AND EACH MOULD).

4.3.2 Cell culture on HA-based hydrogels

To study the cell culture applicability of HA-based hydrogels, hCMEC/D3 were cultured on 5% HA-TA/Dex-TA/Gel-TA hydrogels as well as on collagen-I coated surfaces which are used as a positive control. During this culture, cell morphology as well as cell viability were monitored. It is known that these cells are able to grow and form a proper monolayer on collagen-I coated tissue culture plastic (TCP)²⁶. As can be seen in Figure 5 (A, E, I and M), both seeding densities resulted in the formation of a cell monolayer after one day of culture on both surfaces. The characteristic cobblestone morphology of the endothelial cells cultured on the gels is comparable to the morphology of the cells cultured on the collagen-I coated surface. The final concentration of supplemented gelatin used in these experiments was 0.5 mg mL⁻¹ and 1 mg mL⁻¹. No significant difference in cell morphology nor viability of the cells on these two mixed gels could be observed. However, there is a significant difference in cell viability when the cell seeding density is changed. As can be seen from the presto blue assay in Figure 6, a lower seeding density, from day 3, results in a significant higher cell viability on HA-based hydrogels. This higher viability does not directly match with the results obtained from the immunofluorescence images. A possible explanation for this observation is the washing steps prior to fluorescently labelling the cells. These washing steps take out the dead cells from the monolayer leaving an optically healthy-looking cell layer.

Cells that were cultured on top of the HA-based hydrogel are able to remodel the gels which can be concluded by the irregularity of the focus plane that increases over time (Figure 5 E-H and Figure 5 M-P). Zheng *et al.* reported on this hydrogel remodelling by HUVECs that were cultured onto a collagen-I hydrogel matrix²⁰. In their research, cells were grown in a rectangular shaped channel and within 3 days of culture, the cells had remodelled the channel into a circular shape. A noteworthy difference between the collagen-I gels used by Zheng *et al.* and the HA-based gels used in this research is that the HA-based gels have an elastic modulus which is one order of magnitude higher. This increase in stiffness does not seem to influence the cells negatively. Cellular contraction leading to hydrogel deformation might also result in a decrease of total hydrogel volume²⁷ which is not desirable when using the gel as final device.

FIGURE 5 HCMEC/D3 SEEDING IN 7.5×10^{-4} CELLS CM^{-2} (A-H) AND 15×10^{-4} CELLS CM^{-2} (I – P) DENSITY ON A COLLAGEN-1 COATED SURFACE AND ON HA-TA/DEX-TA/GEL-TA GELS (1 mg mL^{-1}). CELLS ARE LABELLED FLUORESCENTLY TO OBSERVE THE CELL MORPHOLOGY OVER TIME. NUCLEI ARE LABELLED WITH NUCBLUE (BLUE) AND ACTIN FILAMENTS ARE LABELLED WITH ACTINRED (RED). NO CLEAR DIFFERENCES IN FLUORESCENT INTENSITY CAN BE SEEN IN THESE IMAGES AS ALL CONDITIONS SHOW A WELL GROWN CELL LAYER FROM DAY 1 TO 7. IT CAN BE SEEN THAT OVER TIME, THE IMAGES BECOME BLURRY AT RANDOM PLACES INDICATING REMODELLING OF THE GEL BY THE CELLS. SCALEBARS REPRESENT $400 \mu\text{M}$.

Even though these results show a good cell viability on the 5% HA-TA/Dex-TA/Gel-TA hydrogels, the conditions used during these static experiments are not similar to the conditions that cells will be exposed to in the proposed microfluidic device. In such a closed device, cells experience a limited nutrient supply, limited waste removal and increased exposure to shear stress; the latter with physiological relevance. Previous research has shown that cell culture under these conditions inside a microfluidic channel is possible ^{12, 28}.

FIGURE 6 THE INTENSITY MEASURED USING A PRESTO BLUE ASSAY IS CORRECTED FOR CELL NUMBER, SHOWING THE INTENSITY PER HCMEC/D3 CELL IN VARIOUS CONDITIONS. THE RESULTS ARE NORMALIZED TO A TIME AND SUBSTRATE MATCHED CONTROL. HCMEC/D3 ARE CULTURED ON COLLAGEN-I AS A POSITIVE CONTROL AS THIS IS KNOWN AS REGULAR CULTURE CONDITION. TWO DIFFERENT CELL SEEDING DENSITIES WERE USED. THE TIME POINTS (T1-T4) CORRESPOND TO 1, 3, 5 AND 7 DAYS AFTER CELL SEEDING RESPECTIVELY. SIGNIFICANCE: *** REPRESENTS P-VALUE $\leq$ 0.001

4.4 Conclusion and Outlook

To create a more physiologically relevant representation of a brain capillary *in vitro*, we have developed a system where we use soft lithography to imprint a small (<50 µm) channel structure into a HA-based hydrogel. Using microfabrication technologies, a holder is created in which a channel is milled. By placing the holder onto a silicon chip containing a positive mould structure, a cavity is created in which a hydrogel can be injected. A HA-based hydrogel composed of HA-TA, Dex-TA and Gel-TA was injected successfully into the cavity. The hydrogel concentration should be at least 5% to allow for good transfer of the photoresist mould into the gel by soft lithography. Agarose, a gel that was often used for soft lithography applications is used to compare the gelating and cell culture results of the HA-based gels with. Exact replication of

the dimensions of the photoresist into the gel was not possible for all gels. However, most gels show a good replication when the actual width is compared with the mould width of the used silicon chip. Especially the 10% HA-TA/Dex-TA/Gel-TA and the 2% agarose hydrogels show a good replication of the used moulds. Once the gels were fully gelled, the PMMA support structure was transferred to a glass slide. To assess good sealing of the gel onto the glass slide, a solution containing micro beads was flushed through the channels to observe possible leakages. Beads were found inside the channels along the entire length, however at some spots, beads were able to migrate underneath the gel indicating lack of sealing. Better sealing was attempted by allowing the hydrogel to swell by immersion in a buffer solution, prior to adhering to the glass slide. This did not result in full sealing of the channel as beads were still found outside the channel. To overcome the problem of bad hydrogel to glass adherence, glass slides were treated with TA prior to placing the hydrogel on top, to allow for chemical attachment of the gel to the surface. However, all the reactive sites in the hydrogel were used during crosslinking resulting in no covalent binding to the TA coated surface. Partially curing the hydrogel prior to contact with the coated surface was in this setting not possible as the gel was too soft for channel transfer to be successful. So far, clamping the hydrogel channel tightly onto the glass slide seemed the best way to obtain a relatively well sealed channel. For future experiments, the glass surface can be treated with an extremely thin layer of hydrogel such that the system still allows for electrical and optical analysis through the glass slide. This method has proven to work multiple times, however in all the previously published work, the extra layer of hydrogel is relatively thick ^{20, 21, 29}.

HA-based hydrogels with a gel concentration of 5% and 10% were used as cell culture surface to see whether the stiffness and composition of these gels has an influence on the viability or the morphology of the cells. Within these experiments, the seeding density of the endothelial cells as well as the concentration of added gelatin was varied. Only an increase in seeding density showed to have an influence by showing a lower cell viability compared to the lower seeding density. Furthermore, all other conditions show a high cell viability after 7 days of culture. Deformation of the gel was observed in some samples, indicating the remodelling ability of the cells despite the relatively high elastic modulus of the gel (~5-10 kPa). This deformation might lead to a decrease in hydrogel volume. Once the hydrogel chip is formed and cells are

starting to reduce the gel volume by remodelling, the adherence of the hydrogel to the support structure and the bottom glass slide might be disrupted. Therefore, proper adhesion of the hydrogel to the surrounding surface should be optimized further. The cell seeding experiments in this study are all carried out in 2D, meaning that the cells do not experience the same environmental morphology as they would inside a microfluidic channel. Furthermore, cells lack the shear stress caused by fluid flow. In future experiments, we attempt to culture cells inside the small microfluidic channels imprinted in the hydrogels to see whether they are able to form a physiologically relevant cell layer which is applicable for further research.

4.5 References

1. J. W. Song, W. Gu, N. Futai, K. A. Warner, J. E. Nor and S. Takayama, *Analytical Chemistry*, 2005, **77**, 3993-3999.
2. A. Reinitz, J. DeStefano, M. Ye, A. D. Wong and P. C. Searson, *Microvascular research*, 2015, **99**, 8-18.
3. S. Kim, W. Kim, S. Lim and J. S. Jeon, *Bioengineering*, 2017, **4**, 8.
4. A. Cochrane, H. J. Albers, R. Passier, C. L. Mummery, A. van den Berg, V. V. Orlova and A. D. van der Meer, *Advanced Drug Delivery Reviews*, 2018.
5. C. E. Fernandez, R. W. Yen, S. M. Perez, H. W. Bedell, T. J. Povsic, W. M. Reichert and G. A. Truskey, *Scientific reports*, 2016, **6**, 21579-21579.
6. S. Chien, *American Journal of Physiology-Heart and Circulatory Physiology*, 2007, **292**, H1209-H1224.
7. R. G. Mannino, D. R. Myers, B. Ahn, Y. Wang, R. Margo, H. Gole, A. S. Lin, R. E. Guldberg, D. P. Giddens, L. H. Timmins and W. A. Lam, *Scientific Reports*, 2015, **5**, 12401.
8. J. Nie, Q. Gao, Y. Wang, J. Zeng, H. Zhao, Y. Sun, J. Shen, H. Ramezani, Z. Fu, Z. Liu, M. Xiang, J. Fu, P. Zhao, W. Chen and Y. He, *Small*, 2018, **14**, 1802368.
9. Y. Shin, S. Han, J. S. Jeon, K. Yamamoto, I. K. Zervantonakis, R. Sudo, R. D. Kamm and S. Chung, *Nature Protocols*, 2012, **7**, 1247.
10. M. Campisi, Y. Shin, T. Osaki, C. Hajal, V. Chiono and R. D. Kamm, *Biomaterials*, 2018, **180**, 117-129.
11. A. Herland, A. D. van der Meer, E. A. FitzGerald, T.-E. Park, J. J. F. Sleeboom and D. E. Ingber, *PLOS ONE*, 2016, **11**, e0150360.
12. K. M. Chrobak, D. R. Potter and J. Tien, *Microvascular Research*, 2006, **71**, 185-196.
13. A. Yamada, R. Renault, A. Chikina, B. Venzac, I. Pereiro, S. Coscoy, M. Verhulsel, M. C. Parrini, C. Villard, J.-L. Viovy and S. Descroix, *Lab on a Chip*, 2016, **16**, 4691-4701.
14. W. J. Polacheck, M. L. Kutys, J. B. Tefft and C. S. Chen, *Nature Protocols*, 2019, **14**, 1425-1454.
15. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.

16. C. M. Peppiatt, C. Howarth, P. Mobbs and D. Attwell, *Nature*, 2006, **443**, 700-704.
17. J. R. Sanes, *Annual Review of Neuroscience*, 1989, **12**, 491-516.
18. J. A. Burdick and G. D. Prestwich, *Advanced Materials*, 2011, **23**, H41-H56.
19. A. L. Placone, P. M. McGuiggan, D. E. Bergles, H. Guerrero-Cazares, A. Quiñones-Hinojosa and P. C. Searson, *Biomaterials*, 2015, **42**, 134-143.
20. Y. Zheng, J. Chen, M. Craven, N. W. Choi, S. Totorica, A. Diaz-Santana, P. Kermani, B. Hempstead, C. Fischbach-Teschl, J. A. López and A. D. Stroock, *Proceedings of the National Academy of Sciences*, 2012, **109**, 9342-9347.
21. Y. Ling, J. Rubin, Y. Deng, C. Huang, U. Demirci, J. M. Karp and A. Khademhosseini, *Lab on a Chip*, 2007, **7**, 756-762.
22. S.-Y. Cheng, S. Heilman, M. Wasserman, S. Archer, M. L. Shuler and M. Wu, *Lab on a Chip*, 2007, **7**, 763-769.
23. S. Budday, R. Nay, R. de Rooij, P. Steinmann, T. Wyrobek, T. C. Ovaert and E. Kuhl, *Journal of the mechanical behavior of biomedical materials*, 2015, **46**, 318-330.
24. J. W. H. Wennink, K. Niederer, A. I. Bochyńska, L. S. Moreira Teixeira, M. Karperien, J. Feijen and P. J. Dijkstra, *Macromolecular Symposia*, 2011, **309-310**, 213-221.
25. H. Holback, Y. Yeo and K. Park, in *Biomedical Hydrogels*, ed. S. Rimmer, Woodhead Publishing, 2011, pp. 3-24.
26. E. Colombo, F. Calcaterra, M. Cappelletti, D. Mavilio and S. Della Bella, *PLOS ONE*, 2013, **8**, e66734.
27. M. Ahearne, *Interface Focus*, 2014, **4**, 20130038-20130038.
28. N. Koike, D. Fukumura, O. Gralla, P. Au, J. S. Schechner and R. K. Jain, *Nature*, 2004, **428**, 138-139.
29. Y. Qiu, B. Ahn, Y. Sakurai, C. E. Hansen, R. Tran, P. N. Mimche, R. G. Mannino, J. C. Ciciliano, T. J. Lamb, C. H. Joiner, S. F. Ofori-Acquah and W. A. Lam, *Nature Biomedical Engineering*, 2018, **2**, 453-463.

Impedance spectroscopy in a semi-circular blood-brain barrier on-chip to assess barrier properties

Organ-on-chip systems strive to become more and more realistic representations of the in vivo situation. Using microfabrication techniques, physiologically relevant structures can be created in which patient specific tissues are cultured. These systems all have their own limitations. Vessels on-chip are often relatively large and show variations between experiments. Smaller, more capillary-like models give a better representation of the in vivo situation. However, these capillary-like models lack the ability to properly characterize the cultured cell layer in real-time. Here we developed a brain capillary on-chip cultured onto an array of electrodes which can be used to measure the trans-endothelial electrical resistance of the cultured cell layer.

This Chapter is adapted from:

Assessing barrier properties using impedance spectroscopy in a semi-circular blood-brain barrier on-chip
F. Avgidis[†], M.P. Tibbe[†], D.S. de Bruijn, A.M. Leferink, J.C.T. Eijkel and L.I. Segerink ([†] These authors contributed equally)

Manuscript in preparation

5.1 Introduction

The blood-brain barrier (BBB) is a biological structure that acts as a “gatekeeper” between the peripheral blood circulation and the central nervous system (CNS). It tightly controls the flux of solutes from the blood to the brain, only allowing the passage of chemicals that are necessary for neuronal functioning. The main structural elements of the BBB are cerebral blood vessels with a radius of several micrometres. A network of over 600 km of these capillaries delivers the necessary nutrients to the brain ¹. These capillaries are formed by endothelial cells tightly packed together to form a continuous cylindrical structure. An important characteristic of cerebral capillaries that differentiates them from capillaries in the rest of the body, is the presence of intercellular tight junctions. These tight junctions restrict the paracellular transport of solutes ². Disruption of these tight junctions is associated with several diseases such as Alzheimer’s disease ³, stroke ⁴, encephalopathy ⁵, and Parkinson’s disease ⁶. Nevertheless, reversible tight junction disruption can also be beneficial if employed as a gateway for drug delivery to the brain. Hence, high-fidelity *in vitro* models of the BBB could, on the one hand, assist in better understanding the biological origins of diseases that affect the BBB and, on the other hand, allow for better screening of novel neurotherapeutics ⁷.

Although the physiology of the BBB has been thoroughly investigated in primary cultures of brain endothelial cells, these traditional cell cultures do not imitate the actual, three-dimensional structure of cerebral blood vessels, and do not allow for label-free assessment of the barrier tightness. The latter has been addressed with the advent of the Transwell system. This system consists of two fluidic compartments separated by a porous polymer membrane, making the investigation of the permeability of the cell layer possible. Furthermore, Transwell systems allow for the insertion of an electrode in each compartment that can then be used to measure trans-endothelial electrical resistance (TEER), a quantitative measure of the integrity of tight junctions in cell monolayers ⁸. Although TEER measurements in Transwell systems are presented very regularly in literature, the TEER values reported show significant variability ⁹. This has been attributed to two factors: first, the electrodes are most often manipulated manually, and their location with respect to the porous membrane can affect the resistive readout ¹⁰ and second,

it is often assumed that the entire cell culture area contributes equally to the measurement, which has been shown to be false ¹¹.

Recent alternatives to the Transwell system are microfluidic models of the BBB that allow for better emulation of the physiology of the cortical capillary, while consuming minimal amounts of reagents. Over the past few years, several such microfluidic “organ-on-chip” (OOC) systems were developed to imitate BBB functionality on-chip. Most of these systems integrate electrodes for the electrical assessment of the barrier tightness. Nevertheless, instead of recreating the three-dimensional structure of a cortical capillary, the vast majority of these models include a non-physiological membrane that separates the basolateral and apical fluidic compartments ^{7, 12-17}. Therefore, all these models recreate a two-dimensional (2D) endothelial layer rather than a three-dimensional capillary. Conversely, a few microfluidic models of the BBB do imitate the actual circular shape of a capillary, but they do not exhibit the appropriate physiologically relevant size and do not allow for electrical assessment of the barrier tightness due to design limitations ^{18,19}.

Here, we present an adapted version of the BBB model presented in Chapter 4. This model, unlike previously reported models, reflects the actual size and circular shape of a human brain microvessel, while still allowing for real-time and label-free assessment of the barrier integrity through an array of integrated electrodes. We have employed finite element modelling to optimize the geometry and placement of the integrated electrodes in order to achieve high sensitivity and linearity between measured resistance and TEER values. Unlike many previously reported models that relied on the insertion of metal wires acting as electrodes above and below the cultured cells on-chip ^{7, 17, 20}, we chose to use electrodes sputtered on a glass substrate. This allows us to minimize the cost of the device by reusing the same electrodes over multiple microfluidic devices, while ensuring that the relative position of the electrodes with respect to the channel is always the same. To assess the barrier integrity, impedance spectroscopy using 4 electrodes can be performed which allows us to extract both cell layer resistance and capacitance while being less prone to the influence of the electrode-electrolyte interface compared to 2-point impedance spectroscopy ¹¹. Simultaneously, immunofluorescent staining of the tight junction protein zonula occludins-1 (ZO-1) ²¹ can be conducted to correlate changes in impedance with changes in protein localization. As a proof of concept, we employed this immunofluorescent staining to study the

possibility to transiently modulate the tightness of the BBB in a dose-dependent manner by altering the calcium concentration of the cell medium²². Temporarily impairing the tight junction proteins, which reduces the overall tightness of the cell layer, is useful for targeted drug delivery to the CNS²³. Subsequently, to validate the use of our OOC system in drug response experiments, we studied the role of a common antioxidant, vitamin C, in induced oxidative stress. To achieve a high-fidelity BBB model, it is essential to couple the physiological effect of astrocytes on the cortical capillary. Co-culture of astrocytes and brain endothelial cells has shown to upregulate the expression of tight junctions, enzymes, and transporters^{24, 25}. However, it has been shown by Cucullo *et al.* that the influence on barrier tightness is dependent on the used cell type²⁶. In the human brain, astrocytes do not make direct contact with endothelial cells; instead, the two cell types are separated by the basal lamina, a 20 to 100 nm thick layer of extracellular matrix²⁷. Therefore, we hypothesized that growing the cortical capillary in the presence of astrocyte-conditioned medium could have a similar effect on the endothelial cells compared to a co-culture with astrocytes. We elucidated this effect by observing differences in ZO-1 expression by cells grown in the presence and absence of astrocyte-conditioned medium and then challenging them with hydrogen peroxide (H_2O_2), a common oxidizer that damages tissue via oxidative stress. The latter is to test the observation that astrocyte co-culture upregulates antioxidant enzymes in endothelial cells²⁸.

5.2 Materials and Methods

5.2.1 Device design and fabrication

The BBB on-chip consists of a pair of microchannels patterned in polydimethylsiloxane (PDMS), bonded on a glass substrate with embedded electrodes. Each microchannel has a length of 8 mm and a radius of approximately 27 μm , with the total volume of each microchannel being below 10 nL. Each PDMS device consists of two separate parallel channels. Forty-four platinum electrodes are located at the bottom of each microchannel, which can be used to address different micrometer-long regions of the cortical microvessel independently. The effective area of each electrode is $30 \times 60 \mu\text{m}^2$. Electrodes are grouped in sets of four, with the distance between each pair being 200 μm . We arrived at this design through finite element simulations with the purpose of maximizing sensitivity and linearity between measured

resistance and TEER. All electrodes have accessible connection pads at the edges of the glass substrate. A holder was designed and milled in poly-methyl methacrylate (PMMA) using a CNC mill (Datron Neo, NH, USA) and subsequently fitted with spring contacts to allow the electrical interfacing between the assembled chip and an impedance analyser. Microscale features were fabricated on a silicon wafer using the AZ®40XT positive photoresist (Microchemicals GmbH, Germany). The photoresist was reflowed by ramping the temperature of the wafer from 60°C to 140°C (12°C min⁻¹) and then baking it at 140°C for 60 seconds to achieve semi-circular channels with a height of approximately 27 µm. The wafer was then coated overnight with chlorotrimethylsilane (CTMS; Sigma-Aldrich, MO, USA) to avoid PDMS adhesion. PDMS prepolymer (Sylgard 184; Dow Corning, MI, USA) was then mixed thoroughly with curing agent at a 10:1 w/w ratio and the mixture was poured over the silicon wafer containing the microscale structures. Then, the PDMS structure was degassed for 30 minutes in a vacuum desiccator and subsequently cured at 80°C for 2 hours. The PDMS slice with the channel imprints was then peeled from the silicon wafer, and two inlets were punched at either end of each channel using a biopsy puncher with a diameter of 0.5 mm. PDMS devices were then rinsed with isopropanol, ethanol, and distilled water and dried using compressed air. To fabricate glass slides containing recessed platinum electrodes, MEMpax® borosilicate glass wafers were cleaned in fuming nitric acid, after which the electrode pattern was patterned onto the glass surface by standard photolithography. Bare areas were wet etched in a buffered hydrogen fluoride (HF) etchant (BOE 7:1, Technic) to a depth of 135 nm. To allow for platinum adhesion, a 10 nm thick layer of tantalum was sputtered onto the surface followed by sputtering a 125 nm thick layer of platinum using an in house made DC sputter gun with 200 W sputtering power at 0.66 Pa. When dissolving the photoresist in acetone, the residual platinum outside the electrode area was removed. Glass wafers were diced into 25 x 75 mm² sized slides. To facilitate the bonding of the PDMS devices to the glass slide containing the sputtered electrodes, both surfaces were activated in an oxygen plasma at 50 W for 40 seconds. If a glass slide was reused, residual PDMS was removed by immersing the slide in acetone overnight. Alignment of the channel and the electrodes was achieved manually under a stereoscopic microscope. To ensure more permanent sealing of the two surfaces, the bonded devices were placed at 80°C for 90 minutes. The complete device design is shown in Figure 1.

FIGURE 1 EXPLODED VIEW OF THE DEVICE. INSET: PHASE CONTRAST IMAGE OF ONE OF THE TWO CHANNELS. THREE OUT OF ELEVEN ELECTRODE SETS ARE SHOWN.

5.2.2 Electrical simulations

When the impedance of a cell layer is assessed using 4-point impedance spectroscopy, not all sub-volumes of the cell layer contribute equally to the total impedance. Cell volumes closer and between the electrodes contribute more significantly than volumes far from the electrodes. We define a current-carrying pair of electrodes that is used to inject current and a pick-up pair that measures the subsequent voltage drop. The generated field is picked up the strongest by the pick-up pair when it is exactly in line with the field generated by the current-carrying pair²⁹, Supplementary Figure B1 illustrates this effect. This effect can be expressed by a quantity termed “sensitivity”. The sensitivity of a sub-volume is a measure of the contribution of this volume on the total impedance of the cell layer, and it is defined as^{30, 31}:

$$S = \frac{\mathbf{J}_1 \cdot \mathbf{J}_2}{I^2} \quad (1)$$

Where $\mathbf{J}_1$ and $\mathbf{J}_2$ are the current density fields produced as a result of a current I injected through the current-carrying electrodes and pick-up electrodes, respectively¹¹. A larger positive sensitivity value means that the given sub-volume has greater influence on the total impedance. Interestingly, there are also zones of negative sensitivity, where the contribution to the total impedance is underestimated. Using finite element modelling (COMSOL Multiphysics, version 5.1), we performed a series of simulations to determine

Impedance spectroscopy in a semi-circular blood-brain barrier on-chip to assess barrier properties

the optimal electrode configuration to minimize non-linearities in the sensitivity of the system.

5.2.3 Impedance spectroscopy measurements

All impedance measurements were performed using the HF2IS Impedance Spectroscope (Zurich Instruments, Switzerland) operating in 4-point measurement configuration. Schematics of the connection topologies are shown in Supplementary Figure B2.

FIGURE 2 (A) SCHEMATIC REPRESENTATION OF THE SEMI-CYLINDRICAL CHANNEL WITH A LAYER OF ENDOTHELIAL CELLS GROWN ON A GLASS SLIDE PATTERNED WITH ELECTRODES. (B) EQUIVALENT LUMPED ELEMENT CIRCUIT USED FOR THE FIT.

Impedance spectra were fitted using a custom Matlab script (Matlab, version R2018A) with the transfer function of an equivalent lumped-element circuit as seen in Figure 2B. During impedance measurements and ZO-1 visualization, the devices were taped on a heated microscope stage that maintained the temperature at 37°C.

5.2.4 Cell culture and immunofluorescence

Immortalized human cerebral microvascular endothelial cells (hCMEC/D3 cell line, passages 29 to 36; Merck Millipore, MA, USA) were cultured in endothelial growth medium (EGM; Cell Applications, Inc., San Diego, CA, USA) in T75 culture flasks, coated with 40 mg mL⁻¹ human plasma fibronectin (YoProteins, Sweden) in phosphate buffered saline (PBS; Sigma-Aldrich). Cell cultures were maintained in a humidified water-jacketed incubator (37°C, 5% CO₂) and flasks with >70% confluency were subcultured, and the remaining cells were seeded in devices. Astrocyte-conditioned medium was obtained by cultivating primary human astrocytes (ScienCell Research Laboratories, CA, USA) for two days in astrocyte growth medium supplemented with 2% v/v fetal bovine serum, 1% astrocyte growth supplement (AGS, 100x), and 1% penicillin/streptomycin solution (P/S, 10,000 units mL⁻¹ of Penicillin and 10,000 µg mL⁻¹ of Streptomycin), all from ScienCell Research Laboratories, CA, USA. Before cell seeding, the microfluidic channels were coated with 80 mg mL⁻¹ fibronectin (YoProteins, Sweden) in PBS for at least 4 hours at 37°C. Subsequently, the channels were filled with EGM and stored for an additional 45 minutes at 37°C. Endothelial cells were detached from confluent flasks using 0.05% trypsin-EDTA (Gibco). Cells were resuspended in fresh EGM and diluted to a concentration of 6 x 10⁶ cells mL⁻¹ which corresponds to approximately 55 cells per microchannel. PBS was pipetted on top of each PDMS device to ensure that the two inlets are at the same hydrostatic pressure and cells were injected through a single inlet using a 0.5 mm syringe needle. This seeding method minimizes the amount of air bubbles in each channel during cell seeding and ensures that cells are not washed away from the channel due to pressure difference created from a slight mismatch in the fluid volume of the inlets. After 1 hour of static incubation, pipette tips filled with equal amounts of EGM were inserted in both inlets to act as reservoirs. The medium was refreshed daily for the duration of each experiment by inserting new pipette tips filled with fresh medium in the inlets. Depending on the experiment, the endothelial medium was supplemented either with 1 mM ascorbic acid (vitamin C; Sigma-Aldrich) or 50% v/v astrocyte-conditioned medium. In experiments where the tight junctions were transiently modulated, EGM was replaced with either ethylenedis(oxyethylenenitrilo)tetraacetic acid (EGTA; Sigma-Aldrich) or adenosine triphosphate (ATP; Sigma-Aldrich) in PBS.

Cells were analysed by immunofluorescence staining of either actin filaments (F-actin) or the tight junction protein zonula occludens-1 (ZO-1). For F-actin staining, cells were washed with pre-warmed PBS and then fixed for 30 minutes at room temperature with 2.5% v/v Glutaraldehyde (Sigma-Aldrich) in PBS. Following a washing step with PBS, cells were permeated for 15 minutes at room temperature with 0.3% v/v Triton-X (Sigma-Aldrich) in PBS. After washing with PBS, actin filaments were stained with ActinRed and nuclei were stained with NucBlue (2 drops of each dye per 1 mL PBS; both from ReadyProbes Reagent, Molecular Probes, Life Technologies) for 30 minutes at room temperature. Finally, cells were washed again in PBS. For ZO-1 staining, cells were washed with pre-warmed PBS and then fixed for 20 minutes at room temperature with 2.5% v/v glutaraldehyde in PBS. Following a washing step with PBS, cells were permeated and blocked for 30 minutes at room temperature with 0.1% v/v Triton-X and 5% w/v bovine serum albumin (BSA; Sigma-Aldrich) in PBS. After washing again with PBS, cells were incubated for 90 minutes at room temperature with 5 $\mu\text{g mL}^{-1}$ primary anti-ZO-1 antibody (rabbit polyclonal antibody; Thermo Fisher Scientific) and 0.5% w/v BSA in PBS. The cells were then washed with PBS supplemented with 0.1% w/v BSA and incubated for 1 hour at room temperature with 5 $\mu\text{g mL}^{-1}$ secondary antibody conjugated with Alexa Fluor 488 (goat anti-rabbit; Abcam, UK) in PBS. Finally, the nuclei were stained with NucBlue (2 drops per 1 mL PBS) for 20 minutes at room temperature, and cells were washed a final time in PBS. Images were captured with either a Nikon Instruments A1 confocal laser microscope or with an EVOS M5000 imaging system and analysed with ImageJ.

After exposure to the calcium depleting ligands EGTA and ATP, cells in control cultures were analysed using immunofluorescence to see whether altered localization of the tight junction protein ZO-1 happens, which would be in accordance with the expected outcome of the experiment. Cells in control cultures were grown in glass-bottom wells (GWST-5030; WillCo Wells B.V., Amsterdam, The Netherlands) coated with 80 mg mL^{-1} human plasma fibronectin in PBS. For each condition, we performed two to four technical replicates. Cells used for seeding the microfluidic device and the control culture originated from a clonal population. To quantify ZO-1 localization, greyscale images of up to 400 cells for each technical replicate were captured, and the number of localized, cell-to-cell junctions was extracted. All data are expressed as the mean number of localized tight junctions per replicate,

normalized by the number of nuclei. Apoptotic cells (apparent due to the presence of lysosomes) were excluded from the analysis and mitotic cells were counted as a single cell.

5.3 Results and Discussion

5.3.1 Electrical simulations

To calculate the sensitivity, the current I was first injected through the current-carrying electrodes and J_1 was extracted, then the same current was injected through the pick-up electrodes, which in turn allowed us to extract J_2 . Since the length of the electrodes is limited by the width of the channel (60 μm) and their height is determined by the fabrication process to be 120 nm, we were free to vary the width of each electrode and the distance between the electrodes. We found that the maximum sensitivity for small electrode separation distances scales with the electrode width in the power of 1.6, with the maximum sensitivity always found between the pick-up and current-carrying electrodes (Supplementary Figure B3). Since the ideal sensitivity is 1, we chose the relatively small electrode width of 30 μm . Next, we varied the separation between all four electrodes in each set, and we found that the maximum sensitivity increases linearly with the separation distance. Interestingly, large separation distances also produced a very large region of negative sensitivity where the minimum sensitivity was approximately 25% of the maximum sensitivity (Supplementary Figure B4). Lastly, we kept the separation between the two pick-up electrodes at the small distance of 10 μm and varied the separation between the pick-up electrode set and the two current-carrying electrodes. We found that the maximum sensitivity scales again linearly with the separation distances, but the slope of the sensitivity was significantly less steep (Supplementary Figure B5); therefore, we decided to use a moderate separation distance of 20 μm . The final design is shown in Supplementary Figure B6.

Using the final design now as a starting position, we simulated the sensitivity assuming a cell layer with a height of 1 μm for two different cell-layer geometries: a concave cell layer and a semi-cylindrical cell layer, while also varying the TEER of the cell layers (Supplementary Figure B7). This led to two interesting observations. First the sensitivity converges to the ideal value of 1 for higher TEER values and for larger channel heights (or smaller cell layer

thicknesses). Secondly, we observed that between adjacent electrode pairs there is an area of 200 μm where the sensitivity contribution is predominately linear and approaches 1 for the expected TEER values (reported *in vivo* TEER values are in the 1 $\text{k}\Omega\text{ cm}^2$ range ³²). We therefore used the following equation to relate the measured TEER of that region with the actual TEER of the cell layer:

$$\begin{aligned} TEER_{measured} &= (R - R_{blank})A \\ &= (\rho - \rho_{blank})l_{cell} = \left(\frac{E}{J} - \frac{E_{R \rightarrow 0}}{J_{R \rightarrow 0}}\right)l_{cell} \end{aligned} \quad (2)$$

Where R is the total measured resistance, R_{blank} is the resistance in absence of cells, A is the cell culture area, ρ is the resistivity of the cell layer, ρ_{blank} is the resistivity in absence of cells (here, equal to the resistivity of the medium), l is the length along the channel that is covered by a cell layer, E is the measured electric field, and J is the measured current density. The resistivity of the cell layer relates to the actual TEER of the cell layer as follows:

$$TEER = \rho \frac{h}{A} \quad (3)$$

Using equations 2 and 3, we can also relate the actual TEER of the cell layer with the measured resistance (Figure 3). The two quantities scale linearly, with the only difference between the concave and semi-cylindrical cell layers being a difference in the slope. To simplify the connection topology, we also explored the possibility to measure TEER by utilizing electrodes from two different pairs (Supplementary Figure B6B), this “interchanged” connection topology reduced the number of necessary connections to the impedance spectroscopy from (at least) eight to four (Supplementary Figure B2). We performed simulations to determine the sensitivity of this new system (Supplementary Figure B8). Although the existence of a large negative component is apparent between the pick-up pair and the current-carrying electrodes, the region between the two pairs exhibits a linear relationship between TEER and measured resistance and the scaling of the two quantities was very similar to that of the original topology (Figure 3). Taking into account the abovementioned characteristics, we decided that this “interchanged” connection topology is most suitable.

FIGURE 3 SIMULATION RESULTS SHOWING THE SCALING RELATIONSHIP BETWEEN TEER AND MEASURED RESISTANCE. FOR ALL REPORTED EXPERIMENTS WE HAVE USED THE “INTERCHANGED” TOPOLOGY AND ASSUMED A SEMI-CYLINDRICAL CELL-LAYER. THEREFORE, THE SCALING FACTOR (THE SLOPE OF THE PLOT) IS 10.

5.3.2 Impedance spectroscopy

Endothelial cells were seeded in the devices and cultured for up to seven days. Most of the cells spread and aligned along the long axis of the channel after one day of growth. After static incubation over five days, the resulting microvasculature closely mimicked the size and shape of a human brain microvessel (Figure 4). After examining the microchannel using phase-contrast imaging, regions where the microvessel is fully formed can be selected for assessment of the electrical characteristics of the cell layer by employing the appropriate set of electrodes. Traditionally, OOC systems that make use of electrical characterization of the cell layer do not allow for measurement area selection, resulting in possibly erroneous measurements caused by discontinuities in the cell layer ⁹. We circumvent this problem by having multiple separately addressable electrodes in each device.

A schematic overview of the measurement set-up can be found in Figure 2A. A current with a certain frequency is injected with electrodes into the semi-circular channel. Typically, the current-injection electrodes do not have a cell layer on top of them, but for the measurements this has no influence. However, the pick-up electrodes are covered by the cell layer. These electrodes measure the voltage drop and this drop can be related to the composition of the cell layer. Compared to a conventional TEER measurement, our set-up deviates since the impedance is not measured through the cell layer but in parallel to it, since the current-injection electrodes are considered to be at one side of the layer, while the pick-up electrodes are at the other side. Although this seems

counterintuitive, a statement about the cell layer can be made using this system. Crone and Olesen used a comparable set-up to measure the electrical resistance of microvessels in the frog brain, by injecting a current into a capillary and measuring the potential decay over distance and relate this to the TEER³³. Our set-up uses a similar approach, whereby a current is injected in the semi-circular channel (and thus microvessel) and the potential drop at the pick-up electrodes outside the microvessel is measured.

FIGURE 4 (A) PHASE CONTRAST IMAGE OF BRAIN ENDOTHELIAL CELLS (HCMEC/D3) DURING THE SEEDING PROCESS. (B) IMAGE OF THE SAME CELLS 24 HOURS AFTER SEEDING. (C) CONFOCAL IMAGE OF A CELL LAYER AFTER 120 HOURS OF GROWTH (RED: F-ACTIN). AT THE BACK OF THE MICROFLUIDIC CHANNEL, THE INLET IS VISIBLE.

Our set-up can be modelled with an equivalent circuit model (Figure 2B). The resistor R_{medium} accounts for the resistance of the medium, while the capacitor C_{cell} and resistor R_{cell} placed in parallel, account for the capacitive and resistive properties of the cell layer, respectively. R_{medium} is placed in parallel with the parallel combination of R_{cell} and C_{cell} to reflect the spatial arrangement of the device.

Although impedance measurements using 4 electrodes should in principle not suffer from electrode polarization impedance, electrodes with non-uniform polarization over their surface could still exhibit electrode polarization³⁴, thus making the inclusion of a CPE necessary in order to model this effect. The 'trust-region-reflective' algorithm used to fit the impedance spectrum requires a set of starting parameters to determine the values of the components (R_{medium} , R_{cell} and C_{cell}) of the equivalent circuit model. For R_{medium} we were able to approximate the value using:

$$R_{\text{medium}} = \rho \frac{l}{A} \quad (4)$$

Where l is the length of the channel, A the cross-sectional area of the channel, and ρ is the resistivity of the electrolyte, which we measured to be $0.645 \, \Omega \, \text{m}$ for both PBS and EGM at 37°C . We therefore arrived at a value of approximately $10^5 \, \Omega$ for R_{medium} . Using values for conventional TEER measurements and adapting these for our electrode design, we were able to express starting values for C_{cell} and R_{cell} of $10^{-10} \, \text{F}$ and $10^7 \, \Omega$ respectively²⁹. Additionally, the expression for the impedance of the CPE is given by:

$$Z_{\text{CPE}} = \frac{1}{Y(i2\pi f)^n} \quad (5)$$

Where Y is the capacitance of the CPE and n is an empirical fit parameter reflecting the non-linearity of the element³⁵. The values for n lie between 0 (ideal resistor) and 1 (ideal capacitor) while its typical values when used to model double-layer capacitance are 0.8 to 1. Typical values for Y are 20 to 60 μF for every $1 \, \text{cm}^2$ of electrode area. We choose not to use this parameter as starting value, but assumed that this is constant ($\text{CPE}=10^{-8} \, \text{F}$ and $n=0.8$) for our configuration. When using these values, the algorithm proved to be robust against a range of initial values for C_{cell} and R_{cell} . As a result of the algorithm, the R_{cell} , C_{cell} and R_{medium} will be given that gives the best fit on the measured impedance spectrum. Besides the model fitting, all experiments on the microfluidic BBB were independently verified using quantitative immunostaining.

Often the TEER is not determined by fitting a model to the impedance spectrum. In most studies the absolute impedances at a certain frequency or multiple frequencies are determined and these are used to perform statements

about the cell layer. However, using that approach, information is lost. For example, van der Helm et al, showed that the capacitance of the cell layer is related to the cell area ²⁹. Here we tried to perform impedance measurements in our device to make a statement about the cell layer. However, interpretation of these results seems to be too complex; it is not clear yet how changes in cell layer affect the impedance signal. Additionally, the fitting of the model was in some cases not perfect, especially not for higher frequencies ($>10^5$ Hz) partly due to the presence of parasitic capacitance which was not modelled. Therefore, we conclude that more experiments and electrode characterization need to be performed, before statements about the cell layer can be made using impedance measurements. A first step will be further characterization of the measurement set-up by measuring a chip without cells and with varying conducting liquids. Secondly, the measurements set-up needs to be tested as the used impedance analyser has a relatively low input impedance of 1 M Ω which might influence the 4-point measurements. Currently a 4-point measurement was performed, but when measuring the cell layer parallel to the medium, it might be better to perform 2-point measurements using the pick-up electrodes, since you will measure the impedance through the cell layer instead of parallel to it.

5.3.3 Varying extracellular and intracellular calcium concentration

We explored the possibility of transiently opening the tight junctions as a possible method of targeted drug delivery which is otherwise greatly hindered by the BBB; only molecules with a molecular mass below 400-500 Da and high lipid solubility can cross from the bloodstream to the brain ³⁶. Nevertheless, since all brain cells are only a few micrometers away from a capillary, once the BBB is crossed drugs can quickly diffuse to the whole brain ³⁷. A way to achieve that is by transiently modulating the tight junctions through local calcium depletion. The assembly of tight and gap junctions requires adherens junctions, and the adherens junctions between endothelial cells contain cadherins, a type of cell adhesion molecule. Extracellular calcium is used to stabilize these cadherins ³⁸; therefore, depleting calcium from the cell medium should increase the permeability of the cell layer. EGTA, a strong calcium ion chelator, has been tested as a tight junction modulator ³⁹. To verify this, we introduced 5 mM EGTA to a monolayer of hCMEC/D3 which resulted in a decrease in ZO-

1 localization. Consistent with previous reports that used the same EGTA concentration ¹⁰, microscopic observation of the cell layer revealed that EGTA did not cause any clear cell detachment, therefore we did not have to correct for changes in the cell-layer geometry. Although EGTA has high affinity for calcium ions, it also sequesters other metal ions from the cell medium, so a change in medium resistance can be expected. We observe that the decrease in calcium from the cell medium correlates with a disruption in tight junction-mediated cell-cell adhesion. We performed ZO-1 immunostaining in cell layers treated with varying concentrations of EGTA for 90 minutes and observed that most cells detached from each other and a sizeable minority of cells adopted a spherical conformation (Figure 5). For higher EGTA concentrations, the immunostaining was predominately cytoplasmic. We quantify these results in Figure 6. It is clear that the EGTA-mediated disruption is dose-dependent, and our data suggest that calcium is completely depleted at concentrations above 10 mM. We observed very few apoptotic cells after EGTA incubation, a corollary of its low cytotoxicity.

FIGURE 5 ZO-1 STAINING OF CONTROL CULTURE AND CELLS TREATED WITH 15 mM EGTA. HIGHER INTENSITY STAINING AT THE CELL CELL INTERFACE INDICATES TIGHT JUNCTIONS. IN THE CONTROL CULTURE THE TIGHT JUNCTION STAINING IS CONTINUOUS, WHILE IN THE EGTA-TREATED CULTURE ONLY A FEW TIGHT JUNCTIONS ARE VISIBLE (INDICATED BY ARROWS). THE REST OF THE CELLS IN THE CULTURE DETACHED FROM EACH OTHER AND ADOPTED A SPHERICAL SHAPE. SCALE BARS REPRESENT 25 μ M.

FIGURE 6 IMMUNOSTAINING IN A TWO-DIMENSIONAL CULTURE REVEALS THE DOSE-DEPENDENT EFFECT OF EGTA ON TIGHT JUNCTIONS. THE CLOSED CIRCLES REPRESENT THE MEAN OF THE MEASUREMENTS (N=4) AT THAT CONCENTRATION.

5.3.4 The effect of vitamin C on the endothelium

We employed our engineered BBB to elucidate the effect of ascorbic acid (vitamin C), a common antioxidant, against oxidative stress. Reactive oxygen species (ROS) that cause oxidative stress are involved in several neurological conditions. We have grown monolayers stemmed from a clonal cell culture in the presence and absence of 1 mM vitamin C and then exposed them to hydrogen peroxide (H_2O_2), a ROS that damages tissue via oxidative stress. The recorded immunostaining of tight junction protein ZO-1 on a two-dimensional cell culture led to the observation of dose-dependent oxidative stress, with higher concentrations of H_2O_2 resulting in fewer tight junctions or a punctate localization pattern, although this effect seems to reach a plateau around 50 μM (Figure 7).

FIGURE 7 IMMUNOSTAINING IN A TWO-DIMENSIONAL CULTURE REVEALS THAT HIGHER H_2O_2 CONCENTRATIONS AFFECT THE LOCALIZATION OF A LARGER NUMBER OF TIGHT JUNCTIONS. THIS EFFECT APPEARS TO REACH A PLATEAU AROUND 50 μM . CLOSED CIRCLES REPRESENT THE MEAN OF THE MEASUREMENTS ($N=2$) AT THAT CONCENTRATION.

Cells grown in the presence of vitamin C showed higher ZO-1 localization but the relative change in tight junction localization after H_2O_2 incubation was similar in both cases. This is consistent with previous reports; Lee *et al.* reported alterations in the ZO-1 localization in bovine brain microvascular endothelial cells after H_2O_2 incubation, while they did not report significant changes in ZO-1 protein expression⁴⁰. Moreover, Lin *et al.* reported that vitamin C prevents BBB disruption in rats after epidural compression of their somatosensory cortex⁴¹, we speculate that this was due to an increase in the initial barrier tightness after vitamin C treatment. Collectively, these results indicate that growth in the presence of vitamin C contributes towards a tighter endothelium and H_2O_2 treatment results in a leakier BBB. However, it is not clear from our data or previous studies whether brain endothelial cells grown in the presence of vitamin C are protected against ROS-induced oxidative stress due to the termination of oxidation reactions by vitamin C.

5.3.5 The effect of astrocyte-conditioned medium on the endothelium

Finally, we explored the effect of astrocytes on the cortical capillary. Astrocytes interact with endothelial cells by wrapping their endfeet protrusions around capillaries. They are known for enhancing tight junction formation, modulating the expression of transporters, and upregulating enzymatic expression ¹. An extracellular matrix layer termed basal lamina separates the endothelial cells and the astrocytic endfeet. Since astrocytes do not make direct contact with endothelial cells and are known to secrete a number of chemical agents, including basic fibroblast growth factor, angiopoietin-1, and glial-derived neurotrophic factor ²⁴, we hypothesized that endothelial growth medium supplemented with astrocyte-derived factors should have a similar effect as co-culturing astrocytes and endothelial cells. Therefore, we obtained ACM and supplemented it with EGM at a 1:1 volumetric ratio. We subsequently grew monolayers of endothelial cells stemmed from a clonal cell culture in the presence of EGM or ACM-supplemented EGM. The immunostaining experiments we performed (Figure 8) show a decrease in tight junction localization in endothelial cells when they are incubated in EGM mixed at a 1:1 volumetric ratio with fresh astrocyte medium (AM) compared to the cells grown in EGM only. This is in agreement with previous experiments using a similar immortalized endothelial cell line. Eigenmann *et al.* reported a decrease in TEER after incubating human brain microvascular endothelial cells (hBMEC) in direct contact and in proximity of astrocytes ⁴². Likewise, Cucullo *et al.* reported no difference in TEER values when co-culturing hCMEC/D3 cells with human astrocytes compared to hCMEC/D3 monoculture ⁴³. These results are nevertheless not in agreement with studies using different sources of endothelial cells in their BBB models: Yeon *et al.* incubated human umbilical vein endothelial cells (HUVECs) with ACM for 2 hours and observed reduced permeability to Evans Blue dye, and several FITC-dextrans (4 and 40 kDa) compared to HUVECs grown in the absence of ACM ⁴⁴. Collectively, these results suggest that the hCMEC/D3 cell line imitates the physiology of primary endothelial-astrocyte co-cultures even in the absence of astrocytes. The reduced barrier tightness when hCMEC/D3 cells are incubated in ACM/EGM mixture could be explained by the decreased concentration in growth factors and nutrients this solution has compared to undiluted EGM.

FIGURE 8 IMMUNOSTAINING IN A TWO-DIMENSIONAL CULTURE SHOWS THAT SUPPLEMENTATION OF EGM WITH ACM OR AM RESULTS IN FEWER LOCALIZED TIGHT JUNCTIONS. CLOSED CIRCLES REPRESENT THE MEAN OF THE MEASUREMENTS ($n=2$) AT THAT CONCENTRATION.

Finally, we exposed the microvessels to H_2O_2 , to test the observation that astrocyte co-culture upregulates antioxidant enzymes in endothelial cells ²⁴. The relative change in the immunostaining experiments was relatively large ($>40\%$) for all three cases and EGM-grown cells exhibited a smaller relative change (Figure 8), which suggests that no upregulation of antioxidant enzymes takes place after ACM incubation. We should note the alternative possibility that astrocytes do excrete paracrine signalling molecules or growth factors, but these molecules either decay on timescales shorter than the incubation time of endothelial cells in the ACM/EGM mixture or that the local concentration of these molecules close to astrocytes is different from the bulk concentration in the ACM/EGM mixture.

5.3.6 General considerations

All primary and control experiments of the same class were performed with cells of the same passage number to avoid variation due to phenotypic drift, de-differentiation, or senescence. However, expression of VE-cadherin and β -catenin, proteins necessary for the establishment of tight junctions, in the hCMEC/D3 cell line has been shown to remain robust over many passages ⁴⁵. Moreover, this cell line has been shown to form tight monolayers even in the

absence of glial cells, such as astrocytes ⁴⁵. We verified this observation by growing cells in the presence and absence of ACM. Although having a cell line that forms a tight endothelial monolayer without the need for a co-culture or supplementation with astrocyte-secreted factors is a useful experimental tool, it is clear that this cell line does not fully recapitulate the *in vivo* physiology. It would be interesting to pursue experiments with other cell lines such as the hBMEC cell line that has been shown to have a higher TEER compared to the hCMEC/D3 cell line but shows a decrease in TEER in the presence of astrocytes ⁴². Quantification of the barrier tightness after H₂O₂ incubation using immunofluorescence staining resulted consistently in a large change in ZO-1 quantification. Other transmembrane proteins, such as Claudins, also contribute to tight junctions. While immunostaining data only captured differences in ZO-1 localization, impedance data would also capture other potential changes in the paracellular pathway, providing a more comprehensive assessment of the physiological effect of the various ligands used in this study. Furthermore, although immunostaining is a valuable experimental tool due to its high specificity, unlike impedance sensing, it does not retain any temporal information about ligand-cell layer interactions.

5.4 Conclusion and Outlook

We have developed a microvascular microfluidic model of the human BBB. Our device has a physiologically relevant shape and size and is designed to perform impedance measurements. The resistance of a cultured cell layer can be determined by performing impedance measurements, using only 2-electrodes measuring perpendicular through the cell layer.

In combination with the hydrogel which we describe in Chapter 4, this device could potentially be used to co-culture multiple cell types without the need for a membrane. Membranes are often fabricated from non-physiological materials, introduce an additional electrical resistance to the system, and numerous particles or dyes used for permeability studies can adhere to them. Therefore, membrane-free systems recapitulate *in vivo* physiology more accurately and allow for better permeability assessment. To our knowledge, this is the first membrane-free BBB microfluidic model that incorporates electrodes for impedance or TEER measurements. We tested the effect of antioxidants and intracellular and extracellular calcium modulation on the tight junctions. Concerning the effect of antioxidants, it would be interesting to

test the effect of other vitamins, such as vitamin E, and compare it to vitamin C. Another possibility would be to test lower concentrations of vitamin C, given that the concentration used here was approximately two orders of magnitude larger than the typical content of endothelial cell growth media. Regarding the modulation of tight junctions, since this effect is reversible, it would be constructive to measure impedance over an extended period of time, until we observe recovery of tight junctions. Finally, it would be beneficial to expose the cell layer to different concentrations of EGTA and compare the relative changes in resistance. This would allow us to fully verify the results we obtained through immunostaining. Last, we could experiment with different ligands that cause a biphasic elevation of intracellular calcium. Except for ATP, compounds such as bradykinin and acetylcholine are known to have a similar effect³⁸. A limitation of the device we have developed is that it does not permit the co-culture of different cell types. A potential solution to that would be patterning channels in a biocompatible hydrogel instead of PDMS. This would allow us to culture other cell types such as astrocytes, pericytes, or neurons inside the hydrogel. We have identified a physiologically relevant hydrogel that has sufficient stiffness to support microfluidic channels, developed an ejection mould for the hydrogel, and verified that astrocytes could grow and proliferate inside this gel. We are currently actively pursuing this line of research.

5.5 References

1. A. D. Wong, M. Ye, A. F. Levy, J. D. Rothstein, D. E. Bergles and P. C. Searson, *Front Neuroeng*, 2013, **6**, 7-7.
2. B. Obermeier, R. Daneman and R. M. Ransohoff, *Nature Medicine*, 2013, **19**, 1584.
3. D. A. Nation, M. D. Sweeney, A. Montagne, A. P. Sagare, L. M. D'Orazio, M. Pachicano, F. Sepehrband, A. R. Nelson, D. P. Buennagel, M. G. Harrington, T. L. S. Benzinger, A. M. Fagan, J. M. Ringman, L. S. Schneider, J. C. Morris, H. C. Chui, M. Law, A. W. Toga and B. V. Zlokovic, *Nature Medicine*, 2019, **25**, 270-276.
4. A. Lippoldt, U. Kniesel, S. Liebner, H. Kalbacher, T. Kirsch, H. Wolburg and H. Haller, *Brain Research*, 2000, **885**, 251-261.
5. D. C. Davies, *J Anat*, 2002, **200**, 639-646.
6. A. L. Bartels, A. T. M. Willemsen, R. Kortekaas, B. M. de Jong, R. de Vries, O. de Klerk, J. C. H. van Oostrom, A. Portman and K. L. Leenders, *J Neural Transm (Vienna)*, 2008, **115**, 1001-1009.
7. Y. I. Wang, H. E. Abaci and M. L. Shuler, *Biotechnol Bioeng*, 2017, **114**, 184-194.
8. B. Srinivasan, A. R. Kolli, M. B. Esch, H. E. Abaci, M. L. Shuler and J. J. Hickman, *J Lab Autom*, 2015, **20**, 107-126.

9. M. Odijk, A. D. van der Meer, D. Levner, H. J. Kim, M. W. van der Helm, L. I. Segerink, J.-P. Frimat, G. A. Hamilton, D. E. Ingber and A. van den Berg, *Lab on a Chip*, 2015, **15**, 745-752.
10. O. Y. F. Henry, R. Villenave, M. J. Cronce, W. D. Leineweber, M. A. Benz and D. E. Ingber, *Lab on a chip*, 2017, **17**, 2264-2271.
11. J. Yeste, X. Illa, C. Gutiérrez, M. Solé, A. Guimerà and R. Villa, *Journal of Physics D: Applied Physics*, 2016, **49**, 375401.
12. R. Booth and H. Kim, *Lab on a Chip*, 2012, **12**, 1784-1792.
13. L. M. Griep, F. Wolbers, B. de Wagenaar, P. M. ter Braak, B. B. Weksler, I. A. Romero, P. O. Couraud, I. Vermes, A. D. van der Meer and A. van den Berg, *Biomedical Microdevices*, 2013, **15**, 145-150.
14. J. A. Brown, V. Pensabene, D. A. Markov, V. Allwardt, M. D. Neely, M. Shi, C. M. Britt, O. S. Hoilett, Q. Yang, B. M. Brewer, P. C. Samson, L. J. McCawley, J. M. May, D. J. Webb, D. Li, A. B. Bowman, R. S. Reiserer and J. P. Wikswo, *Biomicrofluidics*, 2015, **9**, 054124-054124.
15. S. P. Deosarkar, B. Prabhakarandian, B. Wang, J. B. Sheffield, B. Krynska and M. F. Kiani, *PLOS ONE*, 2015, **10**, e0142725.
16. F. R. Walter, S. Valkai, A. Kincses, A. Petneházi, T. Czeller, S. Veszélka, P. Ormos, M. A. Deli and A. Dér, *Sensors and Actuators B: Chemical*, 2016, **222**, 1209-1219.
17. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
18. J. A. Kim, H. N. Kim, S.-K. Im, S. Chung, J. Y. Kang and N. Choi, *Biomicrofluidics*, 2015, **9**, 024115-024115.
19. A. Herland, A. D. van der Meer, E. A. FitzGerald, T.-E. Park, J. J. F. Sleeboom and D. E. Ingber, *PLOS ONE*, 2016, **11**, e0150360.
20. N. J. Douville, Y.-C. Tung, R. Li, J. D. Wang, M. E. H. El-Sayed and S. Takayama, *Analytical Chemistry*, 2010, **82**, 2505-2511.
21. O. Tornavaca, M. Chia, N. Dufton, L. O. Almagro, D. E. Conway, A. M. Randi, M. A. Schwartz, K. Matter and M. S. Balda, *The Journal of Cell Biology*, 2015, **208**, 821.
22. S. Tria, L. H. Jimison, A. Hama, M. Bongo and R. M. Owens, *Biosensors (Basel)*, 2013, **3**, 44-57.
23. S. J. Madsen and H. Hirschberg, *J Biophotonics*, 2010, **3**, 356-367.
24. N. J. Abbott, L. Rönnbäck and E. Hansson, *Nature Reviews Neuroscience*, 2006, **7**, 41-53.
25. S. G. Canfield, M. J. Stebbins, B. S. Morales, S. W. Asai, G. D. Vatine, C. N. Svendsen, S. P. Palecek and E. V. Shusta, *Journal of neurochemistry*, 2017, **140**, 874-888.
26. L. Cucullo, P.-O. Couraud, B. Weksler, I.-A. Romero, M. Hossain, E. Rapp and D. Janigro, *Journal of Cerebral Blood Flow & Metabolism*, 2008, **28**, 312-328.
27. M. W. Brightman and T. S. Reese, *The Journal of cell biology*, 1969, **40**, 648-677.
28. M. L. Schroeter, K. Mertsch, H. Giese, S. Müller, A. Sporbert, B. Hickel and I. E. Blasig, *FEBS Letters*, 1999, **449**, 241-244.

29. M. W. van der Helm, O. Y. F. Henry, A. Bein, T. Hamkins-Indik, M. J. Crounce, W. D. Leineweber, M. Odijk, A. D. van der Meer, J. C. T. Eijkel, D. E. Ingber, A. van den Berg and L. I. Segerink, *Lab on a Chip*, 2019, **19**, 452-463.
30. S. Grimnes and Ø. G. Martinsen, *Journal of Physics D: Applied Physics*, 2006, **40**, 9-14.
31. D. B. Geselowitz, *IEEE Transactions on Biomedical Engineering*, 1971, **BME-18**, 38-41.
32. A. Reichel, D. J. Begley and N. J. Abbott, in *The Blood-Brain Barrier: Biology and Research Protocols*, ed. S. Nag, Humana Press, Totowa, NJ, 2003, pp. 307-324.
33. C. Crone and S. P. Olesen, *Brain Research*, 1982, **241**, 49-55.
34. H. P. Schwan, *Annals of the New York Academy of Sciences*, 1968, **148**, 191-209.
35. J. Wegener, S. Zink, P. Rösen and H. J. Galla, *Pflügers Archiv*, 1999, **437**, 925-934.
36. W. M. Pardridge, *NeuroRx*, 2005, **2**, 3-14.
37. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
38. N. J. Abbott, in *Introduction to the Blood-Brain Barrier: Methodology, Biology and Pathology*, ed. W. M. Pardridge, Cambridge University Press, Cambridge, 1998, pp. 345-353.
39. M. A. Deli, *Biochimica et Biophysica Acta (BBA) - Biomembranes*, 2009, **1788**, 892-910.
40. H.-S. Lee, K. Namkoong, D.-H. Kim, K.-J. Kim, Y.-H. Cheong, S.-S. Kim, W.-B. Lee and K.-Y. Kim, *Microvascular Research*, 2004, **68**, 231-238.
41. J.-L. Lin, Y.-H. Huang, Y.-C. Shen, H.-C. Huang and P.-H. Liu, *J Cereb Blood Flow Metab*, 2010, **30**, 1121-1136.
42. D. E. Eigenmann, G. Xue, K. S. Kim, A. V. Moses, M. Hamburger and M. Oufir, *Fluids Barriers CNS*, 2013, **10**, 33-33.
43. L. Cucullo, P.-O. Couraud, B. Weksler, I.-A. Romero, M. Hossain, E. Rapp and D. Janigro, *Journal of Cerebral Blood Flow & Metabolism*, 2007, **28**, 312-328.
44. J. H. Yeon, D. Na, K. Choi, S.-W. Ryu, C. Choi and J.-K. Park, *Biomedical Microdevices*, 2012, **14**, 1141-1148.
45. B. B. Weksler, E. A. Subileau, N. Perrière, P. Charneau, K. Holloway, M. Leveque, H. Tricoire-Leignel, A. Nicotra, S. Bourdoulous, P. Turowski, D. K. Male, F. Roux, J. Greenwood, I. A. Romero and P. O. Couraud, *The FASEB Journal*, 2005, **19**, 1872-1874.

6

Microfluidic gel patterning by use of a temporary membrane

Cell-gel interfaces can be used to recreate in vivo tissue barriers. To make such a barrier on chip, physical phase guides can be introduced. In this research, we developed a method to create a cell-gel interface by creating a temporary membrane on chip without the use of physical guides. This temporary membrane can be removed once a stable gel interface is formed.

This chapter is adapted from:

Microfluidic gel patterning by use of a temporary membrane for organ-on-chip applications

M. P. Tibbe, A. M. Leferink, A. v. d. Berg, J. C. T. Eijkel and L. I. Segerink

Advanced Materials Technologies, 2018, 3, 1700200

6.1 Introduction

Traditional two-dimensional (2D) and three-dimensional (3D) culture systems allow for analysis of tissue cultures comprising of one or more cell types. In 3D cell culture systems, researchers attempt to mimic the native cellular microenvironment *in vitro* by using engineered scaffolds or hydrogels allowing for the cells to experience specific physicochemical cues. Moreover, cell culture platforms can be designed inside microfluidic chips to allow for controlled fluid flow resulting in a dynamic, more physiological relevant microenvironment¹. When these microfluidic systems are used to model physiological functions of tissues and organs, they are called organs-on-chips (OOCs)^{2, 3}. The field of OOCs is rapidly emerging due to the growing interest in its potential applications. In general, OOC devices contain one or multiple cell types, and can be used for several purposes such as drug screening^{4, 5} or disease modelling^{6, 7}. Several organ functions such as the function of the lung, the gut and the blood-brain barrier (BBB) have already successfully been mimicked on-chip⁸⁻¹².

Most organs function due to the interaction between two tissue sides, the parenchymal side and the vascular endothelium side. This interface is strengthened by connective tissue that is often referred to as the basal lamina or basement membrane¹³. Recreating this native interface on-chip is challenging, mostly due to the limitations that come with microfluidic chip design. Therefore, porous membranes usually made of polycarbonate (PC)^{10, 11, 14-16}, polydimethylsiloxane (PDMS)^{8, 9, 17} or poly-ethylene terephthalate (PET)¹⁸ are used to mimic the basal lamina function acting as a mechanically stable cell substrate and separating two microchannels from each other. As cells are cultured in these channels, the porous membrane serves as a cell-support and functions as a permanent or temporary interface between parenchymal and endothelial tissues allowing them to create basal lamina like structures. Factors such as the porosity, pore size and membrane thickness determine the amount of signal transportation between cell types over the membrane. Large pores, with a pore size of approximately 5 μm and larger, allow for cells to enter the membrane and reach the other cell layer, depending on the thickness, the pore interconnectivity and pore tortuosity of the membrane. Cells penetrating the membrane will have a negative influence on transmembrane measurements, as they hinder the transport of liquid and mass through the pores. Smaller pores allow for paracrine signalling through

the membrane, but disallow direct cell-cell contact. Additionally, the commercially available polymer membranes do not resemble the physiological basement membrane stiffness and are therefore not suitable for realistic OOC applications. To obtain a more physiological relevant OOC system, the barrier between the parenchymal channel and the endothelial channel should allow for direct cell-cell contact without inducing a negative influence on membrane characterization. The use of a temporary membrane will create the opportunity to remove the membrane to establish a co-culture of multiple cell types without having an artificial/synthetic membrane on-chip. Removing the artificial membrane between two cell types is thought to result in an increase of native basal lamina production by the endothelial cells, which creates a stable interface between parenchymal and endothelial cells ¹⁹.

In the case of a BBB on-chip, the influence of the brain microenvironment on the permeability of the BBB is so far unclear. There is, however, a strong indication that an increase in endothelial tight junction complexes is induced by direct contact between brain endothelial cells and astrocytes ²⁰⁻²³. The presence of a physical membrane separating the endothelial cells from the astrocytes on a microfluidic chip is thought to have an influence on the intercellular contact of the endothelial cells. Therefore, systems in which astrocytes and endothelial cells are in direct contact with each other are preferred.

A recent study has shown that it is possible to create a membrane on-chip by having an interfacial polymerization reaction at the interface of two liquids. Zhang *et al.* presented a method to create free-standing polymer films by interfacial polymerization ²⁴. This reaction resulted in two channels, separated by a thin, nanoporous polyamine film. However, removal of this film requires a chemical reaction, unfavourable for the application in an OOC system in which cells are cultured. A reversible membrane fabrication method that will not potentially induce cytotoxicity is therefore required. Chitosan is a biodegradable biomaterial that is suited for membrane production in less harsh non-cytotoxic conditions and is therefore a promising candidate for temporary membranes in OOCs. Chitosan is a polysaccharide derived from the full or partial N-deacetylation of chitin. Chitosan can be protonated after which it becomes soluble in an acidic solution. The opposite reaction, deprotonation of chitosan with a basic buffer, is used by Luo *et al.* to create a membrane on-chip which they used for bacterial cell signalling studies ²⁵. With this

deprotonation method, free-standing, semi-permeable chitosan membranes can be created that have extracellular matrix-like properties such as comparable stiffness, high water content and good cell adhesion.

In this chapter, we propose a method to create chitosan membranes on-chips to be used as temporary barriers in OOC systems and we show that this can be applied to a BBB on-chip. We make use of the solubility of chitosan in acidic conditions to remove the membrane, after fulfilling its primary function as cell substrate, to obtain a membrane-free OOC system.

6.2 Materials and Methods

6.2.1 Device design and fabrication

SU-8 patterned, 4" silicon wafers that will serve as mould for multiple polydimethylsiloxane (PDMS) chips were made by photolithography in a cleanroom environment. PDMS base agent was mixed with PDMS curing agent in a 10:1 wt. ratio (Sylgard 184 Silicone elastomer kit, Dow Corning, MI, USA). To remove entrapped air bubbles, the PDMS was degassed prior to pouring it onto the SU-8 patterned wafer using a desiccator. After pouring the PDMS over the SU-8 patterned wafer, the PDMS was cured at 60°C for 4 hours. The cured PDMS slap was demoulded from the SU-8 patterned wafer and cut into individual chips. Fluidic inlets, with a diameter of 1 mm, were punched into the PDMS chips. Prior to bonding the PDMS chips, the chips and glass microscopy slides were exposed (bond-side up) to an oxygen plasma for 45 seconds. To ensure the bond, the chips were incubated at 60°C for at least 6 hours.

6.2.2 Chitosan preparation

A chitosan solution was prepared by adding chitosan flakes (medium molecular weight, average weight 300,000 g mol⁻¹, Sigma-Aldrich Chemie GmbH, Germany) to deionized water (DI-water). The solution was brought to a pH of 3 by adding 99% Hydrochloric acid (HCl, Sigma-Aldrich Chemie GmbH, Germany) dropwise. After stirring the solution overnight NaOH was added to increase the pH to 5. DI-water was added to bring the solution to 0.5% w/v if necessary. The final chitosan solution was filtered using a 0.2 µm syringe filter (Millex, Merck Millipore, Ireland).

An NHS-fluorescein solution was made by adding 2.5 mg NHS-fluorescein (Thermo Scientific, IL, USA) to 200 μL dimethylformamide (DMF, Sigma-Aldrich Chemie GmbH, Germany) and 800 μL 99% ethanol. To label chitosan fluorescently, 1 μL of NHS-fluorescein solution was added to 2.5 mL of chitosan 0.5% w/v.

6.2.3 Cell seeding and staining

For recreation of the parenchymal tissue in this chip, human astrocytes from the cerebral cortex (hAstro, passage 6-10, ScienCell Research Laboratories, CA, USA) were used. Astrocytes were cultured in poly-L-lysine (PLL, 2 $\mu\text{g mL}^{-1}$ in phosphate buffered saline (PBS) for 1h at 37°C)(Sigma-Aldrich Chemie GmbH, Germany) coated T75 tissue culture flasks with astrocyte medium (AM, 500 mL of basal medium, 10 mL of fetal bovine serum (FBS), 5 mL of astrocyte growth supplement (AGS, 100X) and 5 mL of penicillin/streptomycin solution (P/S, 100X) (ScienCell Research Laboratories, CA, USA)). The astrocytes were incubated at 37°C in a humidified environment with 5% CO_2 . Medium was refreshed every three days. The cell line used to create the vascular side in the described OOC system were human cerebral microvascular endothelial cells (hCMEC/D3 cell line, passage 28-34, kindly provided by Dr. P.-O. Couraud, INSERM, France). hCMEC/D3 cells were cultured in collagen coated T75 flasks (CELLCOAT, Greiner Bio One, Austria). Cells were incubated in humidified air at 37°C with 5% CO_2 . Medium was refreshed every two days.

Astrocytes were mixed at room temperature in a 1:2 ratio with Matrigel (ECM-matrix, Corning, Tewksbury, MA, USA) with an end concentration of astrocytes of 3×10^6 cells mL^{-1} in the gel. After injecting 30 μL of Matrigel solution into the chip, the chip was incubated at 37°C, humidified air with 5% CO_2 , for 24 hours to let the solution form a gel. After 24 hours, the membrane was removed by flushing an acetic acid solution (pH 5) through the opposing channel. For a membrane of 75 μm high and 1500 μm long, 75 μL acetic acid was used. After membrane removal, hCMEC/D3 cells in 30 μL EGM-2 were seeded at 3×10^6 cells mL^{-1} in the opposing channel. Hydrostatic pressure was applied to the cells by placing pipette tips with unequal medium amounts on the inlets and outlets (150 μL and 100 μL respectively).

To stain the hCMEC/D3 cells and astrocytes, detached cells were suspended at a density of 1×10^6 cells mL^{-1} in PBS. Per millilitre of cell suspension, 5 μL cell tracker (DiI or DiO, Vybrant™, Invitrogen™, Thermo Fisher Scientific, Waltham,

MA, USA) was added. The stained cells were incubated for 30 minutes at 37°C. After 30 minutes, the cell suspension was centrifuged for 5 minutes at 1500 rpm. The supernatant was removed, and cells were resuspended in warm (37°C), cell specific medium to obtain the correct concentration. The cells were washed 2 times with medium. Cells were imaged by phase contrast and fluorescently by use of an EVOS XL microscope (EVOS®, PA, USA).

Seeded cells were stained with ActinGreen™ 488 and NucBlue® (both Invitrogen Molecular Probes™, Thermo Fisher Scientific, Waltham, MA, USA) after treatment with 1% Triton-x (Sigma-Aldrich Chemie GmbH, Germany). One drop of each staining solution was added to 1 mL of cell media that was perfused through the chip.

6.3 Results and Discussion

As a starting point, the chip design described by Luo *et al.* was tested, whereby we took the design that included an extra downstream input to balance the pressure at the outlets. We observed that the downstream flow in this layout generally prevented proper membrane attachment at the distal point precluding a stable and reproducible membrane formation. To better guide the growing chitosan membrane to the distal point, we therefore designed and fabricated a new chip by adding an extra outlet (marked with number 5 in Figure 1A) that serves as a fluidic guide for the membrane compared to the designs of Luo *et al.*^{25,26} (Figure 1A and Figure 1B). As can be seen in Figure 2, the membrane starts to form 20 seconds after the chitosan arrives at the origin. After 1 minute, the membrane has reached the extra outlet. Chitosan flow is continued for 10 minutes to create a closed membrane from origin to distal point with sufficient thickness to separate the two channels.

As can be seen in Figure 1A and Figure 1C, a chitosan solution of 0.5% w/v, is focused between a neutral carbonate buffer (pH 7.0) and a basic phosphate buffer (pH 9.6). To operate the device, first a stable fluid interface between the phosphate and carbonate buffer is established. Since the viscosity of the two buffers is comparable, both fluid flows are set to 200 $\mu\text{L min}^{-1}$. As soon as a stable interface is established, the chitosan solution is introduced with a lower flow rate of 20 $\mu\text{L min}^{-1}$, to compensate for the two times higher viscosity of the solution^{27,28} (Figure 1C). After 10 minutes, a stable membrane is formed from origin to distal point and the fluid flow is turned off. To ensure no further

deprotonation, which would result in a thicker membrane, all channels are subsequently perfused with a pH-neutral buffer solution.

FIGURE 1 SCHEMATIC CHIP DESIGN. (A) A BASIC BUFFER (pH 9.6) IS INSERTED VIA INLET 1 (V1). THE CHITOSAN SOLUTION IS INSERTED VIA INLET 2 (V2). THE NEUTRAL BUFFER (pH 7.0) IS INTRODUCED VIA INLET 3 (V3). THIS BUFFER FOCUSES THE CHITOSAN TO THE CENTRE OF THE CHIP AS INDICATED WITH NUMBER 4 TOWARDS THE EXTRA OUTLET INDICATED WITH NUMBER 5. (B) IMAGE OF THE PDMS CHIP. (C) BRIGHT FIELD IMAGE OF THE CHIP AT $t=0$. THE BASIC BUFFER V1 IS STAINED RED WHEREAS THE NEUTRAL BUFFER V3 IS STAINED BLUE. CHITOSAN IS LEFT UNSTAINED. (D) BRIGHT FIELD IMAGE OF A CHITOSAN MEMBRANE AFTER 10 MINUTES OF FORMATION. (E) ENLARGEMENT OF THE CHITOSAN MEMBRANE FROM FIG 1D. THE THICKNESS OF THE MEMBRANE IS APPROXIMATELY 80 μm .

After preparation, it was observed that the membrane had a sharp delimitation at the acidic side and a diffuse border at the basic buffer side (Figure 1E). During the formation of the membrane, the growth was at the acidic side of the membrane. Since the hydroxyl ions diffuse much faster than the larger chitosan molecules, we assume that the membrane growth is due to the diffusion of hydroxyl ions through the chitosan membrane. We assessed the thickness by measuring the thickness in bright field microscopy images of the formed membrane over time (Figure 2 and Figure 3). The growth of the membrane slows down over time as was also observed by Luo *et al*²⁵. The diffusional flux of hydroxyl ions which determines the actual thickness is dependent on the pH gradient and membrane thickness. The average diffusion distance (x) of ions can be described by the following equation: $x = \sqrt{2Dt}$, with t the time and D the diffusion constant.

FIGURE 2 TIME-LAPSE COLLAGE OF THE CHITOSAN MEMBRANE FORMATION. A CHITOSAN SOLUTION (0.5 % w/v) FLOWS INTO THE CHANNEL FROM THE INLET MARKED WITH AN ASTERISK (*) WHEREAS THE BASIC BUFFER FLOWS THROUGH THE CHANNEL MARKED WITH A HASH SIGN (#). (A) AT $T=0$, BOTH FLOWS ARE TURNED ON. (B) 10 SECONDS AFTER THE CHITOSAN FLOW IS TURNED ON, A MEMBRANE STARTS TO FORM AT THE ORIGIN. (C) THE MEMBRANE GROWS IN A STRAIGHT LINE TOWARDS THE DISTAL POINT. (D) AFTER APPROXIMATELY 1 MINUTE, THE MEMBRANE REACHES THE DISTAL POINT. (E AND F) SUBSEQUENTLY, THE MEMBRANE THICKNESS INCREASES WITH TIME TOWARDS THE CHITOSAN FILLED CHANNEL.

When we fit this equation to our measurement data, we obtain a good fit ($R^2 = 0.91$) for a diffusion constant through the membrane of $17.1 \cdot 10^{-11} \text{ m}^2 \text{ s}^{-1}$, which is about 100 times lower than the diffusion constant in water²⁹. Additionally, we notice that, on average, the thickness of the membrane reaches a plateau, leading to a constant thickness of $128 \text{ } \mu\text{m}$ after 7 minutes, indicating that the hydroxyl ions do not diffuse further through the membrane (Figure 3).

It is important to note that the thickness of the membrane can vary per experiment whilst the formation is influenced by factors such as the fluid viscosities which are dependent on room temperature. Also, small impurities or obstructions in the microfluidic channels can cause the membrane to grow thicker or thinner compared to the average shown in Figure 3.

FIGURE 3 INCREASE IN CHITOSAN MEMBRANE THICKNESS OVER TIME. ASTERISKS SHOW THE ACTUAL MEASURED THICKNESS OF THE MEMBRANE AT TIME INTERVALS OF 60 SECONDS AND THE ERROR BARS INDICATE THE STANDARD DEVIATION (N=3). THE GREEN DOTTED LINE SHOWS THE FIT OF THE FORMULA $x = \sqrt{2Dt}$ WITH A DIFFUSION CONSTANT OF $17.1 \cdot 10^{-11} \text{ M}^2 \text{ S}^{-1}$.

As a result of a thicker membrane, the volume of the bottom channel that is reserved for one specific cell type will be compromised. This is an issue that may influence the read-out of co-culture experiments, since changes in the ratio of two or more cell types can affect the biological outcome due to, e.g., variance in concentration of paracrine signals, changes in nutrient availability, or alternated response on drugs.

TABLE 1 CHITOSAN WAS PREPARED IN THREE DIFFERENT CONCENTRATIONS AND 1500 μM LONG MEMBRANES (N=3) WERE PRODUCED WITH THESE SOLUTIONS. THE MEMBRANE THICKNESS OF ALL THESE MEMBRANES WAS MEASURED IN THE CENTER OF THE CHIP.

Chitosan Concentration			
	0.25% w/v	0.5% w/v	1.0% w/v
Measurement 1	129.3	139.6	94.03
Measurement 2	85.82	133.7	91.67
Measurement 3	73.94	89.91	89.90
Average Thickness (μm)	96.33	121.1	91.86

To assess the influence of the concentration of chitosan in the solution on the thickness of the membrane, two solutions with concentrations of 0.25% and 1.0% w/v were also applied to produce membranes. However, no major differences were observed in the formation and final thicknesses of these membranes (Table 1).

The membrane formation is a reversible process. A membrane-free system is created by dissolving the chitosan membrane via protonation. This is induced by flushing an acetic acid solution (pH 5.0) through one channel. With a flow speed of $75 \mu\text{L min}^{-1}$, it takes the acid 60 seconds to fully dissolve a membrane with a length of $1500 \mu\text{m}$. Consequently, $2000 \mu\text{m}$ long membranes with the same thickness will need 25% more acid and time to dissolve. To validate full membrane removal, chitosan is fluorescently labelled with NHS-fluorescein prior to membrane formation (Supplementary Figure C1). Perfusing the system longer using acetic acid would remove the chitosan membrane entirely. However, when using the appropriate amount of acetic acid such that it does not influence the Matrigel, approximately 10% of chitosan remains at the distal point (Supplementary Figure C1). For viability of the cells in the system, this will not be an issue since chitosan is known for its biocompatibility in *in vitro* systems. Yet, when a thin sheet of chitosan remains on the Matrigel, this may influence the diffusion of water-soluble components and may influence the cell adherence of endothelial cells on the Matrigel. Therefore, the complete removal of the chitosan membrane will have to be carefully assessed for every single experiment.

To explore the applicability of this removable membrane in an OOC device and more specifically in a BBB on-chip, cells are seeded and cultured into the chip. Human astrocytes (retrieved from the cerebral cortex) are chosen as the parenchymal cell type to be cultured in this BBB on-chip system. Once a stable chitosan membrane is formed in the chip, astrocytes incorporated into the natural ECM based Matrigel are seeded through inlet 2 and 3 (Figure 1A). Matrigel is a temperature responsive hydrogel that forms a solid gel after a few hours at 37°C . The chitosan membrane provides a mechanically strong barrier preventing the cell-laden Matrigel from running into the opposite channel as is shown in Figure 4A.

FIGURE 4 ASTROCYTES IN MATRIGEL ARE SEEDED FROM THE OUTLET MARKED WITH AN ASTERIX (*). ASTROCYTES ARE HOMOGENEOUSLY DISTRIBUTED THROUGH THE MATRIGEL (A, D). MORPHOLOGY AFTER MEMBRANE REMOVAL IS NOT CHANGED (B, E). HCMEC/D3 CELLS WERE STAINED GREEN WITH A DiO CELL-TRACKER (C, F). ASTROCYTES WERE STAINED RED WITH A DiI CELL-TRACKER TO ASSESS CELL DISTRIBUTION INSIDE THE CHANNEL.

The opposing channel is continuously perfused with astrocyte medium during seeding to prevent the membrane from collapsing due to pressure differences. The morphology of the astrocytes seeded in the Matrigel is similar to the morphology of the same type of astrocytes cultured in a standard tissue culture flask (Figure 5). Astrocytes are stained fluorescently with a cell tracker (Figure 4D) to see whether they would be able to pass the membrane. As can be seen from Figure 4A and Figure 4C, astrocytes are only present in the channel in which they were seeded indicating the disability of the cells to pass the chitosan membrane. After 18 hours, the astrocytes become attached to the hydrogel and start to adapt their elongated morphology (Figure 5A) which they also show in their physiological microenvironment^{30, 31}. A next step is to remove the chitosan membrane using a mild acetic solution. Due to the high collagen content in Matrigel, it will be dissolved slowly when it encounters acetic acid upon membrane removal. Therefore, in contrast to membrane-removal in the gel-free system as mentioned above, the exact amount and residence time of acetic acid required to dissolve only the chitosan and not the

Matrigel was determined from observations and found to be 75 μL and 60 seconds, respectively (Figure 4B and Figure 4E).

FIGURE 5 ASTROCYTES CULTURED IN A MATRIGEL HYDROGEL (A) SHOW THE SAME MORPHOLOGY AS ASTROCYTES CULTURED IN A NORMAL, UNCOATED TISSUE CULTURE FLASK (B).

PBS was perfused continuously through the empty channel, prior to, and after removal of the membrane with acetic acid to remove excess acid. Comparing the morphology of the astrocytes in Figure 4D and Figure 4E, it can be concluded that membrane removal does not have an influence on cell morphology in the gel. To control cell viability after membrane removal, a live/dead cell viability assay was conducted on the astrocytes at the interface (Figure 6). In Figure 6B it can be observed that the cells remained viable and kept their sprouted morphology in the Matrigel, despite the membrane removal with an acidic solution

FIGURE 6 ASTROCYTES IN MATRIGEL WERE SEEDED IN THE CHIP WHILE THE CHITOSAN MEMBRANE FUNCTIONED AS A TEMPORARY BARRIER. (A) AFTER 24 HOURS THE CELLS SHOWED THEIR SPROUTED MORPHOLOGY. FIGURE B SHOWS VIABLE ASTROCYTES IN GREEN AND DEAD CELLS IN RED. (C) SUBSEQUENTLY, THE CELLS WERE TREATED WITH TRITON-X AS A POSITIVE CONTROL FOR CELL DEATH IN THE LIVE/DEAD STAINING.

FIGURE 7 HIGH QUALITY FLUORESCENCE IMAGE OF A CO-CULTURE OF HUMAN ASTROCYTES IN THE BOTTOM CHANNEL AND hCMEC/D3 IN THE TOP CHANNEL. THE IMAGE IS OBTAINED BY STITCHING SIX SEPARATE HIGH MAGNIFICATION IMAGES. ACTIN FILAMENTS AND NUCLEI ARE STAINED WITH ACTINGREEN™ AND NUCBLUE® RESPECTIVELY. THE SCALE BAR REPRESENTS 200 μM .

After membrane removal, brain microvascular endothelial cells (BMVECs, hCMEC/D3) were seeded into the empty channel (inlet 1 in Figure 1). These endothelial cells grew on the surface of the Matrigel forming an interface with the astrocytes (Figure 4C and Figure 4F in green), without having a membrane between the cell types. To show cell-cell contact at the interface, high magnification images were taken at various focal planes, combined as a z-project image in Fiji³² and stitched in a full channel-width figure in Photoshop (Figure 7). Direct cell-cell can be observed in the centre of the image in which a large amount of overlapping cells is found.

As a proof of concept, we applied a slight adjustment in the chip design and demonstrated that two membranes can be made in a single chip creating three separated channels (Figure 8). Chitosan is introduced through a small, 100 μm wide, middle inlet where it comes in contact on two sides with the basic buffer and gets deprotonated. By increasing the flow speed of chitosan to 30 $\mu\text{l min}^{-1}$ and decreasing the flow speed of the basic buffer to 100 $\mu\text{l min}^{-1}$ an open channel in between the two membranes is formed. Increasing the basic buffer flow rate will result in merging of the membranes and thus a closed centre channel. Decreasing the basic buffer flow rate will result in a wider middle channel, up to 100 μm .

FIGURE 8 DOUBLE CHITOSAN MEMBRANE SEPARATING THREE CHANNELS FROM EACH OTHER. THE MIDDLE CHANNEL IS STILL FLUIDICALLY ACCESSIBLE AFTER MEMBRANE FORMATION WHICH IS SHOWN BY APPLYING A COLOURED FOOD DYE.

In this study, a method to obtain a mechanically stable membrane of chitosan in a microfluidic channel was presented. Although this method translates to any other cross-linkable material that can have their polymerization or gelation reaction on a liquid-liquid interface ^{24, 33}, a reversible and biocompatible reaction, such as the reaction shown in this study, can only be achieved when the membrane material is not covalently cross-linked. A candidate material for a method similar as the one presented here is the polysaccharide alginate that is ionically cross-linked by divalent cations to form a hydrogel. However, despite the biocompatibility of alginate, it lacks the ability for cells to bind to the extremely hydrophilic polymer chains. Yet, the cell binding capability of alginate can be improved by the addition of arginylglycylaspartic acid (RGD) groups ³⁴⁻³⁶.

6.4 Conclusion and Outlook

Summarizing we demonstrated successful cell-laden hydrogel patterning inside a microfluidic chip by use of a removable chitosan membrane without the need for structural additions such as columns in the channel to hold the gel in place ³⁷. The latter is the traditional approach limiting the interfacial contact area which resembles the cell-barrier. It was possible to create a co-culture of human astrocytes and brain endothelial cells inside our microfluidic system using a temporary barrier of the polysaccharide chitosan. A biocompatible, astrocyte containing, hydrogel was patterned against the chitosan “wall” after

which the chitosan can be dissolved by use of a mild acidic solution which did not influence the cell containing gel layer. Endothelial cells were subsequently seeded against the hydrogel surface to create direct contact between the endothelial cells and the astrocytes. We observed direct cell-cell contact between the two cell types over the entire length of the hydrogel surface (Figure 7). This technique offers the user a tool to temporarily create barriers on-chip to be used for hydrogel or cell patterning.

We also showed that by adding an extra inlet to the chip, it was possible to create two membranes simultaneously. The system described in Figure 8Figure can be used to co-culture more than two different cell types separately in one device without having a physical membrane for separation. Using this device, complex OOC systems can be created to simulate tissues comprised of multiple cell types.

6.5 References

1. D. Huh, G. A. Hamilton and D. E. Ingber, *Trends in Cell Biology*, 2011, **21**, 745-754.
2. S. N. Bhatia and D. E. Ingber, *Nature Biotechnology*, 2014, **32**, 760-772.
3. F. Zheng, F. Fu, Y. Cheng, C. Wang, Y. Zhao and Z. Gu, *Small*, 2016, **12**, 2253-2282.
4. S. L. Faley, M. Copland, D. Wlodkowic, W. Kolch, K. T. Seale, J. P. Wikswo and J. M. Cooper, *Lab on a Chip*, 2009, **9**, 2659-2664.
5. Z. Xu, Y. Gao, Y. Hao, E. Li, Y. Wang, J. Zhang, W. Wang, Z. Gao and Q. Wang, *Biomaterials*, 2013, **34**, 4109-4117.
6. A. Gunther, S. Yasotharan, A. Vagaon, C. Lochovsky, S. Pinto, J. Yang, C. Lau, J. Voigtlaender-Bolz and S.-S. Bolz, *Lab on a Chip*, 2010, **10**, 2341-2349.
7. E. Westein, A. D. van der Meer, M. J. E. Kuijpers, J.-P. Frimat, A. van den Berg and J. W. M. Heemskerk, *Proceedings of the National Academy of Sciences*, 2013, **110**, 1357-1362.
8. D. Huh, B. D. Matthews, A. Mammoto, M. Montoya-Zavala, H. Y. Hsin and D. E. Ingber, *Science*, 2010, **328**, 1662-1668.
9. H. J. Kim, D. Huh, G. Hamilton and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2165-2174.
10. R. Booth and H. Kim, *Lab on a Chip*, 2012, **12**, 1784-1792.
11. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
12. M. W. van der Helm, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Tissue Barriers*, 2016, **4**, e1142493.
13. K. M. Baeten and K. Akassoglou, *Developmental Neurobiology*, 2011, **71**, 1018-1039.

14. L. M. Griep, F. Wolbers, B. Wagenaar, P. M. Braak, B. B. Weksler, I. A. Romero, P. O. Couraud, I. Vermes, A. D. Meer and A. Berg, *Biomedical Microdevices*, 2012, **15**, 145-150.
15. A. K. H. Achyuta, A. J. Conway, R. B. Crouse, E. C. Bannister, R. N. Lee, C. P. Katnik, A. A. Behensky, J. Cuevas and S. S. Sundaram, *Lab on a Chip*, 2013, **13**, 542-553.
16. J. A. Brown, V. Pensabene, D. A. Markov, V. Allwardt, M. D. Neely, M. Shi, C. M. Britt, O. S. Hoilett, Q. Yang, B. M. Brewer, P. C. Samson, L. J. McCawley, J. M. May, D. J. Webb, D. Li, A. B. Bowman, R. S. Reiserer and J. P. Wikswo, *Biomicrofluidics*, 2015, **9**, 054124-054124.
17. D. Huh, Y.-s. Torisawa, G. A. Hamilton, H. J. Kim and D. E. Ingber, *Lab on a Chip*, 2012, **12**, 2156-2164.
18. F. R. Walter, S. Valkai, A. Kincses, A. Petnehazi, T. Czeller, S. Veszelka, P. Ormos, M. A. Deli and A. Der, *Sensors and Actuators B-Chemical*, 2016, **222**, 1209-1219.
19. A. Herland, A. D. van der Meer, E. A. FitzGerald, T.-E. Park, J. J. F. Sleeboom and D. E. Ingber, *PLOS ONE*, 2016, **11**, e0150360.
20. J. A. Holash, D. M. Noden and P. A. Stewart, *Developmental Dynamics*, 1993, **197**, 14-25.
21. N. J. Abbott, L. Rönnbäck and E. Hansson, *Nature Reviews Neuroscience*, 2006, **7**, 41.
22. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
23. F. L. Cardoso, D. Brites and M. A. Brito, *Brain Research Reviews*, 2010, **64**, 328-363.
24. Y. Zhang, N. E. Benes and R. G. H. Lammertink, *Lab on a Chip*, 2015, **15**, 575-580.
25. X. Luo, D. L. Berlin, J. Betz, G. F. Payne, W. E. Bentley and G. W. Rubloff, *Lab on a Chip*, 2010, **10**, 59-65.
26. X. Luo, H. C. Wu, C. Y. Tsao, Y. Cheng, J. Betz, G. F. Payne, G. W. Rubloff and W. E. Bentley, *Biomaterials*, 2012, **33**, 5136-5143.
27. W. M. Haynes, in *CRC Handbook of Chemistry and Physics*, ed. W. M. Haynes, CRC Press, 2013-2014.
28. A. Martínez, E. Chornet and D. Rodrigue, *Journal of Texture Studies*, 2004, **35**, 53-74.
29. S. H. Lee and J. C. Rasaiah, *The Journal of Chemical Physics*, 2011, **135**, 124505.
30. M. A. Olude, O. A. Mustapha, O. A. Aderounmu, J. O. Olopade and A. O. Ihunwo, *Frontiers in Neuroanatomy*, 2015, **9**, 67.
31. M. V. Sofroniew and H. V. Vinters, *Acta Neuropathologica*, 2010, **119**, 7-35.
32. J. Schindelin, I. Arganda-Carreras, E. Frise, V. Kaynig, M. Longair, T. Pietzsch, S. Preibisch, C. Rueden, S. Saalfeld, B. Schmid, J.-Y. Tinevez, D. J. White, V. Hartenstein, K. Eliceiri, P. Tomancak and A. Cardona, *Nature Methods*, 2012, **9**, 10.1038/nmeth.2019.
33. C. Hong, K. Rachel, R. Zimei, S. Andrei and V. Pankaj, *Biofabrication*, 2010, **2**, 035002.
34. K. Y. Lee and D. J. Mooney, *Chemical Reviews*, 2001, **101**, 1869-1880.

- 35. K. Y. Lee and D. J. Mooney, *Progress in Polymer Science*, 2012, **37**, 106-126.
- 36. J. M. Silva, A. R. C. Duarte, S. G. Caridade, C. Picart, R. L. Reis and J. F. Mano, *Biomacromolecules*, 2014, **15**, 3817-3826.
- 37. M. Kang, W. Park, S. Na, S.-M. Paik, H. Lee, J. W. Park, H.-Y. Kim and N. L. Jeon, *Small*, 2015, **11**, 2789-2797.

Endothelial cell-sheets as a replacement for non-physiological membranes in organs-on-chips

Most organ-on-chip systems that incorporate two compartments with a membrane in between utilize a thick, non-transparent and physiologically irrelevant membrane to separate multiple cell types from each other. As these horizontal cell culture systems need a support structure for cells to attach to, we cannot fully remove the physical interface between the two compartments. Here, we try to produce a brain endothelial cell sheet to replace the currently used membranes in a microfluidic blood-brain barrier on-chip system. This monolayer of cells should be able to remain viable after transfer to the organ-on-chip system.

7.1 Introduction

Cell sheet engineering is a method that makes use of different methods to detach a full-grown cell sheet from its growing surface, to be used for tissue engineering purposes. It is a method that has originally been developed for tissue reconstruction of organ structures, as these show a cell sheet structure *in vivo*^{1,2}. The big advantage of this technique is the fact that there is no need for proteolytic enzymes to detach the cells leaving the intercellular bonds and the connected extracellular matrix (ECM) intact. With this technique the cells are able to detach by changing the surface characteristics instead of having to break protein cell to cell bonds using for example trypsin. The most used method of cell sheet harvesting is by use of temperature responsive surfaces. These are standard cell culture surfaces with a thin (~20 nm) layer of a temperature responsive polymer grafted onto the surface. Poly(-isopropylacrylamide) (PIPAAm) is an example of such a polymer which can be grafted onto culture dish surfaces using electron beam polymerization. PIPAAm has a lower critical solution temperature (LCST) of 32°C in aqueous solution³, at which the polymer chains undergo a sharp coil-globule transition resulting in an increased hydrophilicity once the temperature drops below the LCST (Figure 1A). Below LCST, a hydration layer between the polymer chains and the cell layer arising from the hydrophilicity, causes the cells to detach. Above the LCST, the polymer chains repel water molecules which results in a hydrophobic surface, ideal for cell attachment^{1,2}. So far, multiple different cell types have been used to create cell sheets. Shimizu *et al.* used cells sheet engineering to create a viable, pulsatile layer of cardiac tissue. The cellular contact that facilitates the electrical transmission, resulting in pulsation of the tissue remains intact after transfer using a temperature responsive PIPAAm surface. On top of that, due to the mechanical stability of the cell layers, it is possible to stack them onto each other to create a three-dimensional (3D) cardiac tissue⁴. Additionally corneal epithelial cells have been successfully used in cell sheet transfer. The direct transfer of such a cell sheet onto the host stroma without having to use a transfer membrane is beneficial for further recovery⁵. So far, cell sheet engineering has only been applied for a few tissues and it has been used to create tissue surrogates *in vitro*^{6,7}.

For decades, people have been co-culturing cells in numerous different configurations. The recent development of organs-on-chip (OOC) systems creates a whole new way of co-culturing different cell types⁸. In these systems,

cells are typically cultured separately in different microfluidic channels, separated by a physical membrane. This way, the *in vivo* cellular interaction can be simulated *in vitro*, offering a new platform for disease modelling and drug studies. The porosity allows for communication between the two compartments. Most used membranes are relatively thick ($\sim 15\ \mu\text{m}$) compared to the *in vivo* structure of a basement membrane *in vivo* ($\sim 20 - 200\ \text{nm}$)^{9, 10}. Therefore, it might have an influence on the actual behaviour of the cells inside the OOC system as they do not have the direct contact they would experience *in vivo*. Thin ($\sim 500\ \text{nm}$) membranes such as the silicon nitride membrane presented by Ma *et al.* decreases the distance between cultured cells¹¹. However, these membranes have a Young's modulus in the GPa range¹² whereas tissue culture plastic has a Young's modulus of $\sim 10\ \text{MPa}$ ¹³. This increased stiffness is assumed to have an influence on the cultured cell layer as the brain tissue only has an elastic modulus of $0.5 - 1\ \text{kPa}$ ¹⁴.

The blood-brain barrier (BBB) is an endothelial cell barrier that separates the peripheral blood from the brain's interstitial fluid. The BBB is regulated by direct contact of endothelial cells with pericytes, astrocytes and other microglia¹⁵. The highly specialized endothelial cells that form the barrier are known to form a very tight barrier that does not allow for molecular diffusion into the brain tissue. The tightness of the barrier is maintained by the continuous tight junctions between the endothelial cells¹⁶. To recreate direct cell-cell contact *in vitro*, we propose to use cell sheet engineering to create an endothelial cell sheet with intact ECM to replace the currently used, $10\ \mu\text{m}$ thick, polymer membrane in a BBB on-chip system. In the past, cell sheets have successfully been fabricated using different cell types such as muscle and epithelial cells. Moran *et al.* has shown that although creating a cell sheet from endothelial is possible, transferring it intact onto another surface is extremely challenging, if not impossible¹⁷. The main problems they faced were the folding and shrinking of the sheets due to the high cytoskeletal tension caused partially by the tight intercellular junctions. To ensure cell sheets to remain flat upon release, a method using a plunger-like manipulator was developed by Haraguchi *et al.*¹⁸. By placing a thick hydrogel such as gelatin on top of the cell sheet prior to release, the sheet is stabilized and endothelial cells will be able to attach to it¹⁹. The gelatin mould is then attached to a plunger which is used to pick up the gelatin with the attached cell sheet and transfer it onto or into another device such as a cell culture surface. By increasing the temperature

again, the gelatin will dissolve resulting in full release of the transferred cell sheet. In this chapter we make use of this plunger-like manipulator to facilitate endothelial cell sheet transfer.

Here, we create cell sheets using human cerebral microvascular endothelial cells (hCMEC/D3) which have the potential to be used in our BBB on-chip system²⁰. As has been shown before, endothelial cell sheets tend to fold over itself. We hypothesize that hCMEC/D3 cells show a similar or even increased cellular tension due to the large number of tight junctions between the cells. The viability of the cell layer and the transfer ability are studied by use of a live/dead viability assay and phase contrast microscopy. Proliferation of the cells after transfer is an important feature of cell layer viability, therefore a scratch test is used. After analysing the transfer applicability of the cells onto a new cell culture surface, as a proof of concept, the transfer of a hCMEC/D3 cell sheet onto an ECM coated chip is analysed.

7.2 Materials and Methods

7.2.1 Cell sheet formation

HCMEC/D3 cells (Merck Millipore, Germany) were cultured in collagen-I pre-coated T75 flasks (Cellcoat, Greiner Bio-One) at 37 °C and 5% CO₂. Endothelial cell growth medium (ECGM, Sigma Aldrich, Germany) was replaced every 2 days until cells reached full confluency. After reaching the desired confluency levels, cells are detached using Trypsin-EDTA (0.05%, Thermo Fisher Scientific). To create a cell sheet, cells are seeded onto temperature responsive surfaces (Figure 1B), therefore, thermoresponsive PIPAAm grafted surfaces (96 and 24 wells plates and 35 mm dishes, Nunc[™] UpCell, Thermo Fisher Scientific) were used. To test whether adding ECM proteins to the culture surface prior to cell seeding improves the structure of the cell layer, different ECM protein coatings were added to the thermoresponsive surfaces. Three different coatings were tested being: collagen-I (rat-tail, 200 µg mL⁻¹, Corning, MA, USA), laminin (human fibroblasts, 10 µg mL⁻¹, Sigma Aldrich, USA) and fibronectin (human, 40 µg mL⁻¹, YoProteins, Sweden). All proteins were diluted in 1x phosphate buffered saline (PBS, Merck, Germany) and surfaces were fully covered with protein solution prior to 2 hours incubation at 37°C and 5% CO₂. After incubation, excess protein solution was removed and ECGM was placed on top of the surface until cell seeding. For each experiment, 50,000 cells cm⁻²

were seeded onto the pre-treated surface. As a control, cells were also seeded on bare PIPAAm surfaces. Cells were grown at 37°C and 5% CO₂ until they reach 95% confluency after 3-4 days (Figure 1C).

7.2.2 Cell sheet transfer

Initially two different methods were used for cell sheet transfer: gelatin coated plunger like manipulators and cell adhesive membranes. The cell adhesive membranes, that is recommended by the thermoresponsive culture surface manufacturer, turned out to be unsuitable for the cell type used in these experiments as the endothelial cells would not attach properly to the membrane. Therefore, we focus on the cell sheet transfer by use of a plunger like manipulator, henceforth plunger, with gelatin.

The plunger was designed in SolidWorks® 2018 (Dassault Systèmes, France) and 3D printed using a FormLabs Form2 SLA printer (USA) with Form4 clear resin. After printing, the devices were washed with >99.5% isopropanol (IPA) (Sigma Aldrich, USA) for 20 minutes to remove uncured material from the outside prior to exposing the devices to ultra-violet (UV)-light (wavelength: 405 nm) for 60 minutes to fully cure the material. Devices were hardened in an oven at 60°C for 2 hours to completely polymerize the surface. A mould for gelatin was made by pouring a 6 mm thick slap of polydimethylsiloxane (PDMS) (1 : 10, curing agent : base agent, Sylgard 184 Silicone elastomer kit, Dow Corning, USA) around the plungers in a culture dish. The PDMS slap containing the holes is cut into small 2 x 2 cm pieces all containing one hole, which we call “gel holder”. Gelatin did not stick properly to the 3D-printed devices, therefore, a coating of 3-aminopropyl triethoxysilane (APTES, Sigma Aldrich, USA) and glutaraldehyde (Sigma Aldrich, USA) was applied to the devices. First, the devices were immersed in APTES solution for 30 minutes (1 : 30, APTES : dH₂O). The devices were rinsed thoroughly with 99.9% ethanol (Sigma Aldrich, USA) after which they were immersed in 10% glutaraldehyde (Sigma Aldrich, USA) for 30 minutes. The devices were rinsed with dH₂O prior to drying them using N₂. The gelatin hydrogel used to attach to the coated devices was prepared by dissolving gelatin from porcine skin (13% w/v, Sigma Aldrich, USA) in PBS and heating it up to 60°C while continuously being stirred for 15 minutes. Subsequently, the solution was neutralized by adding 1 mL of 1 M NaOH. The coated plungers were placed upside down with the PDMS gel holder on top of the plunger. The liquid gelatin was filter sterilized (0.22 µm

pore size syringe filter, Millex®, Ireland) and poured into the hole of the PDMS gel holder. The devices are kept upside down and were placed at 4°C to solidify the gelatin in 15 minutes. Medium was removed from the cells and the plungers were placed, gelatin side down, onto the cell layer (Figure 1D). ECGM at room temperature (RT) was added to the wells and the cells were incubated for 15 to 30 minutes at 4°C. The plungers were lifted gently after the cell layers had detached from the thermoresponsive surface (Figure 1E). The plunger with the attached cell sheets were transferred into a new, fibronectin coated well plate and incubated for 30 minutes at 37°C to melt the gelatin (Figure 1F). Once the gelatin was melted, the plungers were removed, and the wells were washed with warm (37°C) ECGM. Cell culture was continued for at least 6 days after transfer.

A different method, also using gelatin was applied to part of the samples. This method did not use a PDMS mould to pre-form the gelatin, as the gelatin was poured directly onto the cell layer with the idea to bind the detaching cells while the gelatin cures. A warm (37 °C), gelatin solution of 13% w/v in PBS was poured onto the detaching cell layer and the plate was incubated at 4 °C for 15 minutes to allow for further detachment and fast solidification of the gelatin. The release of the cell layer onto a new surface was initiated by heating the plate to 37 °C which resulted in melting of the gelatin. A second, method for cell transfer was deployed by pouring warm (37 °C) gelatin directly onto the cell sheet, and placing the plungers on the still liquid gelatin. The gelatin was solidified by placing the well plates, including the gelatin and plungers, in the refrigerator. After 15 minutes the gelatin was hard enough to start the cell sheet transfer.

To test whether it is possible to attach an endothelial cell sheet onto a microfluidic chip, cell sheets were produced as reported before and transferred onto an ECM-coated microfluidic chip. The chip, containing a straight channel (500 µm wide, 300 µm deep), was fabricated by mixing PDMS curing agent with base agent in a 1 : 10 ratio (Sylgard 184 Silicone elastomer kit, Dow Corning, USA). After mixing, the PDMS was degassed for 30 minutes in a desiccator and poured onto a SU-8 photo-patterned mould. After curing the PDMS for 2 hours at 60 °C, the PDMS was peeled off from the mould and cut into separate chips which can be divided into top and bottom parts. Holes of 1 mm, that serve as fluidic inlets in the chip, were punched in the top part of the chips using a biopsy punch. The cell sheet was attached to the bottom side of

the chip, which must be coated with an ECM protein prior to cell sheet transfer. The chips were immersed in APTES solution for 30 minutes (1 : 30, APTES : dH₂O). The chips were rinsed thoroughly with 99.9% ethanol (Sigma Aldrich, USA) prior to immersion in 10% glutaraldehyde (Sigma Aldrich, USA) for 30 minutes. A 100 µg mL⁻¹ collagen-I coating was applied by immersing the entire chip in a collagen-I solution in PBS. After detaching the cell sheet using the gelatin cast method, the detached sheet was placed on top of the collagen-I coated chip. The whole set-up was then incubated at 37°C while being immersed in ECGM (Figure 1F). After the gelatin was dissolved, the chip with cells is washed and optically analysed. As cell sheet transfer was not always successful, closure of the chip with the top part has not yet been achieved.

7.2.3 Cell sheet analysis

The analysis of the cell sheet transfer has been divided into multiple steps. The first being the optical analysis of the cell layers prior to transfer using a phase contrast microscope (EVOS®, Thermo Fisher Scientific, USA). After transfer, the cells were again analysed by phase contrast microscopy to observe the cell morphology. The viability of the cells after transfer is a tell-tale marker of the impact the transfer has on the cell layer. Therefore, a live/dead viability assay was conducted after transfer of the cells to a new surface. The transferred and adhered cells were allowed to grow for 6 days prior to applying the live/dead viability assay (LIVE/DEAD™ Viability/Cytotoxicity Kit for mammalian cells, Thermo Fisher Scientific, USA) following the manufacturer's protocol. To test proliferation of the transferred cell layer, a scratch test was performed. As soon as the cell sheet had adhered to the new surface, approximately 24 hours after transfer, a scratch was made in the cell layer using a pipette tip. Closure of the gap was observed daily using phase contrast microscopy.

FIGURE 1 SCHEMATIC REPRESENTATION OF THE CELL SHEET FORMATION AND TRANSFER. (A) A PIPAAm COATED WELL WHICH IS HYDROPHILIC BELOW 20 °C (B) HCMEC/D3 ARE SEEDED ONTO THE HYDROPHOBIC PIPAAm SURFACE AT 37 °C TO INITIATE CELL ATTACHMENT. (C) CELLS FORM A MONOLAYER AFTER APPROXIMATELY 3 TO 4 DAYS. (D) MELTED GELATIN (37 °C), OR A PLUNGER LIKE MANIPULATOR WITH SOLID GELATIN ATTACHED TO IT IS PLACED ONTO THE MONOLAYER SO NEUTRALIZE THE FOLDING BEHAVIOUR OF THE CELLS. (E) WHEN DECREASING THE TEMPERATURE OF THE SYSTEM BELOW 20 °C, THE PIPAAm SURFACE BECOMES HYDROPHILIC RESULTING IN DETACHMENT OF THE CELL LAYER. (F) THE GELATIN WITH THE ATTACHED CELL SHEET CAN NOW BE TRANSFERRED TO A NEW, ECM COATED WELL.

7.3 Results and Discussion

Several experiments have been conducted to study the transfer ability of hCMEC/D3 cells. First, hCMEC/D3 cells were grown on PIPAAm coated tissue culture plastic (TCP) and on fibronectin coated PIPAAm to see whether these cells can form a proper monolayer on these surfaces. It can be seen in Figure 2A that after 3 to 4 days, with a starting seeding density of 50,000 cells cm^{-2} cells form a monolayer that is interrupted in the middle of the wells on the untreated culture surface. Cells cultured on fibronectin form an uninterrupted monolayer after 3 to 4 days (Figure 2C). No significant differences in cells cultured on laminin, collagen-I and fibronectin coated PIPAAm plates were observed, therefore we chose to only show fibronectin (Figure 2).

FIGURE 2 PHASE CONTRAST IMAGES OF THE SEEDED hCMEC/D3 AFTER 3 DAYS OF GROWTH. (A) AN INTERRUPTED CELL LAYER IS SEEN ON THE UN-COATED SURFACE. (B) AFTER TRANSFER USING A GELATIN COATED PLUNGER, THE UNCOATED WELL IS EMPTY. (C) A CLOSED MONOLAYER OF CELLS IS OBTAINED WHEN GROWING hCMEC/D3 FOR 3 TO 4 DAYS ON A FIBRONECTIN COATED SURFACE. (D) AFTER TRANSFER OF THE CELL SHEET THAT WAS GROWN ON A FIBRONECTIN COATED WELL, PART OF THE CELL SHEET REMAINS ATTACHED TO THE SURFACE. SCALE BARS REPRESENT 1000 μM (A, B AND D) AND 400 μM (C).

After lowering the temperature below the LCST of PIPAAm, the cells start to detach quickly. The plungers were placed onto the cells and after incubation at 4°C the detached cells were transferred to a new well. However, from Figure 2D it becomes clear the cells grown on fibronectin remain partially on the original culture surface resulting in a ruptured cell sheet whereas all the cells were removed from the untreated well (Figure 2B). We assume that the fibronectin protein structure gets entangled with the PIPAAm brushes causing a bond which prevents detachment of the cells. Similar behaviour was seen for cells sheets cultured on laminin and collagen-I coated wells (data not shown). In a second experiment, the cell layer cultured on uncoated PIPAAm did not attach to the gelatin before it detached from the surface and thus, remained in the original well. Since it detached from the surface already, it was observed that the cell sheet folds upon release as described by Moran *et al.*¹⁷. Cell sheet folding is probably caused by the high intercellular tension present in the brain endothelial cells. Attachment to a surface causes high tension inside the cytoskeleton of the cells²¹. Once they detach, the tension is released, resulting in shrinkage of the surface area, similar to the behaviour cells show when they are treated with a digestive enzyme and become spherical. Because in most experiments the cell sheets did not attach properly to the gelatin layer, the resulting detached cell layer showed different results such as folded sheets, disintegrated sheets and shrivelled cells (Figure 3).

FIGURE 3 PHASE CONTRAST IMAGES OF THREE DIFFERENT, NEGATIVE OUTCOMES OF hCMEC/D3 SHEET TRANSFER. (A) CELL SHEETS THAT ARE NOT PROPERLY RE-ATTACHED AFTER TRANSFER FOLD INTO CELL CLUMPS. (B) CELLS DETACH FROM EACH OTHER DUE TO DISTURBANCES IN THE CYTOSKELETON LEADING TO A DISINTEGRATION OF THE CELL SHEET. (C) CELLS THAT ARE NOT ABLE TO RE-ATTACH TO THE NEW SURFACE BECOME SHRIVELLED. SCALEBARS REPRESENT 750 μM .

Abovementioned results show that picking up cell sheets using plunger-like manipulators is possible but far from consistent. Therefore, a new method was developed that makes use of liquid gelatin. With this so-called gel casting

method, a layer of liquid gelatin is casted onto the detaching cell sheet after which the cells are captured inside the gel as the gelatin solidifies. To test this method, cells were seeded on a PIPAAm coated well plate containing no additional ECM coating. Once a monolayer of cells had formed, gelatin was poured on top of the layer. The solid gelatin with the incorporated cell layer was transferred onto a new cell culture surface. The original cell culture surface did not contain any cells after the casted gelatin was removed. Therefore, we expect a full cell sheet to be transferred to the new culture surface. However, it turned out that one hour after transfer approximately 10% of the culture surface is confluent with newly attached cells. This indicates no successful re-attachment of a full cell sheet. It is possible that cells that were not able to attach after transfer were washed away during the washing steps that are necessary to remove excess gelatin from the well. Despite the low number of transferred cells, we looked at the cell viability (Figure 4) and proliferation (Figure 5).

FIGURE 4 LIVE/DEAD VIABILITY ASSAY. (A) MERGED FLUORESCENCE IMAGE OF A TRANSFERRED CELL SHEET, LIVING CELLS ARE STAINED GREEN USING CALCEIN-AM AND DEAD CELLS ARE STAINED RED USING ETHIDIUM HOMODIMER. SEPARATE GREEN (B) AND RED (C) CHANNELS ARE SHOWN IN GRAYSCALE. (D) A MAGNIFICATION OF (A) WHERE CLUSTERS OF DEAD CELLS CAN BE OBSERVED. SEPARATE GREEN (E) AND RED (F) CHANNELS ARE SHOWN IN GRAYSCALE. SCALEBARS REPRESENT 800 μM (A – C) AND 250 μM (D – F).

Results from the live/dead viability assay show that there is a high amount of dead cells and a low amount of live cells indicating that parts of the transferred sheet are still viable whilst other parts did not survive the transfer (Figure 4).

The dead cells are more clustered which suggests that the cell sheet is folded at these spots making it unable to attach to the new, fibronectin coated surface, resulting in apoptotic or necrotic cell clusters. After five days of re-attachment, the cells have formed a proper monolayer again which indicates good proliferation. To validate this proliferation, a scratch test, where a wound area is created by making a scratch in the cell layer (Figure 5A), is conducted. In the middle of the cell monolayer, a gap is created by scratching away part of the cell layer. After 1 day, the cells start to proliferate and migrate towards the centre of the opened area (Figure 5B). After five days of culture, the entire wound area is closed again as can be seen in Figure 5C.

FIGURE 5 PHASE CONTRAST IMAGES OF THE SCRATCH TEST PERFORMED ON A CELL LAYER WHICH ORIGINATED FROM RE-ATTACHED hCMEC/D3. (A) A SCRATCH IS MADE IN THE CELL LAYER AT $T=0$. (B) AFTER 24 HOURS, THE CELLS START TO MIGRATE TOWARDS THE CENTRE OF THE WOUND AREA. (C) AFTER 5 DAYS, THE WOUND AREA IS FULLY CLOSED BY A MONOLAYER OF CELLS. SCALEBARS REPRESENT $750\ \mu\text{m}$.

Together with the live/dead viability assay, we can conclude that the cells that are able to attach after transfer stay viable and proliferative. A combined method, which makes use of both a plunger and gelatin casting was tested as well. Once the liquid gelatin was poured onto the cells, a plunger with additional pillars for stability (Supplementary Figure D1), was placed on top of the gelatin. Once the gelatin solidifies, the gel was cut loose from the well plate and the plunger facilitated transfer of the gel to a new well.

To be able to use the technique of cell sheet engineering in an OOC system, the attachment of a transferred cell sheet onto a PDMS microfluidic chip must be tested. We chose to use collagen-I to coat the PDMS chips as it has proven to have a good affinity with PDMS²² and in our experiments the cells behave similar on collagen as on fibronectin. Cells were cultured into a monolayer and after picking them up with the gel cast method, they were placed on top of the coated and uncoated PDMS surface. The chips show good homogeneous

coverage of the cell layer as can be seen in Figure 6A, whereas the cell sheet appears to break above the channels (Figure 6B). The cells that are covering the chip show an unhealthy morphology, as they appear to have shrivelled (Figure 6). These preliminary results show that transfer of a cell sheet onto a coated microfluidic chip is possible. However, the channels used in these experiments are relatively large (500 μm wide) which makes the cell sheet above the channel prone to collapsing. As this is an open cell culture system, the culture is very prone to infections. Therefore, closure of the chip system with an additional PDMS layer directly after cell attachment is preferable. This will possibly result in necrosis of the cells that are in between the two layers. The negative influence of the cell necrosis on the healthy cells in the open cross-sectional area of the chip has to be considered ^{23,24}.

FIGURE 6 PHASE CONTRAST IMAGE OF A CELL SHEET TRANSFERRED TO A CHIP CONTAINING A 500 μm WIDE, STRAIGHT CHANNEL. (A) AN INTACT CELL SHEET IS TRANSFERRED TO THE CHIP, HOWEVER; CELLS ON THE SURFACE OF THE CHIP SHOW A SLIGHTLY SHRIVELLED MORPHOLOGY. (B) CELLS ON TOP OF THE CHANNEL HAVE COLLAPSED INTO THE CHANNEL AS CAN BE SEEN BY THE DIFFERENCE IN FOCUS PLANE. SCALEBARS REPRESENT 800 μm .

7.4 Conclusion and Outlook

We show the formation and transfer of cell sheets from the brain endothelial cell line hCMEC/D3. Transfer of these cell sheets depends on multiple factors. The first one being the original surface on which they are grown. Cell sheets grown on an additional layer of fibronectin form a monolayer faster compared to cells grown on a PIPAAm surface. However, adding a layer of fibronectin onto the PIPAAm coated surface prior to cell seeding results in unequal detachment of the cell layer. The first transfer method that was tested made use of a pre-formed gelatin plug attached to a plunger. This solid gelatin plug

is placed onto the cell layer after which the layer can be detached. After transfer with this method, parts of the cell layer remain on the original surface, possibly due to the inhomogeneity of the gelatin surface that is in contact with the cells. Parts of the cell sheet that were successfully transferred to a new surface show clear signs of cellular instability. Cell sheets that are unable to re-attach tend to fold or disintegrate whereas individual cells shrivel.

To be able to transfer a more consistent cell layer, a new method was tested where the solid gelatin is replaced by liquid gelatin that was poured directly onto the detaching cell layer. Using this way, the full layer is covered with gelatin resulting in entrapment of the complete cell sheet inside the gel. During the solidification of the gelatin, a plunger was placed on top of the gelatin to facilitate the gel transfer. After transferring the cell sheet to a new surface, only partial re-attachment was observed in all occasions. The attached cells were viable and proliferative, as shown by the scratch test. As a proof of concept, we showed the transfer of a hCMEC/D3 cell sheet onto a collagen coated PDMS microfluidic chip. The used chips have a rather large channel width which the cell sheet cannot bridge, resulting in a collapsed cell layer above the channel. In future experiments, the dimensions of the chip must be optimized so that the channel is small enough for the cell sheet to not break. When a cell sheet has been successfully attached to a PDMS chip, the chip has to be closed onto a glass slide or onto a second PDMS layer. As has been shown in the past, cell sheet engineering allows for the formation of large cell sheets. Once the endothelial cell sheet formation has been optimized, it is possible to create a large monolayer of cells which can be divided into multiple smaller samples to be transferred onto individual devices. To create a more realistic BBB on-chip system, a combination of brain endothelial cells and pericytes is preferred. Haraguchi *et al.* have shown that stacking multiple cell types to create a tissue structure *in vitro* is possible¹⁸. In future experiments a cell sheet of pericytes can be incorporated with endothelial cells and astrocytes to create a mechanically strong cell sheet construct to be used as an *in vivo* BBB model.

7.5 References

1. M. Yamato and T. Okano, *Materials Today*, 2004, **7**, 42-47.
2. J. Yang, M. Yamato, C. Kohno, A. Nishimoto, H. Sekine, F. Fukai and T. Okano, *Biomaterials*, 2005, **26**, 6415-6422.

3. L. M. Geever, D. M. Devine, M. J. D. Nugent, J. E. Kennedy, J. G. Lyons, A. Hanley and C. L. Higginbotham, *European Polymer Journal*, 2006, **42**, 2540-2548.
4. T. Shimizu, M. Yamato, Y. Isoi, T. Akutsu, T. Setomaru, K. Abe, A. Kikuchi, M. Umezu and T. Okano, *Circulation Research*, 2002, **90**, e40-e48.
5. K. Nishida, M. Yamato, Y. Hayashida, K. Watanabe, K. Yamamoto, E. Adachi, S. Nagai, A. Kikuchi, N. Maeda, H. Watanabe, T. Okano and Y. Tano, *New England Journal of Medicine*, 2004, **351**, 1187-1196.
6. K. Sakaguchi, T. Shimizu, S. Horaguchi, H. Sekine, M. Yamato, M. Umezu and T. Okano, *Scientific Reports*, 2013, **3**, 1316.
7. T. Sasagawa, T. Shimizu, S. Sekiya, Y. Haraguchi, M. Yamato, Y. Sawa and T. Okano, *Biomaterials*, 2010, **31**, 1646-1654.
8. S. N. Bhatia and D. E. Ingber, *Nature Biotechnology*, 2014, **32**, 760-772.
9. R. Jayadev and D. R. Sherwood, *Current Biology*, 2017, **27**, R207-R211.
10. M. S. Thomsen, L. J. Routhe and T. Moos, *J Cereb Blood Flow Metab*, 2017, **37**, 3300-3317.
11. S. H. Ma, L. A. Lepak, R. J. Hussain, W. Shain and M. L. Shuler, *Lab on a Chip*, 2005, **5**, 74-85.
12. Z. Gan, C. Wang and Z. Chen, *Surfaces*, 2018, **1**, 59-72.
13. D. E. Discher, P. Janmey and Y.-l. Wang, *Science*, 2005, **310**, 1139-1143.
14. M. Akhmanova, E. Osidak, S. Domogatsky, S. Rodin and A. Domogatskaya, *Stem Cells Int*, 2015, **2015**, 167025-167025.
15. M.-A. Lécuyer, H. Kebir and A. Prat, *Biochimica et Biophysica Acta (BBA) - Molecular Basis of Disease*, 2016, **1862**, 472-482.
16. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
17. M. T. Moran, W. M. Carroll, A. Gorelov and Y. Rochev, *J R Soc Interface*, 2007, **4**, 1151-1157.
18. Y. Haraguchi, T. Shimizu, T. Sasagawa, H. Sekine, K. Sakaguchi, T. Kikuchi, W. Sekine, S. Sekiya, M. Yamato, M. Umezu and T. Okano, *Nature Protocols*, 2012, **7**, 850.
19. T. S. Panetti, D. F. Hannah, C. Avraamides, J. P. Gaughan, C. Marcinkiewicz, A. Huttenlocher and D. F. Mosher, *Journal of Thrombosis and Haemostasis*, 2004, **2**, 1645-1656.
20. D. E. Eigenmann, G. Xue, K. S. Kim, A. V. Moses, M. Hamburger and M. Oufir, *Fluids and Barriers of the CNS*, 2013, **10**, 33.
21. B. D. Matthews, D. R. Overby, R. Mannix and D. E. Ingber, *Journal of Cell Science*, 2006, **119**, 508.
22. Z. Qian, D. Ross, W. Jia, Q. Xing and F. Zhao, *Bioactive Materials*, 2018, **3**, 167-173.
23. A. Pérez-Garijo and H. Steller, *Development (Cambridge, England)*, 2015, **142**, 3253-3262.
24. Y. Yang, L. Hou, Y. Li, J. Ni and L. Liu, *Cell Death Dis*, 2013, **4**, e723-e723.

Summary and outlook

This chapter summarizes all the results and conclusions that are reported in this thesis. In the final outlook, suggestions for further research as well as the answer to the question “what is the best membrane for my chip” is being discussed.

8.1 Summary

Organs-on-chips are devices that are used to engineer an organ-specific microenvironment into a microfluidic chip. These realistic systems serve as models for disease modelling and drug research. The ease of fabrication, small scale and low amount of used volumes make the systems very cost effective for *in vitro* studies. Several factors such as material choice, device design and cell choice contribute to a controlled cell culture environment. Although these systems have shown promising results so far, there are still hurdles to be taken before these systems can replace the current gold standard which is still the use of animal models. Organ-on-chip systems often contain two microfluidic compartments or channels in which cells are cultured. These compartments are separated by a porous, polymer membrane which allows for diffusion of molecules from one channel to the other, while it offers a cell culture surface for the cells to attach to. In this thesis, the role and necessity of the membrane inside organ-on-chip systems and specifically inside a blood-brain barrier (BBB) on-chip, is being studied.

Traditionally, the membrane used is a relatively thick (tens of μm), porous polymer membrane which introduces a large distance between the cell culture compartments. As this cell separation distance is a lot smaller in the physiological situation (few nm), we chose to look at the ability to either fully remove or replace the currently used membranes in organs-on-chips. In **Chapter 2** the most used organ-on-chip systems and the membranes they include are being described. When a membrane is used, its biocompatibility can be increased by changing the morphology and topology of the membrane. In **Chapter 3** the use of thin, polydimethylsiloxane (PDMS) membranes as an alternative for the currently used thick polycarbonate membranes in a Transwell set-up was discussed, whereas **Chapter 4-7** focused on the fabrication of membrane-free systems. In **Chapter 4** the development of a hydrogel chip with a physiologically relevant size and structure was shown. The development of a standardized trans epithelial electrical resistance (TEER) measurement set-up inside a semi-circular organ-on-chip system was described in **Chapter 5**. Another method to create a membrane-free system is the use of a temporary barrier inside a microfluidic chip as was described in **Chapter 6**. Finally, in **Chapter 7** a tissue engineering technique, namely cell sheet engineering was proposed to be used with brain endothelial cells.

As the membrane in an organ-on-chip system replaces the *in vivo* basement membrane, it should resemble its thickness and mechanical properties. In **Chapter 3** the thickness of the membrane used was addressed by comparing cell cultures on an often used, 10 μm thick polycarbonate membrane which has a random pore distribution, with a 5-fold thinner PDMS membrane with a controllable pore layout. Our PDMS membranes are optically transparent which is caused by the small thickness in combination with the orientation of the pores on the surface which is due to the fabrication process fully perpendicular to the surface. A co-culture of human brain endothelial cells and human astrocytes was initiated onto the PDMS membranes as well as on the PC membranes to compare the cell culture behaviour in a Transwell cell culture set-up. Visualization of the tight junction protein ZO-1 showed no relevant differences between the cells cultured on both membranes. Using scanning electron microscopy, it was shown that the PDMS membranes with a pore size of 5 μm allow for cell migration towards the other side of the membrane. A permeability study was performed to observe the transport of 4 kDa FITC-Dextran through the cell layer that was cultured onto the membranes. It revealed that cell layers cultured on polycarbonate membranes are 6x more permeable compared to PDMS membranes with the same pore size. Although the porosity of the polycarbonate is 4x higher compared to that of the PDMS membrane, it also indicates that the endothelial cell barrier on a polycarbonate membrane is less tight. The optical clarity together with the decreased permeability of the cell layer on PDMS membranes are two improvements of this newly developed membrane making it a good alternative for the traditionally used polycarbonate membrane.

The development of a membrane free system was studied in **Chapter 4** by the development of a hydrogel-based chip system. To increase the physiological relevance of an organ-on-chip system, the environment in which the cells are cultured should resemble the *in vivo* situation in the best possible way. We used soft lithography to create a semi-circular channel structure inside a hyaluronic acid based hydrogel. A gel holder and a gel injection set-up were developed to ensure good reproducibility of each fabricated chip. To close the channel, the gel was placed onto a glass slide. By flushing a solution containing microbeads through the channel, leakages were detected. Attempts were made to improve sealing of the gel to the glass slide by adding a chemically reactive group to the surface to which the hydrogel could bind. However, to allow for

good transfer of the channel structure into the gel, it has to be fully cured leaving no functional groups available to bind to the modified glass surface. This system provides the physiologically relevant shape, size and structural environment of a brain microvessel.

Chapter 5 describes an impedance measurement method that can be applied to the system developed in **Chapter 4**. The hydrogel was replaced by PDMS to allow for quick and cheap reproduction of the chip. To assess the quality of a cell layer cultured in the device, an impedance measurement set-up consisting of 44 electrodes in each microchannel, was included into the bottom glass slide. To assess the electrodes, the gel holder developed in **Chapter 4** was adjusted to fit spring pins that connect to the electrodes on the glass slide. The array of electrodes on which the brain endothelial cells are grown allows for direct impedance measurements of the cell layer, which is a direct measure for cell layer integrity. A problem that many organ-on-chip systems face when using TEER or impedance for cell layer assessment is the cell layer integrity. Which, if not intact, has a big influence on the measured impedance. This system allows for site specific impedance measurements after optical analyses of the cell layer. To analyse the measurement method, brain endothelial cells that were cultured in the device were exposed to a chelating agent that depletes the external calcium leading to breakdown of the tight junctions. Results from the impedance measurements were not sufficient to draw conclusions from. This decrease in tight junctions was observed as a decrease in ZO-1 localization in the endothelial cell layer. Furthermore, we applied oxidative stress to the endothelial cells after we treated them with astrocyte conditioned media to study the influence of astrocyte secreted factors on endothelial cells that experience oxidative stress. The influence of the astrocyte secreted medium did not contribute significantly to the amount of tight junctions and thus the tightness of the layer, which suggests that the used brain endothelial cells form a proper tight cell layer in the absence of astrocytes.

A totally different approach to create a cell-gel interface on chip was shown in **Chapter 6**. Chitosan is a polysaccharide that can form a gel-like solid upon contact with a basic buffer. In **Chapter 6** we designed a microfluidic device in which we were able to form a chitosan membrane in the middle of the channel by bringing a laminar flow of chitosan in contact with a laminar flow of basic buffer. Once the membrane had formed a physical barrier inside the chip, a cell-laden hydrogel was seeded on one side of the chitosan membrane. After the gel

had become solid, the chitosan membrane could easily be removed again by flushing a mild acidic solution along the surface. The acidity of this solution did not have a negative effect on the astrocytes that were present inside the hydrogel. Following the membrane removal, a layer of brain endothelial cells was seeded along the length of the gel. Direct cell-cell contact between astrocytes and endothelial cells was observed along the length of the hydrogel.

Finally, in **Chapter 7** we tried to transfer a brain endothelial cell layer from one surface to another to assess the potential use of cell sheet engineering for organ-on-chip purposes. First, a monolayer of brain endothelial cells was grown onto a temperature responsive cell culture surface after which the temperature was reduced to detach the cell layer. To allow transfer of the layer, a gelatin coated plunger was placed on top of the endothelial cells prior to detachment. The gelatin layer was supposed to prevent the cell layer from shrinking due to the high intracellular tension. Cell detachment occurred faster than re-attachment to the gelatin layer, causing the cell layer to rupture. To overcome this problem, warm gelatin was poured onto the cell layer prior to cell detachment. Solidification of the gelatin at 4 °C led to cell entrapment in the gel. Once the gel was transferred the cells were not able to re-attach fast enough to the new surface, resulting again in rupture and folding of the cell layer. These results indicated that this technique is not suitable for the cell type that is needed inside a BBB on chip.

8.2 Outlook

8.2.1 Material choice

The BBB is a complex organ of which the function and drug response is being studied thoroughly *in vitro*. The development of organ-on-chip systems led to the development of the BBB on-chip ¹⁻⁵. The majority of BBB on-chip systems is made from PDMS because of its good material properties such as the gas permeability, transparency, biocompatibility and flexibility. A big disadvantage of PDMS is its ability to absorb small molecules such as drugs and tracers ⁶. P-glycoprotein is an important transporter protein which acts as a drug transporter mechanism in brain endothelial cells. It can be assessed by the lipophilic, positron emission tomography (PET), tracer molecule (R)-[¹¹C]verapamil ⁷. However, verapamil is known to absorb to untreated PDMS ⁶, like also other molecules of interest for BBB research. Therefore, developing a

proper coating or creating a PDMS free organ-on-chip system is preferable to allow the use of PDMS in drug permeability studies. Van Meer *et al.* tested the use of a lipid-based cell binding coating and showed that less molecules were absorbed by the PDMS surface while still allowing for good cell adhesion⁸. The PDMS membrane developed in **Chapter 3** is not suitable for certain drug permeability studies. Therefore it should also be treated with a coating which should not influence the permeability of the membrane. A lipid bilayer coating as proposed by van Weerd *et al.* would be suitable⁸.

In **Chapter 4** a chip solely consisting of a hyaluronic acid-based hydrogel was developed. The extracellular matrix inside an *in vivo* neurovascular unit consists mainly of laminin and hyaluronic acid⁹. Although the used gel resembled the hyaluronic acid component inside the neurovascular unit, the elastic modulus was much higher¹⁰ compared to the elastic modulus of brain tissue¹¹. Therefore, endothelial cells grown on these hydrogels might behave unnaturally as it is known that the cell culture surface stiffness influences cell behaviour¹². However, it was not possible to replicate a channel structure inside a gel with a lower elastic modulus. The *in vivo* extracellular matrix is a mixture of multiple proteins and cells which all contribute to the structural integrity. It is expected that introducing other proteins and cells inside the hydrogel structure leads to an improved cell culture environment for brain endothelial cells. Such a complete, but complex hydrogel might also be used in the system described in **Chapter 6**.

8.2.2 Readout methods

In organ-on-chip systems, the integrity of the cultured endothelial cell layer can be assessed in multiple ways. In 2D systems such as Transwell cell cultures, the permeability can be studied by looking at the diffusion of small molecules through a cell layer. This method is also applicable in organ-on-chip systems where it is more prone to erroneous measurement outcomes. Sampling the effluents from the outlet is a difficult process that is susceptible to measurements variability. A more consistent measurement method is by measuring the TEER or impedance of a cell layer. This method can be applied in 2D as well as in 3D systems. Van der Helm *et al.* showed the possibility of measuring TEER inside a BBB on-chip with integrated electrodes¹³. Although this method has proven its functionality, the manual electrode placement can cause measurement variations. The impedance measurement that was

described in **Chapter 5** allows for reproducible impedance measurements of cell layers inside a semi-circular microfluidic device. Here, we cultured endothelial cells inside a PDMS channel. To improve the physiological relevance of the system, the PDMS should be replaced with a cell-laden hydrogel. However, including an extra conducting volume would also contribute to the impedance measurement. In that case, the model we propose here should be adapted to the new situation. The simplicity of the measurement design makes it applicable in multiple cell culture devices that have a direct connection of the cell culture chamber with a glass slide. However, the measurement set-up has to be reconsidered each time to obtain the most complete and reliable results for each measurement.

8.2.3 Membrane: yes or no?

During this thesis, the question whether a membrane in an organ-on-chip system is necessary or not was addressed. There is no short and simple answer to this question. We found that choosing a membrane or choosing a membrane-free system all depends on the final application and design of the system. Some systems simply do not allow for the removal of the membrane as the cells use it as a cell culture surface. In these systems, the currently used, thick membranes can potentially be replaced by the thin PDMS membrane we developed and which we describe in **Chapter 2**. Multiple studies have shown that it is possible to integrate a PDMS membrane in a microfluidic system. Cell culture on these membranes inside a microfluidic chip was so far not successful. Incorporating this thin membrane inside a microfluidic chip would allow for direct cell-cell contact whilst the cells are experiencing physiologically relevant culture conditions with fluid flow that induces shear stress.

In **Chapter 6** we showed that there is an opportunity to create a membrane-free chip system in which a co-culture of brain endothelial cells and astrocytes was established. Getting this system to work in a reproducible way turned out to be a challenge due to external variations such as temperature, chip cleanliness and fluid flow variations. The created polysaccharide membranes show variations in thickness and placement. Physical phase guides would solve this problem ¹⁴. However, these guides introduce an extra surface area where there cannot be any cell-gel contact. In large systems such as the OrganoPlate® of Mimetas, this surface area can be neglected. When designing smaller

channels, the cell-gel area should be as large as possible to create the most cell-cell contact. Another approach which can be applied to create micrometer sized membrane-free BBB on-chip systems is a technique shown by Loessberg-Zahl *et al.* who make use of laminar flow patterning of hydrogels inside a microfluidic system¹⁵. One problem with these flow patterning devices is the vertical structure of the cell-gel interface, which makes observation and characterization of the cell layer challenging.

In **Chapter 7** we studied the possibility of obtaining a free-standing endothelial cell sheet using hCMEC/D3 cells. However, due to the high inter- and intracellular tension of the cells, it was not possible to transfer an intact cell sheet from one substrate to another. By including multiple cell types in a single cell sheet, it might be possible to increase its rigidity which would prevent folding and disintegration. This way, a complex tissue structure can be created and transferred to, for example, a microfluidic chip as a replacement of the currently used polymer membranes.

It can be concluded that there is an ideal solution for each application which depends on the goal of the application, the used cells, the chip design and the readout method. Each of these individual components contribute to the choice whether to use or not to use a membrane in an organ-on-chip system.

8.3 References

1. R. Booth and H. Kim, *Annals of Biomedical Engineering*, 2014, **42**, 2379-2391.
2. M. Campisi, Y. Shin, T. Osaki, C. Hajal, V. Chiono and R. D. Kamm, *Biomaterials*, 2018, **180**, 117-129.
3. H. Cho, J. H. Seo, K. H. K. Wong, Y. Terasaki, J. Park, K. Bong, K. Arai, E. H. Lo and D. Irimia, *Scientific Reports*, 2015, **5**, 15222.
4. L. M. Griep, F. Wolbers, B. Wagenaar, P. M. Braak, B. B. Weksler, I. A. Romero, P. O. Couraud, I. Vermes, A. D. Meer and A. Berg, *Biomedical Microdevices*, 2012, **15**, 145-150.
5. M. W. van der Helm, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Tissue Barriers*, 2016, **4**, e1142493.
6. B. J. van Meer, H. de Vries, K. S. A. Firth, J. van Weerd, L. G. J. Tertoolen, H. B. J. Karperien, P. Jonkheijm, C. Denning, A. P. Ijzerman and C. L. Mummery, *Biochemical and Biophysical Research Communications*, 2017, **482**, 323-328.
7. G. Luurtsema, P. Elsinga, R. Dierckx, R. Boellaard and A. van Waarde, *Current Pharmaceutical Design*, 2016, **22**, 5779-5785.

8. J. van Weerd, M. Karperien and P. Jonkheijm, *Advanced Healthcare Materials*, 2015, **4**, 2743-2779.
9. N. J. Abbott, A. A. K. Patabendige, D. E. M. Dolman, S. R. Yusof and D. J. Begley, *Neurobiology of Disease*, 2010, **37**, 13-25.
10. J. W. H. Wennink, K. Niederer, A. I. Bochyńska, L. S. Moreira Teixeira, M. Karperien, J. Feijen and P. J. Dijkstra, *Macromolecular Symposia*, 2011, **309-310**, 213-221.
11. S. Budday, R. Nay, R. de Rooij, P. Steinmann, T. Wyrobek, T. C. Ovaert and E. Kuhl, *Journal of the mechanical behavior of biomedical materials*, 2015, **46**, 318-330.
12. R. G. Wells, *Hepatology*, 2008, **47**, 1394-1400.
13. M. W. van der Helm, M. Odijk, J.-P. Frimat, A. D. van der Meer, J. C. T. Eijkel, A. van den Berg and L. I. Segerink, *Biosensors and Bioelectronics*, 2016, **85**, 924-929.
14. M. Jang, P. Neuzil, T. Volk, A. Manz and A. Kleber, *Biomicrofluidics*, 2015, **9**, 034113-034113.
15. J. Loessberg-Zahl, A. D. van der Meer, A. van den Berg and J. C. T. Eijkel, *Lab on a Chip*, 2019, **19**, 206-213.

Appendix

Supplementary information and figures

A. Supplementary information Chapter 3

SUPPLEMENTARY FIGURE A1 LIVE/DEAD VIABILITY ASSAY ANALYSIS USING IMAGEJ FUNCTION “FIND MAXIMA” WHICH HIGHLIGHTS AND COUNTS PIXELS ABOVE A CERTAIN INTENSITY THRESHOLD. THE AMOUNT OF LIVING CELLS (A) IS APPROXIMATELY 80% WHEREAS THE AMOUNT OF DEAD CELLS (B) IS APPROXIMATELY 20%. SCALEBARS REPRESENT 250 μm .

SUPPLEMENTARY FIGURE A2 SEM IMAGE OF hCMEC/D3 CELLS CULTURED FOR 4 DAYS ON A PDMS MEMBRANE WITH 5 μm PORE SIZE. (A) THE TOP SIDE OF THE MEMBRANE SHOWS A PROPER MONOLAYER OF CELLS WITH THE CHARACTERISTIC COBBLESTONE MORPHOLOGY. (B) ON THE BACKSIDE OF THE MEMBRANE, WHERE NO CELLS WERE SEEDDED, ENDOTHELIAL CELLS ARE FOUND AS A RESULT OF CELL MIGRATION THROUGH THE 5 μm PORES.

SUPPLEMENTARY FIGURE A3 SCANNING ELECTRON MICROSCOPY IMAGE OF hCMEC/D3 CULTURED ON POLYCARBONATE MEMBRANES IN THE PRESENCE (A & B) AND ABSENCE (C & D) OF HUMAN ASTROCYTES.

First the channels of the live/dead image are split into a GFP and a RFP image. The window/levels are equalized for all images as well as the brightness/contrast. After standardization of the images, the function “find maxima” is used to count the fluorescent pixels. The noise tolerance is set to 2000 for GFP and 2500 for RFP to correct for the background noise (Supplementary Figure A1).

SUPPLEMENTARY FIGURE A4 LIVE DEAD VIABILITY ASSAY SHOWING THE AVERAGE MEASURED PERCENTAGE (ERROR BARS = 1SD, $n=3$) OF LIVING CELLS ON PDMS AND PC MEMBRANES AT T=4 DAYS AND T=7 DAYS. THE AMOUNT OF LIVE AND DEAD CELLS IS COUNTED USING THE “FIND MAXIMA” METHOD IN IMAGEJ. FOR EACH SAMPLE, AT LEAST 1500 CELLS WERE COUNTED. NO SIGNIFICANCE DIFFERENCE IN VIABILITY BETWEEN THE TWO MEMBRANES AT BOTH TIME POINTS WAS FOUND (P -VALUE > 0.05, “NS” REPRESENTS NOT SIGNIFICANT).

B. Supplementary information Chapter 5

SUPPLEMENTARY FIGURE B1 SCHEMATIC ILLUSTRATION OF THE SENSITIVITY DISTRIBUTION OF A FOUR-PROBE IMPEDANCE SENSING SET-UP INSIDE A CYLINDER. IF THE FIELDS ALIGN, THE SENSITIVITY IS HIGH. IF THE FIELDS ARE PERPENDICULAR TO EACH OTHER, THE SENSITIVITY IS 0. WHEN THE FIELDS ARE OPPOSITE FROM EACH OTHER, THE NET SENSITIVITY IS NEGATIVE.

SUPPLEMENTARY FIGURE B2 CONNECTION TOPOLOGY OF THE IMPEDANCE SPECTROSCOPE. (A) “REGULAR” TOPOLOGY. (B) “INTERCHANGED” TOPOLOGY.

SUPPLEMENTARY FIGURE B3 SCALING RELATIONSHIP BETWEEN ELECTRODE WIDTH AND SENSITIVITY. THE AREA BETWEEN A SINGLE CURRENT CARRYING ELECTRODE AND A PICKUP CURRENT ELECTRODE IS SHOWN. THE SHARP INCREASE IN SENSITIVITY IS ALWAYS FOUND IN THE REGION BETWEEN THE TWO ELECTRODES. FITTED LINE: $y = x^{1.6} - 31$.

SUPPLEMENTARY FIGURE B4 SCALING RELATIONSHIP BETWEEN ELECTRODE SEPARATION AND SENSITIVITY. THE AREA BETWEEN A SINGLE CC AND PU IS SHOWN

SUPPLEMENTARY FIGURE B5 SCALING RELATIONSHIP BETWEEN SEPARATION OF CC AND PU ELECTRODE SETS AND SENSITIVITY. THE AREA BETWEEN A SINGLE CC AND PU IS SHOWN.

SUPPLEMENTARY FIGURE B6 SCHEMATIC 2D ILLUSTRATION OF THE FINAL ELECTRODE DESIGN. (A) THE “REGULAR” TOPOLOGY. (B) THE “INTERCHANGED” TOPOLOGY.

SUPPLEMENTARY FIGURE B7 ELECTRODE SENSITIVITY OF “REGULAR” ELECTRODE CONFIGURATION. THE POSITIONS OF ELECTRODES ARE INDICATED ON THE BOTTOM OF THE GRAPH. THE AREA WITH THE DASHED RECTANGLE IS USED TO EXTRACT THE RELATIONSHIP BETWEEN RESISTANCE AND TEER (FIGURE 2 OF THE MAIN TEXT).

SUPPLEMENTARY FIGURE B8 SENSITIVITY OF “INTERCHANGED” ELECTRODE CONFIGURATION. THE POSITIONS OF THE ELECTRODES ARE INDICATED ON THE BOTTOM OF THE GRAPH. THE AREA WITHIN THE DASHED RECTANGLE IS USED TO EXTRACT THE RELATIONSHIP BETWEEN RESISTANCE AND TEER (FIGURE 2 OF THE MAIN TEXT).

C. Supplementary information Chapter 6

SUPPLEMENTARY FIGURE C1 TIME LAPSE OF CHITOSAN MEMBRANE REMOVAL. TO VISUALIZE THE REMOVAL OF THE CHITOSAN MEMBRANE BY USE OF AN ACETIC ACID SOLUTION, THE CHITOSAN IS LABELED FLUORESCENTLY WITH A NHS-FLUORESCIN. THE ACIDIC SOLUTION IS INTRODUCED FROM THE SIDE MARKED WITH A #-SIGN. AFTER APPROXIMATELY 3 MINUTES, 90% OF THE MEMBRANE IS DISSOLVED LEAVING A SMALL TRAIL AT THE DISTAL POINT. THIS PART IS NOT REMOVED ENTIRELY AS THIS WOULD CAUSE HARM TO THE MATRIGEL LAYER.

D. Supplementary information Chapter 7

SUPPLEMENTARY FIGURE D1 SCHEMATIC OVERVIEW OF PLUNGER DESIGN. CLOCKWISE STARTING LEFT: SIDE VIEW OF PLUNGER. ISOMETRIC VIEW OF PLUNGER. TOP VIEW OF PLUNGER.

The plunger shown in Supplementary Figure D1 is designed to fit in a 24-wells plate, with space left to fit a needle next to the base to remove excess gelatin. The plunger has 6 pillars on which it can stand. These pillars are 1.7 mm tall, span 30 degrees of the base and are 0.7 mm thick. The pillars are strong enough to support the whole plunger, whilst giving space for the gelatin to solidify under it. The centre of gravity is designed to be low, so the plunger would not tip over. This means that the handle is smaller than the base of the plunger, 10 mm and 14 mm respectively. The total height of the plunger is 28.5 mm. All corners are rounded with a fillet, to smoothen the 3D printing process.

Scientific output

Journal articles

F. Avgidis[†], M.P. Tibbe[†], D.S. de Bruijn, A.M. Leferink, J.C.T. Eijkel and L.I. Segerink ([†] These authors contributed equally), *Assessing barrier properties using impedance spectroscopy in a semi-circular blood-brain barrier on-chip*, Manuscript in preparation.

A.M. Leferink, M.P. Tibbe, E.G.B.M. Bossink, L.E. de Heus, H. van Vossen, A. van den Berg, L. Moroni, R.K. Truckenmüller, *Shape-defined solid micro-objects from poly(d,l-lactic acid) as cell-supportive counterparts in bottom-up tissue engineering*, (2019), *Materials Today Bio*, 4, 100025

H. Le-The, M.P. Tibbe, J. Loessberg-Zahl, M. Palma do Carmo, M.W. van der Helm, J. Bomer, A. van den Berg, A.M. Leferink, L.I. Segerink, J.C.T. Eijkel, *Large-scale fabrication of free-standing and sub- μm PDMS through-hole membranes*, (2018), *Nanoscale*, 10, p. 7711-7718.

M.P. Tibbe, A.M. Leferink, A. van den Berg, J.C.T. Eijkel, L.I. Segerink, *Microfluidic gel patterning method by use of a temporary membrane for organ-on-chip applications*, (2018), *Advanced Materials Technologies*, 3, 1700200.

M.P. Tibbe, A.D. van der Meer, A. van den Berg, D. Stamatialis, L.I. Segerink, *Membranes for organs-on-chips*, (2017), Book chapter in: *Biomedical Membranes and (Bio)Artificial Organs*. Chapter 11: p. 295-321.

Conference contributions

F. Avgidis, M.P. Tibbe, A.M. Leferink, L.I. Segerink, *Assessing barrier properties using impedance spectroscopy in a semi-circular, blood-brain barrier on-chip*, MicroTAS (poster presentation), 27-31 October 2019, Basel, Switzerland.

M. Zakharova, M.W. van der Helm, M. Palma do Carmo, H. Le-The, M.P. Tibbe, A.D. van der Meer, K. Broersen, J.C.T. Eijkel, L.I. Segerink, *Multiplexed organ-on-chip device for increased throughput analysis of the tissue barrier function*, MicroTAS (poster presentation), 27-31 October 2019, Basel, Switzerland.

M.P. Tibbe, H. Le-The, J.C.T. Eijkel, A. van den Berg, A.M. Leferink, L.I. Segerink, *Transwell integrated porous sub-micrometer PDMS membranes as alternative cell culture platform*, EMBS Macro and Nanotechnology Conference (poster presentation), 10-14 December 2018, Kauai, HI, USA.

M.P. Tibbe, H. Le-The, A.M. Leferink, J.C.T. Eijkel, L.I. Segerink, *Porous sub-micrometer PDMS membranes as cell culture substrates in a microfluidic chip*, International Conference on Microtechnologies in Medicine and Biology (MMB) (poster presentation), 26-28 March 2018, Monterey, CA, USA.

M.P. Tibbe, A. van den Berg, L.I. Segerink, *Reversible on-chip fabrication of a porous biopolymer membrane used for blood-brain barrier on-chip applications*, International Organ-on-Chip Symposium (poster presentation), 2-3 May 2017, Lausanne, Switzerland.

M.P. Tibbe, A. van den Berg, L.I. Segerink, *Reversible on-chip fabrication of a porous biopolymer membrane used for blood-brain barrier on-chip applications*, NanoBioTech (poster presentation), 7-9 November 2016, Montreux, Switzerland.

Funding and contributions

Funding

The work in this thesis was funded by the ERC advanced grant VESCEL (grant no. 669768) of prof. dr. ir. Albert van den Berg. Part of the work presented in **Chapter 3** is supported by the Netherlands Center for Multiscale Catalytic Energy Conversion (MCEC), and the Netherlands Organisation for Scientific Research (NWO) Gravitation programme funded by the Ministry of Education, Culture and Science of the government of the Netherlands.

Contributions

The research presented in this thesis was carried out in collaboration with the people listed below. My supervisors, prof. dr. ir. Loes Segerink, prof. dr. ir. Albert van den Berg and dr. ir. Anne Leferink all provided input for all of the chapters presented in this thesis. Prof. dr. Jan Eijkel critically evaluated; and gave input to **Chapter 5** and **Chapter 6**. During the cell culture experiments, Paul ter Braak gave advise and assisted when needed.

Chapter 2 was based on a publication co-authored with dr. ir. Andries van der Meer and prof. dr. Dimitrios Stamatiadis.

Chapter 3 describes the use of a PDMS membrane developed by dr. Hai Le-The. We worked together in optimizing the membranes to be used for cell culture applications. Mariia Zacharova fabricated some of the used membranes.

During her Master assignment, Laura de Heus developed a hydrogel chip which is described in **Chapter 4**. Hans de Boer assisted with the development of the chip holder. The used hyaluronic acid based hydrogel was kindly provided to us by Jan Hendriks of the Developmental BioEngineering group (University of Twente).

During his Master Assignment Fotis Avgidis designed and developed a measurement set-up to be implemented in the hydrogel chip described in **Chapter 4**. In **Chapter 5** the results of the developed measurement set-up are described. Johan Bomer fabricated the electrode slides in the cleanroom.

Douwe de Bruijn contributed to this chapter by analysing results and writing parts of the used Matlab script.

Chapter 7 is a proof of concept chapter on which four students have worked. Bachelor student Marlowe Noll developed the first prototype of the plunger like manipulator for cell sheet transfer. During his internship, Saxion student Thomas Visscher further investigated the use of hydrogels to transfer endothelial cell sheets. Visiting Erasmus student, Catarina Lourenço developed a new method to better stabilize the cell sheet during detachment. Finally, during his capita selecta, Jasper ten Napel repeated some of the experiments. Joshua Loessberg-Zahl assisted with 3D-printing of the plunger like manipulators.