Sustainable Polyelectrolyte Complex Membranes Produced via Aqueous Phase Separation

Muhammad Irshad Baig

**SUSTAINABLE POLYELECTROLYTE COMPLEX
MEMBRANES PRODUCED VIA AQUEOUS PHASE
SEPARATION**

Muhammad Irshad Baig

**SUSTAINABLE POLYELECTROLYTE COMPLEX
MEMBRANES PRODUCED VIA AQUEOUS PHASE
SEPARATION**

DISSERTATION

to obtain
the degree of doctor at the Universiteit Twente,
on the authority of the rector magnificus,
prof. dr. ir. A. Veldkamp,
on account of the decision of the Doctorate Board
to be publicly defended
on Friday 8 October 2021 at 14.45 hours

by

Muhammad Irshad Baig

born on the 7th of June, 1991
in Rawalpindi, Pakistan

This dissertation has been approved by:

Supervisor

prof. dr. ir. W.M. de Vos

Cover design: Muhammad Irshad Baig

Printed by: Gildeprint – The Netherlands

Lay-out: Muhammad Irshad Baig

ISBN: 978-90-365-5241-7

DOI: 10.3990/1.9789036552417

© 2021 Muhammad Irshad Baig, The Netherlands. All rights reserved. No parts of this thesis may be reproduced, stored in a retrieval system or transmitted in any form or by any means without permission of the author. Alle rechten voorbehouden. Niets uit deze uitgave mag worden vermenigvuldigd, in enige vorm of op enige wijze, zonder voorafgaande schriftelijke toestemming van de auteur.

Graduation Committee:

Chair / secretary:

prof. dr. J.L. Herek

University of Twente, The Netherlands

Supervisor:

prof. dr. ir. Wiebe de Vos

University of Twente, The Netherlands

Committee members:

prof. dr. Suzana Nunes

KAUST, Saudi Arabia

prof. dr. Ernst Sudhölter

Technische Universiteit Delft, The Netherlands

prof. dr. Christian Nijhuis

University of Twente, The Netherlands

dr. Michael Duits

University of Twente, The Netherlands

dr. Pilar Ruiz Ramiro

University of Twente, The Netherlands

The research work presented in this thesis was carried out at the Membrane Surface Science, MSuS, group of the Faculty of Science and Technology (TNW) of the University of Twente, The Netherlands.

The project received funding from the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation programme (ERC StG 714744 SAMBA).

European Research Council

Contents

Contents	i
1 Introduction	1
1.1 Sustainability	3
1.2 Sustainability in Industry	4
1.3 Green/Sustainable Chemistry	5
1.4 Polymeric Membranes and the need for sustainability	6
1.4.1 Thermally Induced Phase Separation	6
1.4.2 Non-solvent induced phase separation (NIPS)	6
1.4.3 Membrane formation mechanism in NIPS	7
1.4.4 Unsustainable organic aprotic solvents	9
1.5 Green solvents and sustainable approaches for membrane production	10
1.6 Polyelectrolytes and Polyelectrolyte Complexation	12
1.6.1 Polyelectrolytes	12
1.6.2 Polyelectrolyte Complexation (PEC) and membranes	13
1.7 Thesis outline	16
1.8 References	18
2 Sustainable Membrane Production Through Polyelectrolyte Complexation Induced Aqueous Phase Separation	29
2.1 Introduction	30
2.2 Experimental Section	33
2.2.1 Materials	33
2.2.2 Preparation of polyelectrolyte casting solutions	33
2.2.3 Viscosity Measurements	34
2.2.4 Membrane fabrication	35
2.2.5 Membrane characterization	35
2.2.6 Pure water permeability and retention tests	35
2.3 Results and Discussion	37
2.4 Conclusion	44
2.5 Supporting Information – S2	46
2.6 References	54
3 Tuning the Structure and Performance of Polyelectrolyte Complexation based Aqueous	

Phase Separation membranes	59
3.1 Introduction	60
3.2 Experimental	62
3.2.1 Materials	62
3.2.2 Preparation and casting of polyelectrolyte solutions	62
3.2.3 Viscosity measurements	62
3.2.4 Characterization of the membranes	63
3.2.5 Pure water permeability and retention tests	63
3.3 Results and Discussion	64
3.3.1 Effect of added NaOH on the polyelectrolyte casting solutions	64
3.3.2 Effect of PSS:PAH monomer mixing ratio	66
3.3.3 Effect of pH of the coagulation bath	69
3.3.4 Effect of GA concentration in the coagulation bath	72
3.3.5 Chemical stability of the membranes	75
3.4 Conclusions	76
3.5 Supporting Information – S3	78
3.6 References	90
 4 Enhancing the separation performance of Aqueous Phase Separation based membranes through polyelectrolyte multilayer coatings and interfacial polymerization	 95
4.1 Introduction	96
4.2 Experimental Section	98
4.2.1 Materials	98
4.2.2 Membrane Fabrication	99
4.2.3 Multilayer coatings	100
4.2.4 Interfacial Polymerization	100
4.2.5 Characterization	101
4.3 Results and Discussions	102
4.3.1 Multilayer coatings	102
4.3.2 Interfacial Polymerization	106
4.4 Conclusions	109
4.5 Supporting Information – S4	111
4.6 References	116
 5 Sustainable Aqueous Phase Separation Membranes Prepared through mild pH shift induced Polyelectrolyte Complexation of PSS and PEI	 121
5.1 Introduction	122
5.2 Experimental Section	124
5.2.1 Materials	124
5.2.2 Preparation of casting solutions	124
5.2.3 Membrane casting	125
5.2.4 Membrane characterization	125
5.3 Results and Discussion	127
5.3.1 Effect of acetate buffer concentration	127
5.3.2 Effect of buffer pH in the bath	130
5.3.3 Effect of crosslinker	134

5.3.4	Effect of PEI molecular weight	137
5.3.5	Comparison with other APS membranes	141
5.4	Conclusions	142
5.5	Supporting Information – S5	144
5.6	References	155
6	Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation	161
6.1	Introduction	162
6.2	Experimental Section	166
6.2.1	Materials	166
6.2.2	Solution preparation	166
6.2.3	Casting	166
6.2.4	Membrane characterization	167
6.3	Results and Discussion	168
6.3.1	Selection of suitable polyelectrolyte mixture: Effect of molecular weight	168
6.3.2	Effect of overall polymer concentration	170
6.3.3	Effect of coagulation bath salinity	172
6.4	Conclusion	177
6.5	Supporting Information – S6	179
6.6	References	187
7	Hollow fiber PSS-PEI membranes prepared via sustainable Aqueous Phase Separation	193
7.1	Introduction	194
7.2	Experimental Section	196
7.2.1	Materials	196
7.2.2	Preparation of the dope solution	196
7.2.3	Hollow fiber membrane spinning	197
7.2.4	Membrane characterization	197
7.3	Results and Discussion	200
7.3.1	Composition of the bore liquid	200
7.3.2	Effect of acetate buffer concentration in the coagulation bath	203
7.3.3	Effect of the coagulation bath pH	207
7.4	Conclusions	210
7.5	Supporting Information – S7	212
7.6	References	216
8	Summary and Outlook	221
8.1	Summary	222
8.2	Outlook	224
8.2.1	PSS-PAH membranes	225
8.2.2	PSS-PEI membranes	226
8.2.3	PSS-PDADMAC membranes	227
8.2.4	Challenges for current APS membranes	230
8.2.5	Other polyelectrolyte systems for APS membrane production	231
8.2.6	Bio-derived polyelectrolytes and achieving complete sustainability	235

8.3	Overall conclusions	236
8.4	References	238
	Samenvatting	243
	Acknowledgements	247
	List of Publications	251
	About the author	253

"Knowing how to think empowers you far beyond those who know only what to think."

- Neil deGrasse Tyson

Chapter 1.

Introduction

On 14th February 1990, the Voyager I space probe tilted its camera towards Earth on the request of a famous scientist, astrophysicist, and the member of the mission's imaging team, Carl Sagan. The image it captured that day, **Figure 1.1**, forever changed the perspective of the place we all call home, the Earth.

From a distance of 6 billion kilometers, our Earth is nothing but a speck of dust in an infinite abyss of space. Nobody, except Carl Sagan himself, could have explained any better what the image portrayed. In his famous book, "Pale Blue Dot: A Vision of the Human Future in Space", he wrote, and I quote, *"Look again at that dot. That's here. That's home. That's us. On it everyone you love, everyone you know, everyone you ever heard of, every human being who ever was, lived out their lives. The aggregate of our joy and suffering, thousands of confident religions, ideologies, and economic doctrines, every hunter and forager, every hero and coward, every creator and destroyer of civilization, every king and peasant, every young couple in love, every mother and father, hopeful child, inventor and explorer, every teacher of morals, every corrupt politician, every "superstar," every "supreme leader," every saint and sinner in the history of our species lived there-on a mote of dust suspended in a sunbeam"* [1]. The pale blue dot, which is indeed one of its kind, is all that we have for now. It is certainly the only planet that supports life as we know. It is undeniably our collective responsibility to relish and preserve our home, the home which in recent times is in dire need of our support.

Figure 1.1 Earth as the 'Pale Blue Dot'. Image taken by Voyager 1 spacecraft from 6 billion kilometers away. The Earth can be seen as nothing but a fine particle of dust suspended in the vastness of space. The white circle is just a guide to the eye. Image credit *NASA/JPL-Caltech*.

Massive deforestation, rapid and unplanned urbanization, pollution, and our over reliance on fossil fuels has caused a major change in the earth's atmosphere. The Earth's resources are limited and the human population that utilizes those resources keeps growing at a rapid pace. The challenges are immense and therefore, governments and institutions around the world have been actively pursuing a case for saving our planet from the ultimate environmental disaster. In such times, the concept of sustainability becomes imperative. Sustainability is also a collective responsibility and encompasses the environment, us the people, and our world economy.

1.1 Sustainability

Nature itself works on the principle of complete environmental sustainability through the maintenance of ecosystems by comprehensive recycling and codependence of species. From the natural water cycle, carbon and nitrogen cycles, to food chains, the natural world provides for its inhabitants while also taking from them to create a balanced ecosystem. In nature, the recycling loop is usually not direct. Complex organic molecules are broken down into simpler ones which are then utilized by a variety of ecosystems before being transformed into completely new materials. One of the simplest examples is that of a dung beetle (*Coleoptera: Scarabaeidae*) which consumes animal excretions and converts it into nutrients for soil that are beneficial for plant life [2]. There are numerous such examples in the natural world where nature works to create a perfect balance between different ecosystems.

The concept of sustainability has also been partly utilized by the ancient human civilizations. The Indus Valley Civilization (ca. 3300 BC) were pioneers of urban planning, development, and sustainable architecture [3]. The world's first known sanitation and drainage system was built by the inhabitants of the Indus Valley Civilization where each house had a covered wastewater drainage system [3]. Furthermore, the houses were designed in such a way so as to keep them cool with breeze from the south in the summer months. Similarly, the ancient Egyptians utilized the annual flooding of river Nile to their advantage in order to support their sustainable food supply [4].

However, as the human population grew, so too did deforestation, invasive farming, and the domestication of animals, deteriorating the relationship of humans with their environment. With the industrial revolution beginning in the late 18th century and continuing throughout the 19th and 20th century, this imbalance grew larger with exponential increases in the atmosphere's carbon dioxide levels causing global warming and climate change.

No real efforts were made to address this issue until at least the 1980s when the Intergovernmental Panel on Climate Change (IPCC) was set up under the United Nations in 1989 to scientifically study and assess the impacts of climate change [5]. The Earth Summit in 1992 brought together 178 countries to adopt a comprehensive plan for sustainable development that protects the environment while improving human lives [6]. The major breakthrough, however, was achieved in 2015 when the United Nations set 17 distinct sustainable development goals (SDGs) and 169 targets for the year 2030 with the aim to improve human life and to protect the planet [7]. Governments around the world, especially the European Union are keen on implementing the SDGs and its targets before 2030 by making policies and legislation that oblige the industry towards adapting sustainable solutions. While the SDGs include several types of aims, this thesis only focuses on industrial sustainable manufacturing.

1.2 Sustainability in Industry

Earlier approaches towards getting industry to make their manufacturing processes more sustainable were mostly carried out under the banner of Environmentally Conscious Manufacturing (ECM) [8,9]. This required coming up with methodologies and processes for manufacturing new products from conceptual design, distribution, and finally end of life (EOL) disposal, in a manner that satisfied environmental standards and requirements. Similarly, the concepts of corporate social responsibility and corporate citizenship were introduced to compel the industry to take more responsibility and to get involved in ecofriendly activities [10]. However, such initiatives barely made any impact on the manufacturing processes. The continuous environmental degradation resulted in tougher legislations thereby also leading to penalties for non-compliance. In addition, the growing public interest in the environment and sustainable practices, especially in the last decade or so, has driven many corporations towards adopting cleaner and more transparent practices.

Electric power generation, for example, has seen a major shift towards generating power using green and sustainable sources such as solar, wind, and hydro. The European Union (EU) is undoubtedly the forerunner in renewable energy and in recent years has implemented extensive legislation to reduce greenhouse emissions from fossil fuel power plants [11]. The EU aims to increase the share of renewable energy in its final energy consumption to 27–30% by 2030 [11]. There has already been considerable progress regarding this goal with countries including Germany, Denmark, Finland, The Netherlands, among others, investing heavily in solar and wind energy. The national railways of The Netherlands, Nederlandse Spoorwegen, runs its trains entirely on electricity generated by wind [12]. Similarly, Germany aims to increase the share of its renewable energy in the final energy production to 80% by 2050 [13]. These are just a few examples of a global race towards energy sustainability where the focus is now shifting towards generating electric power from renewable sources [14].

A similar transition towards sustainability can also be found in many other industries. Tesla has already pioneered electric vehicles and has completely eliminated gasoline and diesel from its automobiles. Other automobile manufacturers are following Tesla's footsteps and heavily investing in their electric vehicles technology. Additionally, the two largest automobile manufacturers in the world, Volkswagen Group and Toyota Motors, plan to be CO₂ neutral companies by 2050 [15,16]. Similarly, the merchant shipping operators aim to reduce their carbon footprint [17], where the largest shipping company, Maersk, intends to operate net-zero emission vessels by 2023 [18]. The concept of sustainability has also been keenly implemented by the food and beverage industry. For instance, The Coca Cola Company is already working on developing sustainable packaging and recycling every bottle and can that is produced in their facilities [19]. The fast food chains McDonalds and KFC have implemented policies that require their franchises to use packaging that comes from renewable, recycled and certified sources [20,21]. One of the largest E-commerce companies, Amazon, is on its way to powering their operations with 100% renewable energy by 2025 [22]. Furthermore, Amazon has ordered over 100,000 fully-electric delivery vehicles for their logistics operations [22].

While all these steps towards a cleaner environment from all the above mentioned organizations and industries must be appreciated, it should also be recognized that these steps are certainly not enough to achieve complete environmental sustainability. The Great Pacific Garbage Patch,

located between Hawaii and California, paints a grim picture of such sustainability efforts. Similarly, oil spillages and waste disposal in our oceans has significantly impacted the marine ecosystem. While there are considerable efforts devoted towards mitigating environmental pollution, there is still a long way to go before a fair balance between humans and their environment can be achieved. Furthermore, complete sustainability where Earth's resources are utilized and fully replenished is still a distant dream. But small consistent efforts towards saving our planet and its environment can certainly take us one step closer to achieving this dream.

1.3 Green/Sustainable Chemistry

By far the largest stake holder that can ensure environmental sustainability is the chemical industry. All the industries mentioned before can only cut carbon emissions if the products they use are obtained/manufactured in a sustainable and greener approach. Most of the chemical manufacturing today is based on carbon, which is a finite resource obtained from Earth. Carbon is utilized in its various forms to produce a wide array of products ranging from a simple pen to components of a space shuttle. Once used, most of the products are then wasted as it has become increasingly difficult to reutilize or recycle them, with most incinerated, or ending up in landfill sites or even worse, in our vast and unprotected oceans.

Over the past few decades, the chemical industry has made significant improvements in the manufacturing processes to address this issue by adapting what is called as the “Green Chemistry” approach, introduced in late 90's by Paul Anastas and John Warner [23]. Simply put, Green Chemistry employs raw materials preferably obtained from renewable sources, reduces/eliminates waste, and prevents the use of hazardous substances in the production and usage of chemical products. Unlike cleaning and treating pollution and waste, Green Chemistry reduces the waste at its source by limiting or completely eliminating the use of hazardous substances, solvents, and other compounds. For instance, a hazardous product that is widely used for a certain application should be replaced with a more sustainable and greener product. In this manner, the demand for such hazardous products will eventually diminish and the product will no longer be produced. This is chemical sustainability in its most simplest form.

Indeed, it is not easy to replace all hazardous chemicals but their use can be restricted while searching for more green alternatives. Green chemistry and sustainable chemistry can therefore be thought of as synonyms which outlines 12 principles that act as guidelines for sustainable manufacturing and design [24]. These principles apply to all the aspects of the process life-cycle starting from design, raw materials, syntheses, biodegradability and toxicity of the chemicals used. One of these principles is 'solvents' which is also one of the most actively researched areas [25]. Most of the solvents used in chemical processes are toxic, flammable, and/or corrosive and therefore require expensive recycling and treatment processes [24]. According to one study, a large percentage of industrial waste is made up of these types of solvents [26]. There are increasing efforts to minimize and/or eliminate the use of such organic solvents and to find solvent free or green solvent approaches for the chemical processes [27]. Numerous industries that used hazardous solvents in the past have tried to either limit the use or have completely shifted to greener alternatives. It is only natural that the polymeric membrane industry also realizes the need for sustainable manufacturing and focuses on developing greener membrane fabrication protocols.

This brings us to the topic of this thesis; sustainability in membrane fabrication.

1.4 Polymeric Membranes and the need for sustainability

As mentioned in **section 1.2**, many industries are on a path towards sustainable development and some of them have even made significant progress in achieving their SDGs. However, the polymeric membrane industry, a multi-billion dollar industry, lags behind in this drive towards sustainability. This is partly due to the lack of scalable green alternatives and also somewhat due to the relatively below par separation properties of membranes produced through existing green approaches. Before delving into more details of sustainable membrane fabrication, it is pertinent to understand how polymeric membranes are currently produced and why this approach is unsustainable.

Polymeric membranes can be produced through a multitude of techniques among which phase separation is by far the most frequently applied method. The two major phase separation approaches are thermally induced phase separation (TIPS) and non-solvent induced phase separation (NIPS).

1.4.1 Thermally Induced Phase Separation

In TIPS, a polymer is first dissolved in a high boiling point solvent at elevated temperatures followed by casting it into a desired shape. The cast solution is then cooled which induces phase separation. The polymer solidifies via crystallization, gelation, or glass transition after which the solvent is removed typically by solvent extraction [28–33]. Polymeric membranes produced via TIPS generally have symmetric and porous structures that can be used for microfiltration and membrane contactor applications [34]. Asymmetric membranes can also be obtained via TIPS by introducing a thermal gradient during the cooling of the polymer solution [28,35,36]. TIPS is generally chosen when the polymers are difficult to dissolve in common organic solvents at room temperature [32]. Despite being known for its simplicity and ability to prepare anisotropic and isotropic structures, the TIPS technique is more energy intensive than NIPS [37].

1.4.2 Non-solvent induced phase separation (NIPS)

NIPS is one of the most popular phase inversion methods due to its versatility that allows the production of membranes with various morphologies and pore sizes. A schematic illustration of the NIPS process is shown in **Figure 1.2**. In this technique, a polymer is first dissolved in an organic solvent, typically N-methylpyrrolidone (NMP). The polymer solution is then cast into a desired shape and immersed in a non-solvent bath, typically water. The polymer, being insoluble in water, precipitates into a porous solid film, a membrane [38–44]. The polymer rich phase forms the bulk and the polymer lean phase forms the pores of the membrane. Thus in NIPS, a liquid polymer solution is transformed into a solid film via controlled precipitation. NIPS is also widely known as immersion precipitation. Both symmetric and asymmetric membranes with tunable pore sizes and morphologies can easily be prepared using this method.

The NIPS technique was first demonstrated in the 1960's by a graduate student Sidney Loeb, and a Post Doc from University of California, Los Angeles, Srinivasa Sourirajan, when they prepared integrally skinned asymmetric Cellulose Acetate membranes for seawater desalination

Figure 1.2 Schematic illustration of the membrane fabrication process via the Non-solvent induced phase separation NIPS technique.

[45]. In such asymmetric membranes, the separation is achieved at the thin skin layer whereas the porous support provides the mechanical strength. It was a major breakthrough in the field of membrane science that proved to be a foundation that ultimately led to large scale production of membranes for seawater desalination using reverse osmosis. Over the past five decades abundant knowledge has been generated in regards to NIPS membranes where researchers have meticulously investigated various parameters that affect the membrane formation and the resulting structure. These membrane formation mechanisms are discussed in detail in the next section.

1.4.3 Membrane formation mechanism in NIPS

The final structure and morphology of a NIPS membrane is determined by a combination of thermodynamic and kinetic aspects of phase separation. Since the NIPS process comprises of three components i.e. a polymer, solvent, and a non-solvent, the thermodynamic interactions between these components are best visualized using a ternary phase diagram, first presented by Strathmann *et al.* in 1971 [38]. In their studies, thermodynamic aspects of phase separation were discussed in detail in terms of instantaneous and delayed demixing which provided diverse membrane structures [38,40]. Over the years numerous studies have been conducted on understanding and explaining the ternary phase diagram, both, experimentally [38,46–49] and theoretically [50–55].

A typical ternary phase diagram is illustrated in **Figure 1.3** where the corners of the triangle represent pure components and any point inside the triangle corresponds to a mixture of these components [56].

The red binodal line in **Figure 1.3** separates the one phase thermodynamically stable region, where all the components are miscible, from the two phase region where the system separates into a polymer rich and a polymer lean phase. The precipitation route from initial polymer

Figure 1.3 Schematic illustration of a ternary phase diagram indicating the binodal and the path a polymer solution takes towards precipitation. Reprinted from Sadrzadeh *et al.* [56] with permission from Elsevier, Copyright (2013).

solution to the final membrane composition is shown by the broken line. As the precipitation proceeds, the viscosity of the precipitated polymer continues to increase until it becomes high enough to be classified as a solid (solidification point). Drawing a tie line at this point reveals the composition of the polymer rich and lean phases. At the final membrane composition point as shown in **Figure 1.3**, the solid polymer-rich and the liquid polymer-lean phases are in equilibrium. The polymer-rich phase constitutes the bulk of the membrane while the polymer-lean phase constitutes membrane pores that are filled with non-solvent till the membrane is taken out of the precipitation bath. The position of the final membrane composition point on the Polymer–Non-solvent axis on the ternary phase diagram determines the final overall porosity of the resulting membrane. The binodal curve (liquid-liquid demixing) in the ternary phase diagram is usually determined by measuring the cloud points using titration or turbidity measurements [46].

Based on the ternary phase diagram, Strathmann *et al.* described liquid-liquid demixing as either instantaneous or delayed [40]. If the miscibility gap, shown as MG in **Figure 1.3**, is shorter, the polymer solution is close to being thermodynamically unstable and therefore, precipitates rapidly upon immersion in a non-solvent, thus *instantaneous demixing*. This typically leads to membranes having thin skin layers with large ‘finger-like’ macrovoids in the substructures. On the other hand, if the miscibility gap is larger, the liquid-liquid demixing takes longer time resulting in membranes with dense top layers having ‘sponge-like’ substructures, i.e. *delayed demixing* [40,41].

The demixing terms can also be related to the kinetic aspects of phase inversion i.e. the rate of solvent and non-solvent exchange. The driving force for such an exchange is the difference in chemical potential of the solvent and non-solvent over both the phases. This difference is largest when the polymer solution first comes in contact with the non-solvent bath resulting in the highest exchange rate at this point, consequently forming a thin top layer that acts as a diffusion barrier. As the diffusion of solvent from polymer solution into the non-solvent bath (and vice

versa) continues, the chemical potential difference reduces and the exchange rate slows down.

Phase separation is indeed a dynamic process where the composition of the three components continues to change until complete precipitation is observed. Intuitively, this complex precipitation process is greatly influenced by a number of parameters such as the polymer solution concentration, type of polymer and solvents, miscibility of solvent and non-solvent, composition of polymer solution, the non-solvent bath, and casting temperature [37,57].

Increasing the polymer concentration, thereby increasing the solution viscosity, slows down the solvent exchange and therefore, suppresses the formation of macrovoids typically resulting in denser membranes [37,39,58–60]. The miscibility of solvent and non-solvent is another vital parameter that dictates the kinetics of solvent exchange. As described earlier, a rapid solvent and non-solvent exchange typically forms asymmetric porous membranes. Similarly, additives in the polymer solution act as non-solvent materials that reduce the solvent power in the polymer solution [61,62]. Additives are typically added as pore forming agents, viscosity enhancers and/or phase inversion kinetics accelerators. Polymers like polyethylene glycol (PEG) and polyvinylpyrrolidone (PVP) and inorganic materials like LiCl are the most commonly used additives in polymer solutions [63]. Furthermore, addition of solvent in the non-solvent bath can slow down the precipitation rate resulting in microporous membranes [39,43]. Accordingly, all these parameters, among many others, can be systematically controlled to obtain various types of membrane morphologies ranging from dense to porous. The availability of a wide variety of polymers, both rubbery and glassy, provides additional tuning parameters to obtain all sorts of desirable membranes. As a result, the polymer/solvent combination becomes a vital parameter that controls morphology and properties of resultant membranes. A higher miscibility of polymer in the solvent typically results in porous membranes while non-porous membranes are usually obtained when the miscibility is low. Typically, aprotic organic solvents such as dimethyl formamide (DMF), dimethyl sulfoxide (DMSO), dimethyl acetamide (DMAc), and *N*-methylpyrrolidone (NMP) are used for preparing asymmetric polymeric membranes [44].

Over the years a plethora of knowledge has been generated addressing the effects of all such parameters that affect the thermodynamics and kinetics of phase inversion. NIPS is indeed a versatile technique where the membrane formation mechanisms are well-known and thoroughly investigated and as a result, became a desirable technique to produce polymeric membranes for almost all commercial applications.

1.4.4 Unsustainable organic aprotic solvents

As mentioned in **section 1.3**, one of the 12 principles of green chemistry is ‘solvents’. It requires that the solvents and auxiliaries that are being used shall be made safe and if toxic, shall not be used at all. Wang *et al.* conducted a survey of relevant literature from 2014 – 2019 on NIPS membranes and enlisted the most commonly used solvents by their frequency of use, see **Figure 1.4** [64].

It is evident that dimethyl acetamide (DMAc), dimethylformamide (DMF), and *N*-methylpyrrolidone (NMP) are the most commonly used solvents for membrane production, NMP being the foremost choice. Unfortunately, these solvents are reprotoxic, harmful to the environment, unsustainable, and therefore have been identified as substances of very high concern (SVHC) [65]. Consequently, they have been added to the Registration, Evaluation,

Figure 1.4 Frequency of use of most commonly used (a) solvents and (b) polymers for producing NIPS membranes in literature. Data obtained by Wang *et al.* [64] from publications from 2014 – 2019, reprinted with permission from Elsevier, Copyright (2019).

Authorization, and Restriction of chemicals (REACH) of the European Chemicals Agency [66]. Apart from being used as solvents in higher concentrations, these chemicals are completely mixed in the non-solvent bath after the NIPS membrane production, thereby contaminating the wastewater stream. According to the studies conducted by Razali *et al.*, an estimated 20 – 100 billion liters of such contaminated wastewater is produced annually by the membrane industry [67]. Disposing such a waste stream itself becomes challenging and requires expensive treatment cycles. Owing to the environmental and human safety hazards, NMP has been restricted for use in the European Union through the REACH legislation since May 2020 [68]. Such restriction requires significant improvements in the health and safety protocols for using NMP and similar toxic solvents to ensure workers and environmental safety.

There is no doubt that reprotoxic organic solvents need to be further restricted and possibly banned if the principles of green chemistry and the sustainable development goals are to be followed. Following the directives of the European Commission, there are growing demands to ban these solvents at least in the European Union in future [69]. The stringent legislative crackdown on such chemicals and growing environmental concerns have opened up a research area in the field of green solvents for polymeric membrane production.

1.5 Green solvents and sustainable approaches for membrane production

Plato, in his Socratic Dialogue, Republic', wrote, "*Our need will be the real creator*" [70]. Over the centuries, these words were molded into the famous proverb that we all learned as a kid, "Necessity is the mother of invention". History suggests that the greatest innovations always happen in the times of need. The need of the hour, in terms of NIPS membranes, is the development and use of sustainable green solvents. Such a solvent should ideally be completely non-toxic, preferable biodegradable, obtained from renewable sources, water soluble/miscible, have low molecular weight, and a higher boiling point. The search for such an ideal solvent

has a long way to go but significant progress is being made in this field. This thesis eventually demonstrates that using the most abundant solvent on Earth, water, might just be the answer. This will be discussed in detail in the next section.

Over the last decade or so, numerous studies have been conducted to identify sustainable alternative solvents to the reprotoxic NMP and DMAc. A review by Figoli *et al.* in 2014 highlighted several environmentally friendly and even biodegradable solvents for membrane production [71]. These included methyl lactate and ethyl lactate for the production of ultrafiltration (UF) type cellulose acetate membranes having a molecular weight cut-off (MWCO) in the range of 15 to 35 kDa [72]. However, the resultant membranes showed defects, inhomogeneity, macrovoids on the surface, and large differences in pure water permeability.

Solvents like Dimethyl sulfoxide (DMSO), γ -Butyrolactone (γ -BL), and certain ionic liquids were also investigated as possible alternatives to traditional organic solvents [71,73]. DMSO in particular is obtained from the wood pulp industry and is renewable. However, recently there have been some concerns regarding its toxicity in vitro [74].

Matsuyama *et al.* prepared microfiltration type cellulose acetate membranes having pore sizes in the range of 1–2 μm using supercritical CO_2 [75,76]. This process yielded the benefit of recovering the solvent and recycling the supercritical CO_2 . Still, more systematic studies are needed to evaluate the applicability of this process because it requires utilization of specialized equipment, precise CO_2 pressure control, and is currently limited to only a few polymers.

A new non-reprotoxic and biodegradable solvent, TamiSolve[®] NxG, was used by Marino *et al.* to prepare Poly(vinylidene fluoride-hexafluoropropylene) P(VDF-HFP) membranes having pore sizes ranging from 20 nm to 450 nm [77]. However, the use of TamiSolve[®] NxG for other polymers has not yet been shown which potentially limits its applicability.

The search for a sustainable solvent continued with Hassankiadeh *et al.* proposing Rhodiasolv[®] PolarClean as a biodegradable solvent for preparing high permeability hollow fiber membranes via TIPS [78]. PolarClean[®] is one of the most promising green solvents for preparing polymeric membranes and has been used to prepare membranes with conventional polymers such as Polyethersulfone (PES) [79], Polysulfone (PSf) [80] and Poly(vinyl chloride) (PVC) [81]. The major advantage of using PolarClean[®] is that it shows high solubility for conventional polymers, has lower toxicity, and can be used to prepare various types of membranes [64,82–85]. Its multistep synthesis protocol and higher price, almost twice that of NMP, limits its widespread use at the moment [79].

Acetyl tributyl citrate (ATBC), also known as *Citroflex*[®] A4, is an environmentally friendly diluent that has been used to prepare Poly(vinylidene fluoride) (PVDF) membranes via TIPS [83,86]. ATBC is made by esterification of acetic acid and tributylcitrate and is typically used as plasticizer for PVC and urethane polymer systems [87]. Currently, ATBC is only limited to TIPS because it is not miscible with water and therefore, cannot be used to produce NIPS membranes.

In another instant, Dihydrolevoglucosenone (*Cyrene*TM) was investigated by Marino *et al.* as a bio-derived green solvent for preparing PES and PVDF membranes having pore sizes in the range of 20 nm to 120 nm and 30 nm to 550 nm, respectively [88]. *Cyrene*TM is derived from cellulose, has a similar polarity to NMP and therefore, is one of the most promising green solvents. Recent studies have shown that it can also dissolve PVC to prepare polymer inclusion membranes [89].

CyreneTM is a relatively new addition to the family of green solvents for membrane production and only a few studies have investigated its applicability. Therefore, more research is needed to establish its widespread usage and versatility.

It has been established that the sustainability drive in the polymeric membranes industry is on the right track and a number of research groups have been actively pursuing the search for a green solvent to produce membranes with tunable pore sizes and morphology. The literature on sustainable membranes and green solvents has been growing during the past five years with several review articles being published on the subject [90–94]. While most of the solvents mentioned above have benefits such as biodegradability, lower toxicity, and/or renewability, questions remain over their usage as universal solvents to obtain membranes for all sort of applications. Most of these green solvents are still limited to only a specific type of polymer and in some cases the membrane production protocols are cumbersome. Furthermore, most of the membranes prepared using these green solvents have limited control over pore size and structure. Therefore, a universal solution to address all such challenges is necessary. This can be obtained by utilizing the most abundant solvent on earth, water.

Most conventional polymers are insoluble in water and that is one of the reasons why it is not readily investigated as a solvent. Consequently, a different class of polymers, called polyelectrolytes (charged polymers), have to be used for an aqueous based phase inversion approach.

1.6 Polyelectrolytes and Polyelectrolyte Complexation

1.6.1 Polyelectrolytes

Polyelectrolytes (PEs) are water soluble macromolecules that bear a charge on their repeating unit and have oppositely charged counter-ions to preserve electro-neutrality [95]. Polyelectrolytes are typically divided into either strong or weak polycations and polyanions. Polycations are positively charged while polyanions are negatively charged polyelectrolytes.

A strong polyelectrolyte is the one whose charge is independent of the pH of the aqueous solution. Typical examples include poly(diallyldimethylammonium chloride) (PDADMAC) [96] and poly(sodium styrene sulfonate) (NaPSS) [97], see **Figure 1.5**. By contrast, the charge of weak polyelectrolytes can be manipulated by changing the pH of the aqueous solution. Consequently, the chain conformation and the solubility of a weak polyelectrolyte is pH dependent [98]. Some examples include poly(allylamine hydrochloride) (PAH), poly(acrylic acid) (PAA), and polyethyleneimine (PEI).

Polyelectrolytes are used in various fields including biomedicine, cosmetics, food, pharmaceutical, gels etc. [99]. One of the major applications for polyelectrolytes is in the pharmaceutical and biomedicine industry where they have been used for drug delivery, tissue cell culture, as coating materials, and binding agents among numerous other applications [95]. The field of polymeric membranes has also utilized PEs, though mainly as a coating layer on a porous membrane support. As water soluble macromolecules, PEs are indeed materials of interest with interesting properties and applications.

Figure 1.5 Chemical structures of strong polyelectrolytes such as a) poly(sodium styrene sulfonate) (NaPSS), c) poly(diallyldimethylammonium chloride) (PDADMAC) and weak polyelectrolytes like b) poly(allylamine hydrochloride) (PAH), d) polyethyleimine (PEI). The charge on the weak polyelectrolytes PAH and PEI is pH-dependent and hence, can be manipulated.

1.6.2 Polyelectrolyte Complexation (PEC) and membranes

Mixing aqueous solutions of oppositely charged polyelectrolytes typically results in phase separation of the PE chains, forming a polyelectrolyte complex (PEC), shown schematically in **Figure 1.6** [100–103].

The driving force for PEC formation is the increase in entropy due to the release of counterions. However, studies have shown that electrostatics, hydrophobic interactions and hydrogen bonding may also contribute to the complexation process [102]. In simplest terms, the PEC formation can be represented by eq. 1.1 [104]:

Where Pol^+ and Pol^- is polycation and polyanion respectively, and A^- and B^+ are the counter-ions. $\text{Pol}^+ \text{Pol}^-$ represents the intrinsic ion pair that determines the structure, phase, and properties of PEC.

PECs can range from being polymer-lean viscous liquids, called ‘coacervates’ to polymer-rich solid-like materials called ‘precipitates’ [105]. The water-rich coacervates are commonly used in the field of biomedical science as bio-adhesives [106], scaffolds for tissue growth [107], and for

Figure 1.6 Schematic diagram illustrating the formation of a polyelectrolyte complex upon mixing oppositely charged polyelectrolytes. The driving force for the formation of complex is the increase in entropy due to the release of counter-ions.

drug delivery applications [108]. On the other hand, solid PEC precipitates have been used in multiple applications as first shown by Michaels in the 1960s who pioneered the research on PECs [100]. After that, the research on PECs gained momentum with focus on understanding the formation mechanisms and finding potential applications. Recently, Schaaf *et al.* highlighted several applications of solid PECs and so-called ‘saloplastics’ (salt plasticized PECs) [109].

Similar to the membrane formation mechanism via NIPS as discussed in **section 1.4.3**, the PEC formation is also governed by thermodynamic and kinetic aspects [102,103]. The thermodynamics of PEC formation are quite complicated and most aspects are beyond the scope of this thesis. For further deliberation, the reader is guided to publications by Thünemann *et al.* [102] and van der Gucht *et al.* [103]. The most important factors dictating PEC structure and properties include the linear charge density, chain stiffness, molecular weights and concentration of the polyelectrolytes, mixing procedure and mixing ratios, type of salt, concentration of salt, pH, nature of ionic group, hydrophobicity, and structure of the polyelectrolyte [95,110].

Some of these parameters have a greater impact on the kinetics of PEC formation than others and they critically influence the final structure and properties. For instance, even if the mixing ratio is 1:1, the final stoichiometry in the PEC can deviate leading to a charged PEC. Salt tends to weaken the electrostatic interactions between the polyelectrolytes and facilitates rearrangements of chains in PECs [102]. Added salt slows down the kinetics of PEC formation. In addition, the size of PEC aggregates tends to be larger at higher ionic strengths. The two factors (mixing ratio and salt concentration) are emphasized here because they will be used to produce PEC membranes later in the thesis.

Certainly, the polyelectrolytes and their complexes are quite sensitive to their environment making them interesting materials with fascinating properties. An important point to make

here is that the formation of PEC only needs aqueous solvents at ambient temperatures, making complexation a non-toxic and environmentally friendly process. Naturally, the process of preparing membranes using PECs would be sustainable as it would completely rely on water.

In the field of membrane science, PECs found applications after Decher *et al.* obtained self-assembled polyelectrolyte multilayers (PEM) by alternatively coating polycations and polyanions on solid supports [111]. The so-called ‘layer by layer (LBL)’ approach gained widespread attention in the membrane field because it provided ultra-thin coatings with tunable structures and properties [112]. Multiple reviews outlining the formation, structure, properties, and applications of PEMs have been published in the last decades that outline how versatile and successful this technique has been for obtaining dense functional coatings [113–115]. PEM membranes prepared by the LBL approach have been used for all sorts of membrane applications including pervaporation, nanofiltration, reverse osmosis, and gas separation, as described in a review article by Joseph *et al.* [112]. However, all PEM membranes are coatings on a support membrane which is still prepared using organic solvents via the NIPS process. Moreover, the LBL approach is not perfect for the fabrication of PEM membranes because the process is laborious and time consuming. Therefore, it is beneficial to have a single step formation mechanism that provides free-standing PEC membranes. Since PEC formation is based on an aqueous system, it is an ideal system to prepare organic solvent free membranes that can be used for a range of applications.

Over the years detailed efforts have been devoted to preparing such PEC membranes. Bromberg prepared PEC composite membranes for ion-exchange applications by impregnating nitrocellulose ultrafilters with polyelectrolytes [116]. Nam *et al.* prepared PEC membranes having a high water flux using poly(acrylic acid) and chitosan for pervaporation applications [117]. These works lead to several other studies that also developed PEC membranes for pervaporation applications [118–122]. Richau *et al.* prepared PEC membranes using a different approach called the ‘interfacial reaction method’ where one polyelectrolyte is first cast on a glass plate followed by spreading a layer of second polyelectrolyte on top of it [123,124]. All these PEC membranes were useful for pervaporation applications because their swelling degree could be controlled by simply changing the pH. The ionic crosslinking density is significantly influenced by the pH such that a higher degree of crosslinking reduces the swelling degree resulting in higher selectivity. However, the major drawback of the interfacial PEC process was the inhomogeneity in the membrane surface and lack of control on the degree of (ionic) crosslinking.

The properties and performance of the PEC membranes discussed so far have been promising however, in most cases, a support membrane prepared by NIPS still has to be used because of the difficulties in obtaining processible PEC membranes [125–128]. Furthermore, most of the PEC membranes were prepared in a multistep approach where a polyelectrolyte complex is prepared first and then either re-dissolved or post processed [129,130], providing extremely little to no control over the properties of the final PEC membrane.

To address all these challenges, a one-step, scalable aqueous based approach is required to prepare PEC membranes through a process that provides similar control over the membrane structure and morphology as the traditional NIPS. In this thesis, such an approach is introduced and discussed in detail. Briefly, the one-step approach was made possible by first preparing a homogeneous solution of a strong and a weak polyelectrolyte at a higher pH/higher salt concentration, followed by precipitation in a low pH /de-ionized water bath.

Similar to NIPS, the thermodynamics of the polyelectrolyte solution and the kinetics of precipitation/complexation can be easily controlled to obtain various types of structures and morphologies. Several tuning parameters are at disposal that can be manipulated to obtain desired membrane structures. The most prominent aspect of this approach is that it is completely water based and eliminates the use of reprotoxic organic solvents such as NMP. This new approach is, therefore, termed ‘Aqueous Phase Separation (APS)’.

Four different types of polyelectrolytes were used in this work to prepare free-standing PEC membranes, see **Figure 1.5**. These include poly(diallyldimethylammonium chloride) (PDADMAC), poly(sodium 4-styrene sulfonate) (NaPSS) as strong polyelectrolytes and poly(allylamine hydrochloride) (PAH), branched polyethyleneimine (PEI) as the weak polyelectrolytes.

1.7 Thesis outline

The value of an idea lies in the using of it. All the preface and discussion we had before boils down to the actual verification and validation of the idea. The aim of this work is to develop a phase inversion technique for the production of polymeric membranes without using reprotoxic organic solvents. This is achieved by using water as both the solvent and non-solvent for producing polyelectrolyte complex membranes. The versatility of this new ‘Aqueous Phase Separation (APS)’ approach was realized by exploring several parameters that influence the membrane structure and morphology. Similar to the traditional NIPS, factors such as the molecular weight of the polyelectrolytes, casting solution concentration, and bath conditions were explored as tuning parameters to obtain membranes for micro-, ultra-, and nanofiltration applications. Furthermore, the thesis takes this technique one step further in terms of scalability by demonstrating that the APS process can also be used to produce excellent hollow fiber membranes. This thesis describes in detail the various polyelectrolyte systems and the tuning parameters used to produce more sustainable polymeric membranes. The following chapters will give a detailed account of how APS works and how membranes with tunable structures can be prepared.

Chapter 2 gives the first account of complexation-induced APS where a combination of a strong polyanion i.e. PSS and a weak polycation i.e. PAH is used to prepare flat sheet PEC membranes. A homogeneous solution of the two polyelectrolytes is prepared at high pH and precipitated in a low pH bath to obtain pH-induced phase separation membranes with diverse morphologies.

Chapter 3 further explores various parameters that influence the PSS-PAH membrane formation mechanisms such as the pH of the casting solution and precipitation bath, polyelectrolyte monomer mixing ratio, and concentration of crosslinking agent.

Chapter 4 explores the possibility of using APS membranes as supports for functional coatings. Interfacial polymerization and polyelectrolyte multilayer coatings were built on top of ultrafiltration type PSS-PAH membranes resulting in thin selective top layers, thereby improving the nanofiltration performance of the membranes. The major advantage of using APS membranes for coatings is the inherent charge and the excess amine groups in the PSS-PAH membranes that facilitate the multilayer buildup as well as binding of the polyamide layer. Just like NIPS membranes, APS membranes act as excellent support membranes for coatings.

Chapter 5 investigates a different polyelectrolyte system to prepare APS membranes. Here, PSS is complexed with PEI to fabricate excellent nanofiltration type membranes at even milder pH conditions by use of a buffered coagulation bath. This approach is even more environmentally friendly and provides membranes with excellent properties and performance.

Chapter 6 investigates a salt induced phase separation approach for fabrication of APS based PEC membranes. This chapter demonstrates the PSS-PDADMAC membranes can be prepared using only salt as the switch for phase inversion. A homogeneous solution of the two electrolytes is prepared at high salt concentrations where the charges are screened. A thin film of this solution is precipitated in deionized water that induces phase separation resulting in polyelectrolyte complexation. The obtained PEC membranes show decent nanofiltration performance.

Chapter 7 takes the APS approach one step further by demonstrating that the hollow fiber geometry can also be obtained using this novel technique. PSS-PEI hollow fiber membranes with varying pore sizes and separation performance are prepared highlighting the significant potential of APS.

In the end, in **Chapter 8**, I reflect on the results obtained during the duration of my PhD work on APS membranes and outline unexplored areas of interest. In addition, recommendations on how to achieve complete sustainability in the field of polymeric membranes are given.

1.8 References

- [1] C. Sagan, *Pale blue dot: a vision of the human future in space*, Random House, New York, 1994.
- [2] J. Brown, C.H. Scholtz, J.-L. Janeau, S. Grellier, P. Podwojewski, Dung beetles (Coleoptera: Scarabaeidae) can improve soil hydrological properties, *Appl. Soil Ecol.* 46 (2010) 9–16. doi.org/10.1016/j.apsoil.2010.05.010.
- [3] S. Iqbal, Energy Efficiency in Architecture Design in Mohenjo-Daro BT- Cities' Vocabularies: The Influences and Formations, in: N. Mohareb, A. Versaci, Y. Mahgoub, S. Maruthaveeran, F. Alberti (Eds.), Springer International Publishing, Cham, (2021) 203–208.
- [4] H.R. El-Ramady, S.M. El-Marsafawy, L.N. Lewis, Sustainable Agriculture and Climate Changes in Egypt BT- Sustainable Agriculture Reviews: Volume 12, in: E. Lichtfouse (Ed.), Springer Netherlands, Dordrecht, (2013) 41–95. doi:10.1007/978-94-007-5961-9_2.
- [5] S. Agrawala, Context and Early Origins of the Intergovernmental Panel on Climate Change, *Clim. Change.* 39 (1998) 605–620. doi:10.1023/A:1005315532386.
- [6] W.H. Organization, Health and environment in sustainable development: five years after the Earth Summit, World Health Organization, (No. WHO/EHG/97.8) 1997.
- [7] B.X. Lee, F. Kjaerulf, S. Turner, L. Cohen, P.D. Donnelly, R. Muggah, R. Davis, A. Realini, B. Kieselbach, L.S. MacGregor, Transforming our world: implementing the 2030 agenda through sustainable development goal indicators, *J. Public Health Policy.* 37 (2016) 13–31.
- [8] A. Gungor, S.M. Gupta, Issues in environmentally conscious manufacturing and product recovery: a survey, *Comput. Ind. Eng.* 36 (1999) 811–853.
- [9] M.A. Ilgin, S.M. Gupta, Environmentally conscious manufacturing and product recovery (ECMPRO): A review of the state of the art, *J. Environ. Manage.* 91 (2010) 563–591. doi.org/10.1016/j.jenvman.2009.09.037.
- [10] D. Matten, A. Crane, Corporate citizenship: Toward an extended theoretical conceptualization, *Acad. Manag. Rev.* 30 (2005) 166–179.
- [11] A. Mehedintu, M. Sterpu, G. Soava, Estimation and Forecasts for the Share of Renewable Energy Consumption in Final Energy Consumption by 2020 in the European Union, *Sustain.* 10 (2018). doi:10.3390/su10051515.
- [12] NS, Green energy for train, bus and station, (n.d.). <https://www.ns.nl/en/about-ns/sustainability/climate-neutral/green-energy-for-train-bus-and-station.html> (accessed April 21, 2021).
- [13] T. Pregger, J. Nitsch, T. Naegler, Long-term scenarios and strategies for the deployment of renewable energies in Germany, *Energy Policy.* 59 (2013) 350–360. doi.org/10.1016/j.enpol.2013.03.049.
- [14] S. Chu, Y. Cui, N. Liu, The path towards sustainable energy, *Nat. Mater.* 16 (2017) 16–22. doi:10.1038/nmat4834.

- [15] Volkswagen, Strategy TOGETHER 2025+, (n.d.). <https://www.volkswagenag.com/en/sustainability/environment/strategy-together-2025.html> (accessed April 21, 2021).
- [16] Toyota, Sustainability, (n.d.). <https://global.toyota/en/sustainability/> (accessed April 21, 2021).
- [17] J.S.L. Lam, K. Lai, Developing environmental sustainability by ANP-QFD approach: the case of shipping operations, *J. Clean. Prod.* 105 (2015) 275–284. doi.org/10.1016/j.jclepro.2014.09.070.
- [18] Maersk, Sustainability at A.P. Moller - Maersk, (n.d.). <https://www.maersk.com/about/sustainability/commitments-2020/decarbonising-logistics> (accessed April 21, 2021).
- [19] The Coca Cola Company, SUSTAINABLE BUSINESS, (n.d.). <https://www.coca-colacompany.com/sustainable-business> (accessed April 21, 2021).
- [20] McDonald's, Our Planet, (n.d.). <https://corporate.mcdonalds.com/corpmcd/our-purpose-and-impact/our-planet.html> (accessed April 21, 2021).
- [21] KFC, Planet Farm to fingers practices that are earth friendly, (n.d.). <https://global.kfc.com/our-social-impact#planet> (accessed April 21, 2021).
- [22] Amazon.com, Our Planet, (n.d.). <https://www.aboutamazon.com/planet> (accessed April 21, 2021).
- [23] P.T. Anastas, J.C. Warner, Principles of green chemistry, *Green Chem. Theory Pract.* (1998) 29–56.
- [24] P. Anastas, N. Eghbali, Green chemistry: principles and practice, *Chem. Soc. Rev.* 39 (2010) 301–312.
- [25] R.A. Sheldon, Green solvents for sustainable organic synthesis: state of the art, *Green Chem.* 7 (2005) 267–278. doi:10.1039/B418069K.
- [26] D.J.C. Constable, A.D. Curzons, V.L. Cunningham, Metrics to 'green' chemistry—which are the best?, *Green Chem.* 4 (2002) 521–527. doi:10.1039/B206169B.
- [27] Chapter 2 'Solvent free' Chemistry, in: *Altern. Solvents Green Chem.*, The Royal Society of Chemistry, (2009) 23–43. doi:10.1039/9781847559524-00023.
- [28] D.R. Lloyd, K.E. Kinzer, H.S. Tseng, Microporous membrane formation via thermally induced phase separation. I. Solid-liquid phase separation, *J. Memb. Sci.* 52 (1990) 239–261. doi.org/10.1016/S0376-7388(00)85130-3.
- [29] H. Matsuyama, H. Okafuji, T. Maki, M. Teramoto, N. Kubota, Preparation of polyethylene hollow fiber membrane via thermally induced phase separation, *J. Memb. Sci.* 223 (2003) 119–126. doi.org/10.1016/S0376-7388(03)00314-4.
- [30] M. Gu, J. Zhang, X. Wang, H. Tao, L. Ge, Formation of poly (vinylidene fluoride)(PVDF) membranes via thermally induced phase separation, *Desalination*. 192 (2006) 160–167.
- [31] S. Ramaswamy, A.R. Greenberg, W.B. Krantz, Fabrication of poly (ECTFE) membranes via thermally induced phase separation, *J. Memb. Sci.* 210 (2002) 175–180.

- [32] D. Li, W.B. Krantz, A.R. Greenberg, R.L. Sani, Membrane formation via thermally induced phase separation (TIPS): Model development and validation, *J. Memb. Sci.* 279 (2006) 50–60.
- [33] H. Matsuyama, T. Maki, M. Teramoto, K. Asano, Effect of polypropylene molecular weight on porous membrane formation by thermally induced phase separation, *J. Memb. Sci.* 204 (2002) 323–328.
- [34] J.T. Jung, J.F. Kim, H.H. Wang, E. di Nicolo, E. Drioli, Y.M. Lee, Understanding the non-solvent induced phase separation (NIPS) effect during the fabrication of microporous PVDF membranes via thermally induced phase separation (TIPS), *J. Memb. Sci.* 514 (2016) 250–263. doi:10.1016/j.memsci.2016.04.069.
- [35] H. Matsuyama, M. Yuasa, Y. Kitamura, M. Teramoto, D.R. Lloyd, Structure control of anisotropic and asymmetric polypropylene membrane prepared by thermally induced phase separation, *J. Memb. Sci.* 179 (2000) 91–100.
- [36] H. Matsuyama, S. Berghmans, D.R. Lloyd, Formation of anisotropic membranes via thermally induced phase separation, *Polymer (Guildf)*. 40 (1999) 2289–2301.
- [37] M. Mulder, Basic principles of membrane technology, Kluwer Academic Publishers, Dordrecht, The Netherlands, 1996.
- [38] H. Strathmann, P. Scheible, R.W. Baker, A rationale for the preparation of Loeb-Sourirajan-type cellulose acetate membranes, *J. Appl. Polym. Sci.* 15 (1971) 811–828. doi.org/10.1002/app.1971.070150404.
- [39] H. Strathmann, K. Kock, P. Amar, R.W. Baker, The formation mechanism of asymmetric membranes, *Desalination*. 16 (1975) 179–203. doi:10.1016/S0011-9164(00)82092-5.
- [40] H. Strathmann, K. Kock, The formation mechanism of phase inversion membranes, *Desalination*. 21 (1977) 241–255. doi:10.1016/S0011-9164(00)88244-2.
- [41] A.J. Reuvers, J.W.A. van den Berg, C.A. Smolders, Formation of membranes by means of immersion precipitation. Part I. A model to describe mass transfer during immersion precipitation, *J. Memb. Sci.* 34 (1987) 45–65. doi:10.1016/S0376-7388(00)80020-4.
- [42] R.W. Baker, Membrane technology and applications, Third Edit, John Wiley & Sons, Chichester, UK, 2012.
- [43] J.G. Wijmans, J.P.B. Baaij, C.A. Smolders, The mechanism of formation of microporous or skinned membranes produced by immersion precipitation, *J. Memb. Sci.* 14 (1983) 263–274.
- [44] I. Pinnau, B.D. Freeman, Formation and Modification of Polymeric Membranes: Overview, in: *Membr. Form. Modif.*, American Chemical Society, (1999) 1. doi:10.1021/bk-2000-0744.ch001.
- [45] S. Loeb, S. Sourirajan, Sea Water Demineralization by Means of an Osmotic Membrane, in: *Saline Water Conversion—II*, American Chemical Society, (1963) 117-132 SE–9. doi:10.1021/ba-1963-0038.ch009.
- [46] J.G. Wijmans, J. Kant, M.H. V Mulder, C.A. Smolders, Phase separation phenomena in solutions of polysulfone in mixtures of a solvent and a nonsolvent: relationship with membrane formation, *Polymer (Guildf)*. 26 (1985) 1539–1545. doi.org/10.1016/0032-3861(85)90090-4.

- [47] W.J. Koros, *Synthetic Polymeric Membranes: A Structural Perspective*, Second Edition By R. E. Kesting, John Wiley & Sons, (1985), 348, *AIChE J.* 33 (1987) 171–172. doi.org/10.1002/aic.690330129.
- [48] A.J. Reuvers, C.A. Smolders, Formation of membranes by means of immersion precipitation: Part II. the mechanism of formation of membranes prepared from the system cellulose acetate-acetone-water, *J. Memb. Sci.* 34 (1987) 67–86. doi.org/10.1016/S0376-7388(00)80021-6.
- [49] *Synthetic Membranes and Membrane Separation Processing*, *Sep. Purif. Methods.* 23 (1994) 71–73. doi:10.1080/03602549408001291.
- [50] L. Yilmaz, A.J. McHugh, Modeling of asymmetric membrane formation. II. The effects of surface boundary conditions, *J. Appl. Polym. Sci.* 35 (1988) 1967–1979. doi.org/10.1002/app.1988.070350722.
- [51] C.S. Tsay, A.J. Mchugh, Mass transfer modeling of asymmetric membrane formation by phase inversion, *J. Polym. Sci. Part B Polym. Phys.* 28 (1990) 1327–1365. doi.org/10.1002/polb.1990.090280810.
- [52] P. Radovanovic, S.W. Thiel, S.-T. Hwang, Formation of asymmetric polysulfone membranes by immersion precipitation. Part I. Modelling mass transport during gelation, *J. Memb. Sci.* 65 (1992) 213–229. doi.org/10.1016/0376-7388(92)87024-R.
- [53] G.R. Fernandes, J.C. Pinto, R. Nobrega, Modeling and simulation of the phase-inversion process during membrane preparation, *J. Appl. Polym. Sci.* 82 (2001) 3036–3051. doi.org/10.1002/app.2159.
- [54] J. Barzin, B. Sadatnia, Theoretical phase diagram calculation and membrane morphology evaluation for water/solvent/polyethersulfone systems, *Polymer (Guildf).* 48 (2007) 1620–1631. doi.org/10.1016/j.polymer.2007.01.049.
- [55] S.S. Shojaie, W.B. Krantz, A.R. Greenberg, Dense polymer film and membrane formation via the dry-cast process part I. Model development, *J. Memb. Sci.* 94 (1994) 255–280. doi.org/10.1016/0376-7388(93)E0228-C.
- [56] M. Sadrzadeh, S. Bhattacharjee, Rational design of phase inversion membranes by tailoring thermodynamics and kinetics of casting solution using polymer additives, *J. Memb. Sci.* 441 (2013) 31–44. doi:10.1016/j.memsci.2013.04.009.
- [57] G.R. Guillen, Y. Pan, M. Li, E.M. V Hoek, Preparation and characterization of membranes formed by nonsolvent induced phase separation: A review, *Ind. Eng. Chem. Res.* 50 (2011) 3798–3817. doi:10.1021/ie101928r.
- [58] G. Bakeri, A.F. Ismail, M. Shariaty-Niassar, T. Matsuura, Effect of polymer concentration on the structure and performance of polyetherimide hollow fiber membranes, *J. Memb. Sci.* 363 (2010) 103–111. doi:10.1016/j.memsci.2010.07.018.
- [59] A. Idris, Z. Man, A.S. Maulud, M.S. Khan, Effects of Phase Separation Behavior on Morphology and Performance of Polycarbonate Membranes., *Membranes (Basel).* 7 (2017). doi:10.3390/membranes7020021.
- [60] H. Matsuyama, M. Teramoto, R.Y.O. Nakatani, T. Maki, Membrane formation via phase

separation induced by penetration of nonsolvent from vapor phase. II. Membrane morphology, *J. Appl. Polym. Sci.* 74 (1999) 171–178.

[61] J.-H. Kim, K.-H. Lee, Effect of PEG additive on membrane formation by phase inversion, *J. Memb. Sci.* 138 (1998) 153–163. doi.org/10.1016/S0376-7388(97)00224-X.

[62] K.W. Lee, B.K. Seo, S.T. Nam, M.J. Han, Trade-off between thermodynamic enhancement and kinetic hindrance during phase inversion in the preparation of polysulfone membranes, *Desalination*. 159 (2003) 289–296. doi:10.1016/S0011-9164(03)90081-6.

[63] R.M. Boom, I.M. Wienk, T. van den Boomgaard, C.A. Smolders, Microstructures in phase inversion membranes. Part 2. The role of a polymeric additive, *J. Memb. Sci.* 73 (1992) 277–292. doi.org/10.1016/0376-7388(92)80135-7.

[64] H.H. Wang, J.T. Jung, J.F. Kim, S. Kim, E. Drioli, Y.M. Lee, A novel green solvent alternative for polymeric membrane preparation via nonsolvent-induced phase separation (NIPS), *J. Memb. Sci.* 574 (2019) 44–54. doi:10.1016/j.memsci.2018.12.051.

[65] J. Sherwood, T.J. Farmer, J.H. Clark, Catalyst: Possible Consequences of the *N*-Methyl Pyrrolidone REACH Restriction, *Chem.* 4 (2018) 2010–2012. doi:10.1016/j.chempr.2018.08.035.

[66] L. Bergkamp, N. Herbatschek, Regulating Chemical Substances under REACH: The Choice between Authorization and Restriction and the Case of Dipolar Aprotic Solvents, *Rev. Eur. Comp. Int. Environ. Law*. 23 (2014) 221–245. doi:10.1111/reel.12083.

[67] M. Razali, J.F. Kim, M. Attfield, P.M. Budd, E. Drioli, Y.M. Lee, G. Szekely, Sustainable wastewater treatment and recycling in membrane manufacturing, *Green Chem.* 17 (2015) 5196–5205. doi:10.1039/c5gc01937k.

[68] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restr. Off. J. Eur. Union. 99 (2018) 3.

[69] D. Kim, O.R. Salazar, S.P. Nunes, Membrane manufacture for peptide separation, *Green Chem.* 18 (2016) 5151–5159. doi:10.1039/C6GC01259K.

[70] Plato, *Plato's Republic: the Greek text / edited with notes and essays by B. Jowett and Lewis Campbell.*, Oxford: Clarendon Press, 1894.

[71] A. Figoli, T. Marino, S. Simone, E. Di Nicolò, X.-M. Li, T. He, S. Tornaghi, E. Drioli, Towards non-toxic solvents for membrane preparation: a review, *Green Chem.* 16 (2014) 4034. doi:10.1039/C4GC00613E.

[72] Y. Medina-Gonzalez, P. Aimar, J.F. Lahitte, J.C. Remigy, Towards green membranes: Preparation of cellulose acetate ultrafiltration membranes using methyl lactate as a biosolvent, *Int. J. Sustain. Eng.* 4 (2011) 75–83. doi:10.1080/19397038.2010.497230.

[73] T. Marino, F. Galiano, S. Simone, A. Figoli, DMSO EVOLTM as novel non-toxic solvent for polyethersulfone membrane preparation, *Environ. Sci. Pollut. Res.* 26 (2019) 14774–14785. doi:10.1007/s11356-018-3575-9.

- [74] M. Verheijen, M. Lienhard, Y. Schrooders, O. Clayton, R. Nudischer, S. Boerno, B. Timmermann, N. Selevsek, R. Schlapbach, H. Gmuender, S. Gotta, J. Geraedts, R. Herwig, J. Kleinjans, F. Caiment, DMSO induces drastic changes in human cellular processes and epigenetic landscape in vitro, *Sci. Rep.* 9 (2019) 4641. doi:10.1038/s41598-019-40660-0.
- [75] H. Matsuyama, H. Yano, T. Maki, M. Teramoto, K. Mishima, K. Matsuyama, Formation of porous flat membrane by phase separation with supercritical CO₂, *J. Memb. Sci.* 194 (2001) 157–163. doi.org/10.1016/S0376-7388(01)00436-7.
- [76] H. Matsuyama, A. Yamamoto, H. Yano, T. Maki, M. Teramoto, K. Mishima, K. Matsuyama, Effect of organic solvents on membrane formation by phase separation with supercritical CO₂, *J. Memb. Sci.* 204 (2002) 81–87. doi.org/10.1016/S0376-7388(02)00018-2.
- [77] T. Marino, F. Russo, A. Criscuoli, A. Figoli, TamiSolve® NxG as novel solvent for polymeric membrane preparation, *J. Memb. Sci.* 542 (2017) 418–429. doi.org/10.1016/j.memsci.2017.08.038.
- [78] N.T. Hassankiadeh, Z. Cui, J.H. Kim, D.W. Shin, S.Y. Lee, A. Sanguineti, V. Arcella, Y.M. Lee, E. Drioli, Microporous poly(vinylidene fluoride) hollow fiber membranes fabricated with PolarClean as water-soluble green diluent and additives, *J. Memb. Sci.* 479 (2015) 204–212. doi.org/10.1016/j.memsci.2015.01.031.
- [79] C. Ursino, F. Russo, R.M. Ferrari, M.P. De Santo, E. Di Nicolò, T. He, F. Galiano, A. Figoli, Polyethersulfone hollow fiber membranes prepared with PolarClean® as a more sustainable solvent, *J. Memb. Sci.* 608 (2020) 118216. doi.org/10.1016/j.memsci.2020.118216.
- [80] X. Dong, A. Al-Jumaily, I.C. Escobar, Investigation of the Use of a Bio-Derived Solvent for Non-Solvent-Induced Phase Separation (NIPS) Fabrication of Polysulfone Membranes, *Membr.* 8 (2018). doi:10.3390/membranes8020023.
- [81] W. Xie, A. Tiraferri, B. Liu, P. Tang, F. Wang, S. Chen, A. Figoli, L.-Y. Chu, First Exploration on a Poly(vinyl chloride) Ultrafiltration Membrane Prepared by Using the Sustainable Green Solvent PolarClean, *ACS Sustain. Chem. Eng.* 8 (2020) 91–101. doi:10.1021/acssuschemeng.9b04287.
- [82] J.T. Jung, J.F. Kim, H.H. Wang, E. di Nicolo, E. Drioli, Y.M. Lee, Understanding the non-solvent induced phase separation (NIPS) effect during the fabrication of microporous PVDF membranes via thermally induced phase separation (TIPS), *J. Memb. Sci.* 514 (2016) 250–263. doi.org/10.1016/j.memsci.2016.04.069.
- [83] Z. Cui, N.T. Hassankiadeh, S.Y. Lee, J.M. Lee, K.T. Woo, A. Sanguineti, V. Arcella, Y.M. Lee, E. Drioli, Poly(vinylidene fluoride) membrane preparation with an environmental diluent via thermally induced phase separation, *J. Memb. Sci.* 444 (2013) 223–236. doi.org/10.1016/j.memsci.2013.05.031.
- [84] J.T. Jung, H.H. Wang, J.F. Kim, J. Lee, J.S. Kim, E. Drioli, Y.M. Lee, Tailoring nonsolvent-thermally induced phase separation (N-TIPS) effect using triple spinneret to fabricate high performance PVDF hollow fiber membranes, *J. Memb. Sci.* 559 (2018) 117–126. doi.org/10.1016/j.memsci.2018.04.054.
- [85] T. Marino, E. Blasi, S. Tornaghi, E. Di Nicolò, A. Figoli, Polyethersulfone membranes prepared with Rhodiasolv® PolarClean as water soluble green solvent, *J. Memb. Sci.* 549 (2018)

192–204. doi.org/10.1016/j.memsci.2017.12.007.

[86] J.F. Kim, J.T. Jung, H.H. Wang, S.Y. Lee, T. Moore, A. Sanguineti, E. Drioli, Y.M. Lee, Microporous PVDF membranes via thermally induced phase separation (TIPS) and stretching methods, *J. Memb. Sci.* 509 (2016) 94–104. doi.org/10.1016/j.memsci.2016.02.050.

[87] M.-B. Coltelli, I. Della Maggiore, M. Bertoldo, F. Signori, S. Bronco, F. Ciardelli, Poly(lactic acid) properties as a consequence of poly(butylene adipate-co-terephthalate) blending and acetyl tributyl citrate plasticization, *J. Appl. Polym. Sci.* 110 (2008) 1250–1262. doi.org/10.1002/app.28512.

[88] T. Marino, F. Galiano, A. Molino, A. Figoli, New frontiers in sustainable membrane preparation: CyreneTM as green bioderived solvent, *J. Memb. Sci.* 580 (2019) 224–234. doi:10.1016/j.memsci.2019.03.034.

[89] C.A. Carner, C.F. Croft, S.D. Kolev, M.I.G.S. Almeida, Green solvents for the fabrication of polymer inclusion membranes (PIMs), *Sep. Purif. Technol.* 239 (2020) 116486. doi.org/10.1016/j.seppur.2019.116486.

[90] W. Xie, T. Li, A. Tiraferri, E. Drioli, A. Figoli, J.C. Crittenden, B. Liu, Toward the Next Generation of Sustainable Membranes from Green Chemistry Principles, *ACS Sustain. Chem. Eng.* 9 (2021) 50–75. doi:10.1021/acssuschemeng.0c07119.

[91] H.Y. Nguyen Thi, B.T. Nguyen, J.F. Kim, Sustainable Fabrication of Organic Solvent Nanofiltration Membranes, *Membr.* 11 (2021). doi:10.3390/membranes11010019.

[92] S.P. Nunes, P.Z. Culfaz-Emecen, G.Z. Ramon, T. Visser, G.H. Koops, W. Jin, M. Ulbricht, Thinking the future of membranes: Perspectives for advanced and new membrane materials and manufacturing processes, *J. Memb. Sci.* 598 (2020) 117761. doi:10.1016/j.memsci.2019.117761.

[93] X. Dong, D. Lu, T.A.L. Harris, I.C. Escobar, Polymers and Solvents Used in Membrane Fabrication: A Review Focusing on Sustainable Membrane Development, *Membr.* 11 (2021). doi:10.3390/membranes11050309.

[94] W.J. Lee, P.S. Goh, W.J. Lau, A.F. Ismail, N. Hilal, Green Approaches for Sustainable Development of Liquid Separation Membrane, *Membr.* 11 (2021). doi:10.3390/membranes11040235.

[95] V.S. Meka, M.K.G. Sing, M.R. Pichika, S.R. Nali, V.R.M. Kolapalli, P. Kesharwani, A comprehensive review on polyelectrolyte complexes, *Drug Discov. Today.* 22 (2017) 1697–1706. doi:10.1016/j.drudis.2017.06.008.

[96] J.E. Boothe, H.G. Flock, M.F. Hoover, Some Homo- and Copolymerization Studies of Dimethyldiallylammonium Chloride, *J. Macromol. Sci. Part A - Chem.* 4 (1970) 1419–1430. doi:10.1080/00222337008081734.

[97] A. Jensen, F. Basolo, H.M. Neumann, The Binding of Metal Complexes by Polystyrene Sulfonate Ion¹, *J. Am. Chem. Soc.* 81 (1959) 509–512. doi:10.1021/ja01512a001.

[98] D. V Pergushov, A.H.E. Müller, F.H. Schacher, Micellar interpolyelectrolyte complexes, *Chem. Soc. Rev.* 41 (2012) 6888–6901. doi:10.1039/C2CS35135H.

- [99] E.J. Vandenberg, W.R. Diveley, L.J. Filar, S.R. Patel, H.G. Barth, The synthesis and solution properties of some rigid-chain, water-soluble polymers: Poly[N,N-(sulfo-phenylene)phthalamides] and poly[N,N'-(sulfo-p-phenylene)pyromellitimide], *J. Polym. Sci. Part A Polym. Chem.* 27 (1989) 3745–3757. doi.org/10.1002/pola.1989.080271115.
- [100] A.S. Michaels, Polyelectrolyte Complexes, *Ind. Eng. Chem.* 57 (1965) 32–40. doi:10.1021/ie50670a007.
- [101] B. Philipp, H. Dautzenberg, K.J. Linow, J. Kötz, W. Dawydoff, Polyelectrolyte complexes - recent developments and open problems, *Prog. Polym. Sci.* 14 (1989) 91–172. doi:10.1016/0079-6700(89)90018-X.
- [102] A.F. Thünemann, M. Müller, H. Dautzenberg, J.-F. Joanny, H. Löwen, Polyelectrolyte Complexes, (2004) 113–171. doi:10.1007/b11350.
- [103] J. van der Gucht, E. Spruijt, M. Lemmers, M.A. Cohen Stuart, Polyelectrolyte complexes: Bulk phases and colloidal systems, *J. Colloid Interface Sci.* 361 (2011) 407–422. doi:10.1016/j.jcis.2011.05.080.
- [104] S. Manoj Lalwani, C.I. Eneh, J.L. Lutkenhaus, Emerging trends in the dynamics of polyelectrolyte complexes, *Phys. Chem. Chem. Phys.* 22 (2020) 24157–24177. doi:10.1039/D0CP03696J.
- [105] Q. Wang, J.B. Schlenoff, The polyelectrolyte complex/coacervate continuum, *Macromolecules.* 47 (2014) 3108–3116. doi:10.1021/ma500500q.
- [106] R.J. Stewart, C.S. Wang, H. Shao, Complex coacervates as a foundation for synthetic underwater adhesives., *Adv. Colloid Interface Sci.* 167 (2011) 85–93. doi:10.1016/j.cis.2010.10.009.
- [107] H. Cui, X. Zhuang, C. He, Y. Wei, X. Chen, High performance and reversible ionic polypeptide hydrogel based on charge-driven assembly for biomedical applications., *Acta Biomater.* 11 (2015) 183–190. doi:10.1016/j.actbio.2014.09.017.
- [108] A. Harada, K. Kataoka, Supramolecular assemblies of block copolymers in aqueous media as nanocontainers relevant to biological applications, *Prog. Polym. Sci.* 31 (2006) 949–982. doi.org/10.1016/j.progpolymsci.2006.09.004.
- [109] P. Schaaf, J.B. Schlenoff, Saloplastics: Processing compact polyelectrolyte complexes, *Adv. Mater.* 27 (2015) 2420–2432. doi:10.1002/adma.201500176.
- [110] A.D. Kulkarni, Y.H. Vanjari, K.H. Sancheti, H.M. Patel, V.S. Belgamwar, S.J. Surana, C. V. Pardeshi, Polyelectrolyte complexes: mechanisms, critical experimental aspects, and applications, *Artif. Cells, Nanomedicine Biotechnol.* 44 (2016) 1615–1625. doi:10.3109/21691401.2015.1129624.
- [111] G. Decher, Fuzzy Nanoassemblies: Toward Layered Polymeric Multicomposites, *Science* (80-.). 277 (1997) 1232–1237. doi:10.1126/science.277.5330.1232.
- [112] N. Joseph, P. Ahmadiannamini, R. Hoogenboom, I.F.J. Vankelecom, Layer-by-layer preparation of polyelectrolyte multilayer membranes for separation, *Polym. Chem.* 5 (2014) 1817–1831. doi:10.1039/c3py01262j.

- [113] M. Schönhoff, Self-assembled polyelectrolyte multilayers, *Curr. Opin. Colloid Interface Sci.* 8 (2003) 86–95. doi.org/10.1016/S1359-0294(03)00003-7.
- [114] K. Ariga, J.P. Hill, Q. Ji, Layer-by-layer assembly as a versatile bottom-up nanofabrication technique for exploratory research and realistic application, *Phys. Chem. Chem. Phys.* 9 (2007) 2319–2340. doi:10.1039/b700410a.
- [115] W. Yuan, G.-M. Weng, J. Lipton, C.M. Li, P.R. Van Tassel, A.D. Taylor, Weak polyelectrolyte-based multilayers via layer-by-layer assembly: Approaches, properties, and applications, *Adv. Colloid Interface Sci.* 282 (2020) 102200. doi.org/10.1016/j.cis.2020.102200.
- [116] L.E. Bromberg, Composite membranes based on polyelectrolyte complexes, *J. Memb. Sci.* 62 (1991) 131–143. doi.org/10.1016/0376-7388(91)80057-D.
- [117] S.Y. Nam, Y.M. Lee, Pervaporation and properties of chitosan-poly(acrylic acid) complex membranes, *J. Memb. Sci.* 135 (1997) 161–171. doi.org/10.1016/S0376-7388(97)00144-0.
- [118] S.Y. Nam, Y.M. Lee, Pervaporation separation of methanol/methyl t-butyl ether through chitosan composite membrane modified with surfactants, *J. Memb. Sci.* 157 (1999) 63–71.
- [119] R.Y.M. Huang, R. Pal, G.Y. Moon, Pervaporation dehydration of aqueous ethanol and isopropanol mixtures through alginate/chitosan two ply composite membranes supported by poly(vinylidene fluoride) porous membrane, *J. Memb. Sci.* 167 (2000) 275–289. doi.org/10.1016/S0376-7388(99)00293-8.
- [120] Y. Li, H. Jia, Q. Cheng, F. Pan, Z. Jiang, Sodium alginate-gelatin polyelectrolyte complex membranes with both high water vapor permeance and high permselectivity, *J. Memb. Sci.* 375 (2011) 304–312. doi:10.1016/j.memsci.2011.03.058.
- [121] X.S. Wang, Q.F. An, T. Liu, Q. Zhao, W.S. Hung, K.R. Lee, C.J. Gao, Novel polyelectrolyte complex membranes containing free sulfate groups with improved pervaporation dehydration of ethanol, *J. Memb. Sci.* 452 (2014) 73–81. doi:10.1016/j.memsci.2013.10.028.
- [122] X.-S. Wang, Q.-F. An, Q. Zhao, K.-R. Lee, J.-W. Qian, C.-J. Gao, Homogeneous polyelectrolyte complex membranes incorporated with strong ion-pairs with high pervaporation performance for dehydration of ethanol, *J. Memb. Sci.* 435 (2013) 71–79. doi.org/10.1016/j.memsci.2013.02.008.
- [123] K. Richau, H.-H. Schwarz, R. Apostel, D. Paul, Dehydration of organics by pervaporation with polyelectrolyte complex membranes: some considerations concerning the separation mechanism, *J. Memb. Sci.* 113 (1996) 31–41. doi.org/10.1016/0376-7388(95)00212-X.
- [124] H.-H. Schwarz, J. Lukáš, K. Richau, Surface and permeability properties of membranes from polyelectrolyte complexes and polyelectrolyte surfactant complexes, *J. Memb. Sci.* 218 (2003) 1–9. doi.org/10.1016/S0376-7388(02)00548-3.
- [125] Y. Ji, Q. An, Q. Zhao, H. Chen, J. Qian, C. Gao, Fabrication and performance of a new type of charged nanofiltration membrane based on polyelectrolyte complex, *J. Memb. Sci.* 357 (2010) 80–89. doi:10.1016/j.memsci.2010.04.003.
- [126] Q. Zhao, J.-W. Qian, Q.-F. An, Q. Yang, P. Zhang, A facile route for fabricating novel polyelectrolyte complex membrane with high pervaporation performance in isopropanol

dehydration, *J. Memb. Sci.* 320 (2008) 8–12. doi.org/10.1016/j.memsci.2008.04.040.

[127] Q. Zhao, Y.-L. Ji, J.-K. Wu, L.-L. Shao, Q.-F. An, C.-J. Gao, Polyelectrolyte complex nanofiltration membranes: performance modulation via casting solution pH, *RSC Adv.* 4 (2014) 52808–52814. doi:10.1039/C4RA09164G.

[128] Q. Zhao, Q. An, Z. Sun, J. Qian, K.-R. Lee, C. Gao, J.-Y. Lai, Studies on Structures and Ultrahigh Permeability of Novel Polyelectrolyte Complex Membranes, *J. Phys. Chem. B.* 114 (2010) 8100–8106. doi:10.1021/jp102707z.

[129] P. Bernabé, C. Peniche, W. Argüelles-Monal, Swelling behavior of chitosan/pectin polyelectrolyte complex membranes. Effect of thermal crosslinking, *Polym. Bull.* 55 (2005) 367–375. doi:10.1007/s00289-005-0439-5.

[130] M. Gierszewska, J. Ostrowska-Czubenko, E. Chrzanowska, pH-responsive chitosan/alginate polyelectrolyte complex membranes reinforced by tripolyphosphate, *Eur. Polym. J.* 101 (2018) 282–290. doi.org/10.1016/j.eurpolymj.2018.02.031.

“A scientist in his laboratory is not a mere technician: he is also a child confronting natural phenomena that impress him as though they were fairy tales.”

- Marie Curie

Chapter 2.

Sustainable Membrane Production Through Polyelectrolyte Complexation Induced Aqueous Phase Separation

This chapter is published as:

M.I. Baig, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.

Abstract

Non-solvent induced phase separation (NIPS) is the most common approach to produce polymeric membranes. Unfortunately, NIPS relies heavily on aprotic organic solvents like *N*-methylpyrrolidone. These solvents are unsustainable, repro-toxic for humans, and are therefore becoming increasingly restricted within the European Union. A new and sustainable method, Aqueous Phase Separation (APS), is reported that eliminates the use of organic solvents. A homogeneous solution of two polyelectrolytes, the strong polyanion poly(sodium 4-styrenesulfonate) (PSS) and the weak polycation poly(allylamine hydrochloride) (PAH), is prepared at high pH, where PAH is uncharged. Immersing a film of this solution in a low pH bath charges the PAH and results in a controlled precipitation, forming a porous water-insoluble polyelectrolyte complex, a membrane. Pore sizes can be tuned from micrometers to just a few nanometers, and even to dense films, simply by tuning the polyelectrolyte concentrations, molecular weights and by changing the salinity of the bath. This leads to excellent examples of microfiltration, ultrafiltration, and nanofiltration membranes. Polyelectrolyte complexation induced APS is a viable and sustainable approach to membrane production that provides excellent control over membrane properties and even allows new types of separations.

2.1 Introduction

Membrane technology is widely used in many applications, for example, in the production of drinking water, the treatment of wastewater, the separation of chemicals, and kidney dialysis [1]. Most of the commercially available membranes are made from polymers using a technique now known as non-solvent induced phase separation (NIPS). NIPS began with the work of Loeb and Sourirajan which successfully produced reverse osmosis membranes with an asymmetric structure i.e. a thin dense layer on top supported by a microporous substructure [2]. This was a big breakthrough in membrane technology because with NIPS it became possible to prepare defect-free asymmetric membranes in a continuous process with great control over the pore size and structure. The discovery of NIPS made membrane technology the important separation technique that it is today and NIPS is still the core technique to prepare membranes.

The NIPS process is a simple and elegant approach. First, a polymer is dissolved in a solvent that can mix with water in any quantity, typically a dipolar aprotic solvent, such as *N*-methylpyrrolidone (NMP) [3]. Then, the polymer solution is cast as a thin film and subsequently immersed in a so-called ‘non-solvent’ bath, that is nearly always water. As the solvent (NMP) and non-solvent (water) are miscible, they undergo an exchange such that the water diffuses into the polymer solution and the NMP diffuses out. The process continues until the polymer becomes insoluble and coagulates (phase separates) as a solid porous film [4]. The final membrane morphology can be tailored to a great extent by manipulating parameters such as the type of polymer, the choice of solvent and non-solvent, precipitation time, and composition of the coagulation bath [3,5–7]. Over the past few decades, abundant knowledge has been generated in the field of NIPS based membranes for almost all the membrane based separation applications.

However, the NIPS process comes with a clear downside. It relies heavily on dipolar aprotic solvents (like NMP) which are unsustainable, harmful to the environment, and repro-toxic for humans [8]. According to Razali *et al.*, the membrane industry produces around 50 billion

liters of wastewater each year that is contaminated with NMP and *N,N*-dimethylformamide (DMF) [9]. Due to the high costs of these solvents and environmental legislation, they have to be recycled, requiring an expensive closed cycle of process streams. Furthermore, the residual solvent must be fully removed from the membrane before it can be used for medical applications or the production of drinking water. Recently, the European Union has restricted the use of NMP throughout the EU [10]. As a result, NMP cannot be used in a concentration $\geq 0.3\%$ after May 2020, unless the manufacturers and consumers take appropriate risk management protocols. Therefore, there is a growing need to devise alternative strategies for the production of polymeric membranes in a way that is more environmentally friendly and sustainable.

Water is one of the most abundantly available solvents on earth. However, the traditional polymers that are used in NIPS are insoluble in water. Therefore, a different class of polymers called polyelectrolytes (PE) can be used because of their water solubility. PEs are charged polymers with either positive or negative charges on their repeating units, surrounded by small counter-ions. When two oppositely charged polyelectrolytes are mixed they can form a water-insoluble solid known as a polyelectrolyte complex (PEC) [11]. The driving force for polyelectrolyte complexation is an increase in entropy due to the release of bound counter-ions. Polyelectrolyte complexation can lead to well-defined structures for encapsulation and drug delivery [12], while polyelectrolyte complexes can also be processed into plastic-like materials, so-called saloplastics, with good material properties [13]. Furthermore, polyelectrolyte complexation can lead to well-defined thin films, polyelectrolyte multilayers, as demonstrated by Decher *et al.* by alternate deposition of polycations and polyanions [14]. This approach has gained widespread attention with thin multilayers being prepared in layer-by-layer fashion for several applications such as nanofiltration [15–17], reverse osmosis [18], and gas separation [19]. Polyelectrolyte multilayer based membranes have excellent separation properties, demonstrating that polyelectrolyte based materials hold great promise for separation, yet they still require a membrane support that was prepared by NIPS.

Recently, de Vos showed that it is possible to prepare completely porous membranes entirely in water by using pH-responsive polyelectrolytes [20]. For pH-responsive PEs, water can act as both, a solvent and a non-solvent depending on its solution pH. The weak polybase poly(4-vinylpyridine), is charged and soluble in water at low pH, but uncharged and insoluble in water at high pH. This phase transition can be controlled to form porous membranes with high water fluxes. De Vos also demonstrated a first example, where polyelectrolyte complexation leads to phase separation to produce a free-standing membranes. Sadman *et al.* recently reported a similar approach based on polyelectrolyte complexation achieved by using salt concentration as a trigger [21]. Membranes with pore sizes ranging from microns to several hundred nanometers were prepared by dissolving a PEC in KBr salt solution to form a complex coacervate. This coacervate was then cast as a film and allowed to precipitate in deionized water followed by immersion in a pH 13 bath. The resulting membranes were able to retain approximately 99% of polystyrene beads of 100 nm size with a permeability lying in the ultrafiltration regime. Although the process eliminates the use of organic solvents, the downsides were that it is time-consuming because it requires extensive solution preparation and includes a two-step coagulation process. Moreover, the complex coacervates require an equilibration time ranging from 1 day to 1 month [21]. But most importantly, limited control over pore size and geometry was reported.

To truly replace NIPS with a more environmentally friendly process, it is essential to design

Figure 2.1 Schematic illustration of Aqueous Phase Separation (APS) by polyelectrolyte complexation. A homogeneous solution of PSS and PAH is cast on a glass plate. The plate is then immersed in a low pH bath which charges the PAH. This leads to the formation of an insoluble polyelectrolyte complex (driven by counter-ion release) that precipitates as a porous film, a membrane. The kinetics of phase separation governs the final structure of the membrane that, allows the production of a wide variety of membranes.

an equally simple approach with the same degree of control over membrane structure. In this work, we employ polyelectrolyte complexation to prepare free-standing membranes using an Aqueous Phase Separation (APS) technique. In our approach, pH is used to trigger complexation in a simple one-step process that allows membranes with tunable pore sizes to be prepared. Poly(sodium 4-styrenesulfonate) (PSS) and poly(allylamine hydrochloride) (PAH) are chosen as the strong and weak PEs, respectively, and because of their high charge density, they form smooth, dense, and stable complexes when mixed together [22,23]. At a pH above its pK_a , i.e. approximately 9 [24], PAH is uncharged and the chains exist in their collapsed coiled state [25]. PSS, on the other hand, remains charged over the entire pH range and exists in an extended chain conformation due to the charge repulsion within the chains [26]. A homogeneous mixture of PSS and PAH is prepared at a high pH; here PAH is uncharged, which prevents it from complexing with PSS. (**Figure 2.1**). This homogeneous solution is then cast as a thin film and immersed in a coagulation bath at low pH, which induces complexation and phase inversion. An aqueous crosslinking step is employed during phase inversion to improve the mechanical stability of the membranes. We will demonstrate that our APS approach is similar to NIPS in that the membrane pore size can be controlled through a number of simple parameters including the molecular weights of the PEs, the concentrations of PEs in the casting solution, and the salt concentration in the coagulation bath. APS allows many different classes of membranes to be made including microfiltration membranes that allow the treatment of oily

wastewater, ultrafiltration membranes that can effectively concentrate protein solutions, and nanofiltration membranes that can remove small micropollutants from drinking water. The large degree of control over membrane structure makes our simple and scalable APS approach a viable alternative to the organic solvent based NIPS approach and has the potential to allow the production of sustainable polymeric membranes for all applications.

2.2 Experimental Section

2.2.1 Materials

Poly(sodium 4-styrenesulfonate) (PSS) sodium salt was purchased from Sigma-Aldrich (Netherlands) as 25 wt% (Mw ~200 kDa) and 30 wt% (Mw ~1000 kDa) aqueous solutions. Poly(allylamine hydrochloride) (PAH) in powder form (Mw ~17.5 kDa) was purchased from Sigma-Aldrich (Netherlands). PAH as 40 wt% aqueous solution (Mw ~150 kDa) was purchased from Nittobo Medical Co. Ltd., Japan. Sodium hydroxide (NaOH) pellets (>98%), Glutaraldehyde (GA) (50 wt% aqueous solution), Sodium Chloride (NaCl) (>99.5%), Hydrochloric acid (HCl) (ACS reagent, 37%), Glycerol solution (86–89%), n-hexadecane (99%), Oil red EGN (analytical standard), Sodium dodecyl sulfate (SDS) (>99%), Polyethylene glycol (PEG) with different molecular weights, Albumin from bovine serum (BSA) as lyophilized powder ($\geq 98\%$), Citric acid in powder form (99%), and MgSO_4 (>99.5%) were purchased from Sigma-Aldrich (Netherlands). The micropollutants Atenolol (>98%), Atrazine (analytical standard), Bezafibrate (>98%), Bisphenol-A (>99%), Bromothymol blue (>95%), Naproxen (analytical standard), Phenolphthalein (analytical standard), and Sulfamethoxazole (analytical standard) were all purchased from Sigma-Aldrich (Netherlands). Deionized water was obtained from a Milli-Q® Ultrapure water purification system. All the chemicals were used without any further purification.

2.2.2 Preparation of polyelectrolyte casting solutions

Two sets of casting solutions were prepared using different molecular weights (Mw) of PSS and PAH (**Table 2.1**). Low Mw PE solutions (PSS 200 kDa, PAH 17.5 kDa) were prepared under the following conditions. First, PAH powder (Mw 17.5 kDa) was dissolved in deionized water under continuous stirring to obtain a 30 wt% aqueous stock solution. The pH of this solution was approximately 3, measured using a handheld pH meter (pH 110, VWR). Since PAH is a weak polyelectrolyte with a pK_a value of approximately 9, it stays positively charged in aqueous solutions at pH 3 [24]. Therefore, when this PAH solution is mixed with the strong polyelectrolyte PSS it forms a PEC. This solid complex cannot be further processed for membrane fabrication. Hence, a homogeneous PE solution is required which can be processed and cast as a membrane. In order to prepare this homogeneous mixture, PAH needs to be deprotonated so that it does not complex with PSS. Therefore, 5 M NaOH solution was added to PAH such that the ratio of wt% NaOH to wt% PAH monomer was constant at 0.7. For example, to prepare a 15 g solution having 10 wt% PAH, 3.91 g deionized water and 6.09 g of 5 M NaOH solution was added to 5 g of PAH stock solution (30 wt%). Following this procedure, PAH solutions of various concentrations (10–20 wt%) were prepared (**Table 2.1**). On the other hand, PSS (30 wt%, Mw ~200 kDa) was diluted with deionized water to prepare a set of solutions having the same PE concentration as PAH i.e. (10–20 wt%). The two polyelectrolyte solutions of equal concentrations

Table 2.1 Two sets of PSS-PAH casting solutions used in this work.

PSS, Mw (kDa)	PAH, Mw (kDa)	Polyelectrolyte solution concentration (wt%)	Nomenclature
200	17.5	10	Low Mw PE
		12	
		14	
		16	
		18	
		20	
1000	150	8	High Mw PE
		10	
		12	

(e.g., 10 wt% PSS and 10 wt% PAH) were then mixed in a 1:2 monomer ratio (PSS:PAH). The monomer ratio was calculated based on the molecular weights of individual monomers. To obtain a 10 wt% PE casting solution, 7.87 g of 10 wt% PSS was added to 7.13 g of 10 wt% PAH. It is important to mention that casting solutions with other monomer ratios (PSS:PAH) such as 1:0.5, 1:1, 1:3, 1:4, and 1:5 were also prepared in this study. However, these ratios did not result in sufficiently stable membranes. The ratio 1:2 was chosen because the membranes prepared with this ratio exhibited the best mechanical stability. Furthermore, it has been shown by Riegler and Essler that PAH charges substantially overcompensate the PSS charges in PSS-PAH films which indicates that the two polyelectrolytes naturally form non-stoichiometric complexes [27].

Similarly, casting solutions of high Mw PEs were prepared under the following conditions. First, a set of PAH solutions having different concentrations (8–12 wt%) was prepared by diluting aqueous PAH (40 wt%, Mw 150 kDa) with deionized water followed by addition of 5 M NaOH. In this case, the NaOH:PAH wt% ratio was kept constant at 0.5. For instance, to prepare a 15 g solution having 10 wt% PAH, 6.90 g deionized water and 4.35 g of 5 M NaOH was added to 3.75 g PAH stock solution (40 wt%). Likewise, PSS (25 wt%, Mw 1000 kDa) was diluted with deionized water to obtain a series of solutions having the desired concentrations (8, 10, and 12 wt%). The two PE solutions (8 wt% PSS and 8 wt% PAH) were then mixed in PSS:PAH monomer ratio of 1:2 to obtain a homogeneous casting solution having 8 wt% PE. Following the same method, casting solutions containing 10 wt%, and 12 wt% PE were prepared by mixing the corresponding PE solutions in 1:2 (PSS:PAH) monomer ratio.

2.2.3 Viscosity Measurements

The viscosity of all the PE casting solutions was measured using a HAAKE™ Viscotester™ 550 Rotational Viscometer (ThermoFisher Scientific, USA). The PE casting solution (~15 mL) was poured into the spindle cylinder (SV-DIN) which was then mounted on the viscometer. The dynamic viscosity was measured as a function of shear rate (2.5 – 250 s⁻¹). Two samples of each PE solution were tested for their dynamic viscosity at 293 K and the average value at a shear rate of 2.57 s⁻¹ is reported here.

2.2.4 Membrane fabrication

Each solution prepared using low Mw PE was cast on a glass plate using a casting knife (gap = 0.4 mm). The glass plate was then immediately immersed into an acidic water bath at pH ~ 1 containing 0.05 wt% glutaraldehyde (GA) as a crosslinker. The pH of the coagulation bath was adjusted by adding HCl. At pH ~ 1 , the PAH becomes fully ionized and complexes with PSS. The resulting PEC precipitates as a white solid film. Casting solutions prepared using high Mw PEs were cast in a similar manner using a casting knife (gap = 0.6 mm). The coagulation bath was the same as mentioned above. In addition, these PE solutions were also cast and then immersed in coagulation baths (pH ~ 1 , 0.05 wt% GA) containing different concentrations of NaCl ranging from 1 M to 4 M.

The resulting films were removed from the coagulation bath and washed with deionized water to remove any excess salts and/or PE. The membrane samples for permeability tests were stored in deionized water. The membrane samples for SEM were kept in 20 wt% glycerol solution for 2 h followed by drying under ambient conditions in order to prevent the pores from collapsing.

2.2.5 Membrane characterization

The surface and cross-section morphology of the membranes was analyzed using scanning electron microscopy SEM (JSM-6010LA and JSM-7610F, field-emission electron microscope, JEOL, Japan). For cross-section images, the membrane samples were first immersed in liquid nitrogen before carefully fracturing them to preserve the pore structure. All the samples were vacuum dried at 30 °C for 24 h before coating them with a 5 nm thick layer of Platinum using a Quorum Q150T ES sputter coater (Quorum Technologies Ltd., United Kingdom). The membrane pore sizes were measured from the top surface SEM images using the ImageJ software. From the data, histograms were produced for each membrane. For the low Mw PE membranes, a total of 32 bins each with a size of 0.05 nm was used. For the high Mw PE membranes, a total of 40 bins each with a size of 0.5 nm was used. The zeta potential of the membranes was measured using a SurPASS electrokinetic analyzer (Anton Paar, Graz, Austria). Zeta potential values were calculated by measuring the streaming current versus pressure in a 5 mM KCl solution using equation 2.1:

$$\zeta = \frac{dI}{dP} \frac{\eta}{\varepsilon \varepsilon_0} \kappa_B R \quad (2.1)$$

Where ζ is the zeta potential (V), I is the streaming current (A), P is the pressure (Pa), η is the dynamic viscosity of electrolyte solution (Pa-s), ε is the dielectric constant of the electrolyte solution, ε_0 is the vacuum permittivity (F-m⁻¹), κ_B is the bulk electrolyte conductivity (S-m⁻¹), and R is the resistance (Ω) inside the streaming channel.

2.2.6 Pure water permeability and retention tests

Samples were prepared by cutting the membranes into circular disks of 25 mm diameter. Pure water permeability tests were conducted using a dead-end cell setup (Figure S2.1, supporting information). Deionized water from a Milli-Q[®] water purification system was used as the feed solution. The samples were first compacted at 4 bar of pressure until a constant flux was achieved.

The permeate mass was measured as a function of time using an electronic weight balance that was connected to a computer. Pure water permeability, P ($\text{L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$), was then calculated using equation 2.2:

$$P = \frac{Jw}{\Delta p} \quad (2.2)$$

Where Jw is the pure water flux ($\text{L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}$) calculated by measuring the change in permeate volume (L) per unit membrane area (0.38 cm^2), per unit time (h). Δp is the trans-membrane pressure difference (bar). Three samples from each membrane were tested and the average value with the standard deviation is reported.

Three different types of retention tests were conducted based on the pore sizes of the membranes. Retention tests for microfiltration membranes were conducted using an oil-in-water emulsion. The emulsion consisting of n-hexadecane ($100 \text{ mg}\cdot\text{L}^{-1}$) in sodium dodecyl sulfate ($463 \text{ mg}\cdot\text{L}^{-1}$) was prepared according to the procedure reported by Dickhout *et al.* [28]. The average oil droplet size was 3–4 μm . An oil-soluble dye, Oil red EGN, was added ($0.02 \text{ g}\cdot\text{L}^{-1}$) to the emulsion during stirring as a marker for oil droplets. Retention tests were conducted on three different membrane samples at 0.4 bar pressure on a dead-end cell. The cell containing the membrane and the vessel containing feed emulsion was stirred to maintain emulsion stability. Permeate samples were collected and analyzed using UV-vis spectrophotometer (Shimadzu UV-1800, Japan) at $\lambda_{\text{max}} = 521 \text{ nm}$ (maximum absorbance wavelength of Oil red EGN). Retention, R (%) was calculated using equation 2.3:

$$R = \left[1 - \frac{C_p}{C_f} \right] \times 100 \quad (2.3)$$

Where C_p and C_f is the concentration of species at the permeate and feed side, respectively. In a dead-end cell, the feed concentration is constantly changing above the membrane surface because of the constant enrichment. Therefore, C_f was taken as a mean of initial feed concentration and retentate concentration.

Ultrafiltration membranes were characterized by a protein retention test. BSA ($1 \text{ g}\cdot\text{L}^{-1}$) was dissolved in a 0.1 M citrate buffer at pH 5.5. The solution was then filtered through the membranes in a dead-end permeation cell. Permeate and retentate was analyzed by UV-vis spectrophotometer at $\lambda_{\text{max}} = 280 \text{ nm}$. The retention was calculated using equation 2.3.

Nanofiltration separation performance was characterized using a mixture of eight different micropollutants (Table S2.1, supporting information). The micropollutant mixture ($3 \text{ mg}\cdot\text{L}^{-1}$ of each compound) was prepared in deionized water and the pH of the solution was adjusted to 5.8 using 0.1 M NaOH. The mixture was filtered through the membranes in a dead-end cell for a minimum of 24 h to ensure a steady-state retention. Permeate samples were collected and analyzed using UltiMate 3000 UHPLC (ThermoFisher Scientific, USA). The separation was done on ACCLAIM RSLC C18 $2.2 \mu\text{m}$ column (ThermoScientific, USA). First, a calibration curve was made by analyzing different concentrations of feed solutions (Figure S2.7, supporting information). The retention was then calculated using equation 2.3. Three samples of each membrane were tested for micropollutant retention measurements to ensure reproducibility. MgSO_4 retention

tests were conducted using 5 mM MgSO₄ feed solution. The feed, retentate, and permeate conductivity was measured using a handheld conductivity meter (WTWTM CondTM 3210).

2.3 Results and Discussion

In this work, a new Aqueous Phase Separation (APS) approach is proposed that uses water as a solvent and non-solvent for the polyelectrolytes. The phase separation is driven by a pH switch. A homogeneous PE solution of PSS and PAH is prepared at high pH (pH $\sim$ 14) in a monomer ratio of 1:2 (PSS:PAH). PAH is uncharged at high pH and this prevents it from forming a complex with PSS. The homogeneous solution is then cast on a glass plate and immersed in a low pH (pH $\sim$ 1) coagulation bath. Here, the PAH becomes charged and complexes with PSS, inducing precipitation into a solid, porous polyelectrolyte complex film. Herein, the molecular weights of the PEs (low and high Mw pairs), the concentrations of PEs in the casting solution, and the salt concentration in the coagulation bath are all explored as parameters to tune membrane pore size and structure.

Porous structures can be formed without the need for crosslinking with reasonable mechanical properties. However, a strong benefit of the polyelectrolyte system used, i.e. PSS:PAH in a 1:2 ratio, is that there is an excess of primary amine groups which are free to be crosslinked to provide additional mechanical strength to the membrane. In this work, the excess of PAH is crosslinked using glutaraldehyde (GA) via a Schiff base reaction (*Figure S2.2, supporting information*) [29]. Importantly, this reaction can be performed in water and is therefore combined with the coagulation step, which in turn means that no additional processing steps are required during membrane fabrication. The GA concentration used is very low (0.05 wt%) and this concentration is considered to be safe under standard lab safety conditions [30]. With this crosslinking step, the mechanical properties improve and therefore, this approach is used throughout this work. The membranes prepared using low and high Mw PE solutions are discussed separately (see **Table 2.1** in the Experimental Section for casting solution compositions), with membranes from the low Mw PE solutions discussed first.

Figure 2.2a shows the cross-section and top surface scanning electron microscopy (SEM) images of the membranes prepared using low Mw PEs as a function of casting solution concentration. These images immediately demonstrate that porous polyelectrolyte films can be formed by APS. The structure contains large macrovoids, but also a membrane matrix with a sponge-like morphology with inter-connected pores of 1–5 μ m in size. The membranes have a relatively well-defined top layer of 1–2 μ m in thickness where the smallest pores are found. All these membranes have an asymmetric structure, the most desired structure for membranes, where a thin layer with smaller pores is responsible for the separation behavior, while a thicker more open layer provides the mechanical strength.

The precipitation mechanism of APS is simple and has much in common with the traditional NIPS process. As discussed earlier, in NIPS, the polymer solution is immersed in a non-solvent bath (typically water) to induce precipitation. The polymer is insoluble in water and therefore, precipitates as a membrane. The kinetics of phase inversion in NIPS largely govern the final morphology and pore structure of the resulting membrane [6]. Similarly, in APS (**Figure 2.1**), precipitation occurs when the high pH PE solution comes in contact with the low pH coagulation bath. At low pH, the weak polycation PAH becomes charged and complexes with the strong

Figure 2.2 a) Cross-section and top surface SEM images of membranes prepared using low Mw polyelectrolytes showing the effect of solution concentration (wt%) on membrane pore structure, b) pore size distribution, and c) pure water permeability and n-hexadecane retention. All the pore size distributions were calculated by generating histograms with 32 bins each with a size of $0.05\ \mu\text{m}$.

polyanion PSS. The resulting polyelectrolyte complex is insoluble in water and thus precipitates as a porous film. The precipitation of the PE film is a dynamic process which progresses at different locations throughout the film. As in NIPS, the top layer is where the precipitation begins, which leads to the smallest pores. This first layer of precipitated polymer then slows down the exchange of H^+ and OH^- between the bath and the film and thus the precipitation, leading to the formation of bigger pores deeper within the film.

It is known from the traditional NIPS process that higher polymer concentrations result in smaller pore sizes and lower overall porosity [7]. This is also seen in our work and is shown in the SEM images of **Figure 2.2a** where the pore size decreases with increasing PE concentration. The pore size distribution of these membranes was estimated by analyzing the top surface SEM images using ImageJ software with the results presented in **Figure 2.2b**. Membranes prepared using the 12 wt% PE solution have relatively larger pores in the top surface; the average pore size is $\sim 0.23\ \mu\text{m}$ and pore size distribution is broad and skewed toward larger pore sizes. The average membrane pore size decreases to $\sim 0.16\ \mu\text{m}$ when the PE concentration in the casting solution

Figure 2.3 Dynamic viscosity of the PSS-PAH polyelectrolyte casting solutions as a function of PE concentration in the casting solution. The dynamic viscosity was measured at 298 K at a shear rate of 2.57 s^{-1} . Square symbols (■) are for the solutions prepared using low molecular weight polyelectrolytes (PSS 200 kDa, PAH 17.5 kDa). Triangle symbols (▲) are for solutions prepared using high molecular weight polyelectrolytes (PSS 1000 kDa, PAH 150 kDa).

is increased to 16 wt%. At 20 wt% PE, the average pore size is $\sim 0.08 \text{ }\mu\text{m}$, with the pores easier to see in the high magnification FE-SEM image, *Figure S2.3, supporting information*. The pore size distribution becomes narrower with the increasing concentration of PE in the solution (**Figure 2.2b**).

The changes in membrane pore size as a function of PE concentration can be related to the kinetics of the phase separation. Here, the kinetics are greatly influenced by the viscosity of the casting solution as this, in part, determines the rate of solvent and non-solvent exchange. Therefore, the large differences in membrane microstructure as a function of PE concentration in the casting solution, observed in **Figure 2.2a**, can be related to the viscosity of the casting solutions. **Figure 2.3** shows the dynamic viscosity of the low and high Mw PE solutions as a function of PE concentration. For the low Mw PE solutions, the dynamic viscosity gradually increases with the PE concentration from 10 wt% to 16 wt%. After 16 wt%, there is a dramatic increase in the viscosity of the solution which most likely arises from an increase in chain entanglements. At 20 wt%, the dynamic viscosity is around 20 Pa·s. This is almost 8 times larger than the solution viscosity of 10 wt% PE (2.6 Pa·s). Such a large difference in the casting solution viscosity has a significant impact on the precipitation kinetics. As the solution viscosity increases, the onset of precipitation is delayed; so-called delayed demixing. For NIPS, Smolders *et al.* found that instantaneous demixing leads to a more porous structure while delayed demixing results in a denser structure [6]. The increase in PE solution viscosity results in membranes that have relatively denser structures (**Figure 2.2a**, 20 wt% PE). The results obtained for PEC membranes are in accordance with what is already known about the relationship of viscosity and kinetics of

phase inversion of traditional NIPS membranes [6].

The pure water permeability of a membrane is a vital parameter that provides insight into membrane porosity, its substructure, and its hydrophilicity. **Figure 2.2c** shows the pure water permeability of the membranes with respect to PE concentration in the casting solution. As discussed previously, at lower PE concentration the resulting membrane has an open structure which leads to high water permeability of $\sim 3200 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ for the membranes prepared with 10 wt% PE. Increases in the PE concentration result in membranes with smaller pores and hence lower water permeability values. The pure water permeability drops from $\sim 1600 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ at 12 wt% PE to $\sim 360 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ at 16 wt% PE. The trend continues up to 20 wt% PE, where the membranes have a water permeability of $\sim 150 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. The water permeability values obtained for these membranes are in the range of typical microfiltration and ultrafiltration membranes.

The removal of oil droplets from wastewater is an important application for microfiltration and ultrafiltration membranes [31]. Therefore, an oil-in-water emulsion was prepared and treated using the membranes discussed above. The oil (n-hexadecane) droplet retention increases from 74% to 100% when the PE concentration is increased from 10 wt% to 20 wt% (see **Figure 2.2c**), in line with smaller and thus more selective pores. The lower oil droplet retention of 74% at 10 wt% PE can also be attributed to the presence of significantly larger pores (see **Figure 2.2a** and **2b**). The closed structure of the membranes at higher concentrations of PE retains the oil droplets (3–4 μm) while allowing only the water to permeate through. Such retentions also demonstrates that these membranes can be produced without defects, as the presence of defects would substantially lower the retention.

In summary, for the membranes prepared using low Mw PEs, it is indeed possible to prepare highly permeable and selective PEC membranes using just a pH switch. Moreover, all these membranes have good mechanical properties and are easy to handle. Clearly, APS is a versatile process where a wide range of microfiltration membranes can be prepared simply by tuning the PE concentration in the casting solution for a given set of PE molecular weights. Another important parameter is the pH of the coagulation bath. As already shown, membrane formation greatly depends on the precipitation kinetics. Precipitation will occur faster if the pH of the coagulation bath is lowered further. This is because the driving force for complexation is the release of counter-ions. At lower pH, this driving force increases because of the larger difference in pH between the PE solution and the coagulation bath. This results in faster complexation. However, if the pH is reduced to 0.5, the precipitation occurs too fast and the resulting membranes become brittle. On the other hand, when the pH of the coagulation bath is increased above 1 (pH 1.5 and 2), the complexation slows down to a degree which prevents the formation of a stable membrane.

Moving on to the high Mw PE, **Figure 2.4a** shows the SEM microstructure of membranes as a function of PE concentration. Again, porous PEC films are formed. At the lower PE concentrations, 8 and 10 wt% PE, macrovoids are observed in the cross-section images which disappear at 12 wt% PE. All the membranes are asymmetric with well-defined top layers containing the smallest pores. The top surface FE-SEM images reveal that the pores become smaller as the PE concentration in the casting solution is increased from 8 to 10 to 12 wt%. Again, the pore size distribution was estimated from the top surface images using ImageJ software. Membranes prepared using 8 wt% PE solution had an average pore size of $\sim 4.5 \text{ nm}$ with a broad

Figure 2.4 a) Cross-section and top surface SEM images of membranes prepared using high Mw PE solutions showing the effect of concentration of PE in solution on membrane structure, b) pore size distribution, and c) pure water permeability and BSA retention. All the pore size distributions were calculated by generating histograms with 40 bins each with a size of 0.5 nm.

distribution skewed toward higher pore size (**Figure 2.4b**). As the PE concentration increases, the pore size distribution becomes narrower and the average pore size decreases to ~ 3.8 nm for 10 wt% PE and further to ~ 1.9 nm for 12 wt% PE. These pore sizes, identify these membranes as dense ultrafiltration membranes, with relevant applications in water treatment, but also, for example, concentration of proteins in food applications.

As discussed earlier, there is a direct relationship between the PE solution concentration and the solution viscosity. The dynamic viscosity of the 8 wt% PE solution was measured to be 9.8 Pa·s. This increased to 22 Pa·s for 10 wt% PE and further to 41.4 Pa·s for 12 wt% PE (see **Figure 2.3**). Such a drastic increase in the solution viscosity causes a delay in demixing during the phase inversion process, resulting in a sponge-like structure with a dense top layer. This can also be seen in the SEM cross-section images of the membranes in **Figure 2.4a** where the morphology gradually shifts from finger-like macrovoids (8 wt% and 10 wt%) to a sponge-like structure with a denser top layer (12 wt%). A higher PE concentration in the casting solution leads to the formation of a denser top layer which hinders the formation of finger-like macrovoids. *Figure S2.4 in supporting*

information shows the time-lapse photographs of the precipitation of these membranes.

Figure 2.4c shows the pure water permeability and BSA retention of the membranes prepared using the three PE concentrations. Pure water permeability decreases as a function of PE concentration. Membranes prepared with 8 wt% PE had the highest permeability among this set ($24.5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) with $\sim 85\%$ BSA retention. Some BSA molecules permeate through primarily because of the existence of pores $>10 \text{ nm}$ (see **Figure 2.4b**). Also, the average pore size of the membrane ($\sim 4.5 \text{ nm}$) is larger than the hydrodynamic radius of BSA (4.3 nm) [32]. At 10 wt% PE, the permeability drops to $17 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ with BSA retention increasing to $\sim 92\%$. Similarly, at 12 wt% PE, $\sim 98\%$ of BSA was retained by the membrane while having a pure water permeability of $12.5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. The average pore size of this membrane was estimated to be $\sim 1.9 \text{ nm}$ (**Figure 2.4b**). It can be concluded that the membranes separate BSA molecules based on the size-exclusion mechanism. The high retentions also demonstrate that little to no defects were present in these membranes.

Comparing the results for the membranes prepared with low and high Mw PE solutions, there is an association between membrane morphology and the molecular weights of the PEs. This can also be correlated to the dynamic viscosities of the casting solutions prepared using different Mw of PEs but having the same PE concentrations, **Figure 2.3**. For example at a fixed concentration of 12 wt% PE, the low Mw PE solution had a dynamic viscosity of $3.3 \text{ Pa}\cdot\text{s}$ while the high Mw PE solution had a dynamic viscosity of $41.4 \text{ Pa}\cdot\text{s}$. This substantial difference is due to the large difference in the molecular weights of the PEs used. Chain entanglement is greater for high Mw PEs and this causes the dynamic viscosity of the solution to increase. These results show that by simply tuning the Mw of the PEs, it is possible to fabricate membranes that can be used for microfiltration and also ultrafiltration applications.

To reduce the membrane pore size even further, NaCl was added to the coagulation bath. It is known from the literature that the addition of salt increases the mobility of PE chains in polyelectrolyte complexes [13,33]. **Figure 2.5a** shows the cross-section and top surface SEM images of the membranes prepared at different concentrations of NaCl in the coagulation bath. In all cases, asymmetric films are formed, but now the membranes have dense top layers with no observable pores. While the top surface is dense for all of these membranes, cross-section SEM images reveal that the substructure changes significantly as a function of NaCl concentration in the bath. Membranes prepared using 1 M NaCl showed relatively larger voids in the substructure. Also, the voids are located near the top surface. As the NaCl concentration in the coagulation bath increases, the voids in the substructure reduce in size, making the membranes more compact. For comparison, full cross-section SEM images of two different membranes are shown in *Figure S2.5 (supporting information)*. This shows that the membranes become denser with the addition of NaCl in the coagulation bath due to the increased PE chain mobility. Time-lapse photographs of the phase inversion at different NaCl concentration are shown in *Figure S2.6 (supporting information)*. It can be observed that the membranes coagulated in the 4 M NaCl bath become opaque faster. These results show that it is not only the PE concentration and the molecular weight that is important in controlling the membrane structure, but NaCl concentration in the coagulation bath is also a tuning parameter. The ability to control PE mobility during APS is also where this approach goes beyond the traditional NIPS process where such a tuning parameter simply does not exist.

Pure water permeability and retention tests were also performed on these membranes. The

a)

Figure 2.5 a) SEM images of cross-section and top surface, b) Pure water permeability and average micropollutant retention c) micropollutant retention of membrane prepared using 12 wt% PE (high Mw) having 4 M NaCl in the coagulation bath. The symbol inside the parenthesis represents the charge on the molecule at pH 5.8.

membranes were tested against a cocktail of micropollutant molecules (Table S2.1). These small organic molecules stem from medicine and pesticide usage and end up in the environment through wastewater streams. The micropollutant mixture has both charged and uncharged molecules. In addition, the molecular weight of these molecules is in the range of $216\text{--}624 \text{ g} \cdot \text{mol}^{-1}$. This mixture of micropollutants was selected because it covers positive, negative, and neutral molecules and also contains hydrophilic and hydrophobic molecules so that an assessment of charge and size-based separation can be made [16]. Good approaches to remove the micropollutants are urgently needed. These molecules are notoriously difficult to remove due to their small size and their widely varying molecular properties, and they are only removed with reverse osmosis (RO) membranes or dense nanofiltration class membranes.

Figure 2.5b shows that the water permeability decreases as the membranes become more compact due to the addition of NaCl in the coagulation bath. While the permeability decreases with increasing NaCl in the coagulation bath, the average micropollutant retention increases sharply from being extremely low at 0 M of salt up to a significant 80% at 4 M of salt, **Figure 2.5b**. A detailed graph showing the retentions of all the eight micropollutants as a function of NaCl

concentration in bath is presented in *Figure S2.8 (supporting information)*. Membranes prepared in 4 M NaCl had a permeability of $\sim 2 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ with the highest retentions for the eight micropollutants tested (**Figure 2.5c**). Retentions of 100% are reached for Bromothymol blue, again a clear indication that no defects are formed in the membranes prepared using this APS approach. Looking more closely at **Figure 2.5c**, one can see that both the charged and uncharged molecules were largely retained by the membranes. This demonstrates that the separation of organic molecules is most likely achieved due to the size-exclusion mechanism with some additional charge based effects [34]. Since the membranes themselves are positively charged as shown by the streaming potential in *Figure S2.9, supporting information*, the high retention (>98%) of the positively charged Atenolol molecule is expected.

As mentioned earlier, typically reverse osmosis and dense nanofiltration membranes are used to remove micropollutants from wastewater and drinking water. A downside of these membranes is that they also have very high ion retention, retaining not only the micropollutants but also all salts in solution. This leads to a complex and difficult to treat waste stream, containing high concentrations of micropollutants and salt. Moreover, the clean water often needs to be remineralized before use. When studying the salt retention of our membranes, we found low salt retentions, 0–10% for MgSO_4 . With our new APS approach to membrane production, we also use new materials (polyelectrolyte complexes) that, especially as dense membranes, might have different separation properties compared to that of common commercial membranes. Indeed the properties seen here (high micropollutant retention and low salt retentions) would be desirable for applications such as drinking water production, where removal of organic molecules without the removal of essential salts is wanted. Our new membrane materials might also come with new challenges as polyelectrolyte complexes are known to plasticize at high ionic strengths [13]. To study this, the membranes prepared in a 4 M NaCl coagulation bath were immersed in 1 M NaCl and 1 M KBr solutions for 5 days. We find that the water permeability of these membranes is not affected by such a long exposure to these highly saline solutions (see also *Figure S2.10* in the *supporting information*). The polyelectrolyte complex membranes are thus stable and resistant to plasticization by NaCl and KBr at least up to concentrations of 1 M.

2.4 Conclusion

In this work, we have proposed a new approach that allows sustainable membrane production with excellent control over membrane structure. The Aqueous Phase Separation (APS) technique employs a combination of strong and a weak polyelectrolyte (PE) that, on one hand, can form a polyelectrolyte complex at low pH conditions and on the other hand, can be mixed at high pH to form a homogeneous one-phase solution. The phase separation that occurs when immersing a film of the high pH homogeneous polyelectrolyte solution in a low pH bath leads to the formation of membranes with desired structures and excellent properties. Here asymmetric membranes with tunable pore sizes are prepared based on PSS and PAH as polyanion and polycation. To guarantee the stability of the membranes, an aqueous crosslinking step was applied during the phase inversion process. By utilizing tuning parameters such as polyelectrolyte concentration and molecular weight, the membrane pore size was tuned from micrometers down to just a few nanometers. This allowed the production of microfiltration membranes that are well-suited to remove dispersed oil from wastewater and ultrafiltration membranes that are able to concentrate dilute protein solutions. This large degree of control over pore size is very similar to that

found for the traditional solvent based NIPS method. A higher viscosity of the casting solution, obtained by using both, higher polyelectrolyte concentrations and higher PE molecular weights, led to slower phase inversion kinetics and thus denser top layers, just like in NIPS. But with APS we can also go beyond the standard tuning parameters associated with NIPS. Indeed, it was observed that adding NaCl to the coagulation bath results in even denser membranes due to the higher mobility of polyelectrolytes during complexation. The membranes prepared using 4 M NaCl in coagulation bath showed high retention (80%) towards small and notoriously difficult to retain micropollutants but extremely low salt retentions. Such membranes would be highly desirable for many applications where it is important to retain organics without retaining salts. More importantly, this demonstrates that APS is not just a sustainable alternative to NIPS, it also allows for the production of membranes with new separation properties that opens up the possibility of new separation processes. With the demonstrated control over pore size and membrane structure and allowing for the production of membranes with excellent separation properties, the completely water-based APS process is truly an alternative to the now dominant solvent-based NIPS approach. The similarities between APS and NIPS are a real advantage and current NIPS-based membrane production lines could also be used for large scale APS. Furthermore, the many types of polyelectrolytes that could potentially be used for this approach, in combination with the new tuning parameters associated with APS (salt concentration, pH), will allow optimization of this process towards many applications.

Acknowledgements

This project has received funding from the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation programme (ERC StG 714744 SAMBA). W.d.V and J.D.W acknowledge funding support from the "Vernieuwingsimpuls" programme through project number VIDI 723.015.003 (financed by the Netherlands Organization for Scientific Research, NWO).

2.5 Supporting Information – S2

Figure S2.1 Schematic illustration of the dead-end filtration setup. Micropollutant and oil-water emulsion retention tests were also conducted on a similar setup.

Figure S2.2 Reaction scheme showing the formation of Schiff-base imine from a reaction between an aldehyde and an amine.

Table S2.1 Micropollutant types and their molecular weights.

Micropollutant	Type	Molecular weight (g·mol ⁻¹)	Charge at pH 5.8
Atrazine	Herbicide	216	0
Bisphenol-A	Endocrine disruptor	228	0
Naproxen	Anti-inflammatory	230	-
Sulfamethoxazole	Anti-bacterial	263	0/-
Atenolol	β -blocker medicine	267	+
Phenolphthalein	pH indicator	318	0
Bezafibrate	Lipid lowering drug	361	-
Bromothymol Blue	pH indicator dye	624	0

Figure S2.3 Top surface FE-SEM image of the membrane prepared using 20 wt% PE (low Mw). Pore size in excess of 100 nm can be seen in the top layer.

Figure S2.4 Time-lapse photographs showing the membrane formation process as a function of polyelectrolyte solution concentration. The membranes were prepared using solution containing high Mw PSS and PAH at 12 wt% concentration. The time (t) in the photos indicate the time after immersion of the glass plate in the coagulation bath.

Figure S2.5 Cross-section SEM images of membranes prepared in different NaCl concentrations in the coagulation bath. The pore size in the substructure reduces significantly as the concentration of NaCl is increased.

Figure S2.6 Time-lapse photographs showing the membrane formation process as a function of NaCl concentration in the coagulation bath. The membranes were prepared using solution containing high Mw PSS and PAH at 12wt% concentration. The time (t) in the photos indicate the time after immersion of the plate in the coagulation bath.

Figure S2.7 Calibration curve for the micropollutant mix. The absorbance values were obtained by HPLC for all the micropollutants. A straight line was obtained for the graph between absorbance (y-axis) and known micropollutant solution concentration (x-axis). The absorbance values obtained from permeate samples (by HPLC) were then fitted into the linear equation of the calibration curves to get the permeate concentration.

Figure S2.8 Micropollutant retentions of the membranes prepared in different concentration of NaCl in the coagulation bath (pH ~1, 5 mM GA). The sign inside the parenthesis on x-axis indicates the charge on the micropollutant molecules. The micropollutants on x-axis are arranged based on their molecular weights (low to high).

Figure S2.9 Zeta potential of the membrane as a function of pH. The membrane remains positively charged at neutral pH mainly due to the excess of PAH in the complex.

Figure S2.10 Pure water permeability of membranes before and after immersion in 1 M NaCl and 1 M KBr solutions. The membranes prepared in 4 M NaCl coagulation bath were kept in the salt solutions for 5 days. After 5 days, the membranes were taken out, washed with deionized water, and tested for their pure water permeability at a pressure of 4 bar. Three membrane samples were tested and the average value is reported here with the standard deviation.

2.6 References

- [1] R.W. Baker, *Membrane technology and applications*, Third Edit, John Wiley & Sons, Chichester, UK, 2012.
- [2] S. Loeb, S. Sourirajan, Sea Water Demineralization by Means of an Osmotic Membrane, in: *Saline Water Conversion—II*, American Chemical Society, (1963) 117-132 SE-9. doi:10.1021/ba-1963-0038.ch009.
- [3] H. Strathmann, K. Kock, P. Amar, R.W. Baker, The formation mechanism of asymmetric membranes, *Desalination*. 16 (1975) 179–203. doi:10.1016/S0011-9164(00)82092-5.
- [4] A.J. Reuvers, J.W.A. van den Berg, C.A. Smolders, Formation of membranes by means of immersion precipitation. Part I. A model to describe mass transfer during immersion precipitation, *J. Memb. Sci.* 34 (1987) 45–65. doi:10.1016/S0376-7388(00)80020-4.
- [5] M. Ulbricht, Advanced functional polymer membranes, *Polymer (Guildf)*. 47 (2006) 2217–2262. doi:10.1016/j.polymer.2006.01.084. [6] C.A. Smolders, A.J. Reuvers, R.M. Boom, I.M. Wienk, Microstructures in phase-inversion membranes. Part 1. Formation of macrovoids, *J. Memb. Sci.* 73 (1992) 259–275. doi:10.1016/0376-7388(92)80134-6.
- [7] H. Strathmann, K. Kock, The formation mechanism of phase inversion membranes, *Desalination*. 21 (1977) 241–255. doi:10.1016/S0011-9164(00)88244-2.
- [8] D. Prat, J. Hayler, A. Wells, A survey of solvent selection guides, *Green Chem.* 16 (2014) 4546–4551. doi:10.1039/c4gc01149j.
- [9] M. Razali, J.F. Kim, M. Attfield, P.M. Budd, E. Drioli, Y.M. Lee, G. Szekely, Sustainable wastewater treatment and recycling in membrane manufacturing, *Green Chem.* 17 (2015) 5196–5205. doi:10.1039/c5gc01937k.
- [10] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restr. Off. J. Eur. Union. 99 (2018) 3.
- [11] A.S. Michaels, Polyelectrolyte Complexes, *Ind. Eng. Chem.* 57 (1965) 32–40. doi:10.1021/ie50670a007.
- [12] I.K. Voets, A. de Keizer, M.A. Cohen Stuart, Complex coacervate core micelles, *Adv. Colloid Interface Sci.* 147–148 (2009) 300–318. doi:10.1016/j.cis.2008.09.012.
- [13] P. Schaaf, J.B. Schlenoff, Saloplastics: Processing compact polyelectrolyte complexes, *Adv. Mater.* 27 (2015) 2420–2432. doi:10.1002/adma.201500176.
- [14] G. Decher, J. -D Hong, Buildup of ultrathin multilayer films by a self-assembly process, 1 consecutive adsorption of anionic and cationic bipolar amphiphiles on charged surfaces, *Makromol. Chemie. Macromol. Symp.* 46 (1991) 321–327. doi:10.1002/masy.19910460145.
- [15] Y. Ji, Q. An, Q. Zhao, H. Chen, J. Qian, C. Gao, Fabrication and performance of a new type of charged nanofiltration membrane based on polyelectrolyte complex, *J. Memb. Sci.* 357 (2010) 80–89. doi:10.1016/j.memsci.2010.04.003.

- [16] J. De Grooth, D.M. Reurink, J. Ploegmakers, W.M. De Vos, K. Nijmeijer, Charged micropollutant removal with hollow fiber nanofiltration membranes based on polycation/polyzwitterion/polyanion multilayers, *ACS Appl. Mater. Interfaces*. 6 (2014) 17009–17017. doi:10.1021/am504630a.
- [17] D.M. Reurink, J.P. Haven, I. Achterhuis, S. Lindhoud, (Erik) H.D.W. Roesink, W.M. de Vos, Annealing of Polyelectrolyte Multilayers for Control over Ion Permeation, *Adv. Mater. Interfaces*. 5 (2018). doi:10.1002/admi.201800651.
- [18] W. Jin, A. Toutianoush, B. Tieke, Use of polyelectrolyte layer-by-layer assemblies as nanofiltration and reverse osmosis membranes, *Langmuir*. 19 (2003) 2550–2553. doi:10.1021/la020926f.
- [19] J.-M. Leväsalmi, T.J. McCarthy, Poly(4-methyl-1-pentene)-Supported Polyelectrolyte Multilayer Films: Preparation and Gas Permeability, *Macromolecules*. 30 (1997) 1752–1757. doi:10.1021/ma961245s.
- [20] W.M. De Vos, (Universiteit Twente), Aqueous phase separation method, U.S. Patent Application no. 15/972,273, 2018.
- [21] K. Sadman, D.E. Delgado, Y. Won, Q. Wang, K.A. Gray, K.R. Shull, Versatile and High-Throughput Polyelectrolyte Complex Membranes via Phase Inversion, *ACS Appl. Mater. Interfaces*. 11 (2019) 16018–16026. doi:10.1021/acsami.9b02115.
- [22] L. Yang, C. Tang, M. Ahmad, A. Yaroshchuk, M.L. Bruening, High Selectivities among Monovalent Cations in Dialysis through Cation-Exchange Membranes Coated with Polyelectrolyte Multilayers, *ACS Appl. Mater. Interfaces*. 10 (2018) 44134–44143. doi:10.1021/acsami.8b16434.
- [23] Z. Feldötö, I. Varga, E. Blomberg, Influence of salt and rinsing protocol on the structure of PAH/PSS polyelectrolyte multilayers, *Langmuir*. 26 (2010) 17048–17057. doi:10.1021/la102351f.
- [24] L. Li, S. Srivastava, M. Andreev, A.B. Marciel, J.J. De Pablo, M. V. Tirrell, Phase Behavior and Salt Partitioning in Polyelectrolyte Complex Coacervates, *Macromolecules*. 51 (2018) 2988–2995. doi:10.1021/acs.macromol.8b00238.
- [25] X. Jiang, C. Ortiz, P.T. Hammond, Exploring the rules for selective deposition: Interactions of model polyamines on acid and oligoethylene oxide surfaces, *Langmuir*. 18 (2002) 1131–1143. doi:10.1021/la010832q.
- [26] Z. Adamczyk, B. Jachimska, T. Jasiński, P. Warszyński, M. Wasilewska, Structure of poly (sodium 4-styrenesulfonate) (PSS) in electrolyte solutions: Theoretical modeling and measurements, *Colloids Surfaces A Physicochem. Eng. Asp.* 343 (2009) 96–103. doi:10.1016/j.colsurfa.2009.01.035.
- [27] H. Riegler, F. Essler, Polyelectrolytes. 2: Intrinsic or extrinsic charge compensation? Quantitative charge analysis of PAH/PSS multilayers, *Langmuir*. 18 (2002) 6694–6698. doi:10.1021/la020108n.
- [28] J.M. Dickhout, J.M. Kleijn, R.G.H. Lammertink, W.M. De Vos, Adhesion of emulsified oil droplets to hydrophilic and hydrophobic surfaces-effect of surfactant charge, surfactant concentration and ionic strength, *Soft Matter*. 14 (2018) 5452–5460. doi:10.1039/C8SM00476E.

- [29] W. Tong, C. Gao, H. Möhwald, Manipulating the properties of polyelectrolyte microcapsules by glutaraldehyde crosslinking, *Chem. Mater.* 17 (2005) 4610–4616. doi:10.1021/cm0507516.
- [30] T. Takigawa, Y. Endo, Effects of glutaraldehyde exposure on human health, *J. Occup. Health.* 48 (2006) 75–87. doi:10.1539/joh.48.75.
- [31] M. Padaki, R. Surya Murali, M.S. Abdullah, N. Misdan, A. Moslehyani, M.A. Kassim, N. Hilal, A.F. Ismail, Membrane technology enhancement in oil-water separation. A review, *Desalination.* 357 (2015) 197–207. doi:10.1016/j.desal.2014.11.023.
- [32] B. Jachimska, M. Wasilewska, Z. Adamczyk, Characterization of globular protein solutions by dynamic light scattering, electrophoretic mobility, and viscosity measurements, *Langmuir.* 24 (2008) 6867–6872. doi:10.1021/la800548p.
- [33] H.W. Jomaa, J.B. Schlenoff, Salt-induced polyelectrolyte interdiffusion in multilayered films: A neutron reflectivity study, *Macromolecules.* 38 (2005) 8473–8480. doi:10.1021/ma050072g.
- [34] L.D. Nghiem, A.I. Schäfer, M. Elimelech, Pharmaceutical retention mechanisms by nanofiltration membranes, *Environ. Sci. Technol.* 39 (2005) 7698–7705. doi:10.1021/es0507665.

“The noblest pleasure is the joy of understanding.”

- Leonardo da Vinci

Chapter 3.

Tuning the Structure and Performance of Polyelectrolyte Complexation based Aqueous Phase Separation membranes

This chapter is published as:

M.I. Baig, J.D. Willott, W.M. de Vos, Tuning the structure and performance of polyelectrolyte complexation based aqueous phase separation membranes, *J. Memb. Sci.* 615 (2020) 118502. doi:10.1016/j.memsci.2020.118502.

Abstract

Aqueous Phase Separation (APS) provides a new and sustainable platform to fabricate polymeric membranes entirely in water. Still, little is known on how the casting solution and coagulation bath compositions can be used to tune membrane structure and performance. This work comprises a detailed investigation on tuning parameters to tailor the morphology, pore size distribution, and water permeability of polyelectrolyte complex membranes prepared from poly(sodium 4-styrenesulfonate) (PSS) and poly(allylamine hydrochloride) (PAH). To avoid complexation of PAH and PSS in the casting solution, an optimum amount of base (NaOH) must be added to deprotonate PAH. In addition, the monomer mixing ratio of PSS to PAH significantly influences membrane morphology by modulating the interactions between the two polyelectrolytes. Coagulation bath pH can be used to control the driving force for complexation. Decreasing bath pH facilitates the formation of denser membranes, allowing $\sim 97\%$ protein retentions, whereas increasing bath pH leads to more open membrane structures. Changing the concentration of crosslinker in the coagulation bath allows tuning of membrane pore size from ~ 2 nm to ~ 46 nm, while simultaneously influencing membrane mechanical properties. Overall, this work highlights several key parameters to tune APS membrane morphology, demonstrating the versatility of APS to prepare optimized sustainable membranes for specific applications.

3.1 Introduction

Polymeric membranes are pre-dominantly produced by the non-solvent induced phase separation (NIPS) approach. The first NIPS membranes were prepared by Loeb and Sourirajan for sea water desalination when they showed that a liquid polymer solution could be precipitated, in a controlled manner, to form solid asymmetric membranes with dense skin layers and porous support structures [1]. From that moment onward the NIPS process gained widespread attention from researchers and industry alike and since then polymeric membranes have become widely applied, for example in water treatment, kidney dialysis and gas separation applications [2].

Over the past 60 years, the NIPS approach has been very successful, as it is a simple and a scalable approach. First, a polymer is dissolved in an organic solvent, typically *N*-methyl pyrrolidone (NMP), to obtain a homogeneous solution. For flat sheet membranes, the polymer solution is cast on a substrate and subsequently immersed in a non-solvent bath, which is typically water. The polymer is insoluble in water and hence, after contact, it phase separates into a solid porous film, with the speed of phase separation determined by the rate of solvent–non-solvent exchange. Strathman *et al.* found that membrane structure, including the pore size, greatly depends on both the thermodynamic and kinetic aspects of the phase inversion [3,4]. Their results indicated that faster precipitation rates generally result in membranes with ‘finger-like’ macrovoids in the structure. On the other hand, slower precipitation rates generally result in membranes with ‘sponge-like’ morphologies. This degree of control over membrane structure and pore size, enabled the NIPS approach to be widely used for the fabrication of microfiltration and ultrafiltration membranes in addition to excellent supports for nanofiltration, reverse osmosis, and dense gas separation membranes [5].

For NIPS there are several key parameters that can be used to tune the membrane morphology, especially related to the composition of the casting solution and the coagulation bath. For casting

solutions, the polymer concentration is one such parameter that has been widely studied. Higher polymer concentrations in the casting solution result in membranes having denser structures with narrow pore size distribution [6–8]. This is because the solvent and non-solvent exchange is slowed down due to the higher viscosity of the polymer solution at higher concentrations, leading to membranes with thicker and denser top layers. Casting solutions can also be modified by the addition of additives such as polyethyleneglycol (PEG) and polyvinylpyrrolidone (PVP), which function as pore formers, hydrophilic agents, viscosity increasers or phase separation accelerators [9,10]. Generally, the additives leach out of the casting solution into the non-solvent bath during the phase inversion process affecting the rate of polymer precipitation [11]. The kinetics of membrane formation during NIPS can also be controlled by changing the coagulation bath conditions. A high miscibility of solvent and non-solvent generally results in porous membranes with macrovoids in the sub-structure, while a lower miscibility results in asymmetric membranes with dense top layers. Addition of solvent to the coagulation bath is known to slow down the precipitation rate by lowering the non-solvent activity, and generally this reduces macrovoid formation [12]. For in-depth descriptions of the NIPS process and the full suite of membrane tuning parameters in NIPS, we guide the readers to several review articles [12–15].

While NIPS is currently the foremost technique for producing commercial membranes, the most used solvent in this process, NMP, is reprotoxic for humans and therefore not a sustainable choice for membrane fabrication [16]. Indeed, NMP has recently become restricted within the European Union through REACH legislation [17]; leading to increased interest in developing more sustainable approaches to polymeric membrane fabrication. Polyelectrolytes, are one class of polymer that have long exhibited interesting properties as membrane materials [18]. Our research group has proposed several more sustainable approaches to membrane fabrication, where water is used both as the solvent and non-solvent to prepare polyelectrolytes-based membranes [19–21]. In one very promising version of this Aqueous Phase Separation (APS) approach, the phase inversion is achieved by polyelectrolyte complexation of a strong polyelectrolyte e.g. poly(sodium 4-styrenesulfonate, PSS) and a weak polyelectrolyte e.g. poly(allylamine hydrochloride) (PAH). For this system, a homogeneous solution of PSS and PAH is prepared at a high pH, where the weak polybase PAH is uncharged and can be mixed with PSS without forming a polyelectrolyte complex. The PSS-PAH solution is cast on a glass plate and immersed in a low pH coagulation bath. The pH gradient from a high pH in the solution to a low pH in the bath allows the PAH to acquire charge and to form a water-insoluble polyelectrolyte complex with PSS. Similar to NIPS, the casting solution in APS is transformed from a liquid phase to a solid phase via phase inversion. In **Chapter 2**, we have shown that the polyelectrolyte concentration and the molecular weight both play an important role in determining the resulting membrane morphology and separation performance, with excellent examples of microfiltration, ultrafiltration, and nanofiltration membranes produced.

Beyond our initial work on complexation-induced APS described in **Chapter 2**, there are many other important parameters that can be used to control membrane formation. In this work, we systematically investigate the effects of various parameters that give control over the final PSS-PAH membrane structure and separation performance. The concentration of sodium hydroxide in the individual PAH solution and the effect of monomer mixing ratio of PSS to PAH was investigated in detail to identify the optimum casting solution composition(s). Moreover, the coagulation bath conditions such as the pH and the amount of crosslinker were varied to better understand their effects on membrane pore sizes and morphology. The findings of this

work contribute towards a better understanding of how to optimize the performance of APS membranes towards specific applications.

3.2 Experimental

3.2.1 Materials

Poly(sodium 4-styrenesulfonate) (PSS, 25 wt% in water, $M_w \sim 1000$ kDa), sodium hydroxide (NaOH, >98% pellets), hydrochloric acid (HCl, ACS reagent, 37%), glutaraldehyde (GA, 50 wt% in water), citric acid (>99.5%, powder), glycerol solution (86–89% in water), and bovine serum albumin (BSA, >98wt% lyophilized powder) were purchased from Merck, The Netherlands. Poly(allylamine hydrochloride) (PAH, 40 wt% in water, $M_w \sim 150$ kDa) was purchased from Nittobo Medical Co., Ltd. Japan. Sodium hypochlorite solution, NaClO (6–14% active chlorine) was purchased from Merck Germany. Deionized water was obtained from a Milli-Q® water purification system (Merck-Millipore).

3.2.2 Preparation and casting of polyelectrolyte solutions

The stock solution of PSS (25 wt% in water) was diluted to 12 wt% using deionized water. Similarly, the stock solution of PAH (40 wt% in water) was diluted to 12 wt% using deionized water and a small volume of a 10 M NaOH solution. The effect of NaOH concentration was studied by varying the amount of NaOH in PAH solution such that the ratio R (C_{NaOH}/C_{PAH}) varied from 0.1 to 1.25 as shown in **Table 3.1**, where C_{NaOH} (wt%) and C_{PAH} (wt%) are the concentrations of NaOH and PAH in the initial PAH solution, respectively. Here, the order of addition of NaOH is vital; i.e. adding NaOH to PSS instead of PAH and then mixing the two solutions does not give homogeneous casting solutions. After preparation of the PSS solution and the pH-adjusted PAH solution, they were mixed to achieve final casting solutions (see **Table 3.1**) with monomer ratios of PSS:PAH of 2:1, 1:1, 1:2, 1:3 and 1:4. The homogeneity of the final casting solutions was studied via turbidity measurements using a Turb® 430 IR – WTW™ portable turbidity meter.

The homogeneous polyelectrolyte casting solutions were cast as thin films on glass plates using a casting bar with a gap height of 0.6 mm. The cast films were immediately immersed in a coagulation bath composed of deionized water at varying pH values (0.25, 0.5, 0.75, 1, 1.25, and 1.5, adjusted using HCl) and different GA concentrations (0 wt%, 0.05 wt%, 0.1 wt%, 0.2 wt%, and 0.5 wt%). After coagulation, the precipitated films (membranes) were removed from the bath and stored in deionized water until further use.

3.2.3 Viscosity measurements

The dynamic viscosity of the polyelectrolyte casting solutions was measured on HAAKE™ Viscotester™ 550 Rotational Viscometer (ThermoFisher Scientific, USA). Approximately 15 mL of the polyelectrolyte solution was poured into the standard spindle cylinder (SV-DIN). The cylinder was mounted on the viscometer and the dynamic viscosity of the solutions was measured as a function of shear rate ($2.5\text{--}250\text{ s}^{-1}$). Two samples of each polyelectrolyte solution were

Table 3.1 Final compositions of polyelectrolyte casting solutions used in this work.

$R (C_{\text{NaOH}}/C_{\text{PAH}})^{(a)}$	PSS:PAH monomer molar mixing ratio	Amount of PSS (wt%)	Amount of PAH (wt%)	Amount of NaOH (wt%) ^(b)	Amount of water (wt%)
0.5	2:1	9.8	2.2	1.1	86.9
0.5	1:1	8.3	3.7	1.9	86.1
0.1				0.6	87.4
0.25				1.4	86.6
0.5	1:2	6.3	5.7	2.9	85.1
0.75				4.3	83.7
1				5.7	82.3
1.25				7.1	80.9
0.5	1:3	5.1	6.9	3.5	84.6
0.5	1:4	4.3	7.7	3.9	84.1

^(a)for initial PAH solution ^(b)in terms of 100% NaOH

measured and the average value extrapolated to zero shear conditions is reported here along with the standard deviation. All the measurements were performed at 20 °C.

3.2.4 Characterization of the membranes

For scanning electron microscopy (SEM) imaging, membrane samples were first placed in 20 wt% glycerol solution for 2 h followed by drying in air. Afterwards for cross-section SEM imaging, the dried samples were first immersed in liquid N₂ before being carefully fractured. The samples were then dried further in a vacuum oven at 30 °C for 24 h before sputter coating them with a 5 nm layer of Pt/Pd (80%/20%) using Quorum Q150T ES sputter coater (Quorum Technologies Ltd., UK). Electron microscopy images were then taken by SEM (JSM 6010LA, JEOL, Japan). Fourier-transform infrared spectroscopy (FTIR) was performed on Spectrum TwoTM (Perkin Elmer, USA) in the wavenumber range 4000 cm⁻¹ to 600 cm⁻¹.

3.2.5 Pure water permeability and retention tests

The membrane was cut into a circular disk of 25 mm diameter and placed in a dead-end Amicon[®] cell. Deionized water from Milli-Q[®] water purification system was used as the feed. The cell was pressurized using N₂ gas. A pressure of 4 bar was applied at the beginning of the measurement until a steady state permeate flux was obtained. Permeate mass was measured as a function of time using a weight balance connected to a computer. Pure water permeability was calculated using equation 3.1:

$$P = \frac{Jw}{\Delta p} \quad (3.1)$$

Where P is the pure water permeability L·m⁻²·h⁻¹·bar⁻¹, Jw is the water flux (L·m⁻²·h⁻¹), Δp is the

pressure difference between the feed and permeate side (bar).

The separation performance of the membranes was studied using a BSA solution (1 g·L⁻¹, Mw ~66 kg·mol⁻¹, average hydrodynamic diameter of 8.6 nm [22]) prepared in a 0.1 M citrate buffer at pH 5.5. The solution was fed to a dead-end Amicon[®] cell equipped with a magnetic stirrer positioned above the membrane sample. Retention tests were performed at 3 bar of transmembrane pressure. Permeate and retentate samples were collected and analyzed using UV-vis spectrophotometry (Shimadzu UV-1800, Japan) at $\lambda_{max} = 280$ nm (i.e. the maximum absorbance wavelength of BSA). Retention (R in %) was calculated using equation 3.2:

$$R = \left[1 - \frac{C_p}{C_f} \right] \times 100 \quad (3.2)$$

Where C_p is the concentration of BSA in the permeate and C_f is taken as the average of feed and retentate concentrations because in the dead-end configuration, the concentration of feed solution above the membrane surface is not constant.

3.3 Results and Discussion

Various parameters to influence the formation of PSS-PAH membranes by APS were studied and are discussed in four separate sections. The first two sections focus on the preparation and processing of polyelectrolyte casting solutions, including on the added amount of NaOH and on polyelectrolyte ratios. In contrast, the last two sections describe how coagulation bath conditions such as pH and crosslinker concentration can be used to tune membrane morphology, pore size, and separation performance.

3.3.1 Effect of added NaOH on the polyelectrolyte casting solutions

Two important choices in this pH-triggered APS approach, based on the polyelectrolyte pair PSS-PAH, are the pH of the casting solution and the total polymer concentration. In **Chapter 2** we reported that the optimum polyelectrolyte solution concentration to give stable PSS-PAH ultrafiltration type membranes was 12 wt%, and this was used as the starting point to further showcase the versatility of pH-triggered, polyelectrolyte complexation APS. PSS is a strong polyanion that remains in a charged state over the entire pH range (pH 1–14). On the other hand, PAH is a weak polycation with a pK_a value of ~9 [23], which means that when $pH \gg pK_a$, PAH will be uncharged. When a PSS solution is mixed with a PAH solution that has not been adjusted to a high pH with NaOH, a polyelectrolyte complex is formed. Here, complexation occurs because the pH of the unadjusted PAH solution is approximately 3, i.e. $pH < pK_a$. At pH 3, PAH is protonated and thus forms a polyelectrolyte complex with PSS upon mixing.

In order to obtain a homogeneous casting solution of PSS and PAH, it is necessary to make the weak polyelectrolyte PAH uncharged so that it does not complex with PSS. This was achieved by adding NaOH to the PAH solution. The addition of base deprotonates PAH making it uncharged (i.e. $pH \gg pK_a$). A series of PAH solutions (all at 12 wt% PAH) were prepared by adding different amounts of NaOH (C_{NaOH}) in order to find the optimum conditions to obtain homogeneous solutions when mixed with PSS (see *Figure S3.1* for photographs of the PAH only solutions).

Figure 3.1 Polyelectrolyte casting solutions of PSS and PAH (monomer mixing ratio of 1:2) prepared according to **Table 3.1**. Here $R = (C_{\text{NaOH}}/C_{\text{PAH}})$, where C_{NaOH} is the concentration of NaOH in PAH solution (wt%) and C_{PAH} is the concentration of PAH (wt%). All the solutions contain a total of 12 wt% polyelectrolyte.

The ratio $R = C_{\text{NaOH}}/C_{\text{PAH}}$ was varied according to **Table 3.1**. This ratio is a vital descriptor for the system as the NaOH concentration controls the deprotonation and thus charge of the weak polybase PAH, moreover for these viscous solutions at high hydroxide ion contents the pH cannot be accurately determined. All the prepared PAH solutions were clear and homogeneous except for $R = 1.25$ where the solution separates into a polymer rich and polymer lean phase (see *Figure S3.1, supporting information*). This is because PAH loses its charge at high pH and adopts a coiled conformation. The transition of PAH chains from extended conformation at $\text{pH} \ll \text{p}K_a$ [24], to coiled conformation at $\text{pH} \gg \text{p}K_a$ increases the hydrophobic interactions by reducing the repulsion between the PAH chains. At sufficiently large amounts of NaOH in the PAH solution such as $R = 1.25$, the high ionic strength of the solution may mean that PAH behaves more like a neutral polymer and thus is more prone to phase separation. This phase behavior can also be correlated to the polyelectrolyte “salting-out” effect [25].

The PAH solutions were mixed with PSS solutions in a monomer ratio of 1:2 (PSS:PAH) according to **Table 3.1** (see **Figure 3.1** for photographs of the mixed solutions). The choice of this specific monomer ratio will become apparent in the next section. **Figure 3.1** shows that a white complex was formed for solutions where $R = 0.1$ and 0.25 , indicating that the amount of NaOH added was insufficient to prevent polyelectrolyte complexation. A homogeneous solution was, however, obtained when R was 0.5 . At $R = 0.75$, the solution was slightly cloudy. Further increases of R to 1.0 and 1.25 resulted in completely cloudy solutions most likely due to the aggregation of the polyelectrolyte chains due to salting out effects [26]. In addition, the latter two solutions were more gel-like than liquid-like. The behavior from $R = 0.75$ onwards was confirmed by turbidity measurements where the solution turbidity increased dramatically above $R = 0.5$ (see *Figure S3.2, supporting information*). The homogeneous polyelectrolyte solution with $R = 0.5$ was chosen for further experimentation.

Figure 3.2 Effect of monomer mixing ratio (PSS:PAH) on the zero shear rate dynamic viscosity of the polyelectrolyte solutions. All the solutions have a concentration of 12 wt% polyelectrolyte.

3.3.2 Effect of PSS:PAH monomer mixing ratio

With R fixed at 0.5, a set of polyelectrolyte casting solutions were prepared at different monomer mixing ratios of PSS:PAH i.e. 4:1, 2:1, 1:1, 1:2, 1:3, and 1:4 (see Figure S3.3 in supporting information for the photographs of the casting solutions). The casting solution with monomer ratio 4:1 was unstable, with two distinct phases observed a few minutes after stirring making it unsuitable for casting. Casting solutions at the other monomer mixing ratios were all homogeneous. **Figure 3.2** shows the dynamic viscosities of these casting solutions.

Viscosity increases when the monomer ratio is changed from 2:1 to 1:1 and then it increases slightly further for the 1:2 ratio. Increasing the amount of PAH further by changing the monomer mixing ratio to 1:3 and then to 1:4 results in a decrease in the solution viscosity. A maximum in dynamic viscosity (~ 48 Pa·s) is thus observed for the 1:2 PSS/PAH ratio. In comparison, the individual PSS solution at 12 wt% had a dynamic viscosity of 1 Pa·s, while the 12 wt% PAH solution ($R = 0.5$) had an even lower viscosity of 0.7 Pa·s. Increasing the monomer ratio of PSS:PAH evidently increases the mutual interaction between the two polyelectrolytes as the dynamic viscosity of the solutions increases up to a monomer ratio of 1:2. The maximum in the dynamic viscosity is likely due to a combination of electrostatic and hydrophobic interactions as reported in the previous studies [27,28]. There is always a balance between these two interactions, and in this case the interactions have a maximum at a monomer mixing ratio of 1:2. Literature shows that for PSS/PAH polyelectrolyte multilayers, PAH charges overcompensate PSS charges resulting in a strong deviation from 1:1 stoichiometry [29], in line with our observations. The shear stress vs shear rate graph in Figure S3.4 in supporting information shows the shear thinning effect of casting

Figure 3.3 Polyelectrolyte complex films (membranes) prepared using 12 wt% casting solution with different monomer mixing ratios of PSS:PAH. Membranes were prepared in a coagulation bath at pH 1 with 0.05 wt% GA. Membranes are stored in deionized water in these photographs.

solutions prepared at different PSS to PAH monomer ratios. Shear stress increases dramatically with the shear rate for the solution of 1:2 monomer mixing ratio, indicating stronger interactions between PSS and PAH chains. On the other hand, the increase in shear stress with shear rate is less abrupt for the 2:1 mixing ratio solution suggesting much weaker interactions between PSS and PAH. When the PSS:PAH ratio increases beyond 1:2, the dynamic viscosity decreases to 40 Pa·s for the 1:3 ratio and 25 Pa·s for the 1:4 ratio. This behavior is most likely due to decreased PSS-PAH interactions at these ratios.

The PSS-PAH casting solutions with monomer ratios of 2:1 through to 1:4 were cast on glass plates as 0.6 mm thin films and immediately immersed in coagulation baths at pH 1 with 0.05 wt% GA. GA is a commonly used chemical for the crosslinking of PAH due to its ability to react with the amines in aqueous conditions [30,31]. The aldehyde groups of GA react with the amine groups of PAH to form imine ($-C=N-$) bonds as shown in the reaction scheme in *Figure S3.5, supporting information*. The concentration of GA in the coagulation bath and the bath pH are very important parameters that have a significant influence on membrane structure and performance and these factors will be discussed in the later sections.

Figure 3.3 shows photographs of the polyelectrolyte complex membranes prepared with casting solutions of different monomer mixing ratios. At the monomer mixing ratio of 2:1, the resulting film resembled a membrane, but did not have the mechanical strength to be further processed. At 1:1 monomer mixing ratio, the resulting films were relatively brittle and could not be handled further for pure water permeability measurements without rupturing. While at 1:2 mixing ratio, the resulting films were mechanically stable. Increasing the mixing ratio to 1:3 and to 1:4 resulted in films that were relatively soft with uneven top surfaces.

Figure 3.4 shows the cross-section and top surface SEM images of the films shown in **Figure 3.3**. Films prepared using a monomer mixing ratio of 2:1 were too weak to be processed for SEM analysis. The cross-section SEM image shown in **Figure 3.4a** reveals that there are no macrovoids in the substructure of the 1:1 PSS-PAH film. At 1:2 monomer mixing ratio (**Figure 3.4b**), the resulting films showed small voids in the substructure. For the monomer mixing ratios of 1:3 and 1:4, the resulting films have finger-like macrovoids that exist throughout the thickness of the film (see *Figure S3.6, supporting information*). Another observation from the SEM images of *Figure S3.6* is that the 1:3 and 1:4 membranes are much thicker than 1:1 and 1:2. This could most likely be due to the excess of positively charged PAH in the polyelectrolyte complex membrane which can

Figure 3.4 Scanning electron microscopy (SEM) images of the films (membranes) prepared using polyelectrolyte solutions with varying monomer ratios (PSS:PAH): a) 1:1, b) 1:2, c) 1:3, and d) 1:4. The top panel shows cross-section images while the bottom panel shows top surface SEM images.

lead to swelling in the structure. In addition, the top surface of 1:3 and 1:4 membranes is uneven and shows signs of inhomogeneity (**Figure 3.4c** and **d**), which can also be seen in the photographs shown in **Figure 3.3** where the films have an inhomogeneous appearance.

The existence or absence of finger-like macrovoids is usually correlated with the viscosity of the casting solution, which affects the phase inversion kinetics, as explained in detail by Smolders *et al.* [32]. The finger-like macrovoid morphology is usually obtained when the casting solution viscosity is low, favoring instantaneous demixing (quick phase inversion). However, in our case, the differences in the viscosity of casting solutions at 1:1, 1:2, and 1:3 monomer mixing ratios is small, but still the morphology of the resultant membranes is significantly different. This suggests that the aggregation behavior of the polyelectrolyte complex varies with different monomer ratios. We expect that as the monomer mixing ratio is increased from 1:1 to 1:4, the polyelectrolyte chains tend to form more loosely packed structures. A possible reason for such behavior could be that at larger excess amounts of PAH, such as for the 1:2 and especially the 1:3 and 1:4 mixing ratios, there is also an excess amount of charge present in the polyelectrolyte complex. In water such excess charge would result in swelling and thus a much more open material. Moreover, the excess charge could hinder phase separation, only allowing the formation of a much more swollen and open material. Indeed, the SEM images shown in **Figure 3.4** and **Figure S3.6** (supporting information) demonstrate that the 1:1 and 1:2 mixing ratio membranes have denser structures than 1:3 and 1:4 membranes. Furthermore, the 1:3 and 1:4 membranes were physically more soft as will be shown by the permeability data. In case of 1:4 mixing ratio, the existence of finger-like macrovoids could likely also be due to the lower solution viscosity.

The pure water permeability of the films shown in **Figure 3.3** and **Figure 3.4** are presented in **Figure 3.5**. The permeabilities were expected to be low, as SEM images clearly showed membranes with relatively denser top layers. The 1:2 monomer mixing ratio membrane had a pure water permeability of $\sim 15 \text{ L} \cdot \text{m}^{-2} \cdot \text{h}^{-1} \cdot \text{bar}^{-1}$. When the mixing ratio is increased to 1:3 and then to 1:4, the permeability of the resulting membrane did not change significantly. However, the variance between the water permeability values measured for three different samples of

Figure 3.5 Effect of PSS:PAH monomer mixing ratio on the pure water permeability of the resulting membranes. The permeability measurements were performed at a transmembrane pressure of 4 bar.

the 1:3 and 1:4 membranes was higher confirming that these membrane structures were not homogeneous (see the SEM images in **Figure 3.4c** and **d**). Another major difference here is that the 1:4 mixing ratio membranes undergo extensive structural compaction at 4 bar of applied water pressure compared to the 1:2 and 1:3 membranes (see *Figure S3.7, supporting information*). Structural (or pore) compaction manifests as a decrease in water permeability over time, which typically stabilizes after some time period. The compaction shown in *Figure S3.7* for the 1:4 membrane signifies that it is physically softer and more porous. Due to the high variance in water permeability values and their inhomogeneous structure, 1:3 and 1:4 membranes could not be used for further processing. As the membranes prepared from solutions with a monomer ratio of 1:2 showed stable and reproducible pure water fluxes (see *Figure S3.7, supporting information*), this ratio was selected for further investigations.

3.3.3 Effect of pH of the coagulation bath

In this APS approach, the membrane formation is driven by a pH gradient from the casting solution (high pH) to the coagulation bath (low pH). So naturally, the pH of the coagulation bath will have a significant impact on the phase inversion kinetics and resulting membrane morphology. Therefore to understand the influence of this parameter, a solution with monomer ratio of 1:2 was cast, as before, and immersed in coagulation baths at different pH values (with 0.05 wt% GA). The pH of the bath was varied from 0.25 to 1.5 with increments of 0.25 (adjusted using HCl). Photographs of the cast membranes are shown in *Figure S3.8, supporting information*. The membranes prepared at pH = 0.25 were relatively rigid as compared to the others. As the

Figure 3.6 Cross-section and top surface SEM images of the PSS:PAH (1:2) membranes prepared in coagulation baths with different pH values and fixed GA concentration of 0.05 wt%. Coagulation bath pH; (a, g) 0.25, (b, h) 0.5, (c, i) 0.75, (d, j) 1, (e, k) 1.25, and (f, l) 1.5.

pH of the coagulation bath increases, the membranes lose some of their rigidity but they remain mechanically stable and can be operated up to 20 bar of applied water pressure (*Figure S3.12, supporting information*). The membranes prepared at pH 1.25 and 1.5 visibly showed rougher surfaces than the other membranes.

Cross-section and top surface SEM images of these membranes are presented in **Figure 3.6**. Cross-section images indicate that all the membranes have a skin layer on top with a porous substructure. It is important to mention that the top layer is not fully dense, but rather contains small pores as will be revealed later from the BSA retention measurements. The substructure directly beneath the top layer in the cross-section SEM images of **Figure 3.6** changes drastically when the pH of the coagulation bath is increased from 0.25 through to 1.5. At pH 0.25 (**Figure 3.6a**), the substructure does not show clear pores at the shown magnification. But when the coagulation bath pH is increased to 0.5, small pores start to appear in the substructure (**Figure 3.6b**). As the pH of the bath is increased further, the size and density of these pores also

increases. The cross-section images in **Figure 3.6c-f** show a skin layer with a porous substructure. Due to the higher polyelectrolyte concentrations and high viscosities of the PSS-PAH casting solutions, no finger-like macrovoids were observed in any of these membranes [19].

The pH-switch in APS can be considered analogous to the “solvent - non-solvent” transition in traditional NIPS. In this version of APS, the polyelectrolytes in the casting solution are soluble and miscible with each other in water at pH ~ 14 . Decreases in pH, as seen earlier in **Figure 3.1**, results in complexation and phase separation. This is because as the pH of the solution is lowered (towards and then below the pK_a of PAH), PAH becomes charged and therefore can undergo complexation with the fully charged PSS. In other words, at high pH conditions, water acts as a solvent while at low pH conditions, water acts as a non-solvent for the PSS-PAH solution.

At very low pH conditions in the coagulation bath, such as pH 0.25, the driving force for polyelectrolyte complexation is much larger than at even slightly higher pH values, and this low pH results in faster precipitation of the membranes. The reason for this is that the difference between the pH of polyelectrolyte casting solution ($\sim 13-14$) and the coagulation bath (pH 0.25) is large, resulting in a strong driving force for the H^+ ions in the bath to diffuse into the polyelectrolyte solution. Rapid exchange of H^+ ions results in immediate polyelectrolyte complexation between PSS and PAH and hence faster precipitation. It is known from literature on the NIPS process that a stronger interaction between the solvent and the non-solvent results in denser membranes [33]. The same is also true for APS membranes prepared in a coagulation bath at pH 0.25, where the abundance of H^+ ions results in stronger interactions with the polyelectrolyte casting solution, favoring denser complexes. This effect is also seen in the SEM images of **Figure 3.6a, g** where the membrane do not contain any visible pores at the shown magnification. However, there is a stark difference between the substructures of APS and NIPS membranes when the precipitation rate is fast. As mentioned earlier, instantaneous demixing in NIPS typically results in membranes that contain macrovoids in the substructure. But in case of APS, the H^+ ions continue to diffuse through the skin layer because of their small size. In other words, there is little mass transfer hindrance for the H^+ ions and therefore, the precipitation below the skin layer continues and this acts to prevent the formation of macrovoids. In APS, the limiting parameter then is the concentration of H^+ ions (or pH) in the coagulation bath, and this determines the porosity of the substructure. With increases in bath pH (less H^+ ions), the driving force for complexation gradually decreases and this results in a slower precipitation rate and hence results in membranes with a more porous substructures.

Figure 3.7 shows the pure water permeability and BSA retention of the membranes prepared in coagulation baths with varying pH values. The membranes prepared at pH 0.25 had a pure water permeability of $\sim 5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ with $\sim 98\%$ BSA retention. The pure water permeability and BSA retention remained similar ($\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ and 97%) for the membranes prepared in coagulation baths with pH 0.5 through to 1. This behavior indicates that the membranes are ultrafiltration type membranes that are well suited for the concentration of protein solutions. When the pH of the coagulation bath was increased to 1.25 and 1.5, the pure water permeability of the resultant membranes increased to $\sim 30 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ and $110 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively. The membranes prepared at these pH conditions had defects in the structure due to the inhomogeneous surface (see *Figure S3.8* for photographs of the membranes) and therefore, as expected, these membranes did not show any BSA retention.

The water permeability of the membranes prepared at pH 1 and 1.5 coagulation bath were also

Figure 3.7 Pure water permeability and BSA retention of the membranes prepared in coagulation baths of varying pH values. Pure water permeability and BSA ($1 \text{ g}\cdot\text{L}^{-1}$) retention measurements were conducted at transmembrane pressures of 4 and 3 bar, respectively.

measured at 20 bar of applied pressure in order to further explore the mechanical strength of these membranes (see *Figure S3.12* in the *supporting information*). Membranes prepared using the pH 1 coagulation bath showed stable permeability ($\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) up to 20 bar of applied water pressure indicating that the membrane structure remains intact. However, the membranes prepared in pH 1.5 coagulation bath showed a decrease in water permeability with increasing water pressure, which shows that these membrane undergo slight structural compaction at increased pressures.

It is clear that the pH of the coagulation bath is an important parameter to tune the properties of APS membranes because it directly affects the rate of phase inversion. The membranes prepared in pH 1 coagulation bath were chosen for further experiments because of their high BSA retention and higher water permeability.

3.3.4 Effect of GA concentration in the coagulation bath

In the described APS approach, a small amount of crosslinker (GA) is added to the coagulation bath to obtain improved mechanical properties. Up until now, the GA concentration in the coagulation bath was kept constant at 0.05 wt%. However, the concentration of GA also affects the properties of the resultant membranes as it determines the crosslinking density causing the densification of the structure [34]. To investigate the effect of GA on the final membrane properties, membranes were prepared in baths at pH 1 with varying GA concentrations i.e. from no GA to 0.5 wt% GA (see *Figure S3.9* for photographs of the resultant membranes).

Figure 3.8 Cross-section and top surface SEM images of the PSS:PAH (1:2) membranes prepared in a coagulation bath at pH 1 with different concentrations of GA in the coagulation bath; (a, g) without GA, (b, h) 0.05 wt% GA, (c, i) 0.1 wt% GA, (d, j) 0.15 wt% GA, (e, k) 0.2 wt% GA, and (f, l) 0.5 wt% GA.

Figure 3.8 shows the SEM images of the membranes prepared with varying concentrations of GA in the coagulation bath. It appears from the cross-section SEM images that the thickness of the top layer increases with increasing amount of GA. The membranes prepared at GA > 0.15 wt% were physically more rigid, while at 0.5 wt% GA, the resulting membranes were too brittle to be used for the water permeability measurements. Cross-section SEM images reveal that the pore size of the substructure reduces significantly with the addition of GA in the bath until 0.15 wt%. It is important to mention here that the polyelectrolyte complexation/precipitation process occurs at the same time as the crosslinking reaction. These two kinetic parameters are likely linked, which results in different membrane structures.

FTIR spectra of the membranes is shown in *Figure S3.11, supporting information*. After crosslinking, imine bonds will be formed and this peak should appear between 1635 cm^{-1} and 1645 cm^{-1} [35,36]. However, amine (N–H bending) groups from the non-crosslinked moieties also give rise to a

Figure 3.9 Effect of GA concentration in the coagulation bath on the pure water permeability of the resultant PSS:PAH (1:2) membranes. The pH of the coagulation bath was kept constant at 1. Permeability measurements were conducted at a transmembrane pressure of 4 bar.

characteristic peak between 1580 cm^{-1} and 1627 cm^{-1} [35]. As these two regions are very close to each other, it is very difficult to draw any conclusions on the effect of GA concentration from the FTIR spectra.

The average pore size of these membranes was estimated by analyzing the top surface SEM images shown in **Figure 3.8** using ImageJ software. The pore size distributions are shown in *Figure S3.10, supporting information*. The average pore sizes are summarized in **Figure 3.9** where the error bars are an indication of pore size distribution. The average pore sizes measured using the SEM images may not reflect the true pore size of the membranes during operation, but they do provide insight into the relative differences in pore size between the different membranes. The membranes prepared without the GA in the bath had an average surface pore size of $\sim 46 \text{ nm}$. Increasing the GA to 0.05 wt% resulted in membranes with an average pore size of $\sim 2 \text{ nm}$. Further increases in the amount of GA crosslinker in the coagulation bath resulted in an increased surface pore size of the membrane to $\sim 18 \text{ nm}$ at 0.1 wt% GA, and then to $\sim 46 \text{ nm}$ at 0.2 wt% GA. At 0.5 wt% GA, the average pore size was estimated to be $\sim 450 \text{ nm}$ (not shown in the figure). It is important to note here that the crosslinking reaction of PAH with GA occurs at the same time as the polyelectrolyte complexation of PAH with PSS. Therefore, as the concentration of GA is increased, the crosslinking reaction becomes more likely and this may compete more with the polyelectrolyte complexation. In turn, this would result in less PAH being available for complexation with PSS and may lead to the formation of larger voids in the resultant complex and hence the greater measured pore sizes of the membranes. The overall behavior indicates that there exists an optimum concentration of GA, which results in membranes with the most compact structure. A similar optimum concentration of GA has been reported by Duong *et al.* for

the PSS-PAH multilayer based membranes [37]. For APS with PSS/PAH the GA concentration can be seen as an additional control parameter to control the eventual membrane pore size, a parameter not available in traditional NIPS.

Figure 3.9 also shows the effect of GA concentration present in the coagulation bath on the pure water permeability of the resulting membranes. Following the same trend as the membrane pore sizes, the pure water permeability shows a minimum at 0.05 wt% GA, in line with the smallest observed pores. Membranes prepared without GA in the bath showed a pure water permeability of $\sim 45 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, while the pure water permeability decreases to $\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ for the membranes prepared with 0.05 wt% GA. This is the same membrane that was able to retain $\sim 97\%$ BSA discussed in the previous section. Further increases in the amount of GA in the bath, results in membranes with a higher water permeability, which is due to the increase in the average pore size of the membranes.

The water permeability of the membranes prepared in coagulation baths containing different amounts of GA was also measured at 20 bar of applied pressure to further evaluate their mechanical stability (see *Figure S3.13* in the *supporting information*). The results show that the pure water permeability decreases as the applied pressure is increased to 20 bar, suggesting that a degree of structural compaction occurs. At 0.05 wt% GA in the bath, the resultant membranes exhibited stable water permeability even up to 20 bar (see *Figure S3.12*, *supporting information*). Upon increasing the concentration of GA in the bath to 0.2 wt%, the membrane pore size increases to $\sim 46 \text{ nm}$ and the membrane shows compaction under pressure, but importantly the membrane does not rupture and operation can continue accounting for the structural compaction.

The results reveal that the concentration of GA is a key parameter for PSS/PAH based APS that acts to improve the mechanical properties and separation performance of the membranes.

3.3.5 Chemical stability of the membranes

The chemical stability of membranes prepared using the coagulation bath at pH 1 with 0.05 wt% GA were studied by immersing them in aqueous solutions at different pH values, specifically 1, 7, 8, 10, and 12 for 7 days and subsequently measuring their water permeability. The results shown in *Figure S3.14* in the *supporting information* reveal that the pure water permeability of the treated membranes remains the same at $\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ when immersed in pH 1–8 solutions. However, the membranes immersed in pH 10 and 12 solutions exhibited increased pure water permeability i.e. ~ 300 and $\sim 3400 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively. At pH > 8 (greater than the apparent pK_a of PAH), the PAH becomes deprotonated, losing its charge. It is possible that at pH 10 and 12 some of the PSS-PAH complex is broken because of the uncharging of PAH leading to a more open membrane structure. Re-washing this complex membrane with deionized water does not fully recover the complex to its original, untreated state, suggesting irreversible structural changes.

Sodium hypochlorite (NaClO) is a common oxidant used for cleaning polymeric membranes [38]. To evaluate the stability of the PSS-PAH membranes against NaClO treatment, again the membranes prepared in pH 1 bath with 0.05 wt% GA were immersed in different concentrations of NaClO aqueous solutions. The solutions were prepared by diluting NaClO to 300 ppm, 800 ppm, and 1200 ppm with deionized water. The pH of the solutions was adjusted to 8 using

0.1 M NaOH or 0.1 M HCl solution. The membranes were immersed in the NaClO solutions for 1 hour, subsequently removed and then washed with deionized water before their pure water permeability was re-measured. The results as shown in *Figure S3.15* in the *supporting information* and reveal that the pure water permeability of the membranes does not change after exposure to NaClO solutions even up to 1200 ppm.hr showing that the PSS-PAH membranes are stable against a NaClO cleaning treatment.

3.4 Conclusions

Just like NIPS, the fabrication of Aqueous Phase Separation (APS) membranes via polyelectrolyte complexation of PSS and PAH is a versatile approach involving many different tuning parameters. All these parameters influence the thermodynamics and kinetics of phase inversion in one way or the other. In this study, we have systematically investigated the effect of polyelectrolyte casting solution composition and the coagulation bath conditions on the structure, morphology, and properties of PSS-PAH membranes. The results indicate that the casting solution composition is one crucial parameter that controls the mutual interactions between PSS and PAH. Here, an optimum amount of base ($R = \text{NaOH}/\text{PAH} = 0.5$) was added to the PAH solution to obtain homogeneous casting solutions when mixed with PSS. R values < 0.5 resulted in polyelectrolyte complexation in the casting solution while $R > 0.5$ resulted in a difficult to process viscous gel-like phase. Similarly, the monomer mixing ratio of PSS to PAH in the casting solution is a critical parameter that greatly influences the membrane formation process. It was found that the monomer mixing ratio of 1:2 (PSS:PAH) resulted in a casting solutions with a desired high dynamic viscosity of 48 Pa·s, due to stronger interactions between the two polyelectrolytes. A clear optimum in the casting solution composition was thus observed, but it was found that the conditions of the coagulation bath had a greater influence on the membrane pore size and separation performance. The kinetics of phase inversion could be controlled by varying the pH of the coagulation bath. Results revealed that at pH 0.25–1, the membranes showed stable water permeability and high BSA retentions ($\sim 97\%$), with lower pH values leading to denser membranes. Increasing the bath pH beyond pH 1, resulted in the slowing down of the precipitation rate and this induced inhomogeneity in the resulting membrane structures. At a coagulation bath pH > 1 , the resulting membranes showed higher water permeabilities and much lower protein retentions. The concentration of glutaraldehyde (GA) in the bath, which was used to crosslink the PAH chains, was varied from 0 to 0.5 wt%. The presence of the crosslinking agent improved the mechanical stability and density (lower pore size) of the membranes. The surface pore size of the membranes could be tuned from ~ 2 nm (without GA) to ~ 46 nm (with 0.2 wt% GA). At 0.05 wt% GA in bath, the resulting ultrafiltration type membranes showed water permeability of $\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ and $\sim 97\%$ BSA retention. Moreover, the membranes show chemical stability upon treatment with NaClO solutions till 1200 ppm.hr.

Overall in this work, and to a lesser extent in our earlier work described in **Chapter 2**, we have established that membrane fabrication by the APS approach has a lot of similarities with the traditional NIPS process. From the molecular weights of the polyelectrolytes used, to the composition of the casting solutions, and also the coagulation bath conditions, each parameter/step is crucial in determining the morphology and separation performance of the resulting membranes. This study based on the complexation of PSS and PAH highlights the many parameters that are available to fine tune the properties of polyelectrolyte complex

membranes prepared by APS. With these tuning parameters sustainable membranes could be optimized for specific applications. Additional parameters such as the addition of additives to the polyelectrolyte casting solution as well as moving to less extreme pH conditions, facilitated by using different polyelectrolyte pairs, will be the focus of our future research to further highlight the significant potential of APS as a sustainable approach to membrane production. Moreover, polyelectrolytes with easily crosslinkable side groups could be used to avoid the use of glutaraldehyde in the coagulation bath.

Acknowledgements

This work was supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (ERC StG 714744 SAMBA). W.d.V and J.D.W acknowledge funding support from the "Vernieuwingsimpuls" program through project number VIDI 723.015.003 (financed by the Netherlands Organization for Scientific Research, NWO).

3.5 Supporting Information – S3

Figure S3.1 Photographs of PAH solutions (12 wt%) with different amounts of NaOH. Here $R = C_{\text{NaOH}}/C_{\text{PAH}}$, where C_{NaOH} is the concentration of NaOH in PAH solution (wt%) and C_{PAH} is the concentration of PAH (12 wt%). At $R = 1.25$, the PAH solution shows two distinct phases i.e. polyelectrolyte rich phase (top) and polyelectrolyte poor phase (bottom).

Figure S3.2 Turbidity of the PSS:PAH (1:2) casting solutions as a function of $R (C_{\text{NaOH}}/C_{\text{PAH}})$.

Figure S3.3 Photographs of polyelectrolyte solutions of PSS:PAH having different monomer mixing ratios. The solution having a monomer mixing ratio 4:1 (PSS:PAH) shows two distinct regions where it splits into a clear water-like liquid and a more viscous gel-like material at the bottom.

Figure S3.4 Shear stress vs shear rate curve showing the shear thinning effect of the two polyelectrolyte solutions having different monomer mixing ratios of PSS:PAH. The shear stress increases rapidly with the increasing shear rate for polyelectrolyte solution with 1:2 mixing ratio as compared to 2:1 (PSS:PAH). This indicates that the interactions between PSS and PAH chains are much larger in case of 1:2 than 2:1 mixing ratio.

Figure S3.5 Schematic illustration showing the reaction between the amine groups of poly(allylamine hydrochloride) and aldehyde groups of glutaraldehyde (GA) via a Schiff-base reaction mechanism. The resulting imine bonds ($-\text{C}=\text{N}-$) crosslinks the PAH chains.

Figure S3.6 SEM images of the membranes showing the full cross-section view. Monomer mixing ratios PSS:PAH, a) 1:1, b) 1:2, c) 1:3, and d) 1:4.

Figure S3.7 Pure water permeability vs elapsed time for the membrane prepared from casting solution with monomer ratio 1:2 and 1:4 (PSS-PAH). The membrane prepared with 1:4 PSS-PAH monomer ratio solution shows extensive compaction as compared to 1:2 membrane which shows negligible compaction. The membrane prepared using 1:3 monomer mixing ratio solution showed a similar trend as 1:2 membrane i.e. negligible compaction.

Figure S3.8 Effect of pH of the coagulation bath on PSS:PAH (1:2) membranes. The GA concentration was kept constant at 0.05 wt% in all the coagulation baths. The membranes are stored in deionized water for these photographs.

Figure S3.9 Photographs of the PSS:PAH (1:2) membranes prepared in varying concentrations of GA in the coagulation bath. The membranes are stored in deionized water for these photographs.

Figure S3.10 Pore size distribution of the membranes prepared in coagulation bath containing different amounts of GA; a) without GA, b) 0.05 wt% GA, c) 0.1 wt% GA, d) 0.2 wt% GA, and e) 0.5 wt% GA. Pore size was calculated by analyzing the top surface SEM images using ImageJ software.

Figure S3.11 FTIR spectra of PSS-PAH (1:2) membranes prepared in coagulation bath containing different amounts of GA. Imine (--C=N--) characteristic peak usually appears at $\sim 1645\text{ cm}^{-1}$ and amine (N--H bending) characteristic peak appears in the range 1580 cm^{-1} to 1650 cm^{-1} . Due to the small amount of GA (0.05 – 0.5 wt%) and overlap of imine and amine characteristic peaks, there is no difference in the IR spectra of with and without GA membranes.

Figure S3.12 High pressure mechanical stability tests of PSS:PAH (1:2) membranes. The membranes were prepared in pH 1 and pH 1.5 coagulation bath containing 0.05 wt% GA. The membranes prepared in pH 1 bath showed stable pure permeability with increasing applied water pressure. On the other hand, the membranes prepared in pH 1.5 coagulation bath showed compaction with increasing applied water pressure.

Figure S3.13 High pressure mechanical stability tests of PSS:PAH (1:2) membranes. The membranes were prepared in pH 1 coagulation bath containing different amounts of GA. Both the membranes, i.e. without GA and 0.2 wt% GA in the bath, showed compaction with increasing pressure. This is possibly due to the larger average surface pore size (~ 46 nm) of the membranes.

Figure S3.14 Pure water permeability of the membranes after exposure to different pH solutions for 1 week. The membranes were immersed in aqueous solutions at different pHs for 1 week. The membranes were taken out, washed with water and tested for pure water permeability. The results indicate that the pure water permeability of the membranes remain stable i.e. $\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ even after exposure to pH 1 – 8 solutions for 1 week. The pure water permeability increases after exposure of the membranes to pH 10 and pH 12 solutions.

Figure S3.15 Pure water permeability of the membranes after exposure to different concentrations of NaClO solutions at pH 8 for 1 hour. The results indicate that the pure water permeability of the membranes remain completely stable i.e. $\sim 15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ even after exposure to 1200 ppm.hr NaClO solution.

3.6 References

- [1] S. Loeb, S. Sourirajan, Sea Water Demineralization by Means of an Osmotic Membrane, Saline Water Conversion—II, American Chemical Society. SE-9 (1963) 117-132. doi:10.1021/ba-1963-0038.ch009.
- [2] R.W. Baker, Membrane technology and applications, Third Edit, John Wiley & Sons, Chichester, UK, 2012.
- [3] H. Strathmann, K. Kock, The formation mechanism of phase inversion membranes, Desalination. 21 (1977) 241–255. doi:10.1016/S0011-9164(00)88244-2.
- [4] H. Strathmann, K. Kock, P. Amar, R.W. Baker, The formation mechanism of asymmetric membranes, Desalination. 16 (1975) 179–203. doi:10.1016/S0011-9164(00)82092-5.
- [5] M. Mulder, Basic principles of membrane technology, Kluwer Academic Publishers, Dordrecht, The Netherlands, 1996.
- [6] A.K. Holda, B. Aernouts, W. Saeys, I.F.J. Vankelecom, Study of polymer concentration and evaporation time as phase inversion parameters for polysulfone-based SRNF membranes, J. Memb. Sci. 442 (2013) 196–205. doi:10.1016/j.memsci.2013.04.017.
- [7] G. Bakeri, A.F. Ismail, M. Shariaty-Niassar, T. Matsuura, Effect of polymer concentration on the structure and performance of polyetherimide hollow fiber membranes, J. Memb. Sci. 363 (2010) 103–111. doi:10.1016/j.memsci.2010.07.018.
- [8] H.H. Wang, J.T. Jung, J.F. Kim, S. Kim, E. Drioli, Y.M. Lee, A novel green solvent alternative for polymeric membrane preparation via nonsolvent-induced phase separation (NIPS), J. Memb. Sci. 574 (2019) 44–54. doi:10.1016/j.memsci.2018.12.051.
- [9] H. Susanto, M. Ulbricht, Characteristics, performance and stability of polyethersulfone ultrafiltration membranes prepared by phase separation method using different macromolecular additives, J. Memb. Sci. 327 (2009) 125–135. doi:10.1016/j.memsci.2008.11.025.
- [10] K.W. Lee, B.K. Seo, S.T. Nam, M.J. Han, Trade-off between thermodynamic enhancement and kinetic hindrance during phase inversion in the preparation of polysulfone membranes, Desalination. 159 (2003) 289–296. doi:10.1016/S0011-9164(03)90081-6.
- [11] M. Sadrzadeh, S. Bhattacharjee, Rational design of phase inversion membranes by tailoring thermodynamics and kinetics of casting solution using polymer additives, J. Memb. Sci. 441 (2013) 31–44. doi:10.1016/j.memsci.2013.04.009.
- [12] G.R. Guillen, Y. Pan, M. Li, E.M. V Hoek, Preparation and characterization of membranes formed by nonsolvent induced phase separation: A review, Ind. Eng. Chem. Res. 50 (2011) 3798–3817. doi:10.1021/ie101928r.
- [13] A.K. Holda, I.F.J. Vankelecom, Understanding and guiding the phase inversion process for synthesis of solvent resistant nanofiltration membranes, J. Appl. Polym. Sci. 132 (2015). doi:10.1002/app.42130.
- [14] X.M. Tan, D. Rodrigue, A review on porous polymeric membrane preparation. Part I: Production techniques with polysulfone and poly (vinylidene fluoride), Polymers (Basel). 11

(2019). doi:10.3390/polym11071160.

[15] P. Van De Witte, P.J.J. Dijkstra, J.W.A. Van Den Berg, J. Feijen, Phase separation processes in polymer solutions in relation to membrane formation, *J. Memb. Sci.* 117 (1996) 1–31. doi:10.1016/0376-7388(96)00088-9.

[16] D. Prat, J. Hayler, A. Wells, A survey of solvent selection guides, *Green Chem.* 16 (2014) 4546–4551. doi:10.1039/c4gc01149j.

[17] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restr. Off. J. Eur. Union. 99 (2018) 3.

[18] A.S. Michaels, Polyelectrolyte Complexes, *Ind. Eng. Chem.* 57 (1965) 32–40. doi:10.1021/ie50670a007.

[19] M.I. Baig, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.

[20] J.D. Willott, W.M. Nielen, W.M. de Vos, Stimuli-Responsive Membranes through Sustainable Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 659–667. doi:10.1021/acsapm.9b01006.

[21] W.M. De Vos, (Universiteit Twente), Aqueous phase separation method, U.S. Patent Application no. 15/972,273, 2018.

[22] B. Jachimska, M. Wasilewska, Z. Adamczyk, Characterization of globular protein solutions by dynamic light scattering, electrophoretic mobility, and viscosity measurements, *Langmuir*. 24 (2008) 6867–6872. doi:10.1021/la800548p.

[23] L. Li, S. Srivastava, M. Andreev, A.B. Marciel, J.J. De Pablo, M. V. Tirrell, Phase Behavior and Salt Partitioning in Polyelectrolyte Complex Coacervates, *Macromolecules*. 51 (2018) 2988–2995. doi:10.1021/acs.macromol.8b00238.

[24] X. Jiang, C. Ortiz, P.T. Hammond, Exploring the rules for selective deposition: Interactions of model polyamines on acid and oligoethylene oxide surfaces, *Langmuir*. 18 (2002) 1131–1143. doi:10.1021/la010832q.

[25] N. Volk, D. Vollmer, M. Schmidt, W. Oppermann, K. Huber, Conformation and Phase Diagrams of Flexible Polyelectrolytes, *Adv. Polym. Sci.* 166 (2004) 29–65. doi:10.1007/b11348.

[26] K. Murakawa, D.R. King, T. Sun, H. Guo, T. Kurokawa, J.P. Gong, Polyelectrolyte complexation via viscoelastic phase separation results in tough and self-recovering porous hydrogels, *J. Mater. Chem. B*. 7 (2019) 5296–5305. doi:10.1039/c9tb01376h.

[27] M. Tsianou, A.L. Kjøniksen, K. Thuresson, B. Nyström, Light scattering and viscoelasticity in aqueous mixtures of oppositely charged and hydrophobically modified polyelectrolytes, *Macromolecules*. 32 (1999) 2974–2982. doi:10.1021/ma981619c.

[28] F.E. Antunes, B. Lindman, M.G. Miguel, Mixed systems of hydrophobically modified polyelectrolytes: Controlling rheology by charge and hydrophobe stoichiometry and interaction

strength, *Langmuir*. 21 (2005) 10188–10196. doi:10.1021/la050590k.

[29] H. Riegler, F. Essler, Polyelectrolytes. 2: Intrinsic or extrinsic charge compensation? Quantitative charge analysis of PAH/PSS multilayers, *Langmuir*. 18 (2002) 6694–6698. doi:10.1021/la020108n.

[30] W. Tong, C. Gao, H. Möhwald, Manipulating the properties of polyelectrolyte microcapsules by glutaraldehyde crosslinking, *Chem. Mater.* 17 (2005) 4610–4616. doi:10.1021/cm0507516.

[31] A. Biswas, A.T. Nagaraja, Y.H. You, J.R. Roberts, M.J. McShane, Crosslinked nanofilms for tunable permeability control in a composite microdomain system, *RSC Adv.* 6 (2016) 71781–71790. doi:10.1039/C6RA13507B.

[32] C.A. Smolders, A.J. Reuvers, R.M. Boom, I.M. Wienk, Microstructures in phase-inversion membranes. Part 1. Formation of macrovoids, *J. Memb. Sci.* 73 (1992) 259–275. doi:10.1016/0376-7388(92)80134-6.

[33] K.Y. Chun, S.H. Jang, H.S. Kim, Y.W. Kim, H.S. Han, Y. Il Joe, Effects of solvent on the pore formation in asymmetric 6FDA-4,4'ODA polyimide membrane: Terms of thermodynamics, precipitation kinetics, and physical factors, *J. Memb. Sci.* 169 (2000) 197–214. doi:10.1016/S0376-7388(99)00336-1.

[34] Y. Li, S. Zhao, L. Setiawan, L. Zhang, R. Wang, Integral hollow fiber membrane with chemical crosslinking for pressure retarded osmosis operated in the orientation of active layer facing feed solution, *J. Memb. Sci.* 550 (2018) 163–172. doi:10.1016/j.memsci.2017.12.074.

[35] S.D. Tuong, H. Lee, H. Kim, Chemical fixation of polyelectrolyte multilayers on polymer substrates, *Macromol. Res.* 16 (2008) 373–378. doi:10.1007/BF03218531.

[36] K.L. Cho, A.J. Hill, F. Caruso, S.E. Kentish, Chlorine resistant glutaraldehyde crosslinked polyelectrolyte multilayer membranes for desalination, *Adv. Mater.* 27 (2015) 2791–2796. doi:10.1002/adma.201405783.

[37] P.H.H. Duong, J. Zuo, T.S. Chung, Highly crosslinked layer-by-layer polyelectrolyte FO membranes: Understanding effects of salt concentration and deposition time on FO performance, *J. Memb. Sci.* 427 (2013) 411–421. doi:10.1016/j.memsci.2012.10.014.

[38] C. Ramos, F. Zecchino, D. Ezquerro, V. Diez, Chemical cleaning of membranes from an anaerobic membrane bioreactor treating food industry wastewater, *J. Memb. Sci.* 458 (2014) 179–188. doi:10.1016/j.memsci.2014.01.067.

“The important thing is not to stop questioning. Curiosity has its own reason for existing.”

- Albert Einstein

Chapter 4.

Enhancing the separation performance of Aqueous Phase Separation based membranes through polyelectrolyte multilayer coatings and interfacial polymerization

This chapter is published as:

M.I. Baig, J.D. Willott, W.M. de Vos, Enhancing the Separation Performance of Aqueous Phase Separation-Based Membranes through Polyelectrolyte Multilayer Coatings and Interfacial Polymerization, ACS Appl. Polym. Mater. (2021). doi:10.1021/acsapm.1c00457.

Abstract

The Aqueous Phase Separation (APS) technique allows membrane fabrication without use of unsustainable organic solvents, while at the same time it provides extensive control over the membrane pore size and its morphology. Herein, we investigate if polyelectrolyte complexation induced APS ultrafiltration membranes can be the basis for different types of nanofiltration membranes. We demonstrate that APS membranes can be used as support membranes for functional surface coatings like thin polyelectrolyte multilayer (PEMs) and interfacial polymerization (IP) coatings. Three different polyelectrolyte multilayers were fabricated on poly(sodium 4-styrene sulfonate) (PSS) poly(allylamine hydrochloride) (PAH) APS ultrafiltration membranes and only 4.5 bilayers were needed to create nanofiltration membranes with molecular weight cut-off (MWCO) values of 210–390 Da while maintaining a roughly constant water permeability ($\sim 1.7 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$). The PEM coated membranes showed excellent MgCl_2 ($\sim 98\%$), NaCl ($\sim 70\%$) and organic micropollutant retention values ($>90\%$). Similarly, fabricating thin polyamide layers on the ultrafiltration PSS-PAH APS membranes by IP resulted in nanofiltration membranes with MWCO values of ~ 200 Da. This work shows for the first time that APS membranes can indeed be utilized as excellent support membranes for performing functional coatings without requiring any form of pre-treatment.

4.1 Introduction

Membrane technology is gradually moving towards greener and more sustainable production techniques [1,2]. In this regard, Aqueous Phase Separation (APS) has been introduced as one of the more sustainable approaches to produce polymeric membranes. This new approach eliminates the use of reprotoxic organic solvents, such as *N*-methylpyrrolidone (NMP), the most commonly used organic solvent in the Non-solvent Induced Phase Separation (NIPS) process. Instead, APS makes use of water as solvent and non-solvent to achieve phase separation. Currently there are two commonly applied APS methods. The first makes use of water soluble pH-responsive polyelectrolytes where the phase separation is achieved by simply changing the pH of the cast film containing only one type of polyelectrolyte such as poly(4-vinylpyridine) (P4VP) [3] or polystyrene-*alt*-maleic acid (PSaMA) copolymer [4]. Membranes ranging from microfiltration type to dense nanofiltration type can be successfully prepared using this method.

The second APS method uses a mixture of two polyelectrolytes i.e. a polyanion and a polycation, to obtain a polyelectrolyte complex (PEC) membrane. Sadman *et al.* utilized this method to produce porous PEC membranes using coacervates of poly(styrene sulfonate) (PSS) and poly(*N*-ethyl-4-vinylpyridinium) (QVP-C2) [5]. The PSS-QVP-C2 membranes presented in their work demonstrated a good water flux, organic solvent stability, and excellent rejection of polystyrene beads of ~ 100 nm in size. However, this polyelectrolyte system had its own limitations with membrane fabrication protocols are at times lengthy, while the control over the membrane pore size was limited. In another instance, Durmaz *et al.* obtained dense nanofiltration type PEC membranes having a molecular weight cut-off of <300 Da using a solution of PSS and poly(diallyldimethylammonium chloride) (PDADMAC) that was prepared at high salt concentrations and precipitated in deionized water [6]. This method is also known as the 'salinity change induced APS' because the phase separation is achieved by lowering the salt concentration in the polyelectrolyte solution thereby forming a polyelectrolyte complex membrane. A

similar method was also applied by Kamp *et al.* to produce ultra- and nanofiltration type PSS-PDADMAC membranes [7]. However, the downsides of these PSS-PDADMAC membranes in both works are the relatively lower water permeabilities i.e. $\sim 0.1 - 1 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ and the limited control over the membrane pore size. Another interesting method is the 'pH shift induced APS' where a polycation and polyanion solution is prepared at high pH and precipitated in low pH conditions (or vice versa) to achieve phase separation. In **Chapter 2** and **Chapter 3**, we have successfully employed this method to obtain PEC membranes with tunable pore sizes ranging from micro- to nanofiltration using a mixture of PSS-poly(allylamine hydrochloride) (PAH). While the pore size of the PSS-PAH membranes could be controlled from $\sim 200 \text{ nm}$ to $\sim 2 \text{ nm}$, dense nanofiltration membranes were not obtained. The open nanofiltration (or tight ultrafiltration) type PSS-PAH membranes obtained in these chapters did not show any significant retention of salts and showed only $\sim 80\%$ average retention of a range of organic micropollutants. For most nanofiltration applications, the membranes need to be able to retain salts and organic micropollutants in excess of 90%. Similarly, in another work by Durmaz *et al.* on 'pH shift induced APS', PSS and poly(acrylic acid) (PAA) were used to obtain only microfiltration type PEC membranes [10].

Traditionally, most dense membranes, such as nanofiltration and reverse osmosis membranes, are based on porous support membranes prepared by NIPS and subsequently coated with thin layers of another material. In a similar fashion it stands to reason that porous APS membranes can and should be used as support membranes in a similar fashion.

Numerous coating strategies are available in the literature to improve the performance of polymeric membranes in terms of their water flux, selectivity, chemical resistance, mechanical properties, and antifouling ability [11]. Among these, one of the most commonly applied is Interfacial Polymerization (IP) where a thin polyamide film is coated on the membrane surface via a reaction of two or more monomers such as, *m*-phenylenediamine (MPD) in the aqueous phase, and trimesoyl chloride (TMC) in the organic phase [12]. Over the years, IP has been well-studied in terms of the types of monomers, the concentrations of the monomers, and other reaction conditions to obtain thin film composite (TFC) and nanocomposite membranes [12–18]. TFC membranes obtained via IP typically have excellent salt retentions [19,20] and chemical/physical stability [21] and are still the most preferred option for commercial nanofiltration membranes.

In recent years, another interesting coating approach that utilizes polyelectrolytes has gained significant attention. The so-called layer-by-layer (LBL) approach was first described by Decher to obtain self-assembled polyelectrolyte multilayers (PEM) by alternatively coating polycations and polyanions on solid supports [22]. This process can be used to prepare thin layers (usually 10–50 nm) on the surface of charged porous support membranes due to electrostatic interactions of the oppositely charged polyelectrolytes [23]. The PEM approach has proven to be a very versatile method to obtain ultrathin and dense coatings because of the ability to fine-tune their properties through, for example, the number of bilayers, salt concentration, and the pH of the coating solutions [24–26]. In addition, the PEM-coated membranes have also shown excellent chemical stability and resistance against cleaning/backwashing processes [27]. Common and successful PEM coatings include PSS-PDADMAC, PSS-PAH, PAA-PAH, and PSS-PEI [28]. Each polyelectrolyte pair has different properties and performance and this can be further fine-tuned by controlling the coating process. For instance PSS-PAH multilayer coatings have lower

polyelectrolyte mobility and typically show higher water permeability with good salt retentions [29]. The PSS-PDADMAC multilayer coatings show excellent physical and chemical stability against back flushing [30] and show a particularly high anion selectivity towards sulfate and phosphate [31,32]. On the other hand, PSS-PEI multilayer coatings form dense complexes and therefore, show relatively lower water permeabilities but with excellent salt and organic molecules retentions [33]. In addition, the PSS-PAH and PSS-PDADMAC multilayer coatings have the polycation in excess in bulk and therefore are more susceptible to swelling [33]. In comparison, the PSS-PEI coatings have significantly less excess of polycation and therefore, have less degree of swelling.

In this work, we use the advantages of PEM and IP coatings and demonstrate that APS based membranes can also act as excellent supports for these functional coatings. One of the major advantages of using APS membranes for PEM coatings is the inherent charge of these membranes which facilitates the adsorption of charged polyelectrolytes. In **Chapter 2** it was shown that the PSS-PAH based APS membranes have positive charge on their surface. As a result, these support membranes can be directly coated with a layer of polyanion without any pre-treatment processes. Similarly, the excess amount of PAH in the PSS-PAH support membranes provides amine groups that can take part in the interfacial polymerization process by reacting with the TMC, thereby improving the adhesion of the IP layer to the support membrane. In this work, the support PSS-PAH based APS membranes are prepared following the protocols extensively discussed in **Chapter 2**. PEM coatings are performed using three different polyelectrolyte pairs i.e. PSS-PAH, PSS-PDADMAC, and PSS-PEI. **Figure 4.1** shows the chemical structures of these polyelectrolytes. The multilayer membranes are coated on the APS support membranes to densify the top surface structure and provide the membranes with nanofiltration performance. Similarly, IP was performed on porous (ultrafiltration) PSS-PAH membranes and the IP reaction conditions were optimized to obtain stable TFC membranes. Finally, all the coated membranes are tested for their nanofiltration performance using a range of different salts and organic micropollutants. This study showcases the versatility of APS membranes by demonstrating that they can function as support membranes for a multitude of surface coatings without requiring any pre-treatment.

4.2 Experimental Section

4.2.1 Materials

The chemicals Poly(sodium 4-styrene sulfonate) (PSS, 30 wt% with Mw ~200 kDa and 25 wt% with Mw ~1000 kDa), Poly(diallyldimethylammonium chloride) (PDADMAC, 20wt%, Mw ~200 – 350 kDa), branched Polyethyleneimine (PEI, 50 wt%, Mw ~750 kDa), sodium hydroxide (NaOH, >98%) sodium chloride (NaCl, >99.5%), hydrochloric acid (HCl, 37%, ACS reagent), glutaraldehyde (GA, 50 wt%), glycerol solution (86–89 wt%), *m*-Phenylenediamine (99%, MPD), 1,3,5-Benzenetricarbonyl trichloride (98%, TMC), *n*-Hexane ($\geq 99\%$), magnesium sulfate (MgSO_4 , >99.5%), sodium sulfate (Na_2SO_4 , 99%), magnesium chloride hexahydrate ($\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$, $\geq 99\%$), sodium chloride (NaCl, $\geq 99.5\%$), polyethylene glycol (PEG) with different molecular weights (Mw 200, 400, 600, 1500, and 2000 $\text{g}\cdot\text{mol}^{-1}$), atrazine (analytical standard), atenolol (>98%), bezafibrate (>98%), bromothymol blue (>95%), bisphenol-A (>99%), naproxen (analytical standard), phenolphthalein (analytical standard), and sulfamethoxazole

Figure 4.1 Chemical structures of the polyelectrolytes used for performing PEM coatings on the APS membrane supports. a) Poly(sodium 4-styrene sulfonate) (PSS), b) Poly(allylamine hydrochloride) (PAH), c) Poly(diallyldimethylammonium chloride) (PDADMAC), and d) branched Polyethyleneimine (PEI).

(analytical standard) were purchased from Merck (The Netherlands). Poly(allylamine hydrochloride) (PAH, 40 wt%, Mw ~ 150 kDa) was purchased from Nittobo Medical Co. Ltd., Japan. Deionized water was obtained from a Milli-Q[®] Ultrapure water purification system.

4.2.2 Membrane Fabrication

The polyelectrolyte complex membranes were prepared using recipes reported in **Chapter 2**. Briefly, first a 25 wt% PSS (Mw ~ 1000 kDa) solution was diluted to 12 wt% using deionized water. Second, 40 wt% PAH (Mw ~ 150 kDa) was diluted to 12 wt% by the addition of deionized water and 10 M NaOH solution. The NaOH solution was added such that the ratio of wt% NaOH to wt% PAH was constant at 0.5. The reason to add NaOH is to increase the pH of the aqueous PAH solution to ~ 14 , thereby making it uncharged so that it can be mixed with PSS without forming a polyelectrolyte complex. Finally, the 12 wt% PSS and PAH solutions were mixed in a monomer mixing ratio of PSS to PAH of 1:2. The ratios are based on the monomer weight of the polyelectrolytes i.e. ~ 206 g $\cdot\text{mol}^{-1}$ for PSS and ~ 93.5 g $\cdot\text{mol}^{-1}$ for PAH. This ratio of polyelectrolytes was selected because it results in mechanically stable membranes as shown earlier in **Chapter 3**. The casting solution was constantly stirred until it became homogeneous.

The solution was then cast as a thin film on a glass plate using a casting bar having a gap of 0.6 mm. To obtain the open nanofiltration type membrane supports for multilayer coatings, the cast solution was immediately immersed in a coagulation bath at pH 1 (adjusted using HCl) containing 0.05 wt% GA and 4 M NaCl. This composition of the coagulation bath was chosen because it results in open nanofiltration type PSS-PAH membranes as mentioned in **Chapter 2**. Here GA is used as a crosslinking agent for the amines of PAH while NaCl facilitates the polyelectrolyte chain rearrangement resulting in a denser complex. On the other hand, the ultrafiltration type membrane supports for interfacial polymerization were obtained by immersing the PSS-PAH cast films in a coagulation bath at pH 1 (adjusted using HCl) containing 0.05 wt% GA without any NaCl. The cast films immediately precipitated at low pH and turned opaque. The films were then removed from the bath after 24 h and kept in deionized water for further use.

4.2.3 Multilayer coatings

Three different types of multilayer coatings were applied in this work i.e. PSS-PAH, PSS-PDADMAC, and PSS-PEI. The coating solutions contained $1\text{g}\cdot\text{L}^{-1}$ of polyelectrolyte (polyanion or polycation) in 500 mM NaCl solution. This concentration of NaCl was chosen because thicker multilayer coatings are obtained at higher salt concentrations because of the increased extrinsic charge compensation within the multilayers [34]. The pH of all the polyelectrolyte solutions was set to 6 by adding 0.1 M NaOH/HCl. PSS and PDADMAC are strong polyelectrolytes, meaning that the pH of the solution has no impact on their charge. On the other hand, PAH and PEI are weak polyelectrolytes whose charge is dependent on the pH of the solution. It is known from literature that PSS-PAH multilayer membranes when coated at pH 6, form dense PEMs that show high retention of organic micropollutants [35]. Therefore, pH 6 was chosen as the coating solution pH for performing multilayer coatings. The multilayers were built using the following protocol. The support membranes were first soaked in 500 mM NaCl solution for 15 min followed by a 15 min dip coat in $1\text{g}\cdot\text{L}^{-1}$ PSS (polyanion, $M_w \sim 200$ kDa) solution. Afterwards, the membranes were taken out and immediately washed in three steps with 500 mM NaCl solution for 15 min each. The membranes were then dipped in $1\text{g}\cdot\text{L}^{-1}$ polycation (either PAH, PDADMAC, or PEI) solution for 15 min followed by a three step wash in 500 mM NaCl solution for 15 min each. This process produced one bilayer. The procedure was repeated to obtain 4.5 bilayers of each PSS-PAH, PSS-PDADMAC, and PSS-PEI with PSS as the ending layer. The PEM membranes with 4.5 bilayers are referred to as PSS-PAH_(4.5), PSS-PDADMAC_(4.5) and PSS-PEI_(4.5). The coated flat sheet membranes were stored in deionized water for further usage.

4.2.4 Interfacial Polymerization

Interfacial polymerization was carried out using MPD and TMC as monomers. A 2 wt% MPD solution was prepared in deionized water and stirred until it became homogeneous. A 0.2 wt% TMC solution was prepared by dissolving TMC in n-Hexane. The IP coating was then applied on the ultrafiltration type PSS-PAH membranes using the following protocol. First, the membranes were immersed in the aqueous MPD solution for 10 min. When the membranes were taken out, they appeared shiny due to the presence of water on the surface, which was removed by means of a rubber roller. Afterwards, the membranes were vertically dried inside an aerated fume hood until

they appeared dry and dull [12]. The MPD saturated membrane supports were then immersed in the TMC solution for 3 minutes to initiate the interfacial polymerization reaction after which they were dried again in the fume hood for 30 s before heat treatment in an oven at 70 °C for 5 min. The membranes were taken out, washed with deionized water, and stored in deionized water for further usage.

4.2.5 Characterization

Scanning electron microscopy (SEM) was performed on JSM-6010LA, JEOL, Japan. The membrane samples for SEM were first immersed in a 20 wt% Glycerol solution for 4 h and then dried in an aerated fume hood for 24 h. This procedure ensures that the pores of the membranes remain intact. For cross-section images, the dried membrane samples were immersed in liquid N₂ and carefully fractured to reveal the full cross-section. All the membrane samples were kept in a vacuum oven at 30 °C for 24 h before sputter coating them with a 5 nm thin layer of Pt/Pd alloy using a sputter coater Quorum Q150T ES (Quorum Technologies, Ltd., UK). Fourier Transformed Infrared (FTIR) spectroscopy was conducted on Spectrum TwoTM (Perkin Elmer, USA) in ATR (attenuated total reflectance) mode in the wavenumber range 600 cm⁻¹ to 4000 cm⁻¹.

The charge on the membrane surface was determined at pH 6 using SurPASS electrokinetic analyzer (Anton Paar, Graz, Austria) by measuring the streaming current versus pressure in a 5 mM KCl solution.

For the pure water permeability (PWP) measurements, the membranes were cut into circular disks having a diameter of 25 mm and then mounted on a dead-end Amicon[®] cell. The exposed surface area of the membranes was ~3.8 cm². The vessel containing the feed water was pressurized to 4 bar using N₂ gas. The permeate mass was measured as a function of time via mass balance connected to a computer. The PWP (P) was calculated using equation 4.1:

$$P = \frac{Jw}{\Delta p} \quad (4.1)$$

Where Jw is the water flux calculated by measuring the change in permeate volume (in liters) per membrane area (3.8 cm²) over time (h) and Δp is the pressure difference (bar) between the feed and permeate side.

The molecular weight cut-off (MWCO) of the membranes was determined using a feed solution of PEG having different molecular weights i.e. 200 g·mol⁻¹ to 2000 g·mol⁻¹, each at a concentration of 1 g·L⁻¹ in water. The mixture was filtered through the membranes in a dead-end cell at 3 bar and the permeate and retentate samples were collected. The feed, retentate, and permeate were then analyzed via Gel Permeation Chromatography (GPC, Agilent 1200/1260 Infinity GPC/SEC series, Polymer Standards Service data center and column compartment) using Milli-Q water eluent containing 50 mg·L⁻¹ NaN₃, at 1 mL·min⁻¹, through 1000 Å, 10 μm Polymer Standards Service Suprema 8 × 300 mm column and 30 Å, 10 μm column connected in series. GPC determines the concentration of PEGs via refractive index detection. The retention

(*R*) was calculated using equation 4.2:

$$R = \left[1 - \frac{C_p}{\left(\frac{C_f + C_r}{2} \right)} \right] \times 100 \quad (4.2)$$

Where C_p , C_f , and C_r are the concentration in permeate, feed, and retentate side, respectively. Here, an average of feed and retentate concentration is taken because the concentration of the feed solution in a dead-end cell is always changing. A sieving curve of retention vs. molecular weight of PEG was plotted and the MWCO was determined as shown in *Figure S4.4, supporting information*.

A 5 mM aqueous solution of four different types of salts i.e. MgCl_2 , MgSO_4 , Na_2SO_4 , and NaCl was filtered through the membranes at 4 bar of feed pressure. The feed, retentate, and permeate samples were collected and measured for their conductivity using a handheld WTWTM Cond 3210TM conductivity meter (Xylem Analytics, Germany). A calibration curve was obtained by plotting conductivity as a function of known concentrations of salt solutions. Consequently, the concentration of either type of salt in the actual feed, retentate, and permeate was determined according to the calibration curve and the retention was calculated using equation 4.2.

A cocktail mixture of eight different types of micropollutants was prepared by dissolving $3 \text{ mg}\cdot\text{L}^{-1}$ of each micropollutant in deionized water followed by adjusting the solution pH to 5.8 using 0.1 M NaOH. At this pH, the micropollutants are either positively charged, negatively charged, or neutral. Such a diverse combination of micropollutants can provide an assessment on the charge-based and size-based separation of molecules by the membranes. The mixture was filtered through the membranes for 24 h to achieve steady state permeation before collecting the feed, retentate, and permeate samples. These samples were analyzed on UltiMate 3000 UHPLC (ThermoFisher Scientific, USA) using a $2.2 \mu\text{m}$ ACCLAIM RSLC C18 column (ThermoFisher Scientific, USA) for separation. A calibration curve was first obtained using known concentrations of micropollutant cocktail mixture. The concentrations of micropollutants in feed, retentate, and permeate was estimated according to the calibration curve obtained using known concentrations of micropollutant cocktail mixture. The retention was then calculated using equation 4.2.

4.3 Results and Discussions

4.3.1 Multilayer coatings

When considering APS based membranes as supports for PEM coatings, the natural charge of the APS membranes can be considered as a real advantage, allowing easy coatings. The top surface and cross-section SEM images of all three different types of PEM membranes coated with 4.5 bilayers are shown in **Figure 4.2** along with the uncoated APS support membrane.

The PSS-PAH_(4.5) membranes showed relatively smooth top surfaces as compared to the PSS-PDADMAC_(4.5) and PSS-PEI_(4.5), see **Figure 4.2c, e, and g**. It is well known that PSS-PAH multilayers have lower mobility [29] and a higher number of interactions within the multilayer [36] as compared to the others studied in this work, which could explain the smooth texture

Figure 4.2 Top surface and cross-section SEM images of (a-b) APS support membrane and the PEM membranes coated with 4.5 bilayers of PSS-PAH (c-d), PSS-PDADMAC (e-f), and PSS-PEI (g-h).

of PSS-PAH PEMs. On the other hand, the PSS-PDADMAC and PSS-PEI coated membranes exhibited rougher and more uneven surfaces containing aggregates and also some degree of layering (especially in case of PSS-PEI) as seen in **Figure 4.2e** and **g**. Chen *et al.* also found similar morphologies for PEMs and concluded that such morphology could possibly be due to the inhomogeneous charge distribution on the substrate that could lead to isolated deposition of material [37]. However, in case of PSS-PEI multilayer membranes, the uneven top surfaces could possibly be due to the branched nature of the higher molecular weight PEI which forms

Figure 4.3 a) Pure water permeability and molecular weight cut-off, b) Salt retentions of PSS-PAH_(4.5), PSS-PDADMAC_(4.5), and PSS-PEI_(4.5) membranes. The support membrane showed negligible salt retentions as compared to the enhanced salt retentions by the PEM coated membranes. The retention tests were conducted at a feed pressure of 4 bar.

slightly thicker coatings. Nevertheless, the membranes contained no defects as will be established later by the organic micropollutant retention experiments. The cross-section SEM images of the PEM coated membranes, shown in **Figure 4.2d, f, and h**, do not reveal any significant information because it is difficult to estimate the PEM layer thickness via SEM images, especially as the coated material is very similar in nature to the materials of the support membranes. A better estimate of PEM thickness is obtained by utilizing the optical fixed-angle reflectometry or ellipsometry. For these systems that has been done in literature, coming to estimated thicknesses of ~ 25 nm for PSS-PDADMAC, ~ 16 nm for PSS-PEI [38], and ~ 20 nm for PSS-PAH [39].

Figure 4.3a shows the pure water permeability (PWP) and molecular weight cut-off (MWCO) of the three different types of PEM coated membranes. For reference, the PWP of the support APS membranes was $\sim 2 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. The PWP and salt retentions of the PEM membranes with 1.5 to 3.5 bilayers is shown in *Figure S4.1–S4.3, supporting information*. For all three PEM coatings excellent NF performance is observed, a large improvement compared to just the support membrane. However, the three different polyelectrolyte systems do show varying PWP and MWCO values, in accordance with the previous studies [31]. The PWP of PSS-PAH_(4.5) and PSS-PDADMAC_(4.5) coated membranes was almost similar i.e. $\sim 1.7 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. On the other hand, the PSS-PEI_(4.5) membranes showed a lower PWP of $\sim 1.4 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. Such a trend is observed because the PSS-PEI multilayer membranes are known to be denser than PSS-PDADMAC and PSS-PAH [33]. For branched PEI the charge density is higher than that of PDADMAC and PAH. Consequently, the number of ion pairs per number of carbon atoms in the resulting polyelectrolyte complex is higher for PSS-PEI_(4.5) as compared to the rest. A higher charge density leading to a higher density of ionic crosslinks, coupled with lower excess charge as described in the introduction, usually results in a lower permeation rate [40]. The dense nature of PSS-PEI_(4.5) was also confirmed by the MWCO of these PEM membranes. The MWCO of the relatively less dense PSS-PAH_(4.5) and PSS-PDADMAC_(4.5) was estimated to be $\sim 392 \pm 6$ Da and $\sim 384 \pm 3$ Da, see *Figure S4.4a, b in supporting information*. In comparison, the dense PSS-PEI_(4.5) membranes showed a MWCO of $\sim 205 \pm 4$, *Figure S4.4c*.

The separation performance of the membranes prepared in this work is compared to the commercial membranes in terms of their PWP and the NaCl retention and is presented in *Table S4.1, supporting information*. The water permeabilities of the APS support membranes ($\sim 2 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) and the PEM membranes reported here are relatively lower as compared to most commercial membranes used for nanofiltration applications. This is indeed a current limitation of the APS membranes and future efforts could be devoted towards increasing the PWP of the support membranes. One possible way is to utilize additives such as polyethylene glycol (PEG) in the polyelectrolyte casting solution which is also commonly used for NIPS membranes as pore former [41]. Nevertheless, the sustainable APS membrane supports show decent salt selectivity while facilitating the PEM formation due to their inherent surface charge.

Figure 4.3b shows the retention of four different types of salts by the support membrane and the different PEM membranes. The salts that were used for the retention measurements contain both monovalent and divalent anions/cations which can also give a fair indication of the charge in the bulk of PEM membranes. As expected, the support membrane showed negligible ($<10\%$) retention of the four types of salts. For the PEM membranes, the retention trend follows the permeability data such that the membranes with lower water permeability showed the higher retentions. PSS-PEI_(4.5) showed the highest retention for all four types of salts because of its dense nature. The higher retention of MgCl_2 as compared to the other salts is due to the net positive charge on the PEM membrane surfaces which was confirmed by measuring the surface streaming potential of these membranes. PSS-PAH_(4.5) membranes had a streaming potential of $\sim 9 \pm 0.4 \text{ mV}$, PSS-PDADMAC_(4.5) $\sim 9 \pm 0.2 \text{ mV}$, and PSS-PEI_(4.5) $\sim 4 \pm 0.7 \text{ mV}$. The salt retention results indicate that the separation mechanism is most likely to be a combination of the size exclusion and Donnan exclusion mechanisms. A positively charged membrane will repel the cations and attract the anions based on the Donnan exclusion mechanism [42]. The higher rejection of divalent cation Mg^{2+} and a lower rejection of divalent anion SO_4^{2-} is then expected. Looking at the streaming potentials of the three type of membranes, it can be observed that PSS-PEI_(4.5) has relatively lower charge of $\sim 4 \text{ mV}$ as compared to the other two systems. This confirms our earlier statement that PSS-PEI_(4.5) has the highest number of ion pairs per number of carbon atoms among the three PEMs resulting in less overall charge and also a more dense layer. The results clearly indicate that coating a thin layer of PEM on top of the APS membranes can lead to the formation of excellent nanofiltration type membranes. The versatility of the LBL approach allows further optimization of the membranes' separation performance by simply tuning the number of bilayers, salt concentration, and the pH of the coating solutions.

To further quantify the nanofiltration separation performance of the PEM membranes, a mixture of eight different types of micropollutants was prepared and filtered through the membranes, see *Figure S4.5 in the supporting information* for the chemical structures of these micropollutants. These micropollutants are mostly pesticides, pharmaceuticals, and plasticizers and are most commonly found in rivers and other ground water sources [43]. The mixture contains both hydrophilic/hydrophobic and charged/uncharged molecules with molecular weights in the range of 200 Da to 700 Da. **Table 4.1** presents the micropollutant retentions of the PEM membranes studied in this work.

As expected, the neutral molecules like Atrazine, Bisphenol-A, Phenolphthalein, and Bromothymol blue are highly rejected based on their sizes according to the MWCO of the PEM membranes. Bromothymol blue, being the largest molecule (Mw $\sim 624 \text{ Da}$) is completely retained

Table 4.1 Micropollutant retentions of the PEM membranes. The concentration of the mixture was $3 \text{ mg}\cdot\text{L}^{-1}$ of each compound and the pH was adjusted to 5.8.

Micropollutant	Mw (Da)	Charge	Retention (%)		
			PSS-PAH _(4.5)	PSS-PDADMAC _(4.5)	PSS-PEI _(4.5)
Atenolol	267	+	60	97	97
Atrazine	216	0	50	62	90
Bisphenol-A	228	0	50	53	92
Phenolphthalein	318	0	75	87	97
Bromothymol blue	624	0	100	100	100
Sulfamethoxazole	253	0/-	26	30	56
Naproxen	229	-	94	95	97
Bezafibrate	361	-	89	89	99

by the membranes, also demonstrating that all three membrane types are defect free. The positively charged Atenolol shows higher retentions because of the positively charged membrane surface. Overall, the PSS-PAH_(4.5) shows an average micropollutant retention of $\sim 68\%$, PSS-PDADMAC_(4.5) $\sim 77\%$, and PSS-PEI_(4.5) $\sim 91\%$. The results also suggest that the separation of the organic micropollutant is not governed only by size exclusion and Donnan exclusion mechanisms, steric hindrance and dielectric effects are also known to affect the retentions in typical nanofiltration membranes [44]. The separation is likely based on a combination of these mechanisms.

It can certainly be concluded that by only coating 4.5 bilayers of PEMs, the otherwise open nanofiltration type APS membrane can be made into a dense nanofiltration type. The real advantage is that the PEMs can be applied without any pre-treatment due to the natural charge of the APS support membranes which facilitates the adsorption of polyelectrolytes for the multilayer buildup. These results also suggest that PSS-PAH based APS membranes can be effectively used as supports to build PEMs based membranes with excellent separation properties. It is also pertinent to mention that the aim of this work was not to obtain the best performing PEM membranes but to show that APS membranes, just like NIPS membranes, can be excellent support membranes for functional coatings.

4.3.2 Interfacial Polymerization

Interfacial polymerization was carried out on the ultrafiltration type PSS-PAH membranes having an average pore size of $\sim 4.5 \text{ nm}$, calculated in **Chapter 2**. The existence of the IP coated polyamide layer was confirmed by FTIR spectra shown in **Figure 4.4**.

In case of the PSS-PAH support membrane, the sharp absorbance bands at 1008 cm^{-1} , 1036 cm^{-1} , 1123 cm^{-1} , and the overlapping bands at 1180 cm^{-1} and 1208 cm^{-1} are assigned to the S=O stretching modes in PSS [45]. Other characteristic peaks of PSS appear at 1601 cm^{-1} , 1495 cm^{-1} , 1453 cm^{-1} , and 1411 cm^{-1} all of which are assigned to the aromatic --C=C-- stretching. The

Figure 4.4 FTIR spectra of the ultrafiltration type PSS-PAH support and the IP coated thin film composite (TFC) membrane. The appearance of absorbance bands at 1545 cm^{-1} , 1611 cm^{-1} , and 1660 cm^{-1} confirm the presence of polyamide in TFC membranes.

relatively less prominent peaks observed in the IR spectra of the support membranes at 1603 cm^{-1} and 1522 cm^{-1} can be assigned to asymmetric and symmetric vibrations of $-\text{NH}_3^+$, respectively [46].

The FTIR spectra of the IP coated TFC membrane showed additional bands at 1660 cm^{-1} (C=O stretching vibrations in amide I), 1611 cm^{-1} (aromatic ring breathing, N-H bending/stretching, amide II), and 1545 cm^{-1} (C-N stretching of amide), all of which are characteristic polyamide bands [47]. The FTIR spectra reveals that the PSS-PAH support membranes are indeed coated with a thin layer of polyamide.

The SEM images of the pristine support membrane and the TFC membrane are shown in **Figure 4.5**. Comparing SEM images in **Figure 4.5a** and **b**, it can be seen that the TFC membrane had a slightly rough top surface with a typical leaf-like morphology that is most associated with a polyamide layer [48].

The difference between the pristine support and the TFC membrane is evident by looking at the cross-section SEM images in **Figure 4.5**. The PSS-PAH support membrane shows an asymmetric structure with the pore size getting larger as you move from top to bottom of the cross-section, see **Figure 4.5c**. On the other hand, the TFC membrane has a relatively denser and more closed structure at the given magnification, **Figure 4.5d**. This indicates that the polyamide layer has reduced the pore size and/or completely closed the pores near to the membrane top surface. This happens because upon immersing the porous support membrane in the MPD solution, the near surface pores are completely filled with the aqueous solution. The MPD molecules remain inside the pores even after drying with a rubber roller. When the support is subsequently immersed

Figure 4.5 Top surface and cross-section SEM images of the APS support membrane (a) (c), and IP coated membrane (b) (d).

in the organic TMC solution, the MPD molecules diffuse towards the organic front because of their higher solubility in organic solvent and immediately react with TMC to form a polyamide nuclei. The newly formed nuclei grows laterally until it combines with other nuclei to form a polyamide layer [12]. The diffusion of MPD molecules and the subsequent reaction with TMC gives rise to the typical leaf-like morphology associated with the polyamide layer.

The charge on the TFC membrane surface was determined to be approximately -35 ± 0.5 mV at pH 6. The polyamide layer is negatively charged because of the dissociation of the carboxyl groups [49]. The negatively charged TFC membrane is thus expected to have high retentions of divalent anions.

The pure water permeability at 4 bar of applied water pressure was measured for the TFC membrane. In comparison with the support membrane, which had a permeability of $\sim 12.5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, the TFC membranes showed significantly lower water permeability of $\sim 1.1 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. This is fully expected behavior because the TFC membrane is significantly denser than the support membrane and therefore there is higher resistance to the passage of water, see **Figure 4.5c, d**. The MWCO of the IP coated TFC membranes was measured to be $\sim 200 \pm 3$ Da.

The nanofiltration performance of the membrane was determined by filtering four different types of salt solutions and the retentions are showed in **Figure 4.6**. As expected for a negatively charged dense membrane, the rejection of Na_2SO_4 is the highest i.e. $\sim 86\%$. MgSO_4 and MgCl_2 are $\sim 77.5\%$ and $\sim 70\%$ retained by the TFC membrane. The least rejection was of NaCl , which was only $\sim 58\%$ retained. The retentions of salts are in accordance with the Donnan exclusion

Figure 4.6 Salt retentions of the TFC membranes. Retention tests were conducted using 5 mM salt solution at a feed pressure of 4 bar.

mechanism. A thin polyamide coating successfully transformed an ultrafiltration type membrane into dense nanofiltration type membrane.

The major difference between the LBL approach for PEM assembly and the IP in this work is the thickness and density of the final surface coating. Most IP coatings are known to be ~ 100 nm – 300 nm thick [50] but PEM coatings are typically thinner, ~ 50 nm. A thicker selective layer increases the resistance for the water molecules consequently resulting in lower pure water permeabilities as observed for the TFC membranes in this work. Both the PEM and IP coatings have advantages and disadvantages. The coating process is longer in PEMs while IP is fairly easy and takes considerably less time and is still the preferred option for commercial applications. Additionally, the excess amine groups in the APS support membrane could covalently bind the IP layer for better adhesion. In this work, we have added APS membranes to the list of supports that can be used to perform functional coatings without any pre-treatment process. Future efforts could also be devoted towards developing and optimizing these coatings for reverse osmosis and gas separation applications using the sustainably produced APS membranes as the support.

4.4 Conclusions

For the first time, we have successfully demonstrated that APS based membranes can act as excellent supports for fabricating nanofiltration type membranes with thin selective top layers. Polyelectrolyte multilayer (PEM) assembly and interfacial polymerization (IP) was employed to fabricate thin films on the surface of PSS-PAH APS membranes. The APS membranes were used as supports to coat different multilayers composed of three pairs of polyelectrolytes i.e. PSS-

PAH, PSS-PDADMAC, and PSS-PEI. The results revealed that by simply coating 4.5 bilayers of PEM, the APS support membranes can be transformed into nanofiltration type membranes with excellent salt retentions and water permeabilities. The membranes coated using PSS-PAH had a molecular weight cut-off (MWCO) of ~ 392 Da while those prepared using PSS-PDADMAC had MWCO of ~ 384 Da. These membranes showed decent rejections of salts e.g. $>90\%$ MgCl_2 rejections. The PSS-PEI membranes were found to have the densest top layers with a molecular weight cut-off of ~ 205 Da and rejected $\sim 98\%$ MgCl_2 with rejections organic micropollutants in excess of 90% . The IP coating was also very successful in transforming the ultrafiltration type PSS-PAH APS membranes into nanofiltration type ones. The resulting thin film composite membranes had a significantly denser structure and lower MWCO of ~ 200 Da with good retentions of salts. The APS support membranes even have natural advantages: their charge allows for easy application of PEMs while the used primary amines allows covalent bonding of the IP layer. Here we also show that the properties of APS membranes can be further fine-tuned to obtain desirable separation performances.

Acknowledgements

This work was supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (ERC StG 714744 SAMBA). WdV and JDW acknowledge funding support from the "Vernieuwingsimpuls" programme through project VIDI 723.015.003 (financed by the Netherlands Organization for Scientific Research, NWO).

4.5 Supporting Information – S4

Figure S4.1 a) Pure water permeability and b) salt retentions of the PSS-PAH multilayer membranes showing the effect of number of bilayers on the membrane permeability and salt retentions.

Figure S4.2 a) Pure water permeability and b) salt retentions of the PSS-PDADMAC multilayer membranes showing the effect of number of bilayers on the membrane permeability and salt retentions.

Figure S4.3 a) Pure water permeability and b) salt retentions of the PSS-PEI multilayer membranes showing the effect of number of bilayers on the membrane permeability and salt retentions.

Figure S4.4 Sieving curves obtained by gel permeation chromatography showing the retention of Polyethylene glycol (PEG) as a function of its molecular weight for three types of multilayer coatings. a) PSS-PAH_(4.5), PSS-PDADMAC_(4.5), and PSS-PEI_(4.5). The molecular weight cut-off was estimated by taking the 90th percentile of the maximum retention obtained.

Figure S4.5 Chemical structures and molecular weights of the eight types of micropollutants used in this work.

Table S4.1 Comparison of pure water permeability and retention of NIPS based commercial membranes with APS membranes coated in this work.

Membrane	Material	Manufacturer	Pure water permeability ($\text{L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$)	NaCl retention (%)	Reference
NF270	Polyamide TFC	Dow Filmtec	11	80	Dang <i>et al.</i> [a]
TFC-HR	Polyamide TFC	Koch	3.5	99	Xu <i>et al.</i> [b]
XLE	Polyamide TFC	Dow Filmtec	9	99	Xu <i>et al.</i> [b]
SC-3100	Ceullulose acetate	Toray	1.3	94	Kimura <i>et al.</i> [c]
NF90	Polyamide TFC	Dow Filmtec	6	93	Yüksel <i>et al.</i> [d]
Desal HL	Polyamide TFC	GE Osmonics	10.5	55	Caus <i>et al.</i> [e]
APS IP	Polyamide TFC	This work	1.1	58	This work
APS PEM	PSS-PAH	This work	1.7	58	This work
	PSS-PDADMAC	This work	1.7	64	This work
	PSS-PEI	This work	1.4	70	This work

References – Supporting information – S4

- [a] H.Q. Dang, W.E. Price, L.D. Nghiem, The effects of feed solution temperature on pore size and trace organic contaminant rejection by the nanofiltration membrane NF270, *Sep. Purif. Technol.* 125 (2014) 43–51. doi.org/10.1016/j.seppur.2013.12.043.
- [b] P. Xu, J.E. Drewes, C. Bellona, G. Amy, T.-U. Kim, M. Adam, T. Heberer, Rejection of emerging organic micropollutants in nanofiltration-reverse osmosis membrane applications., *Water Environ. Res. a Res. Publ. Water Environ. Fed.* 77 (2005) 40–48. doi:10.2175/106143005x41609.
- [c] K. Kimura, S. Toshima, G. Amy, Y. Watanabe, Rejection of neutral endocrine disrupting compounds (EDCs) and pharmaceutical active compounds (PhACs) by RO membranes, *J. Memb. Sci.* 245 (2004) 71–78. doi.org/10.1016/j.memsci.2004.07.018.
- [d] S. Yüksel, N. Kabay, M. Yüksel, Removal of bisphenol A (BPA) from water by various nanofiltration (NF) and reverse osmosis (RO) membranes, *J. Hazard. Mater.* 263 (2013) 307–310. doi:10.1016/j.jhazmat.2013.05.020.
- [e] A. Caus, S. Vanderhaegen, L. Braeken, B. Van der Bruggen, Integrated nanofiltration cascades with low salt rejection for complete removal of pesticides in drinking water production, *Desalination.* 241 (2009) 111–117. doi:10.1016/j.desal.2008.01.061.

4.6 References

- [1] S.P. Nunes, P.Z. Culfaz-Emecen, G.Z. Ramon, T. Visser, G.H. Koops, W. Jin, M. Ulbricht, Thinking the future of membranes: Perspectives for advanced and new membrane materials and manufacturing processes, *J. Memb. Sci.* 598 (2020) 117761. doi:10.1016/j.memsci.2019.117761.
- [2] D. Kim, S.P. Nunes, Green solvents for membrane manufacture: Recent trends and perspectives, *Curr. Opin. Green Sustain. Chem.* 28 (2021) 100427. doi:10.1016/j.cogsc.2020.100427.
- [3] J. D. Willott, W. M. Nielen, W. M. de Vos, Stimuli-Responsive Membranes through Sustainable Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2019) 659–667. doi:10.1021/acsapm.9b01006.
- [4] W.M. Nielen, J.D. Willott, W.M. de Vos, Aqueous Phase Separation of Responsive Copolymers for Sustainable and Mechanically Stable Membranes, *ACS Appl. Polym. Mater.* 2 (2020) 1702–1710. doi:10.1021/acsapm.0c00119.
- [5] K. Sadman, D.E. Delgado, Y. Won, Q. Wang, K.A. Gray, K.R. Shull, Versatile and High-Throughput Polyelectrolyte Complex Membranes via Phase Inversion, *ACS Appl. Mater. Interfaces.* 11 (2019) 16018–16026. doi:10.1021/acsami.9b02115.
- [6] E. N. Durmaz, M. I. Baig, J. D. Willott, W. M. de Vos, Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 2612–2621. doi:10.1021/acsapm.0c00255.
- [7] J. Kamp, S. Emonds, J. Borowec, M.A. Restrepo Toro, M. Wessling, On the organic solvent free preparation of ultrafiltration and nanofiltration membranes using polyelectrolyte complexation in an all aqueous phase inversion process, *J. Memb. Sci.* 618 (2021). doi:10.1016/j.memsci.2020.118632.
- [8] M.I. Baig, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.
- [9] M.I. Baig, J.D. Willott, W.M. de Vos, Tuning the structure and performance of polyelectrolyte complexation based aqueous phase separation membranes, *J. Memb. Sci.* 615 (2020) 118502. doi:10.1016/j.memsci.2020.118502.
- [10] E.N. Durmaz, J.D. Willott, A. Fatima, W.M. de Vos, Weak polyanion and strong polycation complex based membranes: Linking aqueous phase separation to traditional membrane fabrication, *Eur. Polym. J.* 139 (2020) 110015. doi.org/10.1016/j.eurpolymj.2020.110015.
- [11] M.O. Mavukkandy, S.A. McBride, D.M. Warsinger, N. Dizge, S.W. Hasan, H.A. Arafat, Thin film deposition techniques for polymeric membranes– A review, *J. Memb. Sci.* 610 (2020) 118258. doi:10.1016/j.memsci.2020.118258.
- [12] A.K. Ghosh, B.H. Jeong, X. Huang, E.M.V. Hoek, Impacts of reaction and curing conditions on polyamide composite reverse osmosis membrane properties, *J. Memb. Sci.* 311 (2008) 34–45. doi:10.1016/j.memsci.2007.11.038.

- [13] B.-H. Jeong, E.M.V. Hoek, Y. Yan, A. Subramani, X. Huang, G. Hurwitz, A.K. Ghosh, A. Jawor, Interfacial polymerization of thin film nanocomposites: A new concept for reverse osmosis membranes, *J. Memb. Sci.* 294 (2007) 1–7. doi:10.1016/j.memsci.2007.02.025.
- [14] J. Wei, X. Liu, C. Qiu, R. Wang, C.Y. Tang, Influence of monomer concentrations on the performance of polyamide-based thin film composite forward osmosis membranes, *J. Memb. Sci.* 381 (2011) 110–117. doi:10.1016/j.memsci.2011.07.034.
- [15] Y. Song, P. Sun, L. Henry, B. Sun, Mechanisms of structure and performance controlled thin film composite membrane formation via interfacial polymerization process, *J. Memb. Sci.* 251 (2005) 67–79. doi:10.1016/j.memsci.2004.10.042.
- [16] J.M. Gohil, P. Ray, A review on semi-aromatic polyamide TFC membranes prepared by interfacial polymerization: Potential for water treatment and desalination, *Sep. Purif. Technol.* 181 (2017) 159–182. doi:10.1016/j.seppur.2017.03.020.
- [17] C.W. Tsai, C. Tsai, R.C. Ruaan, C.C. Hu, K.R. Lee, Interfacially polymerized layers for oxygen enrichment: A method to overcome Robeson's upper-bound limit, *ACS Appl. Mater. Interfaces.* 5 (2013) 5563–5568. doi:10.1021/am4008006.
- [18] J. Lee, C.M. Doherty, A.J. Hill, S.E. Kentish, Water vapor sorption and free volume in the aromatic polyamide layer of reverse osmosis membranes, *J. Memb. Sci.* 425–426 (2013) 217–226. doi:10.1016/j.memsci.2012.08.054.
- [19] Z. Yao, H. Guo, Z. Yang, C. Lin, B. Zhu, Y. Dong, C.Y. Tang, Reactable substrate participating interfacial polymerization for thin film composite membranes with enhanced salt rejection performance, *Desalination.* 436 (2018) 1–7. doi:10.1016/j.desal.2018.01.039.
- [20] X. Li, Q. Li, W. Fang, R. Wang, W.B. Krantz, Effects of the support on the characteristics and permselectivity of thin film composite membranes, *J. Memb. Sci.* 580 (2019) 12–23. doi:10.1016/j.memsci.2019.03.003.
- [21] P. Karami, B. Khorshidi, M. McGregor, J.T. Peichel, J.B.P. Soares, M. Sadrzadeh, Thermally stable thin film composite polymeric membranes for water treatment: A review, *J. Clean. Prod.* 250 (2020). doi:10.1016/j.jclepro.2019.119447.
- [22] G. Decher, Fuzzy Nanoassemblies: Toward Layered Polymeric Multicomposites, *Science* (80). 277 (1997) 1232–1237. doi:10.1126/science.277.5330.1232.
- [23] J.B. Schlenoff, S.T. Dubas, Mechanism of polyelectrolyte multilayer growth: Charge overcompensation and distribution, *Macromolecules.* 34 (2001) 592–598. doi:10.1021/ma0003093.
- [24] N. Joseph, P. Ahmadiannamini, R. Hoogenboom, I.F.J. Vankelecom, Layer-by-layer preparation of polyelectrolyte multilayer membranes for separation, *Polym. Chem.* 5 (2014) 1817–1831. doi:10.1039/c3py01262j.
- [25] K. Ariga, J.P. Hill, Q. Ji, Layer-by-layer assembly as a versatile bottom-up nanofabrication technique for exploratory research and realistic application, *Phys. Chem. Chem. Phys.* 9 (2007) 2319–2340. doi:10.1039/b700410a.

- [26] X. Li, C. Liu, B. Van Der Bruggen, Polyelectrolytes self-Assembly: Versatile membrane fabrication strategy, *J. Mater. Chem. A* 8 (2020) 20870–20896. doi:10.1039/d0ta07154d.
- [27] L.Y. Ng, A.W. Mohammad, C.Y. Ng, C.P. Leo, R. Rohani, Development of nanofiltration membrane with high salt selectivity and performance stability using polyelectrolyte multilayers, *Desalination* 351 (2014) 19–26. doi:10.1016/j.desal.2014.07.020.
- [28] N. Joseph, P. Ahmadiannamini, R. Hoogenboom, I.F.J. Vankelecom, Layer-by-layer preparation of polyelectrolyte multilayer membranes for separation, *Polym. Chem.* 5 (2014) 1817–1831. doi:10.1039/c3py01262j.
- [29] J. Schmitt, T. Grünewald, G. Decher, P.S. Pershan, K. Kjaer, M. Lösche, Internal Structure of Layer-by-Layer Adsorbed Polyelectrolyte Films: A Neutron and X-ray Reflectivity Study, *Macromolecules* 26 (1993) 7058–7063. doi:10.1021/ma00077a052.
- [30] W. Shan, P. Bacchin, P. Aimar, M.L. Bruening, V. V Tarabara, Polyelectrolyte multilayer films as backflushable nanofiltration membranes with tunable hydrophilicity and surface charge, *J. Memb. Sci.* 349 (2010) 268–278. doi:10.1016/j.memsci.2009.11.059.
- [31] S.U. Hong, R. Malaisamy, M.L. Bruening, Optimization of flux and selectivity in $\text{Cl}^-/\text{SO}_4^{2-}$ separations with multilayer polyelectrolyte membranes, *J. Memb. Sci.* 283 (2006) 366–372. doi:10.1016/j.memsci.2006.07.007.
- [32] S.U. Hong, L. Ouyang, M.L. Bruening, Recovery of phosphate using multilayer polyelectrolyte nanofiltration membranes, *J. Memb. Sci.* 327 (2009) 2–5. doi:10.1016/j.memsci.2008.11.035.
- [33] D.M. Reurink, J.D. Willott, H.D.W. Roesink, W.M. De Vos, Role of Polycation and Crosslinking in Polyelectrolyte Multilayer Membranes, *ACS Appl. Polym. Mater.* 2 (2020) 5278–5289. doi:10.1021/acsapm.0c00992.
- [34] R.M. DuChanois, R. Epsztein, J.A. Trivedi, M. Elimelech, Controlling pore structure of polyelectrolyte multilayer nanofiltration membranes by tuning polyelectrolyte-salt interactions, *J. Memb. Sci.* 581 (2019) 413–420. doi:10.1016/j.memsci.2019.03.077.
- [35] S. Ilyas, S.M. Abtahi, N. Akkiliç, H.D.W. Roesink, W.M. de Vos, Weak polyelectrolyte multilayers as tunable separation layers for micro-pollutant removal by hollow fiber nanofiltration membranes, *J. Memb. Sci.* 537 (2017) 220–228. doi.org/10.1016/j.memsci.2017.05.027.
- [36] E. te Brinke, I. Achterhuis, D.M. Reurink, J. de Groot, W.M. de Vos, Multiple Approaches to the Buildup of Asymmetric Polyelectrolyte Multilayer Membranes for Efficient Water Purification, *ACS Appl. Polym. Mater.* 2 (2020) 715–724. doi:10.1021/acsapm.9b01038.
- [37] Y. Chen, F. Xiangli, W. Jin, N. Xu, Streaming potential characterization of LBL membranes on porous ceramic supports, *AIChE J.* 53 (2007) 969–977. doi.org/10.1002/aic.11126.
- [38] T. Ormanci-Acar, M. Mohammadifakhr, N.E. Benes, W.M. de Vos, Defect free hollow fiber reverse osmosis membranes by combining layer-by-layer and interfacial polymerization, *J. Memb. Sci.* 610 (2020) 118277. doi:10.1016/j.memsci.2020.118277.
- [39] S.U. Hong, M.D. Miller, M.L. Bruening, Removal of dyes, sugars, and amino acids from NaCl

solutions using multilayer polyelectrolyte nanofiltration membranes, *Ind. Eng. Chem. Res.* 45 (2006) 6284–6288. doi:10.1021/ie060239+.

[40] L. Krasemann, B. Tieke, Selective ion transport across self-assembled alternating multilayers of cationic and anionic polyelectrolytes, *Langmuir*. 16 (2000) 287–290. doi:10.1021/la991240z.

[41] R.M. Boom, I.M. Wienk, T. van den Boomgaard, C.A. Smolders, Microstructures in phase inversion membranes. Part 2. The role of a polymeric additive, *J. Memb. Sci.* 73 (1992) 277–292. doi.org/10.1016/0376-7388(92)80135-7.

[42] F.G. Donnan, Theory of membrane equilibria and membrane potentials in the presence of non-dialysing electrolytes. A contribution to physical-chemical physiology, *J. Memb. Sci.* 100 (1995) 45–55. doi:10.1016/0376-7388(94)00297-C.

[43] A. Verliefde, E. Cornelissen, G. Amy, B. Van der Bruggen, H. van Dijk, Priority organic micropollutants in water sources in Flanders and the Netherlands and assessment of removal possibilities with nanofiltration, *Environ. Pollut.* 146 (2007) 281–289. doi:10.1016/j.envpol.2006.01.051.

[44] A. Anand, B. Unnikrishnan, J.Y. Mao, H.J. Lin, C.C. Huang, Graphene-based nanofiltration membranes for improving salt rejection, water flux and antifouling—A review, *Desalination*. 429 (2018) 119–133. doi:10.1016/j.desal.2017.12.012.

[45] N.L. Benbow, J.L. Webber, P. Pawliszak, D.A. Sebben, T.T.M. Ho, J. Vongsivut, M.J. Tobin, M. Krasowska, D.A. Beattie, A Novel Soft Contact Piezo-Controlled Liquid Cell for Probing Polymer Films under Confinement using Synchrotron FTIR Microspectroscopy, *Sci. Rep.* 8 (2018) 17804. doi:10.1038/s41598-018-34673-4.

[46] K. Itano, J. Choi, M.F. Rubner, Mechanism of the pH-Induced Discontinuous Swelling/Deswelling Transitions of Poly(allylamine hydrochloride)-Containing Polyelectrolyte Multilayer Films, *Macromolecules*. 38 (2005) 3450–3460. doi:10.1021/ma047667g.

[47] A.P. Rao, S. V. Joshi, J.J. Trivedi, C. V. Devmurari, V.J. Shah, Structure-performance correlation of polyamide thin film composite membranes: Effect of coating conditions on film formation, *J. Memb. Sci.* 211 (2003) 13–24. doi:10.1016/S0376-7388(02)00305-8.

[48] C.Y. Tang, Y.N. Kwon, J.O. Leckie, Effect of membrane chemistry and coating layer on physiochemical properties of thin film composite polyamide RO and NF membranes. I. FTIR and XPS characterization of polyamide and coating layer chemistry, *Desalination*. 242 (2009) 149–167. doi:10.1016/j.desal.2008.04.003.

[49] S. Liu, C. Wu, W.S. Hung, X. Lu, K.R. Lee, One-step constructed ultrathin Janus polyamide nanofilms with opposite charges for highly efficient nanofiltration, *J. Mater. Chem. A*. 5 (2017) 22988–22996. doi:10.1039/c7ta07582k.

[50] P. Veerababu, B.B. Vyas, P.S. Singh, P. Ray, Limiting thickness of polyamide-polysulfone thin-film-composite nanofiltration membrane, *Desalination*. 346 (2014) 19–29. doi:10.1016/j.desal.2014.05.007.

“Somewhere, something incredible is waiting to be known.”

- Carl Sagan

Chapter 5.

Sustainable Aqueous Phase Separation Membranes Prepared through mild pH shift induced Polyelectrolyte Complexation of PSS and PEI

This chapter is published as:

M.I. Baig, P.P.I. Sari, J. Li, J.D. Willott, W.M. de Vos, Sustainable Aqueous Phase Separation membranes prepared through mild pH shift induced polyelectrolyte complexation of PSS and PEI, *J. Memb. Sci.* 625 (2021) 119114. doi:10.1016/j.memsci.2021.119114.

Abstract

pH-shift induced Aqueous phase separation (APS) is a novel and more sustainable water-based approach to create microfiltration, ultrafiltration, and nanofiltration membranes. APS allows for control over membrane pore size and structure in ways analogous to traditional non-solvent induced phase separation (NIPS). Unfortunately, existing APS approaches require extreme pH shifts (from pH 14 to pH 1) to obtain successful membranes, limiting their applicability for large scale production. Here we demonstrate that APS membranes, with tunable pore sizes ranging from ~ 80 nm to dense nanofiltration type, can be prepared using a mild pH shift (pH 12 to pH 4) based on the complexation of poly(styrene sulfonate) (PSS) and branched polyethyleneimine (PEI) in acetate buffer coagulation baths. The molecular weight of PEI, the concentration and the pH value of the buffer solution, and the concentration of glutaraldehyde crosslinking agent were systematically varied to control and optimize the membrane fabrication conditions. It was found that tight nanofiltration membranes having a molecular weight cut-off of ~ 200 g $\cdot$ mol $^{-1}$ and excellent salt (97% MgCl $_2$) and micropollutant retentions ($\sim 96\%$) could be prepared alongside ultra/microfiltration type membranes with an average pore size of ~ 60 nm. These results indicate that APS membranes with tunable pore sizes can be prepared under mild pH conditions with excellent control over separation properties.

5.1 Introduction

Non-solvent induced phase separation, commonly referred to as NIPS, is by far the most commonly employed technique to prepare polymeric membranes. It is a versatile technique that allows the production of various different types of membranes in a simple one-step process whereby a liquid polymer solution is transformed into a solid porous membrane via controlled precipitation [1]. The phase separation rate can be controlled to obtain different membrane morphologies. A slower precipitation rate typically leads to the formation of sponge-like structures with dense top layers that exhibit high salt retentions and low water fluxes. On the other hand, a faster precipitation rate typically results in asymmetric membranes having macrovoids and more porous top layers that show high water fluxes [2]. In addition, the polymer concentration of the casting/dope solution along with the coagulation bath conditions dictate the final structure of the membranes. A higher polymer concentration increases the solution's viscosity thereby slowing down the precipitation rate resulting in denser membranes [3]. The wide range of polymers available and numerous tuning parameters means that membranes for microfiltration, ultrafiltration, nanofiltration, reverse osmosis, and gas separation can be produced using NIPS [4]. Such proven control over the pore size and structure enabled NIPS to be the foremost and preferred technique for commercial polymeric membrane production.

A major downside of NIPS is that the most commonly used solvent in this technique, *N*-methylpyrrolidone (NMP), has been proven to be reprotoxic [5]. Consequently, NMP has been restricted for use in the European Union through the Regulation (EC) No. (EU) 2018/588 of the European Parliament and the Council on the Registration, Evaluation, Authorization, and Restriction of Chemicals (REACH) [6,7]. The search for greener solvents for membrane fabrication predates the EU restriction. In 2014 Figoli *et al.* reviewed several alternate solvents that have been used to produce NIPS and thermally induced phase separation (TIPS) membranes [8–10]. Some of these 'green' solvents include CyreneTM, ionic liquids, ethyl lactate, and super

critical CO₂. However, tuning the pore size of the membrane for desired application still remained a major challenge. A different approach was first introduced by de Vos that utilized water as a solvent to prepare Aqueous Phase Separation (APS) membranes using polyelectrolytes [11]. Polyelectrolytes are polymers that carry a charge on their repeating unit along with small counter-ions. As a result, the polyelectrolytes are readily soluble in water. De Vos demonstrated that a weak polyelectrolyte such as poly(4-vinylpyridine), which is soluble in water only at low pH conditions can be precipitated at high pH conditions to form porous films [11]. However these membranes exhibited limited mechanical stability and relatively poor control over the pore size [12]. Another interesting approach was polyelectrolyte complex (PEC) membranes, where a casting solution of a weak and strong polyelectrolyte was precipitated in coagulation baths at low pH conditions to obtain porous membranes [11]. A PEC is formed when two oppositely charged polyelectrolytes are mixed together whereby the driving force for complexation is provided by the entropy gain due to the release of the counter-ions [13,14]. Polyelectrolytes have long been used to prepare PEC membranes and free-standing capsules and their numerous applications have been reported in literature [15–17]. In earlier chapters, we have demonstrated the versatility of APS method by fabricating microfiltration, ultrafiltration, and nanofiltration PEC membranes. In that version of APS, a homogeneous solution of a strong polyelectrolyte poly(sodium 4-styrenesulfonate) PSS, and a weak polyelectrolyte poly(allylamine hydrochloride) (PAH) was prepared at $\sim$ pH 14 and precipitated in a $\sim$ pH 1 coagulation bath. Several parameters such as the molecular weight of the polyelectrolytes, solution concentration, pH of the bath, salinity of the bath, and the amount of crosslinker can be tuned to obtain desirable membrane pore sizes [18,19]. However, the extreme pH conditions required to prepare the PSS-PAH membranes are far from ideal for larger scale membrane production as they can for example lead to corrosion of the equipment. One attempt to resolve this problem is a salinity change induced APS, where the casting solution, composed of two polyelectrolytes dissolved at high salt concentrations, is precipitated in deionized water (or even tap water) to obtain PEC membranes [20–22]. Salinity change induced APS is indeed a promising alternate to the pH switch induced APS, however, in one version it gives limited control over the membrane pore size in addition to low water permeabilities [21,22], and in another version it is rather laborious [20]. A truly sustainable alternative to NIPS that has the similar control over the membrane pore size still remains a major challenge.

In this work, we demonstrate that pH switch induced APS is possible at much milder pH conditions, while retaining excellent control over pore size and membrane structure. Here, the weak polycation polyethyleneimine (PEI) is used in its branched form in combination with the strong polyanion PSS. The combination of PSS and PEI has already been successfully applied as polyelectrolyte multilayer coatings on polymeric support membranes for nanofiltration applications [23,24]. PSS-PEI multilayer coated membranes have shown excellent divalent ion retentions with a water permeability of $\sim 5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ [24]. Herein, we demonstrate that PSS-PEI solutions can be mixed directly without any additives (i.e. no added base) to form a homogeneous casting solutions, which can subsequently be cast as thin films and precipitated in much less extreme pH (3.6 – 5) acetate buffer baths to obtain PEC membranes. The molecular weight of PEI, the concentration and pH value of the acetate buffer, as well as the concentration of the crosslinking agent were all varied in order to study their effect on membrane structure and morphology. These parameters were fine-tuned and allowed for control over the pore size of the membranes. The findings of this work offer insight into the PSS-PEI system as one of the

most promising APS approaches for the production of a wide variety of sustainable membranes.

5.2 Experimental Section

5.2.1 Materials

Poly(sodium 4-styrene sulfonate) (PSS, Mw $\sim$ 1000 kDa) was purchased from Sigma-Aldrich (Netherlands) as 25 wt% aqueous solution. Branched Polyethyleneimine (PEI) was purchased from Sigma-Aldrich (Netherlands) as 50 wt% aqueous solution (Mw $\sim$ 750 kDa) and >99 wt% (Mw $\sim$ 25 kDa). The chemicals sodium acetate (anhydrous, Reagentplus, 99.0%), acetic acid (glacial, ACS reagent, $\geq$ 99.7%), glutaraldehyde (GA, 50 wt% aqueous solution), glycerol solution (86-89%), Sodium Dodecyl Sulfate (SDS, >99%), n-hexadecane (>99%), oil red EGN (analytical standard), sodium hydroxide (NaOH, pellets, >98%), hydrochloric acid (HCl, ACS reagent, 37%), magnesium chloride hexahydrate ($\text{MgCl}_2 \cdot 6\text{H}_2\text{O}$) ($\geq$ 99%), sodium chloride (NaCl, >99.5%), magnesium sulfate (MgSO_4 , >99.5%), sodium sulfate (Na_2SO_4 , ACS reagent, 99%, anhydrous, granular), polyethylene glycol (PEG) with different molecular weights (Mw 200, 400, 600, 1500, and 2000 $\text{g} \cdot \text{mol}^{-1}$) were purchased from Sigma-Aldrich (Netherlands). The micropollutants atenolol (>98%), atrazine (analytical standard), bezafibrate (>98%), bisphenol-A (>99%), bromothymol blue (>95%), naproxen (analytical standard), phenolphthalein (analytical standard), and sulfamethoxazole (analytical standard) were purchased from Sigma-Aldrich (Netherlands). Deionized water was obtained from a Milli-Q[®] Ultrapure water purification system. All the chemicals were used as received.

5.2.2 Preparation of casting solutions

Two sets of casting solutions were prepared in this work based on the molecular weights (Mw) of PEI (25 and 750 kDa). The casting solutions were prepared using the following scheme. First, PEI was diluted using deionized water to obtain 25 wt% aqueous solution. Afterwards, PSS (25 wt%) and PEI (25 %) were mixed together in a PSS:PEI monomer molar mixing ratio of 1:2 to obtain a 25 wt% casting solution. The molar ratio was calculated based on the molecular weights of the monomers; PSS = 206.21 $\text{g} \cdot \text{mol}^{-1}$ and PEI = 43.04 $\text{g} \cdot \text{mol}^{-1}$ (per ethylenimine unit). The resultant casting solutions were continuously stirred until they became homogeneous. The PSS-PEI casting solutions were also prepared in other ratios of PSS to PEI such as 4:1, 2:1, 1:1, 1:3, and 1:4. The casting solutions having the monomer mixing ratios of 4:1 and 2:1 did not result in a precipitate rather formed a soft gel-like material. In comparison, the ratios 1:1, 1:3, and 1:4 formed a precipitate however, did not result in membranes with adequate mechanical strength. The final compositions of the two different sets of casting solutions used in this work are shown in **Table 5.1**.

The casting solutions prepared using 1000 kDa PSS and 25 kDa PEI are referred to as PSS-PEI (25 kDa) and similarly, the solutions prepared using 1000 kDa PSS and 750 kDa PEI will be referred to as PSS-PEI (750 kDa). The number inside the parenthesis represents the molecular weight of PEI (kDa) used to prepare the casting solutions.

The viscosity of all the casting solutions was measured on a HAAKE[™] Viscotester[™] 550 Rotational Viscometer (ThermoFisher Scientific, USA). Approximately 20 mL casting solution was poured into the SV-DIN spindle cylinder assembly and mounted on the Viscotester. The

Table 5.1 Composition of the casting solutions prepared using different molecular weights of PEI.

Mw PSS (kDa)	Mw PEI (kDa)	PSS:PEI monomer molar mixing ratio	Amount of PSS (wt%)	Amount of PEI (wt%)	Amount of water (wt%)
1000	25	1:2	17.6	7.4	75
1000	750	1:2	17.6	7.4	75

dynamic viscosity was obtained at 20 °C as a function of increasing shear rate (24.9 s⁻¹ to 1000 s⁻¹). The dynamic viscosity is reported at 24.9 s⁻¹ shear rate. Two samples were tested for each composition of casting solution and the average value with standard deviation is reported.

5.2.3 Membrane casting

The PSS-PEI (25 kDa) solutions were first cast on a glass plate as thin film using a casting bar with a gap height of 0.5 mm. The glass plate was immediately immersed in a coagulation bath at pH 1, adjusted using HCl, with the addition of 0.01 wt% glutaraldehyde (GA). The amount of the GA crosslinker in wt% was calculated based on the total weight of the coagulation bath.

In addition, the PSS-PEI (25 kDa) solutions were also cast as 0.5 mm thin films in different concentrations of acetic acid – sodium acetate buffer baths at pH 4, i.e. 0.1 M – 0.5 M. Furthermore the effect of the pH of 0.5 M acetate buffer bath on the membrane structure was studied by varying the pH from 3.6 to pH 5. This was achieved by varying the amounts of acetic acid and sodium acetate that was added to the bath. Following the same protocol, PSS-PEI (750 kDa) solutions were cast on glass plates as 0.5 mm thin films and immediately immersed in 0.5 M acetate baths at different values of pH (3.6 – 5).

Similarly, 0.5 M acetate buffer baths were prepared at different values of pH, i.e. pH 3.6 to pH 5, but this time, with the addition of 0.01 wt% GA. PSS-PEI (25 kDa) and PSS-PEI (750 kDa) solutions were then cast and immersed in these baths to obtain crosslinked membranes. The precipitated membranes were removed from the glutaraldehyde-containing coagulation bath after 24 h and stored in deionized water for further processing.

5.2.4 Membrane characterization

The structure and morphology of the membranes was examined using a scanning electron microscope, SEM (JSM-6010LA, JEOL, Japan) and Field Emission SEM (JSM-7610F, JEOL, Japan). The membrane samples for SEM imaging were first immersed in 20 wt% glycerol solution for 4 h followed by drying under constant air flow inside the fume hood. This was done to prevent the pore structure of the membranes from collapsing upon drying. For cross-section imaging, the glycerol-dried membrane samples were immersed in liquid nitrogen for 10 s and then carefully fractured to expose the cross-section. All the samples were then stored in a vacuum oven at 30 °C for 24 h before sputter coating them with a 5 nm thin layer of Pt/Pd alloy using Quorum Q150T ES (Quorum Technologies, Ltd., UK) sputter coater. The pores on the top surface SEM images

of the membranes were measured manually using ImageJ software to determine the average pore size of the membranes.

The streaming potential of nanofiltration membranes was determined at pH 6 using SurPASS electrokinetic analyzer (Anton Paar, Graz, Austria) by measuring the streaming current versus pressure in a 5 mM KCl solution using equation 5.1:

$$\zeta = \frac{dI}{dP} \frac{\eta}{\varepsilon \varepsilon_0} \kappa_B R \quad (5.1)$$

The pure water permeability (PWP) of the membranes was determined on dead-end Amicon[®] cells. The membranes were first cut into a circular disk having a diameter of 25 mm followed by mounting them on the dead-end cell. The effective surface area of the membranes was approximately 3.8 cm². Nitrogen gas was used to pressurize the vessel containing the feed water. The permeability tests were conducted at an applied water pressure of 4 bar. The permeate mass was automatically measured as a function of time using a weighing balance connected to a computer. The PWP was calculated using equation 5.2:

$$P = \frac{Jw}{\Delta p} \quad (5.2)$$

Where P is the pure water permeability in L·m⁻²·h⁻¹·bar⁻¹, Jw is the water flux obtained from the change of permeate volume (in liters) per unit membrane area (3.8 cm²) per unit time (h) and Δp is the pressure difference between the feed and permeate side (bar).

An oil-in-water emulsion was prepared to analyze the microfiltration performance of the membranes. For this purpose, n-hexadecane (100 mg·L⁻¹) in sodium dodecyl sulfate (463 mg·L⁻¹) with Oil red EGN (20 mg·L⁻¹) emulsion was prepared using the protocol described by Dickhout *et al.* [25]. The average diameter of the oil droplet was 3–4 μm. Oil red EGN is an oil soluble dye that is used as a marker for oil droplets. The oil droplet retention tests were conducted at 0.4 bar of applied pressure on a dead-end cell under continuous stirring. The feed, permeate, and retentate were analyzed on a UV-vis spectrophotometer (Shimadzu UV-1800, Japan) at $\lambda_{\max} = 521$ nm which is the maximum absorbance wavelength of Oil red EGN. A calibration curve was first obtained with known concentrations of n-hexadecane in SDS emulsion. The retention R (%) was then calculated using equation 5.3. Three samples of each membranes were tested for their oil droplet retention and the average value is reported.

$$R = \left[1 - \frac{C_p}{\left(\frac{C_f + C_r}{2} \right)} \right] \times 100 \quad (5.3)$$

Where C_p is the concentration in the permeate, C_f is the concentration in the feed, and C_r is the concentration in the retentate. Here, the average of C_f and C_r is taken because the retention experiments were conducted in a dead-end cell configuration where the concentration of feed is constantly changing above the membrane surface.

Molecular weight cut-off (MWCO) of the nanofiltration type membranes was determined using an aqueous solution containing different Mw of PEGs. The solution was prepared by dissolving 200, 400, 600, 1500, and 2000 g·mol⁻¹ PEG, each with a concentration of 1 g·L⁻¹, in deionized water. The solution was then filtered through the membranes in a dead-end cell. The feed, permeate, and retentate were analyzed using Gel Permeation Chromatography (GPC, Agilent 1200/1260 Infinity GPC/SEC series, Polymer Standards Service data center and column compartment) using Milli-Q water eluent containing 50 mg·L⁻¹ NaN₃, at 1 mL·min⁻¹, through 1000 Å, 10 µm Polymer Standards Service Suprema 8 × 300 mm column and 30 Å, 10 µm column connected in series. The concentration of different PEGs was determined in the feed, retentate, and permeate samples via refractive index. The retention was then calculated using equation 5.3. A sieving curve of Retention (%) vs molecular weight (g·mol⁻¹) was obtained and the molecular weight cut-off was estimated.

The nanofiltration performance of the membranes was also analyzed by conducting the salt retention tests in a dead-end cell configuration. A 5 mM solution of MgCl₂, NaCl, MgSO₄, or Na₂SO₄ was prepared and used as the feed. The salt solution was filtered through the membranes followed by testing the conductivity of the permeate and retentate streams using a handheld WTWTM Cond 3210TM conductivity meter (Xylem Analytics, Germany). A calibration curve was first made by measuring the conductivity of salt solutions with known concentrations. The retention was then calculated using the same equation 5.3.

A mixture containing eight different types of common micropollutants (Mw ranging from 216 – 624 g·mol⁻¹) was prepared by adding 3 mg·L⁻¹ of each micropollutant in deionized water and adjusting the pH to 5.8 using 0.1 M NaOH. These micropollutants are commonly found in river waters and constitute of herbicides, endocrine disrupting chemicals, and pH indicators. The mixture solution was filtered through the membranes for at least 24 h to achieve steady state permeation and to eliminate the effects of adsorption. The permeate, retentate, and feed samples were collected once the steady state was achieved and analyzed using UltiMate 3000 UHPLC (ThermoFisher Scientific, USA). The separation was carried out using a 2.2 µm ACCLAIM RSLC C18 column (ThermoFisher Scientific, USA). A calibration curve was first created with known concentrations of the micropollutants in the cocktail mixture. The concentrations of the micropollutants in feed, permeate, and retentate were calculated based on the calibration curve. The retention was then estimated using equation 5.3.

5.3 Results and Discussion

Here the formation of PSS-PEI based membranes through pH-switch induced APS will be discussed in 5 distinct sections. Initially we focus on the conditions in the coagulation bath; varying the buffer concentration, pH and crosslinker content. Subsequently we study the effect of PEI Mw in the casting solution. Finally we discuss the differences and similarities between the PSS/PEI systems studied here and the earlier studied PAH/PSS membranes.

5.3.1 Effect of acetate buffer concentration

The PSS-PEI casting solution was prepared by mixing PSS (25%) and PEI (25%) solutions is a 1:2 ratio of PSS to PAH monomers. It is known from **Chapter 3** and from another work in literature

that combining a weak and a strong PE in APS approaches and an excess of the weak PE leads to the best results [26]. Initial investigations indicated the 1:2 ratio as optimal for PSS-PEI. The formed solution was completely clear and was found to have a pH of 12. Indeed at such a pH, PEI is expected to be uncharged as the pH is well above the pK_a of the primary and secondary amines and just above the pK_a of the tertiary amines that make up PEI, preventing complexation.

In **Chapter 3**, a coagulation bath of pH 1 was found to be optimal for the formation of PSS-PAH membranes. Such a low pH in the coagulation bath was required to have sufficient driving force for a quick solvent (high pH) to non-solvent (low pH) exchange, to allow membrane formation. In this work we use an alternative aqueous non-solvent, a pH 4 acetate buffer. The buffer capacity of the acetate will still allow a high driving force for exchange, while an extreme pH is not required.

The PSS-PEI (25 kDa) solution was cast on glass plates using a casting bar of 0.5 mm gap height. Afterwards, the glass plates were immediately immersed in different concentrations of pH 4 acetate buffer, i.e. 0.1–0.5 M, to find an optimum concentration of buffer for the membrane fabrication. At pH 4, PEI is fully charged and consequently forms a polyelectrolyte complex (PEC) with PSS. The PEC is insoluble in water and precipitates as a white solid film. *Figure S5.1, supporting information* shows the real time photos of the precipitation/phase separation process of these films in different concentrations of pH 4 acetate buffer bath. These snapshots distinctly show that the onset of phase separation is significantly different at different concentrations of the acetate buffer. At a concentration of 0.1 M, no phase separation is observed until 1 s after the immersion, see *Figure S5.1*. On the other hand, the membrane prepared in 0.5 M acetate buffer bath immediately turned opaque/white indicating an instantaneous phase inversion. In addition to the onset of precipitation/phase separation, another important process is the precipitation rate which is essentially the time it takes for the film to become fully opaque once the phase separation has started. Therefore it is important to make a clear distinction between these two processes. It can be seen from *Figure S5.1* that both the onset of phase separation, and the precipitation rate is slower at the buffer concentration of 0.1 M. On the other hand, at the concentration of 0.5 M, the onset of phase separation is instantaneous and the precipitation rate is significantly faster than at 0.1 M. In conclusion, increasing the acetate buffer concentration results in immediate phase separation with a faster rate of precipitation. At higher concentrations the greater buffer capacity of the acetate buffer allows faster pH changes in the casted film leading to faster onset of precipitation and a faster precipitation rate as will also be discussed later.

Figure 5.1 shows the SEM images of the membranes prepared in different concentrations of acetate buffer. The membranes prepared at low concentrations, i.e. 0.1–0.3 M, were brittle, had cracks on the surface, and therefore, could not be used for any further tests. On the other hand, mechanically stable membranes were obtained when the acetate buffer concentration was 0.4 M or 0.5 M. Here, by suitable mechanical stability, we mean that the membranes could be cut into circular disks without them cracking and could be subjected to at least 4 bar of applied pressure during PWP measurements.

Figure 5.1 SEM images and photographs of PSS-PEI (25 kDa) membranes prepared in different concentrations of acetate buffer at pH 4. a) 0.1 M, b) 0.2 M, c) 0.3 M, d) 0.4 M, and e) 0.5 M acetate buffer.

The effect of different precipitation rates on the membrane structure are even more obvious when looking at the cross-section SEM images shown in **Figure 5.1a–c**. Finger-like macrovoids appear only when the concentration of the acetate buffer exceeds 0.3 M. As explained earlier, the rate of precipitation increases with the increase in buffer concentration. This is in line with the traditional NIPS, where the finger-like macrovoids are formed as a result of a higher precipitation rates [2]. The same result was also observed in this version of APS, where higher precipitation rates led to asymmetric membranes with macrovoids. These results reveal that the concentration of the acetate buffer is an important parameter to control the structure of the membranes and their mechanical stability.

The top surface SEM images shown in **Figure 5.1a–c** reveal that the membranes with relatively dense top layers are obtained when increasing the acetate buffer concentration. At 0.1 M–0.3 M acetate buffer concentration, the top surfaces have defects and small cracks (**Figure 5.1a–c**). Increasing the acetate buffer concentration to 0.4 M and then further to 0.5 M resulted in densification of the top surface of the membranes. This is because at higher concentrations, the acetate buffer has a greater buffering capacity which readily acts to reduce the pH of the PSS-PEI cast film. At high buffer concentrations, the weak polycation PEI can acquire charge more readily which leads to a rapid formation of a white, solid, water-insoluble PSS-PEI polyelectrolyte complex. It can be seen from the photographs of the membranes shown in **Figure 5.1** that mechanically stable membranes were only obtained when the concentrations of the acetate buffer bath were 0.4 M and 0.5 M. Further increasing the acetate buffer concentration to 1 M resulted in even denser membranes that had a pure water permeability of $0.36 \pm 0.01 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, *Figure S5.2, supporting information*. However in addition to a low water permeability, such a high concentration of buffer is not ideal for the large scale production of these membranes. Therefore, the concentration of the buffer bath was fixed at 0.5 M for all further experiments since this concentration resulted in dense and the most mechanically stable membranes. The membranes prepared in 0.4 M and 0.5 M buffer baths were tested for their PWP at 4 bar of applied pressure. The membranes prepared in 0.4 M acetate bath at pH 4 had a water permeability of $\sim 32 \pm 6 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ while the ones prepared in 0.5 M bath had a permeability of $\sim 4 \pm 0.5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. These initial results are very promising as they demonstrate that for the PSS-PEI system it is indeed possible to obtain membranes using just a mild pH switch (pH 12 to pH 4) by making use of a buffer based coagulation bath.

5.3.2 Effect of buffer pH in the bath

To further understand the influence of coagulation bath conditions on membrane structure, the PSS-PEI (25 kDa) solution was cast in 0.5 M acetate buffer coagulation baths at different pH values i.e. 3.6, 4, 4.5, and 5. The real time photographs of the precipitation are shown in *Figure S5.3, supporting information*. Here, the onset of phase separation was instantaneous irrespective of the pH of the bath while the rate of precipitation varied as the pH of the bath was decreased. At a bath pH of 3.6 and 4, the films immediately (<1 s) turned completely opaque/white indicating the formation of solid, porous films. In comparison, at pH 5, the films were relatively transparent after 1 s of immersion indicating a relatively slower precipitation rate. In addition, the rate of precipitation decreased with the increasing pH. Such precipitation behavior is intuitive because this version of APS relies on a change in pH to drive the precipitation, and the pH of the coagulation bath can be thought of as a driving force for polyelectrolyte complexation [19,26], as it can determine the degree of protonation (charge) of the weak polycation PEI. The branched

PEI used in this work consists of 31% primary, 39% secondary, and 30% tertiary amines all of which have different pK_a values, i.e. 4.5, 6.7, and 11.6, respectively [27,28]. Therefore, at pH values less than the pK_a of primary amines (i.e. at pH <4.5), PEI can exist in its fully protonated state resulting in stronger electrostatic interactions with PSS i.e. a higher density of ionic crosslinks. As a result, the membranes prepared in pH 3.6 and pH 4 buffer precipitated faster and were mechanically stronger (see *Figure S5.4* for the photographs of the membranes). At pH 4.5 and 5, it is likely that not all the amine residues within PEI are protonated (charged) and therefore, the resulting polyelectrolyte complex has a lower density of ion pairing than at pH 3.6 and 4 and thus the films are mechanically weaker.

Figure 5.2 shows the top surface and cross-section SEM images of the membranes prepared at different buffer pH values. All the membranes exhibit the typical asymmetric morphology with denser top layers followed by porous sub-structures with finger-like macrovoids. At pH 3.6, the top surface of the resultant membranes had inhomogeneous structure and defects with a cross-section having typical finger-like macrovoids as shown in **Figure 5.2a**. The inhomogeneity on the membrane top surface is most likely due to the relatively rapid rate of precipitation at pH 3.6 (compared to higher pH values), which does not give adequate time for the polyelectrolyte chains to rearrange, also resulting in relatively brittle membranes. At pH 4, the resultant membranes had smooth and dense top layers with relatively dense finger-like macrovoids in the support structure, see **Figure 5.2b**. Increasing the pH of the acetate buffer bath to pH 4.5 and 5 resulted in membranes with porous top surfaces as can be seen in **Figure 5.2c** and **d**. One possible reason for these porous top surfaces could be the lower degree of ionic crosslinks caused by relatively lower degree of PEI protonation at pH 4.5 and pH 5. The membranes prepared in pH 4.5 and 5 baths were too brittle to be used for any applications, see the photographs in *Figure S5.4, supporting information*.

The PWP of the membranes prepared in pH 3.6 and pH 4 buffer baths was measured, with the former having a permeability of $\sim 280 \pm 30 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ while the latter a permeability of $\sim 4 \pm 0.5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. These values are in accordance with the top surface morphology of these membranes shown in **Figure 5.2a** and **b** with the membranes prepared at pH 3.6 having a more porous and uneven top layer compared to the membranes prepared at pH 4. In addition, the membranes prepared at pH 3.6 were relatively brittle which may have resulted in the development of micro-cracks on the membrane surface while operating under elevated pressures, thereby increasing the pure water permeability. A denser structure obtained at pH 4 provides a greater resistance for water permeation.

The PSS-PEI (25 kDa) membranes prepared in pH 4 buffer bath were evaluated for their molecular weight cut-off (MWCO) which is one of the key parameters that determines the potential applicability of the membrane. The MWCO of these membranes as determined by the sieving curve shown in *Figure S5.5a*, was $260 \pm 60 \text{ g}\cdot\text{mol}^{-1}$, which is in the range of typical nanofiltration type membranes ($200\text{--}1000 \text{ g}\cdot\text{mol}^{-1}$) [29].

Figure 5.2 Top surface and cross-section SEM images of PSS-PEI (25 kDa) membranes showing the effect of acetate buffer pH in coagulation bath on the membrane structure. The membranes were cast in 0.5 M acetate buffer coagulation baths at different values of pH i.e. a) pH 3.6, b) pH 4, c) pH 4.5, and d) pH 5.

Figure 5.3 Retention of a) salts and b) micropollutants by PSS-PEI (25 kDa) membranes prepared in pH 4 acetate buffer. The tests were conducted in a dead-end cell configuration at a feed pressure of 4 bar for salts and 3 bar for micropollutants. The sign inside the parenthesis for micropollutants represents their charge at pH 5.8. The membranes had a pure water permeability of $\sim 4 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$.

Figure 5.3a shows the retention of four different types of salts by the membrane prepared in pH 4 bath. These salts were chosen because they consist of both monovalent and divalent anions and cations and thus providing insight into the charge and separation mechanism(s) of the membranes. Due to the excess of PEI in the membranes, it is expected that the membranes will be overall positively charged. This was confirmed by measuring the streaming potential of the membrane surface which was approximately +10 mV at pH 6. According to the Donnan exclusion mechanism, a membrane with fixed positively charged groups will repel cations and attract anions [30]. From **Figure 5.3a** it is clear that the retention of salts containing divalent cations such as MgCl₂ and MgSO₄ is higher, 81% and 44% respectively, as compared to the retention of monovalent cations NaCl (27% retention) and Na₂SO₄ (32%), revealing that the separation is largely based on charges. However, if Donnan exclusion was the only mechanism, Na₂SO₄ should have been rejected less than NaCl, due to the attractive interactions between the membrane and the divalent anion SO₄²⁻. Size exclusion, steric hindrance and dielectric effects are also known to determine the salt retentions of typical nanofiltration membranes [31].

In order to further evaluate the size exclusion and steric effects occurring during separation, a mixture of eight different types of micropollutants was filtered through the PSS-PEI (25 kDa) pH 4 membranes and the retentions are summarized in **Figure 5.3b**. The positively charged Atenolol, with a Mw of 266 g·mol⁻¹, was only retained 41% suggesting again that the retention of charged molecules is not only governed by Donnan exclusion but also by size exclusion and solution-diffusion mechanism. This can be seen by looking at the retentions of negatively charged molecules such as Sulfamethoxazole (Mw 256 g·mol⁻¹, 45% retention), Naproxen (Mw 230 g·mol⁻¹, 87% retention), and Bezafibrate (Mw 362 g·mol⁻¹, 64% retention). Here, Naproxen is retained more than Sulfamethoxazole even though the former has a lower molecular weight. This can be explained according to the solution-diffusion mechanism which also takes into account the affinity of the micropollutant(s) for the membrane(s). In this case the affinity is related to

the hydrophilicity/hydrophobicity of the micropollutant molecules. The octanol-water partition coefficient ($\log K_{OW}$) is one measure of the hydrophilicity of a compound [32]. Sulfamethoxazole is hydrophilic with a $\log K_{OW}$ of ~ 0.89 while Naproxen is a hydrophobic compound with $\log K_{OW} \sim 3.18$. Consequently, Sulfamethoxazole readily diffuses through the hydrophilic PEC membrane because of its higher affinity for the membrane and therefore, always shows lower retention than Naproxen.

The retention trend of the neutral molecules like Atrazine, Bisphenol A, Phenolphthalein, and Bromothymol Blue follow the size exclusion mechanism in accordance with the MWCO ($260 \text{ g}\cdot\text{mol}^{-1}$) of the membrane such that Atrazine ($216 \text{ g}\cdot\text{mol}^{-1}$) is retained only 53% while Bromothymol Blue ($624 \text{ g}\cdot\text{mol}^{-1}$) is completely retained by the membrane. This high retention of Bromothymol Blue is important, as it also demonstrates the membrane to be completely defect free.

5.3.3 Effect of crosslinker

From **Chapter 2** and **3** we know that glutaraldehyde (GA) crosslinking densifies the structure of the polyelectrolyte complex APS membranes and improves the solute rejections in polyelectrolyte multilayer membranes [33,34]. This is because the GA readily reacts with amine groups under aqueous conditions to form imine bonds ($-\text{C}=\text{N}-$) via Schiff base reaction [35]. In case of PEI, the imine bonds are formed by the reaction of GA with the primary amines [36]. Therefore, GA was added as a crosslinking agent in the 0.5 M acetate buffer coagulation bath in order to further densify the membrane structure and improve overall mechanical strength. The PSS-PEI (25 kDa) solutions were cast and immersed in acetate buffer baths at different pH values (pH 3.6–5) with the addition of 0.01 wt% GA. The wt% concentration of GA is with respect to the total weight of the coagulation bath (i.e. 0.1 g GA per 1000 g of coagulation bath). GA concentration was kept as low as possible because it is a toxic chemical at higher concentrations [37], and a concentration of 0.01 wt% falls well below the standard lab safety conditions. Upon immersion of the cast films into the baths, the precipitation and the crosslinking reaction between the primary amine groups of PEI occurs simultaneously. It is difficult to determine the exact degree of crosslinking, but since the PSS:PEI monomer mixing ratio in the casting solution was 1:2, there is an excess of PEI that can readily react with GA to form the imine crosslinks. As of the amines in PEI only the primary ones can react, and as there is a limited GA available in the coagulation bath, we know that the maximum degree of crosslinking (assuming full conversion) cannot exceed 23% of the PEI amines.

The onset of phase separation and the precipitation rates of these membranes were identical to the ones prepared without the addition of GA, i.e. similar to *Figure S5.3*. Increasing the pH of the coagulation bath resulted in slower rates of precipitation and hence, less stable membranes as discussed in **section 3.2**, where the driving force for complexation as well as the protonation (charge) of PEI decreases with higher pH. As a result, the membranes prepared in pH 4.5 and 5 buffer baths were too brittle to be used for further processing.

Figure 5.4 shows the SEM images of the membranes prepared in acetate buffer baths with the addition of 0.01 wt% GA. All the membranes are asymmetric with relatively dense top layers and more open cross-sections. At pH 3.6, the resultant membranes had a relatively porous top layer with typical finger-link macrovoids in the cross-section, **Figure 5.4a**.

Figure 5.4 Top surface and cross-section SEM images of crosslinked PSS-PEI (25 kDa) membranes showing the effect of acetate buffer pH in coagulation bath on the membrane structure. The membranes were cast in 0.5 M acetate buffer coagulation baths at different values of pH with the addition of 0.01 wt% GA. a) pH 3.6, b) pH 4, c) pH 4.5, and d) pH 5.

The pore size of pH 3.6 membrane, estimated by ImageJ analysis of x10,000 magnification SEM images, was approximately 200 ± 80 nm, *Figure S5.6, supporting information*. It is important to mention that the pore size estimation via SEM images is not an accurate way to determine the pore size of the membranes rather it gives a reasonable estimation to compare different membranes. The top surface SEM image of pH 3.6 membrane prepared with 0.01 wt% GA shows that membrane surface is slightly denser compared to the membranes prepared at the same pH but without the addition of GA (compare **Figure 5.2a** and **Figure 5.4a**). Increasing the bath pH to 4 results in a much denser top layer and more compact cross-section, **Figure 5.4b**. These SEM images are not that different to the image shown in **Figure 5.2b** where the membranes were prepared without the GA. However, the GA crosslinking has indeed densified the membrane structure as will be seen by the permeability and retention tests. The FE-SEM images at even higher magnification (x50,000) shown in *Figure S5.7 (supporting information)* reveal the defects on the pH 3.6 membrane and show that the pH 4 membrane is significantly denser as no defects or pores could be seen even at such magnifications. At pH 4.5 and 5, the membranes again show a typical asymmetric structure with cracks on the top surface but these membranes were unusable due to their brittle nature.

The mechanically stable membranes obtained in pH 3.6 and pH 4 acetate buffer baths were tested for their PWP. Since the top surface of the pH 3.6 membrane was relatively porous, it is not surprising that the PWP was approximately $32 \pm 3 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. In comparison, the denser membrane obtained at pH 4 had a permeability of $1.7 \pm 0.2 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. The MWCO of this membrane is $200 \pm 2 \text{ g}\cdot\text{mol}^{-1}$, see *Figure S5.5b in supporting information*.

To evaluate the nanofiltration performance of the membrane prepared in pH 4 acetate buffer with 0.01 wt% GA, the same range of mono- and divalent salts as earlier were filtered through the membrane with the results shown in **Figure 5.5a**. As expected for a positively charged membrane, MgCl_2 retention was the highest at $\sim 97\%$ followed by $\sim 94\%$ for MgSO_4 . In comparison, NaCl and Na_2SO_4 retentions were $\sim 66\%$ and $\sim 70\%$, respectively. These retention results confirm that this nanofiltration membrane functions by a combination of Donnan exclusion and size exclusion mechanisms.

Figure 5.5b shows the retention of the eight different micropollutants by the same membrane. This membrane showed excellent retention of all types of micropollutants tested; average micropollutant retention of $\sim 96\%$. The positively charged Atenolol was 97% retained. The neutral molecules like Atrazine ($\text{Mw} \sim 216 \text{ g}\cdot\text{mol}^{-1}$), Bisphenol-A ($\text{Mw} \sim 228 \text{ g}\cdot\text{mol}^{-1}$), Phenolphthalein ($\text{Mw} \sim 318 \text{ g}\cdot\text{mol}^{-1}$), and Bromothymol Blue ($\text{Mw} \sim 624 \text{ g}\cdot\text{mol}^{-1}$) showed a retention of 93%, 94%, 99%, and 100% respectively. These retentions are in accordance with the $200 \text{ g}\cdot\text{mol}^{-1}$ MWCO measured for this membrane. These results indicate that the PSS-PEI (25 kDa) membranes prepared in pH 4 acetate buffer with 0.01 wt% GA are excellent nanofiltration type membranes. Furthermore, the membrane exhibited stable performance over 5 days of continuous operation, see *Figure S5.8, supporting information*. Crosslinking with GA is thus clearly an excellent approach to further control the separation properties of the prepared PSS-PEI based membranes.

The pH stability test of the membranes was conducted by keeping them in pH 1, pH 8, pH 10, and pH 12 aqueous solutions for 10 days and then removing and washing them with deionized water. The pure water permeability of the treated membranes was re-measured and compared with the untreated membranes. It was found that the membranes treated in pH 1 up to pH 8 showed

Figure 5.5 Retention of a) salts and b) micropollutants by PSS-PEI (25 kDa) membranes prepared in pH 4 acetate buffer with 0.01 wt% GA. The tests were conducted in a dead-end cell configuration at a feed pressure of 4 bar for salts and 3 bar for micropollutants. The sign inside the parenthesis for micropollutants represents their charge at pH 5.8. The membranes had a pure water permeability of $\sim 1.7 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$

the same water permeability as the untreated versions. However, the pH 10 and pH 12 treated membranes became unstable in the high pH solutions, see *Figure S5.9, supporting information*. At such a high pH, PEI becomes uncharged resulting in the possible de-complexation of the polyelectrolyte complex. Higher degrees of crosslinking would likely lead to increased stability at higher pH.

5.3.4 Effect of PEI molecular weight

The Mw of PEI in the casting solution was increased to 750 kDa while keeping the Mw of PSS constant at 1000 kDa. The PSS-PEI (750 kDa) solutions were then also cast on glass plates as 0.5 mm thin films and immersed in coagulation baths at different values of pH. The onset of precipitation was instantaneous in all the different pH baths, however, the rate of precipitation was slower at pH 4.5 compared to pH 4 and even slower at pH 5. The effect of bath pH on the rate of precipitation was similar for PSS-PEI (25 kDa) and PSS-PEI (750 kDa) membranes, where higher pH (i.e. closer to pH of casting solution, thus a lower driving force for precipitation) slows down the rate of precipitation. The photographs of the resultant membranes are shown in *Figure S5.10, supporting information*. The membranes prepared in pH 4.5 bath showed an inhomogeneous structure while those prepared in pH 5 were too brittle to be used for any further processing. The reason for inhomogeneous surface is unclear. One possible reason could be that the larger molecular weight of PEI causes the chains to rearrange during the precipitation process due to the relatively slower rate of precipitation. As a result, the membrane surface has regions with different densities as can be seen in the photograph in *Figure S5.10, supporting information*. Similarly, at pH 5 the rate of precipitation is even more slower as compared to pH 4.5, causing the membrane to lose its structural integrity as it becomes brittle. The top surface and cross-section SEM images of the resultant membranes are shown in **Figure 5.6**.

Figure 5.6 Top surface and cross-section SEM images of PSS-PEI (750 kDa) membranes showing the effect of acetate buffer pH in coagulation bath on the membrane structure. The membranes were cast in 0.5 M acetate buffer coagulation baths at different values of pH i.e. a) pH 3.6, b) pH 4, c) pH 4.5, and d) pH 5.

Top surface SEM images of the membranes prepared in pH 3.6 coagulation revealed small pores and defects in the top layer (**Figure 5.6a**). Increasing the pH of the acetate buffer bath gives membranes with relatively larger pores as seen in **Figure 5.6b**. Moreover, the number of pores also increases at pH 4. The pore sizes of these membranes was estimated from the SEM images and the average pore size of the pH 3.6 and pH 4 bath membranes was approximately 60 ± 45 nm and 80 ± 60 nm, respectively, see *Figure S5.11, supporting information*. **Figure 5.6c** shows the top surface image of the membrane prepared in pH 4.5 bath. This membrane also had defects and small pores on the surface. Increasing the bath pH to 5 resulted in films with larger surface pores ranging from 50 nm to 650 nm, but as mentioned earlier this film was too brittle to be used any further. The cross-section images shown in **Figure 5.6** indicate little difference in the morphology of the membranes prepared in pH 3.6–4.5; the membranes are asymmetric with finger-like macrovoids. In comparison, at pH 5 the membranes have a relatively open structure. The full cross-section morphology of the membranes prepared in different pH baths is shown in *Figure S5.12, supporting information*.

Figure 5.7 shows the pure water permeability and n-hexadecane oil droplet retention of the PSS-PEI (750 kDa) membranes prepared in acetate buffer baths at different values of pH. The PWP of the membranes prepared in pH 3.6 baths was $\sim 65 \pm 6$ L·m⁻²·h⁻¹·bar⁻¹ with 100% retention of the oil droplets. Similarly, the membranes prepared in pH 4 buffer bath had a permeability of $\sim 130 \pm 25$ L·m⁻²·h⁻¹·bar⁻¹ with 100% retention of oil droplets.

Similar to the protocol followed for PSS-PEI (25 kDa), 0.01 wt% GA was added to the coagulation bath to investigate the effect on membrane structure and performance. Addition of the

Figure 5.7 Pure water permeability and n-hexadecane oil droplet retention of PSS-PEI (750 kDa) membranes prepared in 0.5 M acetate buffer bath at pH 4. The oil droplet retention test was conducted at a feed pressure of 0.4 bar.

Table 5.2 Dynamic viscosity of the polyelectrolyte casting solutions at 24.9 s^{-1} shear rate. The casting solution concentration was 25 wt% overall polymer.

Membrane	Dynamic viscosity at 24.9 s^{-1} shear rate (Pa·s)
PSS-PEI (25 kDa)	1.0 ± 0.2
PSS-PEI (750 kDa)	2.1 ± 0.3

crosslinker in such amounts slightly reduced the pore sizes of the membranes as can be seen from the top surface SEM images shown in *Figure S5.13, supporting information*. The average pore size of the pH 4 membranes was approximately $\sim 60 \text{ nm}$, measured from SEM image using ImageJ software. Comparing the top surface images shown in **Figure 5.6a-d** to the images shown in *Figure S5.13a-d*, one can observe the reduction in porosity and slight densification of the membranes upon addition of GA. However, for microfiltration applications, it is desirable to have a more open and porous structure with high water permeability. Therefore, PSS-PEI (750 kDa) membranes prepared in baths with the addition of GA are not ideally suited for microfiltration applications.

From **Chapter 2** it is known that polyelectrolyte molecular weight is a major control parameter for the pore size and morphology of the APS polyelectrolyte complexation membranes. Paring two relatively low Mw polyelectrolytes (PSS $\sim 200 \text{ kDa}$ and PAH $\sim 17.5 \text{ kDa}$), yielded microfiltration type membranes with average pore sizes in the range of $80\text{--}230 \text{ nm}$. On the other hand, ultrafiltration (pore size $\sim 4.5 \text{ nm}$) and relatively dense nanofiltration type membranes were obtained with higher molecular weight pairings (PSS $\sim 1000 \text{ kDa}$ and PAH $\sim 150 \text{ kDa}$). There are several causes for this molecular weight dependent behavior. One is the viscosity of the casting solutions, which is directly dependent on the Mw of the polyelectrolytes used. The effect of casting/dope solution viscosity is well-known from traditional NIPS where a lower solution viscosity typically results in relatively porous membranes with macrovoids due to a fast precipitation rate [38]. Similarly, a polymer solution with higher viscosity gives denser membranes with lower overall porosity. The Mw of the polyelectrolytes used can also significantly affect the structure of the resultant polyelectrolyte complex [39,40].

However, for the PSS-PEI membranes prepared in this work, the effect of polyelectrolyte molecular weight is different to previous versions of APS and also to NIPS membranes. Here, we keep the Mw of PSS fixed at 1000 kDa , and study two distinct branched PEI Mw's of $\sim 25 \text{ kDa}$ and $\sim 750 \text{ kDa}$. The dynamic viscosity of both these casting solutions at 24.9 s^{-1} shear rate is shown in **Table 5.2**.

The dynamic viscosity of a 25 wt% PSS-PEI (25 kDa) solution was $\sim 1 \text{ Pa}\cdot\text{s}$, while for the same concentration of 25 wt% overall polymer, the viscosity of PSS-PEI (750 kDa) was $\sim 2.1 \text{ Pa}\cdot\text{s}$. In both the cases, the resultant membranes prepared in pH 4 acetate buffer bath showed asymmetric structures with finger-like macrovoids, see **Figure 5.2b** and **Figure 5.6b**. This is because the onset of phase separation for both the films with different Mw of PEI was almost instantaneous ($<1 \text{ s}$), see *Figure S5.14, supporting information*. As mentioned above, these findings contradict the results of traditional NIPS as well as the PSS-PAH based APS membranes, where higher solution viscosities give denser membranes without macrovoids. The unexpected effect of polyelectrolyte

Mw for PSS-PEI membranes is likely due to the branched nature of PEI. The commercially available PEI having the Mw ~ 25 kDa and ~ 750 kDa was characterized by von Harpe *et al.* [27] where they measured the relative ratio of secondary to tertiary amines which is essentially the ratio of linear to branched structures in one molecule. Their results indicated that for PEI having a Mw of ~ 25 kDa, the ratio of secondary to tertiary amines was 1.3 while for PEI with Mw ~ 750 kDa it was 1.13 [27], which means that the latter has more degree of branching. Therefore, we hypothesize that low Mw chains of branched PEI (~ 25 kDa) are able to pack more closely together upon complexation with PSS. In comparison, higher Mw chains of PEI (~ 750 kDa), where branching plays a more significant role, form less compact (more open) structures upon complexation with PSS.

This section thus makes clear that by a simple change of PEI Mw, we can transition from the dense membranes produced earlier to very relevant porous membranes.

5.3.5 Comparison with other APS membranes

The PSS-PEI membranes have numerous advantages over other PEC based APS membranes. For instance, as reported in **Chapter 2** regarding the PSS-PAH membranes, the pH of the PAH solution has to be increased to $\sim$ pH 14 i.e. beyond its pK_a value of 9 by the addition of NaOH to obtain a homogeneous casting solution. As a consequence, extremely low pH values, such as a pH 1 coagulation bath, are required to neutralize the added NaOH for obtaining stable PSS-PAH membranes. On the other hand, the PSS-PEI solutions have an advantage that a clear casting solution can already be obtained at pH 12 without adding caustic NaOH. Consequently, extreme pH coagulation baths are not essential to precipitate PSS-PEI. As shown in this work, microfiltration and nanofiltration type PSS-PEI membranes with excellent performance can simply be obtained at benign conditions of pH 4, by making use of a buffer solution. This makes the PSS-PEI based APS approach to be a more sustainable and environmentally friendly version. Another advantage of the PSS-PEI is the lower dynamic viscosity of the casting solution used to obtain nanofiltration type membranes i.e. ~ 1 Pa·s of PSS-PEI (25 kDa) as compared to ~ 48 Pa·s of the PSS-PAH solution, even at higher polymer concentrations. This makes the former convenient to use for the production of flat sheet membranes. In addition, the nanofiltration type membranes obtained with PSS-PAH only showed an average of $\sim 80\%$ retention of the micropollutants and did not show any significant retentions of the four types of salts, indicating that the obtained membranes were not as dense as commercial nanofiltration type membranes. On the other hand, the PSS-PEI (25 kDa) membranes prepared in 0.5 M acetate buffer bath at pH 4 showed an average of $\sim 96\%$ retention of organic micropollutants in addition to the excellent salt retentions in excess of 94% for $MgCl_2$ and $MgSO_4$.

In contrast, the nanofiltration membranes prepared using the salinity change induced APS approach show relatively lower water permeabilities of $\sim 0.1 - 1$ L·m $^{-2}$ ·h $^{-1}$ ·bar $^{-1}$ [21,22] when compared to the pH-shift induced PSS-PAH and PSS-PEI membranes. Similarly, the nanofiltration type APS membranes prepared using the pH-responsive polyelectrolytes, such as polystyrene-alt-maleic acid, show a lower pure water permeability of $\sim 0.3 - 0.5$ L·m $^{-2}$ ·h $^{-1}$ ·bar $^{-1}$ [41,42]. **Figure 5.8** shows a comparison in terms of MWCO and $MgSO_4$ retention of different polyelectrolyte based APS membranes reported in literature so far. A membrane with a higher pure water permeability and salt retention combined with a lower molecular weight cut-off is ideal for nanofiltration applications. The graph shown in **Figure 5.8** clearly indicates that the

Figure 5.8 A comparison of a) MWCO and b) MgSO₄ retention vs. pure water permeability of different APS membranes reported in the literature. The PSS-PEI membranes reported in this work show better pure water permeability as compared to the other polyelectrolyte based APS membranes.

PSS-PEI membranes reported in this work have higher pure water permeability with equivalent MWCO and MgSO₄ retention as compared to the other APS membranes.

Indeed the membranes obtained using PSS and PEI indeed prove the versatility of the APS technique. However, there are still a few challenges that remain. One of the challenges in case of PSS-PEI (750 kDa) membranes is the relatively smaller pore size of ~ 80 nm and lower water permeability of ~ 120 L·m⁻²·h⁻¹·bar⁻¹. For most microfiltration membranes, the average pore size is in the range of 100 nm to 10 μ m [29]. There exist a room for improvement here to obtain PSS-PEI membranes having comparable performances to most commercially available microfiltration membranes. Future efforts could also be devoted to increase the pure water permeability of the PSS-PEI (25 kDa) nanofiltration membranes and to obtain ultrafiltration types by tuning the pore size of the membranes.

5.4 Conclusions

In this study, pH-shift induced Aqueous Phase Separation (APS) was employed to prepare tunable PSS-PEI polyelectrolyte complex (PEC) membranes by a more sustainable approach. Unlike the existing PEC based APS approaches, the polyelectrolyte PSS and PEI solutions can be directly mixed to obtain a homogeneous casting solution at pH 12 without any addition of acid/base or salt. Immersing this PSS-PEI solution in an acetate buffer bath at lower pH causes PEI to acquire charge thereby forming a polyelectrolyte complex with PSS. Several key parameters such as the molecular weight of PEI, the concentration and pH of the acetate buffer, and the concentration of GA crosslinker were varied to investigate the effect on membrane structure and morphology. The results show that the concentration of the acetate buffer is one of the most vital parameters that influences both the onset and the rate of precipitation of PSS-PEI membranes. A slower precipitation rate was observed at low buffer concentrations of 0.1 M – 0.3 M because of the lower buffering capacity, while at 0.4 M and 0.5 M concentrations, the buffering capacity increases causing rapid phase inversion of the membranes which resulted in asymmetric structures. pH of the acetate buffer bath is another key parameter that influences

the charge on PEI and also effects the rate of precipitation by acting as a driving force for the polyelectrolyte complexation. At pH 3.6 and pH 4, PEI is fully charged resulting in rapid formation of stable PSS-PEI complex membranes. Conversely, PEI is not expected to be fully charged at pH 4.5 and 5 and as a result the membranes obtained in these pH baths precipitated at a slower rate and were mechanically unstable. The molecular weight of PEI is another tuning parameter that was found to significantly influence the resulting membrane pore sizes. Using relatively low molecular weight of PEI, such as ~ 25 kDa, nanofiltration type membranes in pH 4 bath with a molecular weight cut-off (MWCO) of ~ 260 g $\cdot$ mol $^{-1}$ were made. These membranes had a pure water permeability of ~ 4 L $\cdot$ m $^{-2}$ $\cdot$ h $^{-1}$ $\cdot$ bar $^{-1}$ and showed decent retentions for MgCl $_2$ ($\sim 81\%$) and MgSO $_4$ ($\sim 44\%$). Furthermore, adding only 0.01 wt% glutaraldehyde in the bath significantly densified the membranes by forming imine crosslinks. The crosslinked membranes had a pure water permeability of ~ 1.7 L $\cdot$ m $^{-2}$ $\cdot$ h $^{-1}$ $\cdot$ bar $^{-1}$ and had a MWCO of ~ 200 g $\cdot$ mol $^{-1}$ with MgCl $_2$ and MgSO $_4$ retentions of $\sim 97\%$ and $\sim 94\%$. These membranes also showed excellent micropollutant retentions in excess of 90%. On the other hand, using higher molecular weight of PEI i.e. ~ 750 kDa resulted in microfiltration type membranes in pH 4 baths with an average pore size of ~ 60 nm. These membranes had a pure water permeability of ~ 130 L $\cdot$ m $^{-2}$ $\cdot$ h $^{-1}$ $\cdot$ bar $^{-1}$ and exhibited 100% retention of oil from an oil-in-water emulsion. The findings of this work signify that PSS-PEI membranes with tunable pore sizes and excellent separation properties can be readily prepared using just a mild pH switch, further improving the sustainability of the highly promising APS technique.

Acknowledgements

This work was supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (ERC StG 714744 SAMBA). WdV and JDW acknowledge funding support from the "Vemieuwingsimpuls" programme through project VIDI 723.015.003 (financed by the Netherlands Organization for Scientific Research, NWO). PPI Sari thanks the European Commission - Education, Audiovisual and Culture Executive Agency (EACEA) for the Erasmus Mundus scholarship under the program: Erasmus Mundus Master in Membrane Engineering for a Sustainable World (EM3E-4SW), Project Number- 574441-EPP-1-2016-1-FR-EPPKA1-JMD-MOB. We also thank Bob Siemerink for his help with FE-SEM.

5.5 Supporting Information – S5

Figure S5.1 Time-lapse photographs of PSS-PEI (25 kDa) membranes prepared in pH 4 acetate buffer bath at different concentration of acetate buffer. The membrane shown in the top row was prepared in 0.1 M while the one shown at the bottom row was prepared in 0.5 M acetate buffer bath. The time (t) in the photos indicate the time after immersion of the glass plate in the coagulation bath.

Figure S5.2 Top surface and cross-section SEM images of PSS-PEI (25 kDa) membranes prepared in 1 M acetate buffer bath at pH 4.

Figure S5.3 Time-lapse photographs of PSS-PEI (25 kDa) membranes prepared in 0.5 M acetate buffer bath at different pH. The time (t) in the photos indicate the time after immersion of the glass plate in the coagulation bath.

Figure S5.4 Photographs of PSS-PEI (25 kDa) membranes prepared in 0.5 M acetate buffer baths at different values of pH.

Figure S5.5 Sieving curves obtained by Gel Permeation Chromatography (GPC) for estimating the molecular weight cut-off of PSS-PEI (25 kDa) membranes prepared in 0.5 M acetate buffer at pH 4. a) 0 wt% GA and b) 0.01 wt% GA in the coagulation bath.

Figure S5.6 Pore size distribution of the PSS:PEI (25 kDa) membranes prepared in 0.5 M acetate buffer baths at pH 3.6 with the addition of 0.01 wt% GA. The pore size was estimated by measuring the individual pores from the top surface SEM image shown as **Figure 5.1a** in section 5.3.1. The average pore size was estimated by generating a histogram with a bin size of 25 nm.

Figure S5.7 Top surface FE-SEM images of the membranes prepared in 0.5 M acetate buffer at pH 4 with 0.01 wt% GA.

Figure S5.8 Long term pure water permeability of the PSS-PEI (25 kDa) membranes prepared in pH 4 acetate buffer with 0.01 wt% GA. The test was conducted with three different membranes at 4 bar of applied water pressure.

Figure S5.9 Photographs of the PSS-PEI (25) membranes after 10 days in pH 1 – pH 12 solutions. The membranes were prepared in 0.5 M acetate buffer bath at pH 4.

Figure S5.10 Photographs of the PSS-PEI (750 kDa) membranes prepared in 0.5 M acetate buffer baths at different values of pH.

Figure S5.11 Pore size distribution of the PSS:PEI (750 kDa) membranes prepared in 0.5 M acetate buffer baths at pH 3.6 and pH 4. The pore size was estimated by measuring the individual pores from the top surface SEM image shown as **Figure 5.6a, b** in section 5.3.4. The average pore size was estimated by generating a histogram with a bin size of 20 nm.

Figure S5.12 SEM images of PSS-PEI (750 kDa) membranes prepared in coagulation baths at different pH showing the full cross-section morphology. a) pH 3.6, b) pH 4, c) pH 4.5, and d) pH 5. It was observed that the membranes prepared in pH 4.5 had delaminated structures with pH 5 showing extreme delamination as only a small portion of the membrane can be seen in the image. A possible reason for delamination could be the brittle nature of these membranes and relatively porous support, such as in case of pH 5 membranes, which causes the structure to collapse.

Figure S5.13 Top surface and cross-section SEM images of crosslinked PSS-PEI (750 kDa) membranes showing the effect of coagulation bath pH on the membrane structure. The membranes were cast in 0.5 M acetate buffer coagulation baths at different values of pH with the addition of 0.01 wt% GA. a) pH 3.6, b) pH 4, c) pH 4.5, and d) pH 5.

Figure S5.14 Time-lapse photographs of PSS-PEI (25 kDa) and PSS-PEI (750 kDa) membranes prepared in 0.5 M acetate buffer bath at pH 4. The time (t) in the photos indicate the time after immersion of the glass plate in the coagulation bath.

5.6 References

- [1] S. Loeb, S. Sourirajan, Sea Water Demineralization by Means of an Osmotic Membrane, in: Saline Water Conversion—II, American Chemical Society. SE-9 (1963) 117-132. doi:10.1021/ba-1963-0038.ch009.
- [2] H. Strathmann, K. Kock, P. Amar, R.W. Baker, The formation mechanism of asymmetric membranes, Desalination. 16 (1975) 179–203. doi:10.1016/S0011-9164(00)82092-5.
- [3] H. Strathmann, K. Kock, The formation mechanism of phase inversion membranes, Desalination. 21 (1977) 241–255. doi:10.1016/S0011-9164(00)88244-2.
- [4] G.R. Guillen, Y. Pan, M. Li, E.M.V. Hoek, Preparation and characterization of membranes formed by nonsolvent induced phase separation: A review, Ind. Eng. Chem. Res. 50 (2011) 3798–3817. doi:10.1021/ie101928r.
- [5] D. Prat, J. Hayler, A. Wells, A survey of solvent selection guides, Green Chem. 16 (2014) 4546–4551. doi:10.1039/c4gc01149j.
- [6] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restr. Off. J. Eur. Union. 99 (2018) 3.
- [7] J. Sherwood, T.J. Farmer, J.H. Clark, Catalyst: Possible Consequences of the *N*-Methyl Pyrrolidone REACH Restriction, Chem. 4 (2018) 2010–2012. doi:10.1016/j.chempr.2018.08.035.
- [8] A. Figoli, T. Marino, S. Simone, E. Di Nicolò, X.-M. Li, T. He, S. Tornaghi, E. Drioli, Towards non-toxic solvents for membrane preparation: a review, Green Chem. 16 (2014) 4034. doi:10.1039/C4GC00613E.
- [9] T. Marino, F. Galiano, A. Molino, A. Figoli, New frontiers in sustainable membrane preparation: Cyrene™ as green bioderived solvent, J. Memb. Sci. 580 (2019) 224–234. doi:10.1016/j.memsci.2019.03.034.
- [10] T. Marino, F. Galiano, S. Simone, A. Figoli, DMSO EVOL™ as novel non-toxic solvent for polyethersulfone membrane preparation, Environ. Sci. Pollut. Res. 26 (2019) 14774–14785. doi:10.1007/s11356-018-3575-9.
- [11] W.M. De Vos, (Universiteit Twente), Aqueous phase separation method, U.S. Patent Application no. 15/972,273, 2018.
- [12] J. D. Willott, W. M. Nielen, W. M. de Vos, Stimuli-Responsive Membranes through Sustainable Aqueous Phase Separation, ACS Appl. Polym. Mater. 2 (2019) 659–667. doi:10.1021/acsapm.9b01006.
- [13] B. Philipp, H. Dautzenberg, K.J. Linow, J. Kötz, W. Dawydoff, Polyelectrolyte complexes - recent developments and open problems, Prog. Polym. Sci. 14 (1989) 91–172. doi:10.1016/0079-6700(89)90018-X.
- [14] J. Fu, H.M. Fares, J.B. Schlenoff, Ion-Pairing Strength in Polyelectrolyte Complexes, Macromolecules. 50 (2017) 1066–1074. doi:10.1021/acs.macromol.6b02445.

- [15] A.S. Michaels, Polyelectrolyte Complexes, *Ind. Eng. Chem.* 57 (1965) 32–40. doi:10.1021/ie50670a007.
- [16] M. Gai, J. Frueh, V.L. Kudryavtseva, R. Mao, M. V. Kiryukhin, G.B. Sukhorukov, Patterned Microstructure Fabrication: Polyelectrolyte Complexes vs Polyelectrolyte Multilayers, *Sci. Rep.* 6 (2016). doi:10.1038/srep37000.
- [17] A.A. Antipov, G.B. Sukhorukov, Polyelectrolyte multilayer capsules as vehicles with tunable permeability, in: *Adv. Colloid Interface Sci.* 111 (2004) 49–61. doi:10.1016/j.cis.2004.07.006.
- [18] M.I. Baig, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.
- [19] M.I. Baig, J.D. Willott, W.M. de Vos, Tuning the structure and performance of polyelectrolyte complexation based aqueous phase separation membranes, *J. Memb. Sci.* 615 (2020) 118502. doi:10.1016/j.memsci.2020.118502.
- [20] K. Sadman, D. E. Delgado, Y. Won, Q. Wang, K. A. Gray, K. R. Shull, Versatile and High-Throughput Polyelectrolyte Complex Membranes via Phase Inversion, *ACS Appl. Mater. Interfaces.* 11 (2019) 16018–16026. doi:10.1021/acsami.9b02115.
- [21] E. N. Durmaz, M. I. Baig, J. D. Willott, W. M. de Vos, Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 2612–2621. doi:10.1021/acsapm.0c00255.
- [22] J. Kamp, S. Emonds, J. Borowec, M.A. Restrepo Toro, M. Wessling, On the organic solvent free preparation of ultrafiltration and nanofiltration membranes using polyelectrolyte complexation in an all aqueous phase inversion process, *J. Memb. Sci.* 618 (2021) 118632. doi:10.1016/j.memsci.2020.118632.
- [23] H. Guo, Y. Ma, P. Sun, S. Cui, Z. Qin, Y. Liang, Self-cleaning and antifouling nanofiltration membranes - Superhydrophilic multilayered polyelectrolyte/CSH composite films towards rejection of dyes, *RSC Adv.* 5 (2015) 63429–63438. doi:10.1039/c5ra11438a.
- [24] Z. Qin, C. Geng, H. Guo, Z. Du, G. Zhang, S. Ji, Synthesis of positively charged polyelectrolyte multilayer membranes for removal of divalent metal ions, *J. Mater. Res.* 28 (2013) 1449–1457. doi:10.1557/jmr.2013.126.
- [25] J.M. Dickhout, J.M. Kleijn, R.G.H. Lammertink, W.M. De Vos, Adhesion of emulsified oil droplets to hydrophilic and hydrophobic surfaces-effect of surfactant charge, surfactant concentration and ionic strength, *Soft Matter.* 14 (2018) 5452–5460. doi:10.1039/C8SM00476E.
- [26] E.N. Durmaz, J.D. Willott, A. Fatima, W.M. de Vos, Weak polyanion and strong polycation complex based membranes: Linking aqueous phase separation to traditional membrane fabrication, *Eur. Polym. J.* 139 (2020) 110015. doi.org/10.1016/j.eurpolymj.2020.110015.
- [27] A. Von Harpe, H. Petersen, Y. Li, T. Kissel, Characterization of commercially available and synthesized polyethylenimines for gene delivery, *J. Control. Release.* 69 (2000) 309–322. doi:10.1016/S0168-3659(00)00317-5.
- [28] K.D. Demadis, M. Paspalaki, J. Theodorou, Controlled release of bis(phosphonate)

pharmaceuticals from cationic biodegradable polymeric matrices, *Ind. Eng. Chem. Res.* 50 (2011) 5873–5876. doi:10.1021/ie102546g.

[29] R.W. Baker, *Membrane technology and applications*, Third Edit, John Wiley & Sons, Chichester, UK, 2012.

[30] F.G. Donnan, Theory of membrane equilibria and membrane potentials in the presence of non-dialysing electrolytes. A contribution to physical-chemical physiology, *J. Memb. Sci.* 100 (1995) 45–55. doi:10.1016/0376-7388(94)00297-C.

[31] A. Anand, B. Unnikrishnan, J.Y. Mao, H.J. Lin, C.C. Huang, Graphene-based nanofiltration membranes for improving salt rejection, water flux and antifouling—A review, *Desalination*. 429 (2018) 119–133. doi:10.1016/j.desal.2017.12.012.

[32] A. Leo, C. Hansch, D. Elkins, Partition coefficients and their uses, *Chem. Rev.* 71 (1971) 525–616. doi:10.1021/cr60274a001.

[33] K.L. Cho, A.J. Hill, F. Caruso, S.E. Kentish, Chlorine resistant glutaraldehyde crosslinked polyelectrolyte multilayer membranes for desalination, *Adv. Mater.* 27 (2015) 2791–2796. doi:10.1002/adma.201405783.

[34] E. Virga, J. de Grooth, K. Žvab, W.M. de Vos, Stable Polyelectrolyte Multilayer-Based Hollow Fiber Nanofiltration Membranes for Produced Water Treatment, *ACS Appl. Polym. Mater.* 1 (2019) 2230–2239. doi:10.1021/acsapm.9b00503.

[35] W. Tong, C. Gao, H. Möhwald, Manipulating the properties of polyelectrolyte microcapsules by glutaraldehyde crosslinking, *Chem. Mater.* 17 (2005) 4610–4616. doi:10.1021/cm0507516.

[36] J.B. Lindén, M. Larsson, S. Kaur, W.M. Skinner, S.J. Miklavcic, T. Nann, I.M. Kempson, M. Nydén, Polyethyleneimine for copper absorption II: kinetics, selectivity and efficiency from seawater, *RSC Adv.* 5 (2015) 51883–51890. doi:10.1039/c5ra08029k.

[37] T. Takigawa, Y. Endo, Effects of glutaraldehyde exposure on human health, *J. Occup. Health.* 48 (2006) 75–87. doi:10.1539/joh.48.75.

[38] C.A. Smolders, A.J. Reuvers, R.M. Boom, I.M. Wienk, Microstructures in phase-inversion membranes. Part 1. Formation of macrovoids, *J. Memb. Sci.* 73 (1992) 259–275. doi:10.1016/0376-7388(92)80134-6.

[39] E.G. Towle, I. Ding, A.M. Peterson, Impact of molecular weight on polyelectrolyte multilayer assembly and surface properties, *J. Colloid Interface Sci.* 570 (2020) 135–142. doi:10.1016/j.jcis.2020.02.114.

[40] V. Starchenko, M. Müller, N. Lebovka, Sizing of PDADMAC/PSS complex aggregates by polyelectrolyte and salt concentration and PSS molecular weight, *J. Phys. Chem. B.* 116 (2012) 14961–14967. doi:10.1021/jp3095243.

[41] W.M. Nielen, J.D. Willott, W.M. de Vos, Aqueous Phase Separation of Responsive Copolymers for Sustainable and Mechanically Stable Membranes, *ACS Appl. Polym. Mater.* 2 (2020) 1702–1710. doi:10.1021/acsapm.0c00119.

[42] W.M. Nielen, J.D. Willott, Z.M. Esguerra, W.M. de Vos, Ion specific effects on aqueous phase separation of responsive copolymers for sustainable membranes, *J. Colloid Interface Sci.* 576

(2020) 186–194. doi:10.1016/j.jcis.2020.04.125.

“An experiment is a question which science poses to Nature and a measurement is the recording of Nature’s answer.”

- Max Planck

Chapter 6.

Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation

This chapter is published as:

E. N. Durmaz, **M. I. Baig**, J. D. Willott, W. M. de Vos, Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 2612–2621. doi:10.1021/acsapm.0c00255.

Abstract

Polymeric membranes are used on very large scales for drinking water production and kidney dialysis, but they are nearly always prepared using large quantities of unsustainable and toxic aprotic solvents. In this study, a water-based, sustainable and simple way of making polymeric membranes is presented without the need for harmful solvents or extreme pH conditions. Membranes were prepared from water-insoluble polyelectrolyte complexes (PECs) via aqueous phase separation (APS). Strong PEs, poly(sodium 4-styrenesulfonate) (PSS) and poly(diallyldimethylammonium chloride) (PDADMAC) were mixed in the presence of excess of salt, thereby preventing complexation. Immersing a thin film of this mixture into a low salinity bath induces complexation and consequently the precipitation of a solid PEC-based membrane. This approach leads to asymmetric nanofiltration membranes, with thin dense top layers and porous, macrovoid-free, support layers. While the PSS molecular weight and the total polymer concentrations of the casting mixture did not significantly affect the membrane structure, they did affect the film formation process, the resulting mechanical stability of the films and the membrane separation properties. The salt concentration of the coagulation bath has a large effect on membrane structure and allows for control over the thickness of the separation layer. The nanofiltration membranes prepared by APS have a low molecular weight cut-off (<300 Da), a high MgSO_4 retention ($\sim 80\%$) and good stability even at high pressures (10 bar). PE complexation induced APS is simple and sustainable way to prepare membranes where membrane structure and performance can be tuned with molecular weight, polymer concentration and ionic strength.

6.1 Introduction

Non-solvent Induced Phase Separation (NIPS) became the dominant technique to produce polymeric membranes shortly after its discovery in the 1960s. In this technique, a homogeneous polymer solution is cast and then immersed in a coagulation bath that contains non-solvent which has a low affinity for the polymer. The non-solvent, typically water, should be completely miscible with the solvent so that the non-solvent will replace the solvent when the cast film is immersed in the coagulation bath. Immersion in the non-solvent bath leads to the controlled precipitation of the polymer film into a porous membrane. The membrane structure and thus its performance depend on both the polymer/solvent/non-solvent interactions (thermodynamics) and the mass transport through the system (kinetics). For example, fast and immediate precipitation of a polymer often leads to asymmetric membranes [1]. These asymmetric membranes have thin, dense skin layers on top, that provide selectivity, and thicker porous parts that provide mechanical strength. The natural tendency of NIPS to form asymmetric structures is an important reason why NIPS was a major breakthrough [2].

NIPS is a simple and versatile technique, however, the solvents used for this process are nearly always dipolar aprotic solvents and these are mostly reprotoxic and harmful to the environment [3]. The most commonly used solvent is *N*-methylpyrrolidone (NMP), a solvent that has recently come under increased scrutiny, with the European Union introducing new regulations to restrict its usage from 2020 [4]. Figoli and co-workers reviewed publications using numerous non-toxic solvent replacements for NIPS and thermally induced phase separation (TIPS) processes [5]. In their detailed review, several solvents were evaluated as promising candidates to replace these harmful solvents; however, most of the alternatives come with their own downsides. Specifically,

some of the alternatives are unable to dissolve the desired polymers at high concentrations [6], others are expensive (e.g. ionic liquids) or produced using limited natural resources (e.g. solvents containing phosphorous) or have problematic hazardous properties (e.g. ionic liquids, dimethyl sulfoxide) [5]. Finally, the solvents should ideally be recyclable, and should thus be easy to separate from the non-solvent water after membrane formation.

While greener organic solvents are promising, an even more sustainable approach would be to use water as both the solvent and the non-solvent. To achieve this, a polymer is required that is soluble and insoluble in aqueous media depending on conditions such as pH, salinity and temperature. For example, poly(vinyl alcohol) [7] and hydroxypropylcellulose [8] membranes have been prepared in aqueous media via TIPS, followed by chemical crosslinking for stability. The membranes were evaluated in terms of phase behavior, mechanical properties, swelling and pure water permeabilities, but were not studied for their separation behavior. A major downside of TIPS is that typically only symmetric membranes can be formed; for asymmetric membranes a concentration gradient through the casting film (from top to bottom) is required as is the case for traditional NIPS [9]. Inspired by the traditional NIPS process, de Vos showed that aqueous phase separation can be achieved using weak polyelectrolytes whose solubility is pH-dependent [10]. Using this approach, Willott *et al.* prepared porous poly(4-vinylpyridine) asymmetric and symmetric membranes by variations of casting solution and coagulation bath composition [11].

Polyelectrolytes (PEs) are polymers that have charged repeating units accompanied by small counter-ions and due to the charged nature of the repeating units they dissociate in a polar media (e.g. water). When two oppositely charged PEs are mixed, they interact and can form polyelectrolyte complexes (PECs) which are typically water-insoluble. An important point to understand, especially for this work is that the driving force for complexation is the entropic gain via release of small counter-ions [12]. PEs are classified as weak or strong depending on the pH-response of the charges. If the monomers can dissociate or be neutralized depending on the pH of the medium, then the PE is classified as weak. On the other hand, for strong PEs the repeating units remain charged over entire pH range (i.e. pH 1–14). In this case, charges cannot be neutralized, but they can be screened by high salinity (i.e. excess counter-ions). The phase behavior of PECs as a function of salt concentration reveals that PECs exist in a homogeneous solution phase at high salinity while they are solid precipitates at low salinity [13,14]. These two points suggests that a phase separation method utilizing polyelectrolyte complexation can be used to prepare membranes. Significantly, PE complexation can be performed entirely in aqueous media thus eliminating the need for toxic solvents.

Coating layers of PECs sequentially, namely polyelectrolyte multilayers (PEMs) on porous support membranes has been demonstrated to give the membranes with excellent performance such as selectivity [15–19], stability [20], resistance to fouling [21,22], and hydrophilicity [16,21,23,24]. Of all systems studied, the combination of poly(sodium 4-styrenesulfonate) (PSS) and poly(diallyldimethylammonium chloride) (PDADMAC) was found to be especially promising due to the high resistance against chemical cleaning, showing a 100 times higher chemical stability against oxidants [20] and better selectivity towards fluoride [25], sulfate [26], and phosphate [27] ions compared to commercial membranes. pH stability of this PE pair is also outstanding, PSS-PDADMAC multilayer films exhibited similar wetting properties between pH 4 and 11 [28]. More significantly, PSS-PDADMAC coated membranes showed stable MgSO_4 retention even at high acid concentrations such as 3 M HCl [29]. Thus, polyelectrolyte

multilayer based nanofiltration membranes, especially of PSS and PDADMAC, hold a great promise. Unfortunately, the preparation of PEM membranes is very time consuming and laborious. Moreover, the support membrane is still produced with NIPS which requires the harmful solvents. For decades, using PEMs was the main way to facilitate polyelectrolyte complexes as functional materials since bulk PECs were known to be unprocessable due to being infusible and very brittle in dry state [30]. In 2009, the concept of saloplastics were introduced and pioneered to production of a new set of PEC-based materials [31]. The term saloplastic basically refers to polyelectrolyte complexes that can be processed after treatment with saline water. Schlenoff and coworkers demonstrated a great variety of possibilities that these materials can be applied [31–35]. Porous saloplastic materials are obtained by centrifugation [31,36] and electrospinning [37] of coacervate phases, or by desalting homogeneous PE solution in between semi-permeable membranes [38]. In addition, doped PECs can be extruded to obtain dense materials in various shapes (tape, tube, rod, fiber) [32,33] or spin coated [34,39], cast [40,41], and pressed in between templates [42,43] to obtain transparent films. Moreover, some of the saloplastics show self-healing behavior which can operate under room temperature and tuned by type of salt [35,44]. The majority of saloplastics reported in literature are composed of PSS-PDADMAC [31–34,37–39,42,43,45] emphasizing its properties such as chemical and thermal stability, biocompatibility and no requirement for crosslinking agent.

Addition to saloplastics mentioned above, PE complexation has been used by Sadman *et al.* to prepare porous membranes [46]. In their work, PECs were obtained by mixing two strong PE solutions. After PECs were extruded and treated with salt water annealing, they were partially dissolved at varying salt solutions to obtain coacervates and then cast into thin films. The resultant membranes had high pure water permeability (75 to $400 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) and high rejection towards polystyrene beads (100 nm and larger), indicating that these membranes were in the ultrafiltration (UF) range. This study showed that making membranes on the basis of polyelectrolyte complexation is possible, however, there were a couple of drawbacks related to the membrane production procedure. Besides the multiple step membrane preparation process, casting coacervates in different salinities instead of homogeneous solutions results in change in polymer concentration, and the hydration of the coacervates, which provides limited control over the membrane structure and performance and only UF membranes were prepared. In **Chapter 2** we demonstrated that it is also possible to prepare membranes by casting homogeneous PE mixtures instead of coacervates. A switch between two extreme pH regimes was used to control the complexation of a strong polyanion and a weak polycation. Polymer molecular weight, polymer concentration and coagulation bath salinity were the factors that gave a great control over the membrane structure and resulted in membranes ranging from microfiltration (MF) type to nanofiltration (NF) type.

In this work, we discuss the formation and performance of the PEC based nanofiltration membranes prepared by aqueous phase separation (APS). We use PSS and PDADMAC as the strong polyanion and polycation pair, respectively. Herein, a simple change in salt concentration is used to control complexation instead of switching between extreme pH values as was used in **Chapter 2**. Therefore by using a salt-switch, the membrane formation conditions are milder and the requirement for using a weak and strong PE pair is removed. In this study, a homogeneous mixture of the two strong PEs is prepared at a high salinity where the entropic driving force for complexation is eliminated. Therefore, the PE chains are in a dissolved and coiled form and surrounded by an excess of counter-ions (**Figure 6.1**). The homogeneous polyelectrolyte

Figure 6.1 A schematic illustration of membrane preparation procedure for salt triggered complexation induced aqueous phase separation. Homogeneous mixture of two oppositely charged PEs are mixed at high salinity, casted on a substrate and immersed in a low salinity bath.

mixture is cast on a substrate and immersed in a low salinity water bath. This dilutes the excess of counter-ions, and allows polyelectrolyte complexation based on counter-ion release. The oppositely charged PE chains interact with each other and form a water-insoluble polyelectrolyte complex. The precipitated polymer is considered to have an amorphous, entangled structure [30] and the charges are mostly compensated by an oppositely charged monomer rather than small counter-ions (see **Figure 6.1**). In preparing the PSS-PDADMAC membranes by complexation induced APS, we intend to combine the excellent separation performance of PSS-PDADMAC PEM-based nanofiltration membranes with a simple and sustainable production process. We investigate the effects of polymer concentration, molecular weight and coagulation bath salinity on membrane structure and performance. We show that nanofiltration membranes are obtained, of which the structure and performance can be tuned with the salinity of the coagulation bath. The performance of the membranes is studied by pure water permeability, salt retention and molecular weight cut-off measurements, at pressures up to 10 bars.

6.2 Experimental Section

6.2.1 Materials

Poly(sodium 4-styrenesulfonate) (PSS, Mw $\sim$ 70 kDa, 200 kDa and 1000 kDa in aqueous solution), Poly(diallyldimethylammonium chloride) (PDADMAC, Mw $\sim$ 200-350 kDa, 20 wt% in water), Magnesium Sulfate (MgSO_4) and 2-propanol (IPA) were purchased from Sigma-Aldrich. Poly(ethylene glycol) (PEG) of different molecular weights (200, 400, 600, 1000, 1500 and 2000 Da) were purchased from Merck. Sodium Chloride (NaCl, pharmaceutical grade, SanalP) was kindly supplied by Akzo Nobel.

6.2.2 Solution preparation

The as received PSS and PDADMAC solutions were used to prepare casting solutions containing 10 wt%, 12.5 wt%, and 15.4 wt% total polymer. Firstly, water (if needed) and NaCl were added to PSS and PDADMAC solutions, separately. After the solutions became homogeneous, they were mixed such that the monomer ratio is stoichiometric. Here, a stoichiometric monomer ratio means that the ratio of PSS monomers to PDADMAC monomers is equal to 1. For the mixtures with 17.5 wt% and 20 wt% polymer, stock solutions of PSS and PDADMAC were dried (separately) in an oven at 80 °C overnight. Then, the desired solutions were prepared by mixing the dried polymer, NaCl, and water. PSS and PDADMAC solutions were mixed and stirred over 16 hours to form a stoichiometric, amber-colored, homogeneous mixture. The mixture was left overnight, without stirring, to remove air bubbles. Properties of PE casting mixtures used in this study are listed in **Table 6.1**.

Table 6.1 Properties of the homogeneous PE mixtures used for membrane preparation.

PSS Mw (kDa)	PDADMAC Mw (kDa)	Total polymer concentration (wt%)
70		15.5
200		15.4
1000		15.5
200	200 – 350	10.0
200		12.5
200		17.5
200		20.0

6.2.3 Casting

Homogeneous mixtures were cast at a thickness 0.3 mm with casting knife on a transparent plastic sheet (referred to as acetate sheet by the provider, JEJE Produkt) and immediately immersed in a coagulation bath. The coagulation bath consisted of either Milli-Q[®] water (resistivity at 25 °C is 18.2 M Ω .cm) called 0 M, or 0.5 M, 1.0 M, 1.5 M and 2.0 M NaCl. After 10 minutes in the desired coagulation bath, the membranes were transferred to washing baths containing demineralized water and the washing bath was refreshed four times in total, to remove

any remaining salt. PSS-PDADMAC complexes do not swell in many organic solvents like isopropanol [47]. Therefore after the washing steps, the membranes were immersed in 30 vol%, then 60 vol%, then 90 vol% and lastly pure IPA baths so that membranes could be removed from the substrate without causing any deformation of the membrane. Membranes were stored in IPA prior to any filtration test.

6.2.4 Membrane characterization

Membrane samples were taken from IPA and air dried, then they were broken after immersion in liquid nitrogen. The samples were sputter coated with a 5 nm chromium layer (Quorum Q150T ES). Then the cross-section and surface morphologies of the membranes were investigated by scanning electron microscopy (SEM, JSM6010LA) integrated with energy dispersive X-ray spectrometer (EDS).

Besides observing and comparing cross-section morphologies of the membranes, the average skin layer thicknesses were also measured. To do that, cross-section images at x5000 magnification were analyzed with ImageJ software. The distance between the top edge of the cross-section and the closest visible pore to the edge is defined as the skin layer thickness. Multiple positions were measured and the average value is reported as the skin layer thickness of the membrane. A representative skin layer thickness measurement is given in *Figure S6.1* in the *supporting information*.

Membrane samples were taken from IPA, rinsed with demineralized water to exchange IPA and then the membranes were tested in terms of their filtration performance. First, pure water permeability measurements were conducted. For that, the membranes were placed in dead-end filtration cells in which pure water was pressurized towards the filtration system by nitrogen gas. Permeate was collected and its weight was measured as a function of time, giving the pure water flux (Jw). The membrane active area for the cells operated at 4 bar was 3.0 cm², while for the cells operated at 10 bar this was 15.3 cm². The permeability was calculated by taking the slope of flux over transmembrane pressure, Δp (bar), equation 6.1:

$$P = \frac{Jw}{\Delta p} \quad (6.1)$$

Where P is the permeability L·m⁻²·h⁻¹·bar⁻¹, and Jw is the water flux. After the pure water permeability measurements, the membranes were subjected to retention tests. For these tests, the same dead-end set-up was used and instead of pure water, a solution containing the carefully selected probe molecule (MgSO₄ and PEG) was fed while stirring the feed solution within the dead-end cell. Retention of the membrane was calculated using equation 6.2:

$$R = \left[1 - \frac{C_p}{\left(\frac{C_f + C_r}{2} \right)} \right] \times 100 \quad (6.2)$$

Where C_p , C_f , and C_r are the concentrations of the solute in the permeate, feed and in the retentate, respectively. The feed is the solution that was in the cell prior to the rejection test,

while the retentate is the solution that was left in the cell after the test (see *Figure S6.2* in the *supporting information*).

Pure water permeability and retention measurements were performed at the same transmembrane pressure for the same membrane piece (either 4 bar or 10 bar). Retention tests were performed for either a 5 mM MgSO_4 solution or a mixture of PEG molecules to investigate the molecular weight cut-off (MWCO) of the membranes. For both cases, approximately 20 mL of solution was fed to the filtration cell. The permeate was collected such that recovery ratio (permeate/feed, g/g) does not exceed 1/3 for MgSO_4 retention tests and 1/20 for MWCO tests in order to keep concentration polarization to a minimum. For MgSO_4 retention, concentrations of feed, permeate, and retentate samples were calculated by analyzing the conductivities of the samples. For MWCO measurements, a mixture of PEGs with molecular weights of 200, 400, 600, 1000, 1500 and 2000 Da was prepared so that each PEG was at a concentration of 1 g·L⁻¹. Samples were analyzed by Gel Permeation Chromatography with a size exclusion column (Agilent 1200/1260 Infinity GPC/SEC series, Polymer Standards Service column compartment and data center (UDC 810 Interface). Sample solution flow rate was 1 mL·min⁻¹ and eluent was 50 mg·L⁻¹ NaN_3 in Milli-Q[®] water, samples went through two Polymer Standards Service Suprema 8x300 mm columns in series: 1000 Å, 10 μm followed by 30 Å, 10 μm. Concentration vs molecular weight curves were obtained for feed, permeate, and retentate samples and converted into retention vs molecular weight graphs (i.e. a sieving curve). MWCO is defined as the molecular weight of the solute that the membrane retains by 90% i.e. where the sieving curve reaches the 90% level [48]. In this work, for some of these membranes, the sieving curve did not reach exactly 90% retention, although it reaches a plateau. This is an indication of a defect on the membrane and therefore, the maximum retention level that the curve reached was considered as the 100% rejection level. The MWCO value was estimated relative to the level considered for total rejection (see *Figure S6.3* in the *supporting information*).

6.3 Results and Discussion

In this work, porous polymeric films were prepared from polyelectrolyte complexes with the aqueous phase separation technique (see **Figure 6.1**). Diffusion of salt out of the film upon exposure to a low salinity bath was used to trigger PE complexation. In this section, we first explain the selection of a suitable polyelectrolyte mixture, more specifically we discuss the effect of PSS molecular weight and polymer concentration of the mixtures. Thereafter, we discuss the effect of coagulation bath salinity on the structure and the performance of the resulting membranes.

6.3.1 Selection of suitable polyelectrolyte mixture: Effect of molecular weight

Films were prepared by immersing a thin layer of a homogeneous PE mixture into a coagulation bath containing Milli-Q[®] water. These mixtures had the same polymer and salt concentrations (15.5 wt% polymer and 18 wt% NaCl) and only the PSS molecular weight was varied (70 kDa, 200 kDa and 1000 kDa) which will be referred as 70 kDa PSS, 200 kDa PSS and 1000 kDa PSS, respectively.

SEM images of the films are presented in **Figure 6.2**. Cross-section images of the films are shown

Figure 6.2 SEM images of cross-section and top surfaces of the membranes prepared with mixtures of varying PSS molecular weight. All cross-section images are at x1000 magnification while top surface images at x5000 magnification.

in the left column, and the top surface images are shown in the right column. The cross-section images clearly show that all the films have an asymmetric structure with thin dense layers at the top and porous support layers below. Higher magnification SEM images (Figure S6.4 and S6.5 in *supporting information*) show no visible pores on the surface (up to that magnification) indicating the density of the selective layers. Moreover, support layers have interconnected pore structure, with pores visible through other pores (i.e. open-cell spongy structure). Therefore it is expected that the selective layers dominate the resistance to permeation, while the support layers are highly permeable. These SEM images immediately demonstrate that our approach successfully leads to the formation of membranes with the highly desired asymmetric structure. Also striking is that no macrovoids are observed in the support structure: macrovoids are a common and generally undesired feature when preparing membranes by NIPS. The viscosity of the casting solution is typically a major factor controlling the phase inversion kinetics. Solutions with different viscosities are expected to phase separate at different rates and therefore lead to membranes with different cross-section morphologies. Although, there is a substantial difference in the viscosities of the mixtures with 70 kDa, 200 kDa and 1000 kDa PSS (see Table S6.1 in the *supporting information*), all three membranes have essentially the same asymmetric structure.

For all three asymmetric films, no defects and/or pores were observed from the surface SEM images at magnifications up to x10000 (see *Figure S6.4* in the *supporting information*). Some of the surface SEM images in this paper show particle-like structures on the membranes (like the ones prepared with 70 kDa and 1000 kDa PSS). The exact cause of these structures could not be determined, however, they are considered to be polymer precipitates since no substantial difference from the bulk of the film can be observed from the elemental analysis (see *Figure S6.6* in the *supporting information*). Additionally, no effect of these impurities was observed on the membrane performance tests.

No substantial differences between the films can be seen from the SEM images, but conversely there are distinct differences in the membrane performance. The pure water permeability (PWP) values of the membranes were measured at 4 bar with a dead-end filtration set-up. While a stable flux could not be achieved with the 70 kDa PSS film, the 200 kDa and 1000 kDa PSS films had stable PWP values of approximately $1.0 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ and $0.4 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively. Longer polymer chains (i.e. higher molecular weight) results in more chain entanglements and this in turn provides films with a greater mechanical strength [49]. A stable water flux was not observed for the 70 kDa PSS film, while the 200 kDa PSS and 1000 kDa PSS films showed good stability, indicating that higher molecular weights are needed to obtain enough entanglement for mechanical stability. *Figure S6.7* in the *supporting information* shows that the skin layer thicknesses of membranes prepared with the 200 kDa PSS and the 1000 kDa PSS are very close to each other, while the PWP values are quite different. This indicates that the membrane skin layer becomes denser with more entanglements leading to a lower permeability. Although the 1000 kDa PSS membrane is expected to show a better rejection, it has a much lower permeability than the 200 kDa PSS membrane and the membrane formation procedure is much more difficult and time-consuming compared to the 200 kDa PSS membrane due to gelation of the 1000 kDa PSS solution (see *Figure S6.8* in the *supporting information*). Since the 70 kDa PSS film did not show a stable membrane performance and the 1000 kDa mixture has such a high viscosity, the 200 kDa PSS mixture was used for further experiments.

6.3.2 Effect of overall polymer concentration

The polymer concentration of the casting solution is a widely used parameter for the NIPS process to control membrane structure [48]. For APS, homogeneous PE mixtures with different polymer concentrations ranging from 10 wt% to 20 wt% were prepared (see **Table 6.1**). 10 wt% polyelectrolyte mixture with 18 wt% salt is slightly turbid than the other (see *Figure S6.9* in the *supporting information*), however, that mixture was cast and formed a continuous film. **Figure 6.3** shows the cross-section and surface SEM images of the films prepared with mixtures at these different polymer concentrations. Films mentioned in this section will be referred to by the polymer concentration of the casting mixture.

Except for the 10 wt% film, all these films again have an asymmetric structure with a thin skin layer and a porous and sponge-like support layer. The cross-section of the 10 wt% film shows delamination within the entire structure and the surface is porous (defects) unlike others. For the 12.5 wt% film there is a dense skin layer, however, the skin layer is very thin and has some defects on the surface. Both of these films were mechanically weak and therefore, were not investigated further. Increasing the polymer concentration is known to reduce membrane pore size [48], and this has been observed for porous PSS-PDADMAC films in literature [38]. Therefore, polymer

Figure 6.3 SEM images for cross-section and top surfaces of the membranes prepared with mixtures of varying total polymer concentration. All cross-section images are at x2500 magnification and focused on the upper part of the membrane while surface images at x5000 magnification.

concentrations higher than 12.5 wt% are needed for mechanically stable membranes. SEM images

of the 15.4 wt%, 17.5 wt% and 20 wt% films are nearly identical. They have thicker skin layers (Figure S6.7 in the *supporting information*) when compared to 12.5 wt% film and similar pore structure for the support layers is observed. Again, to investigate the membrane properties, pure water permeability tests were conducted at 4 bar with a dead-end filtration set-up. Obtained PWP values are 1.0, 0.1, and 0.2 L·m⁻²·h⁻¹·bar⁻¹ for 15.4 wt%, 17.5 wt% and 20 wt% membranes, respectively. Skin layer thicknesses and the decrease in the PWP clearly show that increasing the polymer concentration densifies the skin layer leading to a lower water transport. These three membranes are good candidates to investigate further, but importantly, the preparation procedure (see Experimental Section) and high viscosity of the PE mixtures at 17.5 wt% and 20 wt% polymer (see Table S6.1 in the *supporting information*) makes them non-ideal for membrane production. For this reason the concentration of 15.4 wt% polymer mixture was chosen for all further experiments.

6.3.3 Effect of coagulation bath salinity

So far, the different polyelectrolyte mixtures were prepared and evaluated in terms of the membranes that they form. Although increasing the molecular weight of PSS and increasing the total polymer concentration does not affect the membrane morphology significantly, these factors do affect the membrane properties. The homogeneous polyelectrolyte mixture prepared using 200 kDa PSS and having 15.4 wt% polymer was chosen as the most promising mixture, because it is easy to prepare then cast and it leads to reasonable pure water permeabilities. In the following, this mixture is used and the NaCl concentration in the coagulation bath is varied from 0 M to 2 M to obtain membranes. The salinity of the coagulation bath will reduce the driving force for the complexation and thus slow down the diffusion of ions from the casting mixture to the bath. Therefore, it is expected that different membrane structures and performances can be obtained by varying the coagulation bath salinity.

Figure 6.4 shows SEM images of the films prepared with coagulation baths of different salinity. The left column gives images focused on the upper part of the cross-section, the right column gives the top surface images. It can be observed that all films have an asymmetric structure with a thin dense skin layer and porous support layer. The porous support layer is sponge-like in structure for the 0 M, 0.5 M and 1 M films, with relatively small interconnected pores. However, for 1.5 M and 2.0 M films, the internal pores are much larger and this makes the films mechanically less stable. As in the traditional phase separation process, precipitation kinetics are expected to be the major factor in determining the membrane structure. As the NaCl concentration in the coagulation bath increases, the precipitation takes longer (see Figure S6.10 in the *supporting information*). Since the driving force for polyelectrolyte complexation is the entropic gain due to the release of counter-ions, the salt ions present in the coagulation bath limit this release which leads to a slower complexation process and consequently, a slower precipitation of the PEC. It can be seen in Figure S6.10 in the *supporting information* that the precipitation rate of the 2.0 M film is much slower than the others, in fact, in order to solidify the film fully, it has to be transferred to a washing bath of demineralized water. Additionally, salt is known to be a plasticizer for PECs [30,50,51] and PSS-PDADMAC multilayers are known to undergo a so-called glass transition in salinities higher than 1.5 M NaCl [52,53]; because of this, many studies use 2.0 M NaCl to anneal PSS-PDADMAC multilayers [52,54]. Therefore, it is speculated that the combination of longer precipitation times and more mobile PE chains resulted in larger pores and/or defects for 1.5 M and 2.0 M films. Besides the large defects in the skin layer seen in the 2.0 M film surface SEM

Figure 6.4 SEM images for upper part of cross-section and top surfaces of the membranes prepared with varying salt concentrations of coagulation bath. All images are at x5000 magnification.

image, large cavities in the cross-section of the 1.5 M and 2.0 M films indicate that these films will not be as mechanically stable. Indeed, during the PWP measurements on these films, the

Table 6.2 Skin layer thickness and molecular weight cut-off values of membranes.

Membrane	Skin layer thickness (μm) ^(a)	MWCO (Da) ^(b)
0 M	0.6 ± 0.2	250 ± 30
0.5 M	1.0 ± 0.2	280 ± 40
1.0 M	1.2 ± 0.4	250 ± 30

^(a)Skin layer thicknesses were measured for at least 10 different points from one SEM image.

^(b)MWCO values are average of 3 measurements.

water flux was not stable and reproducible. Therefore, we did not continue characterizing these films further.

Morphology of a membrane is one of the factors that directly affects the membrane performances, however, especially for dense membranes, molecular properties such as charge and affinity towards solutes become very important. In this section we discuss the performance of the membranes prepared with the PE mixture with 200 kDa PSS and 15.4 wt% polymer, coagulated in either 0 M, 0.5 M or 1.0 M NaCl baths. For asymmetric membranes, the dense part (i.e. skin layer) provides the membrane its selectivity while porous part is very permeable and gives the mechanical support to the membrane. Therefore the resistance of the membrane towards water permeation is dominated by the skin layer and its thickness is inversely correlated to the permeability [2]. Comparing the 0 M, 0.5 M and 1.0 M films, the skin layer is the thickest for 1.0 M film (see **Table 6.2**) and the thinnest for 0 M film. Therefore, it is expected that the 1.0 M membrane will have the lowest permeability (the highest water resistance). The PWP values of membranes (**Figure 6.5**) range from $0.4 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ to $1.0 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. These values indicate that the membranes are in the dense nanofiltration (NF) range, and they are in agreement with what we expected from SEM images.

In order to understand the application range of these membranes, molecular weight cut-off measurements were performed. We stress that the MWCO values reported here provide information on the separation properties of the active separation layer. Still, in many cases we also observed defects that decreased the overall MWCO of the membranes. The high polydispersity of especially the PDADMAC studied in this work could play a major role in the occurrence of these defects, as polydispersity is known to affect phase separation behavior of the polymer in relation to membrane formation [55]. Reducing the occurrence of defects in these PSS-PDADMAC membranes will be critical in their further development.

Membranes with MWCO values between 200 Da and 1000 Da are considered as NF membranes [2] and as shown in **Table 6.2**, all three PEC membranes fall in this range and can be considered as dense NF membranes. Based on this criteria, these membranes would be very suitable for the removal or concentration of small organic molecules, for example in bio-refineries or in the removal of organics from waste water [2].

To further evaluate the performance of these novel NF membranes, the separation performance of the membranes towards multivalent ions was studied. For that, 5 mM of MgSO_4 is used as feed solution. Plain bars in **Figure 6.5** show the performance of three different membranes at 4 bar in

Figure 6.5 Pure water permeability and MgSO_4 retention of the membranes. The left hand side of the dashed line (plain bars) shows the results of the filtrations at 4 bar while the right hand side of the line (patterned bars) is at 10 bar. Pure water permeability values are the average and error bars are the standard deviation of at least five measurements. Retention values are from at least three different measurements.

terms of pure water permeability (pink/red bars) and MgSO_4 retention (white bars). Although the PWP values progressively decrease with increasing skin layer thickness, MgSO_4 retentions of the membranes increase from approximately 62% to 81%.

The MWCO, PWP, and salt retention data shows that these membranes perform in the NF range, however, NF membranes are preferably operated at pressures higher than 4 bar [48]. In order to understand if these membranes can operate under these more challenging conditions, filtration experiments were also performed at 10 bar for the 0 M membrane. Patterned bars in **Figure 6.5** show the performance at 10 bar. Firstly, the PWP at 4 bar is $1.0 \pm 0.2 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, while the one at 10 bar is also $1.0 \pm 0.1 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. This constant PWP illustrates that the membrane flux is linearly proportional to the transmembrane pressure, moreover, the membranes can withstand 10 bar of pressure without structural compaction or defect formation. It needs to be noted that for this membrane 10 bar was found to be the limit of stability, above this pressure an unstable performance was observed. However, at 10 bar, the water flux was stable for over 20 continuous hours and over a total of 50 hours during the PWP measurements. **Figure 6.5** shows that the MgSO_4 retention at 10 bar is approximately 83%, while at 4 bar the retention is around 63%. This is in line with the expectation that these membranes function as dense membranes that separate on the basis of solution diffusion. An increase in pressure leads to a higher driving force for water permeation but not for the salt molecules. With increased water transport and similar salt transport the effective retention increases [2].

The PWP values reported here are consistently low relative to the ones of PSS-PDADMAC multilayer membranes in literature (5 to $15 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) [20,29,56–59]. This variation might

Figure 6.6 Pure water permeability values of 0 M, 0.5 M, and 1.0 M membranes. The test was performed once for all the three membranes for approximately 55 hours.

be due to differences in selective layer thickness and density. On the other hand, MgSO_4 retentions are reasonably comparable, in literature, best results varies from 60% to more than 90%. Besides experimental differences, the defects observed in MWCO tests may be the cause of being near to the low-end of this range. Although this comparison indicates there is still room for improvement, it also implies that membrane formation via salinity change APS technique is a good direction to follow for the preparation of sustainable NF membranes.

The stability of the membranes was not only evaluated as a function of transmembrane pressure but also as a function of time. Structural compaction is typically indicated by a decrease in water flux over time and is generally seen for polymeric membranes at the beginning of a filtration. However, a stable membrane is expected to maintain a persistent flux after the initial compaction period. In **Figure 6.6**, the water permeability of 0 M, 0.5 M and 1.0 M membranes are given. The pure water permeability tests were continued over 55 hours for each membrane. After a compaction period of less than 5 hours (not included in the graph), the membranes showed a stable permeability. It needs to be noted that the erratic flux behavior is not an indication of instability of the flux but they are deviations resulting from the experimental set-up. These membranes thus show excellent stability over time when exposed to pure water. In some cases, exposure to MgSO_4 during the retention tests lead to a drop in flux. We expect that the ions are taken up by the membrane leading to some plasticization of the membrane matrix.

Together with the mechanical stability, these PSS-PDADMAC membranes are expected to be stable in organic solvents and under extreme pH conditions [29,47]. Indeed, 0 M membranes showed no observable changes when they are immersed in 1 M NaOH and 1 M HCl for 40 days (see *Figure S6.11* in supporting information).

In this work, PSS-PDADMAC polyelectrolyte complex membranes were prepared via a simple aqueous phase separation approach that does not use any organic solvents or harsh aqueous conditions like extreme pH values. This APS system has a natural tendency to form asymmetric, nanofiltration membranes. The membrane morphology can be tuned by coagulation bath salinity and the resultant membranes are macrovoid-free which is a highly beneficial feature for a phase separation approach. Separation performance and mechanical stability of the membranes indicate that they are promising candidates for NF applications. Moreover, after being used, the salts from the coagulation baths can easily be recycled making the overall system much more sustainable compared to conventional phase separation membranes. Overall, this study shows a unique and sustainable way of making polymeric nanofiltration membranes with good separation properties.

6.4 Conclusion

In this study, we produced membranes by aqueous phase separation (APS) induced by polyelectrolyte complexation. Complexation is achieved by exposing a thin film of a homogeneous mixture of polyanion and polycation prepared at high salinity to a coagulation bath with a low salinity. Complexation of the two strong polyelectrolytes leads to phase separation and to the formation of asymmetric membranes with dense top layers and porous support layers. The effects of polyanion molecular weight, total polymer concentration of the mixture, and the coagulation bath salinity on membrane formation were investigated. It was seen that increasing both the molecular weight of PSS and the total polymer concentration led to denser membrane matrices and also improved the mechanical properties of the films; likely due to more chain entanglements. The optimal casting mixture was found to be the one with 200 kDa PSS and 15.4 wt% polymer which combined the positives of ease of preparation with good mechanical properties of the resulting membranes.

In the second part of this work, the coagulation bath salinity was varied and resultant membranes were studied in terms of their morphology, permeability and retention performances. SEM cross-section images revealed that increasing the coagulation bath salinity resulted in membranes with thicker skin layers and larger pores in the support layers. At high bath salinities, namely 1.5 M and 2.0 M NaCl, the combined effects of longer precipitation times and more mobile PE chains resulted in structures that could not be used as stable membranes. However, at lower salinities (0 M, 0.5 M and 1.0 M NaCl), useful membrane structures were obtained. These membranes had water permeabilities ranging from 0.4 to 1.0 L·m⁻²·h⁻¹·bar⁻¹ and MWCO values between 200 and 300 Da. Together with these low MWCO values, good MgSO₄ retentions (>60%) were found showing that these membranes indeed function as nanofiltration membranes. All of these membranes show good long term stability at 4 bar of applied pressure, with the membrane produced at 0 M NaCl having good long term stability even at 10 bar. An increase in transmembrane pressure led to significant increases in ion retention (from approximately 60 to 80%), as expected for dense membranes that separate species on the basis of solution diffusion mechanism.

We have demonstrated that it is possible to prepare novel nanofiltration membranes with good mechanical properties and separation performance in a simple single step aqueous phase separation process. Further optimization of the APS process is expected to lead to higher water

fluxes, selectivities and better mechanical properties. This work thus demonstrates that APS is a very relevant and sustainable alternative to the traditional aprotic solvent based NIPS process. Interesting for future work is the fact that PSS-PDADMAC complexes are very stable in organic solvents, especially in non-polar ones [47]. Therefore, in further research these nanofiltration membranes will be investigated in terms of their organic solvent nanofiltration performance.

Acknowledgements

This work was supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (ERC StG 714744 SAMBA). W.d.V and J.D.W acknowledge funding support from the "Vernieuwingsimpuls" program through project number VIDI 723.015.003 (financed by the Netherlands Organization for Scientific Research, NWO).

6.5 Supporting Information – S6

Figure S6.1 A representative scheme for measurement of the skin layer thickness of PEC membranes. Green bars show the places that are measured and the average of the result of over 10 green bars were taken and reported as skin layer thickness in the paper.

Figure S6.2 Schematic drawing of dead-end filtration cells, indicating the feed, retentate and permeate solutions.

Figure S6.3 An example for sieving curves. This curve is for a 0.5 M membrane MWCO measurement. As mentioned in the paper, many times sieving curve did not reach the 100% retention level. Then a relative total rejection level was estimated as the maximum retention obtained from higher molecular weights. MWCO value was estimated as the molecular weight where the sieving curve reached the new 90%.

Figure S6.4 A representative SEM image of the membrane top surface at x10000 magnification. There is no pores observed up to this magnification. This image is for a membrane prepared from the mixture with 200 kDa PSS and 15.4% polymer and coagulation bath was Milli-Q[®] water.

Figure S6.5 A representative SEM image of the membrane cross-section focused near the skin layer at x10000 magnification. There is a dense skin layer and porous support layer with inter connected pores. This image is for a membrane prepared from the mixture with 200 kDa PSS and 15.4% polymer and coagulation bath was Milli-Q[®] water.

Figure S6.6 SEM image of a 0 M membrane and EDS map showing carbon, nitrogen, oxygen and sulfur distribution. Other than the particle at the bottom of the image, the map shows even distribution of the elements throughout the film. Therefore the particles on the surface are considered to be polymer-sourced.

Table S6.1 Compositions and viscosities of PE mixtures used in this study. Coaxial cylinder type rotational viscometer (HAAKETM ViscotesterTM 550, ThermoFisher Scientific, USA) was used to measure the viscosity of polyelectrolyte mixtures. Approximately 15 mL of mixture was poured into outer cylinder (SV-DIN) then inner cylinder is placed and viscometer was assembled. The dynamic viscosity was measured as a function of shear rate ($2.5 - 250 \text{ s}^{-1}$) at 293 K and the extrapolated values at 0 shear rate are reported below.

PSS Mw (kDa)	PDADMAC Mw (kDa)	Total polymer concentration (wt%)	Viscosity at zero s^{-1} shear rate (Pa·s)
70	200 – 350	15.5	2.7
200	200 – 350	15.4	6.8
1000	200 – 350	15.5	14.5
200	200 – 350	17.5	10.7
200	200 – 350	20.0	21.9

Figure S6.7 The skin layer thicknesses of the membranes prepared with mixtures of varying PSS molecular weight and varying polymer concentration. Mixtures with different PSS molecular weight have 15.4% polymer in total, and mixtures of varying polymer concentrations were prepared with 200 kDa PSS.

Figure S6.8 Image of 200 kDa and 1000 kDa PSS solutions, one minute after the vials were turned upside down showing that while 200 kDa PSS solution is a viscous liquid, 1000 kDa PSS is a gel.

Figure S6.9 Images of 10 wt% and 15.5 wt% polyelectrolyte solutions. Both solutions have 18 wt% NaCl. 10 wt% solution is slightly more turbid than the other indicating that beginning of phase separation.

Figure S6.10 Immersion of the casting mixture of 200 kDa PSS with 15.4% polymer in different coagulation baths. Salinity of coagulation baths are varying from 0 M to 2 M NaCl. The time-lapse photos indicate that it takes a longer time for the homogeneous clear mixture to become opaque solid film as the salt concentration of the coagulation bath increases. The casting film in 2.0 M NaCl bath was transferred to a washing bath of demineralized water in the 6th minute in order to solidify the film further and complete the phase separation. Inhomogeneity in the opaqueness of the film indicates the uneven density of the precipitated film.

Figure S6.11 Pieces of 0 M membrane immersed in 1 M NaOH (pieces on the top row) and 1 M HCl (pieces at the bottom) for 40 days. No change is observed in terms of opacity and size of the membrane pieces.

6.6 References

- [1] H. Strathmann, Introduction to Membrane Science and Technology, first, Wiley-VCH Verlag & Co. KGaA, Weinheim, 2011.
- [2] R.W. Baker, Membrane technology and applications, Third Edit, John Wiley & Sons, Chichester, UK, 2012.
- [3] D. Prat, J. Hayler, A. Wells, A survey of solvent selection guides, *Green Chem.* 16 (2014) 4546–4551. doi:10.1039/c4gc01149j.
- [4] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament and of the Council concerning the Registration, Evaluation, Authorisation and Restr. Off. J. Eur. Union. 99 (2018) 3.
- [5] A. Figoli, T. Marino, S. Simone, E. Di Nicolò, X.-M. Li, T. He, S. Tornaghi, E. Drioli, Towards non-toxic solvents for membrane preparation: a review, *Green Chem.* 16 (2014) 4034. doi:10.1039/C4GC00613E.
- [6] F. Prézéus, D. Chabni, L. Barna, C. Guigui, J.-C. Remigy, A metrics-based approach to preparing sustainable membranes: application to ultrafiltration, *Green Chem.* 21 (2019) 4457–4469. doi:10.1039/c9gc01178a.
- [7] O. M'barki, A. Hanafia, D. Bouyer, C. Faur, R. Sescousse, U. Delabre, C. Blot, P. Guenoun, A. Deratani, D. Quemener, C. Pochat-Bohatier, Greener method to prepare porous polymer membranes by combining thermally induced phase separation and crosslinking of poly(vinyl alcohol) in water, *J. Memb. Sci.* 458 (2014) 225–235. doi:10.1016/j.memsci.2013.12.013.
- [8] A. Hanafia, C. Faur, A. Deratani, P. Guenoun, H. Garate, D. Quemener, C. Pochat-Bohatier, D. Bouyer, Fabrication of novel porous membrane from biobased water-soluble polymer (hydroxypropylcellulose), *J. Memb. Sci.* 526 (2017) 212–220. doi:10.1016/j.memsci.2016.12.037.
- [9] H. Matsuyama, S. Berghmans, D.R. Lloyd, Formation of anisotropic membranes via thermally induced phase separation, *Polymer (Guildf)*. 40 (1999) 2289–2301.
- [10] W.M. De Vos, (Universiteit Twente), Aqueous phase separation method, U.S. Patent Application no. 15/972,273, 2018.
- [11] J.D. Willott, W.M. Nielen, W.M. de Vos, Stimuli-Responsive Membranes through Sustainable Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 659–667. doi:10.1021/acsapm.9b01006.
- [12] R. v. Klitzing, Internal structure of polyelectrolyte multilayer assemblies, *Phys. Chem. Chem. Phys.* 8 (2006) 5012. doi:10.1039/b607760a.
- [13] S. Lindhoud, M.A.C. Stuart, Relaxation Phenomena During Polyelectrolyte Complex Formation, in: *Polyelectrolyte Complexes Dispersed Solid State I Princ. Theory*, (2014) 139–172. doi:10.1007/12_2012_178.
- [14] S. Ali, V. Prabhu, Relaxation Behavior by Time-Salt and Time-Temperature Superpositions of Polyelectrolyte Complexes from Coacervate to Precipitate, *Gels*. 4 (2018) 11.

doi:10.3390/gels4010011.

- [15] M. Adusumilli, M.L. Bruening, Variation of ion-exchange capacity, ζ potential, and ion-transport selectivities with the number of layers in a multilayer polyelectrolyte film, *Langmuir*. 25 (2009) 7478–7485. doi:10.1021/la900391q.
- [16] W. Shan, P. Bacchin, P. Aimar, M.L. Bruening, V. V Tarabara, Polyelectrolyte multilayer films as backflushable nanofiltration membranes with tunable hydrophilicity and surface charge, *J. Memb. Sci.* 349 (2010) 268–278. doi:10.1016/j.memsci.2009.11.059.
- [17] R. Malaisamy, M.L. Bruening, High-flux nanofiltration membranes prepared by adsorption of multilayer polyelectrolyte membranes on polymeric supports, *Langmuir*. 21 (2005) 10587–10592. doi:10.1021/la051669s.
- [18] B. Tieke, F. Van Ackern, L. Krasemann, A. Toutianoush, Ultrathin self-assembled polyelectrolyte multilayer membranes, *Eur. Phys. J. E.* 5 (2001) 29–39. doi:10.1007/s101890170084.
- [19] L. Krasemann, B. Tieke, Selective ion transport across self-assembled alternating multilayers of cationic and anionic polyelectrolytes, *Langmuir*. 16 (2000) 287–290. doi:10.1021/la991240z.
- [20] J. de Grooth, B. Haakmeester, C. Wever, J. Potreck, W.M. de Vos, K. Nijmeijer, Long term physical and chemical stability of polyelectrolyte multilayer membranes, *J. Memb. Sci.* 489 (2015) 153–159. doi:10.1016/j.memsci.2015.04.031.
- [21] S.Y. Wong, L. Han, K. Timachova, J. Veselinovic, M.N. Hyder, C. Ortiz, A.M. Klibanov, P.T. Hammond, Drastically lowered protein adsorption on microbicidal hydrophobic/hydrophilic polyelectrolyte multilayers., *Biomacromolecules*. 13 (2012) 719–726. doi:10.1021/bm201637e.
- [22] W. Yu, J. Koc, J.A. Finlay, J.L. Clarke, A.S. Clare, A. Rosenhahn, Layer-by-layer constructed hyaluronic acid/chitosan multilayers as antifouling and fouling-release coatings, *Biointerphases*. 14 (2019) 051002. doi:10.1116/1.5110887.
- [23] J. Almodóvar, L.W. Place, J. Gogolski, K. Erickson, M.J. Kipper, Layer-by-layer assembly of polysaccharide-based polyelectrolyte multilayers: A spectroscopic study of hydrophilicity, composition, and ion pairing, *Biomacromolecules*. 12 (2011) 2755–2765. doi:10.1021/bm200519y.
- [24] E. V. Pasco, H. Shi, I. Xagorarakis, S.A. Hashsham, K.N. Parent, M.L. Bruening, V. V. Tarabara, Polyelectrolyte multilayers as anti-adhesive membrane coatings for virus concentration and recovery, *J. Memb. Sci.* 469 (2014) 140–150. doi:10.1016/j.memsci.2014.06.032.
- [25] S.U. Hong, R. Malaisamy, M.L. Bruening, Separation of fluoride from other monovalent anions using multilayer polyelectrolyte nanofiltration membranes, *Langmuir*. 23 (2007) 1716–1722. doi:10.1021/la061701y.
- [26] S.U. Hong, R. Malaisamy, M.L. Bruening, Optimization of flux and selectivity in $\text{Cl}^-/\text{SO}_4^{2-}$ separations with multilayer polyelectrolyte membranes, *J. Memb. Sci.* 283 (2006) 366–372. doi:10.1016/j.memsci.2006.07.007.
- [27] S.U. Hong, L. Ouyang, M.L. Bruening, Recovery of phosphate using multilayer polyelectrolyte nanofiltration membranes, *J. Memb. Sci.* 327 (2009) 2–5. doi:10.1016/j.memsci.2008.11.035.

- [28] M. Elzbieciak, M. Kolasinska, P. Warszynski, Characteristics of polyelectrolyte multilayers: The effect of polyion charge on thickness and wetting properties, *Colloids Surfaces A Physicochem. Eng. Asp.* 321 (2008) 258–261. doi:10.1016/j.colsurfa.2008.01.036.
- [29] K. Remmen, R. Schäfer, S. Hedwig, T. Wintgens, M. Wessling, M. Lenz, Layer-by-layer membrane modification allows scandium recovery by nanofiltration, *Environ. Sci. Water Res. Technol.* 5 (2019) 1683–1688. doi:10.1039/c9ew00509a.
- [30] P. Schaaf, J.B. Schlenoff, Saloplastics: Processing compact polyelectrolyte complexes, *Adv. Mater.* 27 (2015) 2420–2432. doi:10.1002/adma.201500176.
- [31] C.H. Porcel, J.B. Schlenoff, Compact Polyelectrolyte Complexes: “Saloplastic” Candidates for Biomaterials, *Biomacromolecules*. 10 (2009) 2968–2975. doi:10.1021/bm900373c.
- [32] R.F. Shamoun, A. Reisch, J.B. Schlenoff, Extruded saloplastic polyelectrolyte complexes, *Adv. Funct. Mater.* 22 (2012) 1923–1931. doi:10.1002/adfm.201102787.
- [33] Q. Wang, J.B. Schlenoff, Tough strained fibers of a polyelectrolyte complex: pretensioned polymers, *RSC Adv.* 4 (2014) 46675–46679. doi:10.1039/C4RA08733J.
- [34] K.D. Kelly, J.B. Schlenoff, Spin-Coated Polyelectrolyte Coacervate Films, *ACS Appl. Mater. Interfaces*. 7 (2015) 13980–13986. doi:10.1021/acsami.5b02988.
- [35] A. Reisch, E. Roger, T. Phoeung, C. Antheaume, C. Orthlieb, F. Boulmedais, P. Lavalle, J.B. Schlenoff, B. Frisch, P. Schaaf, On the Benefits of Rubbing Salt in the Cut: Self-Healing of Saloplastic PAA/PAH Compact Polyelectrolyte Complexes, *Adv. Mater.* 26 (2014) 2547–2551. doi:10.1002/adma.201304991.
- [36] H.H. Hariri, J.B. Schlenoff, Saloplastic Macroporous Polyelectrolyte Complexes: Cartilage Mimics, *Macromolecules*. 43 (2010) 8656–8663. doi:10.1021/ma1012978.
- [37] X. Meng, S.L. Perry, J.D. Schiffman, Complex Coacervation: Chemically Stable Fibers Electrospun from Aqueous Polyelectrolyte Solutions, *ACS Macro Lett.* 6 (2017) 505–511. doi:10.1021/acsmacrolett.7b00173.
- [38] K. Murakawa, D.R. King, T. Sun, H. Guo, T. Kurokawa, J.P. Gong, Polyelectrolyte complexation via viscoelastic phase separation results in tough and self-recovering porous hydrogels, *J. Mater. Chem. B*. 7 (2019) 5296–5305. doi:10.1039/c9tb01376h.
- [39] I.S. Kurtz, S. Sui, X. Hao, M. Huang, S.L. Perry, J.D. Schiffman, Bacteria-Resistant, Transparent, Free-Standing Films Prepared from Complex Coacervates, *ACS Appl. Bio Mater.* 2 (2019) 3926–3933. doi:10.1021/acsabm.9b00502.
- [40] M. Haile, O. Sarwar, R. Henderson, R. Smith, J.C. Grunlan, Polyelectrolyte Coacervates Deposited as High Gas Barrier Thin Films, *Macromol. Rapid Commun.* 38 (2017) 1600594. doi:10.1002/marc.201600594.
- [41] R.J. Smith, C.T. Long, J.C. Grunlan, Transparent Polyelectrolyte Complex Thin Films with Ultralow Oxygen Transmission Rate, *Langmuir*. 34 (2018) 11086–11091. doi:10.1021/acs.langmuir.8b02391.
- [42] K.G. Nikolaev, S.A. Ulasevich, O. Luneva, O.Y. Orlova, D. Vasileva, S. Vasilev, A.S. Novikov, E. V. Skorb, Humidity-Driven Transparent Holographic Free-Standing Polyelectrolyte Films, *ACS*

Appl. Polym. Mater. 2 (2020) 105–112. doi:10.1021/acsapm.9b01151.

[43] M. Gai, J. Frueh, V.L. Kudryavtseva, R. Mao, M. V. Kiryukhin, G.B. Sukhorukov, Patterned Microstructure Fabrication: Polyelectrolyte Complexes vs Polyelectrolyte Multilayers, *Sci. Rep.* 6 (2016). doi:10.1038/srep37000.

[44] H. Zhang, C. Wang, G. Zhu, N.S. Zacharia, Self-Healing of Bulk Polyelectrolyte Complex Material as a Function of pH and Salt, *ACS Appl. Mater. Interfaces.* 8 (2016) 26258–26265. doi:10.1021/acsami.6b06776.

[45] J. Fu, Q. Wang, J.B. Schlenoff, Extruded Superparamagnetic Saloplastic Polyelectrolyte Nanocomposites, *ACS Appl. Mater. Interfaces.* 7 (2015) 895–901. doi:10.1021/am5074694.

[46] K. Sadman, D. E. Delgado, Y. Won, Q. Wang, K. A. Gray, K. R. Shull, Versatile and High-Throughput Polyelectrolyte Complex Membranes via Phase Inversion, *ACS Appl. Mater. Interfaces.* 11 (2019) 16018–16026. doi:10.1021/acsami.9b02115.

[47] H.M. Fares, Q. Wang, M. Yang, J.B. Schlenoff, Swelling and Inflation in Polyelectrolyte Complexes, *Macromolecules.* 52 (2019) 610–619. doi:10.1021/acs.macromol.8b01838.

[48] M. Mulder, *Basic Principles of Membrane Technology*, 2nd ed., Kluwer Academic Publishers, Dordrecht, 1996.

[49] R. Seymour, C. Carraher, *Structure-Property Relationships In Polymer*, 1st ed., Plenum Press, New York, 1984.

[50] R. Zhang, Y. Zhang, H.S. Antila, J.L. Lutkenhaus, M. Sammalkorpi, Role of salt and water in the plasticization of PDAC/PSS polyelectrolyte assemblies, *J. Phys. Chem. B.* 121 (2017) 322–333. doi:10.1021/acs.jpcc.6b12315.

[51] L. Han, Z. Mao, H. Wuliyasu, J. Wu, X. Gong, Y. Yang, C. Gao, Modulating the structure and properties of poly(sodium 4-styrenesulfonate)/ poly(diallyldimethylammonium chloride) multilayers with concentrated salt solutions, *Langmuir.* 28 (2012) 193–199. doi:10.1021/la2040533.

[52] D.M. Reurink, J.P. Haven, I. Achterhuis, S. Lindhoud, (Erik) H.D.W. Roesink, W.M. de Vos, Annealing of Polyelectrolyte Multilayers for Control over Ion Permeation, *Adv. Mater. Interfaces.* 5 (2018). doi:10.1002/admi.201800651.

[53] R.F. Shamoun, H.H. Hariri, R.A. Ghostine, J.B. Schlenoff, Thermal transformations in extruded saloplastic polyelectrolyte complexes, *Macromolecules.* 45 (2012) 9759–9767. doi:10.1021/ma302075p.

[54] H.M. Fares, Y.E. Ghoussoub, R.L. Surmaitis, J.B. Schlenoff, Toward ion-free polyelectrolyte multilayers: Cyclic salt annealing, *Langmuir.* 31 (2015) 5787–5795. doi:10.1021/la504910y.

[55] P. Van De Witte, P.J.J. Dijkstra, J.W.A. Van Den Berg, J. Feijen, Phase separation processes in polymer solutions in relation to membrane formation, *J. Memb. Sci.* 117 (1996) 1–31. doi:10.1016/0376-7388(96)00088-9.

[56] C.V. Gherasim, T. Luelf, H. Roth, M. Wessling, Dual-Charged Hollow Fiber Membranes for Low-Pressure Nanofiltration Based on Polyelectrolyte Complexes: One-Step Fabrication

with Tailored Functionalities, *ACS Appl. Mater. Interfaces*. 8 (2016) 19145–19157. doi:10.1021/acsami.6b05706.

[57] D. Menne, J. Kamp, J. Erik Wong, M. Wessling, Precise tuning of salt retention of backwashable polyelectrolyte multilayer hollow fiber nanofiltration membranes, *J. Memb. Sci.* 499 (2016) 396–405. doi:10.1016/j.memsci.2015.10.058.

[58] J. Irigoyen, T. Laakso, N. Politakos, L. Dahne, A. Pihlajamäki, M. Mänttari, S.E. Moya, Design and Performance Evaluation of Hybrid Nanofiltration Membranes Based on Multiwalled Carbon Nanotubes and Polyelectrolyte Multilayers for Larger Ion Rejection and Separation, *Macromol. Chem. Phys.* 217 (2016) 804–811. doi:10.1002/macp.201500433.

[59] L.Y. Ng, A.W. Mohammad, C.Y. Ng, R. Rohani, Optimization of polymeric membrane characteristics through thermal treatment and deposition of polyelectrolyte layers using response surface modeling, *Adv. Polym. Technol.* 34 (2015) 1–15. doi:10.1002/adv.21472.

“No water, no life. No blue, no green.”

- Sylvia Earle

Chapter 7.

Hollow fiber PSS-PEI membranes prepared via sustainable Aqueous Phase Separation

This chapter is submitted as:

M. I. Baig, M. Pejman, J. D. Willott, A. Tiraferri, W. M. de Vos, Hollow fiber PSS-PEI membranes prepared via Aqueous Phase Separation

Abstract

Hollow fiber membrane geometry is the preferred choice for many commercial membrane operations. Traditionally, these membranes are prepared via the non-solvent induced phase separation technique (NIPS) where a polymer dope solution is pushed through a spinneret into a non-solvent bath. Unfortunately, the dope solution always contains a reprotoxic organic solvent such as *N*-methylpyrrolidone (NMP). Increasing restrictions on the use of NMP and related solvents have led to the development of sustainable alternatives like the aqueous phase separation (APS) technique which utilizes water as both the solvent and the non-solvent for the production of membranes. In this work, we demonstrate for the first time the production of sustainable hollow fiber membranes via the APS technique in a dry-jet wet spinning process. The dope solution comprising of poly(sodium 4-styrenesulfonate) (PSS) and polyethyleneimine (PEI) is prepared by directly mixing the two polyelectrolytes in a monomer molar mixing ratio of 1:2 (PSS:PEI) at a higher pH. This dope solution along with an aqueous bore liquid is pushed through a single orifice spinneret into an acetate buffer coagulation bath. PEI becomes charged at low pH and immediately forms a polyelectrolyte complex with PSS. The composition of the bore liquid and coagulation bath were systematically varied to study the effect on the structure and performance of the resulting hollow fiber membranes. Microfiltration type PSS-PEI hollow fiber membranes showing a complete retention of oil droplets were obtained via the APS technique. Similarly, ultrafiltration type membranes having a pure water permeability in the range of 12 – 15 L·m⁻²·h⁻¹·bar⁻¹ and a molecular weight cut-off of ~7800 – 11600 Da were successfully prepared. The research presented in this work demonstrates the versatility of APS and brings the approach one step closer to large scale use and production.

7.1 Introduction

Hollow fiber membranes were the result of research and development on reverse osmosis membranes, initiated by industrial giants such as Mahon, Dow and Du Pont in the 1960s [1]. Since then, they have been used as suitable candidates for many applications; from the medical field [2,3] to water purification [4–7] and gas separation [8,9]. There are clear advantages in using the hollow fiber membrane geometry as compared to the flat sheet and tubular geometries; they have higher per unit volume productivity resulting from high packing density and the subsequently substantial collective surface area [1]. To illustrate this point, a 0.04 m³ membrane vessel can house 575 m² of 90 μm-diameter hollow fibers, 30 m² of spiral-wound flat sheet membranes and only 5 m² of membrane area in tubular modulation [10]. Also, hollow fibers can be potted and hosted within standard-sized tubes for mass packing, as opposed to spiral-wound and tubular configurations which require additional hardware such as spacers and/or porous supports.

Preparation of hollow fibers is not without its challenges though. While these membranes allow upscaling for increased productivity, this function stems directly from the number of single fibers produced. Therefore, the fabrication process must be relentlessly stable as one defective membrane could compromise a whole bundle of fibers' performance.

Polymeric hollow fiber membranes are mostly produced via a procedure known as non-solvent induced phase separation (NIPS), first developed by Loeb and Sourirajan for flat sheet membrane

fabrication [11]. In NIPS, a solid membrane is obtained by the controlled precipitation of a polymer solution. However, the polymer solution typically organic contains solvents such as the reprotoxic NMP which is toxic and can adversely affect the human health while at the same time imposes massive recycling costs to satisfy stringent environmental regulations. Growing concerns have led to the restriction of NMP in the EU through the REACH legislation [12].

Water is the most abundant solvent available but this potential remains largely untapped since most polymers used for NIPS simply are not water-soluble. Enter polyelectrolytes (PE), a class of polymers soluble in water with a negative or positive charge on their repeating units, surrounded by counter ions. Upon interaction of two oppositely charged PEs, a gain in entropy due to the release of these counter ions leads to the formation of polyelectrolyte complexes (PEC) which can themselves be water-insoluble solid materials [13,14].

In the previous chapters we have successfully produced flat sheet membranes made of polyelectrolyte complexes in a completely aqueous environment by regulating the pH or the salinity as the phase separation stimuli, thereby completely eliminating the need for NMP [15–18]. In this Aqueous Phase Separation (APS) approach, water acts as both the solvent and the non-solvent according to the pH/salinity conditions. Control over the final pore structure through the phase inversion kinetics allows formation of a range of porous and dense membranes with good performance. Earlier in the thesis we discussed the effects of change in salinity, change in pH, and the crosslinking conditions on the process of PEC membrane preparation [16,19,20]. There, it was concluded that using poly(sodium 4-styrenesulfonate) (PSS) and the polycation poly(ethyleneimine) (PEI) is especially a promising system, as compared to the other systems as it operates under mild pH conditions and leads to higher water permeabilities for similar separation properties. The PSS-PEI pair had clear advantages over the PSS–poly(allylamine hydrochloride) (PSS-PAH) pair and the PSS and poly(diallyldimethylammonium chloride) (PSS-PDADMAC) pairs; it ensures operability in milder sustainable pH ranges as opposed to harsher conditions corresponding to PSS-PAH (pH ~ 14 to pH ~ 1) and improves low fluxes and limited pore size tunability of PSS-PDADMAC [21] while reducing its corresponding labor needed [22].

So far, all the APS studies have focused on producing flat sheet membranes. For larger scale applications, spiral-wound and hollow fiber modulations are primarily used. The hollow fiber membranes also have the advantage of less fouling propensity over the spiral-wound modulation (no need for spacers), while allowing a wide range of polymers to be used for optimal products [1]. Recently, Emonds *et al.* [23] managed to fabricate tubular PEC membranes using PSS-PDADMAC with salinity being the stimulus for phase separation. They managed to fabricate defect-free nanofiltration tubular membranes by adding glycerol to the bore fluid. However, preparing a stable hollow fiber membrane still remains a challenge. Naturally, focusing the attention towards producing hollow fiber PEC membranes is the next step in solvent-free membrane production via the APS for large-scale membrane applications.

In this study, for the first time we prepare PSS-PEI based hollow fiber membranes via the APS method. There are several reasons to choose PSS and PEI as the polyelectrolyte pair to produce hollow fiber membranes. First, the two polyelectrolytes can directly be mixed in aqueous conditions to obtain a homogeneous solution without any additives, as described in **Chapter 5**. In addition, the solution can be precipitated in mild pH of acetate buffer (pH $\sim 3.6 - 5$) conditions to obtain various types of membranes having tunable pore sizes. The concentration and pH of the acetate buffer were found to be the major factors influencing the precipitation

kinetics and the resultant morphology of PSS-PEI membranes. The concentration of the buffer determines its buffer capacity. As a result, the rate of PSS-PEI precipitation increases with the acetate buffer concentration. Here, we utilized the knowledge generated in **Chapter 5** to produce hollow fiber membranes via the dry-jet wet spinning method. In this method, there are two precipitation baths; one on the lumen side (bore liquid) and the second bath is outside the fiber. Consequently, the additional tuning parameters mean that the morphology of the fibers can be carefully controlled by systematically varying the composition of both the baths. Apart from these, the air gap length and the bore to dope flow rate ratio are also relevant during hollow fiber spinning that influence the final structure of the fibers [24–26]. SEM micrographs were recorded of the various fibers produced to observe the impact of individual factors on the shape and pore structure of the fibers. Pure water permeability (PWP) and retention tests were conducted to evaluate the performance of the resultant membranes. The research presented in this chapter provides a foundation for the production of sustainable hollow fiber membranes.

7.2 Experimental Section

7.2.1 Materials

The chemicals poly(sodium 4-styrene sulfonate) (PSS, powder form, Mw ~1000 kDa), branched polyethyleneimine (PEI) (>99%, Mw ~25 kDa), sodium acetate anhydrous (reagent plus, 99%), glacial acetic acid (ACS reagent, ≥99%), glutaraldehyde (GA, 50 wt% in water), glycerol (ACS reagent ≥99.5%), n-hexadecane (>99%), sodium dodecyl sulfate (SDS, >99%), oil red EGN (solvent red 26, analytical standard), polyethylene glycol (PEG) with molecular weights 1500, 3000, 6000, 10000, 20000, and 35000 Da, albumin from bovine serum (BSA) as lyophilized powder (≥98%), sodium phosphate dibasic heptahydrate (>99.9%), and sodium phosphate monobasic dihydrate (>99%) were purchased from Merck, The Netherlands. Milli-Q[®] Ultrapure water purification system was used to obtain deionized water. All the chemicals were used without any further purification.

7.2.2 Preparation of the dope solution

First, a 35 wt% aqueous solution of PSS was prepared by adding deionized water to pure PSS. Similarly, deionized water was added to PEI to obtain a 35 wt% aqueous solution. The two polyelectrolyte solutions were then mixed in a monomer molar mixing ratio of 1:2 of PSS:PEI to obtain a 35 wt% dope solution which was stirred until it became homogeneous. The molar mixing ratio was calculated based on the molecular weights of monomers of PSS (~206 Da) and PEI (~43 Da, per ethyleneimine unit). The composition of the dope solution is mentioned in **Table 7.1**. The pH of the dope solution was ~12 which was measured using a handheld pH meter (pH 110, VWR).

Table 7.1 Composition of the PSS-PEI dope solution.

Dope solution	PSS (wt%)	PEI (wt%)	Water (wt%)
PSS:PEI (1:2)	24.7	10.3	65

The viscosity of the dope solution was measured on a HAAKETM ViscotesterTM 550 Rotational Viscometer (ThermoFisher Scientific, USA). Approximately 25 mL dope solution was poured into SV-DIN spindle cylinder which was then mounted on the viscometer. The dynamic viscosity of the dope solution was measured at 20 °C with increasing shear rate (24.9 s⁻¹ to 1000 s⁻¹). The dope solution had a dynamic viscosity of $\sim 2.5 \pm 0.2$ Pa·s at a shear rate of 24.9 s⁻¹.

7.2.3 Hollow fiber membrane spinning

The PSS-PEI hollow fiber membranes were spun at room temperature using the dry-jet wet spinning method. The dope solution was first poured into a stainless steel syringe (Chemyx Inc, USA) and left to de-gas overnight to remove any air bubbles. The acetate buffer baths, used to precipitate PSS-PEI, were prepared by mixing acetic acid and sodium acetate in specific amounts to obtain buffer baths at pH 4 having different concentrations i.e. 0.1 M, 0.25 M, 0.4 M, 0.5 M, and 0.75 M. Similarly, the pH of the acetate buffer was also controlled from pH 3.6, 4, 4.5, and 5 by changing the amount of acetic acid and sodium acetate while keeping the concentration constant at 0.5 M. Furthermore, 0.01 wt% glutaraldehyde (GA) was added to all the coagulation baths as a crosslinking agent for the amines of PEI. On the other hand, four different types of bore liquids were used to produce hollow fibers: 1) deionized water, 2) aqueous solution of glycerol (30wt% and 50 wt%), 3) 0.25 M acetate buffer at pH 4, and 4) mixture of 0.25 M acetate buffer at pH 4 with 30 wt% glycerol.

Since the pH of the PSS-PEI dope solution is approximately ~ 12 , it is necessary to have a spinneret that can withstand high pH and high salinity. Therefore, a special single-orifice spinneret having no welded parts was used for the production of hollow fiber membranes. The diameter of the spinneret needle was 1 mm with a cap having a diameter of 1.6 mm. The flow rates of the dope and the bore liquid were kept constant at 3 mL·min⁻¹ and the air gap length was kept at ~ 11 cm for all the membranes. First, the bore liquid was pumped through the spinneret needle followed by the dope solution. The resultant fiber was allowed to fall in the coagulation bath under the action of gravity as shown in **Figure 7.1**. The resultant fibers were not drawn, meaning that there was no take-up velocity. The fibers were kept in the coagulation bath for 18 h, which is also the crosslinking time for GA. The fibers were then taken out, thoroughly washed, and stored in deionized water for further use.

7.2.4 Membrane characterization

The surface and cross-section morphology of the hollow fiber membranes was observed using scanning electron microscopy, SEM (JSM-6010LA, JEOL, Japan). All the membrane samples for SEM were first stored in a 20 wt% glycerol solution for 4 h, taken out, and then left to dry inside an aerated fume hood. For cross-section SEM imaging, the glycerol dried hollow fiber membranes were immersed in liquid N₂ for 20 s and carefully fractured to reveal the cross-section. The SEM samples were then stored in a vacuum oven operating at 30 °C for 24 h. Before taking the SEM images, samples were sputter coated with a 5 nm thin layer of Pt/Pd alloy using Quorum Q150T ES (Quorum Technologies, Ltd., UK) sputter coater.

For pure water permeability (PWP) measurements, the hollow fiber membranes were first potted into modules having one fiber each with an effective length of 6.5 cm. For each different type of membrane, three modules were prepared and the average value with standard deviation is

Figure 7.1 Schematic illustration of the dry-jet wet spinning process to produce PSS-PEI hollow fiber membranes via the aqueous phase separation (APS) technique. The dope solution contains the strong polyanion, PSS, in its charged (extended conformation) state and PEI in its uncharged state. The dope solution is pushed through the single-orifice spinneret and is immersed into acetate buffer coagulation bath where PEI becomes charged and forms a polyelectrolyte complex with PSS.

reported here. The PWP was measured in a dead-end configuration with a shell side feed, see Figure S7.1, supporting information. The permeability tests were conducted at an applied water pressure of 1 bar and the mass of the permeating water was measured automatically on a weighing balance connected to a computer. The PWP (P , in $\text{L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$) was calculated using equation 7.1:

$$P = \frac{Jw}{\Delta p} \quad (7.1)$$

Here Jw is the pure water flux calculated from the change in permeate volume (L) per unit effective membrane area (3.26 cm^2) per unit time (h) and Δp is the pressure difference (bar) between the feed and the permeate side.

The microfiltration performance of the membranes was evaluated using an oil-in-water emulsion that was prepared following the procedure described by Dickhout *et al.* [27]. Briefly, $100 \text{ mg}\cdot\text{L}^{-1}$

n-hexadecane containing 20 mg·L⁻¹ Oil red EGN (dye) was added to 463 mg·L⁻¹ SDS while stirring at 14000 rpm for 20 min. The average diameter of the oil droplet in the emulsion was 3–4 μm. Oil red EGN is only soluble in n-hexadecane and therefore, is used as a marker for the oil droplets. The n-hexadecane oil droplet retention tests were conducted at 0.4 bar of feed pressure in the dead-end configuration. The feed and permeate samples were analyzed via UV-vis spectrophotometer (Shimadzu UV-1800, Japan) at $\lambda_{\max} = 521$ nm, which corresponds to the maximum absorbance wavelength of the dye. A calibration curve was obtained with the known concentrations of n-hexadecane in SDS emulsion on the x-axis and the UV-vis absorbance on the y-axis. This calibration curve resulted in a straight line which means that the absorbance data could be directly correlated to the concentration of n-hexadecane in the sample. The retention (*R*) was then calculated using equation 7.2:

$$R = \left[1 - \frac{C_p}{C_f} \right] \times 100 \quad (7.2)$$

Where C_p and C_f are the concentration of n-hexadecane in the permeate and the feed side, respectively.

For determining the molecular weight cut-off (MWCO) of the membranes, an aqueous solution of PEGs having different molecular weights i.e. 1500, 3000, 6000, 10000, 20000, and 35000 Da was used. This solution was prepared by dissolving 1 g·L⁻¹ of each PEG in deionized water. The PEG solution was filtered through the membranes in a dead-end configuration with feed from the shell side. The feed and the permeate were collected and analyzed via Gel Permeation Chromatography (GPC, Agilent 1200/1260 Infinity GPC/SEC series, Polymer Standards Service data center and column compartment). Milli-Q[®] ultrapure water containing 50 mg·L⁻¹ NaN₃ was used as the eluent at flow rate of 1 mL·min⁻¹ through the GPC column (10 μm Polymer Standards Service Suprema 8 × 300 mm 1000 Å and 10 μm 30 Å, connected in series). The concentration of PEGs in feed and permeate were determined via the refractive index and the retentions were then calculated using equation 7.2. MWCO was estimated by constructing a sieving curve of retention (%) on y-axis and the molecular weight of PEG (Da) on the x-axis. The molecular weight of PEG that showed 90% retention was the MWCO of the membrane.

The ultrafiltration performance of the hollow fiber membranes was analyzed similarly by filtering an aqueous solution of BSA through the membranes in a dead-end configuration at 1 bar of pressure with a shell side feed. The solution was prepared by dissolving 0.1 wt% BSA in 0.1 M phosphate buffer at pH 7.4. The pH was adjusted using 0.1 M HCl/NaOH solution. The phosphate buffer consisted of sodium phosphate dibasic heptahydrate and sodium phosphate monobasic dihydrate. The feed and permeate samples were collected and analyzed via UV-vis spectrophotometer at $\lambda_{\max} = 280$ nm which is the maximum absorbance wavelength of BSA. The BSA retention of was calculated using equation 7.2.

7.3 Results and Discussion

7.3.1 Composition of the bore liquid

In comparison to the flat sheet membranes, the hollow fiber membrane geometry provides additional parameters to control the rate of precipitation and hence the resulting membrane morphology. One such parameter is the composition of the bore liquid [28,29]. Having the same bore liquid as the coagulation bath can result in hollow fiber membranes with two skin layers. In this work, the aim was to have skin layer only on the outer surface of the hollow fiber with a relatively porous inner surface (lumen side). This was achieved by having 0.5 M acetate buffer at pH 4 in the coagulation bath which is a strong non-solvent for PSS-PEI and provides a dense skin layer on the outer surface as described in **Chapter 5**. As for the bore liquid, the composition was carefully selected after several trials to obtain mechanically strong membranes having porous lumen side.

First, only deionized water was used as the bore liquid which formed membranes without a proper hollow structure, see **Figure 7.2a**. Water at neutral pH does not trigger polyelectrolyte complexation between PSS and PEI and as a consequence, the direction of precipitation is from the outside of the fiber (acetate buffer bath) towards the inner lumen side (bore side, water). Furthermore, the combination of viscosity and the flow rate of the water in bore liquid is not sufficient to maintain the hollow structure at the lumen side. Therefore, to make the fibers more hollow, the bore liquid flow rate was first increased to 5 mL·min⁻¹ and then to 6 mL·min⁻¹. However, this approach resulted in fibers having thinner walls causing them to break easily. While these initial measurements did not immediately lead to ideal HF membranes, they do already provide clear indications that the HF geometry is possible with the APS approach, but further tuning is required.

Another approach to improve the hollowness of the fibers was to increase the viscosity of the bore liquid. It is known from literature that glycerol increases the viscosity of the bore liquid and prevents the hollow fiber membranes from collapsing [25]. Therefore, aqueous solutions of 30 wt% and 50 wt% glycerol were used as bore liquids and the effects can clearly be observed in the cross-section SEM images shown in **Figure 7.2c** and **e** where the resultant membranes have hollow lumen contours. However, these membranes lacked the mechanical strength to sustain 1 bar of feed water pressure. This is because no precipitation occurs at the lumen side as the combination of water and glycerol is not a non-solvent for PSS-PEI. In this case too, the sole direction of precipitation is from the outside of the fiber (acetate buffer) towards the lumen side. Consequently, the lumen surfaces are completely porous with uneven porosity as shown in **Figure 7.2d-f** and does not provide adequate mechanical strength for the hollow fibers to sustain pressure.

Conversely, using a strong non-solvent for PSS-PEI, such as the acetate buffer, in the bore liquid results in dense skin layers on the lumen of the hollow fiber membranes. *Figure S7.2* in the *supporting information* shows such hollow fiber membranes prepared using different concentrations of pH 4 acetate buffer as the bore liquid. The coagulation bath remained the same i.e. 0.5 M acetate buffer with 0.01 wt% GA. It is known from **Chapter 5** that the rate of precipitation increases with the increase in acetate buffer concentration and denser membranes are typically obtained at a higher concentration of the acetate buffer [32]. This is because the

Figure 7.2 Cross-section and inner (lumen side) surface SEM images of PSS-PEI hollow fiber membranes showing the effect of adding glycerol in the bore liquid. Images a) – b): only water, c) – d), 30 wt% glycerol, and e) – f) 50 wt% glycerol as the bore liquid. The membranes were prepared in coagulation baths containing 0.5 M acetate buffer at pH 4 with 0.01 wt% glutaraldehyde.

buffer capacity increases at higher concentrations thereby lowering the pH of the PSS-PEI casting solution relatively quicker. Since pH is the driving force for this version of APS, a quick change in the solution pH at higher buffer concentrations results in rapid polyelectrolyte complexation of PSS and PEI.

The hollow fiber membranes prepared using acetate buffer in the bore liquid showed skin layers on both the lumen and the outer surfaces as shown in the cross-section images of Figure S7.2a, c, and e. However, the membranes were not perfectly hollow and showed irregular lumen side contours. Especially, when 0.75 M acetate buffer was used as the bore fluid, the resultant membranes showed an oval shaped lumen structure. Peng *et al.* concluded that oval shaped lumen in the hollow fiber membranes is due to the significantly faster precipitation rates and

can be controlled by reducing the rate of precipitation [30]. Since the precipitation rate of the membranes prepared in 0.25 M and 0.5 M acetate buffer is relatively slower than 0.75 M, the oval shaped contour of the hollow fiber does not exist in these membranes. Using a strong non-solvent in the bore means that the dope solution precipitates as soon as it comes in contact with the bore liquid and continues precipitating from the inside throughout the entire length of the air gap (~11 cm in this case, see **Figure 7.1**). A dense skin layer is immediately formed on the lumen side of the fiber due to instantaneous precipitation induced by the acetate buffer and acts as a barrier for further mass transfer. As a result, an asymmetric structure with a dense skin and a porous substructure is formed on the lumen side of the fiber. As soon as the dope solution comes in contact with the coagulation bath, precipitation also starts from the outer surface and continues towards inside. Consequently, a dense skin layer with a porous substructure is also formed at the outer surface of the fiber. These dense skin layers on both the ends of the fiber act as barriers for the solvent (high pH) and non-solvent (low pH buffer) exchange, resulting in asymmetric membrane morphology [31]. As a result, a three layered structure is formed where a highly porous layer is sandwiched between two relatively dense layers which ultimately leads to delamination, see the cross-section images in *Figure S7.2a, c, and e* in the *supporting information*. The rapid rate of precipitation on the lumen side eventually leads to hollow fibers having irregular contours.

The acetate buffer concentration in the bore liquid significantly influences the membrane morphology of the lumen surface. When 0.25 M acetate buffer is used as the bore liquid, the resultant hollow fiber membrane had porous lumen surface as seen in the SEM image shown in *Figure S7.2b*. As the acetate buffer concentration in the bore is increased to 0.5 M and then further to 0.75 M, the lumen side becomes more dense as shown in *Figure S7.2d and f*. This is expected because a higher concentration of acetate buffer leads to more dense membranes as described earlier. However, having dense skin layers on both the lumen and the outer surfaces of the hollow fibers made them mechanically weaker due to their three-layered delaminated structures and could not be processed further.

It has now been established that using glycerol as the bore liquid results in membranes having only outer skin layer and a completely porous lumen side while using acetate buffer as the bore liquid results in membranes having two skin layers with a porous structure sandwiched in between. Therefore, a combination of these two bore liquids can be beneficial to obtain a hollow fiber membrane that has an outer skin layer and also a relatively less porous lumen surface. While the acetate buffer is a strong non-solvent for PSS-PEI and facilitates rapid precipitation, the addition of glycerol to the bore liquid increases its viscosity and slows down the rate of precipitation. Thus, the concentration of glycerol and the acetate buffer can be carefully tuned to obtain desired membrane structures on the lumen side of the fiber. In this case, the concentration of glycerol was fixed at 30 wt% and the concentration of the pH 4 acetate buffer was then varied from 0.25 M to 0.75 M, *Figure S7.3* in *supporting information*. When the bore liquid containing 0.25 M acetate buffer with 30 wt% glycerol was used, the resultant hollow fiber membranes showed a relatively porous lumen surface (see *Figure S7.3b*). As the acetate buffer concentration in the glycerol containing bore is increased to 0.5 M and then further to 0.75 M, the resultant hollow fiber membranes again showed relatively dense skin layers on the lumen side of the fiber, see *Figure S7.3d and f*. As a result, these membranes with two skin layers were mechanically weak and could not sustain water pressures.

Therefore, the composition of the bore liquid was fixed at 0.25 M acetate buffer with 30 wt%

glycerol as this combination resulted in membranes having a proper hollow contour with relatively less porous lumen side.

7.3.2 Effect of acetate buffer concentration in the coagulation bath

Now that the composition of the bore liquid is fixed, the concentration of acetate buffer in the coagulation bath was investigated. **Figure 7.3** shows the cross-section SEM images of the PSS-PEI hollow fiber membranes prepared in different concentrations of the pH 4 acetate buffer in the coagulation bath.

Figure 7.3 Cross-section SEM images of the PSS-PEI hollow fiber membranes showing the effect of acetate buffer concentration in the coagulation bath on the membrane morphology. Images a) – c) 0.1 M, d) – f) 0.25 M, g) – i) 0.4 M, j) – l) 0.5 M, and m) – o) 0.75 M acetate buffer concentration in coagulation bath.

As described earlier, the rate of precipitation increases with the increase in the buffer concentration. The rate of precipitation was significantly slower (>10 min) for membranes prepared in 0.1 M acetate buffer. **Figure 7.3b** shows the cross-section SEM image of the outer surface of the resultant hollow fiber membrane which depicts an asymmetric structure having finger-like macrovoids that are closer to the precipitation front and a more open and delaminated substructure. At lower concentrations such as 0.1 M, the amount of acetate buffer is not sufficient to continue the solvent (high pH) and non-solvent (acetate buffer) exchange throughout the thickness of the fiber. As a result, only a small region close to the coagulation bath precipitates instantaneously while the rest precipitates at relatively slower rate. This can be observed by looking at the cross-section SEM image in **Figure 7.3b** where the region closer to the coagulation bath i.e. the outer surface of the fiber precipitates first, forming an asymmetric structure with finger-like macrovoids. The thickness of this region is approximately $\sim 100\text{ }\mu\text{m}$. A higher magnification image of this region is shown in **Figure 7.3c** where the relatively denser outer most skin layer with more oval shaped macrovoids in the immediate substructure can be clearly observed. After formation of the outer skin, the rate of precipitation is significantly slowed down because the concentration of the buffer is not sufficient to continue the precipitation at the same rate. This results in a more open substructure as observed in the SEM image of lumen surface shown in **Figure 7.4b**. The SEM images also indicate extreme delamination of the membrane making them mechanically fragile.

Increasing the acetate buffer concentration in the coagulation bath to 0.25 M increases the rate of precipitation and resulted in hollow fiber membranes that precipitated instantaneously. These fibers possessed sufficient mechanical strength to be handled for SEM sampling, see **Figure 7.3d–f**. The effects of relatively faster precipitation rate are immediately visible in these images where the cross-section SEM image in **Figure 7.3f** reveal a typical asymmetric structure having a dense top layer (shown in **Figure 7.4c**) with finger-like macrovoids in the substructure. This kind of asymmetric structure is typically associated with instantaneous (rapid) phase separation [31,33]. In addition, the lumen surface of these membranes was relatively less porous, shown in **Figure 7.4d**, as compared to the fibers prepared in 0.1 M acetate buffer bath (**Figure 7.4b**).

Further increasing the acetate buffer concentration to 0.4 M and then to 0.5 M also increased the rate of precipitation resulting in membranes with elongated finger-like macrovoids as seen in **Figure 7.3i** and **l**. Both these membranes had dense top layers as shown by the outer surface SEM images in **Figure 7.4e** and **g**. Furthermore, the lumen surfaces of these membranes were significantly compact as compared to the ones mentioned before, compare **Figure 7.4d, f** and **h**. Further increasing the acetate buffer concentration to 0.75 M resulted in hollow fiber membranes showing irregular lumen structure. These kind of irregularities in the lumen are not uncommon and are mostly related to the spinning conditions such as the bore fluid composition and the flow rate [30]. Santos *et al.* attributed the irregular lumen contour to the rapid formation of a dense skin layer on the inner side of the fiber which causes stresses and strains on the nascent fiber [34]. However, these types of hollow fiber contours are undesired because they can influence the mechanical strength and also the performance of the hollow fiber membranes.

The cross-section SEM image shown in **Figure 7.3n** shows a finger-like macrovoid type structure that continues throughout the thickness of the fiber. This is because the amount of acetate buffer is sufficient to continue the solvent (high pH) and non-solvent (acetate buffer) exchange at a rapid rate until the whole fiber completely precipitates. The lumen surface of this membrane

Figure 7.4 SEM images of the outer and inner (lumen) surfaces of the PSS-PEI hollow fiber membranes prepared in different concentrations of pH 4 acetate buffer. Images a) – b) 0.1 M, c) – d) 0.25 M, e) – f) 0.4 M, g) – h) 0.5 M, and i) – j) 0.75 M.

Figure 7.5 Effect of acetate buffer concentration in the coagulation bath on the pure water permeability and n-hexadecane oil droplet/BSA retention of PSS-PEI hollow fiber membranes. The membranes were prepared in pH 4 acetate buffer containing 0.01 wt% GA.

also showed a relatively denser structure if compared to the rest, see **Figure 7.4j**. The hollow fiber membranes were tested for pure water permeability at 1 bar of applied water pressure and the results are shown in **Figure 7.5**, together with data on their retention behavior.

The hollow fiber membranes prepared in the 0.25 M acetate buffer baths ruptured under water pressure because of their porous structure and weaker mechanical strength. On the other hand, the membranes prepared in 0.4 M buffer showed a higher pure water permeability (PWP) of $\sim 900 \pm 400 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ even though there were no visible pores on the top surface of the membranes, see **Figure 7.4c**. Such a high permeability could possibly be due to the formation of micro-cracks that can appear in the membranes upon application of pressure. Nevertheless, the membranes showed stable PWP and therefore, was also tested for retention. An oil-in-water emulsion having an oil droplet size of 3–4 μm was filtered through the membranes at 0.4 bar of feed pressure. It was found that these membranes retained oil droplets with 100% retention which makes them microfiltration or open ultrafiltration type membranes. Unfortunately, the membranes did not retain any protein (BSA).

On the other hand, the membranes prepared in 0.5 M and 0.75 M acetate buffer baths showed PWP of $\sim 15 \pm 2$ and $12 \pm 5 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively. These values are more in accordance with the microstructure shown in **Figure 7.4g** and **i** where the top surface looks dense and does not show any visible pores at the given magnification. The MWCO of these membranes, determined by sieving curves shown in *Figure S7.4*, was $\sim 11600 \text{ Da}$ for membranes prepared in 0.5 M and $\sim 7800 \text{ Da}$ for the membranes prepared in 0.75 M acetate buffer. These MWCO values are typical for tight ultra-filtration type membranes. Therefore, the membranes were also tested

Figure 7.6 Cross-section SEM images showing the effect of pH of the acetate buffer in the coagulation bath on the membrane morphology. Images a) – c): pH 3.6, d) – f): pH 4.5, and g) – i) pH 5. The membranes were prepared in 0.5 M acetate buffer containing 0.01 wt% GA.

for retention using a 0.1 wt% BSA (protein) solution. BSA is a typical protein solution used for evaluating the performance of ultrafiltration type membranes because it has a molecular weight of ~ 66 kDa and a hydrodynamic radius of ~ 4.3 nm [35]. The BSA solution was filtered through the membranes at a feed pressure of 1 bar and the corresponding retention results are presented in **Figure 7.5**. It was found that the membranes prepared in 0.5 M and 0.75 M acetate buffer completely retained BSA, further demonstrating these membranes to function as tight UF membranes.

The results presented here signify that the structure, morphology, and performance of the PSS-PEI hollow fiber membranes can be tuned by varying the spinning conditions. Both, micro- and tight ultrafiltration type membranes were obtained by simply changing the concentration of the acetate buffer in the coagulation bath. In addition, the amount of glycerol and the acetate buffer added in the bore fluid could be controlled to adjust the precipitation rate on the lumen side. Another viable option to further control the precipitation kinetics in the lumen side would be to add non-solvent, such as water at pH ~ 8 – 10 in the bore liquid that will significantly slow down the precipitation kinetics in the lumen side resulting in porous morphology.

7.3.3 Effect of the coagulation bath pH

In this version of APS, the polyelectrolyte complexation of PSS-PEI is induced by a pH shift. The dope solution has a pH of ~ 12 where PEI remains in its uncharged state. Lowering the pH

Figure 7.7 SEM images of the outer and inner (lumen) surfaces of the PSS-PEI hollow fiber membranes prepared in different pH of 0.5 M acetate buffer. Images a) – b) pH 3.6, c) – d) pH 4.5, and e) – f) pH 5.

of this solution to ~ 4 as shown before, causes PEI to acquire charge and form a polyelectrolyte complex with PSS. As mentioned in **Chapter 5**, the branched PEI used in this work contains 31% primary, 39% secondary, and 30 % tertiary amines, having a pK_a value of 4.5, 6.7, and 11.6, respectively. As a result, varying the pH of the bath influences the charge density of PEI. The extent of polyelectrolyte complexation and the rate of subsequent precipitation can therefore be controlled by varying the pH of the coagulation bath. PSS-PEI hollow fiber membranes were prepared in 0.5 M acetate buffer at different values of the buffer pH such as pH 3.6, pH 4.5, and pH 5 to study the effect on the fiber structure and morphology. **Figure 7.6** shows the cross-section SEM images of the resultant membranes. For the cross-section SEM images of hollow fiber membranes prepared in pH 4, see **Figure 7.3j, k, and l**.

Figure 7.8 Effect of pH of the acetate buffer in the coagulation bath on the pure water permeability of PSS-PEI hollow fiber membranes. The membranes were prepared in 0.5 M acetate buffer containing 0.01 wt% GA.

Since pH determines the charge density of PEI, at $\text{pH} < 4.5$ all the amines of PEI are expected to be charged. As a result, in pH 3.6, PSS and PEI instantly form a highly crosslinked polyelectrolyte complex leading to instantaneous precipitation. This quick precipitation results in typical asymmetric structures with a dense outer layer, shown in **Figure 7.7a**, and finger-like macrovoids shown in the SEM images of **Figure 7.6b** and **c**. The membranes also showed signs of delamination of the lumen side (**Figure 7.6a**) and hence the inner surface image shown in **Figure 7.7b** is not a true representation. Furthermore, these membranes were relatively rigid and fragile.

Increasing the buffer pH in the coagulation bath beyond pH 4.5 ($> \text{pK}_a$ of primary amines) reduces the charge density of PEI leading to a reduced degree of ionic crosslinks. In addition, the membranes precipitate relatively slower. Comparing the cross-section SEM images of **Figure 7.6b**, **e**, and **h**, it can be observed that the region of the outer surface of the fiber which has finger-like macrovoids decreases with increasing the bath pH (4.5 and 5). This is because the rate of PSS-PEI precipitation decreases at elevated pH which affects the formation of macrovoids. The membranes prepared at pH 4.5 and 5 were also not circular as seen in SEM images of **Figure 7.6d** and **g**. The irregular outer surface could possibly be due to the slower rate of precipitation which likely causes hydrodynamic instability in the dope solution while it is precipitating in the coagulation bath. Accordingly, the lumen side of these membranes also showed a more open porous structure visible in **Figure 7.6d** and **g**.

The PWP of the membranes was measured at 1 bar of applied water pressure and the results are shown in **Figure 7.8**. The PWP of membranes prepared in pH 3.6 was $\sim 540 \pm 110 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ which is higher if correlated to the top surface SEM image **Figure 7.7a** which shows no

visible pores at given magnification. As mentioned before, these membranes were rigid and relatively fragile and therefore, could possibly develop micro-cracks at applied water pressures. Consequently, the membranes show higher PWP with a large error bar. The membrane, however, retained 100% of n-hexadecane oil droplet. In comparison, the membranes prepared at pH 4.5 and 5 showed a stable PWP of $\sim 60 \pm 21$ and $260 \pm 46 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively with a smaller error bar. Unfortunately, these membranes did not show any retention for BSA solution meaning that the pore size of these membranes is larger than the size of BSA which is $\sim 9 \text{ nm}$. Therefore, the membranes were used to filter oil droplet from oil-in-water emulsion. **Figure 7.8** shows that the membranes retained 100% oil droplets.

Overall, the presented APS hollow fiber membranes show interesting properties and structures that can be fine-tuned by varying the pH of the acetate buffer. The buffer pH could be used in combination with the buffer concentration to have more control over the precipitation kinetics. For example, slightly lower acetate buffer concentrations e.g. 0.25 M could be used in combination with a low pH (~ 3.6) to obtain a denser structure. On the other hand, a higher concentration of the buffer with a higher pH (~ 5) could be used to obtain mechanically stable porous membranes.

7.4 Conclusions

For the first time we have successfully demonstrated the production of hollow fiber membranes via the sustainable aqueous phase separation technique. A 35 wt% polymer solution comprising of PSS and PEI was prepared by directly mixing the two polyelectrolytes in a monomer molar mixing ratio of 1:2. The high pH dope solution was pushed through a single-orifice spinneret and precipitated in mild acidic conditions of pH 4 using the acetate buffer as the coagulation bath. The appropriate conditions for hollow fiber spinning were identified to produce PSS-PEI membranes having asymmetric membrane morphology. The composition of the bore fluid played a critical role in determining the rate of precipitation, the final structure, and properties of the membranes. It was found that having a dense outer skin layer and a relatively porous inner layer is beneficial for obtaining mechanically stronger hollow fiber membranes. Therefore, a combination of pH 4 acetate buffer and glycerol solution was used as the bore liquid. The acetate buffer acts as a non-solvent for PSS-PEI while the high viscosity of glycerol helps maintain the hollow shape of the fiber. Similarly, the coagulation bath composition was found to have a large influence on the membrane structure and performance. The hollow fiber membranes prepared in low concentrations of the acetate buffer such as 0.1 M and 0.25 M lacked the mechanical strength to sustain water pressures. In comparison, the fibers prepared in 0.4 M, 0.5 M, and 0.75 M showed adequate mechanical strength to be used for permeability tests. The membranes prepared in 0.4 M acetate buffer had a pure water permeability of $\sim 800 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ with 100% oil droplet retention, making them microfiltration type membranes. On the other hand, the membranes prepared in 0.5 M and 0.75 M acetate buffer showed a pure water permeability of ~ 15 and $12 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$, respectively. These membranes were also able to retain 100% of BSA and showed MWCO in the range of $\sim 7800 - 11600 \text{ Da}$ and therefore, can be used for ultrafiltration applications. The pH of the coagulation bath directly affects the ionization degree of PEI. At higher pHs such as pH 4.5 and pH 5 of the acetate buffer, PEI is not fully charged resulting in lesser ionic crosslinks and also slower precipitation rate leading to membranes that possess more open and porous lumen structures. The pure water permeabilities of these membranes was ~ 60

and $\sim 260 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ with 100% oil droplet retentions. In this work, the APS technique has been taken one step closer to large-scale production by demonstrating the successful preparation of hollow fiber membranes. The findings of this work can contribute towards development of more hollow fiber APS membranes utilizing other polyelectrolyte pairs.

Acknowledgements

This work was supported by the European Research Council (ERC) under the European Union's Horizon 2020 research and innovation program (ERC StG 714744 SAMBA). We thank Bob Siemerink for his help with building the hollow fiber membrane spinning setup and Xiaoliu Wen for her help with graphics design.

7.5 Supporting Information – S7

Figure S7.1 Test setup for measuring pure water permeability and retentions of the hollow fiber membranes.

Figure S7.2 Cross-section and inner surface SEM images of the PSS-PEI hollow fiber membranes prepared using different concentrations of the acetate buffer (without glycerol) in the bore fluid. Images a) – b): 0.25 M, c) – d), 0.5 M, e) – f) 0.75 M acetate buffer at pH 4. The membranes were prepared in coagulation baths containing 0.5 M acetate buffer at pH 4 with 0.01 wt% glutaraldehyde. Dope and bore fluid rate: 3 mL $\cdot$ min $^{-1}$.

Figure S7.3 Cross-section and inner surface SEM images of the PSS-PEI hollow fiber membranes prepared using mixture of acetate buffer and glycerol in bore fluid. Images a) – b): 0.25 M, c) – d), 0.5 M, and e) – f) 0.75 M acetate buffer with 30 wt% glycerol as the bore fluid. The membranes were prepared in coagulation baths containing 0.5 M acetate buffer at pH 4 with 0.01 wt% glutaraldehyde. Dope and bore fluid rate: 3 mL·min⁻¹.

Figure S7.4 Sieving curve showing the retention of polyethylene glycol as a function of its molecular weight for PSS-PEI hollow fiber membranes prepared in a) 0.5 M and b) 0.75 M acetate buffer with 0.01 wt% glutaraldehyde. Bore liquid: 0.25 M acetate buffer with 30 wt% glycerol. The molecular weight cut-off (MWCO) is the molecular weight of PEG which is 90% retained.

7.6 References

- [1] R.W. Baker, *Membrane technology and applications*, Third Edit, John Wiley & Sons, Chichester, UK, 2012.
- [2] H. Wu, C. Shi, Q. Zhu, Y. Li, Z. Xu, C. Wei, D. Chen, X. Huang, Capillary-driven blood separation and in-situ electrochemical detection based on 3D conductive gradient hollow fiber membrane., *Biosens. Bioelectron.* 171 (2021) 112722. doi:10.1016/j.bios.2020.112722.
- [3] H. Wu, Z. Ma, C. Wei, M. Jiang, X. Hong, Y. Li, D. Chen, X. Huang, Three-Dimensional Microporous Hollow Fiber Membrane Microfluidic Device Integrated with Selective Separation and Capillary Self-Driven for Point-of-Care Testing, *Anal. Chem.* 92 (2020) 6358–6365. doi:10.1021/acs.analchem.9b05342.
- [4] A. Razmjou, A. Resosudarmo, R.L. Holmes, H. Li, J. Mansouri, V. Chen, The effect of modified TiO₂ nanoparticles on the polyethersulfone ultrafiltration hollow fiber membranes, *Desalination*. 287 (2012) 271–280. doi.org/10.1016/j.desal.2011.11.025.
- [5] T.A. Otitoju, A.L. Ahmad, B.S. Ooi, Polyethersulfone composite hollow-fiber membrane prepared by in-situ growth of silica with highly improved oily wastewater separation performance, *J. Polym. Res.* 24 (2017) 123. doi:10.1007/s10965-017-1268-6.
- [6] C.S. Ong, W.J. Lau, P.S. Goh, B.C. Ng, A.F. Ismail, Preparation and characterization of PVDF–PVP–TiO₂ composite hollow fiber membranes for oily wastewater treatment using submerged membrane system, *Desalin. Water Treat.* 53 (2015) 1213–1223. doi:10.1080/19443994.2013.855679.
- [7] T.A. Otitoju, B.S. Ooi, A.L. Ahmad, Synthesis of 3-aminopropyltriethoxysilane-silica modified polyethersulfone hollow fiber membrane for oil-in-water emulsion separation, *React. Funct. Polym.* 136 (2019) 107–121. doi.org/10.1016/j.reactfunctpolym.2018.12.018.
- [8] M. Etxeberria-Benavides, T. Johnson, S. Cao, B. Zornoza, J. Coronas, J. Sanchez-Lainez, A. Sabetghadam, X. Liu, E. Andres-Garcia, F. Kapteijn, J. Gascon, O. David, PBI mixed matrix hollow fiber membrane: Influence of ZIF-8 filler over H₂/CO₂ separation performance at high temperature and pressure, *Sep. Purif. Technol.* 237 (2020) 116347. doi.org/10.1016/j.seppur.2019.116347.
- [9] W. Qiu, J. Vaughn, G. Liu, L. Xu, M. Brayden, M. Martinez, T. Fitzgibbons, G. Wenz, W.J. Koros, Hyperaging Tuning of a Carbon Molecular-Sieve Hollow Fiber Membrane with Extraordinary Gas-Separation Performance and Stability, *Angew. Chemie Int. Ed.* 58 (2019) 11700–11703. doi.org/10.1002/anie.201904913.
- [10] I. Moch Jr., *Membranes, Hollow-Fiber*, Kirk-Othmer Encycl. Chem. Technol. (2005). doi.org/10.1002/0471238961.0815121213150308.a01.pub2.
- [11] S. Loeb, S. Sourirajan, Sea Water Demineralization by Means of an Osmotic Membrane, in: *Saline Water Conversion—II*, American Chemical Society, (1963) 117-132 SE–9. doi:10.1021/ba-1963-0038.ch009.
- [12] The European Commission, COMMISSION REGULATION (EU) 2018/ 588 - of 18 April 2018 - amending Annex XVII to Regulation (EC) No 1907 / 2006 of the European Parliament

and of the Council concerning the Registration, Evaluation, Authorisation and Restr., Off. J. Eur. Union. 99 (2018) 3.

[13] B. Philipp, H. Dautzenberg, K.J. Linow, J. Kötz, W. Dawydoff, Polyelectrolyte complexes - recent developments and open problems, *Prog. Polym. Sci.* 14 (1989) 91–172. doi:10.1016/0079-6700(89)90018-X.

[14] J. Fu, H.M. Fares, J.B. Schlenoff, Ion-Pairing Strength in Polyelectrolyte Complexes, *Macromolecules*. 50 (2017) 1066–1074. doi:10.1021/acs.macromol.6b02445.

[15] M.I. Baig, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.

[16] E. N. Durmaz, M. I. Baig, J. D. Willott, W. M. de Vos, Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 2612–2621. doi:10.1021/acsapm.0c00255.

[17] W.M. Nielen, J.D. Willott, W.M. de Vos, Aqueous Phase Separation of Responsive Copolymers for Sustainable and Mechanically Stable Membranes, *ACS Appl. Polym. Mater.* 2 (2020) 1702–1710. doi:10.1021/acsapm.0c00119.

[18] J.D. Willott, W.M. Nielen, W.M. de Vos, Stimuli-Responsive Membranes through Sustainable Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 659–667. doi:10.1021/acsapm.9b01006.

[19] M.I. Baig, P.P.I. Sari, J. Li, J.D. Willott, W.M. de Vos, Sustainable Aqueous Phase Separation membranes prepared through mild pH shift induced polyelectrolyte complexation of PSS and PEI, *J. Memb. Sci.* 625 (2021) 119114. doi:10.1016/j.memsci.2021.119114.

[20] M.I. Baig, J.D. Willott, W.M. de Vos, Tuning the structure and performance of polyelectrolyte complexation based aqueous phase separation membranes, *J. Memb. Sci.* 615 (2020) 118502. doi:10.1016/j.memsci.2020.118502.

[21] J. Kamp, S. Emonds, J. Borowec, M.A. Restrepo Toro, M. Wessling, On the organic solvent free preparation of ultrafiltration and nanofiltration membranes using polyelectrolyte complexation in an all aqueous phase inversion process, *J. Memb. Sci.* 618 (2021). doi:10.1016/j.memsci.2020.118632.

[22] K. Sadman, D.E. Delgado, Y. Won, Q. Wang, K.A. Gray, K.R. Shull, Versatile and High-Throughput Polyelectrolyte Complex Membranes via Phase Inversion, *ACS Appl. Mater. Interfaces*. 11 (2019) 16018–16026. doi:10.1021/acsami.9b02115.

[23] S. Emonds, J. Kamp, J. Borowec, H. Roth, M. Wessling, Polyelectrolyte Complex Tubular Membranes via a Salt Dilution Induced Phase Inversion Process, *Adv. Eng. Mater.* 23 (2021) 2001401. doi.org/10.1002/adem.202001401.

[24] N.L. Le, S.P. Nunes, Ethylene glycol as bore fluid for hollow fiber membrane preparation, *J. Memb. Sci.* 533 (2017) 171–178. doi.org/10.1016/j.memsci.2017.03.045.

[25] A.L. Ahmad, T.A. Otitoju, B.S. Ooi, Hollow fiber (HF) membrane fabrication: A review on the effects of solution spinning conditions on morphology and performance, *J. Ind. Eng. Chem.*

70 (2019) 35–50. doi.org/10.1016/j.jiec.2018.10.005.

[26] S.A. McKelvey, D.T. Clausi, W.J. Koros, A guide to establishing hollow fiber macroscopic properties for membrane applications, *J. Memb. Sci.* 124 (1997) 223–232. doi.org/10.1016/S0376-7388(96)00249-9.

[27] J.M. Dickhout, J.M. Kleijn, R.G.H. Lammertink, W.M. De Vos, Adhesion of emulsified oil droplets to hydrophilic and hydrophobic surfaces-effect of surfactant charge, surfactant concentration and ionic strength, *Soft Matter*. 14 (2018) 5452–5460. doi:10.1039/C8SM00476E.

[28] N. Noor, J. Koll, N. Scharnagl, C. Abetz, V. Abetz, Hollow Fiber Membranes of Blends of Polyethersulfone and Sulfonated Polymers, *Membr.* 8 (2018). doi:10.3390/membranes8030054.

[29] S. Bonyadi, T.-S. Chung, W.B. Krantz, Chapter 4 - Investigation of corrugation phenomenon in the inner contour of hollow fibers during the nonsolvent-induced phase-separation process★, in: T.-S. Chung, Y.B.T.-H.F.M. Feng (Eds.), Elsevier, (2021) 85–104. doi.org/10.1016/B978-0-12-821876-1.00003-2.

[30] N. Peng, N. Widjojo, P. Sukitpaneemit, M.M. Teoh, G.G. Lipscomb, T.-S. Chung, J.-Y. Lai, Evolution of polymeric hollow fibers as sustainable technologies: Past, present, and future, *Prog. Polym. Sci.* 37 (2012) 1401–1424. doi.org/10.1016/j.progpolymsci.2012.01.001.

[31] H. Strathmann, K. Kock, P. Amar, R.W. Baker, The formation mechanism of asymmetric membranes, *Desalination*. 16 (1975) 179–203. doi:10.1016/S0011-9164(00)82092-5.

[32] M.I. Baig, P.P.I. Sari, J. Li, J.D. Willott, W.M. de Vos, Sustainable Aqueous Phase Separation membranes prepared through mild pH shift induced polyelectrolyte complexation of PSS and PEI, *J. Memb. Sci.* 625 (2021). doi:10.1016/j.memsci.2021.119114.

[33] C.A. Smolders, A.J. Reuvers, R.M. Boom, I.M. Wienk, Microstructures in phase-inversion membranes. Part 1. Formation of macrovoids, *J. Memb. Sci.* 73 (1992) 259–275. doi:10.1016/0376-7388(92)80134-6.

[34] Y.E. Santoso, T.-S. Chung, K.Y. Wang, M. Weber, Chapter 5 - The investigation of irregular inner skin morphology of hollow fiber membranes at high-speed spinning and the solutions to overcome it★, in: T.-S. Chung, Y.B.T.-H.F.M. Feng (Eds.), Elsevier, (2021) 105–122. doi.org/10.1016/B978-0-12-821876-1.00023-8.

[35] L.D. Nghiem, A.I. Schäfer, M. Elimelech, Pharmaceutical retention mechanisms by nanofiltration membranes, *Environ. Sci. Technol.* 39 (2005) 7698–7705. doi:10.1021/es0507665.

“If human life were long enough to find the ultimate theory, everything would have been solved by previous generations. Nothing would be left to be discovered.”

- Stephen Hawking

Chapter 8.

Summary and Outlook

8.1 Summary

In **Chapter 1**, we started this journey by discussing ‘sustainability’, especially in these crucial times when our relationship with the environment is strained. One way to repair our relationship with the environment is to develop, encourage, and financially support sustainable manufacturing techniques. This can be achieved by implementing and utilizing the 12 principles of Green Chemistry as discussed in **Chapter 1**. Greener technologies and processes are the future and really the only way forward for the humankind and the Earth in the long run. One such effort to pursue a greener production of polymeric membranes has been presented in this thesis. We have successfully demonstrated that membranes can be prepared without using any unsustainable organic solvents. The polyelectrolyte complexation (PEC) based ‘Aqueous Phase Separation (APS)’ technique described in this thesis relies solely on water to produce polymeric membranes. This new technique provides a great deal of control over membrane structure and properties, just like the traditional organic-solvent based approaches. PEC membranes with tunable pore sizes have been prepared and optimized for a multitude of applications. The following sections summarize the major conclusions of the research work conducted in this thesis.

In **Chapter 2** we explored polyelectrolyte complexation as one of the routes to obtain sustainable APS membranes. Here, the phase separation is achieved by changing the pH of the casting solution containing a strong polyanion i.e. poly(sodium 4-styrenesulfonate) (PSS) and a weak polycation i.e. poly(allylamine hydrochloride) (PAH). The casting solution is prepared by mixing the two polyelectrolytes in a monomer molar mixing ratio of 1:2 (PSS:PAH) at pH $\sim$ 14. Immersing a thin film of this solution in a pH $\sim$ 1 bath causes PAH to acquire charge and immediately form a polyelectrolyte complex with PSS. It was found that the molecular weights of the polyelectrolytes and the concentration of the casting solution are crucial parameters that have a significant impact on the membrane structure and properties. Utilizing polyelectrolytes having lower molecular weights typically resulted in porous PEC membranes that are well suited for microfiltration applications. The pore size of these membranes could be controlled from 0.2 μ m down to 80 nm by simply varying the casting solution concentration, thereby affecting the kinetics of phase separation. On the other hand, utilizing higher molecular weight polyelectrolytes resulted in membranes having average pore sizes in the range of 2 – 5 nm, perfectly suited for tight ultrafiltration applications. Additionally, the kinetics of phase separation were controlled by adding NaCl to the precipitation bath, allowing the polyelectrolyte chains to rearrange into dense complexes. Nanofiltration type membranes, well suited for organic micropollutant (Mw 250 – 630 Da) removal, were obtained in this way. We successfully demonstrated that APS is indeed a versatile technique that provides great control over the membrane pore size and structure resulting in membranes that can be used for different applications. This greener approach to membrane fabrication completely eliminates the use of organic solvents while providing excellent membranes.

In **Chapter 3**, we explored various additional factors influencing the thermodynamics of solution and the kinetics of phase separation of the PSS-PAH based APS membranes. Since PAH is a weak polyelectrolyte, it exists in its charged state at neutral and acidic pH. Therefore, in order to prepare a casting solution, NaOH needs to be added to the PAH solution before mixing it with the PSS. The amount of added NaOH is critical as it determines the pH of the solution and as a result, the charge on PAH. A clear homogeneous solution cannot be obtained if the amount of added NaOH in PAH is not enough to completely remove its charge. However, adding

significantly larger amounts of NaOH results in salting-out of PAH. Therefore, it is important to carefully balance the amount of NaOH added to PAH to obtain a clear PSS-PAH casting solution. We also found that the monomer mixing ratio of PSS:PAH significantly influences the mutual interactions of the polyelectrolytes in the casting solution thereby affecting the dynamic viscosity. Consequently, the kinetics of phase separation are severely impacted by the monomer mixing ratios resulting in membranes with different morphologies. Since this version of APS relies on the change in pH to induce phase separation, the pH of the coagulation bath becomes critically important since it is the driving force for complexation. It was found that if the driving force for complexation/phase separation is high, such as from solution pH of ~ 14 to coagulation bath pH ~ 0.5 , the membranes formed instantaneously having dense and brittle structures. On the other hand, at higher bath pHs ($\text{pH} > 1$) the resultant membranes precipitated slower, had porous structures, and were mechanically weak. The pH of the coagulation bath, therefore, also controls the kinetics of polyelectrolyte complexation and the subsequent phase separation, and hence can be fine-tuned to obtain desired membrane morphology. Another important parameter that was found to affect the membrane structure and properties is the amount of crosslinking agent. Glutaraldehyde (GA) was added to the coagulation bath to crosslink the amine groups of PAH. It was revealed that the pore size of the membranes could be tuned from 2 nm through to 450 nm by varying the amount of GA in the coagulation bath. The stability of the PSS-PAH membranes was evaluated by immersing the membranes in highly saline solutions i.e. 1 M NaCl and 1 M KBr for 1 week. The results revealed that the morphology and performance of the membranes remain unaffected after exposure to saline solutions. Additionally, the membranes showed chemical stability against 1200 ppm sodium hypochlorite solution which is typically used as the cleaning agent for polymeric membranes. The results presented in **Chapter 3** thus reveal the versatility of pH shift induced APS technique where numerous tuning parameters are available to produce PSS-PAH membranes with various structures, properties, and performances.

In **Chapter 4**, the applicability of the PSS-PAH membranes was taken one step further by showing that these membranes can also act as excellent support materials for functional coatings. Ultrafiltration type PSS-PAH membranes, obtained in **Chapter 2**, were coated with polyelectrolyte multilayers using three different polyelectrolyte pairs. It was found that only 4.5 bi-layers were required to transform the membranes into dense nanofiltration types that show a molecular weight cut-off (MWCO) in the range of 210 to 390 Da with salt retentions in excess of 90%. In addition, interfacial polymerization (IP) was performed on the PSS-PAH membranes to obtain nanofiltration membranes that yielded excellent separation performance. There are several benefits of using PSS-PAH membranes as supporting materials. For instance, the natural positive charge on the membranes facilitates the multilayer build up without any pre-treatments. Additionally, the excess amines of PAH provide additional bonding with the polyamide layer during IP, thereby improving the adhesion of the coating. These developments demonstrate that the APS approach allows membranes that can be used as excellent supports for functional coatings.

One major downside of these membranes described so far, is that they require extreme pH environments (from pH ~ 14 to pH ~ 1) to induce polyelectrolyte complexation. This problem was alleviated in **Chapter 5** where polyethyleneimine (PEI) was used as a weak polyelectrolyte to prepare PSS-PEI membranes. The benefit of using PEI is that it is easily available in its uncharged state which means that a casting solution can directly be prepared by mixing PSS and PEI without

adding any NaOH. Consequently, extreme pH, for example pH ~ 1 , is not necessary to induce phase separation. The PSS-PEI solution can be precipitated at a benign pH of 4 to obtain PEC membranes. Similar to the PSS-PAH based APS membranes, the impact of several tuning parameters such as the molecular weight of PEI, the concentration and pH of the coagulation bath, and the amount of crosslinking agent was investigated in detail. Contrary to what was observed for the PSS-PAH membranes, using higher molecular weight polyelectrolytes resulted in microfiltration type PSS-PEI membranes and vice versa. This has to do with the branched nature of higher molecular weight PEI (~ 750 kDa) which forms a more open polyelectrolyte complex with PSS. On the other hand, excellent nanofiltration type membranes having a MWCO of ~ 200 Da were obtained using relatively lower molecular weight PEI (~ 25 kDa). PSS-PEI membranes performed even better as compared to the PSS-PAH membranes. In addition, the casting solution viscosity is significantly lower for the former at the same polymer concentration, making it easier to process for flat sheet membrane production. The major benefit, however, remains that these membranes can be prepared at mild pH conditions, making this APS approach even more sustainable and environmentally friendly.

In **Chapter 6** an entirely different approach to prepare PEC membranes was taken where instead of pH, salt was used as the driving force for complexation. Here, a mixture solution of two oppositely charged strong polyelectrolytes i.e. PSS as polyanion and poly(diallyldimethylammonium chloride) (PDADMAC) as polycation, was prepared at high salt concentrations where the charges are screened. The solution was then cast as thin film and immersed in deionized water where the salt diffuses out of the solution leading to polyelectrolyte complexation and subsequent phase separation. Asymmetric nanofiltration membranes having MWCO of <300 Da with dense top layers and porous support were prepared via this approach. The effect of various parameters such as the molecular weights of the polyelectrolytes, the polymer solution concentration, and the bath salinity were investigated in detail. It was found that the salinity of the coagulation bath is a critical parameter that determines the rate of precipitation and the resulting thickness of the separation layer. The foremost advantage of this salt-induced APS is that it does not rely on changes in pH at all while producing sustainable nanofiltration type membranes.

In all described chapters above we described producing flat sheet sustainable membranes via the APS technique. An important step to further establish the versatility of APS lies in the production of hollow fiber (HF) membranes.

In **Chapter 7** we showed that PSS-PEI based hollow fiber membranes can indeed be prepared via the APS technique. HF membranes for micro- and ultrafiltration applications were prepared by carefully tuning the fiber spinning conditions. This approach opens up a world of possibilities for APS membranes where also other polyelectrolyte systems such as the PSS-PAH and PSS-PDADMAC systems could be used for the production of excellent HF membranes. Additionally, efforts could also be devoted to studying other potential polyelectrolyte pairs to develop APS membranes for specific applications which will be discussed later in the coming sections.

8.2 Outlook

In this section further recommendations and a future perspective is presented that outlines various routes that can be taken to improve the existing APS membranes while also providing

a roadmap to achieve a more complete sustainability in the field of polymeric membranes. However, before going into the recommendations, it is important to mention that the research presented in this thesis is still in its infancy, but nonetheless presents an outstanding platform to further advance the field of sustainable membranes.

First the recommendations regarding membranes that are already prepared in this thesis are presented highlighting the potential approaches to improve the properties of these existing APS membranes and other tuning parameters that can provide control over the membrane morphology.

8.2.1 PSS-PAH membranes

The pH shift induced APS technique is versatile and as mentioned earlier, numerous parameters are available to control the precipitation process. As shown in **Chapter 2**, the molecular weight of the polyelectrolytes plays a crucial role in determining the pore size of the resultant membranes. Using PAH having a molecular weight of ~ 17.5 kDa resulted in microfiltration type membranes, while ultrafiltration type membranes were obtained with ~ 150 kDa PAH (without NaCl in bath). Increasing the molecular weight even further to, for example ~ 450 kDa would increase the viscosity of the casting solution while at the same time reducing the pore size of the resultant membranes. In this manner, nanofiltration type membranes could potentially be obtained without having to add NaCl in the coagulation bath.

Talking about NaCl, currently, 4 M of NaCl is required to obtain nanofiltration type membranes that are able to retain on average $\sim 80\%$ of organic micropollutants with molecular weights in the range of ~ 250 to ~ 600 Da. However, these membranes did not show any significant retention of salts like MgSO_4 and MgCl_4 . Such a large amount of NaCl in the bath is also not ideal for large scale production of these membranes. Instead a salt such as KBr could be used which has a higher doping constant than NaCl [1]. It is well known that the type of salt significantly impacts the properties of polyelectrolyte multilayers [2]. Typically thicker multilayers are obtained with KBr as compared to NaCl, at the same ionic strength [3–5]. This could mean that relatively lower amounts of KBr would be needed to facilitate polyelectrolyte chain rearrangements as compared to NaCl. It is expected that denser PEC membranes showing enhanced salt selectivity can possibly be obtained by using KBr instead of NaCl. However, increasing the KBr concentration beyond a certain point could affect the PEC membrane formation itself as it can extrinsically compensate for the charges on the polyelectrolyte chains thereby decreasing the ionic crosslinking density [1]. Therefore, it becomes vital to control the amount of KBr in the coagulation bath to obtain membranes having adequate mechanical strength.

Furthermore, the dynamic viscosity of 12 wt% PSS-PAH solution is approximately 48 Pa-s which is significantly higher than the polymer solutions typically used for producing polymeric membranes. Such a high viscosity makes it a challenge to obtain HF membranes at ambient temperatures. Reducing the polymer concentration is one option to reduce the viscosity but it substantially compromises the mechanical stability of the fibers. The other option is to heat the PSS-PAH solution during the fiber spinning to have a better control over the fiber spinning process. Since viscosity is temperature dependent and the kinetics of phase separation are linked to the viscosity of the solution, temperature of the polymer solution can be used to control the membrane morphology.

8.2.2 PSS-PEI membranes

The case of PSS-PEI membranes is slightly different from PSS-PAH membranes. For instance, the added NaOH in PAH requires extreme pH in the bath to form a PSS-PAH polyelectrolyte complex. This is not the case for PSS-PEI where no base is added to the weak polyelectrolyte. Consequently, a strong acid is not required to complex PSS and PEI. In this study, an acetate buffer was used to produce flat sheet and HF PSS-PEI membranes. This buffer was selected mainly because of the mild pH range that it covers i.e. pH 3.6 to 5.6 and is cheap and readily available. As explained in the previous section, the type of salt is an important parameter that can determine the final properties of PEC because of different doping constants. Buffer solutions with different types of salts could be potentially used to produce PSS-PEI membranes in mild pH conditions. One such example is the citrate buffer which can be prepared in the pH range ~ 3 to pH ~ 6 using non-toxic chemicals. Citric acid, which is one of the components used to prepare the citrate buffer, has three ionizable hydrogen atoms as compared to only one in acetic acid. Consequently, citric acid has three pK_a values and therefore, the pH of the citrate buffer could have a larger influence on the PSS-PEI membrane structure as compared to the acetate buffer.

One other key parameter is the molecular weight of the polyelectrolytes as mentioned before. Microfiltration type flat sheet membranes were obtained using the higher molecular weight branched PEI (~ 750 kDa) while nanofiltration type membranes were obtained with a lower molecular weight PEI (~ 25 kDa). Therefore, it can be hypothesized, based on the results presented in this thesis, that ultrafiltration type membranes could possibly be obtained using PEI having a molecular weight in between the two, such as ~ 270 kDa which is commercially available. One may argue about using linear PEI for producing PEC membranes however, it is quite expensive and notoriously difficult to produce at higher molecular weights. PSS-PEI membranes could also be prepared using branched PEI having different degrees of branching. Currently, microfiltration type PSS-PEI membranes have an average pore size of ~ 80 nm. Using branched PEI with a higher degree of branching could possibly result in a slightly more open polyelectrolyte complex resulting in membranes with even larger pore sizes.

In case of HF membranes, there are several operating parameters that can be manipulated to obtain desired membrane morphologies. First is the concentration of the polymer solution and its viscosity which partly determines the rate of phase separation. A higher polymer concentration improves the mechanical stability and reduces the pore size of the membrane by slowing down the precipitation kinetics. Therefore, the composition of the coagulation bath and the bore fluid become critically important and should be carefully controlled to obtain necessary mechanical strength while maintaining the desired pore morphology. Another important parameter is the ratio of the flow rates of dope and bore fluids that can determine the wall thickness of the hollow fiber. A thicker wall provides more mechanical strength but at the same time reduces the pure water permeability of the membranes.

Similar to what is described for the flat sheet PSS-PEI membranes, other types of buffer solutions should be investigated to study the effect on membrane formation kinetics and the resultant morphologies. In addition, additives such as polyethylene glycol could also be used in the bore fluid to increase the solution viscosity and maintain the hollow structure inside of the fiber while also controlling the membrane formation kinetics. The air gap distance, which is the distance between the spinneret needle and the surface of the coagulation bath, is also an important

parameter during spinning. Depending on the composition of bore fluid and coagulation bath, it determines the membrane pore size and morphology of the resultant membranes. If a strong non-solvent is used as the bore fluid, the air gap distance becomes critically important as the precipitation would begin from the inside and can reach the outer edge of the fiber even before it touches the coagulation bath.

In this work, dense nanofiltration type PSS-PEI hollow fiber membranes could not be obtained even though the coagulation bath composition was the exactly the same as the one which provided nanofiltration flat sheet membranes. Hollow fiber spinning is quite different from flat sheet membrane casting and in most cases, the same recipe would give different membrane morphologies in different geometries [6]. This is because the flat sheet membrane production is a rather static process especially at lab scale, while hollow fiber membrane production is a more dynamic process where several operating parameters are involved. Therefore, controlling the phase separation kinetics and the membrane morphology becomes a challenge in HF spinning. Based on the above mentioned discussion, future efforts could be devoted towards finding the operating conditions that can produce dense nanofiltration type PSS-PEI membranes.

8.2.3 PSS-PDADMAC membranes

The PSS-PDADMAC membranes prepared in **Chapter 6** showed decent nanofiltration performance and had MWCO in the range of 250 – 280 Da. Additionally, the membranes were able to withstand 10 bar of applied water pressure without showing any signs of instability. However, one of the limitations was the lower PWP of these membranes, which was in the range of $0.4 - 1 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. The membranes were prepared using the PSS-PDADMAC solution mixed at a monomer molar mixing ratio of 1:1. As mentioned earlier, the monomer mixing ratio determines the interactions of the polyelectrolyte chains and the structure of the resulting PEC. Therefore, by changing the monomer ratio slightly, it is possible to form a PEC membranes with relatively larger pores that show higher pure water permeability while maintaining the salt selectivity.

In this work, NaCl was used to screen the charges of PSS and PDADMAC in the casting solution. As mentioned in the previous section, the type of salt significantly influences the properties of the resultant PEC due to different doping constants. Therefore, KBr, having higher doping constant than NaCl, should be used to prepare the casting solution. In this way polymer solutions with higher concentrations ($\sim 20 \text{ wt\%}$ as opposed to currently $\sim 15 \text{ wt\%}$) could be prepared as less amount of KBr would be needed to homogenize the polyelectrolyte mixture. The amount of KBr in the solution also affects the phase separation kinetics and therefore, shall be carefully controlled. Similarly, KBr can be added to the coagulation bath to slow down the phase separation kinetics to obtain desirable membrane morphology. Naturally, other types of salts could also be used either in solution or in the coagulation to give further control over the phase separation kinetics and thereby, the resulting membrane structures.

The major advantage of PSS-PDADMAC membranes is that the precipitation process is fairly simple and does not involve any pH change. Membranes are simply prepared in deionized water and because of this specific reason, this polyelectrolyte pair was used first to produce hollow fiber membranes. A $15 \text{ wt\%}$ PSS:PDADMAC dope solution containing $18 \text{ wt\%}$ NaCl was prepared in a monomer molar mixing ratio of 1:1. This is the same solution that was used in **Chapter 6** to obtain nanofiltration type membranes. For hollow fiber membranes, the bore fluid and the coagulation

Figure 8.1 SEM images of PSS-PDADMAC hollow fiber membranes prepared using 20 wt% dope solution containing 15 wt% KBr with two different bore fluid compositions. Images a) to d): without KBr in the bore fluid and images e) to h): with 7.5 wt% KBr in the bore fluid. The SEM images c), d) and g), h) are the cross-section images of the outer and inner surface of the hollow fiber membranes, respectively.

bath contained deionized water. However, the resultant membranes could not maintain their hollow structure and collapsed inside water.

Therefore, NaCl was substituted for KBr to obtain a dope solution having 20 wt% polyelectrolyte and ~15 wt% KBr. Here, the effects of adding KBr are immediately observed in terms of the

dope solution concentration which is now 20 wt% as compared to ~ 15 wt% with NaCl. This is because a lesser amount of KBr is needed to obtain a clear homogeneous PSS-PDADMAC solution. Moreover, the dope solution needs to be closer to the precipitation point, meaning that the amount of salt needs to be just enough to keep the mixture a clear liquid (no precipitation). As a result, the polyelectrolyte complexation and the subsequent phase separation occurs instantaneously. Two different types of bore fluids were used to produce hollow fiber membranes using this dope solution, see **Figure 8.1**. First, HF membranes were prepared using the same bore fluid as the coagulation bath i.e. deionized water (**Figure 8.1a-d**). The idea was to have skin layers on the inside as well as outside of the hollow fiber membranes. Afterwards, 7.5 wt% KBr solution was used as the bore fluid to slow down the precipitation kinetics on the inner side of the hollow fiber membranes (**Figure 8.1e-h**). Adding salt to the bore fluid acts as adding solvent to the non-solvent in terms of traditional solvent-based approaches.

The difference in phase separation kinetics can be seen by looking at the cross-section SEM images shown in **Figure 8.1b** and **f**. When bore fluid without any KBr is used, **Figure 8.1b**, the membrane precipitates from outside as well as inside at the same rate. This quick precipitation leads to the formation of asymmetric structures with a thin dense layer on top and a porous sublayer showing macrovoids. In comparison, when a 7.5 wt% KBr solution is used as the bore fluid, the macrovoids are not as pronounced as before, **Figure 8.1f**. This difference can be clearly observed by looking at the SEM images of the inside surface of the HF membranes shown in **Figure 8.1d** and **h**. The membrane prepared without KBr in the bore fluid showed a dense skin layer on the inside of the fiber **Figure 8.1d**. In comparison, for the membranes prepared using 7.5 wt% KBr solution as bore fluid a more open structure can be seen, **Figure 8.1h**. This is because KBr is a solvent for the PSS-PDADMAC polyelectrolyte pair, and adding solvent to non-solvent slows down the precipitation rate resulting in such membrane morphology. These results clearly indicate that the salt concentration in the bore fluid and also in the coagulation bath can be controlled to obtain membranes with different morphologies. Unfortunately, these PSS-PDADMAC membranes could not be used under pressure because of their poor mechanical strength and excessive swelling in water. Potting these membranes to make a module remains a challenge because the membranes need to be dried before potting with glue. The membranes shrunk slightly after drying from glycerol solution but were strong enough to make a membrane module. However, the membranes swell with water when the modules are tested for PWP measurements. These membranes eventually break from the glued part of the module that holds the membranes together. This is because some part of the membrane is surrounded by solid adhesive and does not come into contact with water. The rest of the membrane swells in water creating stress on the interface between the glued part of the membrane and the swollen membrane, eventually leading to collapse. A possible application of these membranes could be solvent filtration where swelling is not a problem. Solvents such as ethanol or IPA could be filtered using these membranes.

One possible way to control the degree of swelling is to change the monomer molar mixing ratio of the polyelectrolytes. As a result, the stoichiometry of the resultant PEC membrane changes and the charge on the membranes can be effectively controlled. Therefore, to obtain mechanically stronger PSS-PDADMAC hollow fiber membranes, other monomer mixing ratios could be used. Our initial experiments with PSS:PDADMAC (1:0.7) indicated that the resultant PEC membranes showed improved mechanical strength and lesser degree of swelling during PWP measurement. Unfortunately, these membranes could also not be tested under pressure

as they also broke during measurement. Therefore, further research on the effect of salt and the monomer mixing ratios is needed to obtain mechanically stronger PSS-PDADMAC hollow fiber membranes.

8.2.4 Challenges for current APS membranes

While the APS membranes presented in this work have several advantages, it would be unfair not to mention the challenges and certain limitations. For instance, one major property that needs improvement is the pure water permeability (PWP) of the APS membranes. Currently, the PWP of nanofiltration type APS membranes presented in this thesis lies in the range of $0.5 - 4 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$. In comparison, most nanofiltration membranes reported in literature have a PWP in the range of $1 - 40 \text{ L}\cdot\text{m}^{-2}\cdot\text{h}^{-1}\cdot\text{bar}^{-1}$ [7,8]. A membrane with a higher PWP is desired because of energy efficiency. Indeed, APS is still a new approach and hopefully more effort will be devoted towards improving the water permeability of these membranes. One of the ways that may improve the PWP could be to add polyethylene glycol (PEG) in the polyelectrolyte casting solution that can potentially act as pore former. However, the amount of PEG must be carefully optimized such that the selectivity is not compromised. On the other hand, efforts could also be devoted to increasing the selectivity of the APS membranes by making them dense for forward and reverse osmosis applications. There are increasing arguments that suggest that high water permeability has a limited impact on the energy efficiency of the desalination process and highly selective membranes, even with relatively lower water permeabilities, might even be preferable [9–11].

One other limitation is that the stability of PSS-PAH and PSS-PEI membranes is significantly compromised in highly basic solutions having $\text{pH} > 12$ and $\text{pH} > 8$, respectively, as mentioned in **Chapter 3** and **Chapter 5**. This is because the weak polyelectrolytes PAH and PEI begin to deprotonate thereby losing their charge at such high pHs. Consequently, the ionic crosslinking density decreases and the PEC begins to ‘de-complex’. This is not a major concern since the operating pH of most water treatment processes is well below pH 8. Still, one way to improve the pH stability of PSS-PAH and PSS-PEI membranes is by crosslinking the weak polyelectrolytes.

Drying the APS membranes is currently a slight challenge. This problem is not new and is also common for membranes prepared via the traditional solvent-based approaches [12]. Currently, the APS membranes are stored in deionized water before testing them for PWP and retention experiments. Taking the membranes out of water and letting them dry in the ambient atmosphere causes them to either densify and become a hard transparent material, or if low molecular weight polyelectrolytes are used, disintegrate into small pieces. Therefore, the PEC membranes need to be kept hydrated before testing their separation properties. One way to dry these membranes, which was also used in this thesis, is to treat them with a glycerol solution which prevents the pores of the membrane from collapsing. Apart from glycerol, a solvent exchange process can also be used where the water in the membranes is replaced, in steps, with volatile solvents like isopropyl alcohol (IPA) which resides in the pores and evaporates after a while, conserving the pore size. Such techniques are widely used as post-treatment steps for membranes to retain their structure and morphology [13,14]. Further, freeze-drying the membranes can also be potentially used to dry the membranes without significantly altering the membrane structure.

8.2.5 Other polyelectrolyte systems for APS membrane production

In this research, we have used four types of polyelectrolytes to produce PEC membranes. Indeed several other polyelectrolytes with different chemical structures are available that can be used to produce PEC membranes via the APS technique. Some of these polyelectrolytes are shown in Figure 8.2.

Polycations		Polyanions
<p>PDMAEMA</p>	<p>PDDPC</p>	<p>PAA</p>	<p>PVS</p>
<p>PVTAC</p>	<p>PVH</p>	<p>PAMPS</p>	<p>PSS-PS</p>
<p>PAHDAH</p>		<p>SPEEK</p>	

Figure 8.2 Chemical structures of polycations and polyanions that can be used for producing PEC membranes via the APS technique. The polycations include, PDMAEMA: poly(2-(dimethylamino)ethyl methacrylate), PDDPC: poly(*N,N*-dimethyl-3,5-dimethylene piperidinium chloride), PVTAC: poly(vinyl benzyl trimethyl ammonium chloride), PVH: poly(vinylamine hydrochloride), and PAHDAH: poly(allylamine hydrochloride-diallylamine hydrochloride). The polyanions include, PAA: poly(acrylic acid), PVS: poly(vinylsulfonate), PAMPS: poly(acrylamido-2-methylpropanesulfonate), PSS-PS: poly(sodium 4-styrene sulfonate/styrene copolymer), and sulfonated poly(ether ether ketone) (SPEEK).

It has been established in this thesis that a combination of a strong and a weak polyelectrolyte or two strong polyelectrolytes can produce mechanically stable PEC membranes that are able to sustain water pressures and show solute retentions. However, if two weak polyelectrolytes are used, it is generally difficult to obtain mechanically strong PEC membranes. Also, their

morphology is difficult to control. This is because the pH range where both the polyelectrolytes are sufficiently charged is usually quite narrow. A typical example is that of poly(acrylic acid) (PAA) and PAH, see **Figure 8.2** for the chemical structure. PAA is a weak polyanion and has a pK_a value in the range of 5–5.5 [15], while PAH is a weak polycation having a pK_a value of ~ 8.5 –9 [16]. Consequently, PAA is charged at $pH > 5$ and PAH is charged at $pH < 9$. It is important to mention here that pK_a denotes the pH value where half of the repeating units of a polyelectrolyte are charged [17]. The degree of PAA ionization/charging increases with the increase in pH value above pH 5. As a result, the pH range where a highly ionic crosslinked polyelectrolyte complex with PAH can be obtained is around pH 5 to pH 8. Nevertheless, the PAA-PAH pair has been successfully utilized for building polyelectrolyte multilayers on top of porous support membranes [18,19]. However, obtaining free-standing PEC membranes using this pair still remains a challenge.

Fu *et al.* conducted a study on the ion pairing strength of several polyelectrolyte pairs and found that relatively weaker interactions are observed among polyelectrolytes pairs having PAA [20]. All the drawbacks aside, one potential advantage of using weak polyelectrolytes is that the casting solution can be prepared at both acidic or basic conditions. PAA is uncharged in acidic conditions such as pH 2 or 3, and can be mixed with PAH without forming a PEC. Such a solution can then be precipitated at slightly basic ($pH > pK_a$ of PAA) conditions where PAA acquires charge to form a PEC membrane. On the other hand, a PAA-PAH solution can also be prepared at $pH > 9$ where PAH is uncharged and a thin film of this solution can then be precipitated at a relatively lower pH to obtain a PEC membrane. However, to impart mechanical stability, higher molecular weights (>500 kDa) of both the PAA and PAH are to be used. Additionally, the casting solution concentration could be kept higher to obtain mechanically stronger and potentially denser PAA-PAH membranes.

Another potential candidate for producing PEC membranes is PDMAEMA, poly(2-(dimethylamino)ethyl methacrylate), see **Figure 8.2** for structure. PDMAEMA is a weak polycation having a pK_a value of ~ 7 [21] and can be mixed with a strong polyanion such as PSS at $pH > 7$ to obtain a homogeneous casting solution which can then be precipitated in acidic pH conditions to obtain PEC membranes. PSS-PDMAEMA polyelectrolyte complex has successfully been studied for drug delivery applications [22]. One of the benefits of using PDMAEMA is that it can be quaternized by alkyl bromide which not only enhances its water solubility but also makes it a strong polycation. PDMAEMA can easily be paired with other polyanions shown in **Figure 8.2** for instance, PAA, PAMPS, and PSS-PS to obtain PEC membranes. Another advantage of PDMAEMA is that it can be used to produce both pH-induced APS as well as salt-induced APS membranes because of its availability in weak and strong states. The different structures of these polyelectrolytes will provide PECs with interesting properties that can be controlled by changing the PEC formation conditions such as the pH, the molecular weights of the polyelectrolytes, and the ionic strength of the solution. Similarly poly(vinyl benzyl trimethylammonium chloride) (PVTAC), a strong polycation, shown in **Figure 8.2** can be used in pair with a polyanion to produce PEC membranes. If a strong polyanion is used with PVTAC, salt-induced APS would be the preferred route to obtain PEC membranes because it can screen the charges on the polyelectrolyte chains in the solution that cannot be otherwise influenced by the pH change. Strong polyanions such as PSS and poly(acrylamido-2-methylpropanesulfonate) (PAMPS) can be used with PVTAC to prepare PEC membranes.

Some other polycations presented in **Figure 8.2** include poly(vinylamine hydrochloride) (PVH), poly(*N,N*-dimethyl-3,5-dimethylene piperidinium chloride) (PDDPC), and poly(allylamine hydrochloride-diallylamine hydrochloride) (PAHDAH). The chemical structure of PVH is quite similar to PAH and it can be hypothesized that it would most likely behave in the same way as PAH. Similarly, PDDPC is quite similar to PDADMAC in structure and can be paired with strong polyanions such as PSS to obtain a PEC as shown by Fu *et al.* [20].

In the very beginning of this PhD, PAHDAH was paired with PSS to prepare PEC membranes via the pH-induced APS technique. A 15wt% PSS-PAHDAH solution was prepared at high pH and precipitated at pH ~ 1 . The resultant films were porous but brittle and could not be used as membranes. These preliminary results established the feasibility of PAHDAH as one of the polyelectrolytes that can be used to prepare PEC membranes. However, further experiments are required to explore various parameters that can be fine-tuned to obtain mechanically stronger PSS-PAHDAH membranes. Higher casting solution concentration and crosslinking the PAHDAH while precipitation could be one way to improve the mechanical stability of such membranes.

Another polyelectrolyte pair that was investigated in the earlier stages was PSS-PS and PAH. PSS-PS is a copolymer of poly(sodium 4-styrene sulfonate) and polystyrene, see **Figure 8.2** for structure. Similar protocol as described in **Chapter 2** was followed to prepare the PSS-PS:PAH polymer solution. Briefly, NaOH was first added to the PAH solution to make it uncharged. Afterwards, 20 wt% aqueous solution of PSS-PS was mixed with the basic 16 wt% PAH solution in monomer molar mixing ratio of 1:2 to obtain 18 wt% PSS-PS:PAH solution. The solution was cast on a glass plate and immediately immersed in a coagulation bath at pH ~ 1 containing 4 M NaCl and 0.05 wt% glutaraldehyde. The resultant membranes were taken out after 24 h and washed with deionized water for further usage. **Figure 8.3** shows the top and bottom surface and cross-section SEM images of the resultant membranes.

The PSS-PS:PAH membranes were relatively brittle and could not be used for pressure driven membrane processes. The top surface SEM image, **Figure 8.3a**, shows a patterned structure which are basically micro-cracks that appear because of the brittleness. The cross-section image, **Figure 8.3c** and **d**, show a typical asymmetric morphology having a relatively dense top layer with sub-layer having finger-like macrovoids. The images also indicate that precipitation kinetics was fairly quick for these membranes resulting in the formation of macrovoids in the substructure. It can be concluded from these preliminary results that PSS-PS:PAH membranes can indeed be prepared by the APS technique. However to improve the mechanical strength of these membranes, a higher molecular weight PSS-PS in combination with a higher polymer concentration could be used.

The major advantage of using PSS-PS copolymer is that the polyelectrolyte chains are relatively stiff as compared to PSS. In addition, the hydrophobic styrene group of the copolymer, which does not participate in the polyelectrolyte complexation, is resistant to salt doping, possibly resulting in more stable PECs. Furthermore, the amount of water in the final PEC for PSS-PS:PAH membranes is relatively low as compared to PSS-PAH membranes resulting in reduced degree of swelling for the former. As a result, the mechanical properties of the final PECs are influenced by having more hydrophobic moieties in the structure.

Another interesting polyelectrolyte is the sulfonated poly (ether ether ketone) (SPEEK), which is

Figure 8.3 SEM images of the PEC membranes prepared using PSS-PS copolymer and PAH as polyelectrolytes. The polymer solution contained PSS-PS:PAH in 1:2 monomer molar mixing ratio and the concentration was ~ 18 wt%. The molecular weight of PSS-PS was ~ 19 kDa and of PAH was ~ 150 kDa. The membranes were prepared at pH ~ 1 bath containing 4 M NaCl and 0.05 wt% glutaraldehyde. a) top surface, b) bottom surface, and c), d) are the cross-section SEM images of the membranes.

a rigid polymer with an aromatic backbone and has shown high thermal stability and mechanical strength, see **Figure 8.2** for structure. SPEEK acts as a polyanion due to the presence of ionizable sulfonate group and has been used to prepare nanofiltration type multilayer membranes in combination with PDADMAC [23]. In addition, a polyelectrolyte complex of SPEEK with polyaniline (PANI) has been used for pH sensing applications [24]. Due to its lengthy and stiff backbone owing to the styrene group, SPEEK can be an interesting choice to produce mechanically strong free-standing PEC membranes.

In conclusion, hundreds of polyelectrolytes having different structures and properties could potentially be used to prepare PEC membranes via the APS technique, making it even more versatile. Interesting structures and morphologies could be obtained and even fine-tuned for desired applications. However, based on the results presented in this thesis, it can be concluded that a combination of a strong and a weak polyelectrolyte or both strong polyelectrolytes is better in terms of obtaining mechanically stronger PEC membranes. Another interesting route would be to use polyampholytes in combination with the polyelectrolytes. Polyampholytes are charged polymers that have both positive and negative charges. Kudaibergenov *et al.* reviewed

several polyampholyte-polyelectrolyte pairs that are able to form PECs [25]. Polyampholytes such as sulfonated cardo poly(arylene ether sulfone) (SPES) have been used with single-charged 1-butyl-3-methylimidazolium chloride ([BMIM]⁺Cl⁻) to build multilayers via the layer-by-layer approach [26]. However, to the best of our knowledge, there is no published research on free-standing PEC membranes using polyampholytes. Therefore, future efforts could also be devoted towards exploring this field.

8.2.6 Bio-derived polyelectrolytes and achieving complete sustainability

While all the above-mentioned polyelectrolytes have the potential to produce PEC membranes via the APS technique, most of them are still synthetically obtained from petroleum-based non-renewable sources. Same is the case for traditional non-solvent induced phase separation (NIPS), where most of the polymers are obtained from petroleum-based sources. Significant amount of research has been conducted to develop sustainable polymers for NIPS membranes. A few such examples include cellulose [27], bamboo fiber reinforced poly(lactic acid) [28], chitosan [29], and poly(lactic acid) [30]. The major limitation in using bio-derived polymers was the mechanical integrity of the resultant membranes, however, these concerns are now being addressed by researchers. However, control over the resultant NIPS membrane morphology still remains a major challenge and a focus of on-going research.

Similarly, the true sustainability of the APS technique can only be realized by utilizing bio-derived raw materials for producing PEC membranes. Interestingly, nature has long been applying the APS technique by means of the sandcastle worm (*Phragmatopoma Californica*). These worms build tubular honeycomb-like structures underwater by gluing together sand grains using a polyelectrolyte based adhesive [31]. The adhesive is composed of two classes of oppositely charged macromolecules. One class includes polycations that are rich in lysine, glycine, histidine, and tyrosine residues and the other consists of macromolecules that are acidic polyanionic proteins [32]. The sandcastle worm secretes these oppositely charged macromolecules in seawater where they phase separate into a solid porous adhesive. The macromolecules used by the sandcastle worm are quite complex but the concept is the same as aqueous phase separation. A better option for producing PEC membranes via bio-derived polyelectrolytes would be to use raw materials that are readily available and easy to modify.

Recently, Ushimaru *et al.* produced moldable polyelectrolyte complex with tunable mechanical properties using ϵ -poly-L-lysine and Lignosulfonate, which are bio-derived polyelectrolytes, see **Figure 8.4** for the chemical structures [33–35].

Lignosulfonate is a byproduct of wood pulping process and contains abundant sulfonate groups. On the other hand ϵ -polylysine is a naturally occurring cationic polyelectrolyte produced by microorganisms such as *Streptomyces albulus* [34]. It is hypothesized that due to the large number of ionic sulfonate groups in Lignosulfonate, a PEC membrane with stronger interactions with ϵ -polylysine can be prepared under aqueous conditions. In addition, the resultant PEC membrane can be expected to have strong mechanical properties as demonstrated by Ushimaru *et al.* with these bio-derived materials [33].

Other bio-based polyelectrolytes that have been used to prepare PECs are sodium carboxymethylcellulose (CMC) and chitosan (CS) [36–38]. CMC is obtained from cellulose, which itself is a biopolymer and acts as polyanion. CS, on the other hand, is a polycation

Figure 8.4 Chemical structure of bio-derived polyelectrolytes; sodium lignosulfonate (partially shown) and ϵ -poly-L-lysine. The abundant sulfonate groups in lignosulfonate can potentially form PEC membranes with high ionic crosslinking density.

that is obtained from chitin, a chemical compound produced by aquatic life. A CMC-CS mixture solution can be prepared at low pH where CMC is uncharged and can be precipitated at neutral to slightly basic pHs to obtain PEC membranes. Currently, such membranes are being developed by a PhD student at the MST cluster at University of Twente. The membranes have shown promising initial results and are in the process of being optimized. Another bio-based polyelectrolyte pair is the oxidized sodium alginate and CS which has been used to prepare PECs via the layer-by-layer process [39].

Producing membranes with tunable morphologies using these bio-derived polyelectrolytes could be a challenge as the pH range where both the polyelectrolytes are sufficiently charged to give highly crosslinked PEC is generally narrow. Nevertheless, such challenges need to be addressed if APS technique is to be made completely sustainable.

8.3 Overall conclusions

Membrane processes actively contribute towards a healthy and greener environment by producing safe drinking water, treating the wastewater, and separating/purifying gases. It is a technology that continues to grow and evolve. It is only time now that the methods by which these polymeric membranes are produced, be made more environmentally friendly and sustainable. This thesis presents one such technique to produce polymeric membranes in an environmentally sustainable manner without using any organic solvents. Water, the most abundant resource and a universal solvent, was utilized in this research to produce sustainable polymeric membranes. Depending on the pH, water can act as solvent or a non-solvent for the polyelectrolytes. This specific characteristic of polyelectrolytes was utilized to produce pH-induced polyelectrolyte complexation based APS membranes. We successfully demonstrate that

the APS technique provides a great deal of control over the resultant membrane structure, properties, and performance. Just like NIPS, several tuning parameters are available which can be fine-tuned to produce membranes with desired morphology and for specific applications. What is remarkable is that after successfully producing flat-sheet membranes, we have taken the APS technique a step closer to commercialization by also producing hollow fiber membranes which is the preferred geometry for commercial membrane products. However, one may argue that the pure water permeability of our APS membranes is lower than the commercial NIPS membranes. While it is true that this is one of the limitations at the moment, however, we need to keep in mind that the approach is completely new and still in its infancy. It took decades for the currently dominant NIPS process to evolve to the position it is now where almost all the commercial membranes are prepared via this technique. APS is just a few years old and has a lot of potential. It has already achieved remarkable targets in such a short time. Needless to say that there is plenty of room for improvement in terms of the membrane permeability and separation performance and I certainly believe that given the pace of sustainability drive in the membrane industry, it is only a matter of time before the APS membranes will compete head-to-head with the traditional NIPS membranes. The research presented in this thesis and the resultant publications contribute towards scientific understanding of APS membranes and hopefully takes the polymeric membrane production techniques to a new era of sustainability.

8.4 References

- [1] Q. Wang, J.B. Schlenoff, The polyelectrolyte complex/coacervate continuum, *Macromolecules*. 47 (2014) 3108–3116. doi:10.1021/ma500500q.
- [2] J.T. O’Neal, K.G. Wilcox, Y. Zhang, I.M. George, J.L. Lutkenhaus, Comparison of KBr and NaCl effects on the glass transition temperature of hydrated layer-by-layer assemblies, *J. Chem. Phys.* 149 (2018) 163317. doi:10.1063/1.5037491.
- [3] D. Volodkin, R. von Klitzing, Competing mechanisms in polyelectrolyte multilayer formation and swelling: Polycation–polyanion pairing vs. polyelectrolyte–ion pairing, *Curr. Opin. Colloid Interface Sci.* 19 (2014) 25–31. doi.org/10.1016/j.cocis.2014.01.001.
- [4] M. Salomäki, T. Laiho, J. Kankare, Counteranion-Controlled Properties of Polyelectrolyte Multilayers, *Macromolecules*. 37 (2004) 9585–9590. doi:10.1021/ma048701u.
- [5] M. Salomäki, P. Tervasmäki, S. Areva, J. Kankare, The Hofmeister Anion Effect and the Growth of Polyelectrolyte Multilayers, *Langmuir*. 20 (2004) 3679–3683. doi:10.1021/la036328y.
- [6] J. Wang, L. Zheng, Z. Wu, Y. Zhang, X. Zhang, Fabrication of hydrophobic flat sheet and hollow fiber membranes from PVDF and PVDF-CTFE for membrane distillation, *J. Memb. Sci.* 497 (2016) 183–193. doi.org/10.1016/j.memsci.2015.09.024.
- [7] A.W. Mohammad, Y.H. Teow, W.L. Ang, Y.T. Chung, D.L. Oatley-Radcliffe, N. Hilal, Nanofiltration membranes review: Recent advances and future prospects, *Desalination*. 356 (2015) 226–254. doi.org/10.1016/j.desal.2014.10.043.
- [8] Z. Yang, Y. Zhou, Z. Feng, X. Rui, T. Zhang, Z. Zhang, A Review on Reverse Osmosis and Nanofiltration Membranes for Water Purification, *Polym.* 11 (2019). doi:10.3390/polym11081252.
- [9] J.R. Werber, A. Deshmukh, M. Elimelech, The Critical Need for Increased Selectivity, Not Increased Water Permeability, for Desalination Membranes, *Environ. Sci. Technol. Lett.* 3 (2016) 112–120. doi:10.1021/acs.estlett.6b00050.
- [10] M. Elimelech, W.A. Phillip, The Future of Seawater Desalination: Energy, Technology, and the Environment, *Science* (80). 333 (2011) 712 LP – 717. doi:10.1126/science.1200488.
- [11] D. Cohen-Tanugi, R.K. McGovern, S.H. Dave, J.H. Lienhard, J.C. Grossman, Quantifying the potential of ultra-permeable membranes for water desalination, *Energy Environ. Sci.* 7 (2014) 1134–1141. doi:10.1039/C3EE43221A.
- [12] J. da Silva Burgal, L. Peeva, P. Marchetti, A. Livingston, Controlling molecular weight cut-off of PEEK nanofiltration membranes using a drying method, *J. Memb. Sci.* 493 (2015) 524–538. doi.org/10.1016/j.memsci.2015.07.012.
- [13] I. Pinnau, B.D. Freeman, Formation and Modification of Polymeric Membranes: Overview, in: *Membr. Form. Modif.*, American Chemical Society, (1999) 1. doi:10.1021/bk-2000-0744.ch001.
- [14] Drying of water treatment membranes, *Filtr. + Sep.* 55 (2018) 22–27. doi.org/10.1016/S0015-1882(18)30254-4.

- [15] A.I. Petrov, A.A. Antipov, G.B. Sukhorukov, Base-Acid Equilibria in Polyelectrolyte Systems: From Weak Polyelectrolytes to Interpolyelectrolyte Complexes and Multilayered Polyelectrolyte Shells, *Macromolecules*. 36 (2003) 10079–10086. doi:10.1021/ma034516p.
- [16] L. Li, S. Srivastava, M. Andreev, A.B. Marciel, J.J. De Pablo, M. V. Tirrell, Phase Behavior and Salt Partitioning in Polyelectrolyte Complex Coacervates, *Macromolecules*. 51 (2018) 2988–2995. doi:10.1021/acs.macromol.8b00238.
- [17] M.S. Bodnarchuk, K.E.B. Doncom, D.B. Wright, D.M. Heyes, D. Dini, R.K. O'Reilly, Polyelectrolyte pK_a from experiment and molecular dynamics simulation, *RSC Adv.* 7 (2017) 20007–20014. doi:10.1039/C6RA27785C.
- [18] Y. Guo, W. Geng, J. Sun, Layer-by-layer deposition of polyelectrolyte-polyelectrolyte complexes for multilayer film fabrication, *Langmuir*. 25 (2009) 1004–1010. doi:10.1021/la803479a.
- [19] E. te Brinke, D.M. Reurink, I. Achterhuis, J. de Grooth, W.M. de Vos, Asymmetric polyelectrolyte multilayer membranes with ultrathin separation layers for highly efficient micropollutant removal, *Appl. Mater. Today*. 18 (2020) 100471. doi.org/10.1016/j.apmt.2019.100471.
- [20] J. Fu, H.M. Fares, J.B. Schlenoff, Ion-Pairing Strength in Polyelectrolyte Complexes, *Macromolecules*. 50 (2017) 1066–1074. doi:10.1021/acs.macromol.6b02445.
- [21] H. Lee, S.H. Son, R. Sharma, Y.Y. Won, A Discussion of the pH-Dependent Protonation Behaviors of Poly(2-(dimethylamino)ethyl methacrylate) (PDMAEMA) and Poly(ethylenimine-ran-2-ethyl-2-oxazoline) (P(El-r-EOz)), *J. Phys. Chem. B*. 115 (2011) 844–860. doi:10.1021/jp109151s.
- [22] L. Leclercq, M. Boustta, M. Vert, A Physico-chemical Approach of Polyanion-Polycation Interactions Aimed at Better Understanding the In Vivo Behaviour of Polyelectrolyte-based Drug Delivery and Gene Transfection, *J. Drug Target*. 11 (2003) 129–138. doi:10.1080/1061186031000150287.
- [23] P. Ahmadiannamini, X. Li, W. Goyens, B. Meesschaert, I.F.J. Vankelecom, Multilayered PEC nanofiltration membranes based on SPEEK/PDDA for anion separation, *J. Memb. Sci.* 360 (2010) 250–258. doi.org/10.1016/j.memsci.2010.05.021.
- [24] N.Y. Abu-Thabit, Near-Infrared pH Sensor Based on a SPEEK–Polyaniline Polyelectrolyte Complex Membrane, *Proc.* 3 (2019). doi:10.3390/IOC_N_2018-1-05493.
- [25] S.E. Kudaibergenov, N. Nuraje, Intra- and Interpolyelectrolyte Complexes of Polyampholytes, *Polym.* 10 (2018). doi:10.3390/polym10101146.
- [26] G. Chen, G. Wu, L. Wang, S. Zhang, Z. Su, Layer-by-layer assembly of single-charged ions with a rigid polyampholyte, *Chem. Commun.* (2008) 1741–1743. doi:10.1039/B801784K.
- [27] A. Colburn, R.J. Vogler, A. Patel, M. Bezold, J. Craven, C. Liu, D. Bhattacharyya, Composite Membranes Derived from Cellulose and Lignin Sulfonate for Selective Separations and Antifouling Aspects., *Nanomater. (Basel, Switzerland)*. 9 (2019). doi:10.3390/nano9060867.
- [28] H.A. Le Phuong, N.A. Izzati Ayob, C.F. Blanford, N.F. Mohammad Rawi, G. Szekely,

Nonwoven Membrane Supports from Renewable Resources: Bamboo Fiber Reinforced Poly(Lactic Acid) Composites, *ACS Sustain. Chem. Eng.* 7 (2019) 11885–11893. doi:10.1021/acssuschemeng.9b02516.

[29] C. Clasen, T. Wilhelms, W.-M. Kulicke, Formation and Characterization of Chitosan Membranes, *Biomacromolecules*. 7 (2006) 3210–3222. doi:10.1021/bm060486x.

[30] F. Galiano, K. Briceño, T. Marino, A. Molino, K.V. Christensen, A. Figoli, Advances in biopolymer-based membrane preparation and applications, *J. Memb. Sci.* 564 (2018) 562–586. doi.org/10.1016/j.memsci.2018.07.059.

[31] R.J. Stewart, C.S. Wang, I.T. Song, J.P. Jones, The role of coacervation and phase transitions in the sandcastle worm adhesive system, *Adv. Colloid Interface Sci.* 239 (2017) 88–96. doi.org/10.1016/j.cis.2016.06.008.

[32] B.J. Endrizzi, R.J. Stewart, Gluecomics: An Expression Survey of the Adhesive Gland of the Sandcastle Worm, *J. Adhes.* 85 (2009) 546–559. doi:10.1080/00218460902996457.

[33] K. Ushimaru, Y. Hamano, T. Morita, T. Fukuoka, Moldable Material from ϵ -Poly-L-lysine and Lignosulfonate: Mechanical and Self-Healing Properties of a Bio-Based Polyelectrolyte Complex, *ACS Omega*. 4 (2019) 9756–9762. doi:10.1021/acsomega.9b00968.

[34] K. Ushimaru, T. Morita, T. Fukuoka, A bio-based adhesive composed of polyelectrolyte complexes of lignosulfonate and cationic polyelectrolytes, *J. Wood Chem. Technol.* 40 (2020) 172–177. doi:10.1080/02773813.2020.1722701.

[35] J.D. Megiatto, B.M. Cerrutti, E. Frollini, Sodium lignosulfonate as a renewable stabilizing agent for aqueous alumina suspensions, *Int. J. Biol. Macromol.* 82 (2016) 927–932. doi.org/10.1016/j.ijbiomac.2015.11.004.

[36] H. Fukuda, Polyelectrolyte complexes of chitosan with sodium carboxymethylcellulose, *Bull. Chem. Soc. Jpn.* 53 (1980) 837–840.

[37] J. Liuyun, L. Yubao, X. Chengdong, A novel composite membrane of chitosan-carboxymethyl cellulose polyelectrolyte complex membrane filled with nano-hydroxyapatite I. Preparation and properties, *J. Mater. Sci. Mater. Med.* 20 (2009) 1645–1652.

[38] J.C. Roy, A. Ferri, S. Giraud, G. Jinping, F. Salaün, Chitosan–Carboxymethylcellulose-Based Polyelectrolyte Complexation and Microcapsule Shell Formulation, *Int. J. Mol. Sci.* 19 (2018). doi:10.3390/ijms19092521.

[39] B. Mu, C. Lu, P. Liu, Disintegration-controllable stimuli-responsive polyelectrolyte multilayer microcapsules via covalent layer-by-layer assembly, *Colloids Surfaces B Biointerfaces*. 82 (2011) 385–390. doi.org/10.1016/j.colsurfb.2010.09.024.

[40] H.G. Schild, Poly(N-isopropylacrylamide): experiment, theory and application, *Prog. Polym. Sci.* 17 (1992) 163–249. doi.org/10.1016/0079-6700(92)90023-R.

[41] I.A. van Hees, A.H. Hofman, M. Dompé, J. van der Gucht, M. Kamperman, Temperature-responsive polyelectrolyte complexes for bio-inspired underwater adhesives, *Eur. Polym. J.* 141 (2020) 110034. doi.org/10.1016/j.eurpolymj.2020.110034.

- [42] X. Cao, Z. An, RAFT Synthesis in Water of Cationic Polyelectrolytes with Tunable UCST, *Macromol. Rapid Commun.* 36 (2015) 2107–2110. doi.org/10.1002/marc.201500440.
- [43] L. Chen, Y. Honma, T. Mizutani, D.-J. Liaw, J.P. Gong, Y. Osada, Effects of polyelectrolyte complexation on the UCST of zwitterionic polymer, *Polymer (Guildf)*. 41 (2000) 141–147. doi.org/10.1016/S0032-3861(99)00161-5.

Samenvatting

In **Hoofdstuk 1** zijn we deze reis begonnen met het begrip 'duurzaamheid', extra belangrijk in deze cruciale tijd waarin onze relatie met het milieu gespannen is. Een manier om onze relatie met het milieu te herstellen is het ontwikkelen, aanmoedigen en financieel ondersteunen van duurzame productietechnieken. Dit kan worden bereikt door het implementeren en gebruiken van de 12 principes van de Groene Chemie, zoals besproken in Hoofdstuk 1. Duurzamere technologieën en processen zijn de toekomst en de enige manier waarop we als mensheid met de aarde op de lange termijn vooruit kunnen. Dit proefschrift presenteert een nieuwe manier voor een duurzamere productie van polymeermembranen. We hebben succesvol laten zien dat membranen gemaakt kunnen worden zonder niet-duurzame organische oplosmiddelen. De waterige fase scheidingsmethode (APS), gebaseerd op de complexatie van polyelektrolyten (PEC), zoals die in dit proefschrift beschreven wordt, maakt alleen gebruik van water om polymeermembranen te produceren. Met deze nieuwe techniek kunnen de structuur en de eigenschappen van de membranen goed gecontroleerd worden, net als bij de traditionele benaderingen die organische oplosmiddelen gebruiken. PEC-membranen met controleerbare poriegroottes werden gemaakt en geoptimaliseerd voor verschillende toepassingen. De volgende secties vatten de belangrijkste conclusies samen van het onderzoek dat voor dit proefschrift is uitgevoerd.

In **Hoofdstuk 2** hebben we de complexatie van polyelektrolyten onderzocht als een van de routes om duurzame APS membranen te verkrijgen. De fasescheiding is hier verkregen door de pH van de strijkoplossing te veranderen. Deze oplossing bevat een sterk polyanion, poly(natrium-4-styreensulfonaat) (PSS) en een zwak polykation, poly(allylamine hydrochloride) (PAH). De strijkoplossing wordt gemaakt door het mengen van de twee polyelektrolyten in een molaire mengratio van de monomeren van 1:2 (PSS:PAH) bij pH ~ 14 . Het onderdompelen van een dunne film van deze oplossing in een bad met pH ~ 1 leidt ertoe dat PAH een lading op zich neemt en onmiddellijk een polyelektrolytcomplex vormt met PSS. Het onderzoek liet zien dat de molecuulgewichten van de polyelektrolyten en de concentratie van de strijkoplossing cruciale parameters zijn met een significante impact op de membraanstructuur en -eigenschappen. Polyelektrolyten met een lager molecuulgewicht resulteren typisch in een poreus PEC-membraan wat zeer geschikt is voor toepassing als microfiltratiemembraan. De poriegrootte van deze membranen kan gecontroleerd worden van 0.2 μm tot 80 nm door simpelweg het variëren van de concentratie van de strijkoplossing, en daarmee door het beïnvloeden van de kinetiek van de fasescheiding. Aan de andere kant leidt het gebruik van polyelektrolyten met een hoger molecuulgewicht tot membranen met een poriegrootte rond de 2-5 nm, perfect geschikt voor dichte ultrafiltratie toepassingen. Daarnaast werd de kinetiek van de fasescheiding gecontroleerd

door het toevoegen van NaCl aan het neerslagbad, waardoor de polyelektrolytstrengen zich herschikken naar dichte complexen. Dit leidde tot nanofiltratiemembranen, geschikt voor het verwijderen van organische microvervuilingen met een molecuulgewicht van 250-630 Da. We hebben succesvol laten zien dat APS inderdaad een veelzijdige techniek is die een grote controle geeft over de membraanporiegrootte en -structuur, resulterend in membranen die gebruikt kunnen worden voor verschillende toepassingen. Deze duurzamere benadering voor membraanfabricatie maakt geen gebruik van organische oplosmiddelen, maar leidt wel tot excellente membranen.

In **Hoofdstuk 3** hebben we verschillende andere factoren bestudeerd die de thermodynamica van de oplossing en de kinetiek van de fasescheiding van de PSS-PAH gebaseerde APS membranen beïnvloeden. Omdat PAH een zwak elektrolyt is, bestaat het in geladen vorm bij neutrale en zure pH. Om een strijkoplossing te maken, is het daarom noodzakelijk om NaOH toe te voegen aan de PAH oplossing voor deze te mengen met de PSS. De hoeveelheid NaOH die toegevoegd wordt is belangrijk, omdat het de pH van de oplossing bepaalt en daarmee de lading van de PAH. Een heldere, homogene oplossing kan niet worden verkregen als de hoeveelheid NaOH die is toegevoegd aan PAH niet genoeg de lading ervan weghaalt. Het toevoegen van significant grotere hoeveelheden leidt echter tot het neerslaan van de PAH. Daarom is het belangrijk om zorgvuldig de toe te dienen hoeveelheid NaOH te bepalen om een heldere PSS-PAH strijkoplossing te verkrijgen. We hebben ook geconcludeerd dat de monomeermengratio van PSS:PAH de onderlinge interacties van de polyelektrolyten in de strijkoplossing sterk beïnvloedt, en daarmee ook de dynamische viscositeit beïnvloedt. Als gevolg daarvan wordt de kinetiek van de fasescheiding sterk beïnvloed door de monomeermengratio's, resulterend in membranen met verschillende morfologie. Omdat de fasescheiding in deze variant van APS gecreëerd wordt door de verandering in pH, wordt de pH van het coagulatiebad van groot belang omdat het de drijvende kracht is voor complexatie. Deze studie laat zien dat als de drijvende kracht voor complexatie/fasescheiding hoog is, bijvoorbeeld bij een oplossing met pH ~ 14 en een coagulatiebad met pH ~ 0.5 , de membranen instantaan gecreëerd worden met dichte en broze structuren. Aan de andere kant leiden coagulatiebaden met hogere pH's (pH > 1) tot trager precipiterende membranen, poreuze structuren en mechanisch zwakte. De pH van het coagulatiebad controleert dus ook de kinetiek van de complexatie van de polyelektrolyten en de daarop volgende fasescheiding, en moet daarom verfijnd worden om de gewenste membraanmorfologie te verkrijgen. Een andere belangrijke parameter die invloed bleek te hebben op de membraanstructuur- en eigenschappen is de hoeveelheid verknopingsmiddel. Glutaaraldehyde (GA) werd toegevoegd aan het coagulatiebad om de aminogroepen van PAH te verknopen. Dit werk liet zien dat de poriegrootte van de membranen gestuurd kon worden van 2 nm tot 450 nm door het variëren van de hoeveelheid GA in het coagulatiebad. De stabiliteit van de PSS-PAH membranen werd bepaald door de membranen onder te dompelen in zeer zoute oplossingen, namelijk 1 M NaCl en 1 M KBr, gedurende één week. De resultaten laten zien dat de morfologie en de prestaties van de membranen niet beïnvloed werden na blootstelling aan deze zoute oplossingen. Bovendien lieten de membranen chemische stabiliteit zien voor een 1200 ppm natriumhypochloriet oplossing, een oplossing die typisch wordt gebruikt als schoonmaakoplossing voor polymere membranen. De resultaten die gepresenteerd worden in Hoofdstuk 3 laten dus de veelzijdigheid zien van de APS techniek gebaseerd op een verandering in pH, met verschillende verfijningsparameters om PSS-PAH membranen te produceren met verschillende structuren, eigenschappen en prestaties.

In **Hoofdstuk 4** laten we zien dat de PSS-PAH membranen ook gebruikt kunnen worden als goede ondersteuningsmaterialen voor functionele coatings. Ultrafiltratie PSS-PAH membranen, verkregen in Hoofdstuk 2, zijn gecoat met polyelektrolyt multilagen door gebruik te maken van drie verschillende polyelektrolytparen. Het bleek dat slechts 4,5 bilagen nodig waren om deze membranen te veranderen in dichte nanofiltratiemembranen, die een molecular weight cut-off (MWCO) tussen de 210 en 390 Da laten zien met zoutretenties boven de 90%. Een andere benadering was het gebruik van grensvlakpolymerisatie (IP) op de PSS-PAH membranen om nanofiltratiemembranen te verkrijgen met zeer goede scheidingseigenschappen. Er zijn verschillende voordelen verbonden aan het gebruik van PSS-PAH membranen als ondersteuningsmateriaal. De natuurlijke lading op de membranen maakt het bijvoorbeeld mogelijk om multilagen te coaten zonder enige voorbehandeling. Daarnaast zorgt de overmaat aan amines in PAH voor een extra binding met de polyamide laag tijdens IP, wat de adhesie van de coating verbeterd. Deze ontwikkelingen laten zien dat de APS-benadering tot membranen leidt die uitstekend als ondersteuningsmateriaal voor functionele coatings gebruikt kunnen worden.

Een groot nadeel van de membranen die tot dusver beschreven zijn is dat ze een extreme pH (van pH ~ 14 tot pH ~ 1) nodig hebben om de complexatie van polyelektrolyten te veroorzaken. Dit probleem was verholpen in **Hoofdstuk 5**, waar polyethyleenimine (PEI) gebruikt is als zwak polyelektrolyt om PSS-PEI membranen te produceren. Het voordeel van het gebruik van PEI is dat het makkelijk beschikbaar is als ongeladen molecuul, wat betekent dat de strijkoplossing direct gemaakt kan worden door het mengen van PSS en PEI, zonder NaOH toe te voegen. Als gevolg daarvan is een extreme pH, zoals pH ~ 1 , niet nodig om fasescheiding te veroorzaken. De PSS-PEI oplossing kan neerslaan bij een milde pH van 4 om PEC-membranen te verkrijgen. Net als bij de PSS-PAH gebaseerde APS-membranen is ook hier de impact van verschillende verfijningsparameters verder onderzocht, namelijk het molecuulgewicht van PEI, de concentratie en de pH van het coagulatiebad, en de hoeveelheid verknopingsmiddel. In tegenstelling tot wat we gezien hebben voor de PSS-PAH membranen, leidt een hoger molecuulgewicht van de polyelektrolyten tot microfiltratie type PSS-PAH membranen en vice versa. Dit is gerelateerd aan de vertakte natuur van PEI met een hoger molecuulgewicht (~ 750 kDa), wat een meer open polyelektrolyt vormt met PSS. Aan de andere kant zijn excellente nanofiltratie type membranen met een MWCO van ~ 200 Da verkregen met behulp van PEI met een relatief laag molecuulgewicht (~ 25 kDa). PSS-PEI membranen presteerden nog beter in vergelijking met de PSS-PAH membranen. Bovendien is de viscositeit van de strijkoplossing significant lager voor de eerstgenoemde bij dezelfde polymeerconcentratie, wat het proces om vlakke velmembranen te maken vergemakkelijkt. Het belangrijkste voordeel van deze membranen is echter dat ze bij mildere pH condities gemaakt kunnen worden, wat deze APS-benadering nog duurzamer en milieuvriendelijker maakt.

In **Hoofdstuk 6** is een compleet andere benadering om PEC-membranen te fabriceren gekozen, door in plaats van de pH, zout te gebruiken als drijvende kracht voor complexatie. Een mengsel van twee sterke polyelektrolyten met tegenovergestelde lading, namelijk PSS als polyanion en poly(diallyldimethylammoniumchloride) (PDADMAC) als polykation, is gemaakt bij hoge zoutconcentraties waardoor de ladingen afgeschermd zijn. De oplossing werd vervolgens als een dunne film uitgestreken en ondergedompeld in gedemineraliseerd water, waar het zout uit de oplossing diffundeert wat tot de complexatie van polyelektrolyten leidt, en vervolgens tot fasescheiding. Asymmetrische nanofiltratiemembranen met een MWCO van <300 Da met een dichte toplaag en een poreuze ondersteuningslaag werden gemaakt met deze benadering.

Het effect van de verschillende parameters zoals de molecuulgewichten van de polyelektrolyten, de polymeerconcentratie en de zoutconcentratie van het bad werden in detail bestudeerd. Er is gebleken dat de zoutconcentratie van het coagulatiebad een kritische parameter is, die de snelheid van precipitatie en de resulterende dikte van de scheidingslaag bepaalt. Het grootste voordeel van deze fasescheiding die door het zout wordt veroorzaakt, is dat het niet afhangt van een verandering in pH, terwijl het wel duurzame nanofiltratie type membranen produceert.

In alle hierboven beschreven hoofdstukken hebben we de productie van duurzame vlakke velmembranen beschreven, allen gemaakt met de APS-techniek. Een belangrijke stap verder in de veelzijdigheid van APS is het produceren van holle vezelmembranen. In **Hoofdstuk 7** hebben we laten zien dat PSS-PEI gebaseerde holle vezelmembranen inderdaad geproduceerd kunnen worden met de APS-techniek. Holle vezelmembranen voor micro- en ultrafiltratietoepassingen werden gemaakt door zorgvuldig de condities waarbij de vezels gesponnen werden af te stellen. Deze benadering opent een wereld aan mogelijkheden voor de APS-membranen, waarbij ook andere polyelektrolytsystemen zoals de PSS-PAH en PSS-PDADMAC systemen gebruikt zouden kunnen worden voor de productie van excellente holle vezelmembranen. Bovendien zou er ook onderzoek gedaan kunnen worden naar andere potentiële polyelektrolytparen om APS-membranen te ontwikkelen voor specifieke toepassingen.

Acknowledgements

First and foremost I would like to thank **Almighty ALLAH** for blessing me, providing me with all the opportunities, and guiding me through every phase of my life.

The past four years have been an incredible journey for me and I would like to thank each and every individual who has been a part of it.

My journey to University of Twente started when I was doing my MSc in South Korea. My first real interactions with polymer membranes was during my MSc project. During extensive literature study, one affiliation that kept appearing in the research papers was the University of Twente. Soon I realized that the research group at UT was indeed a pioneer in the field of membrane science. Upon the end of my MSc assignment, I actively started looking for a position at UT. I came across a vacancy at relatively newly formed MSuS group, headed by **Wiebe de Vos** where he was looking for a PhD student to work on developing novel polyelectrolyte complex membranes using a sustainable approach. Upon doing some preliminary research, I found that very limited literature is available on the topic and it would be great if I can be part of the group which can potentially become a pioneer on sustainable membranes. I immediately applied for the position.

On a cold December night of 2016, I came back from my lab at KIER, South Korea and I saw an email from Wiebe that he would like to have an interview with me. I was delighted and a few weeks later had an interview with him. This was my first real interaction with Wiebe and to say the least, I was really impressed by the way how he conducted the interview. His friendly and kind nature made me feel extremely comfortable and there, I made my decision that if selected, MSuS group is the perfect place for me. Long story short, after a couple of interviews Wiebe showed confidence in me and hired me for the position. I am extremely grateful to you Wiebe for putting your trust in me for this exciting project. Indeed the project was quite challenging with little to no literature available. The freedom with which you let me pursue this project is something that I always admire. Whenever things were not working or I was stuck on a problem, you were always supportive and helpful. No matter how stressed I was going into the meeting, I always came out with new energy and a lot of motivation from you. Indeed, your guidance and supervision style is something I immensely cherish. No matter how busy you were, you always found time for all of your students. Indeed I have learned quite a lot from you and will always be grateful to you for this opportunity.

I would also like to thank **Joshua Willott** who has been a wonderful daily supervisor. His comments and suggestions regarding experimentation and the manuscript were always valuable.

Apart from that, you are a good friend who is always willing to help. I still relish our talks about Cricket in this football dominated cluster. Thank you again for all the constructive comments and correcting my writings. I wish you the best of luck in your next endeavor.

To my graduation committee members: Prof. Dr. **Suzana Nunes**, Prof. Dr. **Ernst Sudholter**, Prof. Dr. **Christian Nijhuis**, Dr. **Michael Duits**, Dr. **Pilar Ruiz Ramiro**, thank you for taking out the time from your busy schedules to assess my thesis and giving valuable comments.

Now coming back to my early days at the MST cluster in 2017.

I would like to thank **Mary Tjink**, the secretary at that time, for taking care of all the bureaucracy. I would also like to thank the MST staff members; **Antoine, Rob, Jeff, Nieck, Jorris, Walter, Tymen, Erik Roesink, Louis, Henny**, and **Arian** for their comments and suggestions during the Monday morning presentations. Indeed your suggestions have helped me improve my presentation skills. Antoine, I still remember walking up to your office to get the signature on my very first Yellow Card and I asked, "May I come in, Sir?", to which you replied, "Don't call me Sir.". I found it very hard in the beginning to call you and Wiebe by your first names as this was something, coming from Asia, I had never done.

I would also like to thank **Audrey** for helping me with all the official stuff and being a really good friend. It is always a pleasure talking to you.

Thank you **Herman, Erik Rolevink, Harmen, Jan, Frank, Ineke** for your help whenever I needed it. Special thanks to **Bob** (my favorite Bob in the Netherlands!) for your technical help in my project and maintaining a jolly work environment. Also **Iske**, thank you for being super helpful and also talking to me in Urdu at times. You have an incredible gift of learning languages very quickly.

I would also like to thank some previous members of the cluster; **Dennis Reurink, Ahmet Halil, Zamidi, Nora, Özlem, Turkan, Pelin, Almohanad, Jason, Mehrdad, Mariël, Rosalind**, and **Hanieh**. Dennis, thank you for teaching me Dutch greetings in the very beginning and also for providing all the office mates with drop! Mehrdad, it was always fun to talk with you about different languages and cultures and the similarities that exist between our mother tongues, Urdu and Persian. Also thank you **Dona** and **Arputha** for interesting discussions in Urdu/Hindi and providing me with sweets and some tasty food from West Bengal and Tamil Nadu.

I am also grateful to other members of the MST cluster; **Ettore, Burak, Farzaneh, Abimbola, Shuyana, Vanda, Nicole, Nikos, Oguz, Alberto, Youri, Matthijs**, and **Heleen. Denys**, it is always good to talk to you and listen to your well-founded and logical opinions.

I am indebted to **Hans** who translated the summary into Dutch and maintaining a very nice working environment during these Covid times along with Wouter.

The MSuS group, especially the APS team, no doubt consists of one of the best colleagues I have worked with and I would like to express my deep gratitude to all of you.

Elif (the organizer) and I joined the cluster on the same day. In a new environment, it helps a lot to have someone who is also starting their job at the same time. I still remember the day we went to the ICT service desk for our ID cards. Not to mention the uncountable TGS courses that we attended together. It has always been a pleasure working with you, be it in the lab or on the MST Newsletters. I greatly admire your organization skills in the lab and have learnt a

lot from you. Fair to say that you are one of the most organized people I have met. We also often used to talk about how much time is remaining in our respective PhDs and how much more experiments we still needed to do. Gladly, we both have finished writing our theses and I feel proud to have worked with you on the project. Looking forward to reading your thesis and attending the defense ceremony which is just 21 days after mine. I wish the best of luck to you for all your future endeavors.

Wouter (the chemist) I remember being introduced to you by Wiebe on my first day here and you pronounced your name with a hard 'r' at the end (the Dutch way). Me, being new to the country, had no idea what you just said. Nonetheless, I learned it in a few days with a lot of other Dutch words that you taught me in the beginning. Being the chemist in the group, you always helped me with the chemistry. I had a lot of fun talking with you about science fiction, space travel, and survival run. Your miniature collection is something really to be admired. Thank you for being always helpful!

Ameya (the ever-ready) you have been a really good friend and a colleague. Finally we had someone in the MSuS group with whom I can speak in Urdu/Hindi. You are very creative and are always ready for new things and new challenges. I remember your poster that had actual pieces of membrane on it which ultimately got you a prize! I also admire your passion for collecting matchboxes and am really impressed by the sheer number of matchboxes that you own. I wish you the best of luck in your PhD research work and looking forward to reading your thesis too!

Lily (the artist) you have been an incredible friend and a colleague. Your comments and suggestions regarding my experiments in the lab and also on my writing helped me a lot in the project. Also, I am always impressed by your painting, drawing, and digital design skills. Thank you for providing me with delicious Chinese food. I wish you the best of luck with your remaining project.

Thank you **Tao** for providing valuable comments on my project. **Xiaoliu**, thank you for your help with the graphics designing. I would also like to thank you both (and Lily) for teaching me Mahjong, which I have totally forgotten now! **Jéré**, I have learned quite a lot from your presentation skills which I find one of the best. I wish you the best of luck for your thesis. It was a pleasure working with **Mehdi** on developing hollow fiber PEC membranes. Good luck with the rest of your PhD!

Also to our Multilayer team members, you guys are all awesome; **Jurjen**, **Moritz**, **Esra**, and **Wendy** I thank you all.

To my master student **Indira**, thank you for all the hard work you have put into the project. Without you, most of the Chapter 5 would not have been possible. I found you really hardworking and a fast-learning individual, and I wish you the best in your career.

Getting too long, isn't it? Well, since this is the most read part of the thesis, I will make sure you spend some time here!

Next, I would like to thank my friends from Cricket. Our weekly cricket matches provided ultimate entertainment, fierce competitions, some really good friendships, and the feeling of being at home. Thank you **Yawar**, **Ali Waqas**, **Naveed-ur-Rehman**, **Ghayoor**, **Ghazanfar**, **Jahanzeb**, **Bakht**, **Hamza**, **Azan**, **Zain**, **Ikram**, **Ahmed**, **Osama**, **Saeed**, **Faizan**, **Khurram**, **Saurabh**, **Tanuj**, **Mehedi** and **Mizan**.

Thank you **Wasim** for being a very good friend and a flat mate. It was really nice knowing you and I wish the best of luck for your PhD in Germany. Hope to see you soon sometime.

Also thank you **Shaur** for being a great friend since my days in South Korea. From our adventures there to our new adventures here, we have come a long way. Along with our families we have had great times together in the Netherlands and I am surely looking forward to many more. I wish you the best of luck with your PhD too.

Shakil and **Anvar**! Where do I even begin? It would constitute a thesis of its own if I start writing about you guys. As Khalil Gibran rightly said, *"In the sweetness of friendship let there be laughter, for in the dew of little things the heart finds its morning and is refreshed."* Us sharing an apartment in the early days of our PhDs, is a memory I will cherish forever. The bonds that were made stand stronger than ever. Three people, three different personalities, three different countries, but all getting along nicely, as though the three different types of personalities perfectly fitting in a complex piece of a puzzle. Our thought-provoking chats on physics, nature, space-time, cultures and religion, long into the night, with a small bon-fire in the balcony of our apartment while star-gazing, were absolutely priceless. I could go on and on about our countless adventures, European trips, numerous dinners, and the impact you have made on me, but that is the stuff of an autobiography, if I ever become famous enough to write one! Also, thank you **Isha** for being a good friend and wonderful host whenever I visited Shakil and your home.

And to my lovely wife **Saba**, I have the whole life time ahead to be thankful and grateful, and perhaps that too would not be enough. I could not have asked for a better life partner. You joined me in the Netherlands during the last year of my PhD where I had a lot of things to do. You stood by me, supported me, and motivated me whenever I felt stressed. I understand it was not easy for you to come to a new country and live alone while I was at work. However, you have shown incredible resilience and patience and never complained about it. Your words of support always keep me going. I am lucky to have you by my side. We have had great fun together and incredible adventures and certainly I am looking forward to many many more. Thank you for everything! Loads of love.

A big thank you to my sisters **Amna**, **Ayesha** and my brother **Muneeb** for being remarkably supportive. I wish you all a lot of success! And at last, two people in my life, without whom I would not be where I am. I owe everything to my beloved **Papa** and **Mama**. They have been a source of inspiration for me throughout my life, teaching me the true virtues of life and providing me with the best of everything. Your love, never-ending support, prayers, and immense sacrifices motivate me to excel further and be a better person. You have always supported my decisions and helped me achieve my dreams. Thank you for giving me the confidence and self-belief. I wish to make you more proud.

M.I Baig

September 2021

List of Publications

From this Thesis

- [1] **M.I. Baig**, J.D. Willott, W.M. De Vos, Enhancing the Separation Performance of Aqueous Phase Separation-Based Membranes through Polyelectrolyte Multilayer Coatings and Interfacial Polymerization, *ACS Appl. Polym. Mater.* 3 (2021) 3560–3568. doi:10.1021/acsapm.1c00457.
- [2] **M.I. Baig**, P.P.I. Sari, J. Li, J.D. Willott, W.M. de Vos, Sustainable Aqueous Phase Separation membranes prepared through mild pH shift induced polyelectrolyte complexation of PSS and PEI, *J. Memb. Sci.* 625 (2021) 119114. doi:10.1016/j.memsci.2021.119114.
- [3] **M.I. Baig**, J.D. Willott, W.M. de Vos, Tuning the structure and performance of polyelectrolyte complexation based aqueous phase separation membranes, *J. Memb. Sci.* 615 (2020) 118502. doi:10.1016/j.memsci.2020.118502.
- [4] **M.I. Baig**, E.N. Durmaz, J.D. Willott, W.M. de Vos, Sustainable Membrane Production through Polyelectrolyte Complexation Induced Aqueous Phase Separation, *Adv. Funct. Mater.* 30 (2020) 1907344. doi:10.1002/adfm.201907344.
- [5] E. N. Durmaz, **M. I. Baig**, J. D. Willott, W. M. de Vos, Polyelectrolyte Complex Membranes via Salinity Change Induced Aqueous Phase Separation, *ACS Appl. Polym. Mater.* 2 (2020) 2612–2621. doi:10.1021/acsapm.0c00255.

Beyond this Thesis

- [6] **M.I. Baig**, P.G. Ingole, J.D. Jeon, S.U. Hong, W.K. Choi, H.K. Lee, Water vapor transport properties of interfacially polymerized thin film nanocomposite membranes modified with graphene oxide and GO-TiO₂ nanofillers, *Chem. Eng. J.* 373 (2019) 1190–1202. doi:10.1016/j.cej.2019.05.122.
- [7] **M.I. Baig**, P.G. Ingole, J.D. Jeon, S.U. Hong, W.K. Choi, B. Jang, H.K. Lee, Water vapor selective thin film nanocomposite membranes prepared by functionalized Silicon nanoparticles, *Desalination*. 451 (2019) 59–71. doi:10.1016/j.desal.2017.06.005.
- [8] P.G. Ingole, M. Sohail, A.M. Abou-Elanwar, **M. I. Baig**, J.D. Jeon, W.K. Choi, H. Kim, H.K. Lee, Water vapor separation from flue gas using MOF incorporated thin film nanocomposite hollow fiber membranes, *Chem. Eng. J.* 334 (2018) 2450–2458. doi:10.1016/j.cej.2017.11.123.

-
- [9] P.G. Ingole, **M.I. Baig**, W. Choi, X. An, W.K. Choi, J.D. Jeon, H.K. Lee, Synthesis of superhydrophilic Nafion based nanocomposite hollow fiber membranes for water vapor separation, *Chem. Eng. Res. Des.* 127 (2017) 45–51. doi:10.1016/j.cherd.2017.09.003.
- [10] P.G. Ingole, **M.I. Baig**, W. Choi, X. An, W.K. Choi, H.K. Lee, Role of functional nanoparticles to enhance the polymeric membrane performance for mixture gas separation, *J. Ind. Eng. Chem.* 48 (2017) 5–15. doi:10.1016/j.jiec.2016.09.041.
- [11] **M.I. Baig**, P.G. Ingole, W.K. Choi, J.D. Jeon, B. Jang, J.H. Moon, H.K. Lee, Synthesis and characterization of thin film nanocomposite membranes incorporated with surface functionalized Silicon nanoparticles for improved water vapor permeation performance, *Chem. Eng. J.* 308 (2017) 27–39. doi:10.1016/j.ccej.2016.09.033.
- [12] P.G. Ingole, R.R. Pawar, **M.I. Baig**, J.D. Jeon, H.K. Lee, Thin film nanocomposite (TFN) hollow fiber membranes incorporated with functionalized acid-activated bentonite (ABn-NH) clay: Towards enhancement of water vapor permeance and selectivity, *J. Mater. Chem. A* 5 (2017) 20947–20958. doi:10.1039/c7ta04945e.
- [13] **M.I. Baig**, P.G. Ingole, W.K. Choi, S.R. Park, E.C. Kang, H.K. Lee, Development of carboxylated TiO₂ incorporated thin film nanocomposite hollow fiber membranes for flue gas dehydration, *J. Memb. Sci.* 514 (2016) 622–635. doi:10.1016/j.memsci.2016.05.017.
- [14] **M.I. Baig**, P.G. Ingole, W.K. Choi, S.R. Park, E.C. Kang, H.K. Lee, Water vapor permeation behavior of interfacially polymerized polyamide thin film on hollow fiber membrane substrate, *J. Taiwan Inst. Chem. Eng.* 60 (2016) 623–635. doi:10.1016/j.jtice.2015.11.010.
- [15] P.G. Ingole, **M.I. Baig**, W.K. Choi, H.K. Lee, Synthesis and characterization of polyamide/polyester thin-film nanocomposite membranes achieved by functionalized TiO₂ nanoparticles for water vapor separation, *J. Mater. Chem. A* 4 (2016) 5592–5604. doi:10.1039/c6ta00100a.

About the author

Muhammad Irshad Baig was born on the 7th of June 1991 in Rawalpindi, Pakistan. Growing up, he was always curious and fond of science subjects. As a teenager, he used to watch a lot of National Geographic and Discovery Channel and followed TV shows like Mythbusters, How its Made, and How the Universe Works. Taking inspirations from these, he always wanted to pursue a career in science and engineering. After completing his higher secondary school certification in 2009, he got admission in Ghulam Ishaq Khan Institute of Engineering, Sciences, and Technology (GIKI) in Topi, Pakistan where he received his Bachelor of Science in Materials Engineering in 2013. His graduation thesis focused on developing NiTiCu shape memory alloys for actuator applications.

After graduation, he went to South Korea in early 2014 where he pursued Masters of Engineering in Advanced Energy Technology from the Korea University of Science and Technology (UST). His MSc thesis focused on fabricating thin film composite and nanocomposite polymeric membranes for water vapor separation. It was during his MSc that Irshad grew fond of polymeric membranes and soon after graduating in 2016, he found a job as a Researcher in Korea Institute of Energy Research (KIER) where he continued working on developing thin film nanocomposite polymeric membranes for flue gas dehydration. In 2017 he moved to the Netherlands where he joined University of Twente as a PhD student in the Membrane Surface Science (MSuS) group headed by Prof. dr. Wiebe de Vos. The research work presented in this thesis is the result of his PhD study.

In 2021, after completion of his PhD contract, Irshad joined the MSuS group as a Postdoctoral scientific researcher where he will continue the research on Aqueous Phase Separation membranes.

ISBN: 978-90-365-5241-7