A grayscale micrograph showing several large, rounded cells with distinct boundaries. A large, dark, irregularly shaped cluster of nanoparticles is visible, spanning across several cells. The cluster has a textured, granular appearance.

Silicon-Containing Nanoparticles: From Functional Materials to Real-Life Applications

Sida Yin

Silicon-Containing Nanoparticles: From Functional Materials to Real-Life Applications

Sida Yin

Graduation Committee:

Chairman:	Prof. dr. J.L. Herek	University of Twente
Promotor:	Prof. dr. G.J. Vancso	University of Twente
Assistant-promotor:	Dr. ir. J. Duvigneau	University of Twente
Members:	Prof. dr. ir. L. Lefferts	University of Twente
	Prof. dr. A. Blume	University of Twente
	Prof. dr. Ing. N. Benson	Universität Duisburg/Essen
	Dr. O.J. Nguon	University of Twente
	Prof. ir. M. Hedenqvist	KTH Royal Institute of Technology

The research described in this Thesis was carried out in the Materials Science and Technology of Polymers (MTP) group (later Sustainable Polymer Chemistry group), MESA+ Institute for Nanotechnology, Faculty of Science and Technology, University of Twente, the Netherlands.

This research was financially supported by the MESA+ Institute for Nanotechnology, University of Twente, and by the Interreg V project Druckbare RFID - Tags für Massenmärkte (DruIDe).

Cover design: Sida Yin

Printed by: PROEFSCHRIFTMAKEN

ISBN: 978-90-365-5309-4

DOI: 10.3990/1.9789036553094

Copyright © 2021 Sida Yin, The Netherlands. All rights reserved. No parts of this Thesis may be reproduced, stored in a retrieval system or transmitted in any form or by any means without permission of the author. Alle rechten voorbehouden. Niets uit deze uitgave mag worden vermenigvuldigd, in enige vorm of op enige wijze, zonder voorafgaande schriftelijke toestemming van de auteur.

SILICON-CONTAINING NANOPARTICLES:
FROM FUNCTIONAL MATERIALS TO REAL-LIFE APPLICATIONS

DISSERTATION

to obtain
the degree of doctor at the Universiteit Twente,
on the authority of the rector magnificus,
prof. dr. ir. A. Veldkamp,
on account of the decision of the Doctorate Board
to be publicly defended
on Wednesday 15 December 2021 at 12.45 hours

by

Sida Yin

born on the 4th of August, 1990

in Hebei, China

This dissertation has been approved by:

Promotor:

Prof. dr. G.J. Vancso

University of Twente

Assistant-promotor:

Dr. ir. J. Duvigneau

University of Twente

Contents

Contents	I
Chapter 1	1
1.1 Introduction	2
1.2 Concept of this Thesis	5
1.3 References	7
Chapter 2	11
2.1 Silicon and Silica Nanoparticles: An Introduction	12
2.2 Silicon-Containing Nanoparticle Production	14
2.3 Silicon Nanoparticle-Based Electronic Ink	20
2.3.1 Inkjet Printing.....	20
2.3.2 Surface Oxidation of Silicon Nanoparticles.....	22
2.3.3 Surface Modification of Silicon Nanoparticles to Fabricate Stable Colloidal Inks	25
2.3.4 Inkjet Printing of Silicon Nanoparticle Inks	30
2.4 Silicon Nanoparticles as the Next Generation “Magic Bullets” in Biomedical Applications.....	31
2.4.1 Silicon Nanoparticles as Drug Delivery Carriers	32
2.4.2 Photoluminescent Silicon Nanoclusters and Bioimaging	34
2.4.3 Silicon Nanoparticle and Magnetic Resonance Imaging	36
2.5 Surface-Engineered Silica Nanoparticles	38
2.5.1 Surface Roughness Engineering of Silica Nanoparticles	38
2.5.2 Foam Cell Nucleation by Surface Topology Engineered Silica Nanoparticles.....	41
2.5.3 Polymer Nanocomposite Foams.....	43
2.6 Catalytic Effects of Silica Nanoparticles.....	47
2.6.1 Catalytic Activities of Silica Nanoparticles	47

2.7 Concluding Remarks.....	50
2.8 References	50
Chapter 3.....	71
3.1 Introduction.....	72
3.2 Results and Discussion.....	75
3.2.1 SiNP Characterization.....	75
3.2.2 AC to Study SiNP Sedimentation Behavior in Various Solvents	79
3.2.3 Batch Sedimentation Evaluation of SiNP Dispersions	82
3.2.4 Ethylene Glycol and Diethylene Glycol Stability in the Presence of SiNPs	85
3.3 Conclusion	87
3.4 Materials and Methods.....	88
3.5 Supporting Information.....	91
3.6 References	91
Chapter 4.....	97
4.1 Introduction.....	98
4.2 Results and Discussion.....	100
4.2.1 Printing Test of SiNP-Based Inks	100
4.2.2 Surface Modification of SiNPs	101
4.2.3 Characterization of Polymer-Nanoparticle Hybrids	102
4.2.4 Surface Modification of SiNPs	104
4.2.5 Spin-Coating and Diode Fabrication	106
4.3 Conclusion	110
4.4 Materials and Methods.....	110
4.5 References	114
Chapter 5.....	117
5.1 Introduction.....	119

5.2 Results and Discussion	122
5.2.1 SiO ₂ -R NPs Synthesis	122
5.2.2 Nanocomposite Foaming and Multinucleation	126
5.2.3 Multiple Foam Cells Nucleation Mechanism.....	130
5.3 Conclusion.....	133
5.4 Materials and Methods	134
5.5 Supporting Information	139
5.6 References	143
Chapter 6.....	149
6.1 Introduction	151
6.2 Results and Discussion.....	154
6.2.1 SiO ₂ Synthesis and Characterization.....	154
6.2.2 PE/SiO ₂ Composites and Fluorescence Microscopy.....	154
6.2.3 The Origin of the Observed Fluorescent: CQD Isolation and Characterization	155
6.2.4 Role of SiO ₂ NPs in CQD Formation in Heated PE/SiO ₂ Solutions....	157
6.2.5 Effect of SiO ₂ NPs Concentration of Fluorescent Intensity of PE/SiO ₂ Thin Films	159
6.2.6 Fluorescent Spectra of PE/SiO ₂ Thin Films and the Influence of the Reaction Temperature.....	160
6.2.7 Solution Blending CQDs and PE/SiO ₂ Composites with Pure PE.....	162
6.3 Conclusion.....	163
6.4 Materials and Methods	164
6.5 Supporting Information	167
6.6 References	168
Chapter 7.....	173
7.1 Introduction	174

7.2 Long-Term Stability and Printability of SiNP-Based Inks	174
7.3 Strategies for Polymer Immobilization on SiNP Surfaces	176
7.4 SiNPs as Dual Probe for Magnetic Resonance and Fluorescent Imaging.....	177
7.5 References	180
<i>Summary</i>	183
<i>Samenvatting</i>	187
<i>Acknowledgements</i>	191
<i>List of Publications</i>	193
<i>Curriculum Vitae</i>	195

Chapter **1**

General Introduction

1.1 Introduction

Nanoparticles (NPs) are defined as particles with at least one dimension smaller than 100 nm. Although NPs in nanotechnology have been introduced formally only several decades ago, humankind has been using NPs for thousands of years.^{1,2} For example, the famous Lycurgus Cup from 4th century Rome uses metal NPs to produce dichroism.¹ The glass cup appears to be green in reflected light. However, when light passes through, the cup seems to be red and purple. The color change is attributed to the dispersion of gold and silver NPs in the glass matrix that scatter the incoming light.¹

Compared to their bulk form, NPs possess an extremely high surface-to-volume ratio. Therefore, a high percentage of atoms/molecules are exposed at the NPs' surface. As a result, NPs often have unique physicochemical properties, e.g., magnetism, thermal/electrical conductivities, mechanical properties, and antimicrobial activity.^{3,4} Interestingly, since the percentage of surface atoms/molecules is strongly correlated to the particle size, NPs usually have size-tunable physicochemical properties (see Figure 1.1).^{3,5}

Figure 1.1 Comparison of characteristics of bulk materials and corresponding NPs.⁶

NPs are either made by breaking down bulk materials (top-down) or controlled assembly (bottom-up). Both natural phenomena and human activities can produce NPs.⁷ For example, fire results in the formation of carbon NPs.⁷ Living organisms like bacteria and fungi are also masters in nanotechnology in NP fabrication. For instance, bacteria produce selenium NPs by reducing selenite in dairy products.⁸ Nowadays, a wide range of materials and methods are used to make NPs.

Silicon is a particularly interesting material for nanotechnology. Si is the second most

abundant element, and when it is combined with the most abundant element on Earth, oxygen, silicon oxides are formed. Both silicon and silicon oxides have been used to form silicon-containing (Si-containing) NPs with exciting properties (see Figure 1.2). Si-containing NPs have attracted considerable attention from scientists and engineers across multiple disciplines.^{9,10} These Si-containing NPs represent a highly active research field and they are used in several industrial sectors, e.g., electronics, cosmetics, and healthcare.^{9,11–14} In this Thesis, we focus on designing and utilizing non-porous silicon NPs (SiNPs) and non-porous Silica (SiO₂) NPs in emerging application areas, e.g., printable electronics, nanocellular foaming, and chemical applications reaction enablers.

Figure 1.2 Representation of various Si-containing NPs.¹⁵

SiNPs comprise one of the most abundantly used classes of Si-containing NPs. SiNPs are well-known for their photoluminescent properties and size-dependent bandgap.¹⁶ SiNPs have been thoroughly studied in various application areas, e.g., light-emitting diodes (LEDs)¹⁷, drug delivery¹⁸, sensors^{19,20} and bio-imaging^{21–24}. Printing of such SiNPs is considered one of the most promising techniques for the large-scale fabrication of electronic devices.²⁵ However, SiNPs have not yet been widely utilized as electronic

inks for printing like other metal NPs, even though bulk silicon is considered the cornerstone of modern electronics.²⁶ To the best of our knowledge, only a few recent reports describe the use of SiNPs as components in inks to print electronic devices.^{26–29} This is attributed to the highly reactive surface of SiNPs and the inefficient approaches to prepare stable SiNP suspensions in large quantities.³⁰ Moreover, the influence of well-established surface derivatization strategies for stabilizing these dispersions, e.g. by utilizing polymer grafts, on the printability and electrical performance of SiNP-based devices is not yet thoroughly understood. This Thesis contributes to gaining a detailed insight into these fundamentally interesting aspects of NP science and engineering. Firstly, we prepared SiNP suspensions with different organic solvents to evaluate the accuracy of preexisting methods to predict the long-term colloidal stability of non-ideal SiNPs. Secondly, we investigated the influence of polymer grafts on the stability and printability of SiNP hybrid-based inks for printing electronic devices, including assessing the functionality of the printed devices.

SiO₂ NPs form another exciting class of silicon-based NPs that received a considerable amount of attention from the nanotechnology community. SiO₂ NPs can be formed in well developed synthetic approaches, and their properties can then be altered by a wide range of modification.^{31,32} They have been widely utilized in drug delivery, nano-structuring, and bioimaging applications.^{33,34} The Materials Science and Technology of Polymers (MTP) group has recently presented and discussed the utilization of hybrid SiO₂ NPs as high-efficiency heterogeneous foam cell nucleation agents in CO₂-based batch foaming of polymer nanocomposites.^{35,36} To date, the highest nucleation efficiency, i.e., the number of cells obtained per SiO₂ NP added, reported by the MTP group was ~0.5 for poly(dimethylsiloxane) (PDMS) grafted spherical 80 nm SiO₂ NPs.³⁶ In this Thesis, we show that the utilization of surface roughness engineered PDMS grafted SiO₂ NPs can further enhance the nucleation efficiency to values exceeding unity. This opens the possibility of applying new foaming strategies at relatively low saturation pressure (below 60 bar) while maintaining reasonable high cell densities and small cell sizes.

In addition, chemically inert mesoporous silica nanoparticles (MSNs) have been widely implemented as catalyst support for metal-based catalysts.^{37,38} Moreover, it has been reported in literature that the pores of MSNs' can act like nanometric reactors and encapsulate free radicals during polymer degradation.³⁹ The encapsulation of radicals extend their lifetime, which was demonstrated to accelerate polymer degradation. However, the synthetic approaches to prepare MSNs typically involve complex chemical reactions, extended washing steps, and long-time calcination,^{40,41} hampering their low-

cost industrial utilization. Compared to MSNs, Stöber SiO₂ particles are typically obtained by mild reaction conditions.⁴² Moreover, the well-established Stöber process is easily and cost-effectively scaled to industrial levels. We will demonstrate that carbon quantum dots can be obtained by the thermal degradation of polyethylene at mild reaction conditions in the presence of agglomerated SiO₂ NPs. We speculate that the SiO₂ aggregate pores prolong the lifetime of created PE radicals and, therefore, accelerate PE degradation to yield CQDs at modest reaction conditions.

Overall we believe that the results obtain in this Thesis contribute to a better understanding of Si-containing NPs in the presented emerging application areas.

1.2 Concept of this Thesis

Si-containing NPs with different morphologies and surface functionalities have been thoroughly studied and widely implemented in multiple application fields during the last few decades. Among the broad diversity of reported Si-containing NPs, SiNPs and SiO₂ NPs are two promising examples with unique capabilities for several interesting applications. However, a challenge in utilizing the application potential of Si-containing NPs (SiNPs and SiO₂ NPs) is related to the relative infancy of bridging advanced laboratory research and real technological use. With the swift progress in the enabling tools and methods in nanotechnology, new windows have been opened to tackle still open problems (or notoriously difficult challenges) in Si-containing NP research. In this Thesis, we address some of these challenges to ensure continuous progress in the field.

The literature covering general aspects and synthetic strategies of Si-containing NPs is reviewed in Chapter 2. Moreover, recent developments of Si-containing NPs in the selected emerging application areas presented in the subsequent chapters are briefly discussed. This Chapter provides an outline to understand better the opportunities and challenges for integrating Si-containing NPs into real-life applications.

In Chapter 3, we investigate the long-term colloidal stability of SiNPs with a complex geometry and broad size distribution. Theoretical (Stokes' law) and experimental (analytical centrifugation and batch sedimentation testing) approaches are used to predict and measure the colloidal stability of SiNPs in different alcohols and glycols. The insights obtained serve as a first step towards formulating long-term stable complex SiNPs-based inks for printable electronic devices (e.g., RFID tags). Furthermore, the results highlighted the need for surface modification of SiNPs to enhance their long-term colloidal stability in glycols.

Based on the results obtained in Chapter 3, core-shell SiNP/polymer hybrids with poly (methyl methacrylate) and poly (ethylene glycol) methacrylate shells are synthesized through surface-initiated atom transfer radical polymerization (SI-ATRP) to enhance stability and printability of SiNP-based inks for printable electronic devices. The grafted polymer shells help reduce nozzle clogging during printing and prevent potential interactions between particles and solvent during storage. The I-V (current-voltage) characteristics of printed, electronic devices from SiNP/polymer hybrids are evaluated. Furthermore, the I-V characteristics of the printed devices point towards the need to develop the functional SiNP-based electronic inks further.

In Chapter 5, surface roughness engineered SiO₂ NPs (SiO₂-R NPs) with PDMS shells are synthesized and exploited as heterogeneous nucleation agents for CO₂ batch foaming of PMMA nanocellular foams. By combining the reduced free energy for foam cell nucleation inside nanocavities on the particle surface and the high CO₂ absorption of the PDMS shell, multiple foam cells are nucleated from a single particle. This extremely efficient nucleation behavior renders SiO₂-R NPs highly promising nucleation agents for polymer nanocellular foaming.

In Chapter 6, carbon quantum dots (CQDs) fluorescent markers containing polyethylene (PE) are synthesized at mild reaction conditions using SiO₂ NP aggregates as enablers. By taking advantage of the nano-pores residing on the surface of the aggregates, the PE chains that enter the pores can degrade and form CQDs at low temperatures (90-110 °C). Moreover, we demonstrate that PE/CQD composites and PE samples loaded with extracted CQDs could be visually separated from pure unmarked PE upon irradiation with 367 nm light. Thus this Chapter provides a facile solution to synthesize fluorescent markers that are readily used as labeling ingredients for component identification and plastic waste recycling.

Finally, in Chapter 7, we provide an outlook for future directions of SiNPs in printable electronics and bioimaging. For SiNP-based inks, we present and discuss self-immolating polymers and catalyst-free hydrosilylation as the next essential step to enable the large-scale production of hybrid SiNP-based inks with enhanced colloidal stability and printability, with a minimum impact on the performance of printed, electronic devices. In addition, some preliminary results on utilizing multi-crystalline SiNPs as a dual probe for magnetic resonance imaging and fluorescent imaging are presented.

1.3 References

- (1) Freestone, I.; Meeks, N.; Sax, M.; Higgitt, C. The Lycurgus Cup - A Roman Nanotechnology. *Gold Bulletin* **2008**, 40 (4), 270–277.
- (2) Landauer, R. (2018) Information Is Inevitably Physical. In A. J. G. Hey (Ed.). *Feynman and Computation* (pp 77–92). CRC Press.
- (3) Khan, I.; Saeed, K.; Khan, I. Nanoparticles: Properties, Applications and Toxicities. *Arabian Journal of Chemistry* **2019**, 12 (7), 908–931.
- (4) Baig, N.; Kammakakam, I.; Falath, W.; Kammakakam, I. Nanomaterials: A Review of Synthesis Methods, Properties, Recent Progress, and Challenges. *Materials Advances* **2021**, 2 (6), 1821–1871.
- (5) Jeevanandam, J.; Barhoum, A.; Chan, Y. S.; Dufresne, A.; Danquah, M. K. Review on Nanoparticles and Nanostructured Materials: History, Sources, Toxicity and Regulations. *Beilstein Journal of Nanotechnology* **2018**, 9 (1), 1050–1074.
- (6) Huang, C.; Chen, X.; Xue, Z.; Wang, T. Effect of Structure: A New Insight into Nanoparticle Assemblies from Inanimate to Animate. *Science Advances* **2020**, 6 (20), 10.1126/sciadv.aba1321.
- (7) Griffin, S.; Masood, M. I.; Nasim, M. J.; Sarfraz, M.; Ebokaiwe, A. P.; Schäfer, K. H.; Keck, C. M.; Jacob, C. Natural Nanoparticles: A Particular Matter Inspired by Nature. *Antioxidants* **2018**, 7 (1), 3.
- (8) Wright, M. H.; Farooqui, S. M.; White, A. R.; Greene, A. C. Production of Manganese Oxide Nanoparticles by *Shewanella* Species. *Applied and Environmental Microbiology* **2016**, 82 (17), 5402–5409.
- (9) Jeelani, P. G.; Mulay, P.; Venkat, R.; Ramalingam, C. Multifaceted Application of Silica Nanoparticles. A Review. *Silicon* **2020**, 12 (6), 1337–1354.
- (10) Chang, H.; Sun, S. Q. Silicon Nanoparticles: Preparation, Properties, and Applications. *Chinese Physics B* **2014**, 23 (8), 1–14.
- (11) Nayfeh, M. H.; Mitras, L. (2008) Silicon Nanoparticles. New Photonic and Electronic Material at the Transition Between Solid and Molecule. In V. Kumar (Ed.). *Nanosilicon* (pp 1-78). Elsevier.
- (12) O'Farrell, N.; Houlton, A.; Horrocks, B. R. Silicon Nanoparticles: Applications in Cell Biology and Medicine. *International Journal of Nanomedicine* **2006**, 1 (4), 451–472.
- (13) Downing, M. A.; Jain, P. K. Mesoporous Silica Nanoparticles: Synthesis, Properties, and Biomedical Applications. *Nanoparticles for Biomedical Applications: Fundamental Concepts, Biological Interactions and Clinical Applications* **2019**, 42 (10), 267–281.
- (14) Capeletti, L. B.; Loiola, L. M. D.; Picco, A. S.; da Silva Liberato, M.; Cardoso, M. B. Silica Nanoparticle Applications in the Biomedical Field. *Smart Nanoparticles for Biomedicine* **2018**, 17 (19–20), 115–129.
- (15) Croissant, J. G.; Fatieiev, Y.; Khashab, N. M. Degradability and Clearance of Silicon, Organosilica, Silsesquioxane, Silica Mixed Oxide, and Mesoporous Silica Nanoparticles. *Advanced Materials* **2017**, 29 (9), 10.1002/adma.201604634.
- (16) Meier, C.; Gondorf, A.; Lüttjohann, S.; Lorke, A.; Wiggers, H. Silicon Nanoparticles: Absorption, Emission, and the Nature of the Electronic Bandgap.

- Journal of Applied Physics* **2007**, *101* (10), 103112.
- (17) Maier-Flaig, F.; Rinck, J.; Stephan, M.; Bocksrocker, T.; Bruns, M.; Kübel, C.; Powell, A. K.; Ozin, G. A.; Lemmer, U. Multicolor Silicon Light-Emitting Diodes (SiLEDs). *Nano Letters* **2013**, *13* (2), 475–480.
- (18) Haidary, S. M.; Córcoles, E. P.; Ali, N. K. Nanoporous Silicon as Drug Delivery Systems for Cancer Therapies. *Journal of Nanomaterials* **2012**, *2012*, 830503.
- (19) Jalkanen, T.; Mäkilä, E.; Määttä, A.; Tuura, J.; Kaasalainen, M.; Lehto, V. P.; Ihalainen, P.; Peltonen, J.; Salonen, J. Porous Silicon Micro- and Nanoparticles for Printed Humidity Sensors. *Applied Physics Letters* **2012**, *101* (26), 263110.
- (20) Chu, B.; Wang, H.; Song, B.; Peng, F.; Su, Y.; He, Y. Fluorescent and Photostable Silicon Nanoparticles Sensors for Real-Time and Long-Term Intracellular pH Measurement in Live Cells. *Analytical Chemistry* **2016**, *88* (18), 9235–9242.
- (21) Kwiatkowski, G.; Jähnig, F.; Steinhauser, J.; Wespi, P.; Ernst, M.; Kozerke, S. Nanometer Size Silicon Particles for Hyperpolarized MRI. *Scientific Reports* **2017**, *7* (1), 7946.
- (22) Whiting, N.; Hu, J.; Zacharias, N. M.; Lokesh, G. L. R.; Volk, D. E.; Menter, D. G.; Rupaimoole, R.; Previs, R.; Sood, A. K.; Bhattacharya, P. Developing Hyperpolarized Silicon Particles for in Vivo MRI Targeting of Ovarian Cancer. *Journal of Medical Imaging* **2016**, *3* (3), 036001.
- (23) Ji, X.; Peng, F.; Zhong, Y.; Su, Y.; Jiang, X.; Song, C.; Yang, L.; Chu, B.; Lee, S. T.; He, Y. Highly Fluorescent, Photostable, and Ultrasmall Silicon Drug Nanocarriers for Long-Term Tumor Cell Tracking and in-Vivo Cancer Therapy. *Advanced Materials* **2015**, *27* (6), 1029–1034.
- (24) Whiting, N.; Hu, J.; Shah, J. v.; Cassidy, M. C.; Cressman, E.; Millward, N. Z.; Menter, D. G.; Marcus, C. M.; Bhattacharya, P. K. Real-Time MRI-Guided Catheter Tracking Using Hyperpolarized Silicon Particles. *Scientific Reports* **2015**, *5*, 12842.
- (25) Zeng, M.; Zhang, Y. Colloidal Nanoparticle Inks for Printing Functional Devices: Emerging Trends and Future Prospects. *Journal of Materials Chemistry A* **2019**, *7* (41), 23301–23336.
- (26) Gupta, A.; Khalil, A. S. G.; Offer, M.; Geller, M.; Winterer, M.; Lorke, A.; Wiggers, H. Synthesis and Ink-Jet Printing of Highly Luminescing Silicon Nanoparticles for Printable Electronics. *Journal of Nanoscience and Nanotechnology* **2011**, *11* (6), 5028–5033.
- (27) Lawes, S.; Sun, Q.; Lushington, A.; Xiao, B.; Liu, Y.; Sun, X. Inkjet-Printed Silicon as High Performance Anodes for Li-Ion Batteries. *Nano Energy* **2017**, *36*, 313–321.
- (28) Drahi, E.; Blayac, S.; Borbely, A.; Benaben, P. Impact of Ink Synthesis on Processing of Inkjet-Printed Silicon Nanoparticle Thin Films: A Comparison of Rapid Thermal Annealing and Photonic Sintering. *Thin Solid Films* **2015**, *574*, 169–176.
- (29) Drahi, E.; Gupta, A.; Blayac, S.; Saunier, S.; Benaben, P. Characterization of Sintered Inkjet-Printed Silicon Nanoparticle Thin Films for Thermoelectric Devices. *Physica Status Solidi (A) Applications and Materials Science* **2014**, *211* (6), 1301–1307.
- (30) Sailor, M. J. (2017). Chemical Reactivity and Surface Chemistry of Porous

- Silicon. In L. Canham (Ed.). *Handbook of Porous Silicon* (pp 1-20). Springer International Publishing, Cham.
- (31) Badley, R. D.; Ford, W. T.; McEnroe, F. J.; Assink, R. A. Surface Modification of Colloidal Silica. *Langmuir* **1990**, *6* (4), 792–801.
- (32) Ibrahim, I. a. M.; Zikry, a. a. F.; Sharaf, M. a. Preparation of Spherical Silica Nanoparticles: Stober Silica. *Journal of American Science* **2010**, *6* (11), 985–989.
- (33) Barbé, C.; Bartlett, J.; Kong, L.; Finnie, K.; Lin, H. Q.; Larkin, M.; Calleja, S.; Bush, A.; Calleja, G. Silica Particles: A Novel Drug-Delivery System. *Advanced Materials* **2004**, *16* (21), 1959–1966.
- (34) Korzeniowska, B.; Nooney, R.; Wencel, D.; McDonagh, C. Silica Nanoparticles for Cell Imaging and Intracellular Sensing. *Nanotechnology* **2013**, *24* (44), 442002.
- (35) Liu, S.; Yin, S.; Duvigneau, J.; Vancso, G. J. Bubble Seeding Nanocavities: Multiple Polymer Foam Cell Nucleation by Polydimethylsiloxane-Grafted Designer Silica Nanoparticles. *ACS Nano* **2020**, *14* (2), 1623–1634.
- (36) Liu, S.; Zoetebier, B.; Hulsman, L.; Zhang, Y.; Duvigneau, J.; Vancso, G. J. Nanocellular Polymer Foams Nucleated by Core-Shell Nanoparticles. *Polymer* **2016**, *104*, 22–30.
- (37) Shinde, P. S.; Suryawanshi, P. S.; Patil, K. K.; Belekar, V. M.; Sankpal, S. A.; Delekar, S. D.; Jadhav, S. A. A Brief Overview of Recent Progress in Porous Silica as Catalyst Supports. *Journal of Composites Science* **2021**, *5* (3), 75.
- (38) Yu Lai, Dr. C. Mesoporous Silica Nanomaterials Applications in Catalysis. *Journal of Thermodynamics & Catalysis* **2014**, *05* (01), 10–12.
- (39) Sakata, Y.; Azhar Uddin, M.; Muto, A.; Kanada, Y.; Koizumi, K.; Murata, K. Catalytic Degradation of Polyethylene into Fuel Oil over Mesoporous Silica (KFS-16) Catalyst. *Journal of Analytical and Applied Pyrolysis* **1997**, *43* (1), 15–25.
- (40) Mehmood, A.; Ghafar, H.; Yaqoob, S.; Gohar, U. F.; Ahmad, B. Mesoporous Silica Nanoparticles: A Review. *Journal of Developing Drugs* **2017**, *06* (02), 10.4172/2329-6631.1000174.
- (41) Narayan, R.; Nayak, U. Y.; Raichur, A. M.; Garg, S. Mesoporous Silica Nanoparticles: A Comprehensive Review on Synthesis and Recent Advances. *Pharmaceutics* **2018**, *10* (3), 118.
- (42) Stöber, W.; Fink, A.; Bohn, E. Controlled Growth of Monodisperse Silica Spheres in the Micron Size Range. *Journal of Colloid And Interface Science* **1968**, *26* (1), 62–69.

Chapter 2

Emerging Applications of Silicon-Containing Nanoparticles

Silicon-containing nanoparticles are considered a promising class of materials with exciting physical properties and the potential to revolutionize many emerging application areas. This Chapter introduces the fundamental aspects of silicon-containing nanoparticles and their most common production approaches. In addition, we provide a comprehensive overview of the frontiers of silicon-containing nanoparticle research for the growing fields of printable Silicon-containing electronics, theranostics, nanocellular polymer foaming, and catalysis. We include an introduction to readily applicable particle surface modification strategies as well. Finally, the limitations and challenges for the successful commercialization of silicon-containing nanoparticles in the application fields mentioned are also presented and discussed.

2.1 Silicon and Silica Nanoparticles: An Introduction

Silicon (Si) is the second most abundant element on earth. It is a tetravalent semiconductor that is widely used in numerous fields.^{1,2} When combining Si with the most abundant element on Earth, oxygen, silicon oxides are formed, of which SiO₂ is the most naturally occurring. Almost all electronic devices produced today contain Si-containing components like integrated circuit chips, metal-oxide-Si field-effect transistors, or semiconductor memories.³ With the continuous downsizing of silicon-containing (Si-containing) electronic components, the interest in structure-property relationships of nano-sized Si-containing compounds is swiftly increasing.

Nanoparticles (NPs) are typically defined as microscopically small particles with at least one of their dimensions below 100 nm.⁴ Compared to their corresponding bulk form, NPs of the same material often possess unique properties that can open new application areas.⁴ Numerous research efforts have been dedicated to the investigation and utilization of Si- and SiO₂-containing nanomaterials.⁵⁻⁸

Upon entering the nanoscale realm, Si particles start to reveal new properties – like photoluminescence (PL), antimicrobial properties, and a size-dependent electronic bandgap^{9,10} – that are not observed for bulk silicon. Depending on the preparation method, silicon nanoparticles (SiNPs) are either amorphous or crystalline, with diameters ranging from less than one nanometer to a few hundred nanometers.⁹ Due to the highly active H-Si-Si-H surface structure, SiNPs tend to oxidize (aging) when stored in ambient conditions, which results in the formation of a surface-exposed inert SiO₂ layer.¹¹

One of the most intriguing and studied properties of SiNPs is their luminescent ability in the visible spectrum.¹² In the 1990s, Canham¹³ discovered visible red PL of electrochemically etched Si at room temperature. Nearly three decades after the first discovery of PL from SiNPs, the origin of the PL from SiNPs is still under debate.¹⁴⁻¹⁶ The most popular explanation for the observed PL is that by reducing the size of the bulk crystal to nanocrystals or even nanoclusters, the electrons in the material experience quantum confinement, which increases the bandgap.¹⁷ In bulk materials, the band gaps are merged to form a conduction band. By decreasing the material's size, the bandgap increases (see Figure 2.1), resulting in discrete energy levels, which eventually leads to size-dependent PL. The PL of SiNPs possesses several unique properties like i) a broad range of absorption and excitation wavelengths, ii) color (emission) tunability, and iii) monochromatic light emission.¹⁸

Numerous studies have been carried out to explore new application areas for PL SiNPs, such as in sensors^{19,20} and bio-imaging^{21,22}. For example, Maier-Flaig et al.²³ reported multicolor Si-containing light-emitting diodes (Si LED) using well-defined, size-separated SiNPs. SiNPs are also promising candidates in the photovoltaic industry. For instance, the integration of ultrathin films of luminescent SiNPs in polycrystalline solar cells was demonstrated by Stupca et al.²⁴ By incorporating 1 nm blue luminescent or 2.85 nm red luminescent SiNPs, they managed to enhance the power performance by 60 – 70% in the UV region and 10% in the visible region. Similar to the origin of PL, the correlation between the size and PL for SiNPs is still not fully elucidated. However, based on the calculation of the quantum confinement effect, SiNPs need to be smaller than 5 nm to be photoluminescent.²⁵

When looking at silica nanoparticles (SiO₂ NPs), one learns that they are readily dispersed in aqueous solutions and even to some degree biodegradable.^{27,28} SiO₂ particles with diameters across the nanometer length scale until tens of micrometers (see Table 2.1) are prepared with flame pyrolysis and molecular condensation approaches. Unlike SiNPs, the SiO₂ NPs' surface is more chemically inert, and these particles are thus readily stored in ambient conditions without significant changes in surface composition.

Figure 2.1 The size-dependent bandgaps of bulk material, nanocrystals, clusters, and atoms.²⁶

With their low toxicity, good chemical resistance, and optical transparency, SiO₂ NPs are therefore interesting for utilization in drug delivery systems^{29–31}, bio-sensors^{32,33}, and

bio-imaging^{34,35}. For instance, SiO₂ NPs were reported to deliver drugs to specific locations in the body with a precisely controlled release rate profile.³¹ In addition, organic dye-doped SiO₂ NPs have been extensively investigated as the viable imaging agents for nucleic acids, proteins, and pathogen detection.^{36–38}

Before presenting and discussing the emerging Si-containing NP-based applications that are the central topics of the following Chapters of this Thesis, we will first briefly introduce the most common SiNPs and SiO₂ NP production methods.

2.2 Silicon-Containing Nanoparticle Production

During the past few decades, various procedures have been developed to synthesize SiNPs and SiO₂ NPs with control over particle size, morphology and composition.^{39–60} These methods can be categorized into either bottom-up or top-down approaches (see Figure 2.2). Si-containing NPs can be synthesized either as individual particles (primary particles) or as agglomerated particles.^{39,45,53,60} Table 2.1 shows a detailed overview of the most commonly used methods to produce Si and SiO₂ NPs, including their most important characteristics and advantages/disadvantages. Since it is not our scope to review the synthesis of Si and SiO₂ NPs in detail, the interested reader is directed to the references shown in Table 2.1 for a more comprehensive overview.

Figure 2.2 a) Top-down and bottom-up approaches for SiNP synthesis; b) schematic of the Stober reaction for the synthesis of SiO₂.⁶¹

Nowadays, SiNPs can be fabricated via numerous routes, both bottom-up and top-down, with various levels of success.^{53–60} Laser ablation is a physical procedure that has been commonly used to fabricate NPs from their bulk form, including SiNPs. Yoshida et

al.⁵⁴ reported the preparation of nanometer-sized Si crystallites via excimer laser ablation under helium (He) gas atmosphere. They also found a linear dependence of average particle diameter to the inert gas pressure, which can be used to control the size of SiNPs in the nanometer regime. Ball milling is also a standard procedure to break down bulk materials.⁹ Lam et al.⁵³ utilized ball milling of solid graphene with silicon oxide, followed by annealing at 150 °C to prepare SiNPs. The resulting SiNPs showed a broad size distribution and a 1 nm silicon oxide overlayer. Chemical procedures have also been applied to obtain SiNPs. Heath⁵⁷ was the first to report the solution-phase synthesis of SiNPs. Heath successfully reduced silicon halides with sodium naphthalenide in a nonpolar organic solvent to produce hydrogen capped free-standing SiNPs. Recently, Hülser et al.⁶⁰ introduced a cost-efficient and scalable synthetic method for SiNPs using a hot-wall reactor. By mixing diborane inside the reactor with silane, they managed to produce boron-doped SiNPs. They managed to achieve a production rate of 0.75 kg h⁻¹ and an energy efficiency of 1.4 kWh kg⁻¹ for SiNP fabrication. The developments in large-scale and cost-efficient SiNP synthesis allow SiNPs to be transformed from lab-scale research to real-life applications. Besides using bulk silicon or Si-containing molecules, there are also reports that present and discuss the use of low-cost, environmentally friendly raw materials like rice husk and wheat straws to produce PL SiNPs.⁶²

SiO₂ NPs are mainly prepared via precipitation (precipitated silica), high-temperature flame pyrolysis (fumed silica) or by the molecular condensation of silanol in an aqueous solution and hydrothermal treatments (colloidal silica).^{39–52} Precipitated silica is commonly prepared by adding mineral acid (e.g., HCl, H₂SO₄) to the silicate solution. The properties of precipitated silica are strongly dependent on the agitation, pH, temperature, and other environmental parameters.^{41,42} For example, Musić et al.⁴² reported using commercial sodium silicate solution with concentrated H₂SO₄ to prepare precipitated silica with a diameter of 15–30 nm. Furthermore, they demonstrated that their approach is ready for large-scale production without altering the properties of the precipitated silica nanoparticles. Fumed silica is typically fabricated at 1,200–1,400 °C by vapor-phase hydrolysis of silicon tetrachloride (SiCl₄) in a hydrogen-oxygen flame followed by rapid quenching.⁶³ Fumed silica consists of highly coalesced (agglomerated) NPs with a primary particle size ranging from 10–20 nm.⁶⁴ Recently, Chen et al.⁴⁰ introduced a more economical and environmentally friendly approach for fumed silica synthesis by hydrolysis of SiCl₄ with water vapor at a low-temperature range (150 °C to 250 °C). Through this method, they prepared SiO₂ NPs with an average surface area of 418 cm² g⁻¹ and an average size of 141.7 nm at 150 °C.

Compared to fumed silica, colloidal silica particles synthesized via molecular condensation reactions have a narrower size distribution with almost no coalescence (primary particles),⁶⁵ which is desirable for a wide range of application areas, such as bio-sensing, bio-imaging, and drug delivery. The most widely used procedure for colloidal SiO₂ NPs synthesis is the so-called Stöber reaction.^{43–47} This reaction was first reported by Werner Stöber in 1968.⁴⁵ For a standard Stöber reaction, the particles are formed via a sol-gel process from the hydrolysis and condensation of alkyl silicates in the presence of ammonia as a catalyst (Figure 2.2b). One significant advantage of the Stöber reaction, as mentioned, is the ability to produce nearly monodisperse SiO₂ NPs. In addition, the reaction can be easily scaled up and the products are readily transferred to aqueous solutions.⁴⁵ Besides the Stöber reaction, other methods for the preparation of colloidal SiO₂ NPs have been introduced. For example, Gorji et al.⁶⁶ reported a synthetic procedure for the preparation of SiO₂ NPs using tetraethyl orthosilicate (TEOS), polyethylene glycol, and hydrochloric acid. In addition, Zulfiqar et al.⁶⁷ demonstrated the fabrication of SiO₂ NPs using bentonite clay as the primary silica source. They successfully fabricated SiO₂ NPs ranging from 70 nm to 1.4 μm in diameter through the thermal treatment of the bentonite clay in ethanol in the presence of nitric acid.

Having introduced Si and SiO₂ NPs as an interesting class of materials, and shortly reviewing their common production methods, we will focus in the remainder of this Chapter on exciting, emerging, and in our opinion, overlooked application areas of these NPs. Thus, in the following sections we present and discuss the frontiers of Si-containing NPs research and review the utilization of Si-containing NPs as ink for printable electronics (2.3), in biomedical applications (2.4), as nucleation agents for polymer foam cell nucleation (2.5), and as catalysts for chemical reactions (2.6).

Table 2.1 List of selected Si-containing NPs synthesis approaches with their advantages/disadvantages.

Method	Material	Temperature	Diameter (nm)	Advantage	Disadvantage
SiO₂ NP					
flame pyrolysis ³⁹	SiCl ₄ , methane, propane	1500 °C		High reaction speed, hydrophilic surface	Particles are agglomerated
flame pyrolysis ⁴⁰	SiCl ₄ , N ₂ , H ₂ O	125 - 300 °C	6.5-8.2 (P) 141.7-186.1 (A)		
precipitated silica ⁴¹	silica gel, HCl, NaOH, H ₂ SO ₄	RT	50 nm (M)	High solid content	Long reaction time, corrosive substances.
precipitated silica ⁴²	sodium silicate, H ₂ SO ₄	80-90 °C	15-30 nm (M)		
modified Stöber ⁴³	TEOS, NH ₃ , H ₂ O, isopropanol	5, 20 °C	30-930 (M)	High solid content	
modified Stöber ⁴⁴	TEOS, NH ₃ , H ₂ O, ethanol (DMSO), Alexa Fluor 555	RT	13-64 (M)	Adjustable luminescence	
Stöber ⁴⁵	TEOS, NH ₃ , H ₂ O, alcohols	RT	50-2000 (M)		
Stöber ⁴⁶	TEOS, NH ₃ , H ₂ O, ethanol	30 °C	160-600 (M)	Controllable size, short reaction time, good reproducibility	
seeded growth ⁴⁷	TEOS, NH ₃ , H ₂ O, ethanol	10, 25, 40 °C	Up to 2 um (M)		

Mesoporous SiO ₂ NP					
<i>sol-gel</i> ⁴⁸	TEOS, CTAB, CPC, ethanol, NH ₃	RT	400-1100 (particle) 2.81-32.8 (pore)	Controllable pore size and geometry, short reaction time	Surfactants are hard to remove, usually requires long-time calcination
<i>sol-gel</i> ⁴⁹	TEOS, C ₁₄ CluA, NaOH, TMAPS, methanol, H ₂ O	60 °C	2.2-4.7 (pore)		
<i>sol-gel</i> ⁵⁰	TEOS, NH ₃ , H ₂ O, HAD, isopropanol	RT			
<i>sol-gel</i> ⁵¹	TMOS, Pluronic P123, HCl	35 °C	500-2000 (particle) 4 (pore)	No organic solvent, rod-like/hexagonal prisms particles	
<i>sol-gel</i> ⁵²	TEOS, Pluronic P123, citric acid, trisodium citrate, H ₂ O,	RT	500 (particle) 5.8-9.8 (pore)		
SiNP					
<i>ball milling</i> ⁵³	Graphite, SiO ₂ powder	RT	7	Low cost, scalable	
<i>laser ablation</i> ⁵⁴	Single crystalline Si wafer	RT	10	Single crystalline SiNPs	
<i>etching</i> ⁵⁵	Si wafer, HF, ethanol, isopropanol, allylamine, H ₂ PtCl ₆	RT	4.6±1.9	Resistant to aging	Typically have a broad size distribution and require an

<i>inverse micelle</i> ⁵⁶	SiX ₄ (X=Cl, Br, I)	RT	1.8-10	Solution-based	inert/N ₂ atmosphere Some of the methods require high temperature and vacuum
<i>hydrothermal</i> ⁵⁷	SiCl ₄ , HSiCl ₃ /C ₈ H ₁₇ SiCl ₃ , Na, toluene, hexane	385 °C	5		
<i>microwave pyrolysis</i> ⁵⁸	SiH ₄ , H ₂ , Ar	RT	6-11	Single crystalline	
<i>laser pyrolysis</i> ⁵⁹	SiH ₄	RT	2-7	Single crystalline	
<i>hot-wall pyrolysis</i> ⁶⁰	Silane, H ₂ , N ₂	800-100 °C	150-450	Low cost, scalable	

* RT - room temperature; (M) – monodisperse; (P) – primary particle size; (A) – agglomerate size; TMAPS - N-trimethoxysilylpropyl-N,N,N-trimethyl-ammonium chloride; CTAB - n-Hexadecyltrimethylammonium bromide; C₁₄CluA - N-myristoyl-L-glutamic acid; TEOS - tetraethyl orthosilicate; TMOS – tetramethyl orthosilicate; C₈H₁₇SiCl₃ - n-octyltrichlorosilane; HAD - n-hexadecylamine.

2.3 Silicon Nanoparticle-Based Electronic Ink

SiNPs are a promising candidate for the fabrication of low-cost, large-area, lightweight, flexible electronic devices fabricated by printing techniques. Therefore, section 2.3.1. will briefly introduce inkjet printing technology, set forth the requirements of SiNPs based electronic inks, and continue with an in-depth presentation of the oxidative stability (2.3.2), colloidal stability (2.3.3), and printing of SiNPs (2.3.4).

2.3.1 Inkjet Printing

Inkjet printing is considered to be a potential replacement for lithography by electronic component manufacturers.^{68,69} It can produce electronic devices on polymeric substrates or even on paper with improved quality, production speed, and cost-efficiency compared to traditional lithography approaches.^{70,71} The inkjet printing of electronic devices typically involves two steps. The first step is depositing and drying inks to form thin films/conductive patterns. The second is an annealing/sintering step to modify the printed layer microstructure and adjust electrical conductivity.⁶⁸ Inkjet printing is considered to be an advanced and economical approach to manufacturing electronic devices. However, as for any printing technique, the most critical factors for success lie on the ink end. The quality and reproducibility of the inkjet printing process rely on the control of drop formation and the interaction between the deposited drops and substrates. In the last decade metal NPs,^{72,73} conductive polymers,⁷⁴ and organic-metal hybrids⁷⁵ have been extensively studied as conductive inks for inkjet printing of electronic devices.

Figure 2.3 Schematic drawing of a) continuous, b) thermal, and c) piezoelectric drop on demand inkjet printers.⁷⁶

Based on the mechanism of drop formation, inkjet printing can be divided into two

categories: drop on demand (DoD) and continuous inkjet (CIJ) printing (Figure 2.3).⁶⁸ The drop diameters for DoD and CIJ are in the range of 20-50 μm and 100 μm , respectively. The nozzle of a CIJ printer head continuously produces droplets. A charged deflector deflects the unwanted droplets for collection and allowing recycling to avoid ink waste. (We note that there is a risk that the ink gets polluted/altered during ink recycling when exposed to the atmosphere.) The advantage of CIJ printing is that through continuous jetting, the nozzles are continuously kept at a high moisture level, which helps to prevent undesirable nozzle clogging. In DoD printing, a droplet is only ejected from the nozzle when the pressure pulse propagating the ink reaches a certain threshold. This pressure pulse is usually generated by a current pulse that either boils a small portion of the ink in the nozzle chamber or introduces mechanical force to squeeze the chamber through a piezoelectric transducer.⁶⁸ As such, the ink will only be released from the nozzle when needed. This avoids wasting ink and the unnecessary exposure of ink to ambient conditions, which may lead to ink pollution and/or degradation. One of the major disadvantages of DoD printing is the lower production speed compared to CIJ printing.

Nowadays, inkjet printing has been successfully utilized to fabricate various electronic devices like flexible circuits⁷⁷, memory devices⁷⁸, displays^{79,80}, sensors⁸¹⁻⁸³, field-effect transistors (FET)⁸⁴⁻⁸⁸, batteries⁸⁹, and solar cells^{90,91}. For example, Sekitani et al.⁸⁸ used an inkjet printer to manufacture an organic thin-film transistor. Using a subfemtoliter inkjet printer, they fabricated p-channel and n-channel transistors with single-micrometer resolution on rigid and flexible substrates that can operate with a very low voltage (3 V). Molina-Lopez et al.⁸⁷ successfully utilized inkjet printing to build stretchable FET arrays and interconnections (see Figure 2.4). They used poly(3,4-ethylenedioxythiophene)-poly(styrenesulfonate) (PEDOT:PSS) as the source/drain/gate electrodes and interconnects, semiconducting single-walled carbon nanotubes (SC-SWCNTs) as the semiconductive channel, and poly(vinylidene fluoride-co-hexafluoropropylene) (PVDF-HFP) as the gate dielectric. They demonstrated that their printed FETs were able to operate at sub-volt conditions with the capability of maintaining electrical performance up to 20% applied strains.

Figure 2.4 Photo of a printed flexible transistor array bent over a hand.⁸⁷

The examples presented above clearly demonstrate the potential of inkjet printing as enabling technology for the mass production of electronic devices, but like mentioned before, its success is highly dependent on the development of the required inks. The influence of physical parameters like ink viscosity, density, and surface tension on the droplet formation and ink-substrate interactions, are well reported in the open literature.⁹² An additional parameter that requires attention is the long-term stability of the electronic inks. This is considered a pivotal property to utilize inkjet printing as a tool in the industrial manufacturing of electronic devices/components. Therefore, the remainder of this section will provide a comprehensive discussion of factors related to long-term Si-containing ink stability, such as the aging behavior and the colloidal stability of SiNPs, as one of the first steps towards formulating SiNP-based inks for inkjet printing of functional electronic devices.

2.3.2 Surface Oxidation of Silicon Nanoparticles

Most studies reporting on inducing long-term stability to NP suspensions can be categorized as using either steric stabilization or electrostatic stabilization approaches.^{93,94} For the steric stabilization approach, polymeric molecules are adsorbed onto or bonded to a NP's surface to create steric repulsion (see Figure 2.5a). When the distance between two particles is less than twice the polymer layer thickness, the adsorbed/grafted polymers will generate a repulsive entropic force against each other and suppress van der Waals force-induced particle agglomeration.⁹⁴ Electrostatic stabilization is another effective method to overcome van der Waals attraction between particles.⁹⁴ It is based on the principle that the same sign electrically charged particles experience a mutual repulsive force. For the electrostatic stabilization approach, ionic groups are

adsorbed on the particle surface. Counter ions, introduced to the system to maintain electroneutrality, surround the NPs and form electrical double layers. When the electric potential of the double layer is sufficiently high, the van der Waals attraction between particles is suppressed by Coulombic repulsion (see Figure 2.5b).

Figure 2.5 Schematic of a) steric stabilization and b) electrostatic stabilization. The image was adapted from reference ⁹⁵.

To successfully exploit the stabilization mechanisms on SiNP dispersions, we must first understand the surface chemistry of these particles in their initial and aged states. Upon formation, the surface of SiNPs mainly consists of Si-H and Si-Si bonds.⁹⁶ Both these bonds are strong reducing agents that are able to reduce water to hydrogen while forming a surface exposed SiO₂ layer at ambient conditions (see eq. 1-4).

In addition to SiO₂ formation, oxidation of Si-Si bonds at ambient conditions can lead to the generation of new Si-H species exposed at the SiNPs surface (see Figure 2.6).¹¹ First, a surface Si atom is attacked by a nucleophile (OH⁻) to produce a 5-coordinate Si intermediate, followed by Si-Si bond cleavage and Si-O bond formation. The Si-O surface-exposed layer prevents further oxidation of the Si-Si species beneath the surface. However, at higher pH values (i.e. >7), the exposed Si-O bonds disassociate in the aqueous solution, resulting in further, or even complete, oxidation/dissolution of the SiNPs.⁹⁷ For instance, at elevated temperature Si wafers are readily etched in e.g. 10 wt% KOH solutions within tens of seconds to few minutes, depending on the crystallinity of the Si wafer.^{98,99} We note that based upon our experimental observations, SiNPs with a

diameter around 50 nm were dissolved entirely in less than 10 minutes when exposed to similar conditions (i.e. 5 wt% KOH), resulting in the formation of silicic acid species.¹⁰⁰

Figure 2.6 Schematic of the oxidation process for Si-Si/Si-O bonds in an aqueous environment.⁹⁶

Furthermore, Si-H and Si-Si species are also sensitive to oxygen. The oxidation products of these species depend on the oxidation temperature.⁵ Since the Si-Si bond (bond energy 255 kJ mol⁻¹) is weaker than the Si-H bond (bond energy 395 kJ mol⁻¹), the oxidation of SiNPs at room temperature tends to form an overlayer of SiO₂ with the presence of surface-exposed Si-H bonds (Figure 2.7a).⁹⁶ These Si-H species can exist for months or even longer when stored in air at ambient conditions. The long lifetime of Si-H species in air opens the possibility of modifying SiNPs with hydrosilylation, which is one of the most commonly used techniques to attach unsaturated bonds to a Si surface. We will discuss hydrosilylation later in more detail (see Section 2.3.3).

When raising the temperature to 60–100 °C, the oxidation process will break the Si-H and the Si-Si bonds located at the SiNP surface, resulting in a surface with exposed Si-O and Si-OH bonds (Figure 2.7b).¹⁰¹ At temperatures above 200 °C and in the presence of oxygen, the whole skeleton of the SiNPs is converted to silicon dioxide (Figure 2.7c). The time scale of this transformation depends on the type of SiNPs and the oxidation temperature. Microporous and macroporous SiNPs need approximately one hour and three hours, respectively, to achieve complete oxidation.⁹⁶

Figure 2.7 Schematic of the oxidation process for Si-Si/Si-O bond in the oxygen-containing atmosphere for various temperatures.⁹⁶

We note that SiNPs can also undergo chemical and electrochemical oxidation that is considered unlikely to occur during the storage of aqueous SiNP dispersions. As such, it is not expected to influence the long-term stability of Si NP-based inks. Therefore, we will not discuss the chemical and electrochemical oxidation of SiNPs in this Chapter. Instead, the interested reader is directed to references^{96,102,103}. Having established a comprehensive understanding of the surface chemistry of SiNPs, the following section introduces strategies to stabilize SiNP suspensions in more detail.

2.3.3 Surface Modification of Silicon Nanoparticles to Fabricate Stable Colloidal Inks

The complexity of the SiNPs' surface chemistry (see section 3.2) makes it hard to estimate their colloidal stability when solvents are changed during ink formulation. Also, highly active surface moieties like Si-H and Si-O can cause unpredicted complications upon interacting with solvents (see Chapter 3), especially when considering long-term colloidal stability. Therefore, it is common practice to use surface modification strategies to protect the SiNPs, alter their dispersion stability, and even introduce new properties. Numerous efforts have been made to obtain long-term stability of SiNP inks.^{104–108}

As mentioned before, hydrosilylation is widely accepted as an efficient approach to modify surface-exposed Si-H groups. By reacting Si-H with double or triple C-C bonds

in the presence of heat,¹⁰⁹ light,¹¹⁰ or Lewis acid catalyst,¹¹¹ Si-C bonds can be formed on the surface of SiNPs. These surface-exposed Si-CH₂-X moieties have demonstrated excellent stability in aqueous environments compared to Si-OC(O)CH₂- bonds.¹¹² This is ascribed to the low electronegativity of the carbon atom compared to the oxygen atom. Thus, the Si-C is less susceptible to associative attacks by nucleophiles. Hydrosilylation allows one to introduce various organic functional groups to the SiNP surface, for example, carboxylic acid, ester, and ether, which opens up possibilities for further reactions. However, the high sensitivity of hydrosilylation reactions to oxygen and water, and the commonly obtained relatively low surface coverage of functional groups, especially for alkyne-driven hydrosilylation, limit their use for the large-scale surface modification of SiNPs.^{113–115}

Figure 2.8 Schematic of the hypervalent surface interaction of silicon nanocrystals. The Cl terminated Si NCs have a lower LUMO energy compared to H terminated Si NCs. Molecule A represents a molecule with favorable energetic alignment for hypervalent interactions. B molecules are strong Lewis base donors, such as dimethylformamide and pyridine. C molecules are chemically inert molecules, such as hydrocarbon and chlorinated hydrocarbon solvents. D molecules represent protic solvents, such as alcohols containing acidic hydrogens, which hydrolyze the Si-Cl group. HOMO, highest occupied molecular orbital; LUMO, lowest unoccupied molecular orbital.¹⁰⁴

Another approach to enhance the colloidal stability of SiNPs without binding carbon atoms/molecules to the NPs includes careful tuning of their surface composition. Holman

et al.¹¹⁶ reported the successful preparation of stable colloidal suspensions of H- and Cl-terminated germanium (Ge) nanocrystals (NCs) in benzonitrile. Erogbogbo et al.¹¹⁷ prepared stable colloidal suspensions of Ge, Si, and Ge/Si alloy (Si_{1-x}Ge_x) NCs in various solvents. They first prepared pure Si, Ge NPs, and alloyed NPs, subsequently, the NPs were dispersed in both benzonitrile and acetonitrile using extensive sonication without the need for any subsequent surface modification or ion addition. These organic surfactant-free NP inks possess the potential for the low-cost fabrication of functional optoelectronic, thermoelectric and photovoltaic devices. Another successful example of the preparation of stable free-standing colloidal Si nanocrystals (Si NCs) was presented by Kůsová et al.¹⁰⁶ They used extended stirring of oxygen passivated PL Si NCs in xylene and showed that passivation of the particle surface resulted in long-term stability while maintaining the PL property. These PL colloidal Si NCs could be a valuable candidate in biological labeling and colloidal LED. Wheeler et al.¹⁰⁴ reported the formation of free-standing Si NCs and successfully exploited the Cl-termination of Si NCs surfaces to readily engage in hypervalent interactions with hard donor molecules to form a stable colloidal suspension (see Figure 2.8). By terminating the Si NCs' surface with Cl, the acidic Si NCs' surface favorably interacts with donor solvent molecules to create a layer of hard donor molecules immobilized around the particle surface. These thin layers of donor molecules around the Si NCs help to avoid direct contact between particles, therefore preventing agglomeration. By exploiting the hypervalent interaction between the Si NCs and solvent molecules, they successfully produced stable Si NC suspension without using ionic ligands or large organic molecules that could potentially hinder charge transport in the fabricated silicon devices. However, the preparation of free-standing SiNP suspensions by these methods typically requires large amounts of volatile solvents, low reactant concentrations (ppm level), employing (unstable) surface functional groups and typically yield small particle sizes (typically below 10 nm).^{105,107,119} These requirements and small Si-containing particle size limit the widespread application of SiNP dispersions in large-scale industrial applications, such as printing conductive patterns to fabricate functional electrical devices.⁶⁸

Grafting of polymers to the particle surface represents another efficient way to enhance the colloidal stability of NP dispersions.^{119,120} Depending on the type of polymer, grafting can either increase electrostatic repulsion, decrease van der Waals forces, or result in severe steric hindrance to avoid undesirable particle aggregation.¹²¹ In general, there are three methods to anchor polymer chains onto a (particle) surface, i.e. "grafting to", "grafting through", and "grafting from" (see Figure 2.9).¹²² The "grafting to" method is a classical approach to fabricate polymer-particle hybrids.¹²² A standard "grafting to" procedure involves the synthesis of polymers and NPs separately, followed by the

attachment of the polymer chains onto the surface of the particles. For the “grafting to” method, both the polymer molecular weight (M_n) and the polydispersity index (PDI) can be characterized before polymer attachment, which is not possible for the grafting through and grafting from methods (see below). The disadvantage of the “grafting to” method is that typically, low grafting densities are obtained, caused by the steric hindrance of the already attached polymer chains acting on the chains approaching the partly covered substrates.¹²³

“Grafting through” and “grafting from” have in common that polymers are attached to the particle surface during their polymerization.^{124,125} For the grafting through approach, also known as the “macromonomer” method, polymerizable units such as vinyl units are first immobilized at the particle surface (i.e. the macromonomer). Then, depending on the employed polymerization method, monomers, initiators, catalysts, complexing agents are added to the particle suspension to start the polymerization process. During chain propagation, polymerizable units on the particle surface get incorporated in the backbone of the propagating chains, leading to propagating chains anchored onto the particle surface. In this manner, a polymer overlayer on the particle is formed. To date, the mechanism of the “grafting through” method is still not fully understood, even though it has been widely used in scientific research and industrial applications.¹²⁶ In the “grafting from” method, also known as surface-initiated polymerization, functional initiators are covalently attached to the particle surface. In the subsequent step, these initiators are used to initiate polymerization. Due to the nature of this process, “grafting from” tends to give the lowest steric hindrance during polymerization, which results in relatively high grafting densities.

Among the polymerization techniques used for the “grafting from” method, surface-initiated controlled radical polymerization (SI-CRP) is considered one of the most effective approaches to synthesizing polymer-particle hybrids.¹²⁷⁻¹²⁹ In general, there are three controlled radical polymerization (CRP) methods that have been extensively studied: atom transfer radical polymerization (ATRP)^{130,131}, reversible addition-fragmentation chain transfer (RAFT) polymerization^{132,133}, and nitroxide-mediated polymerization (NMP)¹³⁴⁻¹³⁶. The ATRP, RAFT, and NMP methods each have their specific requirements regarding available monomers, functional initiators, and polymer architectures. Compared to RAFT and NMP, ATRP has much more tolerance to functional groups and reaction conditions.¹³⁰ Most importantly, the initiators, transition metal catalysts, and ligands used for ATRP are commercially available. Due to these advantages, surface-initiated ATRP has been extensively investigated for NP surface modification. Therefore in this Chapter, we will briefly introduce surface-initiated ATRP

and present some highlights for Si-containing NP modification via SI-ATRP. Readers interested in RAFT and NMP are directed to ^{132,133} (RAFT) and ^{134–136} (NMP) for more detailed information.

Figure 2.9 Schematic of the “grafting to”, “grafting through”, and “grafting from” approaches used for modification of particle surfaces. Circles: reactive groups to anchor on the surface or used as a chain-growth point (for the “grafting through” approach); lines: polymer chains; rectangles: monomer units (Image was adapted from reference ¹³⁷).

In a classical surface-initiated ATRP reaction, alkyl halide initiators are anchored onto the NPs’ surfaces first, followed by activation by the catalyst system (e.g., Cu^I/ligand complex) to form living radicals and a corresponding metal complex in a higher oxidation state (e.g., Cu^{II}/ligand complex).¹²⁸ During the chain propagation reaction, the radicals are deactivated reversibly by reacting with the Cu^{II}/ligand complex. This reversible activation/deactivation process establishes an equilibrium with most of the growing chains in the dormant state during the polymerization. Thus, growing chains have an equal chance to add one or more monomer units during a short period of active growth time (at the rate of k_p), after which they return to the dormant state (see Figure 2.10). Compared to conventional radical polymerization, in which chains are grown for a very short time (typically 10^{-2} s to a few seconds), polymer chains from ATRP grow slowly

and continuously throughout the polymerization period. Because the living radicals grow with equal probability throughout the entire polymerization process and termination is essentially suppressed, ATRP tends to have relatively low PDI values (1.05-1.2) compared to conventional free-radical polymerizations.

Figure 2.10 Schematic drawing of the ATRP equilibrium.¹³⁸ $\text{P}_n\text{-X}$, P_n^* , Mt^m/L , and $\text{X-Mt}^{m+1}/\text{L}$ represent alkyl halides/macromolecular species, growing radicals, transition metal complexes in their lower oxidation state, and halide ligands coordinated transition metal complexes in their higher oxidation state, respectively. k_{act} , k_{deact} , and k_t refer to the activation, deactivation, and termination rate constants, respectively.

One of the first systematic studies utilizing surface-initiated ATRP with SiO_2 NPs was reported by Patten and von Werner.^{138,139} They demonstrated the fabrication of core-shell structured polymer- SiO_2 NP hybrids with polystyrene and poly(methyl methacrylate) (PMMA). They also showed that the addition of sacrificial free initiators and deactivators (Cu^{II}) provided a sufficient deactivator concentration which avoided uncontrolled polymer chain growth and particle aggregation. Nowadays, various polymers have been grafted from SiO_2 via surface-initiated ATRP, including PS^{139,141}, PMMA^{139,140}, poly(*tert*-butyl acrylate) (PtButA)^{140,141}, and poly(oligo(ethylene glycol)methacrylate) (POEGMA)¹⁴². SiNPs typically form a surface-exposed oxide layer, when stored at ambient conditions,¹⁴³ that can be readily modified with ATRP functional initiators by exploiting well-established silica-based chemical approaches. Thus, surface-initiated ATRP seems promising to fabricate stable dispersions of polymer-SiNP hybrids as electroconductive inks suitable for printing functional devices.

2.3.4 Inkjet Printing of Silicon Nanoparticle Inks

Unlike its bulk form, not much work has been done to utilize SiNPs in electronic devices, including their deposition by inkjet printing. To the best of our knowledge, most of the reports about inkjet printing of SiNP-based inks were published in the last decade.¹⁴⁴⁻¹⁴⁷ Gupta and coworkers are among the pioneers in utilizing inkjet printing for SiNP-based inks.¹⁴⁷ In their work, gas-phase synthesized SiNPs were functionalized with ethyl undecylenate to form stable colloidal suspensions in various organic solvents.

Moreover, they demonstrated using inkjet printing as a processing technique to print SiNP-based inks on glass substrates.¹⁴⁷ Drahi et al. reported on the influence of SiNP surface chemistry and annealing procedure on the microstructure and thermal conductivity of inkjet-printed SiNP thin films.¹⁴⁵ Furthermore, they demonstrated the successful utilization of photonic annealing for the sintering of inkjet-printed SiNP thin films. Compared to traditional thermal annealing, photonic annealing is faster and readily compatible with flexible and low-cost substrates.¹⁴⁵ In a more recent paper, Lawes et al. present the fabrication of a lithium-ion battery anode via the inkjet printing of commercially available SiNPs.¹⁴⁴ The SiNPs-based ink used in their study was formulated by mixing commercially available SiNPs, carbon black and polymer binders (poly(3,4-ethylenedioxythiophene)-poly(styrene sulfonate) (PEDOT:PSS), polyvinylpyrrolidone (PVP), carboxymethyl cellulose (CMC), and Na-alginate) in water with extensive sonication. The lithium-ion battery prepared with an anode printed from the as-prepared SiNP-based inks showed a capacity of over 1700 mA h g⁻¹ for 100 charge-discharge cycles. When the depth-of-discharge was limited to 1000 mA h g⁻¹, the prepared lithium-ion battery has a stable performance over 1000 cycles. The presented and discussed examples clearly demonstrate that the inkjet printing of SiNPs has a bright full future as key enabling technology in printable electronics.

2.4 Silicon Nanoparticles as the Next Generation “Magic Bullets” in Biomedical Applications

More than 100 years ago, Ehrlich postulated the concept of targeting drugs to an intended pathogen and treat it without affecting the surrounding healthy tissue.¹⁴⁶ In popular terms, this is referred to as a magic bullet.¹⁴⁹ It took until the early nineties to develop targeted drug delivery as a popular and well-established research field. Since then, the number of scientific reports has continued to increase. The targeting of a drug to specific sites in the body is of interest since it potentially allows for the administration of effective drugs to diseased cells or tissue without affecting the adjacent healthy cells and tissue and allows to reach hard-to-reach tissue/diseases.¹⁵⁰ Eventually, this contributes to higher drug efficiency at potentially a less drug dose, with lower adverse side effects for the patient, lower costs, and a lower acquired immunity. As we will present and discuss in this section, SiNPs have an established track record in drug delivery applications. However, when looking beyond the field of solely targeted delivery of drugs, it is worth noted that due to the intrinsic properties of Si-containing NPs, they offer a promising platform as theranostic agents. In theranostics, a therapeutic component

(e.g. a drug) is combined with (real-time) diagnostic functionalities.^{151–153} In the remainder of this section, we will present and discuss why SiNPs receive considerable attention as platform material in drug delivery and particularly in the emerging field of theranostics.

2.4.1 Silicon Nanoparticles as Drug Delivery Carriers

Since Si is known for its biocompatibility^{154–156} and is a naturally occurring element in various tissues in the human body (primarily present as orthosilicate (SiO₄⁴⁻)¹⁶⁰), it is considered as a promising building unit for functional particles in biomedical applications. In addition, the degradation products of Si-containing NPs (mainly silicic acid) are non-toxic and readily renal clearable.^{155,157,158} These properties render Si-containing NPs an interesting alternative to compete with NP-based systems for which toxicological and biodegradability concerns exist, like gold NPs, carbon NPs, and various quantum dots.¹⁵⁹

Besides being biocompatible and biodegradable, a targeted drug carrier must meet the following additional criteria to be effective for: i) high drug loading, ii) preservation of drug functionality, and iii) effective targeting. Among the various NP-based platforms, porous SiNPs have attracted considerable attention since they meet these criteria.^{160–163} Therefore, in biomedical nanotechnology, SiNPs are abundantly reported as drug carriers. Since it is not the scope of this work to review the use of SiNPs as drug carriers in-depth, the reader is directed to some selected review papers that cover this in-depth and are considered to be of interest.^{164–168}

Porous SiNPs are produced mainly by the electrochemical anodization of monocrystalline Si wafers.^{5,13,164,169,170} This method uses hydrofluoric acid as the electrolyte in various organic solvents, such as ethanol or acetonitrile. The produced porous Si film is lifted from the Si wafer, and following sonication or milling treatments, micro and NPs are formed. This results in the formation of quasi-spherical porous SiNPs with a relatively broad particle size distribution.

Figure 2.11 Scheme for the preparation of SiNPs by electrochemical etching and TEM image of as-prepared SiNPs. (Picture was modified.)¹⁷⁰

The high porosity (up to 80%) of SiNPs then allows one to obtain high drug loadings.¹⁷¹ It is of pivotal importance to tailor the physicochemical properties of SiNPs to control their degradation time in the bloodstream/targeted tissues.^{162,175–177} It is well-known that the pore size and porosity significantly affect the degradation rate of SiNPs under physiological conditions.¹⁵⁹ In addition, without altering the surface chemical composition, SiNPs tend to degrade relatively quickly. The surface of porous SiNPs mainly consists of silanols, siloxanes, and silicon hydrides. These surface-exposed moieties are readily used in well-known surface chemical engineering processes¹⁶⁰ to tailor surface chemistry and enhance affinity towards specific drugs (hydrophobic or hydrophilic) allowing controlled incorporation and release. In fact, carefully selecting the chemical composition allows one to prolong the SiNPs' lifetime and incorporate a gating function that can control the release of the intended drugs.¹⁶⁰ In addition, tuning the SiNPs surface chemistry facilitates a better dispersion in aqueous media as well as that targeting often required in vivo stealth functionalization.^{161,164,172–174}

For instance, to enhance the blood circulation time of SiNPs, Santos and coworkers¹⁷⁵ reported red blood cell membrane coated porous SiNPs that were loaded with radioactive ¹⁵⁵Tb atoms. The red blood cell membrane coating significantly enhanced the blood half-life compared to bare Si NPs. The authors concluded that the prepared ¹⁵⁵Tb loaded SiNPs could be used in targeted radionuclide therapy combined with a chemotherapeutic payload within the porous SiNPs. In another report, Santos and coworkers¹⁷⁶ showed that

the covalent attachment of a model cancer antigen TRP2, either expressed at the membrane surface or covered by membrane encapsulation, is promising for treating autoimmune diseases by inducing an autoantigen specific immune tolerance. Weitz and coworkers¹⁷⁷ designed and prepared hybrid polymersomes as a versatile drug delivery system. Their design was based on utilizing porous SiNPs conjugated with gold nanorods encapsulated within a hybrid polymersome by using double emulsion templates on a microfluidic chip. This particle design allowed the incorporation of hydrophilic and hydrophobic drugs, and it was demonstrated that the *in vivo* drug delivery efficiency to tumors in mice improved. An exciting feature of this hybrid system is that the conjugated gold nanorods absorb near-infrared laser radiation, which triggered the increased release of doxorubicin hydrochloride and rapamycin under near-infrared laser irradiation during *in vitro* tests. This feature suggests that this hybrid polymer-based drug delivery system has the potential to be applied in photothermal therapy.

Besides the relatively easy tunability of particle geometry and surface chemistry of Si-containing NPs to control the SiNPs drug release rate and biodegradability, they have interesting optoelectronic properties that allow the incorporation of multiple functionalities in one particle.^{177–180} This makes that SiNPs receive considerable attention during the last decade as a multimodal platform for theranostic applications.¹⁸⁰ The following sections (2.4.2 and 2.4.3) will introduce the main concepts of SiNP based (enhanced) imaging in combination with local disease treatment.

2.4.2 Photoluminescent Silicon Nanoclusters and Bioimaging

The earlier discussed biocompatibility and unique optical properties make PL SiNPs a novel, high-quality, and biocompatible fluorescent probe for *in-vivo* imaging. Of particular interest is that SiNPs can be used in near-infrared laser two-photon-excited fluorescence imaging.^{181–184} This allows deeper tissue penetration, and it provides a better spatial selectivity with a reduced autofluorescence of the surrounding biological tissues.^{185,186}

Numerous synthetic strategies – physical, physiochemical, chemical, and electrochemical – have been proposed and developed to fabricate PL SiNPs with a high quantum yield and long-term photostability.^{6,187–190} For example, Zhong et al.¹⁹¹ reported a method to synthesize PL SiNPs with microwave irradiation. Using organosilicon molecules as precursors, they produced 0.1 g PL SiNPs with a quantum yield of 20-25% in less than 10 minutes. In addition, Zhong et al.¹⁹² later reported the fabrication of PL SiNPs by UV radiation of (3-aminopropyl)trimethoxysilane and 1,8-naphthalimide under ambient conditions with a high production rate (i.e. 10 g of PL SiNPs in 40 mins).^{191,192}

Figure 2.12 Photographs of deep red (740 nm), red (675 nm), yellow (592 nm), green (572 nm), and blue (441 nm) light emission from Si NCs when excited at 365 nm.¹⁹³

Besides being able to tune the (optical) properties of SiNPs towards specific *in vivo* applications, their interactions with living cells must be thoroughly understood as well. Of particular importance is that the foreign SiNPs do not induce any toxic effects on the surrounding tissue. Therefore, the cellular behavior of PL SiNPs has been investigated and monitored in living cells by various researchers.^{194–197} For instance, Cao et al.¹⁹⁴ described the detailed mechanism of SiNPs entering living cells. SiNPs were shown to be internalized into cells via clathrin-mediated and caveolae-dependent endocytosis. These authors also demonstrated that SiNPs showed no apparent toxic effects on cell metabolic activity. Recently, Zhou et al.¹⁹⁷ studied the *in-vivo* behavior and molecular imaging of PL SiNPs inside *Caenorhabditis elegans*. They demonstrated that PL SiNPs could be used as nanoprobe for bioimaging inside living organisms.

Various biocompatible molecules like sugar, transferrin, targeting peptides, and polyethyleneimine (PEI), have been used to decorate PL SiNP surfaces for cancer targeting,^{195,196} molecular trackings,¹⁹⁷ and monitoring carbohydrate-carbohydrate interaction dynamics¹⁹⁸. Pang et al.¹⁹⁹ developed PEI-encapsulated SiNPs (PEI-SiNPs) to observe the behavior of gene carriers in living cells in real-time. Their long-term stable PEI-SiNPs showed a DNA-loading capacity of 97% and an adaptable efficiency of 35% for human cervical carcinoma cells, with the capability to maintain 90% of cell viability for 24 and 48 hours after treatment. By attaching peptides (cyclic arginine-glycine-aspartic acid (RGD)) on the PL SiNPs surface, they demonstrated the use of SiNP-RGD as a suitable bio-probe to image cancer cells in real-time. These SiNP-RGDs also showed highly efficient anticancer properties.

Recently, He and coworkers²⁰⁰ studied the use of vancomycin (i.e. a glycopeptide antibiotic) modified SiNPs as a theranostic component in eye drops to diagnose and treat Gram-positive bacteria-induced keratitis (an eye infection). They successfully exploited the high binding affinity of vancomycin to dipeptides on the cell wall of Gram-positive

bacteria to target the incorporated fluorescent SiNPs and by optically monitoring the fluorescence to diagnose keratitis within 10 minutes. In addition, the antimicrobial rate for vancomycin immobilized on SiNPs is 92.5%, which is nearly four times higher than free vancomycin at the same concentration. Therefore, the vancomycin-modified SiNPs are considered an excellent nano theranostics agent capable of simultaneously diagnosing and treating bacteria keratitis.

Interestingly, SiNPs can act as photosensitizers in photodynamic therapy as well.^{201–204} For instance, the *in vitro* PL visualization of SiNPs in living cells and the production of singlet oxygen in these cells was successfully demonstrated by Timoshenko and coworkers.²⁰³ Singlet oxygen is proven to be effective in the treatment of cancer.²⁰⁵ Furthermore, SiNPs are exploited in photothermal therapy in which near-infrared irradiation is used to generate heat locally, resulting in targeted cell death without harming the surrounding tissue.^{206,207} Besides using near-infrared in photodynamic therapy, thermotherapy with SiNPs is possible with ultrasound¹⁶⁹ and radiofrequency^{208,209} radiation.

2.4.3 Silicon Nanoparticle and Magnetic Resonance Imaging

Magnetic resonance imaging (MRI) is a non-invasive technique that is used, among others, for *in-vivo* studies and clinical diagnostics. However, the main challenge of MRI in molecular imaging is the inherently low sensitivity, especially when detecting nuclei with low gyromagnetic ratios and low natural abundances like ^{13}C , ^{29}Si , and ^{15}N . Hyperpolarization is a technique that temporarily increases the nuclear spin polarization of a material far beyond its thermal equilibrium, which enhances the detectability and shortens the MRI acquisition time for nuclei with low gyromagnetic ratios (see Figure 2.13).^{210,211} However, small hyperpolarized ^{13}C -labeled substrates like $[1-^{13}\text{C}]\text{pyruvic}$ often rapidly relax to their equilibrium states (i.e. within 120 s), making it hard to monitor slow biological processes like protein-cell binding and tissue perfusion.^{212,213} Si in the form of particles has a nuclear spin relaxation (T_1) time up to several hours and coherence (T_2) times up to several seconds at room temperature.^{214,215} The long T_1 for Si is due to the existence of a small amount of spin -1/2 ^{29}Si nuclei in a nuclei-spin-free lattice. The extraordinary long T_1 and the already mentioned outstanding biocompatibility make SiNPs a promising imaging agent for *in-vivo* hyperpolarized ^{29}Si MRI.

Figure 2.13 Increase of MRI signal intensity of ^{13}C nuclei via hyperpolarization. DNP = dynamic nuclear polarization, NMR = nuclear magnetic resonance.²¹⁶

The first demonstration of using hyperpolarized Si particles with diameters from 100 nm to 1 μm as MRI agents was reported by Aptekar et al.²¹⁷ The room temperature T_1 for these particles ranged from tens of minutes up to hours depending on the particle size and doping. Inspired by their results, chemists and material scientists developed various synthetic procedures to fabricate Si particles with enhanced T_1 values that could potentially monitor the biochemical reaction *in-vivo*. For example, Tonya et al.²¹⁸ used a metathesis reaction of sodium silicide with silicon tetrachloride to fabricate 10 nm SiNPs, followed by surface modification with alkyl and aromatic ligands. The resulting particles showed T_1 times greater than 600 s, which is five times longer than conventional ball-milled (and larger) SiNPs. Their small particle size allows them to cross the blood-brain barrier and enables their utilization in intracellular studies with MRI.

Whiting et al.²¹⁹ exploited relatively low-cost commercial Si particles with a diameter of 2 μm to demonstrate the use of hyperpolarized ^{29}Si MRI for *in-vivo*, real-time passive angiocatheter tracking in two and three dimensions for over 40 minutes. Advantages of using MRI guidance compared to currently used X-ray fluoroscopy are that MRI allows three-dimensional imaging, other physiologically relevant criteria can be monitored, and the clinical team is not exposed to ionizing radiation. Though promising to replace X-ray fluoroscopy guidance, the proof of concept MRI-based guidance suffered from a lack of spatial resolution (~ 1 mm for MRI guidance versus ~ 0.1 mm for X-ray fluoroscopy). According to the research team, moderate improvements to the ^{29}Si hyperpolarization level, MR hardware, and pulse sequences are required to overcome this limitation. Interestingly, in a follow-up study Whiting and coworkers²²⁰ demonstrated that the

functionalization of commercial SiNPs with APTES, PEG, and oligonucleotide aptamer had little effect on the hyperpolarization buildup, or decay rates, for these particles.

Overall, we can conclude that SiNPs are an exciting platform for multimodal imaging and/or therapeutic applications. Although the research field of theranostic is relatively young, it receives considerable attention, and it is believed that due to their unique properties in combination with good biocompatibility, SiNPs will play an essential role in this regard. Future directions to consider are the development of scalable and reproducible production methods of SiNPs at acceptable costs and to get regulatory clearance for these functional particles.²²¹

2.5 Surface-Engineered Silica Nanoparticles

SiO₂ NPs are another class of NPs that cannot be neglected when considering Si-containing NPs. Unlike SiNPs, SiO₂ NPs typically do not possess new properties compared to their bulk form. However, SiO₂ NPs have the advantage of being cheap and available with a controlled and narrow size distribution. Furthermore, SiO₂ NPs provide ample opportunities to adapt their morphology and are readily derivated by widely accessible surface functionalization strategies.²²² Like other NPs, SiO₂ NPs also have a large surface-to-volume ratio, which provides extremely large interface areas upon adding only a few wt% of particles to polymer composites.^{223–225} While most of the SiO₂ NP-based thermoplastic composites rely on the use of rather smooth particles, the introduction of particle surface roughness allows one to tailor and eventually enhance the surface/interface properties of the resulting composites. This section introduces common strategies to improve SiO₂ NP surface roughness and subsequently we present and discuss how this can significantly enhance polymer foam cell nucleation. We recently introduced the latter as an emerging application area of surface engineered silica NPs.²²⁵

2.5.1 Surface Roughness Engineering of Silica Nanoparticles

Surface roughened SiO₂ NP (SiO₂-R NP) based layers are considered an effective coating material to mimic the structure of lotus leaves.^{226–228} The nanocavities that reside on the surface of the assembled NPs reduce the contact area between a droplet and the surface to minimize the adhesion, resulting in superhydrophobic surface behaviour.^{229,230}

Figure 2.14 Schematic of a) the attachment approach²²⁷ and b) the etching approach⁹⁷ for the fabricating of SiO₂-R NPs.

Chemists and materials scientists have developed different synthetic strategies to prepare SiO₂-R NP. The most common approaches to synthesizing SiO₂-R NP are the attachment and etching methods (see Figure 2.14).^{226,227,231–234} The attachment method is usually a two-step reaction to attach smaller NPs to larger core particles, governed by various interactions, such as complexation, covalent bonding, and hydrogen bonding. For instance, Hu et al.²³¹ reported the fabrication of stimuli-responsive raspberry-like hollow mesoporous colloids by utilizing host-guest complexation. The separately prepared viologen functionalized Fe₃O₄ NPs that were subsequently attached to azobenzene functionalized SiO₂ core particles via the host-guest complexation of cucurbituril molecules. Upon UV-irradiation, the SiO₂ core particles can grab or release the Fe₃O₄ NPs. Alternatively, Blanckenberg et al.²³⁴ synthesized raspberry-like gold-decorated SiO₂ NPs (SS_x-AMPS-Au_n) by growing the secondary particles from the primary particle surface. A gold(III) chloride trihydrate (HAuCl₄) solution was added to an amino-functionalized SiO₂ NP suspension to grow gold NPs on the silica surface. The particles were then used to catalyze the sodium borohydride reductive discoloration of methylene blue in the water. Ming et al.²²⁷ introduced the covalent bonding between two different sizes of SiO₂ using either amino-functionalization or epoxy-functionalization to yield SiO₂-R NPs. Subsequently, the SiO₂-R NPs were deposited on an epoxy film, followed by coating the deposited particles with a PDMS layer to form a dual-sized structured superhydrophobic surface. Instead of coupling amino and epoxy groups to fabricate SiO₂-R NPs, Puretskiy et al.²²⁶ exploited poly(glycidyl methacrylate) polymer brushes as the coupling agent to achieve better mechanical stability and chemical resistance of SiO₂-R NP (see Figure 2.15). They also reported poly(pentafluorostyrene) immobilization on the as-prepared SiO₂-R NPs to obtain a superhydrophobic surface. The major advantage of the attachment approach is that SiO₂-R NPs with a controlled surface roughness can be fabricated by simply adjusting the diameter and concentration ratio of large and small particles. However, the attaching approach typically requires multiple reaction steps. In addition, because the large and small particles are connected by large molecules or

polymer chains, small particles can be detached from the large particle under extreme conditions, like long-term sonication or extrusion.

Another approach encompasses the etching method, which uses the dissolution and re-deposition (growth) of SiO_2 to fabricate SiO_2 -R NP surfaces. For example, Du et al.⁹⁷ synthesized SiO_2 -R particles by etching nearly spherical SiO_2 NPs with NaBH_4 . The dissociation and re-deposition of Si-O bonds on the surface of SiO_2 NPs at high pH results in the formation of SiO_2 -R. Those particles were deposited on polycation and polyanion-coated glass substrates. The particle deposition step was followed by calcination to remove the hydrophilic -OH group from the particle surface. Finally, the as-prepared glass substrates were coated with 1H,1H,2H-, and 2H-perfluorooctyltriethoxysilane to form superhydrophobic surfaces. Due to the nature of the etching process, the surface roughness of the SiO_2 -R is somewhat unpredictable, and according to our experience, it may vary from batch to batch, hampering its wide spread applicability.

Figure 2.15 Schematic of SiO_2 -R NP synthesis. a-c) large particles were grafted with poly(glycidyl methacrylate); d) Small particles are modified with APTES; e) Coupling of large and small particles; f) Immobilizing polymer onto the SiO_2 -R surface.²²⁶

Alternatively to the etching and attaching method, Chen et al.²³⁵ recently reported a one-step dialysis strategy to fabricate SiO_2 -R NPs at mild processing conditions. First, a homogeneous mixture of TEOS, H_2O , and ethanol was added to a dialysis bag. This step

is followed by immersing the dialysis bag into a large reservoir filled with an ammonia/water mixture (10% volume ammonia) to react for four hours. The resulting temporal ammonia concentration gradient results in the formation of porous raspberry-like SiO₂ NP formation. This method is considered to be of particular interest since it does not use any other chemicals than typically used to synthesize SiO₂ NPs.

Most of the literature on surface roughness modified SiO₂ NP is focused on utilizing SiO₂-R NPs to create dual-sized structures to induce superhydrophobicity or using SiO₂ NP as a support for other functional particles. However, by carefully examining the morphology of SiO₂-R NPs and thoroughly investigating the heterogeneous foam cell nucleation theory, we have successfully designed and utilized SiO₂-R as a highly efficient nucleating agent for polymer foam cell nucleation. This is presented and discussed in the following section.

2.5.2 Foam Cell Nucleation by Surface Topology Engineered Silica Nanoparticles

Nucleation is a process of creating a new thermodynamic phase with lower free energy incorporated within a metastable phase with a relatively high free energy. Nucleation can happen in the gas, liquid, and solid phases, *e.g.*, rain, boiling, crystallization. In this part, we focus on gas-liquid nucleation.

Gas-liquid nucleation processes can be either homogeneous or heterogeneous. For homogeneous nucleation, the free energy for critical nucleus formation is²³⁶

$$\Delta G_{crit} = \frac{16\pi\sigma^3}{3\Delta P^2} \quad \text{eq.5}$$

in which ΔP is the pressure difference between two phases if assuming the partial molar volume of gas (*e.g.* CO₂) in the polymer after full saturation is 0. σ is the interfacial tension between the metastable phase and nucleating phase. However, since σ is experimentally inaccessible, it is usually replaced by the surface tension of a flat surface on the macro scale.

Figure 2.16 Schematic illustration of nucleation a) on the spherical particle surface, b) on a flat surface, and c) inside a cavity.

Heterogeneous nucleation is considered thermodynamically more favorable than homogeneous nucleation when the contact angle (θ), as defined in Figure 2.16, is smaller than 180° .²³⁷ A relatively simple heterogeneous nucleation model was deduced and reported by Volmer in 1929.²³⁸ This model assumes that liquid clusters grow on a planar substrate as a spherical cap with a constant wetting angle. Fletcher took this model a step further and extended Volmer's model to gas nucleation on a spherical particle surface.²³⁹ In his work, the particle curvature plays a vital role in the nucleation energy:

$$\Delta G_{crit}^{het} = \frac{16\pi\sigma^3}{3\Delta P^2} * f(m, x) \quad \text{eq.6}$$

where $f(m, x)$ is the energy reduction factor, which depends on the curvature (x) and contact angle (θ). For spherical particles (i.e., a convex substrate, see Figure 2.16a), it is described as

$$f(m, x) = \frac{1}{2} + \frac{1}{2} \left(\frac{1-mx}{g} \right)^3 + \frac{1}{2} x^3 \left[2 - 3 \left(\frac{x-m}{g} \right) + \left(\frac{x-m}{g} \right)^3 \right] + \frac{3}{2} mx^2 \left(\frac{x-m}{g} - 1 \right) \quad \text{eq.7}$$

in which m , w , and g are

$$m = \cos\theta$$

$$x = \frac{R}{r_{crit}}$$

$$g = \sqrt{1 + x^2 - 2mx}$$

$$r = \frac{2\sigma}{P_G - P_L}$$

The extension of Fletcher's work to nanocavities (i.e. a concave surface, see Figure 2.16c) was reported by Liu et al.²⁴⁰ By assuming that the nanocavity is a smooth hollow

sphere, they deduced that the influence factor $f(m,x)$ for a nanocavity is described a

$$f(m,x) = 1 + \left(\frac{1+mx}{g}\right) + x^3 \left[2 - 3 \left(\frac{x+m}{g}\right) + \left(\frac{x+m}{g}\right)^3 \right] + 3mw^2 \left(\frac{x+m}{g} - 1\right) \quad \text{eq.8}$$

in which g is

$$g = \sqrt{1 + x^2 + 2mx}.$$

According to the results reported by Liu et al.,²⁴⁰ nucleation is energetically favorable inside the cavities compared to nucleation by convex and flat surfaces of the same material.²⁴¹ A schematic illustration of a liquid bubble nucleating on the particle surface and inside nanocavity is shown in Figure 2.16. Based on their results for nucleation inside cavities, SiO₂-R was considered a potentially efficient heterogeneous foam cell nucleation agent in nanocellular thermoplastic foaming.

2.5.3 Polymer Nanocomposite Foams

Polymer foaming is a high-profile research area. Low density, nanocellular polymer nanocomposite foams are promising candidates for several applications, especially high-performance thermal insulation.^{241,242} Nowadays, polymer foams can be fabricated either by a continuous process, like extrusion foaming, or a non-continuous process, like batch foaming or injection molding foaming.²⁴³ Continuous foaming typically requires high temperature, high pressure, and high shear rates. Despite this, continuous foaming is widely accepted and applied in the industry since it is a quick, versatile and straightforward process.²⁴⁴ Compared to continuous foaming, non-continuous foaming is a more commonly used approach to prepare nanocellular polymer foams in the lab. In a typical batch foaming process, a polymer sample is saturated with a blowing agent like CO₂ at a specific temperature and pressure. This is followed by releasing the pressure and increasing the temperature to oversaturate the dissolved blowing agent in the polymer matrix, which will induce foam cell nucleation and result in polymer foaming (see Figure 2.17). The major downside of batch foaming is the often required long saturation time (up to weeks), making this method less desirable to be applied at an industrial scale compared to continuous foaming.²⁴⁴ However, due to the easily adjustable and precise process control for each step during batch foaming and the good foam reproducibility, batch foaming is considered a powerful tool to investigate the foaming behavior of polymers.

Figure 2.17 Schematic diagram of batch foaming process.²⁴²

Nanofillers are extensively discussed as heterogeneous nucleation agents for polymer foaming.²⁴⁵ Typically, the addition of nanofillers can dramatically increase the cell density of polymer foams (see Figure 2.18) by rendering heterogeneous nucleation favorable over homogenous nucleation.²⁴⁶ Colton and Suh were the first to demonstrate the use of nanofillers in polymer foaming.^{247–249} They reported that a high cell density was achieved by adding zinc stearate as the heterogeneous nucleation agent in polystyrene (PS) foaming.^{250–252} In addition to increasing cell density, introducing well-dispersed nanofillers to polymers prior to foaming also produces foam cells with narrower size distributions. For example, by adding 9 wt% of nano-silica to PS, the foaming density increased from 10^{11} to 10^{13} cells cm^{-1} , and the cell size was reduced from 0.7–6.0 μm to 0.1–0.8 μm compared to neat PS foams.²⁵³ Various polymer and nanofiller combinations have shown that the addition of nanofillers results in increasing nucleation efficiency as well as in increasing the cell density, e.g., low-density polyethylene (LDPE)-clay²⁵⁴, PS-carbon nanofiber (CNF)²⁵⁵, PS-clay²⁵⁶, PS-SiO₂ NP²⁵⁷, polymethyl methacrylate (PMMA)-clay²⁵⁸, PMMA-multi-walled carbon nanotubes (MWCNTs)²⁵⁸, PMMA-SiO₂ NP²⁵⁹, styrene acrylonitrile resin (SAN)-clay²⁶⁰, and polyurethane (PU)-clay²⁶¹.

Figure 2.18 SEM images of the cross-section of polystyrene foams batch foamed without (A) and with silica-based hybrid NPs as heterogeneous nucleation agents (B). The red arrows in (B) point at some hybrid SiO₂ NPs.²⁶²

In the last decade, Vancso and coworkers^{262–266} reported developing a series of silica core-shell NPs with different polymer shells to enhance the SiO₂ particle dispersion in the polymer matrix and increase the foam cell nucleation efficiency. With PDMS-grafted silica core-shell NPs (SiO₂-PDMS) dispersed in PS film at 4.0 wt%, the cell size and cell density of batched foamed nanocomposites were 600 nm and 4.6×10^{12} cells cm⁻¹, respectively. The nucleation efficiency is approximately 0.33.²⁶⁴ For PMMA SiO₂-PDMS nanocomposites foams, the highest nucleation efficiency achieved is approximately 0.5.²⁶² So far, this is the highest nucleation efficiency reported using smooth SiO₂ NPs. To further increase the nucleation efficiency, it was anticipated that more than a grafted polymer shell on the SiO₂ NPs was required.

Figure 2.19 Schematic representation of the nucleation of multiple cells from a PDMS coated SiO₂-R. The saturation pressure and foaming temperature were 55 bar and 40 °C, respectively. Picture was adapted from reference ²⁶³.

The thermodynamic model reported by Liu et al.,²⁴⁰ directed us towards lowering the critical nucleation energy of nucleating particles by introducing surface-exposed nanocavities. Recently, we successfully exploited SiO₂-R NPs as nano-filler to boost the nucleation efficiency of nanoparticles in polymer foaming.²⁶³ We successfully synthesized PDMS coated SiO₂-R NPs (SiO₂-RP NPs) with a diameter ranging from 80 to 200 nm. For the CO₂-based batch foaming of PMMA, the added SiO₂-RP NPs had a nucleation efficiency of up to 6.2, meaning that each particle was able to nucleate more than one foam cell. The significant increase in nucleation efficiency is ascribed to the capillary condensation of the physical blowing agent (CO₂) inside the nanocavities with the presence of a thin PDMS shell (favorable for nucleation), resulting in locally increased concentrations of CO₂ (see Figure 2.19). The increased blowing agent concentration in the energetically favorable concave nucleation sites is responsible for the significantly enhanced nucleation efficiency of SiO₂-RP NPs. It is believed that further tailoring the morphology of surface-engineered SiO₂ NPs in combination with different thermoplastic foam matrixes will open up new avenues for nanocellular foam morphology control.

2.6 Catalytic Effects of Silica Nanoparticles

A catalyst is defined as a substance that is added to chemical reactions to increase the reaction rate without modifying the overall standard Gibbs energy change in the reaction.²⁶⁷ Usually, the catalyst provides an alternative reaction pathway/mechanism with lower activation energy while leaving the reaction equilibrium intact (see Figure 2.20). Catalysts are generally classified into three categories: homogeneous, heterogeneous, and enzymatic.

Figure 2.20 Energy profile of an endothermic reaction showing the reactants (X), products (Y), activation energy (E_a), and enthalpy (ΔH).²⁶⁸

2.6.1 Catalytic Activities of Silica Nanoparticles

NPs commonly have many unsaturated atoms at the surface and edge due to the unprecedented large surface/volume ratio. These unsaturated atoms can be easily coordinated with the surrounding species, making them ideal candidates for catalytical applications. NP catalysts can maximize exposure of active sites, like a homogeneous catalyst, while retaining the possibility to be separated, purified, and reused like a heterogeneous catalyst.

Noble metal NPs (NMNs), just like noble metals, are a fascinating class of materials in catalysis science because of their outstanding properties.^{269–272} The NMN catalysts commonly suffer from sintering, which can severely influence the catalytic performance of NMN catalysts. Using a support material is an effective approach to prevent NMNs from sintering.

As mentioned, SiO_2 NPs are commonly used as support material for NMN. SiO_2 NPs are well known for their unique properties, such as i) facile synthesis, even at room

temperature, ii) a size that can be easily tuned, iii) non-toxic and inexpensive, and iv) that they are stable in various organic solvents and at relatively high temperatures. Numerous efforts have been made to optimize the catalytic activity of NMN supported by SiO₂ NPs. For example, Song et al.²⁷³ reported the synthesis of SBA-15 (mesoporous silica)-supported 1-7 nm platinum (Pt) NPs via sonication and calcination at elevated temperatures. The resulting SBA-15 supported Pt NPs were tested for ethylene hydrogenation under variant conditions. The SBA-15 supported Pt NPs were stable under 20 torr C₂H₄, 200 torr H₂, and 658 K.

Figure 2.21 The proposed mechanism of SiO₂ catalyzed linear thioether fabrication.²⁷⁴

As widely as SiO₂ NP is used as a support material for NMN, the catalytic activity of SiO₂ NP itself has rarely been presented and discussed in the literature. Banerjee et al.²⁷⁴ were among the pioneers to exploit the catalytic activity of SiO₂ in organic transformations. They discussed that Stöber SiO₂ NPs catalyzed anti-Markovnikov addition of thiols to alkenes and alkynes (see Figure 2.21). With the addition of 1 wt% SiO₂ NPs, the thioethers can be produced at room temperature with a yield of up to 98% in 1.5 hours (see Figure 2.22). It usually takes more than 24 hours for the neat reaction to achieve the same yield. The same authors also utilized the catalytic activity of SiO₂ NPs in the bis-Michael addition of active methylene compounds to conjugated alkenes,²⁷⁵ which was considered possible only with a few catalysts, like ruthenium complex²⁷⁶ and basic ionic liquid catalyst^{277,278}. Kundu et al.²⁷⁹ reported using a commercial silica gel for dithioethers synthesis. By controlling the moisture level of the silica gel (dry/moistened), the authors were able to conduct the regioselective synthesis of 1,2- and 1,3-dithioethers at room temperature by reacting a variety of aromatic thiols with alkyl bromide. Similarly, Nikoofar and Khalili used commercial SiO₂ to catalyze the one-pot synthesis of symmetrical and unsymmetrical 3,3-di(aryl)indolin-2-ones.²⁸⁰ The synthesis was performed under solvent-free conditions with magnetic stirring or grinding at room

temperature. Ramazani et al.²⁸¹ discussed using SiO₂ NPs to prepare ketoamide derivatives at ambient temperature. The ketoamide derivatives were prepared via a one-pot multicomponent condensation reaction catalyzed by SiO₂ NPs.

Figure 2.22 The silica NPs-catalyzed synthesis of linear thioethers.²⁷⁴

Besides the SiO₂ catalyzed chemical synthesis, there is also literature that describes the use of mesoporous SiO₂ to catalyze polymer degradation. The common catalysts for thermal degradation of polymers (e.g., polyethylene, polypropylene, polystyrene) into fuel oil are silica-alumina^{282–286}, zeolites^{283,285,287–289}, fluid catalytic cracking (FCC) catalysts^{290–292}, metal-based catalysts²⁹³, and basic oxides²⁹⁴.

In 1997, Sakata et al. reported using a non-conventional catalyst – mesoporous silica (KFS-16B) – to catalyze polyethylene degradation.²⁹⁵ The sodium silicate powder was calcined to form δ -Na₂Si₂O₅, followed by suspension in water and subsequent filtration to form a wet Kanemite[®] paste. Then the paste was dispersed in hexadecyltrimethylammoniumbromide solution for ion exchange at the desired pH at 70 °C, followed by calcination to form KFS-16B.²⁹⁶ The hexagonal pores ($\varnothing$ 3.6 nm) on the KFS-16B particles acted as nanometric reactor vessels. They could encapsulate free radicals and extend their active time, therefore accelerating the degradation of polyethylene. In later research, Sakata et al. compared the catalytic activity of mesoporous SiO₂ NPs and a solid acidic catalyst to degrade polyethylene and polypropylene into fuel oil.²⁸⁵ Instead of participating in the chemical reaction (i.e. polyethylene degradation), mesoporous SiO₂ NPs acted as a reaction flask. The role of mesoporous SiO₂ NPs during these chemical reactions did not fit the classical catalyst description. However, the presence of mesoporous SiO₂ NPs decreased the reaction temperature, increased the yield, and shortened the time to reach equilibrium. The examples presented and discussed above show the potential of Si-containing NPs as a non-conventional catalyst.

2.7 Concluding Remarks

Si-containing nanoparticles are an exciting and promising class of materials with countless applications. This is mainly ascribed to their (size-dependent) unique properties, low toxicity, and well-established synthetic preparation and derivatization methods. This Chapter presented and discussed the emerging fields of printable silicon nanoparticle-based electronics, theranostics, nanocellular polymer foaming, and catalysis. We recognize that at the forefront in these areas, the use of SiNPs or SiO₂ NPs offers distinguished advantages over existing competing particles. We also identified that the main bottlenecks to solve are their large-scale affordable and reproducible production and legislation to enable biomedical applications. Provided that these challenges will be tackled, SiNPs and SiO₂ NPs are expected to become enabling platform particles that will enhance the development of the discussed emerging research areas to appropriate industrial levels.

2.8 References

- (1) Osborne, I.; Lavine, M.; Coontz, R. Materials for Electronics. Looking beyond Silicon. Introduction. *Science (New York, N.Y.)* **2010**, 327 (5973), 1595.
- (2) Venema, L. Silicon Electronics and Beyond. *Nature* **2011**, 479 (7373), 309.
- (3) Orton, J. (2009). *Semiconductors and the Information Revolution*. Academic Press.
- (4) Capek, I. (2019) Nanotechnology and Nanomaterials. In I. Capek (Ed.). *Nanocomposite Structures and Dispersion* (pp 1–93). Elsevier: Amsterdam.
- (5) Sailor, M. J. (2012). *Porous Silicon in Practice: Preparation, Characterization and Applications*. Wiley-VCH.
- (6) Dasog, M.; Kehrle, J.; Rieger, B.; Veinot, J. G. C. Silicon Nanocrystals and Silicon-Polymer Hybrids: Synthesis, Surface Engineering, and Applications. *Angewandte Chemie - International Edition* **2016**, 55 (7), 2322–2339.
- (7) Jeelani, P. G.; Mulay, P.; Venkat, R.; Ramalingam, C. Multifaceted Application of Silica Nanoparticles. A Review. *Silicon* **2020**, 12 (6), 1337–1354.
- (8) Narayan, R.; Nayak, U. Y.; Raichur, A. M.; Garg, S. Mesoporous Silica Nanoparticles: A Comprehensive Review on Synthesis and Recent Advances. *Pharmaceutics* **2018**, 10 (3), 118.
- (9) Chang, H.; Sun, S. Q. Silicon Nanoparticles: Preparation, Properties, and Applications. *Chinese Physics B* **2014**, 23 (8), 1–14.
- (10) Don, M. M.; San, C. Y.; Jeevanandam, J. (2016) Antimicrobial Properties of Nanobiomaterials and the Mechanism. In A. Grumezescu (Ed.). *Nanobiomaterials in Antimicrobial Therapy: Applications of Nanobiomaterials* (pp 261–312). William Andrew.
- (11) Popelensky, V. M.; Dorofeev, S. G.; Kononov, N. N.; Bubenov, S. S.; Vinokurov, A. A. Room Temperature Oxidation of Si Nanocrystals at Dry and Wet Air.

- Journal of Nanoparticle Research* **2020**, *22* (3), 54.
- (12) Belomoin, G.; Therrien, J.; Smith, A.; Rao, S.; Twesten, R.; Chaieb, S.; Nayfeh, M. H.; Wagner, L.; Mitas, L. Observation of a Magic Discrete Family of Ultrabright Si Nanoparticles. *Applied Physics Letters* **2002**, *80* (5), 841–843.
 - (13) Canham, L. T. Silicon Quantum Wire Array Fabrication by Electrochemical and Chemical Dissolution of Wafers. *Applied Physics Letters* **1990**, *57* (10), 1046–1048.
 - (14) Dohnalová, K.; Fučíková, A.; Umesh, C. P.; Humpolíčková, J.; Paulusse, J. M. J.; Valenta, J.; Zuilhof, H.; Hof, M.; Gregorkiewicz, T. Microscopic Origin of the Fast Blue-Green Luminescence of Chemically Synthesized Non-Oxidized Silicon Quantum Dots. *Small* **2012**, *8* (20), 3185–3191.
 - (15) Wen, X.; Zhang, P.; Smith, T. A.; Anthony, R. J.; Kortshagen, U. R.; Yu, P.; Feng, Y.; Shrestha, S.; Coniber, G.; Huang, S. Tunability Limit of Photoluminescence in Colloidal Silicon Nanocrystals. *Scientific Reports* **2015**, *5* (1), 12469.
 - (16) Sinenikov, R.; Dasog, M.; Beamish, J.; Meldrum, A.; Veinot, J. G. C. Revisiting an Ongoing Debate: What Role Do Surface Groups Play in Silicon Nanocrystal Photoluminescence? *ACS Photonics* **2017**, *4* (8), 1920–1929.
 - (17) Meier, C.; Gondorf, A.; Lüttjohann, S.; Lorke, A.; Wiggers, H. Silicon Nanoparticles: Absorption, Emission, and the Nature of the Electronic Bandgap. *Journal of Applied Physics* **2007**, *101* (10), 103112.
 - (18) Shirahata, N. Colloidal Si Nanocrystals: A Controlled Organic-Inorganic Interface and Its Implications of Color-Tuning and Chemical Design toward Sophisticated Architectures. *Physical Chemistry Chemical Physics* **2011**, *13* (16), 7284–7294.
 - (19) Gonzalez, C. M.; Iqbal, M.; Dasog, M.; Piercey, D. G.; Lockwood, R.; Klapötke, T. M.; Veinot, J. G. C. Detection of High-Energy Compounds Using Photoluminescent Silicon Nanocrystal Paper Based Sensors. *Nanoscale* **2014**, *6* (5), 2608–2612.
 - (20) Sailor, M. J.; Wu, E. C. Photoluminescence-Based Sensing with Porous Silicon Films, Microparticles, and Nanoparticles. *Advanced Functional Materials* **2009**, *19* (20), 3195–3208.
 - (21) Peng, F.; Su, Y.; Zhong, Y.; Fan, C.; Lee, S. T.; He, Y. Silicon Nanomaterials Platform for Bioimaging, Biosensing, and Cancer Therapy. *Accounts of Chemical Research* **2014**, *47* (2), 612–623.
 - (22) Rosso-Vasic, M.; Spruijt, E.; Popović, Z.; Overgaag, K.; Van Lagen, B.; Grandidier, B.; Vanmaekelbergh, D.; Domínguez-Gutiérrez, D.; De Cola, L.; Zuilhof, H. Amine-Terminated Silicon Nanoparticles: Synthesis, Optical Properties and Their Use in Bioimaging. *Journal of Materials Chemistry* **2009**, *19* (33), 5926–5933.
 - (23) Maier-Flaig, F.; Rinck, J.; Stephan, M.; Bocksrocker, T.; Bruns, M.; Kübel, C.; Powell, A. K.; Ozin, G. A.; Lemmer, U. Multicolor Silicon Light-Emitting Diodes (SiLEDs). *Nano Letters* **2013**, *13* (2), 475–480.
 - (24) Stupca, M.; Alsalhi, M.; Al Saud, T.; Almuhanha, A.; Nayfeh, M. H. Enhancement of Polycrystalline Silicon Solar Cells Using Ultrathin Films of Silicon Nanoparticle. *Applied Physics Letters* **2007**, *91* (6), 063107.
 - (25) Cullis, A. G.; Canham, L. T. Visible Light Emission Due to Quantum Size Effects in Highly Porous Crystalline Silicon. *Nature* **1991**, *353* (6342), 335–338.

- (26) Akkerman, Q. A. (2019). Lead Halide Perovskite Nanocrystals - A New Age of Semiconductor Nanocrystals. Università degli Studi di Genova. <https://iris.unige.it/handle/11567/941201>
- (27) Alexander, G. B.; Heston, W. M.; Iler, R. K. The Solubility of Amorphous Silica in Water. *Journal of Physical Chemistry* **1954**, *58* (6), 453–455.
- (28) Shen, D.; Yang, J.; Li, X.; Zhou, L.; Zhang, R.; Li, W.; Chen, L.; Wang, R.; Zhang, F.; Zhao, D. Biphasic Stratification Approach to Three-Dimensional Dendritic Biodegradable Mesoporous Silica Nanospheres. *Nano Letters* **2014**, *14* (2), 923–932.
- (29) Argyo, C.; Weiss, V.; Bräuchle, C.; Bein, T. Multifunctional Mesoporous Silica Nanoparticles as a Universal Platform for Drug Delivery. *Chemistry of Materials* **2014**, *26* (1), 435–451.
- (30) Giri, S.; Trewyn, B. G.; Stellmaker, M. P.; Lin, V. S. Y. Stimuli-Responsive Controlled-Release Delivery System Based on Mesoporous Silica Nanorods Capped with Magnetic Nanoparticles. *Angewandte Chemie - International Edition* **2005**, *44* (32), 5038–5044.
- (31) Barbé, C.; Bartlett, J.; Kong, L.; Finnie, K.; Lin, H. Q.; Larkin, M.; Calleja, S.; Bush, A.; Calleja, G. Silica Particles: A Novel Drug-Delivery System. *Advanced Materials* **2004**, *16* (21), 1959–1966.
- (32) Dave, B. C.; Dunn, B.; Valentine, J. S.; Zink, J. I. Sol-Gel Encapsulation Methods for Biosensors. *Analytical Chemistry* **1994**, *66* (22), 1120A–1127A.
- (33) Lin, V. S. Y.; Lai, C. Y.; Huang, J.; Song, S. A.; Xu, S. Molecular Recognition inside of Multifunctionalized Mesoporous Silicas: Toward Selective Fluorescence Detection of Dopamine and Glucosamine. *Journal of the American Chemical Society* **2001**, *123* (46), 11510–11511.
- (34) Santra, S.; Malhotra, A. Fluorescent Nanoparticle Probes for Imaging of Cancer. *Wiley Interdisciplinary Reviews: Nanomedicine and Nanobiotechnology* **2011**, *3* (5), 501–510.
- (35) He, X.; Duan, J.; Wang, K.; Tan, W.; Lin, X.; He, C. A Novel Fluorescent Label Based on Organic Dye-Doped Silica Nanoparticles for HepG Liver Cancer Cell Recognition. *Journal of Nanoscience and Nanotechnology* **2004**, *4* (6), 585–589.
- (36) Yao, G.; Wang, L.; Wu, Y.; Smith, J.; Xu, J.; Zhao, W.; Lee, E.; Tan, W. FloDots: Luminescent Nanoparticles. *Analytical and Bioanalytical Chemistry* **2006**, *385* (3), 518–524.
- (37) Wang, L.; Yang, C.; Tan, W. Dual-Luminophore-Doped Silica Nanoparticles for Multiplexed Signaling. *Nano Letters* **2005**, *5* (1), 37–43.
- (38) Zhao, X.; Tapecc-Dytioco, R.; Tan, W. Ultrasensitive DNA Detection Using Highly Fluorescent Bioconjugated Nanoparticles. *Journal of the American Chemical Society* **2003**, *125* (38), 11474–11475.
- (39) Ulrich, G. D.; Riehl, J. W. Aggregation and Growth of Submicron Oxide Particles in Flames. *Journal of Colloid And Interface Science* **1982**, *87* (1), 257–265.
- (40) Chen, X.; Jiang, J.; Yan, F.; Tian, S.; Li, K. A Novel Low Temperature Vapor Phase Hydrolysis Method for the Production of Nano-Structured Silica Materials Using Silicon Tetrachloride. *RSC Advances* **2014**, *4* (17), 8703–8710.
- (41) Jal, P.K.; Sudarshan, M.; Saha, A.; Patel, S.; Mishra, B.K. Synthesis and Characterization of Nanosilica Prepared by Precipitation Method. *Colloids and*

- Surfaces A: Physicochemical and Engineering Aspects* **2004**, 240 (1-3), 173-178.
- (42) Musić, S.; Filipović-Vinceković, N.; Sekovanić, L. Precipitation of Amorphous SiO₂ Particles and Their Properties. *Brazilian Journal of Chemical Engineering* **2011**, 28 (1), 89-94.
- (43) Wang, X. D.; Shen, Z. X.; Sang, T.; Cheng, X. bin; Li, M. F.; Chen, L. Y.; Wang, Z. S. Preparation of Spherical Silica Particles by Stöber Process with High Concentration of Tetra-Ethyl-Orthosilicate. *Journal of Colloid and Interface Science* **2010**, 341 (1), 23-29.
- (44) Canton, G.; Riccò, R.; Marinello, F.; Carmignato, S.; Enrichi, F. Modified Stöber Synthesis of Highly Luminescent Dye-Doped Silica Nanoparticles. *Journal of Nanoparticle Research* **2011**, 13 (9), 4349-4356.
- (45) Stöber, W.; Fink, A.; Bohn, E. Controlled Growth of Monodisperse Silica Spheres in the Micron Size Range. *Journal of Colloid And Interface Science* **1968**, 26 (1), 62-69.
- (46) Santamaría Razo, D. A.; Pallavidino, L.; Garrone, E.; Geobaldo, F.; Descrovi, E.; Chiodoni, A.; Giorgis, F. A Version of Stöber Synthesis Enabling the Facile Prediction of Silica Nanospheres Size for the Fabrication of Opal Photonic Crystals. *Journal of Nanoparticle Research* **2008**, 10 (7), 1225-1229.
- (47) Nozawa, K.; Gailhanou, H.; Raison, L.; Panizza, P.; Ushiki, H.; Sellier, E.; Delville, J. P.; Delville, M. H. Smart Control of Monodisperse Stöber Silica Particles: Effect of Reactant Addition Rate on Growth Process. *Langmuir* **2005**, 21 (4), 1516-1523.
- (48) Grün, M.; Lauer, I.; Unger, K. K. The Synthesis of Micrometer- and Submicrometer-Size Spheres of Ordered Mesoporous Oxide MCM-41. *Advanced Materials* **1997**, 9 (3), 254-257.
- (49) Gao, C.; Qiu, H.; Zeng, W.; Sakamoto, Y.; Terasaki, O.; Sakamoto, K.; Chen, Q.; Che, S. Formation Mechanism of Anionic Surfactant-Templated Mesoporous Silica. *Chemistry of Materials* **2006**, 18 (16), 3904-3914.
- (50) Kumar, D.; Schumacher, K.; du Fresne von Hohenesche, C.; Grün, M.; Unger, K. K. MCM-41, MCM-48 and Related Mesoporous Adsorbents: Their Synthesis and Characterisation. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* **2001**, 187-188, 109-116.
- (51) Flodström, K.; Wennerström, H.; Alfredsson, V. Mechanism of Mesoporous Silica Formation, a Time-Resolved NMR and TEM Study of Silica-Block Copolymer Aggregation. *Langmuir* **2004**, 20 (3), 680-688.
- (52) Jammaer, J.; Aerts, A.; D'Haen, J.; Seo, J. W.; Martens, J. A. Convenient Synthesis of Ordered Mesoporous Silica at Room Temperature and Quasi-Neutral PH. *Journal of Materials Chemistry* **2009**, 19 (44), 8290-8293.
- (53) Lam, C.; Zhang, Y. F.; Tang, Y. H.; Lee, C. S.; Bello, I.; Lee, S. T. Large-Scale Synthesis of Ultrafine Si Nanoparticles by Ball Milling. *Journal of Crystal Growth* **2000**, 220 (4), 466-470.
- (54) Yoshida, T.; Takeyama, S.; Yamada, Y.; Mutoh, K. Nanometer-Sized Silicon Crystallites Prepared by Excimer Laser Ablation in Constant Pressure Inert Gas. *Applied Physics Letters* **1996**, 68 (13), 1772-1774.
- (55) Ahire, J. H.; Wang, Q.; Coxon, P. R.; Malhotra, G.; Brydson, R.; Chen, R.; Chao, Y. Highly Luminescent and Nontoxic Amine-Capped Nanoparticles from Porous

- Silicon: Synthesis and Their Use in Biomedical Imaging. *ACS Applied Materials and Interfaces* **2012**, 4 (6), 3285–3292.
- (56) Wilcoxon, J. P.; Samara, G. A.; Provencio, P. N. Optical and Electronic Properties of Si Nanoclusters Synthesized in Inverse Micelles. *Physical Review B - Condensed Matter and Materials Physics* **1999**, 60 (4), 2704–2714.
- (57) Heath, J. R. A Liquid-Solution-Phase Synthesis of Crystalline Silicon. *Science* **1992**, 258 (5085), 1131–1133.
- (58) Knipping, J.; Wiggers, H.; Rellinghaus, B.; Roth, P.; Konjhodzic, D.; Meier, C. Synthesis of High Purity Silicon Nanoparticles in a Low Pressure Microwave Reactor. *Journal of Nanoscience and Nanotechnology* **2004**, 4 (8), 1039–1044.
- (59) Ehbrecht, M.; Huysken, F. Gas-Phase Characterization of Silicon Nanoclusters Produced by Laser Pyrolysis of Silane. *Physical Review B - Condensed Matter and Materials Physics* **1999**, 59 (4), 2975–2985.
- (60) Hülser, T.; Schnurre, S. M.; Wiggers, H.; Schulz, C. Gas-Phase Synthesis of Nanoscale Silicon as an Economical Route towards Sustainable Energy Technology. *KONA Powder and Particle Journal* **2011**, 29 (29), 191–207.
- (61) Smokefoot. highly simplified representation of the condensation of TEOS in sol gel process
<https://commons.wikimedia.org/wiki/File:SolGelCartoon.png>.
- (62) Wu, Y.; Zhong, Y.; Chu, B.; Sun, B.; Song, B.; Wu, S.; Su, Y.; He, Y. Plant-Derived Fluorescent Silicon Nanoparticles Featuring Excitation Wavelength-Dependent Fluorescence Spectra for Anti-Counterfeiting Applications. *Chemical Communications* **2016**, 52 (43), 7047–7050.
- (63) Pratsinis, S. E. Flame Aerosol Synthesis of Ceramic Powders. *Progress in Energy and Combustion Science* **1998**, 24 (3), 197–219.
- (64) Khavryutchenko, V.; Khavryutchenko, A.; Barthel, H. Fumed Silica Synthesis: Influence of Small Molecules on the Particle Formation Process. *Macromolecular Symposia* **2001**, 169 (1), 1–6.
- (65) Rahman, I. A.; Padavettan, V. Synthesis of Silica Nanoparticles by Sol-Gel: Size-Dependent Properties, Surface Modification, and Applications in Silica-Polymer Nanocomposites a Review. *Journal of Nanomaterials* **2012**, 2012, 132424.
- (66) Gorji, B.; Fazaeli, R.; Niksirat, N. Synthesis and Characterizations of Silica Nanoparticles by a New Sol-Gel Method. *Quarterly Journal of Applied Chemical Research* **2012**, 6 (3), 22–26.
- (67) Zulfqar, U.; Subhani, T.; Husain, S. W. Synthesis and Characterization of Silica Nanoparticles from Clay. *Journal of Asian Ceramic Societies* **2016**, 4 (1), 91–96.
- (68) Cummins, G.; Desmulliez, M. P. Y. Inkjet Printing of Conductive Materials: A Review. *Circuit World* **2012**, 38 (4), 193–213.
- (69) Yin, Z. P.; Huang, Y. A.; Bu, N. bin; Wang, X. M.; Xiong, Y. L. Inkjet Printing for Flexible Electronics: Materials, Processes and Equipments. *Chinese Science Bulletin* **2010**, 55 (30), 3383–3407.
- (70) Andò, B.; Baglio, S. Inkjet-Printed Sensors: A Useful Approach for Low Cost, Rapid Prototyping [Instrumentation Notes]. *IEEE Instrumentation and Measurement Magazine* **2011**, 14 (5), 36–40.
- (71) Cruz, S. M. F.; Rocha, L. A.; Viana, J. C. (2018). Printing Technologies on Flexible Substrates for Printed Electronics. In S. Rackauskas (Ed.). *Flexible*

- Electronics*. IntechOpen. doi: 10.5772/intechopen.76161.
- (72) Cauchois, R.; Saadaoui, M.; Yakoub, A.; Inal, K.; Dubois-Bonvalot, B.; Fidalgo, J. C. Impact of Variable Frequency Microwave and Rapid Thermal Sintering on Microstructure of Inkjet-Printed Silver Nanoparticles. *Journal of Materials Science* **2012**, 47 (20), 7110–7116.
- (73) Yakoub, A.; Saadaoui, M.; Benaben, P.; Iliev, P. High Efficiency of Low-Cost Spiral Antennas for RFID, Fully Printed by an Inline Inkjet Process. *Proceedings Large Organic and Printed Electronics Conference*, 2012.
- (74) Sanaur, S.; Whalley, A.; Alameddine, B.; Carnes, M.; Nuckolls, C. Jet-Printed Electrodes and Semiconducting Oligomers for Elaboration of Organic Thin-Film Transistors. *Organic Electronics* **2006**, 7 (5), 423–427.
- (75) Kamyshny, A. Metal-Based Inkjet Inks for Printed Electronics. *The Open Applied Physics Journal* **2011**, 4 (1), 19–36.
- (76) Derby, B. Inkjet Printing of Functional and Structural Materials: Fluid Property Requirements, Feature Stability, and Resolution. *Annual Review of Materials Research* **2010**, 40, 395–414.
- (77) Caironi, M.; Gili, E.; Sakanoue, T.; Cheng, X.; Sirringhaus, H. High Yield, Single Droplet Electrode Arrays for Nanoscale Printed Electronics. *ACS Nano* **2010**, 4 (3), 1451–1456.
- (78) Wang, J.; Cheng, X.; Caironi, M.; Gao, F.; Yang, X.; Greenham, N. C. Entirely Solution-Processed Write-Once-Read-Many-Times Memory Devices and Their Operation Mechanism. *Organic Electronics* **2011**, 12 (7), 1271–1274.
- (79) Mizukami, M.; Cho, S. Il; Watanabe, K.; Abiko, M.; Suzuri, Y.; Tokito, S.; Kido, J. Flexible Organic Light-Emitting Diode Displays Driven by Inkjet-Printed High-Mobility Organic Thin-Film Transistors. *IEEE Electron Device Letters* **2018**, 39 (1), 39–42.
- (80) Templier, F.; Aventurier, B.; Demars, P.; Botrel, J. L.; Martin, P. Fabrication of High Performance Low Temperature Poly-Silicon Backplanes on Metal Foil for Flexible Active-Matrix Organic Light Emission Diode Displays. *Thin Solid Films* **2007**, 515 (19 SPEC. ISS.), 7428–7432.
- (81) Kukkola, J.; Mohl, M.; Leino, A. R.; Tóth, G.; Wu, M. C.; Shchukarev, A.; Popov, A.; Mikkola, J. P.; Lauri, J.; Riihimäki, M.; Lappalainen, J.; Jantunen, H.; Kordás, K. Inkjet-Printed Gas Sensors: Metal Decorated WO₃ Nanoparticles and Their Gas Sensing Properties. *Journal of Materials Chemistry* **2012**, 22 (34), 17878–17886.
- (82) Li, B.; Santhanam, S.; Schultz, L.; Jeffries-EL, M.; Iovu, M. C.; Sauv, G.; Cooper, J.; Zhang, R.; Revelli, J. C.; Kusne, A. G.; Snyder, J. L.; Kowalewski, T.; Weiss, L. E.; McCullough, R. D.; Fedder, G. K.; Lambeth, D. N. Inkjet Printed Chemical Sensor Array Based on Polythiophene Conductive Polymers. *Sensors and Actuators, B: Chemical* **2007**, 123 (2), 651–660.
- (83) Komuro, N.; Takaki, S.; Suzuki, K.; Citterio, D. Inkjet Printed (Bio)Chemical Sensing Devices. *Analytical and Bioanalytical Chemistry* **2013**, 405 (17), 5785–5805.
- (84) Noh, Y. Y.; Zhao, N.; Caironi, M.; Sirringhaus, H. Downscaling of Self-Aligned, All-Printed Polymer Thin-Film Transistors. *Nature Nanotechnology* **2007**, 2 (12), 784–789.

- (85) Minemawari, H.; Yamada, T.; Matsui, H.; Tsutsumi, J. Y.; Haas, S.; Chiba, R.; Kumai, R.; Hasegawa, T. Inkjet Printing of Single-Crystal Films. *Nature* **2011**, 475 (7356), 364–367.
- (86) Baeg, K. J.; Khim, D.; Kim, J.; Kim, D. Y.; Sung, S. W.; Yang, B. Do; Noh, Y. Y. Flexible Complementary Logic Gates Using Inkjet-Printed Polymer Field-Effect Transistors. *IEEE Electron Device Letters* **2013**, 34 (1), 126–128.
- (87) Molina-Lopez, F.; Gao, T. Z.; Kraft, U.; Zhu, C.; Öhlund, T.; Pfattner, R.; Feig, V. R.; Kim, Y.; Wang, S.; Yun, Y.; Bao, Z. Inkjet-Printed Stretchable and Low Voltage Synaptic Transistor Array. *Nature Communications* **2019**, 10 (1), 1–10.
- (88) Sekitani, T.; Noguchi, Y.; Zschieschang, U.; Klauk, H.; Someya, T. Organic Transistors Manufactured Using Inkjet Technology with Subfemtoliter Accuracy. *Proceedings of the National Academy of Sciences of the United States of America* **2008**, 105 (13), 4976–4980.
- (89) Lawes, S.; Sun, Q.; Lushington, A.; Xiao, B.; Liu, Y.; Sun, X. Inkjet-Printed Silicon as High Performance Anodes for Li-Ion Batteries. *Nano Energy* **2017**, 36, 313–321.
- (90) Hoth, C. N.; Schilinsky, P.; Choulis, S. A.; Brabec, C. J. Printing Highly Efficient Organic Solar Cells. *Nano Letters* **2008**, 8 (9), 2806–2813.
- (91) Teichler, A.; Eckardt, R.; Hoepfner, S.; Friebe, C.; Perelaer, J.; Senes, A.; Morana, M.; Brabec, C. J.; Schubert, U. S. Combinatorial Screening of Polymer: Fullerene Blends for Organic Solar Cells by Inkjet Printing. *Advanced Energy Materials* **2011**, 1 (1), 105–114.
- (92) Nayak, L.; Mohanty, S.; Nayak, S. K.; Ramadoss, A. A Review on Inkjet Printing of Nanoparticle Inks for Flexible Electronics. *Journal of Materials Chemistry C* **2019**, 7 (29), 8771–8795.
- (93) Vincent, B. The Effect of Adsorbed Polymers on Dispersion Stability. *Advances in Colloid and Interface Science* **1974**, 4 (2–3), 193–277.
- (94) Yu, W.; Xie, H. A Review on Nanofluids: Preparation, Stability Mechanisms, and Applications. *Journal of Nanomaterials* **2012**, 2012, 435873.
- (95) Physical Stability of Disperse Systems <https://lubrizolcdmo.com/technical-briefs/physical-stability-of-disperse-systems/> (accessed 2020 -10 -11).
- (96) Sailor, M. J. (2017). Chemical Reactivity and Surface Chemistry of Porous Silicon. In L. Canham (Ed.). *Handbook of Porous Silicon* (pp 1-20). Springer, Cham.
- (97) Du, X.; He, J. A Self-Templated Etching Route to Surface-Rough Silica Nanoparticles for Superhydrophobic Coatings. *ACS Applied Materials and Interfaces* **2011**, 3 (4), 1269–1276.
- (98) Dehzangi, A.; Larki, F.; Majlis, B. B.; Naseri, M. G.; Navasery, M.; Abdullah, A. M.; Hutagalung, S. D.; Hamid, N. A.; Noor, M. M.; Vakilian, M.; Saion, E. B. Impact of KOH Etching on Nanostructure Fabricated by Local Anodic Oxidation Method. *International Journal of Electrochemical Science* **2013**, 8 (6), 8084–8096.
- (99) Seidel, H.; Csepregi, L.; Heuberger, A.; Baumgärtel, H. Anisotropic Etching of Crystalline Silicon in Alkaline Solutions: I . Orientation Dependence and Behavior of Passivation Layers. *Journal of The Electrochemical Society* **1990**, 137

- (11), 3612–3626.
- (100) Yin, S. Unpublished Data. *For further reference, the reader is directed to reference 97, which is reporting the etching of planar Si surface with KOH.*
- (101) Ogata, Y.; Niki, H.; Sakka, T.; Iwasaki, M. Oxidation of Porous Silicon under Water Vapor Environment. *Journal of The Electrochemical Society* **1995**, *142* (5), 1595–1601.
- (102) Lehmann, V. The Chemical Dissolution of Silicon. *Electrochemistry of Silicon* **2003**, 23–38.
- (103) Benke, G.; Gnot, W. The Electrochemical Dissolution of Platinum. *Hydrometallurgy* **2002**, *64*, 205–218.
- (104) Wheeler, L. M.; Neale, N. R.; Chen, T.; Kortshagen, U. R. Hypervalent Surface Interactions for Colloidal Stability and Doping of Silicon Nanocrystals. *Nature Communications* **2013**, *4*, 1–10.
- (105) Erogbogbo, F.; Liu, T.; Ramadurai, N.; Tuccarione, P.; Lai, L.; Swihart, M. T.; Prasad, P. N. Creating Ligand-Free Silicon Germanium Alloy Nanocrystal Inks. *ACS Nano* **2011**, *5* (10), 7950–7959.
- (106) Kůsová, K.; Cibulka, O.; Dohnalová, K.; Pelant, I.; Fučíková, A.; Valenta, J. Yellow-Emitting Colloidal Suspensions of Silicon Nanocrystals: Fabrication Technology, Luminescence Performance and Application Prospects. *Physica E: Low-Dimensional Systems and Nanostructures* **2009**, *41* (6), 982–985.
- (107) Bywalez, R.; Karacuban, H.; Nienhaus, H.; Schulz, C.; Wiggers, H. Stabilization of Mid-Sized Silicon Nanoparticles by Functionalization with Acrylic Acid. *Nanoscale Research Letters* **2012**, *7* (1), 76.
- (108) Reindl, A.; Voronov, A.; Gorle, P. K.; Rauscher, M.; Roosen, A.; Peukert, W. Dispersing and Stabilizing Silicon Nanoparticles in a Low-Epsilon Medium. *Colloids and Surfaces A: Physicochemical and Engineering Aspects* **2008**, *320* (1–3), 183–188.
- (109) Boukherroub, R.; Wojtyk, J. T. C.; Wayner, D. D. M.; Lockwood, D. J. Thermal Hydrosilylation of Undecylenic Acid with Porous Silicon. *Journal of The Electrochemical Society* **2002**, *149* (2), H59.
- (110) Stewart, M. P.; Buriak, J. M. Photopatterned Hydrosilylation on Porous Silicon. *Angewandte Chemie - International Edition* **1998**, *37* (23), 3257–3260.
- (111) Buriak, J. M. Organometallic Chemistry on Silicon and Germanium Surfaces. *Chemical Reviews* **2002**, *102* (5), 1271–1308.
- (112) Linford, M. R.; Chidsey, C. E. D. Alkyl Monolayers Covalently Bonded to Silicon Surfaces. *Journal of the American Chemical Society* **1993**, *115* (26), 12631–12632.
- (113) Purkait, T. K.; Iqbal, M.; Wahl, M. H.; Gottschling, K.; Gonzalez, C. M.; Islam, M. A.; Veinot, J. G. C. Borane-Catalyzed Room-Temperature Hydrosilylation of Alkenes/Alkynes on Silicon Nanocrystal Surfaces. *Journal of the American Chemical Society* **2014**, *136* (52), 17914–17917.
- (114) Buriak, J. M. Organometallic Chemistry on Silicon and Germanium Surfaces. *Chemical Reviews* **2002**, *102* (5), 1271–1308.
- (115) Kelly, J. A.; Veinot, J. G. C. An Investigation into Near-UV Hydrosilylation of Freestanding Silicon Nanocrystals. *ACS Nano* **2010**, *4* (8), 4645–4656.
- (116) Holman, Z. C.; Kortshagen, U. R. Nanocrystal Inks without Ligands: Stable

- Colloids of Bare Germanium Nanocrystals. *Nano Letters* **2011**, *11* (5), 2133–2136.
- (117) Erogbogbo, F.; Liu, T.; Ramadurai, N.; Tuccarione, P.; Lai, L.; Swihart, M. T.; Prasad, P. N. Creating Ligand-Free Silicon Germanium Alloy Nanocrystal Inks. *ACS Nano* **2011**, *5* (10), 7950–7959.
- (118) Holman, Z. C.; Kortshagen, U. R. Nanocrystal Inks without Ligands: Stable Colloids of Bare Germanium Nanocrystals. *Nano Letters* **2011**, *11* (5), 2133–2136.
- (119) Grubbs, R. B. Roles of Polymer Ligands in Nanoparticle Stabilization. *Polymer Reviews* **2007**, *47* (2), 197–215.
- (120) Witten, T. A.; Pincus, P. A.; Pincus, P. A. Colloid Stabilization by Long Grafted Polymers. *Macromolecules* **1986**, *19* (10), 2509–2513.
- (121) Milligan, W. O. Colloid Science. By James W. McBain. *The Journal of Physical Chemistry* **1951**, *55* (7), 1277–1277.
- (122) Zhao, B.; Brittain, W. J. Polymer Brushes: Surface-Immobilized Macromolecules. *Progress in Polymer Science (Oxford)* **2000**, *25* (5), 677–710.
- (123) Tsubokawa, N. Surface Grafting of Polymers onto Nanoparticles in a Solvent-Free Dry-System and Applications of Polymer-Grafted Nanoparticles as Novel Functional Hybrid Materials. *Polymer Journal* **2007**, *39* (10), 983–1000.
- (124) Mohammadi Sejoubsari, R.; Martinez, A. P.; Kutes, Y.; Wang, Z.; Dobrynin, A. V.; Adamson, D. H. “Grafting-Through”: Growing Polymer Brushes by Supplying Monomers through the Surface. *Macromolecules* **2016**, *49* (7), 2477–2483.
- (125) Zoppe, J. O.; Ataman, N. C.; Mocny, P.; Wang, J.; Moraes, J.; Klok, H. A. Surface-Initiated Controlled Radical Polymerization: State-of-the-Art, Opportunities, and Challenges in Surface and Interface Engineering with Polymer Brushes. *Chemical Reviews* **2017**, *117* (3), 1105–1318.
- (126) Henze, M.; Mäde, D.; Prucker, O.; Rühle, J. “Grafting through”: Mechanistic Aspects of Radical Polymerization Reactions with Surface-Attached Monomers. *Macromolecules* **2014**, *47* (9), 2929–2937.
- (127) Lizundia, E.; Meaurio, E.; Vilas, J. L. (2016) Grafting of Cellulose Nanocrystals. In D. Puglia & E. Fortunati & J. M. Kenny (Ed.). *Multifunctional Polymeric Nanocomposites Based on Cellulosic Reinforcements* (pp 61–113). William Andrew.
- (128) Braunecker, W. A.; Matyjaszewski, K. Controlled/Living Radical Polymerization: Features, Developments, and Perspectives. *Progress in Polymer Science (Oxford)* **2007**, *32* (1), 93–146.
- (129) Yan, J.; Bockstaller, M. R.; Matyjaszewski, K. Brush-Modified Materials: Control of Molecular Architecture, Assembly Behavior, Properties and Applications. *Progress in Polymer Science* **2020**, *100*, 101180.
- (130) Matyjaszewski, K.; Xia, J. Atom Transfer Radical Polymerization. *Chemical Reviews* **2001**, *101* (9), 2921–2990.
- (131) Matyjaszewski, K. Atom Transfer Radical Polymerization (ATRP): Current Status and Future Perspectives. *Macromolecules* **2012**, *45* (10), 4015–4039.
- (132) Chiefari, J.; Chong, Y. K.; Ercole, F.; Krstina, J.; Jeffery, J.; Le, T. P. T.; Mayadunne, R. T. A.; Meijs, G. F.; Moad, C. L.; Moad, G.; Rizzardo, E.; Thang,

- S. H. Living Free-Radical Polymerization by Reversible Addition - Fragmentation Chain Transfer: The RAFT Process. *Macromolecules* **1998**, *31* (16), 5559–5562.
- (133) Moad, G.; Rizzardo, E.; Thang, S. H. Living Radical Polymerization by the RAFT Process. *Australian Journal of Chemistry* **2005**, *58* (6), 379–410.
- (134) Hawker, C. J.; Bosman, A. W.; Harth, E. New Polymer Synthesis by Nitroxide Mediated Living Radical Polymerizations. *Chemical Reviews* **2001**, *101* (12), 3661–3688.
- (135) Nicolas, J.; Guillaneuf, Y.; Lefay, C.; Bertin, D.; Gigmes, D.; Charleux, B. Nitroxide-Mediated Polymerization. *Progress in Polymer Science* **2013**, *38* (1), 63–235.
- (136) Georges, M. K.; Veregin, R. P. N.; Kazmaier, P. M.; Hamer, G. K. Narrow Molecular Weight Resins by a Free-Radical Polymerization Process. *Macromolecules* **1993**, *26* (11), 2987–2988.
- (137) Matyjaszewski, K. Advanced Materials by Atom Transfer Radical Polymerization. *Advanced Materials* **2018**, *30* (23), 10.1002/adma.201706441.
- (138) Von Werne, T.; Patten, T. E. Preparation of Structurally Well-Defined Polymer-Nanoparticle Hybrids with Controlled/Living Radical Polymerizations. *Journal of the American Chemical Society* **1999**, *121* (32), 7409–7410.
- (139) von Werne, T.; Patten, T. E. Atom Transfer Radical Polymerization from Nanoparticles: A Tool for the Preparation of Well-Defined Hybrid Nanostructures and for Understanding the Chemistry of Controlled/"living" Radical Polymerizations from Surfaces. *Journal of the American Chemical Society* **2001**, *123* (31), 7497–7505.
- (140) Pyun, J.; Jia, S.; Kowalewski, T.; Patterson, G. D.; Matyjaszewski, K. Synthesis and Characterization of Organic/Inorganic Hybrid Nanoparticles: Kinetics of Surface-Initiated Atom Transfer Radical Polymerization and Morphology of Hybrid Nanoparticle Ultrathin Films. *Macromolecules* **2003**, *36* (14), 5094–5104.
- (141) Lei, Z.; Bi, S. Preparation of Polymer Nanocomposites of Core-Shell Structure via Surface-Initiated Atom Transfer Radical Polymerizations. *Materials Letters* **2007**, *61* (16), 3531–3534.
- (142) Perruchot, C.; Khan, M. A.; Kamitsi, A.; Armes, S. P.; Von Werne, T.; Patten, T. E. Synthesis of Well-Defined, Polymer-Grafted Silica Particles by Aqueous ATRP. *Langmuir* **2001**, *17* (15), 4479–4481.
- (143) Popelensky, V. M.; Dorofeev, S. G.; Kononov, N. N.; Bubenov, S. S.; Vinokurov, A. A. Room Temperature Oxidation of Si Nanocrystals at Dry and Wet Air. *Journal of Nanoparticle Research* **2020**, *22* (3), 54.
- (144) Lawes, S.; Sun, Q.; Lushington, A.; Xiao, B.; Liu, Y.; Sun, X. Inkjet-Printed Silicon as High Performance Anodes for Li-Ion Batteries. *Nano Energy* **2017**, *36*, 313–321.
- (145) Drahi, E.; Blayac, S.; Borbely, A.; Benaben, P. Impact of Ink Synthesis on Processing of Inkjet-Printed Silicon Nanoparticle Thin Films: A Comparison of Rapid Thermal Annealing and Photonic Sintering. *Thin Solid Films* **2015**, *574*, 169–176.
- (146) Drahi, E.; Gupta, A.; Blayac, S.; Saunier, S.; Benaben, P. Characterization of Sintered Inkjet-Printed Silicon Nanoparticle Thin Films for Thermoelectric Devices. *Physica Status Solidi (A) Applications and Materials Science* **2014**, *211*

- (6), 1301–1307.
- (147) Gupta, A.; Khalil, A. S. G.; Offer, M.; Geller, M.; Winterer, M.; Lorke, A.; Wiggers, H. Synthesis and Ink-Jet Printing of Highly Luminescing Silicon Nanoparticles for Printable Electronics. *Journal of Nanoscience and Nanotechnology* **2011**, *11* (6), 5028–5033.
- (148) Strebhardt, K.; Ullrich, A. Paul Ehrlich's Magic Bullet Concept: 100 Years of Progress. *Nature Reviews Cancer* **2008**, *8* (6), 473–480.
- (149) Valent, P.; Groner, B.; Schumacher, U.; Superti-Furga, G.; Busslinger, M.; Kralovics, R.; Zielinski, C.; Penninger, J. M.; Kerjaschki, D.; Stingl, G.; Smolen, J. S.; Valenta, R.; Lassmann, H.; Kovar, H.; Jäger, U.; Kornek, G.; Müller, M.; Sörgel, F. Paul Ehrlich (1854-1915) and His Contributions to the Foundation and Birth of Translational Medicine. *Journal of Innate Immunity* **2016**, *8* (2), 111–120.
- (150) Panyam, J.; Labhasetwar, V. Biodegradable Nanoparticles for Drug and Gene Delivery to Cells and Tissue. *Advanced Drug Delivery Reviews* **2003**, *55* (3), 329–347.
- (151) Algar, W. R.; Prasuhn, D. E.; Stewart, M. H.; Jennings, T. L.; Blanco-Canosa, J. B.; Dawson, P. E.; Medintz, I. L. The Controlled Display of Biomolecules on Nanoparticles: A Challenge Suited to Bioorthogonal Chemistry. *Bioconjugate Chemistry* **2011**, *22* (5), 825–858.
- (152) Xie, J.; Lee, S.; Chen, X. Nanoparticle-Based Theranostic Agents. *Advanced Drug Delivery Reviews* **2010**, *62* (11), 1064–1079.
- (153) Rai, P.; Mallidi, S.; Zheng, X.; Rahmanzadeh, R.; Mir, Y.; Elrington, S.; Khurshid, A.; Hasan, T. Development and Applications of Photo-Triggered Theranostic Agents. *Advanced Drug Delivery Reviews* **2010**, *62* (11), 1094–1124.
- (154) Bayliss, S. C.; Heald, R.; Fletcher, D. I.; Buckberry, L. D. Culture of Mammalian Cells on Nanostructured Silicon. *Advanced Materials* **1999**, *11* (4), 318–321.
- (155) Park, J. H.; Gu, L.; Von Maltzahn, G.; Ruoslahti, E.; Bhatia, S. N.; Sailor, M. J. Biodegradable Luminescent Porous Silicon Nanoparticles for in Vivo Applications. *Nature Materials* **2009**, *8* (4), 331–336.
- (156) Cheng, X.; Lowe, S. B.; Reece, P. J.; Gooding, J. J. Colloidal Silicon Quantum Dots: From Preparation to the Modification of Self-Assembled Monolayers (SAMs) for Bio-Applications. *Chemical Society Reviews* **2014**, *43* (8), 2680–2700.
- (157) Chiappini, C.; De Rosa, E.; Martinez, J. O.; Liu, X.; Steele, J.; Stevens, M. M.; Tasciotti, E. Biodegradable Silicon Nanoneedles Delivering Nucleic Acids Intracellularly Induce Localized in Vivo Neovascularization. *Nature Materials* **2015**, *14* (5), 532–539.
- (158) Baati, T.; Al-Kattan, A.; Esteve, M. A.; Njim, L.; Ryabchikov, Y.; Chaspoul, F.; Hammami, M.; Sentis, M.; Kabashin, A. V.; Braguer, D. Ultrapure Laser-Synthesized Si-Based Nanomaterials for Biomedical Applications: In Vivo Assessment of Safety and Biodistribution. *Scientific Reports* **2016**, *6*, 25400.
- (159) Croissant, J. G.; Fatieiev, Y.; Khashab, N. M. Degradability and Clearance of Silicon, Organosilica, Silsesquioxane, Silica Mixed Oxide, and Mesoporous Silica Nanoparticles. *Advanced Materials* **2017**, *29* (9), 10.1002/adma.201604634.
- (160) Li, W.; Liu, Z.; Fontana, F.; Ding, Y.; Liu, D.; Hirvonen, J. T.; Santos, H. A. Tailoring Porous Silicon for Biomedical Applications: From Drug Delivery to

- Cancer Immunotherapy. *Advanced Materials* **2018**, 30 (24), 10.1002/adma.201703740.
- (161) Santos, H. A. (2014). *Porous Silicon for Biomedical Applications*. Woodhead Publishing.
- (162) Salonen, J.; Kaukonen, A. M.; Hirvonen, J.; Lehto, V. P. Mesoporous Silicon in Drug Delivery Applications. *Journal of Pharmaceutical Sciences* **2008**, 97 (2), 632–653.
- (163) Haidary, S. M.; Córcoles, E. P.; Ali, N. K. Nanoporous Silicon as Drug Delivery Systems for Cancer Therapies. *Journal of Nanomaterials* **2012**, 2012, 830503.
- (164) Santos, H. A.; Mäkilä, E.; Airaksinen, A. J.; Bimbo, L. M.; Hirvonen, J. Porous Silicon Nanoparticles for Nanomedicine: Preparation and Biomedical Applications. *Nanomedicine* **2014**, 9 (4), 535–554.
- (165) Venuta, A.; Wolfram, J.; Shen, H.; Ferrari, M. Post-Nano Strategies for Drug Delivery: Multistage Porous Silicon Microvectors. *Journal of Materials Chemistry B* **2017**, 5 (2), 207–219.
- (166) Savage, D. J.; Liu, X.; Curley, S. A.; Ferrari, M.; Serda, R. E. Porous Silicon Advances in Drug Delivery and Immunotherapy. *Current Opinion in Pharmacology* **2013**, 13 (5), 834–841.
- (167) Tasciotti, E.; Liu, X.; Bhavane, R.; Plant, K.; Leonard, A. D.; Price, B. K.; Cheng, M. M. C.; Decuzzi, P.; Tour, J. M.; Robertson, F.; Ferrari, M. Mesoporous Silicon Particles as a Multistage Delivery System for Imaging and Therapeutic Applications. *Nature Nanotechnology* **2008**, 3 (3), 151–157.
- (168) Park, J. H.; Gu, L.; von Maltzahn, G.; Ruoslahti, E.; Bhatia, S. N.; Sailor, M. J. Biodegradable Luminescent Porous Silicon Nanoparticles for in Vivo Applications. *Nature Materials* **2009**, 8 (4), 331–336.
- (169) Sviridov, A. P.; Andreev, V. G.; Ivanova, E. M.; Osminkina, L. A.; Tamarov, K. P.; Timoshenko, V. Y. Porous Silicon Nanoparticles as Sensitizers for Ultrasonic Hyperthermia. *Applied Physics Letters* **2013**, 103 (19), 193110.
- (170) Sviridov, A.; Tamarov, K.; Fesenko, I.; Xu, W.; Andreev, V.; Timoshenko, V.; Lehto, V. P. Cavitation Induced by Janus-like Mesoporous Silicon Nanoparticles Enhances Ultrasound Hyperthermia. *Frontiers in Chemistry* **2019**, 7, 393.
- (171) Anglin, E. J.; Cheng, L.; Freeman, W. R.; Sailor, M. J. Porous Silicon in Drug Delivery Devices and Materials. *Advanced Drug Delivery Reviews* **2008**, 60 (11), 1266–1277.
- (172) Hoang Thi, T. T.; Cao, V. du; Nguyen, T. N. Q.; Hoang, D. T.; Ngo, V. C.; Nguyen, D. H. Functionalized Mesoporous Silica Nanoparticles and Biomedical Applications. *Materials Science and Engineering C* **2019**, 99, 631–656.
- (173) Chen, W.; Glackin, C. A.; Horwitz, M. A.; Zink, J. I. Nanomachines and Other Caps on Mesoporous Silica Nanoparticles for Drug Delivery. *Accounts of Chemical Research* **2019**, 52 (6), 1531–1542.
- (174) Jung, Y.; Huh, Y.; Kim, D. Recent Advances in Surface Engineering of Porous Silicon Nanomaterials for Biomedical Applications. *Microporous and Mesoporous Materials* **2021**, 310, 110673.
- (175) Jakobsson, U.; Mäkilä, E.; Rahikkala, A.; Imlimthan, S.; Lampuoti, J.; Ranjan, S.; Heino, J.; Jalkanen, P.; Köster, U.; Mizohata, K.; Santos, H. A.; Salonen, J.; Airaksinen, A. J.; Sarparanta, M.; Helariutta, K. Preparation and in Vivo

- Evaluation of Red Blood Cell Membrane Coated Porous Silicon Nanoparticles Implanted with ¹⁵⁵Tb. *Nuclear Medicine and Biology* **2020**, 84–85, 102–110.
- (176) Rahikkala, A.; Fontana, F.; Bauleth-Ramos, T.; Correia, A.; Kemell, M.; Seitsonen, J.; Mäkilä, E.; Sarmiento, B.; Salonen, J.; Ruokolainen, J.; Hirvonen, J.; Santos, H. A. Hybrid Red Blood Cell Membrane Coated Porous Silicon Nanoparticles Functionalized with Cancer Antigen Induce Depletion of T Cells. *RSC Advances* **2020**, 10 (58), 35198–35205.
- (177) Zhang, H.; Cui, W.; Qu, X.; Wu, H.; Qu, L.; Zhang, X.; Mäkilä, E.; Salonen, J.; Zhu, Y.; Yang, Z.; Chen, D.; Santos, H. A.; Hai, M.; Weitz, D. A. Photothermal-Responsive Nanosized Hybrid Polymersome as Versatile Therapeutics Codelivery Nanovehicle for Effective Tumor Suppression. *Proceedings of the National Academy of Sciences of the United States of America* **2019**, 116 (16), 7744–7749.
- (178) Wang, C. F.; Sarparanta, M. P.; Mäkilä, E. M.; Hyvönen, M. L. K.; Laakkonen, P. M.; Salonen, J. J.; Hirvonen, J. T.; Airaksinen, A. J.; Santos, H. A. Multifunctional Porous Silicon Nanoparticles for Cancer Theranostics. *Biomaterials* **2015**, 48, 108–118.
- (179) Kumeria, T.; McInnes, S. J. P.; Maher, S.; Santos, A. Porous Silicon for Drug Delivery Applications and Theranostics: Recent Advances, Critical Review and Perspectives. *Expert Opinion on Drug Delivery* **2017**, 14 (12), 1407–1422.
- (180) Airaksinen, A. (2014). Theranostic Imaging with Porous Silicon. In L. Canham (Ed.). *Handbook of Porous Silicon* (pp 1-12). Springer International Publishing.
- (181) Ye, H. L.; Cai, S. J.; Li, S.; He, X. W.; Li, W. Y.; Li, Y. H.; Zhang, Y. K. One-Pot Microwave Synthesis of Water-Dispersible, High Fluorescence Silicon Nanoparticles and Their Imaging Applications in Vitro and in Vivo. *Analytical Chemistry* **2016**, 88 (23), 11631–11638.
- (182) Tu, C.; Ma, X.; Pantazis, P.; Kauzlarich, S. M.; Louie, A. Y. Paramagnetic, Silicon Quantum Dots for Magnetic Resonance and Two-Photon Imaging of Macrophages. *Journal of the American Chemical Society* **2010**, 132 (6), 2016–2023.
- (183) Dou, Y. K.; Shang, Y.; He, X. W.; Li, W. Y.; Li, Y. H.; Zhang, Y. K. Preparation of a Ruthenium-Complex-Functionalized Two-Photon-Excited Red Fluorescence Silicon Nanoparticle Composite for Targeted Fluorescence Imaging and Photodynamic Therapy in Vitro. *ACS Applied Materials and Interfaces* **2019**, 11 (15), 13954–13963.
- (184) Kharin, A. Y.; Lysenko, V. V.; Rogov, A.; Ryabchikov, Y. V.; Geloën, A.; Tishchenko, I.; Marty, O.; Sennikov, P. G.; Kornev, R. A.; Zavestovskaya, I. N.; Kabashin, A. V.; Timoshenko, V. Y. Bi-Modal Nonlinear Optical Contrast from Si Nanoparticles for Cancer Theranostics. *Advanced Optical Materials* **2019**, 7 (13), 1801728.
- (185) Brown, S. Photodynamic Therapy: Two Photons Are Better than One. *Nature Photonics* **2008**, 2 (7), 394–395.
- (186) Shen, Y.; Shuhendler, A. J.; Ye, D.; Xu, J. J.; Chen, H. Y. Two-Photon Excitation Nanoparticles for Photodynamic Therapy. *Chemical Society Reviews* **2016**, 45 (24), 6725–6741.
- (187) Zhou, J.; Yang, Y.; Zhang, C. Y. Toward Biocompatible Semiconductor Quantum

- Dots: From Biosynthesis and Bioconjugation to Biomedical Application. *Chemical Reviews* **2015**, *115* (21), 11669–11717.
- (188) Atkins, T. M.; Thibert, A.; Larsen, D. S.; Dey, S.; Browning, N. D.; Kauzlarich, S. M. Femtosecond Ligand/Core Dynamics of Microwave-Assisted Synthesized Silicon Quantum Dots in Aqueous Solution. *Journal of the American Chemical Society* **2011**, *133* (51), 20664–20667.
- (189) Fojtik, A.; Giersig, M.; Henglein, A. Formation of Nanometer-Size Silicon Particles in a Laser Induced Plasma in SiH₄. *Berichte der Bunsengesellschaft für physikalische Chemie* **1993**, *97* (11), 1493–1496.
- (190) Liu, X.; Zhang, Y.; Yu, T.; Qiao, X.; Gresback, R.; Pi, X.; Yang, D. Optimum Quantum Yield of the Light Emission from 2 to 10 Nm Hydrosilylated Silicon Quantum Dots. *Particle and Particle Systems Characterization* **2016**, *33* (1), 44–52.
- (191) Zhong, Y.; Peng, F.; Bao, F.; Wang, S.; Ji, X.; Yang, L.; Su, Y.; Lee, S. T.; He, Y. Large-Scale Aqueous Synthesis of Fluorescent and Biocompatible Silicon Nanoparticles and Their Use as Highly Photostable Biological Probes. *Journal of the American Chemical Society* **2013**, *135* (22), 8350–8356.
- (192) Zhong, Y.; Sun, X.; Wang, S.; Peng, F.; Bao, F.; Su, Y.; Li, Y.; Lee, S. T.; He, Y. Facile, Large-Quantity Synthesis of Stable, Tunable-Color Silicon Nanoparticles and Their Application for Long-Term Cellular Imaging. *ACS Nano* **2015**, *9* (6), 5958–5967.
- (193) Pi, X. D.; Liptak, R. W.; Deneen Nowak, J.; Wells, N. P.; Carter, C. B.; Campbell, S. A.; Kortshagen, U. Air-Stable Full-Visible-Spectrum Emission from Silicon Nanocrystals Synthesized by an All-Gas-Phase Plasma Approach. *Nanotechnology* **2008**, *19* (24), 245603.
- (194) Cao, Z.; Peng, F.; Hu, Z.; Chu, B.; Zhong, Y.; Su, Y.; He, S.; He, Y. In Vitro Cellular Behaviors and Toxicity Assays of Small-Sized Fluorescent Silicon Nanoparticles. *Nanoscale* **2017**, *9* (22), 7602–7611.
- (195) Ji, X.; Peng, F.; Zhong, Y.; Su, Y.; Jiang, X.; Song, C.; Yang, L.; Chu, B.; Lee, S. T.; He, Y. Highly Fluorescent, Photostable, and Ultrasmall Silicon Drug Nanocarriers for Long-Term Tumor Cell Tracking and in-Vivo Cancer Therapy. *Advanced Materials* **2015**, *27* (6), 1029–1034.
- (196) Tang, M.; Ji, X.; Xu, H.; Zhang, L.; Jiang, A.; Song, B.; Su, Y.; He, Y. Photostable and Biocompatible Fluorescent Silicon Nanoparticles-Based Theranostic Probes for Simultaneous Imaging and Treatment of Ocular Neovascularization. *Analytical Chemistry* **2018**, *90* (13), 8188–8195.
- (197) Zhou, Y.; Zhang, Y.; Zhong, Y.; Fu, R.; Wu, S.; Wang, Q.; Wang, H.; Su, Y.; Zhang, H.; He, Y. The in Vivo Targeted Molecular Imaging of Fluorescent Silicon Nanoparticles in *Caenorhabditis Elegans*. *Nano Research* **2018**, *11* (5), 2336–2346.
- (198) Lai, C. H.; Hütter, J.; Hsu, C. W.; Tanaka, H.; Varela-Aramburu, S.; De Cola, L.; Lepenies, B.; Seeberger, P. H. Analysis of Carbohydrate-Carbohydrate Interactions Using Sugar-Functionalized Silicon Nanoparticles for Cell Imaging. *Nano Letters* **2016**, *16* (1), 807–811.
- (199) Pang, J.; Su, Y.; Zhong, Y.; Peng, F.; Song, B.; He, Y. Fluorescent Silicon Nanoparticle-Based Gene Carriers Featuring Strong Photostability and Feeble

- Cytotoxicity. *Nano Research* **2016**, 9 (10), 3027–3037.
- (200) Zhang, L.; Ji, X.; Su, Y.; Zhai, X.; Xu, H.; Song, B.; Jiang, A.; Guo, D.; He, Y. Fluorescent Silicon Nanoparticles-Based Nanotheranostic Agents for Rapid Diagnosis and Treatment of Bacteria-Induced Keratitis. *Nano Research* **2021**, 14 (1), 52–58.
- (201) Xiao, L.; Gu, L.; Howell, S. B.; Sailor, M. J. Porous Silicon Nanoparticle Photosensitizers for Singlet Oxygen and Their Phototoxicity against Cancer Cells. *ACS Nano* **2011**, 5 (5), 3651–3659.
- (202) Kovalev, D.; Gross, E.; Künzner, N.; Koch, F.; Timoshenko, V. Y.; Fujii, M. Resonant Electronic Energy Transfer from Excitons Confined in Silicon Nanocrystals to Oxygen Molecules. *Physical Review Letters* **2002**, 89 (13), 1374011–1374014.
- (203) Osminkina, L. A.; Tamarov, K. P.; Sviridov, A. P.; Galkin, R. A.; Gongalsky, M. B.; Solovyev, V. v.; Kudryavtsev, A. A.; Timoshenko, V. Y. Photoluminescent Biocompatible Silicon Nanoparticles for Cancer Theranostic Applications. *Journal of Biophotonics* **2012**, 5 (7), 529–535.
- (204) Al-Kattan, A.; Ali, L. M. A.; Daurat, M.; Mattana, E.; Gary-Bobo, M. Biological Assessment of Laser-Synthesized Silicon Nanoparticles Effect in Two-Photon Photodynamic Therapy on Breast Cancer MCF-7 Cells. *Nanomaterials* **2020**, 10 (8), 1–11.
- (205) DeRosa, M. C.; Crutchley, R. J. Photosensitized Singlet Oxygen and Its Applications. *Coordination Chemistry Reviews* **2002**, 233–234, 351–371.
- (206) Lee, C.; Kim, H.; Hong, C.; Kim, M.; Hong, S. S.; Lee, D. H.; Lee, W. I. Porous Silicon as an Agent for Cancer Thermotherapy Based on Near-Infrared Light Irradiation. *Journal of Materials Chemistry* **2008**, 18 (40), 4790–4795.
- (207) Hong, C.; Lee, J.; Zheng, H.; Hong, S. S.; Lee, C. Porous Silicon Nanoparticles for Cancer Photothermotherapy. *Nanoscale Research Letters* **2011**, 6 (1), 321.
- (208) Gongalsky, M.; Gvindzhiliia, G.; Tamarov, K.; Shalygina, O.; Pavlikov, A.; Solovyev, V.; Kudryavtsev, A.; Sivakov, V.; Osminkina, L. A. Radiofrequency Hyperthermia of Cancer Cells Enhanced by Silicic Acid Ions Released during the Biodegradation of Porous Silicon Nanowires. *ACS Omega* **2019**, 4 (6), 10662–10669.
- (209) Tamarov, K. P.; Osminkina, L. A.; Zinovyev, S. v.; Maximova, K. A.; Kargina, J. v.; Gongalsky, M. B.; Ryabchikov, Y.; Al-Kattan, A.; Sviridov, A. P.; Sentis, M.; Ivanov, A. v.; Nikiforov, V. N.; Kabashin, A. v.; Timoshenko, V. Y. Radio Frequency Radiation-Induced Hyperthermia Using Si Nanoparticle-Based Sensitizers for Mild Cancer Therapy. *Scientific Reports* **2014**, 4, 7034.
- (210) Nikolaou, P.; Goodson, B. M.; Chekmenev, E. Y. NMR Hyperpolarization Techniques for Biomedicine. *Chemistry - A European Journal* **2015**, 21 (8), 3156–3166.
- (211) Halse, M. E. Perspectives for Hyperpolarisation in Compact NMR. *TrAC - Trends in Analytical Chemistry* **2016**, 83, 76–83.
- (212) Kwiatkowski, G.; Jähnig, F.; Steinhäuser, J.; Wespi, P.; Ernst, M.; Kozerke, S. Nanometer Size Silicon Particles for Hyperpolarized MRI. *Scientific Reports* **2017**, 7 (1), 7946.
- (213) Keshari, K. R.; Wilson, D. M. Chemistry and Biochemistry of ^{13}C Hyperpolarized

- Magnetic Resonance Using Dynamic Nuclear Polarization. *Chem Soc Rev* **2014**, 43 (5), 1627–1659.
- (214) Seo, H.; Choi, I.; Whiting, N.; Hu, J.; Luu, Q. S.; Pudakalakatti, S.; McCowan, C.; Kim, Y.; Zacharias, N.; Lee, S.; Bhattacharya, P.; Lee, Y. Hyperpolarized Porous Silicon Nanoparticles: Potential Theragnostic Material for ^{29}Si Magnetic Resonance Imaging. *ChemPhysChem* **2018**, 19 (17), 2143–2147.
- (215) Shulman, R. G.; Wyluda, B. J. Nuclear Magnetic Resonance of Si29 in N- and p-Type Silicon. *Physical Review* **1956**, 103 (4), 1127–1129.
- (216) Wang, Z. J.; Ohliger, M. A.; Larson, P. E. Z.; Gordon, J. W.; Bok, R. A.; Slater, J.; Villanueva-Meyer, J. E.; Hess, C. P.; Kurhanewicz, J.; Vigneron, D. B. Hyperpolarized ^{13}C MRI: State of the Art and Future Directions. *Radiology* **2019**, 291 (2), 273–284.
- (217) Aptekar, J. W.; Cassidy, M. C.; Johnson, A. C.; Barton, R. A.; Lee, M.; Ogier, A. C.; Vo, C.; Anahtar, M. N.; Ren, Y.; Bhatia, S. N.; Ramanathan, C.; Cory, D. G.; Hill, A. L.; Mair, R. W.; Rosen, M. S.; Walsworth, R. L.; Marcus, C. M. Silicon Nanoparticles as Hyperpolarized Magnetic Resonance Imaging Agents. *ACS Nano* **2009**, 3 (12), 4003–4008.
- (218) Atkins, T. M.; Cassidy, M. C.; Lee, M.; Ganguly, S.; Marcus, C. M.; Kauzlarich, S. M. Synthesis of Long T 1 Silicon Nanoparticles for Hyperpolarized ^{29}Si Magnetic Resonance Imaging. *ACS Nano* **2013**, 7 (2), 1609–1617.
- (219) Whiting, N.; Hu, J.; Shah, J. V.; Cassidy, M. C.; Cressman, E.; Millward, N. Z.; Menter, D. G.; Marcus, C. M.; Bhattacharya, P. K. Real-Time MRI-Guided Catheter Tracking Using Hyperpolarized Silicon Particles. *Scientific Reports* **2015**, 5, 12842.
- (220) Whiting, N.; Hu, J.; Zacharias, N. M.; Lokesh, G. L. R.; Volk, D. E.; Menter, D. G.; Rupaimoole, R.; Previs, R.; Sood, A. K.; Bhattacharya, P. Developing Hyperpolarized Silicon Particles for in Vivo MRI Targeting of Ovarian Cancer . *Journal of Medical Imaging* **2016**, 3 (3), 036001.
- (221) Singh, D.; Dilnawaz, F.; Sahoo, S. K. Challenges of Moving Theranostic Nanomedicine into the Clinic. *Nanomedicine* **2020**, 15 (2), 111–114.
- (222) Devi, M. G.; Balachandran, S. A Review on Synthesis, Characterization and Applications of Silica Particles. *International Journal of Advanced Engineering Research and Technology (IJAERT)* **2016**, 4 (7), 249–254.
- (223) Fu, S.-Y.; Feng, X.-Q.; Lauke, B.; Mai, Y.-W. Effects of Particle Size, Particle/Matrix Interface Adhesion and Particle Loading on Mechanical Properties of Particulate–Polymer Composites. *Composites Part B: Engineering* **2008**, 39 (6), 933–961.
- (224) Fu, S.; Sun, Z.; Huang, P.; Li, Y.; Hu, N. Some Basic Aspects of Polymer Nanocomposites: A Critical Review. *Nano Materials Science* **2019**, 1 (1), 2–30.
- (225) Hanemann, T.; Szabó, D. V. Polymer-Nanoparticle Composites: From Synthesis to Modern Applications. *Materials* **2010**, 3 (6), 3468–3517.
- (226) Pureskiy, N.; Ionov, L. Synthesis of Robust Raspberry-like Particles Using Polymer Brushes. *Langmuir* **2011**, 27 (6), 3006–3011.
- (227) Ming, W.; Wu, D.; Van Benthem, R.; De With, G. Superhydrophobic Films from Raspberry-like Particles. *Nano Letters* **2005**, 5 (11), 2298–2301.
- (228) Ebert, D.; Bhushan, B. Durable Lotus-Effect Surfaces with Hierarchical Structure

- Using Micro- and Nanosized Hydrophobic Silica Particles. *Journal of Colloid and Interface Science* **2012**, 368 (1), 584–591.
- (229) Li, X. M.; Reinhoudt, D.; Crego-Calama, M. What Do We Need for a Superhydrophobic Surface? A Review on the Recent Progress in the Preparation of Superhydrophobic Surfaces. *Chemical Society Reviews* **2007**, 36 (8), 1350–1368.
- (230) Subhash Latthe, S.; Basavraj Gurav, A.; Shridhar Maruti, C.; Shrikant Vhatkar, R. Recent Progress in Preparation of Superhydrophobic Surfaces: A Review. *Journal of Surface Engineered Materials and Advanced Technology* **2012**, 02 (02), 76–94.
- (231) Hu, C.; West, K. R.; Scherman, O. A. Hollow Mesoporous Raspberry-like Colloids with Removable Caps as Photoresponsive Nanocontainers. *Nanoscale* **2016**, 8 (15), 7840–7844.
- (232) Li, D.; Zhu, Y.; Mao, C. One-Pot Synthesis of Surface Roughness Controlled Hollow Silica Spheres with Enhanced Drug Loading and Release Profiles under Ambient Conditions in Aqueous Solutions. *Journal of Materials Chemistry B* **2013**, 1 (40), 5515–5520.
- (233) Liu, S.; Latthe, S. S.; Yang, H.; Liu, B.; Xing, R. Raspberry-like Superhydrophobic Silica Coatings with Self-Cleaning Properties. *Ceramics International* **2015**, 41 (9), 11719–11725.
- (234) Blanckenberg, A.; Malgas-Enus, R. Raspberry-like Gold-Decorated Silica (SSx–AMPS–Au) Nanoparticles for the Reductive Discoloration of Dyes. *SN Applied Sciences* **2019**, 1 (7), 787.
- (235) Chen, Z.; Xu, J.; Xiang, X.; Ren, D.; Chen, N.; Ye, Z.; Li, X.; Ma, S.; Chen, Q. Facile One-Step Dialysis Strategy for Preparation of Porous Silica Nanoparticles with Rough Surface. *Nano* **2020**, 15 (3), 7–14.
- (236) Blander, M.; Katz, J. L. Bubble Nucleation in Liquids. *AIChE Journal* **1975**, 21 (5), 833–848.
- (237) Mukai, K. (2005). Interfacial Phenomena, Metals Processing and Properties. In S. Seetharaman (Ed.). *Fundamentals of Metallurgy* (pp 237–269). Woodhead Publishing.
- (238) Volmer, M. Über Keimbildung Und Keimwirkung Als Spezialfälle Der Heterogenen Katalyse. *Zeitschrift für Elektrochemie* **1929**, 35 (9), 555–561.
- (239) Fletcher, N. H. Size Effect in Heterogeneous Nucleation. *The Journal of Chemical Physics* **1958**, 29 (3), 572–576.
- (240) Liu, Q.; Zhu, Y.; Yang, G.; Yang, Q. Nucleation Thermodynamics inside Micro/Nanocavity. *Journal of Materials Science and Technology* **2008**, 24 (2), 183–186.
- (241) Costeux, S. CO₂-Blown Nanocellular Foams. *Journal of Applied Polymer Science* **2014**, 131 (23), 10.1002/app.41293.
- (242) Liu, S.; DuVigneau, J.; Vancso, G. J. Nanocellular Polymer Foams as Promising High Performance Thermal Insulation Materials. *European Polymer Journal* **2015**, 65, 33–45.
- (243) Jacobs, L. J. M.; Kemmere, M. F.; Keurentjes, J. T. F. Sustainable Polymer Foaming Using High Pressure Carbon Dioxide: A Review on Fundamentals, Processes and Applications. *Green Chemistry* **2008**, 10 (7), 731–773.
- (244) Sauceau, M.; Fages, J.; Common, A.; Nikitine, C.; Rodier, E. New Challenges in

- Polymer Foaming: A Review of Extrusion Processes Assisted by Supercritical Carbon Dioxide. *Progress in Polymer Science (Oxford)* **2011**, 36 (6), 749–766.
- (245) Lee, L. J.; Zeng, C.; Cao, X.; Han, X.; Shen, J.; Xu, G. Polymer Nanocomposite Foams. *Composites Science and Technology* **2005**, 65 (15-16 SPEC. ISS.), 2344–2363.
- (246) Liu, S. (2017). Designer Nanoparticles as Efficient Nucleation Agents in Polymer Foaming. University of Twente. <https://doi.org/10.3990/1.9789036544023>
- (247) Colton, J. S.; Suh, N. P. The Nucleation of Microcellular Thermoplastic Foam with Additives: Part I: Theoretical Considerations. *Polymer Engineering & Science* **1987**, 27 (7), 485–492.
- (248) Colton, J. S.; Suh, N. P. Nucleation of Microcellular Foam: Theory and Practice. *Polymer Engineering & Science* **1987**, 27 (7), 500–503.
- (249) Colton, J. S.; Suh, N. P. The Nucleation of Microcellular Thermoplastic Foam with Additives: Part II: Experimental Results and Discussion. *Polymer Engineering & Science* **1987**, 27 (7), 493–499.
- (250) Colton, J. S.; Suh, N. P. Nucleation of Microcellular Foam: Theory and Practice. *Polymer Engineering & Science* **1987**, 27 (7), 500–503.
- (251) Colton, J. S.; Suh, N. P. The Nucleation of Microcellular Thermoplastic Foam with Additives: Part I: Theoretical Considerations. *Polymer Engineering & Science* **1987**, 27 (7), 485–492.
- (252) Colton, J. S.; Suh, N. P. The Nucleation of Microcellular Thermoplastic Foam with Additives: Part II: Experimental Results and Discussion. *Polymer Engineering & Science* **1987**, 27 (7), 493–499.
- (253) Zhai, W.; Yu, J.; Wu, L.; Ma, W.; He, J. Heterogeneous Nucleation Uniformizing Cell Size Distribution in Microcellular Nanocomposites Foams. *Polymer* **2006**, 47 (21), 7580–7589.
- (254) Velasco, J. I.; Antunes, M.; Ayyad, O.; López-Cuesta, J. M.; Gaudon, P.; Saiz-Arroyo, C.; Rodríguez-Pérez, M. A.; de Saja, J. A. Foaming Behaviour and Cellular Structure of LDPE/Hectorite Nanocomposites. *Polymer* **2007**, 48 (7), 2098–2108.
- (255) Shen, J.; Zeng, C.; Lee, L. J. Synthesis of Polystyrene-Carbon Nanofibers Nanocomposite Foams. *Polymer* **2005**, 46 (14), 5218–5224.
- (256) Zeng, C.; Han, X.; Lee, L. J.; Koelling, K. W.; Tomasko, D. L. Polymer-Clay Nanocomposite Foams Prepared Using Carbon Dioxide. *Advanced Materials* **2003**, 15 (20), 1743–1747.
- (257) Famili, M. H. N.; Janani, H.; Enayati, M. S. Foaming of a Polymer-Nanoparticle System: Effect of the Particle Properties. *Journal of Applied Polymer Science* **2011**, 119 (5), 2847–2856.
- (258) Chen, L.; Ozisik, R.; Schadler, L. S. The Influence of Carbon Nanotube Aspect Ratio on the Foam Morphology of MWNT/PMMA Nanocomposite Foams. *Polymer* **2010**, 51 (11), 2368–2375.
- (259) Goren, K.; Chen, L.; Schadler, L. S.; Ozisik, R. Influence of Nanoparticle Surface Chemistry and Size on Supercritical Carbon Dioxide Processed Nanocomposite Foam Morphology. *Journal of Supercritical Fluids* **2010**, 51 (3), 420–427.
- (260) Urbanczyk, L.; Calberg, C.; Detrembleur, C.; Jérôme, C.; Alexandre, M. Batch Foaming of SAN/Clay Nanocomposites with ScCO₂: A Very Tunable Way of

- Controlling the Cellular Morphology. *Polymer* **2010**, *51* (15), 3520–3531.
- (261) Harikrishnan, G.; Patro, T. U.; Unni, A. R.; Khakhar, D. V. Clay Nanoplatelet Induced Morphological Evolutions during Polymeric Foaming. *Soft Matter* **2011**, *7* (15), 6801–6804.
- (262) Liu, S.; Eijkelenkamp, R.; Duvigneau, J.; Vancso, G. J. Silica-Assisted Nucleation of Polymer Foam Cells with Nanoscopic Dimensions: Impact of Particle Size, Line Tension, and Surface Functionality. *ACS Applied Materials and Interfaces* **2017**, *9* (43), 37929–37940.
- (263) Liu, S.; Yin, S.; Duvigneau, J.; Vancso, G. J. Bubble Seeding Nanocavities: Multiple Polymer Foam Cell Nucleation by Polydimethylsiloxane-Grafted Designer Silica Nanoparticles. *ACS Nano* **2020**, *14* (2), 1623–1634.
- (264) Vancso, Gyula J.; Duvigneau, Joost; Nederkoorn, P.H.J.; Wassing, T. Polymer Foam Comprising a Polymer and Nanoparticles, and Nanoparticles for the Manufacture of Such Foam. WO2014073960, 2014.
- (265) Liu, S.; Zoetebier, B.; Hulsman, L.; Zhang, Y.; Duvigneau, J.; Vancso, G. J. Nanocellular Polymer Foams Nucleated by Core-Shell Nanoparticles. *Polymer* **2016**, *104*, 22–30.
- (266) Liu, S.; Pandey, A.; Duvigneau, J.; Vancso, J.; Snoeijer, J. H. Size-Dependent Submerging of Nanoparticles in Polymer Melts: Effect of Line Tension. *Macromolecules* **2018**, *51* (7), 2411–2417.
- (267) Laidler, K. J. A Glossary of Terms Used in Chemical Kinetics, Including Reaction Dynamics (IUPAC Recommendations 1996). *Pure and Applied Chemistry* **1996**, *68* (1), 149–192.
- (268) Bkell. Activation energy
https://commons.wikimedia.org/wiki/File:Activation_energy.svg (accessed 2021-09-06).
- (269) Li, H. H.; Yu, S. H. Recent Advances on Controlled Synthesis and Engineering of Hollow Alloyed Nanotubes for Electrocatalysis. *Advanced Materials* **2019**, *31* (38), 1803503.
- (270) Wang, J. L.; Ando, R. A.; Camargo, P. H. C. Investigating the Plasmon-Mediated Catalytic Activity of AgAu Nanoparticles as a Function of Composition: Are Two Metals Better than One? *ACS Catalysis* **2014**, *4* (11), 3815–3819.
- (271) Jia, C. J.; Schüth, F. Colloidal Metal Nanoparticles as a Component of Designed Catalyst. *Physical Chemistry Chemical Physics* **2011**, *13* (7), 2457–2487.
- (272) Liu, L.; Corma, A. Metal Catalysts for Heterogeneous Catalysis: From Single Atoms to Nanoclusters and Nanoparticles. *Chemical Reviews* **2018**, *118* (10), 4981–5079.
- (273) Song, H.; Rioux, R. M.; Hoefelmeyer, J. D.; Komor, R.; Niesz, K.; Grass, M.; Yang, P.; Somorjai, G. A. Hydrothermal Growth of Mesoporous SBA-15 Silica in the Presence of PVP-Stabilized Pt Nanoparticles: Synthesis, Characterization, and Catalytic Properties. *Journal of the American Chemical Society* **2006**, *128* (9), 3027–3037.
- (274) Banerjee, S.; Das, J.; Santra, S. Native Silica Nanoparticle Catalyzed Anti-Markovnikov Addition of Thiols to Inactivated Alkenes and Alkynes: A New Route to Linear and Vinyl Thioethers. *Tetrahedron Letters* **2009**, *50* (1), 124–127.
- (275) Banerjee, S.; Santra, S. Remarkable Catalytic Activity of Silica Nanoparticle in

- the Bis-Michael Addition of Active Methylene Compounds to Conjugated Alkenes. *Tetrahedron Letters* **2009**, 50 (18), 2037–2040.
- (276) Alvarez, S. G.; Hasegawa, S.; Hirano, M.; Komiya, S. Michael Reactions Promoted by H1-O-Enolatoruthenium(II) Complexes Derived from Ru(Cod)(Cot), Diphosphine, and Dimethyl Malonate. *Tetrahedron Letters* **1998**, 39 (29), 5209–5212.
- (277) Ranu, B. C.; Banerjee, S. Ionic Liquid as Catalyst and Reaction Medium. The Dramatic Influence of a Task-Specific Ionic Liquid, [BmIm]OH, in Michael Addition of Active Methylene Compounds to Conjugated Ketones, Carboxylic Esters, and Nitriles. *Organic Letters* **2005**, 7 (14), 3049–3052.
- (278) Ranu, B. C.; Banerjee, S.; Jana, R. Ionic Liquid as Catalyst and Solvent: The Remarkable Effect of a Basic Ionic Liquid, [bmIm]OH on Michael Addition and Alkylation of Active Methylene Compounds. *Tetrahedron* **2007**, 63 (3), 776–782.
- (279) Kundu, S.; Roy, B.; Basu, B. Silica: An Efficient Catalyst for One-Pot Regioselective Synthesis of Dithioethers. *Beilstein Journal of Organic Chemistry* **2014**, 10, 26–33.
- (280) Nikoofar, K.; Khalili, Z. Nano-SiO₂: A Heterogeneous and Reusable Catalyst for the One-Pot Synthesis of Symmetrical and Unsymmetrical 3,3-Di(Aryl)Indolin-2-Ones under Solvent-Free Conditions. *Zeitschrift für Naturforschung - Section B Journal of Chemical Sciences* **2016**, 71 (1), 31–36.
- (281) Ramazani, A.; Dastanra, K.; Zeinali Nasrabadi, F.; Karimi, Z.; Rouhani, M.; Hosseini, M. Silica Nanoparticles as a High Efficient Catalyst for the One-Pot Synthesis of 3-Oxo-3-Phenylpropanamid Derivatives from Isocyanides, Phenylacetaldehyde and Secondary Amines. *Turkish Journal of Chemistry* **2012**, 36 (3), 467–476.
- (282) Uemichi, Y.; Kashiwaya, Y.; Tsukidate, M.; Ayame, A.; Kanoh, H. Product Distribution in Degradation of Polypropylene over Silica-Alumina and CaX Zeolite Catalysts. *Bulletin of the Chemical Society of Japan* **1983**, 56 (9), 2768–2773.
- (283) Songip, A. R.; Masuda, T.; Kuwahara, H.; Hashimoto, K. Test to Screen Catalysts for Reforming Heavy Oil from Waste Plastics. *Applied Catalysis B, Environmental* **1993**, 2 (2–3), 153–164.
- (284) Ishihara, Y.; Nanbu, H.; Ikemura, T.; Takesue, T. Catalytic Decomposition of Polyethylene Using a Tubular Flow Reactor System. *Fuel* **1990**, 69 (8), 978–984.
- (285) Sakata, Y.; Uddin, M. A.; Muto, A. Degradation of Polyethylene and Polypropylene into Fuel Oil by Using Solid Acid and Non-Acid Catalysts. *Journal of Analytical and Applied Pyrolysis* **1999**, 51 (1), 135–155.
- (286) Ishihara, Y.; Nanbu, H.; Saido, K.; Ikemura, T.; Takesue, T. Mechanism for Gas Formation in Polyethylene Catalytic Decomposition. *Polymer* **1992**, 33 (16), 3482–3486.
- (287) Masuda, T.; Kuwahara, H.; Mukai, S. R.; Hashimoto, K. Production of High Quality Gasoline from Waste Polyethylene Derived Heavy Oil over Ni-REY Catalyst in Steam Atmosphere. *Chemical Engineering Science* **1999**, 54 (13–14), 2773–2779.
- (288) Aguado, J.; Serrano, D. P.; Escola, J. M.; Garagorri, E.; Fernández, J. A. Catalytic Conversion of Polyolefins into Fuels over Zeolite Beta. *Polymer Degradation and*

- Stability* **2000**, 69 (1), 11–16.
- (289) Uemichi, Y.; Kashiwaya, Y.; Tsukidate, M.; Ayame, A.; Kanoh, H. Product Distribution in Degradation of Polypropylene over Silica-Alumina and CaX Zeolite Catalysts. *Bulletin of the Chemical Society of Japan* **1983**, 56 (9), 2768–2773.
- (290) Lee, K. H.; Noh, N. S.; Shin, D. H.; Seo, Y. Comparison of Plastic Types for Catalytic Degradation of Waste Plastics into Liquid Product with Spent FCC Catalyst. *Polymer Degradation and Stability* **2002**, 78 (3), 539–544.
- (291) De La Puente, G.; Arandes, J. M.; Sedran, U. A. Recycled Plastics in FCC Feedstocks: Specific Contributions. *Industrial and Engineering Chemistry Research* **1997**, 36 (11), 4530–4534.
- (292) Cardona, S. C.; Corma, A. Tertiary Recycling of Polypropylene by Catalytic Cracking in a Semibatch Stirred Reactor. Use of Spent Equilibrium FCC Commercial Catalyst. *Applied Catalysis B: Environmental* **2000**, 25 (2–3), 151–162.
- (293) Uemichi, Y.; Makino, Y.; Kanazuka, T. Degradation of Polyethylene to Aromatic Hydrocarbons over Metal-Supported Activated Carbon Catalysts. *Journal of Analytical and Applied Pyrolysis* **1989**, 14 (4), 331–344.
- (294) Zhang, Z.; Hirose, T.; Nishio, S.; Morioka, Y.; Azuma, N.; Ueno, A.; Ohkita, H.; Okada, M. Chemical Recycling of Waste Polystyrene into Styrene over Solid Acids and Bases. *Industrial and Engineering Chemistry Research* **1995**, 34 (12), 4514–4519.
- (295) Sakata, Y.; Azhar Uddin, M.; Muto, A.; Kanada, Y.; Koizumi, K.; Murata, K. Catalytic Degradation of Polyethylene into Fuel Oil over Mesoporous Silica (KFS-16) Catalyst. *Journal of Analytical and Applied Pyrolysis* **1997**, 43 (1), 15–25.
- (296) Inagaki, S.; Koiwai, A.; Suzuki, N.; Fukushima, Y.; Kuroda, K. Syntheses of Highly Ordered Mesoporous Materials, FSM-16, Derived from Kanemite. *Bulletin of the Chemical Society of Japan* **1996**, 69 (5), 1449–1457.

Chapter 3

Dispersion Stability of Nonspherical Silicon Nanoparticles: Impact of Solvent Selection and Storage Time

Long-term colloidal stability is of primary concern for numerous nanoparticle dispersion-based applications, such as inkjet printing. In order to assess printability of inks consisting of silicon nanoparticles (SiNPs) with complex agglomerated shapes in various alcohols and glycols, we studied the stability of the dispersions by several approaches. We utilized visual observations, optical turbidity profiling, analytical centrifugation (AC) and dynamic light scattering (for assessing hydrodynamically effective particle diameter values) to optimize colloidal stability under application relevant conditions. Predictions derived from Stokes' law and from AC results were compared to results by traditional (time-consuming) batch sedimentation experiments. We showed that although promising, neither the theoretical prediction using Stokes' law, nor accelerated measurements such as AC, capture particle behavior when considering particle agglomeration, backflow effects on the local particle concentration, and the possible long-term interactions between particles and solvents. For printing applications, long-term dispersion stability of SiNPs is very essential, which underlines the necessity of time-consuming methods for more complex particle geometries.

The contents of this Chapter will be published as: Yin, S.; Nguon, O. J.; Duvinneau, J.; Vancso, G. J. Dispersion Stability of Nonspherical Silicon Nanoparticles: Impact of Solvent Selection and Storage Time. Submitted

3.1 Introduction

The materials chemistry field of colloidal nanoparticles covers an extensive and exciting area of nanotechnology, and therefore, colloidal nanoparticles have been extensively studied in the past few decades.^{1,2} This is mainly attributed to their unique and attractive properties compared to their bulk counterparts. On the one hand, colloidal nanoparticles can behave similarly to molecules in solution while possessing properties of bulk materials. On the other hand, when particles become small enough, quantum effects sometimes result in unexpected material properties.³ These properties give colloidal nanoparticles great potential in several application areas, such as biomedicine, catalysis, energy storage, solar cells, and light-emitting diodes (LEDs).⁴⁻⁶

Colloidal nanoparticle synthesis traces back to the 1950s when Turkevich reported the solution-based synthesis of gold nanoparticles.⁷ In the 1960s, Werner Stöber⁸ and NASA⁹ reported the fabrication of colloidal silica and iron oxide suspensions, respectively. One of the first commercialization of colloidal nanoparticles was achieved in the 1980s when the cosmetics industry added zinc oxide and titanium oxide nanoparticles to sunscreen cream formulations.¹⁰ Currently, colloidal nanoparticles of various elements and compositions are readily prepared via solution-based bottom-up and solid-based top-down approaches.^{1,2,11} Additionally, colloidal nanoparticles are easily modified with different functional organic molecules or tethered polymers to either introduce new properties or enhance colloidal stability.¹² For example, hydrosilylation has been widely used to introduce small organic molecules onto Silicon-containing nanoparticles.¹³

Colloidal Silicon-containing nanoparticles are an exciting category of nanoparticles. Compared to its bulk form, nanosilicon possesses several new and exciting properties, such as photoluminescence (PL), antimicrobial activity, and size-dependent electronic bandgaps.¹⁴ These interesting properties make Silicon-containing nanoparticles a promising candidate as ink components for printing electronic devices.^{15,16} One crucial parameter for formulating silicon nanoparticle-based inks is the long-term colloidal stability.¹⁷

Much effort by scientists and engineers worldwide has been applied to enhancing colloidal stability and better understanding nanoparticle sedimentation behavior.¹⁸⁻²¹ Several factors influence colloidal stability, such as nanoparticle concentration, surface charge, particle size, size distribution, surface chemistry, solvent, and solvent viscosity.^{21,22} Stokes' law is a popular theory that is widely applied to predict nanoparticle

stability.^{23,24} It is commonly used to describe particle settling behavior in Newtonian fluids by simply monitoring the balance between the buoyant and gravitational forces. Stokes' law is only applicable to spherical particles and ignores the interaction between particles.

Figure 3.1 Images of silicon nanoparticles in (a) dispersed, (b) flocculated, and (c) sedimented states after suspension in ethanol, 1-hexane, and water, respectively, with a schematic drawing of the corresponding states (d-f).

Stable colloidal dispersions have great technological relevance in many application areas.^{25–27} In this study, we focused on Si nanoparticles dispersed in various solvents to obtain practical, relevant information about stability windows; such information includes choice of solvent, the influence of external fields (such as gravitational), and time. The targeted application area is the inkjet printing of Si nanoparticles on various substrates to form stable, patterned Si films for subsequent processing into electrical circuits, such as RF security tags. Here, we focus exclusively on colloidal stability as a key enabling parameter for inkjet printing approaches.¹⁷

Due to the extensive number of factors, such as particle size²⁸, shape, surface charge²⁹, and viscosity²⁴, that can influence colloidal stability and the constraints of the theories on colloidal stability, it is difficult to predict nanoparticle stability and sedimentation behavior accurately^{30,31}.

As a result, batch sedimentation testing is a commonly used method to address colloidal nanoparticle stability experimentally.^{32,33} In the batch sedimentation test, the settling behavior of particles with no influence other than the Earth's gravitational field is studied by storing the suspension in a vertical container. Several detection methods are

available to follow particles' sedimentation behavior in dispersion, e.g., photo/video capturing, UV-Vis spectroscopy, dynamic light scattering (DLS), and transmittance electron microscopy.^{33,34} One practical difficulty related to colloidal stability testing in a simple gravitational field is related to the (sometimes extremely) long time needed to obtain a result.

Figure 3.2 Schematic of analytical centrifugation. Colloidal suspensions in a transparent cuvette rotate at several thousand rpm to generate a centrifugal force. While turning, the cuvette passes through a light beam. A detector below the cuvette measures the transmitted light as a function of position within the cuvette at specified time intervals during centrifuge runs.

By applying a centrifugal field on colloidal suspensions, one can accelerate the sedimentation process and explore the effects of physical and chemical properties on nanoparticle colloidal stabilities. These methods can also help investigate the influence of additives, such as electrolytes and polymers, on colloidal stability.³⁵ Analytical centrifugation (AC) (see Figure 3.2) is similar to the widely used analytical ultracentrifugation (AUC). Compared to AUC experiments, AC experiments typically run at a lower rotation speed (i.e., a lower gravitational force), and have been widely utilized to study the long-term stability of suspensions. Recently, AC has been extended for quantitative studies of colloidal nanoparticle sedimentation and particle-particle interactions.^{36–38} AC has the advantage of enabling explorations of nanoparticle colloidal stability on a short timescale compared to batch sedimentation testing (matter of hours

versus months).

AC and the available theoretical sedimentation models are mainly used to study the particle sedimentation behavior of well-defined systems, i.e., particles with a narrow size distribution or known bimodal particle systems.^{36–38} Here, we explore the utilization of AC to study the stability of silicon nanoparticle dispersion with a much more complex shape and surface chemistry to evaluate its potential use and to speed up specific particle system stability tests. The motivation of this study, as previously mentioned, has been the development of silicon nanoparticle-based inks suitable for inkjet printing. Stability is defined here as a desirable shelf life exceeding two months. We investigate the sedimentation behavior of SiNPs in various alcohols and glycols by using Stokes' law and performing AC measurements. In addition, we report the results of batch sedimentation studies.

3.2 Results and Discussion

3.2.1 SiNP Characterization

We determined the particle geometry and surface chemistry by transmission electron microscope (TEM), dynamic light scattering (DLS), X-ray photoelectron spectroscopy (XPS), and Fourier-transform infrared (FTIR) spectroscopy prior to performing the sedimentation studies. Figure 3.3a shows an TEM image of SiNPs deposited on a carbon/copper grid. The magnified TEM image (Figure 3.3b) shows that the primary particles contain amorphous and crystalline domains. The crystalline domains have various orientations, with prominent [111] (0.313 nm) and [220] (0.210 nm) planes, as observed in the TEM image.³⁹ This results from the collisions of nucleating materials in the gas phase fusing to form primary particles during synthesis.⁴⁰

The TEM images reveal that at the edge of the SiNPs, there is a visible, thin amorphous shell with a thickness of approximately 5 Å. From complementary experiments (XPS and IR spectroscopy), we conclude that this layer consists of oxidized silicon, i.e., SiO₂. Due to the high reactivity of SiNPs surface to oxygen, the pristine SiNP surface was instantly oxidized upon exposure to air, leading to the observed Si/SiO₂ core-shell structure. This thin SiO₂ shell protects the SiNPs from further oxidation and maintains their chemical stability under ambient conditions.⁴¹ Furthermore, from Figure 3.3a, it is clear that the primary particles are aggregated through necking (sintering bridges) to form secondary particles consisting of several tens of primary particles. The primary SiNPs have a sphericity close to unity and an average diameter of 50 ± 17 nm

(see Figure 3.3c). Due to the aggregated structure of the SiNPs, characterization of the secondary particle size and shape by microscopy imaging was challenging (see Figure 3.3a and d).

Figure 3.3 a) TEM image of SiNPs deposited on a carbon/copper grid, b) magnified image of the area in the red box shown in (a), the inset shows a fast Fourier transform pattern, c) particle size distribution of the primary SiNPs ($n = 100$) and d) SEM image of SiNPs placed on a graphite holder.

Thus, alternative approaches for size determination, such as DLS, have been employed. Values of the hydrodynamic diameter of the SiNPs were obtained for aqueous dispersions. The diameters determined by TEM and DLS should not be the same value by definition, and we consider DLS data to be a good measure of the diameter of the agglomerated particles.

For the DLS measurements, SiNPs were dispersed in Milli-Q water at a concentration of 25 ppm via intense sonication. The hydrodynamic diameter of the diluted SiNPs in water (see Figure 3.4) shows a distribution ranging from 110 to 550 nm, with an average hydrodynamic diameter of 287 nm (PDI 0.235). We note that for the other solvents used the hydrodynamic radius distribution of the SiNPs was in the same range. For reasons of simplicity we therefore used the values obtained for the water based dispersions in the following calculations.

Figure 3.4 Hydrodynamic diameter obtained by DLS measurements of SiNPs dispersed in water at a concentration of 25 ppm.

Stokes' law was applied to calculate the sedimentation velocity (v) of SiNP in suspensions. The values of v of SiNPs in methanol, ethanol, 1-hexanol, isobutanol, ethylene glycol, and diethylene glycol under Earth's gravity (v_g) and accelerated centrifugal field ($1300 \times g$) (v_{ac}) are presented in Table 3.1. Moreover, the times (t) for SiNPs to settle 1 cm are shown, as well.

Table 3.1 The sedimentation velocity of SiNPs under the Earth's gravity (v_e) and in AC (v_{ac}); and the corresponding time for SiNPs to settle 1 cm t_e and t_{ac} . The values of the average hydrodynamic diameter of SiNPs from the DLS measurements were used for the calculations. The parameters used to perform the calculations can be found in Table S3.1.

	methanol	ethanol	1-hexanol	isobutanol	ethylene glycol	diethylene glycol
v_e (nm s ⁻¹)	40.6	27.6	1176	13.4	3.3	2.4
t_e (h)	69	100.5	237.0	206.8	853.5	1147.4
v_{ac} (μm s ⁻¹)	52.7	35.9	15.2	17.5	4.2	3.1
t_{ac} (min)	3.2	4.7	10.9	9.5	39.4	53.0

As previously mentioned, corresponding colloid stability theories often assume narrow (or even monomodal) size distributions. Due to the substantial width of the particle distribution functions obtained here, we speculate that the theory predictions such as Stokes' law could deviate from the actual sedimentation behavior. In sections 3.2 and 3.3 we will compare the results from Stokes' law predictions with the AC and the batch sedimentation tests.

Figure 3.5 a) Single reflection ATR-FTIR spectrum and b) XPS overview spectrum of SiNPs.

In addition to morphology, surface chemistry is also an essential factor that influences colloidal stability. We determined the surface composition of SiNPs by FTIR spectroscopy and XPS measurements. Figure 3.5a shows an infrared spectrum of the SiNPs. The sharp peak observed at 1058 cm⁻¹ in the FTIR spectrum corresponds to Si-O-Si stretching absorption, which agrees with the presence of the SiO₂ layer observed through the TEM analysis (see Figure 3.3a). The most interesting absorbance bands in Figure 3.5a are visible at 1970 cm⁻¹, 2081 cm⁻¹, 2098 cm⁻¹, and 2270 cm⁻¹, corresponding to the Si-H stretching vibrations of H-Si(Si₃), H-Si(Si₂O), H-Si(SiO₂), and H-Si(SiO₃) bonds, respectively.⁴² The presence of H-Si-O bonds indicates that not all the Si-H bonds were oxidized. It is worth noting that the small peak observed at 2918 cm⁻¹, ascribed to $\nu(\text{C-H})$ absorbance, indicates that organic contaminants are present at the particle surface.

Figure 3.6 a) Si 2p, b) O 1s and c) C 1s XPS core-level spectra of SiNPs. The dotted lines show the deconvolution fitting of the core-level spectra to identify the bonds present.

The XPS spectrum (Figure 3.5b) confirms that SiNPs contain Si, O, and C. The boron dopant (~ 190 eV) is not visible in the XPS spectrum. The missing B peak is ascribed to the relatively low doping level (10^{18} atom cm⁻³) and the tendency of B atoms to migrate to the SiNPs' cores.⁴³ In addition to the low B surface concentration, the overlap of the solid Si 2s band with the B 1s band makes it difficult to detect boron with XPS. According to the XPS analysis, the SiNPs consist of $\sim 26.4\%$ carbon atoms, $\sim 18.6\%$ oxygen atoms,

and 55.0% silicon atoms. We noted that the carbon content was too high to be ascribed to the organic contaminants typically observed solely in XPS measurements. Therefore, the C, O, and Si core-level spectra were examined in detail to determine the nature of the carbon content.

Figure 3.6 shows the Si 2p, O 1s, and C 1s core-level spectra of the SiNPs. In the Si 2p core-level spectrum (Figure 3.6a), the dominant bands observed are 99.16 eV and 99.77 eV, corresponding to the characteristic binding energies for elemental silicon.⁴⁴ The band at 102.68 eV, which corresponds to Si-O bonds, is expected due to the presence of the oxidized silicon layer.⁴⁴ This is confirmed by the peak at 532.27 eV in the O1s core-level spectrum (Figure 3.6b).⁴⁵ The observed difference between the Si-Si and Si-O peak areas in Figure 3.6a indicates that only a small amount of Si-Si bonds was oxidized. This low degree of oxidation is in agreement with the observed thickness of the oxide layer (5 Å) in the TEM images (see Figure 3.3). In the C 1s core spectrum (Figure 3.6c), most of the C atoms present were in the form of C-C/C-H (binding energy 284.87 eV), which is typical for organic contamination on the particle surface.⁴⁶ In addition, some C atoms were bonded to O (C-O/C=O binding energies of 286.48 eV, 289.09 eV, and 534 eV, see Figure 3.6b and Figure 3.6c).⁴⁶ The missing Si-C peak in both the Si and C 1s core-level spectra (100.4 eV and 283.1 eV) indicates that there is no traceable C-Si bonding. Based on these results, we conclude that the 26.4% carbon content measured in XPS originates from the presence of organic contamination that is presumably partially present at the particle surface.

Thus, in addition to the irregular shape and broad size distribution, the complex surface chemistry of the SiNPs could make any theoretical prediction of their sedimentation behavior in different solvents deviate from the actual situation. Therefore, we employed AC and batch sedimentation measurements to assess the colloidal stability of the SiNPs in a selection of various alcohols and glycols. The results are presented and discussed in the next section.

3.2.2 AC to Study SiNP Sedimentation Behavior in Various Solvents

In this section, we discuss the results of the sedimentation experiments under centrifugal force and in the gravitational field. First, we discuss data obtained by an analytical centrifuge. Figure 3.7 shows the temporal evolution of the light transmittance of 0.5 wt% SiNP suspensions in methanol, 1-hexanol, ethylene glycol, ethanol, isobutanol, and diethylene glycol obtained by AC measurements. To quantify the particle sedimentation from the analytical centrifuge results, the instability indexes of SiNPs in different solvents were extrapolated from the light transmittance profiles of the

suspensions between $r = 115$ mm and $r = 125$ mm (see Figure 3.8). One can readily observe that the SiNP dispersion in ethylene glycol and diethylene glycol has the best colloidal stability among the tested solvents under the centrifugal force field used. The instability index for ethylene glycol and diethylene glycol suspensions is well below 0.02 throughout the AC experiment. This means that even after 10 h of centrifugation, most of the particles remained well dispersed in ethylene glycol and diethylene glycol.

Figure 3.7 Time dependent AC light transmittance profile measurements of SiNPs dispersed in methanol (a), 1-hexanol (b), ethylene glycol (c), ethanol (d), isobutanol (e), and diethylene glycol. For each dispersion, the SiNP concentration was 0.5 wt%. The r indicates the distance to the rotation center. To assist the reader, the red arrow in each graph indicates the evolution of time.

Without the presence of electrolytes, van der Waals (vdW) attraction is one of the major causes of particle aggregation.⁴⁷ The vdW attraction between two identical microbodies in a dense medium can be quantified via the Lifshitz theory of vdW forces.⁴⁸ According to the Lifshitz theory and the Hamaker equation, the vdW force intensity strongly depends on the polarizability of the embedding medium.⁴⁹ From the Clausius-Mossotti equation, it is known that the polarizability $\alpha \propto (\epsilon - 1)/(\epsilon + 2)$ (ϵ is the relative permittivity/dielectric constant of the medium).⁵⁰ Therefore, if we only consider vdW forces, the attractive forces between particles in ethylene glycol ($\epsilon = 37.6$ at 303 K) and diethylene glycol ($\epsilon = 29.1$ at 303 K) are weaker than those of 1-hexanol and isobutanol ($\epsilon = 12.7$ and $\epsilon = 17.4$ at 303 K, respectively). This theory would predict that the particles in ethylene glycol and diethylene glycol are less susceptible to aggregation. Additionally, the relatively high viscosities of ethylene glycol and diethylene glycol (16.3 mPa·s and 21.8 mPa·s at room temperature, respectively) reduced Brownian motion, i.e., reduce the

collision rate between particles. Thus, weak vdW attraction and a low collision rate between SiNPs reduce aggregation in these solvents.⁴⁹ The high viscosity also results in a large friction drag force that acts on the settling particles against the settling direction. A considerable friction drag effectively reduces the sedimentation velocity for the particles in the suspension.²⁴ Therefore, when suspended in ethylene glycol and diethylene glycol, the agglomeration rate and sedimentation velocity of the SiNPs should be significantly reduced in the centrifugal field (AC). These predictions corroborate the observations satisfactorily. Only a tiny fraction of the particles/agglomerates with large radii sedimented, and the small particles remained dispersed for a relatively long time.

Figure 3.8 Instability index values of SiNPs dispersed in methanol, ethanol, 1-hexanol, isobutanol, ethylene glycol, and diethylene glycol between $r = 115$ mm and $r = 125$ mm plotted against time.

Methanol and ethanol ($\epsilon=31.7$ and $\epsilon=23.6$ at 303 K, respectively) have dielectric constants comparable to those of glycols, indicating relatively weak vdW attraction between particles compared to 1-hexanol and isobutanol. We observed a fast and nearly uniform concentration decrease along the length of the test tubes for methanol and ethanol suspensions during the AC measurements. The light transmittance for methanol and ethanol increased to more than 80% within one hour and remained constant for the rest of the AC measurements. Therefore, most of the particles in methanol and ethanol sedimented within one hour after the centrifugal force field was applied and these dispersions were considered to be unstable. Similar to those of glycols, the high dielectric constants of methanol and ethanol result in insufficient repulsive forces to successfully stabilize the respective SiNP dispersions. The relatively low viscosities of methanol and ethanol (0.6 mPa·s and 1.2 mPa·s at room temperature, respectively) are ineffective in reducing Brownian motion. As a result, the SiNPs in methanol and ethanol have more frequent collisions, eventually leading to particle aggregation. Additionally, the relatively low viscosities of ethanol and methanol result in a smaller friction drag force. The low friction drag results in an increased sedimentation velocity for the particles dispersed in

methanol/ethanol compared to those dispersed in ethylene glycol and diethylene glycol. From the transmittance and instability index profiles of the SiNP methanol and ethanol dispersions, it is obvious that the particle concentrations (light transmittance) decreased much more slowly at the early stages of the sedimentation process and decreased at a faster rate as time proceeded. This observation is explained by realizing that smaller particles and solvent molecules behave similarly to an effective viscous fluid.⁵¹ This fluid provides a higher friction drag force that slows down sedimentation and generates a backflow when large particles/aggregates move towards the bottom.⁵² As a result of the backflow, smaller particles flow upwards together with the solvent molecules, resulting in a uniform decrease in particle concentration over the sample length instead of hard-sphere sedimentation.⁵² For ethylene glycol and diethylene glycol-based SiNP suspensions, we did not observe a uniform decrease in particle concentration due to the high effective viscosity, which suppressed the backflow.⁵²

For 1-hexanol and isobutanol SiNP suspensions, the temporal evolution of light transmittance profiles suggests that the particle sedimentation process in these suspensions can be interpreted by a combination of the effects that govern the settling behavior in ethylene glycol/diethylene glycol and methanol/ethanol. At early stages of particle sedimentation, the effective viscosity of the suspensions is high enough to suppress/reduce backflow, resulting in a sedimentation profile similar to that of glycols.^{51,53} As the particle concentration decreases and large particles settled to the bottom during the AC measurement, the suspension's effective viscosity decreases, resulting in an increased backflow that reduces particle sedimentation. Therefore, for 1-hexanol and isobutanol SiNP dispersions, the sedimentation shifts from glycol-like behavior during the early stages of the experiment to methanol-like behavior, and uniform particle concentration decreases during the later stages of the measurement.

The AC results shown here suggest that solvents such as ethylene glycol and diethylene glycol provide the best colloidal stability for the SiNPs, which is in good agreement with Stokes' Law predictions (see Table 3.1). Therefore, AC is a useful tool for analyzing the colloidal stability of particle suspensions related to viscosities and densities. However, to determine the shelf life of particle suspensions, other factors like aggregation, chemical stability are also crucial and should not be ignored. In the next section, we will compare the AC stability tests with batch sedimentation tests.

3.2.3 Batch Sedimentation Evaluation of SiNP Dispersions

Figure 3.9 shows a series of images of the batch sedimentation measurements of SiNPs dispersed in methanol, ethanol, 1-hexanol, isobutanol, ethylene glycol, and

diethylene glycol recorded over 90 days. During these experiments, only gravitational forces were present. For the SiNP dispersions in isobutanol and 1-hexanol, the layer near the liquid-gas interface became brighter at days 5 and 10, respectively. Following these initial changes, the SiNP dispersions in isobutanol and 1-hexanol remained unchanged until day 40. After 40 days, clear sedimentation was observed and progressed over time. We note that the camera could not capture particle sedimentation at the bottom of the vials for isobutanol and 1-hexanol and that these results reflect observations made during our regular visual inspections. For the isobutanol and 1-hexanol SiNP dispersions, we explain these results by observing the initial sedimentation of larger particles (< 10 days), after which the smaller NPs were relatively stable for a few weeks (< 40 days) until they eventually agglomerated and the dispersion became unstable (> 40 days).

Figure 3.9 Images of batch sedimentation measurements of SiNP suspensions in methanol, ethanol, 1-hexanol, isobutanol, ethylene glycol, and diethylene glycol recorded with a surveillance camera for 90 days.

For the SiNP dispersions in methanol and ethanol, we noticed no significant sedimentation of particles or changes in the dispersions' appearance during the observation interval. Due to the relatively low viscosity of methanol and ethanol (compared to the other solvents used), the larger particles in methanol and ethanol sedimented much faster, transitioning from the more homogenous, stable dispersion at the start of the experiment.⁵¹ In addition, it is known that the drag force is proportional to

the solvent viscosity,²⁴ i.e., the particles that remain in the ethanol and methanol suspensions should have smaller hydrodynamic diameters than those in isobutanol, 1-hexanol, ethylene glycol, and diethylene glycol after the larger particles settled. These smaller particles need more time to agglomerate and reach a critical size before the dispersion becomes unstable.²⁴ According to Stokes' law predictions (see Table 3.1), even the smallest particles in methanol and ethanol should have settled at least 1 cm after 16 and 23 days, respectively. However, Stokes' law is only applicable for spherical particles, and as shown in Figure 3.3, the SiNPs used in this study are clearly not spherical. Due to the aggregated morphology of the SiNPs, the real gravitational force and drag force can deviate from the theoretical values. Moreover, the alcohol molecules like methanol and ethanol can bond (hydrogen bonding) with their constituent oxygen atoms to the particle surface to form a solvation shell.⁵⁴ This solvation shell could raise the solvation force between particles and effectively reduce the agglomeration rate. This explains why the dispersions of SiNPs in methanol and ethanol were stable for the entire duration of the batch sedimentation experiments.

The results obtained from the batch sedimentation experiments seem to also differ from the results of the AC measurements of the methanol and ethanol SiNP dispersions. When the suspensions are in a centrifugal field, the gravitational force and friction drag increase, resulting in increased sedimentation velocity. However, the excess pressure applied to the suspension from AC could promote particle aggregation, especially for low-density solvents like methanol and ethanol.⁵⁴ Moreover, we speculate that the Brownian motion, which solely depends on particle size and fluid properties, was not influenced by the centrifugal field.²⁴ Thus, in AC measurements, particle collision and agglomeration resulting from Brownian motion are not enhanced. As such, the influence of Brownian motion on colloidal stability is not captured by the AC measurements in the RPM range we used.

The ethylene glycol and diethylene glycol SiNP suspensions were stable during the first 15 and 30 days of the batch sedimentation experiments, respectively. For ethylene glycol, the first trace of sedimentation was observed on day 15, followed by relatively rapid clearance of SiNPs from the dispersion in the following days. On day 40, which is only 25 days after the first trace of sedimentation, most of the SiNPs in ethylene glycol settled at the bottom of the test vial as a thick layer of SiNPs. The supernatant of the suspension was almost transparent. We observed similar behavior for SiNPs dispersed in diethylene glycol, for which the first signs of particle sedimentation were observed at day 30, and most of the particles were sedimented at day 50.

A striking difference that was observed in the SiNP dispersion stability in ethylene glycol and diethylene glycol during AC and batch sedimentation experiments was not expected based on the initial observations of the AC measurements and the accompanying explanation for the high dispersion stability.^{23,24} In addition, unlike for methanol and ethanol suspensions, Stokes' law overestimated the particle stability in ethylene glycol and diethylene glycol. According to Stokes' law predictions, the smallest particles in the ethylene glycol and diethylene glycol will take 197 and 265 days to settle over 1 cm under the Earth's gravity. Two hydroxyl groups in the glycol molecules may bond to different particles (e.g., via hydrogen bonding) and act as a bridging agent. The bridging effect would accelerate particle aggregation and sedimentation. In the next section, the colloidal dispersion stability is investigated in more depth to explain the observed poor stability of the SiNP dispersion in ethylene glycol and diethylene glycol.

3.2.4 Ethylene Glycol and Diethylene Glycol Stability in the Presence of SiNPs

The supernatants from ethylene glycol and diethylene glycol SiNP suspensions were diluted 10 times with Milli-Q water and measured with a pH meter at days 30 and 90. The pH decreased from 5.9 to 5.2 and 6.1 to 5.5 for ethylene glycol and diethylene glycol supernatants, respectively. The changes in pH over time indicated a possible change in the supernatant composition, i.e., the solvent composition, which could explain the unexpected sedimentation behavior for the SiNPs in ethylene glycol and diethylene glycol. To further elucidate the reason behind the abnormally fast sedimentation of the ethylene glycol and diethylene glycol suspensions during the batch sedimentation experiments, the supernatants of ethylene glycol and diethylene glycol suspensions were collected and characterized by FTIR and ion chromatography (IC).

Figure 3.10a shows FTIR spectra of the ethylene glycol and diethylene glycol supernatants collected on day 90. For comparison, FTIR spectra of the pure solvents stored in glass vials for 90 days are also shown. From the FTIR spectra, it is readily observed that for both ethylene glycol and diethylene glycol, the spectra of the supernatants and the corresponding pure solvents are almost identical except for the presence of two small peaks at 1650 cm^{-1} and 1720 cm^{-1} , which correspond to C=C and C=O stretching absorbances, respectively.⁵⁵ The presence of the C=C and C=O groups could be ascribed to the oxidation products of ethylene glycol and diethylene glycol, such as formic acid, glycolic acid, and acetaldehyde.⁵⁶

Figure 3.10 Single reflection ATR-FTIR spectra of a) ethylene glycol and b) diethylene glycol supernatants collected on day 90 of the SiNP dispersion batch sedimentation experiment. FTIR spectra for the pure solvents stored in a glass bottle for 90 days are also shown.

To further clarify the potential presence of oxidation products in the supernatant, ion chromatography was applied. According to literature, the main oxidation products of ethylene glycol are oxalic acid, glycolic acid, and formic acid.⁵⁶ Therefore, the ion chromatograph was calibrated to look for the presence of the anions from the corresponding degradation products. The resulting chromatographs are shown in Figure 3.11.

Figure 3.11 Ion chromatography anion analysis for the supernatants of a) ethylene glycol and b) diethylene glycol collected at day 90 of the SiNPs dispersion batch sedimentation experiments.

In Figure 3.11, the presence of glycolic acid and formic acid in the supernatants of ethylene glycol and diethylene glycol is clearly visible. The chemical structure of formic acid and glycolic acid also explains the C=O and C=C absorbances observed with FTIR spectroscopy (see Figure 3.10). We note that no evidence of oxidation was observed with FTIR spectroscopy for the pure solvent stored in its original vial for the duration of the batch sedimentation experiments. These results confirm that ethylene glycol and diethylene glycol were partially oxidized/degraded in the presence of SiNPs during the

batch sedimentation experiment on a relatively short time scale. Consequently, the acidic degradation products that release free ions can be absorbed onto the SiNP surface and form an electric diffusion layer around the SiNPs. Through the degradation process, the increase in ion concentration decreases the electric double layer thickness, resulting in fast aggregation and sedimentation of the SiNPs.⁵⁷ In a simple control experiment, we slightly acidified freshly made SiNP dispersions in ethylene glycol and diethylene glycol dispersions, resulting in rapid destabilization of the respective dispersions. The reason why the SiNPs induced partial degradation of ethylene glycol and diethylene glycol remains unclear.

Overall, in combination with the previously mentioned limitations of AC to study complex particle dispersion stability, we conclude that although AC is a valuable and proven technique for reducing the time required for colloidal stability studies in research and product development,^{36–38} it has limitations. In particular, shortcomings must be considered when evidence of particle/solvent system chemical instability is sought for, that occurs on time scales that substantially exceed those of the AC measurements. Without prior knowledge of such processes, the more time-consuming batch sedimentation experiments remain of pivotal importance.

3.3 Conclusion

The colloidal stability of nonspherical SiNPs in various solvents was investigated by AC and batch sedimentation measurements. Due to the complex geometry and surface chemistry of SiNPs, differences in dispersion stability from Stokes' law predictions, AC and batch sedimentation measurements were observed for SiNP dispersions in various alcohols and glycols. These differences result from the applicability of Stokes' law and AC measurements on particles with complex geometry and surface chemistry. Both Stokes' law and AC focus on/magnify the influence of viscosity and density on the colloidal stability of particle suspensions. Other factors like i) the influence of Brownian motion on particle agglomeration and sedimentation, ii) the effect of backflow on local particle concentration, and iii) the possible long-term chemical interactions between particles and solvents are underestimated when using Stokes' law predictions or AC measurements. These results underline the importance of conducting time-consuming batch sedimentation experiments to determine the shelf life of colloidal dispersions. Furthermore, future efforts to speed up dispersion stability tests for more complex nanoparticle dispersions must be directed toward identifying accelerated test conditions where the impact of these effects are neglectable.

3.4 Materials and Methods

Materials. Boron-doped silicon nanoparticles with a boron doping level of 5×10^{18} atoms cm^{-3} were a gift from University Duisburg-Essen, Germany. The particles were kept under ambient conditions and used as received. The nanopowder was synthesized via a gas-phase route in a hot-wall reactor, allowing the large-scale production of nanomaterials. A detailed description of the synthesis was reported by Hülser et al.⁵⁸ From now on, we will refer to these nanoparticles as SiNPs. Analytical-grade absolute methanol, absolute ethanol, isobutanol, and acetonitrile were purchased from Merck (Darmstadt, Germany). 1-Hexanol (anhydrous, 99%), ethylene glycol (anhydrous, 99.8%), and diethylene glycol (ReagentPlus, 99%) were purchased from Sigma Aldrich (St. Louis, MO, USA). Milli-Q water was prepared by a Millipore Synergy System (Billerica, MA, USA). Unless otherwise mentioned, all chemicals were used as received.

Preparation of Colloidal Suspensions. Methanol, ethanol, isobutanol, 1-hexanol, ethylene glycol, and diethylene glycol were selected as solvents to prepare the SiNP dispersions to cover a broad range of dielectric constants and viscosities. The dispersions were prepared by dispersing 0.05 g of SiNPs in 9.95 g of each solvent mentioned above, followed by 3 h of sonication (BRANSON 2510, Canada) to form uniform suspensions. The dynamic viscosities of the prepared particle suspensions and viscosity of the pure solvents were measured by a digital viscometer (LVTDV-I, Brookfield Engineering, AMETEK, Berwyn, Pennsylvania, U.S.). Prior to the measurements, the solvents and suspensions were sealed in the bottle and placed in the fume hood for an hour to reach thermal equilibrium.

Characterization of Silicon Nanoparticles. Transmission electron microscopy (TEM) was performed by an FEI Tecnai 20 system (FEI, Eindhoven, the Netherlands). A few drops of diluted particles dispersed in ethanol were deposited on the carbon side of a carbon/copper grid (HC200-Cu) (EMS, Germany) before imaging. Scanning electron microscope (SEM) was performed by a JEOL Field Emission JSM-6330F system (JEOL Benelux, Nieuw-Vennep, the Netherlands). Fourier transform infrared (FTIR) spectra were collected with a Bruker ALPHA single attenuated total reflection (ATR) FTIR spectrometer equipped with an ATR single reflection diamond crystal (Bruker Optic GmbH, Ettlingen, Germany). FTIR spectra were collected in the range of $400\text{--}4000\text{ cm}^{-1}$ (spectral resolution of 4 cm^{-1} , 512 scans). The background spectra were recorded against air. The hydrodynamic radius of the SiNPs in Milli-Q water was determined using dynamic light scattering (DLS) with a Malvern Zetasizer Nano-ZS (Malvern Instruments, Malvern, United Kingdom). A PHI Quantera II (Physical Electronics, Minnesota, US)

equipped with a monochromatic Al K α X-ray source (1486.6 eV) was used to perform X-ray photoelectron spectroscopy (XPS). The angle for the X-ray beam and detector was set at 45°.

Stokes' Law Prediction. Stokes' law for spherical objects was applied to estimate the sedimentation velocity of SiNPs in as-prepared suspensions:

$$v = \frac{2r^2(\rho_2 - \rho_1)}{9\eta} \quad (1)$$

Where r is the average hydrodynamic radius of SiNPs (measured with DLS), ρ_1 and ρ_2 are the density of solvent and SiNPs, respectively. η is the dynamic viscosity of the suspensions.

Analytical Centrifugation. The centrifugal sedimentation experiments were performed using a low-velocity AC (LUMiFuge, LUM GmbH, Germany). The particle concentrations of the suspensions were monitored qualitatively by obtaining the transmitted light intensity against time and position over the sample length (see Figure 3.2). The particle suspensions were transferred into a disposable polycarbonate cell followed by insertion into the LUMiFuge. The LUMiFuge was set at 3000 rpm (~1300 g), and the data collection time was 12 h. The transmission profiles were collected every 5 minutes.

Instability Index. The value of the instability index can be calculated from the AC results.⁵⁹ The light transmittance of the sample at $t=0$ is defined as $T_1(r)$. r is the distance between a given position and the rotation center. The value of clarification (change of particle concentration) T_i^{diff} is defined as $T_i - T_1$. The total clarification ΔT_i is defined as the sum of T_i^{diff} from r_{min} to r_{max} ,

$$\Delta T_i = \sum_{j=r_{min}}^{r_{max}} T_{i,j}^{diff} \quad (2)$$

Where $r_{min}=115$ mm and $r_{max}=125$ mm.

The maximum clarification ΔT_{max} is defined as

$$\Delta T_{max} = \left(\sum_{j=r_{min}}^{r_{max}} T_{end,j} - T_{1,j} \right) * (j_{r_{max}} - j_{r_{min}}) \quad (3)$$

Where T_{end} is the light transmission of the cell with water. In our case, $\overline{T}_{end}$ is 1.

The instability index is defined as the change of the clarification divided by the maximum possible clarification.

$$Instability\ index = \frac{\Delta T_i}{\Delta T_{max}} \quad (4)$$

Batch Sedimentation Testing. The prepared particle suspensions were stored in glass vials with polypropylene caps. Subsequently, the vials were sealed with Parafilm to avoid evaporation and water absorption. The glass vials were stored in a fume hood and recorded with a surveillance camera at 24 fps to observe the sedimentation behavior of the prepared suspensions under standard gravity for 90 days.

Analysis of Supernatants. The supernatants from the SiNP/ethylene glycol and SiNP/diethylene glycol suspensions were collected and filtered with a 200 nm glass filter (Merck Millipore, US) to remove the suspended SiNPs. Then, the supernatants were analyzed with ATR FTIR spectroscopy as described above. The supernatants were diluted with Mili-Q water 1:1 v/v. The pH of the diluted supernatants was measured with a pH meter (S20 SevernEasyTM pH, METTLER TOLEDO, Columbus, Ohio, US). In addition, an ion chromatograph (ICS 90, Dionex/Thermo Fischer, Waltham, Massachusetts, US) equipped with CS 12A (cations) and AS 12A (anions) columns was used for the identification of degradation products in the supernatants. The eluent's working pressure was set to ~2000 psi with a flow rate of 0.5 ml min⁻¹. Before injection for ion chromatography, the supernatants were diluted 10 times with Milli-Q water to avoid overloading the columns.

3.5 Supporting Information

Table S3.1 Physical properties of the solvents and SiNPs used in this study. Dynamic viscosity is the viscosity of a 0.5 wt% SiNPs suspension in the respective solvent.

	density (kg m^{-3})	dielectric constant (303 K)	viscosity (mpa)	dynamic viscosity (mpa)
<i>methanol</i>	792 ⁶⁰	31.7 ⁶⁰	0.6	1.7
<i>ethanol</i>	789 ⁶⁰	23.6 ⁶⁰	1.2	2.5
<i>1-hexanol</i>	814 ⁶¹	12.7 ⁶²	4.7	5.8
<i>isobutanol</i>	802 ⁶³	17.4 ⁶⁴	4.0	5.1
<i>ethylene glycol</i>	1110 ⁶⁵	37.6 ⁶⁵	16.3	16.8
<i>diethylene glycol</i>	1120 ⁶⁵	29.1 ⁶⁵	21.8	22.4
<i>SiNPs</i>	2328	N/A	N/A	N/A

Table S3.2 The sedimentation velocity range of SiNPs under Earth's gravity (v_e) field and AC (v_{ac}); and the corresponding time for SiNPs to settle 1 cm t_e and t_{ac} . The minimum/maximum hydrodynamic diameter of SiNPs obtained by DLS measurements were used to calculate the range of v and t . The parameters used to perform the calculation are shown in Table S3.1.

	<i>methanol</i>	<i>ethanol</i>	<i>1-hexanol</i>	<i>isobutanol</i>	<i>ethylene glycol</i>	<i>diethylene glycol</i>
v_e (nm s^{-1})	7.3-138.8	5.0-94.6	2.1-40.1	2.4-46.0	0.6-11.1	0.5-8.3
t_e (h)	20-379	29.4-556.3	69.2-1311.8	60.4-1144.5	249.3-4723.3	335.2-6349.8
v_{ac} ($\mu\text{m s}^{-1}$)	9.5-180.5	6.5-123	2.8-52.1	3.2-59.8	0.8-14.5	0.6-10.8
t_{ac} (min)	0.9-17.5	1.4-25.7	3.2-60.5	2.8-52.8	11.5-218	15.5-293.1

3.6 References

- (1) Pellegrino, T.; Kudera, S.; Liedl, T.; Javier, A. M.; Manna, L.; Parak, W. J. On the Development of Colloidal Nanoparticles towards Multifunctional Structures and Their Possible Use for Biological Applications. *Small* **2005**, *1* (1), 48–63.
- (2) Lu, Z.; Yin, Y. Colloidal Nanoparticle Clusters: Functional Materials by Design. *Chemical Society Reviews* **2012**, *41* (21), 6874–6887.
- (3) Volokitin, Y.; Sinzig, J.; de Jongh, L. J.; Schmidt, G.; Vargaftik, M. N.; Moiseev, I. I. Quantum-Size Effects in the Thermodynamic Properties of Metallic

- Nanoparticles. *Nature* **1996**, 384 (6610), 621–623.
- (4) Wood, V.; Bulović, V. Colloidal Quantum Dot Light-Emitting Devices. *Nano Reviews* **2010**, 1 (1), 5202.
 - (5) Lohse, S. E.; Murphy, C. J. Applications of Colloidal Inorganic Nanoparticles: From Medicine to Energy. *Journal of the American Chemical Society* **2012**, 134 (38), 15607–15620.
 - (6) Talapin, D. v.; Lee, J. S.; Kovalenko, M. v.; Shevchenko, E. v. Prospects of Colloidal Nanocrystals for Electronic and Optoelectronic Applications. *Chemical Reviews* **2010**, 110 (1), 389–458.
 - (7) Turkevich, J.; Stevenson, P. C.; Hillier, J. A Study of the Nucleation and Growth Processes in the Synthesis of Colloidal Gold. *Discussions of the Faraday Society* **1951**, 11, 55–75.
 - (8) Stöber, W.; Fink, A.; Bohn, E. Controlled Growth of Monodisperse Silica Spheres in the Micron Size Range. *Journal of Colloid And Interface Science* **1968**, 26 (1), 62–69.
 - (9) Stephen, P. S. (1965). Low Viscosity Magnetic Fluid Obtained By the Colloidal Suspension of Magnetic Particles (U.S. Patent No. 3215572). U.S. Patent and Trademark Office. <https://patents.google.com/patent/US3215572A/en>
 - (10) Wang, S. Q.; Tooley, I. R. Photoprotection in the Era of Nanotechnology. *Seminars in cutaneous medicine and surgery* **2011**, 30 (4), 210–3.
 - (11) Wang, Y.; Xia, Y. Bottom-up and Top-down Approaches to the Synthesis of Monodispersed Spherical Colloids of Low Melting-Point Metals. *Nano Letters* **2004**, 4 (10), 2047–2050.
 - (12) Sperling, R. A.; Parak, W. J. Surface Modification, Functionalization and Bioconjugation of Colloidal Inorganic Nanoparticles. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences* **2010**, 368 (1915), 1333–1383.
 - (13) Hofmann, R. J.; Vlatkovic, M.; Wiesbrock, F. Fifty Years of Hydrosilylation in Polymer Science: A Review of Current Trends of Low-Cost Transition-Metal and Metal-Free Catalysts, Non-Thermally Triggered Hydrosilylation Reactions, and Industrial Applications. *Polymers* **2017**, 9 (10), 534.
 - (14) O’Farrell, N.; Houlton, A.; Horrocks, B. R. Silicon Nanoparticles: Applications in Cell Biology and Medicine. *International Journal of Nanomedicine* **2006**, 1 (4), 451–472.
 - (15) Jalkanen, T.; Mäkilä, E.; Määttänen, A.; Tuura, J.; Kaasalainen, M.; Lehto, V. P.; Ihalainen, P.; Peltonen, J.; Salonen, J. Porous Silicon Micro- and Nanoparticles for Printed Humidity Sensors. *Applied Physics Letters* **2012**, 101 (26), 263110.
 - (16) Lawes, S.; Sun, Q.; Lushington, A.; Xiao, B.; Liu, Y.; Sun, X. Inkjet-Printed Silicon as High Performance Anodes for Li-Ion Batteries. *Nano Energy* **2017**, 36, 313–321.
 - (17) Zeng, M.; Zhang, Y. Colloidal Nanoparticle Inks for Printing Functional Devices: Emerging Trends and Future Prospects. *Journal of Materials Chemistry A* **2019**, 7 (41), 23301–23336.
 - (18) Erogbogbo, F.; Liu, T.; Ramadurai, N.; Tuccarione, P.; Lai, L.; Swihart, M. T.; Prasad, P. N. Creating Ligand-Free Silicon Germanium Alloy Nanocrystal Inks. *ACS Nano* **2011**, 5 (10), 7950–7959.

- (19) Wheeler, L. M.; Neale, N. R.; Chen, T.; Kortshagen, U. R. Hypervalent Surface Interactions for Colloidal Stability and Doping of Silicon Nanocrystals. *Nature Communications* **2013**, *4* (5), 1–10.
- (20) Lazzari, S.; Moscatelli, D.; Codari, F.; Salmona, M.; Morbidelli, M.; Diomede, L. Colloidal Stability of Polymeric Nanoparticles in Biological Fluids. *Journal of Nanoparticle Research* **2012**, *14* (6), 920.
- (21) Segets, D.; Marczak, R.; Schäfer, S.; Paula, C.; Gnichwitz, J. F.; Hirsch, A.; Peukert, W. Experimental and Theoretical Studies of the Colloidal Stability of Nanoparticles? A General Interpretation Based on Stability Maps. *ACS Nano* **2011**, *5* (6), 4658–4669.
- (22) Yu, W.; Xie, H. A Review on Nanofluids: Preparation, Stability Mechanisms, and Applications. *Journal of Nanomaterials* **2012**, *2012*, 435873.
- (23) Pau, P. C. F.; Berg, J. O.; McMillan, W. G. Application of Stokes' Law to Ions in Aqueous Solution. *Journal of Physical Chemistry* **1990**, *94* (6), 2671–2679.
- (24) Cheng, P. Y.; Schachman, H. K. Studies on the Validity of the Einstein Viscosity Law and Stokes' Law of Sedimentation. *Journal of Polymer Science* **1955**, *16* (81), 19–30.
- (25) Moore, T. L.; Rodriguez-Lorenzo, L.; Hirsch, V.; Balog, S.; Urban, D.; Jud, C.; Rothen-Rutishauser, B.; Lattuada, M.; Petri-Fink, A. Nanoparticle Colloidal Stability in Cell Culture Media and Impact on Cellular Interactions. *Chemical Society Reviews* **2015**, *44* (17), 6287–6305.
- (26) Studart, A. R.; Amstad, E.; Gauckler, L. J. Colloidal Stabilization of Nanoparticles in Concentrated Suspensions. *Langmuir* **2007**, *23* (3), 1081–1090.
- (27) Schubert, J.; Chanana, M. Coating Matters: Review on Colloidal Stability of Nanoparticles with Biocompatible Coatings in Biological Media, Living Cells and Organisms. *Current Medicinal Chemistry* **2018**, *25* (35), 4553–4586.
- (28) Wiese, G. R.; Healy, T. W. Effect of Particle Size on Colloid Stability. *Transactions of the Faraday Society* **1970**, *66* (0), 490–499.
- (29) Verwey, E. J. W. Theory of the Stability of Lyophobic Colloids. *Journal of Physical and Colloid Chemistry* **1947**, *51* (3), 631–636.
- (30) Boström, M.; Williams, D. R. M.; Ninham, B. W. Specific Ion Effects: Why DLVO Theory Fails for Biology and Colloid Systems. *Physical Review Letters* **2001**, *87* (16), 168103/1-168103/4.
- (31) Liyanage, D. D.; Thamali, R. J. K. A.; Kumbalatar, A. A. K.; Weliwita, J. A.; Witharana, S. An Analysis of Nanoparticle Settling Times in Liquids. *Journal of Nanomaterials* **2016**, *2016*, 7061838.
- (32) Ilyas, S. U.; Pendyala, R.; Marneni, N. Dispersion Behaviour and Agglomeration Effects of Zinc Oxide Nanoparticles in Ethanol-Water Mixtures. *Materials Research Innovations* **2014**, *18*, S6-179-S6-183.
- (33) Alexander, C. M.; Dabrowiak, J. C.; Goodisman, J. Gravitational Sedimentation of Gold Nanoparticles. *Journal of Colloid and Interface Science* **2013**, *396*, 53–62.
- (34) Kops-Werkhoven, M. M.; Fijnaut, H. M. Dynamic Light Scattering and Sedimentation Experiments on Silica Dispersions at Finite Concentrations. *The Journal of Chemical Physics* **1980**, *74* (3), 1618–1625.
- (35) Furst, A.; Taulbee, D. N. (2005). Centrifugation - Analytical Ultracentrifugation.

- In P. Worsfold & A. Townshend & C. Poole (Ed.). *Encyclopedia of Analytical Science (Second Edition)* (pp 469-481). Elsevier.
- (36) Gross-Rother, J.; Herrmann, N.; Blech, M.; Pinnapireddy, S. R.; Garidel, P.; Bakowsky, U. The Application of STEP-Technology® for Particle and Protein Dispersion Detection Studies in Biopharmaceutical Research. *International Journal of Pharmaceutics* **2018**, *543* (1–2), 257–268.
- (37) Walter, J.; Thajudeen, T.; Süß, S.; Segets, D.; Peukert, W. New Possibilities of Accurate Particle Characterisation by Applying Direct Boundary Models to Analytical Centrifugation. *Nanoscale* **2015**, *7* (15), 6574–6587.
- (38) Detloff, T.; Sobisch, T.; Lerche, D. Particle Size Distribution by Space or Time Dependent Extinction Profiles Obtained by Analytical Centrifugation (Concentrated Systems). *Powder Technology* **2007**, *174* (1–2), 50–55.
- (39) Viera, G.; Mikikian, M.; Bertran, E.; Cabarrocas, P. R. I.; Boufendi, L. Atomic Structure of the Nanocrystalline Si Particles Appearing in Nanostructured Si Thin Films Produced in Low-Temperature Radiofrequency Plasmas. *Journal of Applied Physics* **2002**, *92* (8), 4684.
- (40) Altman, I. S.; Agranovski, I. E.; Choi, M. Mechanism of Nanoparticle Agglomeration during the Combustion Synthesis. *Applied Physics Letters* **2005**, *87* (5), 53104.
- (41) Sailor, M. J. (2017). Chemical Reactivity and Surface Chemistry of Porous Silicon. In L. Canham (Ed.). *Handbook of Porous Silicon* (pp 1-20). Springer, Cham.
- (42) He, L.; Kurata, Y.; Inokuma, T.; Hasegawa, S. Analysis of SiH Vibrational Absorption in Amorphous SiO_x:H (0 ≤ x ≤ 2.0) Alloys in Terms of a Charge-Transfer Model. *Applied Physics Letters* **1993**, *63* (2), 162–164.
- (43) Pi, X. D.; Gresback, R.; Liptak, R. W.; Campbell, S. A.; Kortshagen, U. Doping Efficiency, Dopant Location, and Oxidation of Si Nanocrystals. *Applied Physics Letters* **2008**, *92* (12), 123102.
- (44) Yu, B. C.; Hwa, Y.; Park, C. M.; Sohn, H. J. Reaction Mechanism and Enhancement of Cyclability of SiO Anodes by Surface Etching with NaOH for Li-Ion Batteries. *Journal of Materials Chemistry A* **2013**, *1* (15), 4820–4825.
- (45) Wagner, C. D.; Passoja, D. E.; Hillery, H. F.; Kinisky, T. G.; Six, H. A.; Jansen, W. T.; Taylor, J. A. Auger and Photoelectron Line Energy Relationships in Aluminum-Oxygen and Silicon-Oxygen Compounds. *Journal of vacuum science & technology* **1982**, *21* (4), 933–944.
- (46) López, G. P.; Castner, D. G.; Ratner, B. D. XPS O_{1s} Binding Energies for Polymers Containing Hydroxyl, Ether, Ketone and Ester Groups. *Surface and Interface Analysis* **1991**, *17* (5), 267–272.
- (47) Butt, H. J. Measuring Electrostatic, Van Der Waals, and Hydration Forces in Electrolyte Solutions with an Atomic Force Microscope. *Biophysical Journal* **1991**, *60* (6), 1438–1444.
- (48) LIFSHITZ, E. M.; Hamermesh, M. The Theory of Molecular Attractive Forces between Solids. *Perspectives in Theoretical Physics* **1992**, *2* (1), 329–349.
- (49) Israelachvili, J. N. (2011). Van Der Waals Forces between Particles and Surfaces. In J. Israelachvili (Ed.). *Intermolecular and Surface Forces* (pp 253-289) Academic Press: San Diego.

- (50) R. Clausius. (1867). *The Mechanical Theory of Heat*. Cambridge Press.
- (51) Richardson, J. F.; Harker, J. H.; Backhurst, J. R. (2002) Sedimentation. In J. F. Richardson & J. H. Harker & J. Backhurst (Ed.). *Chemical Engineering Series* (pp 237-290). Butterworth-Heinemann: Oxford.
- (52) D'Arrigo, J. (2011). Structure of Predominant Surfactant Components Stabilizing Natural Microbubbles. In J. S. D'Arrigo (Ed.). *Stable Nanoemulsions: Self-Assembly in Nature and Nanomedicine* (pp 107-112); Elsevier.
- (53) Cheng, N.-S. Effect of Concentration on Settling Velocity of Sediment Particles. *Journal of Hydraulic Engineering* **1997**, 123 (8), 728–731.
- (54) Sobisch, T.; Lerche, D. Characterization of Nanostructuring Effects at Solid/Liquid Interfaces by Analytical Centrifugation. *Tenside, Surfactants, Detergents* **2002**, 39 (6), 232–236.
- (55) White, G. F.; Russell, N. J.; Tidswell, E. C. Bacterial Scission of Ether Bonds. *Microbiological Reviews* **1996**, 60 (1), 216–232.
- (56) Rossiter, W. J.; Godette, M.; Brown, P. W.; Galuk, K. G. An Investigation of the Degradation of Aqueous Ethylene Glycol and Propylene Glycol Solutions Using Ion Chromatography. *Solar Energy Materials* **1985**, 11 (5–6), 455–467.
- (57) Israelachvili, J. N. (2011). Electrostatic Forces between Surfaces in Liquids. In J. Israelachvili (Ed.). *Intermolecular and Surface Forces* (pp 291-340). Academic Press: San Diego.
- (58) Hülser, T.; Schnurre, S. M.; Wiggers, H.; Schulz, C. Gas-Phase Synthesis of Nanoscale Silicon as an Economical Route towards Sustainable Energy Technology. *KONA Powder and Particle Journal* **2011**, 29 (29), 191–207.
- (59) T. Detloff. Instability Index Calculation. **2012**, 4 (2013), 1–4.
- (60) González, B.; Calvar, N.; Gómez, E.; Domínguez, Á. Density, Dynamic Viscosity, and Derived Properties of Binary Mixtures of Methanol or Ethanol with Water, Ethyl Acetate, and Methyl Acetate at T = (293.15, 298.15, and 303.15) K. *Journal of Chemical Thermodynamics* **2007**, 39 (12), 1578–1588.
- (61) O'Neil, M. J. (2013). *The Merck Index: An Encyclopedia of Chemicals, Drugs and Biologicals (15th Edition)*. Royal Society of Chemistry, Cambridge.
- (62) Elangovan, S.; Diriba Garbi, T.; Kena Etana, S. Dielectric Relaxation Studies Between Brompheniramine with 1-Butanol, 1-Pentanol and 1-Hexanol at 303K. *Material Science Research India* **2020**, 17 (3), 230–235.
- (63) Rumble, J. R. (2021). *CRC Handbook of Chemistry and Physics*. CRC Press.
- (64) Rizk, H. A.; Elanwar, I. M. Dipole Moments of Glycerol, Isopropyl Alcohol, and Isobutyl Alcohol. *Canadian Journal of Chemistry* **1968**, 46 (4), 10.1139/v68-084.
- (65) Awwad, A. M.; Al-Dujaili, A. H.; Salman, H. E. Relative Permittivities, Densities, and Refractive Indices of the Binary Mixtures of Sulfolane with Ethylene Glycol, Diethylene Glycol, and Poly(Ethylene Glycol) at 303.15 K. *Journal of Chemical and Engineering Data* **2002**, 47 (3), 421–424.

Chapter 4

Polymer Brush Stabilized Silicon Nanoparticle Inks for Printed electronics: Effect on Colloidal Stability, Printability, and Diode Functionality

Formulating stable nanoparticle-based conductive inks is a crucial step for successfully utilizing printing technologies in the low-cost, large-scale manufacturing of thin-film (electronic) devices (TFD). During ink formulation, both the long-term stability and printability of the ink need to be carefully adjusted. In this Chapter we present an approach to tackle both issues for the development of silicon nanoparticle-based inks by employing polymer brush coatings based on poly(methyl methacrylate) and poly(ethylene glycol) methacrylate. The polymer-coated nanoparticles show increased colloidal stability when using ethylene glycol and diethylene glycol as solvents. The printability of the polymer decorated silicon nanoparticle-based inks display improvements, especially nozzle clogging is significantly reduced. Finally, we demonstrate that the polymer coating negatively affects the device performance of printed silicon-based TFD. This we attribute to the inclusion of conductive SiC layers that form during device manufacturing when a polymer brush coating is present on the silicon nanoparticles. We suggest several strategies to avoid the formation of the SiC layers for future work.

Results described in this Chapter from parts of a (confidential) project “DruIDe” funded by the Interreg V project.

4.1 Introduction

Silicon-based thin films are essential components in electronic devices used in our daily lives, e.g. in transistors or solar cells.^{1,2} With significant advances in nanotechnology, new avenues to fabricate devices with silicon-based thin films as functional components have become available.^{3,4} The use of well-established solution-based high throughput printing methods to deposit silicon nanoparticle inks in a spatially controlled manner is considered the first step towards producing thin film (electronic) devices (TFD). Compared to conventional lithography, solution-based processing is advantageous due to its low cost and homogeneous layer formation, especially for large scale manufacturing of TFDs.^{5,6}

Our research was part of a collaborative project, with the objective to supply our collaborators with printable Si nanoparticle containing, stable inks. The project partners (Duisburg University) were then supposed to use these inks in thin printed films and prepare elements for integrated circuits, such as diodes. Thus were interested in developing long-term stable silicon nanoparticle inks that enable the printing of silicon nanoparticle layers and their subsequent laser modification to fabricate functional Si μ -cones layers in printed Schottky diodes on various substrates. At the start of this project, the silicon nanoparticle layers in proof-of-concept devices were prepared by spin coating,⁷ followed by laser treatment to form Si μ -cones. The high crystallinity of the formed Si μ -cones enabled a high operating frequency (switching speed up to 2.84 GHz) for the resulting Schottky diodes. Ultra-high-frequency (UHF) diodes are essential for applications like flexible targeted radio frequency identification (RFID) tags. To enable low-cost and large-scale manufacturing of flexible RFID tags with silicon nanoparticle inks, printing is considered as the processing technique of choice. So far, the RFID tags were built using laboratory processing techniques and the formulation and stability of silicon nanoparticle inks for printing have not been optimized yet.

Spin coating is considered the most straightforward solution processing technique for lab-scale research and development of thin films.^{8,9} Spin coating can produce layers with thicknesses from few nanometers to few micrometers by adjusting the solution viscosity, particle concentration, rotation velocity, and spinning duration.^{10,11} However, spin coating is not scalable to high throughput production and suffers from a high product to waste ratio (approximately 95% is waste). Therefore spin coating is considered unsuitable for large-scale manufacturing of thin film-based devices.¹²

Figure 4.1 Schematic of SiNPs based Schottky diode manufacturing.

Essential for the successful transformation from spin coating to inkjet printing-based production approaches is the formulation of printable silicon nanoparticle-based inks that possess long-term stability. Several factors, like viscosity, density, surface tension, colloidal stability, will influence nanoparticle film formation and reproducibility.^{10,13} The project partners identified control over long-term colloidal stability (storage) to be essential to tackle early on prior to moving to industrial-scale production technologies. In our research we focused on two strategies: i) developing a broad understanding of silicon nanoparticles (SiNPs) colloidal stability in various solvents (see Chapter 3) and ii) utilizing steric stabilization to obtain long-term colloidal stability. The latter approach is presented and discussed in the remainder of this Chapter.

Steric stabilization of colloids can be achieved by various approaches, including surface charge stabilization mechanisms, and attachment of chain molecules (oligo- and polymers) that repel by an entropic spring effect. Here we focus on polymer chain attachment. Physical or covalent attachment of polymer chains to nanoparticle surfaces can create steric hindrance and eventually avoid particle agglomeration.¹⁴ In general, there are three ways to anchor polymer chains to nanoparticle surfaces, namely "grafting to", "grafting from", and "grafting through".¹⁵ Among these methods, "grafting from" by surface initiated-atom transfer radical polymerization (SI-ATRP) is recognized as a convenient approach for synthesizing polymer/particle hybrids which receives considerable attention (see also Chapter 2).^{16–18}

Although colloidal stabilization by employing surface grafted polymers is a well-established technique, there are, to the best of our knowledge, little details in the literature to utilize SI-ATRP for enhancing colloidal stability of conductive nanoparticle inks for

the printing of TFDs. Here we report on the preparation and use of the SI-ATRP based fabrication of PMMA/silicon and poly(ethylene glycol)methyl acrylate (PEGMA)/silicon nanoparticle hybrids and the effect of the polymer shell on the colloidal stability of their respective inks. In the last section of this Chapter, we discuss the effect of the polymer shell on the performance of a diode, followed by an outlook suggesting further developments.

4.2 Results and Discussion

4.2.1 Printing Test of SiNP-Based Inks

Using the colloidal stability data acquired from previous experiments (see Chapter 3), SiNP based inks were prepared by suspending 2 wt% of SiNPs in ethanol or diethylene glycol monobutyl ether (DGBE). Before printing, the inks were diluted to a particle concentration of 1 wt% using ethylene glycol (EG). The addition of EG increased the ink viscosity from 1.23 mPa to 4.02 mPa and from 6.25 mPa to 17.2 mPa for ethanol and DGBE based inks, respectively. This increase in ink viscosity was required to enhance the printability.

Figure 4.2. Images of inkjet-printed SiNP layers on glass (left) and Kapton (middle) substrates. On the right optical microscopy images of SiNP lines on Kapton are shown.

Images of printed SiNP layers are presented in Figure 4.2. When SiNP layers were printed on glass substrates, we see that for ethanol/EG as the ink solvent, the SiNP layer was non-uniform due to the coffee ring effect. When DEGB/EG was used as the solvent, the edges were distorted due to non-optimal ink wetting. Upon changing from glass substrates to Kapton substrates, the layer boundaries were much sharper, and the layers' interior appeared visually homogenous. However, numerous lighter spots inside the

printed areas for both inks deposited on Kapton are visible in the optical microscopy images. These brighter spots could be the result of particle agglomeration upon ink deposition and/or solvent evaporation. Also, shortly after starting to print, the flow-induced aggregation of SiNPs at the contraction zone in the printhead caused 1/3 of the nozzles to clog. This observed printer blocking is attributed to the broad size distribution of SiNPs used in this study (i.e. the hydrodynamic diameter in water ranges from 110 nm to 550 nm). (We note that the SiNPs are aggregates consisting of primary particles with a diameter of $\sim 50 \pm 17$ nm. See Chapter 3 for more details about the SiNPs size distribution.) During printing, larger SiNP agglomerates act as heterogeneous nuclei for aggregation when passing the contraction zone and, consequently, induce nozzle clogging.¹⁹

Thus, our preliminary print tests suggested that pristine SiNPs are unsuitable for the inkjet printing of uniform thin SiNP films. To overcome irreversible particle clogging during printing and obtain more control over substrate wetting, we grafted PMMA and PEGMA from SiNPs.

4.2.2 Surface Modification of SiNPs

Thin polymers shells were grafted from the SiNP surface using SI-ATRP of MMA and EGMA. We selected PMMA and PEGMA to cover a range of suitable ink solvents, i.e. from polar to non-polar. The complete particle modification reaction scheme is presented in Figure 4.3. First, HCl was used to hydrolyze the SiNPs' surface to introduce surface-exposed silanol moieties, followed by their amino functionalization with (3-Aminopropyl)triethoxysilane (APTES). Then the exposed amino functional groups on the particle surface were functionalized with α -Bromoisobutyryl bromide (BiBB) to form SiNP based macroinitiators. Finally, PEGMA and PMMA brushes were grafted from the as-prepared nanoparticle macroinitiator surfaces via SI-ATRP of their respective monomers.

Figure 4.3 Schematic drawing of polymer grafting strategies. SiNPs were hydrolyzed (a) by diluted HCl, followed by amino functionalization (b) to introduce amine groups to the particles' surface. Then, the bromine terminated ATRP initiator (BiBB) was covalently immobilized (c) on the SiNP surface. Subsequently, MMA and PEGMA monomers were grafted from the particles' surface (d) via SI-ATRP to form core-shell polymer/SiNP hybrids.

4.2.3 Characterization of Polymer-Nanoparticle Hybrids

Figure 4.4 shows transmission electron microscope (TEM) images of pristine SiNPs, PMMA grafted SiNPs (SiNPs-PMMA), and PEGMA grafted SiNPs (SiNPs-PEGMA). The TEM images show a core-shell structure for the polymer decorated SiNPs (Figure 4.4b, 4.4c, 4.4e, and 4.4f). The dry shell thickness is approximately 1.8 ± 0.5 nm and 1.7 ± 0.3 nm for the SiNPs-PMMA and SiNPs-PEGMA, respectively.

Next to TEM, Fourier transform infrared (FTIR) spectroscopy and thermogravimetric analysis (TGA) were employed to confirm the successful grafting of polymer shells on SiNPs. Figure 4.5 shows single reflection FTIR absorbance spectra of the pristine SiNPs, SiNPs-PMMA, and SiNPs-PEGMA. The absorbance bands located at 1970 cm^{-1} , 2081 cm^{-1} , 2098 cm^{-1} , and 2270 cm^{-1} in the FTIR spectrum of the SiNPs correspond to Si-H stretching vibration of H-Si(Si₃), H-Si(Si₂O), H-Si(SiO₂), and H-Si(SiO₃), respectively.^{20,21} After polymer grafting, Si-H absorbances remain visible in the FTIR spectra of SiNPs-PMMA and SiNPs-PEGMA. This indicates that a significant amount of the surface exposed Si-H groups were preserved during the surface modification process. Furthermore, the bands observed at 1715 cm^{-1} and near 2900 cm^{-1} in the FTIR spectra of the core-shell SiNPs are ascribed to carbonyl (C=O) absorbances of the ester and C-H absorbances in the grafted polymers, respectively.²² The appearance

of the C-H and C=O absorbances in the FTIR spectra of the hybrid SiNPs confirm the successful grafting of PMMA and PEGMA shells.

Figure 4.4 TEM images of pristine SiNPs (a and d), SiNPs-PMMA (b and e), and SiNPs-PEGMA (c and f). The red arrows point to the grafted polymer shells around the SiNPs.

Figure 4.5 a) Single reflection FTIR absorption spectra of SiNPs, SiNPs-PMMA, and SiNPs-PEGMA. b) TGA thermograms for SiNPs, SiNPs-Br, SiNPs-PMMA, and SiNPs-PEGMA.

TGA was used to determine the amount of grafted polymer to the SiNPs. The non-isothermal thermograms for SiNPs, initiator, immobilized (SiNPs-Br), and PMMA/PEGMA grafted SiNPs are shown in Figure 4.5b. From these thermograms, we determined that approximately 2.1 wt% of ATRP functional initiator was coupled to the surface of the SiNPs. The grafted amount of PMMA and PEGMA to SiNPs was

approximately 8.2% and 11.9%, respectively. Based on the shell thickness values determined by TEM analysis, the amounts of grafted polymers are in qualitative agreement with what we expected. Overall, we conclude that SiNPs-PMMA and SiNPs-PEGMA were successfully prepared.

4.2.4 Surface Modification of SiNPs

Following SiNPs-PMMA and SiNPs-PEGMA preparation, SiNPs based inks were formulated with EG and DGBE as ink solvents. EG and DGBE were selected as a good starting point to develop the SiNPs hybrid inks due to their relatively high boiling point and suitable viscosity for inkjet printing. Both PMMA and PEGMA coating enhance the colloidal stability for SiNPs. In batch sedimentation evaluation, both SiNPs-PMMA and SiNPs-PEGMA remained dispersed in EG for more than 90 days. On the contrary pristine SiNPs revealed the first signs of particle sedimentation after 15 days already.

We adjusted the ink viscosity during printing trials by reducing the particle loading and/or mixing in various other solvents. Table 4.1 shows the composition of the optimized inks we prepared for the printing trials.

Table 4.1 The composition of SiNP, SiNPs-PMMA, and SiNPs-PEGMA based inks.

	<i>Ink 1</i>	<i>Ink 2</i>	<i>Ink 3</i>
Particle	SiNP	SiNPs-PMMA	SiNPs-PEGMA
Particle load	4 wt%	3 wt%	5.5 wt%
Solvent	DGBE	EG/DCM/acetone (2:5:3 v/v)	DGBE

Contrary to SiNPs based inks (see section 3.1), the formulated hybrid SiNPs based inks enabled us to print patterns on titanium/tungsten coated glass substrates, as is shown in Figure 4.6, without significant nozzle clogging (<10% of the nozzles). In addition, when nozzles did clog, they were easily opened by wiping them clean with a tissue and modest rinsing. The reduced nozzle clogging was a significant improvement compared to printing with pristine SiNPs. Figure 4.6b, 4.6d, and 4.6f show confocal microscopy images of 10 pL droplets printed in the drop-on-demand mode on titanium/tungsten coated glass. Table 4.2 presents the drop dimensions and coffee ring ratios for drops printed with the SiNPs, SiNPs-PMMA, and SiNPs-PEGMA based inks.

Figure 4.6. Photos of printed patterns (top) and confocal microscopy images (bottom) of drop-on-demand deposited SiNPs layers on titanium/tungsten coated glass substrates for SiNPs (a and b), SiNPs-PMMA (c and d), and SiNPs-PEGMA (e and f) based inks. The composition of the inks is shown in Table 4.1.

It is noteworthy to point out regarding data shown in Table 4.2 that printing with the SiNPs-PMMA based ink resulted in reduced droplet sizes and silicon layer thicknesses in the order of a few hundred nanometers. A decreased drop size and increase in drop thickness point at a better thin-film quality obtained by printing on the used titanium/tungsten coated glass substrates (compare Figure 4.6b, 4.6d, and 4.6f). In addition, the coffee ring ratio for the SiNPs-PMMA ink was reduced to ~ 2.0 as well. Considering the project objectives we note that the effect of the increased edge thickness compared to the interior of the printed droplets on the final quality of a printed silicon layer was not of primary interest. The project partners considered to elucidate the effect of a polymer shell around the SiNPs on Si μ -cone formation and Schottky diode performance of higher priority, which is presented in the next section of this Chapter.

Table 4.2 Droplet characterization for Ink 1, Ink 2, and Ink 3. The coffee ring ratio is defined as the ratio of the edge thickness to the interior drop thickness.

	<i>Ink 1</i>	<i>Ink 2</i>	<i>Ink 3</i>
Drop diameter (without edge)	53 μm	43 μm	70 μm
Drop thickness	32 nm	645 nm	70 nm
Edge diameter	126 μm	56 μm	122 μm
Edge thickness	95 nm	1285 nm	260 nm
Coffee ring ratio	3.0	2.0	3.7

4.2.5 Spin-Coating and Diode Fabrication

To investigate the effect of a polymer shell around the SiNPs on deposited silicon layers, cone formation, and Schottky diode performance, our project partner at the University Duisburg-Essen, Prof. Bensons' team followed a reported²³ protocol to construct thin-film diodes on titanium/tungsten coated glass substrates as a first step. This protocol utilizes spin-coating of SiNP based inks in ethanol with a relatively high particle loading, i.e. 16.6 wt%, to obtain SiNP layers with a thickness of approximately 450 nm. This thickness is required to have good Si μ cone formation during the laser modification step (See Figure 4.1).

SiNPs and SiNPs-PEGMA were dispersed in ethanol easily. For SiNPs-PMMA dispersions in the tri-solvent mixture, initial spin-coating trials revealed poor film formation, which we ascribed to the complex evaporation behavior of the solvent mixture. Few trials with various other solvents resulted in selecting DMF as a solvent for SiNPs-PMMA inks, giving visually homogeneous layers by spin-coating.

Figure 4.7. SEM images of a) SiNPs, b) SiNPs-PEGMA, and c) SiNPs-PMMA layers deposited on titanium/tungsten coated glass substrate via spin coating. SEM images of Si μ -cones fabricated from laser annealing of the d) SiNP, e) SiNPs-PEGMA, and f) SiNPs-PMMA thin particle layers.

The as-prepared suspensions were deposited on the titanium/tungsten-coated glass substrates via spin coating. From the corresponding SEM images of the different systems shown in Figure 4.7, it is clear that SiNPs/ethanol and SiNPs-PEGMA/ethanol suspension formed smooth particle layers. The SiNPs-PMMA films after drying contained large particle agglomerates and the layers were not uniform. We attributed the formation of

larger agglomerates to the relatively slow drying of the N,N-dimethylformamide-based (DMF-based) ink.

From the SEM images (Figure 4.7d-f), cone formation is observed for laser-treated SiNP, SiNPs-PEGMA, and SiNPs-PMMA layers. The values of the surface cone densities observed are 1.1×10^6 , 1.1×10^6 and 9.1×10^4 cones mm^{-2} , and the average cone widths are 430 ± 60 , 470 ± 50 , and 490 ± 130 nm for the treated SiNP, SiNPs-PEGMA, and SiNPs-PMMA layers, respectively. The cone density and width for SiNPs-PEGMA are in the same order as values of the bare SiNP based μ -cone layers. The Si μ -cones formed for the SiNPs-PMMA layers have a much lower surface density, and cracks in the layer are visible. These observations are attributed to the melting of the larger agglomerates, resulting in forming of a thick silicon layer instead of Si μ -cones, which, upon cooling due to thermal expansion differences between the coating and substrate, result in crack formation. Therefore only the SiNPs and SiNPs-PEGMA based layers were used to construct Schottky diodes.

Figure 4.8. *I-V characteristic of prepared Schottky diodes from SiNPs (red) and SiNPs-PEGMA (blue) spin-coated layers*

Figure 4.8 shows representative I-V (current-voltage) characteristics of devices build with SiNPs and SiNPs-PEGMA particle layers. The rectification ratios were 10.5 and 1.1 (at $|V| = 1$ V) for diodes constructed with Si μ -cones based on SiNPs and SiNPs-PEGMA, respectively. The low rectification ratio for the diode based on the hybrid silicon particles means that we can hardly classify these devices as a diode. Below we provide a possible explanation for the low rectification ratio of the polymer grafted SiNPs based diodes.

X-ray photoelectron spectroscopy (XPS) analysis of the particle-based thin films and the Si μ -cones were used to obtain their composition and identify possible contaminants that could explain the poor rectification behavior of the SiNPs-PEGMA μ -cone based diodes. Table 4.3 presents the atomic concentration of C, O, and Si for SiNP and SiNPs-

PEGMA thin films together with their corresponding μ -cone layer. It is readily observed that the carbon content increased from 11.8% to 30.3% for Si μ -cone after PEGMA grafting. A large amount of C presented in the SiNPs-PEGMA μ -cone could form nitrogen doped silicon carbide, resulting in poor rectification behavior. To further investigate the poor rectification behavior, Si2p core-level spectra were measured for all samples as well. These are shown in Figure 4.9.

For the as-deposited SiNP and SiNPs-PEGMA layers, the dominant bands in the Si2p core-level spectra (Figure 4.9a and 4.9c) are ascribed to the characteristic binding energy for monoatomic Si (97.7 eV and 98.9 eV), Si²⁺ (101.2 eV), and Si³⁺ (102.6 eV).^{24,25} The Si²⁺ and Si³⁺ are most likely originating from the oxidized surface of the silicon nanoparticles (SiO and Si₂O₃, respectively). Following laser modification, the dominant Si2p bands for SiNP μ -cone (Figure 4.9b) are Si¹⁺ (Si-OH and Si₂O, 100.4 eV) and Si⁴⁺ (SiO₂, 103.5 eV), indicating that elemental Si was oxidized.²⁴ The peak located at 100.9 eV in the Si2p core-level spectrum of SiNPs-PEGMA μ -cones (Figure 4.9d) is ascribed to Si-C, which is not observed in any other samples.^{25,26} The formation of Si-C is explained by C atoms (from the polymer shell) bonding with Si atoms to form silicon carbide during the carbonization of the polymer chains.²⁷

Table 4.3 Atomic concentrations of C, O, and Si for SiNP thin film, SiNP μ -cone, SiNPs-PEGMA thin film and SiNPs-PEGMA μ -cone from XPS analysis.

	<i>SiNP film</i>	<i>SiNP μ-cone</i>	<i>SiNPs-PEGMA film</i>	<i>SiNPs-PEGMA μ-cone</i>
C	13%	11.8%	55.9%	30.3%
O	40.3%	52.7%	35%	45.3%
Si	46.8%	33.6%	9.1%	23.4%

Furthermore, we speculate that the SiC impurities present on the Si μ -cones surfaces can interact with nitrogen during diode fabrication, resulting in nitrogen-doped silicon carbide.²⁸ Nitrogen doping typically increases silicon carbide conductivity, leading to a metallic behavior instead of the needed semiconductive behavior of the formed Si μ -cones. This can explain the low rectification ratio of the diodes based on SiNPs-PEGMA layers.

Figure 4.9. Si₂p core-level spectra of SiNP thin film (a), SiNP μ -cone (b), SiNPs-PEGMA thin film (c) and SiNPs-PEGMA μ -cone (d). The dotted lines show peak deconvolution of the core-level spectra to identify the bonds present.

To minimize the influence of polymer grafts on the diode performance, we need to reduce the C content during diode fabrication. Using polymers that rapidly depolymerize into volatile small molecules upon certain triggering events can effectively reduce the C content. Polymers to consider are poly(isobutylene) and poly(α -methylstyrene). Moreover, the molecules used to attach the surface-active ATRP initiators (APTES and BiBB) contain a large amount of C atoms, as well. This could be avoided by exploiting an alternative grafting approach with minimal use of carbon-containing coupling molecules. One of the promising directions for this future work would be to use earth-abundant species catalyzed or catalyst-free hydrosilylation.²⁹

Based on the results presented and discussed, we believe that inkjet printing of hybrid SiNPs based inks with an optimized brush coating is a feasible approach for the large-scale manufacturing of flexible electronic devices, but further research and progress is needed.

4.3 Conclusion

SiNPs-PMMA and SiNPs-PEGMA with a core-shell structure were synthesized via SI-ATRP of their respective monomers. The polymer brush coating reduced the coffee ring effect and nozzle clogging for inkjet printing of thin particle layers on various substrates. Following laser sintering, spin-coated PEGMA grafted SiNP layers were able to form substrates with a uniform Si μ -cone layer with a cone density of 1.1×10^6 and an average cone size of 470 ± 50 nm. The cone density and cone size of SiNPs-PEGMA layers are comparable to that of Si μ -cones prepared from pristine SiNP ink. However, the SiNPs-PEGMA μ -cone-based diodes had a rectification factor of 1.1 (at $|V| = 1$ V), while for pristine SiNPs μ -cone-based diodes, the rectification factor is 10.5. Based on XPS analysis of the formed μ -cone layers, we attributed the low rectification factor for PEGMA modified SiNPs based μ -cones to the formation of nitrogen-doped SiC during diode fabrication. The inclusion of SiC is expected to result in more metallic characteristics instead of semiconductor behavior for the prepared diodes. Though a working diode was not produced, we conclude that polymer grafting is a powerful tool to improve the printability and stability of SiNP inks for large-scale implementation in the production of TFD. Furthermore, we recommend that future research focuses on selecting alternative polymers and coupling strategies for SiNPs to avoid SiC formation in the laser ablation step.

4.4 Materials and Methods

Materials. Boron-doped silicon nanoparticles with a boron doping level of 5×10^{18} atoms cm^{-3} were a gift from University Duisburg-Essen, Germany, and they were used as received. Hereinafter, we refer to these nanoparticles to as SiNPs. Dichloromethane (DCM) $\geq 99.5\%$ was purchased from VWR International (Germany). Copper(I) bromide (CuBr) 98% and (3-aminopropyl)-triethoxysilane (APTES) 97% were received from Aldrich (Milwaukee, WI, USA). Hydrofluoric acid (48%) (HCl), α -bromoisobutyl bromide (BiBB) 98%, methylmethacrylate (MMA), poly(ethylene glycol) methacrylate (Mn ~ 500) (PEGMA500), copper (II) bromide $\geq 99\%$, aluminum oxide (for chromatography), triethylamine (TEA), ethylene glycol (anhydrous, 99.8%), and diethylene glycol (ReagentPlus, 99%) were purchased from Sigma-Aldrich (St. Louis, MO, USA). Butylated hydroxytoluene (BHT) stabilized tetrahydrofuran (THF) for analysis, and N,N-dimethylformamide AR (DMF) were acquired from Biosolve (Valkenswaard, the Netherlands). N,N,N',N',N''-pentamethyldiethylenetriamine (PMDETA) 98% was purchased from Acros Organics (Geel, Belgium). Acetic acid

$\geq 99\%$ and diethylene glycol monobutyl ether (DGBE) for synthesis was obtained from Merck (Darmstadt, Germany). Ethylene glycol (EG) was purchased from VWR (Radnor, PA, USA). MMA and PEGMA were run over an aluminum oxide column to remove the inhibitor. Copper (I) bromide was purified by stirring in glacial acetic acid, followed by filtration and drying in a vacuum oven overnight at 60 °C. Milli-Q water was produced by a Millipore Synergy system (Billerica, MA, USA). Unless specified, all other chemicals were used as received.

Hydrolysis of Silicon Nanoparticles. 5 g SiNPs were suspended in a mixture of 680 ml Milli-Q water and 20 ml ethanol in a 1 L round bottom flask using intense sonication for 1 hour. While stirring at 500 rpm at room temperature, HCl was added dropwise to the suspension until the pH value of the suspension reached approximately 1. Subsequently, the suspension was left to stir at room temperature for 16 h, followed by centrifuging at 13,000 rpm for 30 min to collect the hydrolyzed SiNPs (SiNPs-OH). The SiNPs-OH were redispersed with ethanol and centrifuged. This washing process was repeated two more times.

Amino-Functionalization of Silicon Nanoparticles. The as-prepared SiNPs-OH were redispersed in 700 ml Ethanol in a 1 L round bottom flask by sonication for 1 hour, followed by the addition of 30 ml APTES. Next, the suspension was left to stir at 500 rpm at room temperature for 17 hours. The amino-functionalized SiNPs (SiNPs-NH₂) were collected by centrifugation at 13,000 rpm for 30 min, redispersed in ethanol, and centrifuged again. This washing process was repeated two more times and particles were immediately treated with an ATRP functional initiator in the next step.

ATRP Initiator Immobilization on Silicon Nanoparticles. Freshly prepared SiNPs-NH₂ were dispersed in DMF and centrifuged at 13,000 rpm for 30 min. Next, the collected SiNPs-NH₂ were dispersed in 600 ml DMF in a 1 L round bottom flask using intense sonication for 1 hour. The suspension was cooled in an ice bath to 0 °C, followed by the dropwise addition of 45 ml TEA and 15 ml BiBB for 30 min while stirring at 500 rpm. Subsequently, the mixture was left in the ice bath while stirring for 1 hour. The temperature of the reaction mixture was raised to room temperature and stirring continued for another 16 hours. Following the reaction, the particles were collected by centrifugation at 13,000 rpm for 30 min. The collected initiator immobilized SiNPs (SiNPs-Br) were redispersed in ethanol and centrifuged again to remove unreacted TEA, BiBB, and the salts formed by TEA and HBr. This washing step was repeated two more times. Finally, the as-prepared SiNPs-Br were dispersed in DMF and centrifuged at 13,000 rpm for 30 min. Samples were used immediately for SI-ATRP.

SI-ATRP of PEGMA, or PMMA, from Initiator Immobilized Silicon Nanoparticles. As-prepared SiNPs-Br were dispersed in 400 ml DMF in a 1L round bottom flask by sonication for 1 hour. After sonication, 40 ml PEGMA500 was added to the suspension. Simultaneously, 80 mg CuBr, 25 mg CuBr₂, and 15 ml DMF were added to a 25 ml round bottom flask (flask B). Both flasks were sealed with a rubber septum and bubbled with nitrogen for 30 min. Next, 0.14 ml PMDETA was added to the CuBr/CuBr₂ mixture, followed by 30 min nitrogen purging, after which the mixture in flask B was transferred to the flask containing the SiNPs-Br/PEGMA500 suspension. Subsequently, the reaction flask was submerged into a 70 °C thermostated oil bath and stirred at 500 rpm for 1 hour under a nitrogen atmosphere. The polymer-modified particles were collected by centrifugation at 13,000 rpm for 30 min. Then, the collected PEGMA grafted SiNPs (SiNPs-PEGMA) were redispersed in DMF and centrifuged again. The washing process was repeated 2 more times. Finally, the as-prepared SiNPs-PEGMA were dispersed in ethanol, then centrifuged at 13,000 for 30 min. The collected SiNPs-PEGMA were stored in ethanol.

To prepare PMMA grafted SiNPs (SiNPs-PMMA), we used the same procedure, except that 42.65 ml MMA, 455 mg CuBr, 304 mg CuBr₂, and 0.946 ml PMDETA were employed. In addition, the final solvent transfer of the SiNPs-PMMA was to DCM.

Batch Sedimentation Testing of Inks. SiNPs-PEGMA were suspended in ethylene glycol and diethylene glycol at a concentration of 0.5 wt%, respectively. The suspensions were stored in glass vials with polypropylene caps. Subsequently, the vials were sealed with Parafilm to avoid evaporation and water absorption. The glass vials were stored in ambient conditions and recorded with a surveillance camera at 24 fps to observe the sedimentation behavior of the suspensions.

Particle Characterization. Transmission Electron Microscopy (TEM) was performed by an FEI/Philips CM300 system (FEI, Eindhoven, the Netherlands). Few drops of diluted particle dispersion in ethanol were deposited on the carbon side of a carbon/copper grid (HC200-Cu) (EMS, Germany) before imaging. The typically used electron acceleration voltage was between 3 to 5 keV. Fourier Transform Infrared (FTIR) spectra of the pristine and modified SiNPs were collected with a Bruker ALPHA single attenuated total reflection (ATR) FTIR Spectrometer equipped with an ATR single reflection diamond crystal (Bruker Optic GmbH, Ettlingen, Germany). The spectra were collected in the range of 400-4000 cm⁻¹ (spectral resolution of 4 cm⁻¹, 512 scans). Background spectra were recorded against air. A Malvern Zetasizer Nano-ZS (Malvern Instruments, Malvern, UK) was used to determine the values of the effective

hydrodynamic radius of SiNPs dispersed in Mili-Q water. The weight loss of the pristine and modified SiNPs was monitored with a TGA400 (PerkinElmer, Inc., Waltham, MA, USA). A sample weighing ~6-10 mg was loaded into a platinum pan and set to 50 °C to stabilize. Subsequently, the sample was heated to 800 °C at a heating rate of 10 °C/min with an N₂ flow of 25 ml min⁻¹.

Inkjet Printing of Silicon Nanoparticles. A PiXDOR R&D printer equipped with a 30 pL printer head (128 nozzles) (Meyer Burger, Eindhoven, the Netherlands) was used to print SiNPs ethanol and DGBE dispersions. To prepare the SiNPs based inks, 0.2 g SiNPs were suspended in 4.9 g ethanol or DGBE via sonication (BRANSON 2510, Canada) for 1 hour. Following particle dispersion, 4.9 g of EG was added to the suspension, and the residual mixture was sonicated for 30 minutes. Then the as-prepared SiNPs inks were printed on glass and Kapton substrates. Polymer grafted SiNP based inks were printed with a Dimatix Piezo inkjet 2831 printer (FUJIFILM Dimatix Inc., Santa Clara, CA) PIXDRO LP 50, featuring a DMP-2850 print head and a DMC 11610 cartridge (16 nozzles having a 23 µm diameter, 10 pL nominal drop volume). Inks were prepared by suspending SiNPs or SiNPs-PEGMA in DGBE at a concentration of 4 and 5.5 wt%, respectively, via sonication. SiNPs-PMMA were suspended by sonication in EG/DCM/acetone (2:5:3 v/v) or DCM at a concentration of 3.0 wt% and 2.0 wt%, respectively. The as-prepared inks were printed on glass substrates (15x15 mm) modified with sputter-deposited titanium and tungsten layers (1 µm and 120 nm, respectively).

Spin Coating of Polymer-Modified Silicon Nanoparticles. SiNPs-PEGMA and SiNPs-PMMA were suspended in ethanol and DCM at a concentration of 16.6 wt%, respectively. The as-prepared suspensions were filtered with a 700 nm glass filter (Merck Millipore, US) before being cast on a titanium/tungsten coated glass substrate (15x15 mm), followed by spin coating at 6000 rpm for 30 s (acceleration 6000 rpm/s). To remove residual ethanol in the deposited polymer grafted SiNPs layers, spin-coated substrates were placed on a hotplate thermostated at 80 °C for 5 minutes. Images of the spin-coated thin films were obtained with an optical microscope (Olympus BH-2, Olympus, Tokyo, Japan) and a scanning electron microscope (JEOL Field Emission JSM-7500F, JEOL Benelux, Nieuw-Vennep, the Netherlands).

Schottky Diode Formation. As-deposited SiNP thin films were annealed with an ATLEX-300SI KrF excimer laser (ATL Lasertechnik GmbH, Wermelskirchen, Germany) to form Si µ-cones. The laser's emitting wavelength and pulse duration were 248 nm and 4-6 ns, respectively. The annealing process was performed under a nitrogen environment to avoid oxidation of Si-melt. During the process, the repetition frequency,

the scanning speed, and the effective energy density for the laser were set to 100 Hz, 9.3 mm min⁻¹ and 5 mJ, respectively. SU-8 2000.5 was used as the insulator layer between anode and cathode. It is applied to cover the annealed Si μ -cones on the sample via lithography, followed by 30 s plasma etching to expose the top of the Si μ -cones eventually. The as-prepared sample was dipped in 5 % hydrofluoric acid solution for 20 s to remove the oxidized layer from the top of the Si μ -cones. Then a layer of aluminum (200 nm) was deposited via evaporation to form Schottky contact. The IV characteristics of as-prepared diodes were measured with a KEITHLEY 4200-SCS (Keithley Instruments GmbH, Ohio, U.S.).

4.5 References

- (1) Durrani, Z. A. K.; Ahmed, H. (2008) *Nanosilicon Single-Electron Transistors and Memory*. In V. Kumar (Ed.). *Nanosilicon* (pp335-359). Elsevier.
- (2) O'Farrell, N.; Houlton, A.; Horrocks, B. R. Silicon Nanoparticles: Applications in Cell Biology and Medicine. *International Journal of Nanomedicine* **2006**, *1* (4), 451–472.
- (3) Osborne, I.; Lavine, M.; Coontz, R. Materials for Electronics. Looking beyond Silicon. Introduction. *Science* **2010**, *327* (5973), 1595.
- (4) Venema, L. Silicon Electronics and Beyond. *Nature* **2011**, *479* (7373), 309.
- (5) Cummins, G.; Desmulliez, M. P. Y. Inkjet Printing of Conductive Materials: A Review. *Circuit World* **2012**, *38* (4), 193–213.
- (6) Yin, Z. P.; Huang, Y. A.; Bu, N. bin; Wang, X. M.; Xiong, Y. L. Inkjet Printing for Flexible Electronics: Materials, Processes and Equipments. *Chinese Science Bulletin* **2010**, *55* (30), 3383–3407.
- (7) Kühnel, L.; Neumann, K.; Neises, J.; Langer, F.; Erni, D.; Schmechel, R.; Benson, N. Nanoparticle Ink-based Silicon Schottky Diodes Operating up to 2.84 GHz. *Nano Select* **2020**, *1* (6), 659–665.
- (8) Kim, S. J.; Yoon, S.; Kim, H. J. Review of Solution-Processed Oxide Thin-Film Transistors. *Japanese Journal of Applied Physics* **2014**, *53* (2 PART 2), 02BA02.
- (9) Eslamian, M. Inorganic and Organic Solution-Processed Thin Film Devices. *Nano-Micro Letters* **2017**, *9* (1), 1–23.
- (10) Zabihi, F.; Xie, Y.; Gao, S.; Eslamian, M. Morphology, Conductivity, and Wetting Characteristics of PEDOT:PSS Thin Films Deposited by Spin and Spray Coating. *Applied Surface Science* **2015**, *338*, 163–177.
- (11) Chaudhary, K. T. (2020). Thin Film Deposition: Solution Based Approach. In *Thin Film*. IntechOpen. doi:10.5772/intechopen.94455.
- (12) Cui, Z.; Liao, L. (2020). Coating and Printing Processes. In C. Zheng (Ed.). *Solution Processed Metal Oxide Thin Films for Electronic Applications* (pp 83-97). Elsevier.
- (13) Nayak, L.; Mohanty, S.; Nayak, S. K.; Ramadoss, A. A Review on Inkjet Printing of Nanoparticle Inks for Flexible Electronics. *Journal of Materials Chemistry C* **2019**, *7* (29), 8771–8795.

- (14) Lourenco, C.; Teixeira, M.; Simões, S.; Gaspar, R. Steric Stabilization of Nanoparticles: Size and Surface Properties. *International Journal of Pharmaceutics* **1996**, *138* (1), 1–12.
- (15) Zhao, B.; Brittain, W. J. Polymer Brushes: Surface-Immobilized Macromolecules. *Progress in Polymer Science (Oxford)* **2000**, *25* (5), 677–710.
- (16) Matyjaszewski, K. Atom Transfer Radical Polymerization (ATRP): Current Status and Future Perspectives. *Macromolecules* **2012**, *45* (10), 4015–4039.
- (17) Matyjaszewski, K. Advanced Materials by Atom Transfer Radical Polymerization. *Advanced Materials* **2018**, *30* (23), 1706441.
- (18) Matyjaszewski, K.; Xia, J. Atom Transfer Radical Polymerization. *Chemical Reviews* **2001**, *101* (9), 2921–2990.
- (19) Lee, A.; Sudau, K.; Ahn, K. H.; Lee, S. J.; Willenbacher, N. Optimization of Experimental Parameters to Suppress Nozzle Clogging in Inkjet Printing. *Industrial and Engineering Chemistry Research* **2012**, *51* (40), 13195–13204.
- (20) He, L.; Kurata, Y.; Inokuma, T.; Hasegawa, S. Analysis of SiH Vibrational Absorption in Amorphous SiO_x:H (0 ≤ x ≤ 2.0) Alloys in Terms of a Charge-Transfer Model. *Applied Physics Letters* **1993**, *63* (2), 162–164.
- (21) San Andrés, E.; del Prado, A.; Mártel, I.; González-Díaz, G.; Bravo, D.; López, F. J.; Fernández, M.; Bohne, W.; Röhrich, J.; Selle, B.; Sieber, I. Bonding Configuration and Density of Defects of SiO_xH y Thin Films Deposited by the Electron Cyclotron Resonance Plasma Method. *Journal of Applied Physics* **2003**, *94* (12), 7462–7469.
- (22) Han, S.; Kim, C.; Kwon, D. Thermal Degradation of Poly(Ethyleneglycol). *Polymer Degradation and Stability* **1995**, *47* (2), 203–208.
- (23) Kühnel, L.; Neumann, K.; Neises, J.; Langer, F.; Erni, D.; Schmechel, R.; Benson, N. Nanoparticle Ink-based Silicon Schottky Diodes Operating up to 2.84 GHz. *Nano Select* **2020**, *1* (6), 659–665.
- (24) Ma, J. W.; Lee, W. J.; Bae, J. M.; Jeong, K. S.; Oh, S. H.; Kim, J. H.; Kim, S. H.; Seo, J. H.; Ahn, J. P.; Kim, H.; Cho, M. H. Carrier Mobility Enhancement of Tensile Strained Si and SiGe Nanowires via Surface Defect Engineering. *Nano Letters* **2015**, *15* (11), 7204–7210.
- (25) Amjoud, M.; Reynes, A.; Morancho, R.; Carles, R. Comparative Study of Decomposition by Metal-Organic Chemical Vapour Deposition of Tetraethylsilane and Tetravinylsilane. *Journal of Materials Chemistry* **1992**, *2* (11), 1205–1208.
- (26) Ma, S. L.; Xu, B.; Xu, K. W.; Wu, X. L.; Chu, P. K. Annealing Behavior and Hardness Enhancement of Amorphous SiCN Thin Films. *Journal of Vacuum Science & Technology A: Vacuum, Surfaces, and Films* **2007**, *25* (5), 1407.
- (27) Khashan, K. S.; Ismail, R. A.; Mahdi, R. O. Synthesis of SiC Nanoparticles by SHG 532 Nm Nd:YAG Laser Ablation of Silicon in Ethanol. *Applied Physics A: Materials Science and Processing* **2018**, *124* (6), 443.
- (28) Sullivan, W.; Hettler, C.; Dickens, J. The Effects of Sub-Contact Nitrogen Doping on Silicon Carbide Photoconductive Semiconductor Switches. *Proceedings of the 2012 IEEE International Power Modulator and High Voltage Conference*, **2012**, 77–79.
- (29) Kuciński, K.; Hreczycho, G. Hydrosilylation and Hydroboration in a Sustainable

Manner: From Earth-Abundant Catalysts to Catalyst-Free Solutions. *Green Chemistry* **2020**, 22 (16), 5210–5224.

Chapter 5

Bubble Seeding Nanocavities: Multiple Polymer Foam Cell Nucleation by Polydimethylsiloxane Grafted Designer Silica Nanoparticles

In this Chapter we describe a successful strategy to substantially enhance cell nucleation efficiency in polymer foams by using designer silica nanoparticles as nucleating agents. Bare and poly(dimethylsiloxane) (PDMS) grafted surface roughness engineered silica nanoparticles with diameters from ~ 80 nm to ~ 200 nm were synthesized and exploited as highly efficient cell nucleants in CO₂-blown nanocellular poly(methyl methacrylate) (PMMA) foaming. The successful synthesis of core-shell nanoparticles was confirmed by Fourier transform infrared (FTIR) spectroscopy, thermogravimetric analysis (TGA), Brunauer-Emmett-Teller (BET) measurements, and transmission electron microscopy (TEM). The cell size and cell density of the PMMA micro- and nanocellular foams obtained were determined by scanning electron microscope (SEM). The results show that increased surface roughness enhances the nucleation efficiency of the designer silica particles. This is ascribed to a decreased nucleation free energy for foam cell nucleation in the nanocavities at the melt-nucleator interface. For PDMS grafted surface roughness engineered silica nanoparticles with a diameter of 155 nm and 200 nm multiple cell nucleation events were observed. These hybrid particles had nucleation efficiencies of 3.7 and 6.2, respectively. The surprising increase in nucleation efficiency to above unity is ascribed to the significant increase in CO₂ absorption and capillary condensation in the corresponding PMMA during saturation. This results in the presence of large amounts of the physical blowing agent

close to energetically favorable nucleating points. Additionally, it is shown that as a consequence of cell coalescence the increased number of foam cells is rapidly reduced during the first seconds of foaming. Hence, design of highly efficient nucleating particles, as well as a careful selection of foam matrix materials seem to be of pivotal importance to obtain polymer cellular materials with cell dimensions at the nanoscale. These findings contribute to the fabrication of polymer foams with high thermal insulation capacity, and have relevance in general for the area of cellular materials.

Parts of this Chapter has been published in: Liu, S.; Yin, S.; Duvigneau, J.; Vancso, G. J. Bubble Seeding Nanocavities: Multiple Polymer Foam Cell Nucleation by Polydimethylsiloxane-Grafted Designer Silica Nanoparticles. *ACS Nano* **2020**, *14* (2), 1623–1634. Yin and Liu both contributed to the particle synthesis, corresponding composite preparation, and subsequent batch foaming of the samples. Yin focused more on the particle synthesis and Liu later focused more on the elucidation on the nanocavity induced multiple bubble seeding mechanism.

5.1 Introduction

Nanocellular polymer foams are receiving considerable for a variety of reasons.^{1–6} The thermal conductivity of nanocellular foams is significantly reduced as a result of the Knudsen effect provided that the foam density is sufficiently low.^{3,7} In addition, the mechanical performance in terms of, e.g., the Young's modulus, impact properties and shore hardness is significantly improved compared to microcellular foams with similar foam densities.^{8–10} Thus nanocellular polymer foams with low thermal conductivity can offer great alternative options when considering new classes of materials for instance to achieve reductions in, for instant, fuel consumption and CO₂ emissions in transportation as well as the thermal energy management of buildings.

Nanocellular polymer foam structures can be obtained by various strategies, selective extraction/decomposition,^{11,12} templating/imprinting,^{13–15} chemical/physical foaming,^{2,8,16–19} *etc.* Among these methods, CO₂ based batch foaming is of particular interest, which is ascribed to good control over the foaming conditions, as well as to the low cost and environmental friendliness of CO₂ as a physical blowing agent.¹⁰ However, nanocellular foams fabricated via batch foaming with high porosities (> 85%) and cell densities (> 10¹⁴ cells cm⁻³) have rarely been reported.^{1,20–22} This is ascribed to the fact that it is difficult to nucleate the needed high cell densities in the early stages of foaming. In addition, on the timescale of foaming, cell coalescence is hard to avoid. Frequently used strategies to increase the nucleated cell density rely on increasing the physical blowing agent saturation pressure and/or increasing the pressure release rate.^{4,20,23} The introduction of nanostructured heterogeneous phases to polymers as heterogeneous nucleation sites prior to foaming has been considered a promising approach to obtain nanocellular foams. Examples utilized phase separated block copolymers^{24–27} and inorganic nanofillers as nucleating agents.^{6,17,28–32}

SiO₂ NPs are of particular interest to be employed as heterogeneous nucleation agents in polymer foaming because of their low cost, easy preparation and the simplicity of employing various surface decoration strategies.^{33,34} For instance, Zhai and coworkers³⁰ demonstrated that the incorporation of silica nanoparticles (SiO₂ NPs) in polycarbonate prior to foaming resulted in a higher cell density and more uniform cell size distribution compared to the polycarbonate foams containing no SiO₂ NPs as nucleating agents. Yang and coworkers³⁵ reported that the decoration of SiO₂ NPs with CO₂-philic poly(ionic liquid) significantly enhances the cell nucleation in CO₂ assisted polystyrene foaming compared to the polystyrene foams prepared with bare SiO₂ NPs as nucleating agents. Despite these promising results we note that the nanoparticles (NPs) utilized so far for

nucleation suffered from low nucleation efficiencies, i.e. the number of foam cells obtained per number of NPs per cm^3 added to the polymer matrix prior to foaming was small. Nucleation efficiencies for these inorganic particle based nanofillers are typically far below 0.01.^{17,35–37} This means that hundreds of added particles result in the formation of only 1 foam cell during foaming. In these calculations it is assumed that homogenous nucleation and cell coalescence can be neglected.⁴ Liu and coworkers²⁸ reported on the successful utilization of poly(dimethylsiloxane) (PDMS) grafted SiO_2 NPs with a silica core diameter of 80 nm with a nucleation efficiency of approximately 0.5 for the preparation of CO_2 batch blown poly(methyl methacrylate) (PMMA) foams. The good efficiency of these particles is ascribed to *i*) the low surface energy of the PDMS shell, which reduces the nucleation energy barrier, and *ii*) the higher local CO_2 concentration in the PDMS shell (~ 75 wt%)³⁸ compared to the PMMA matrix (~ 18 wt%).³⁹ Furthermore, they demonstrated that the contribution of line tension significantly reduces the nucleation efficiency of PDMS grafted NPs with a silica core diameter below 40 nm for the used foaming conditions (i.e. CO_2 saturation pressure of 55 bar and foaming at 40 °C).²⁸ Thus the use of smaller particles, e.g., 10 nanometer in diameter, is considered unfavorable while it would in principle allow for the addition of the required high number of potential nucleation sites ($> 10^{15} \text{ cm}^{-3}$) at relatively low weight percentages of particle loading. In fact, increasing the weight percentage of particle loading for particles with large enough diameters (> 60 nm) to incorporate the required number of potential nucleation sites renders the resulting particle filled polymer matrix barely foamable.

Recently, Yang and coworkers⁴⁰ established that cells nucleated from a concave surface have a lower nucleation free energy compared to the free energy of nucleation from flat or convex surfaces (e.g. spherical particles).^{41,42} Inspired by this work, we realized that the surface roughness is an often ignored, but important design parameter for nucleating hybrid particle designs to enhance nanocellular foaming.

One of the most commonly applied techniques to fabricate surface roughness engineered silica nanoparticles (SiO_2 -R NPs) includes attachment of NPs with substantially smaller radius. This method includes a two-step approach that relies on assembling smaller particles onto larger core particles via chemical or physical interactions, to result in the formation of SiO_2 -R NPs.^{43–46} By fine-tuning the diameter and concentration ratio of smaller and larger particles, NPs with a desired surface roughness values can be prepared. Puretskiy and coworkers⁴⁶ successfully exploited the attaching approach by first synthesizing poly(glycidyl methacrylate)-covered core SiO_2 NPs, followed by the attachment of amino-functionalized smaller SiO_2 NPs. Wu and coworkers⁴⁵ reported covalently bonding 70 nm and 700 nm SiO_2 NPs that were

functionalized with amino and epoxy groups, respectively, resulting in SiO₂-R NPs with a diameter of 850 nm. Polymer particles have also been used as the core particles to prepare SiO₂-R NPs with core-shell structure.^{47–49} For example, Xia et al.⁴⁸ reported on the fabrication of poly(styrene)-silica core-shell particles via emulsion polymerization to form a polystyrene (PS) core followed by a sol-gel reaction to coat a rough silica shell. Instead of a sol-gel reaction to attach the silica shell, Wang and coworker⁴⁷ used an attaching approach to achieve better surface topology. By covalently attaching smaller hydrolyzed SiO₂ NPs onto poly(ethyleneglycol dimethacrylate-co-4-vinylpyridine) core particles, they fabricated surface roughened hybrid NPs.

Another possibility to obtain designer NPs with surface roughness control includes using etching method. Recently, Du and coworkers⁵⁰ reported on the synthesis of SiO₂-R NPs by etching of nearly spherical SiO₂ NPs with sodium borohydride (NaBH₄). The surface exposed Si-O bonds dissolve at high pH, resulting in the dissolution of silicate species. Upon supersaturation of the nanoparticle dispersion, silica domains are re-deposited on the SiO₂ NPs surface to form a rough surface. Compared to the above discussed attaching methods, the etching method offers a simpler approach for SiO₂-R NPs fabrication.

In this Chapter we use both the attaching and the etching methods, respectively, to prepare surface roughness engineered SiO₂ NPs for their possible exploitation in a new application area, i.e. as foam cell nucleating agent in nanocellular foaming. Of particular interest is to evaluate the nucleation efficiency of surface roughness engineered particles in the CO₂ blown batch foaming of PMMA and compare the obtained nucleation efficiency values to various other silica nanoparticle based highly efficient nucleating particles.

We show that the SiO₂-R NPs are efficient foam cell nucleators with nucleation efficiencies that are comparable to their PDMS grafted nearly spherical counterparts. Upon decorating the SiO₂-R NPs with a few nanometer thick PDMS shell, multiple foam cell nucleation was observed from a single designer nanoparticle, and the value of highest nucleation efficiency obtained was 6.2 for particles with an overall core diameter of ~200 nm. This nucleation efficiency is nearly 40 times higher compared to that of a pristine, nearly spherical silica nanoparticle with a similar diameter. We show qualitatively that the high nucleation efficiency obtained for PDMS grafted SiO₂-R NPs is ascribed to a significantly increased absorption of CO₂ during saturation. This process results in a higher CO₂ concentration close to the PDMS decorated, and contributes to forming energetically favorable nanocavities at the nucleating surface. The utilization of

surface cavities combined with optimized surface chemistry for efficient heterogeneous nucleation at the macromolecular length scale is of interest for the production of nanocellular foams with high cell densities, and thus with superior thermal insulation properties.

5.2 Results and Discussion

5.2.1 SiO₂-R NPs Synthesis

Two different methods, i.e., attaching and etching, were investigated as methods to control the surface roughness of SiO₂ NPs. Both of these methods use Stöber SiO₂ NPs as the starting material(s).

Figure 5.1a depicts the reaction scheme for the attaching method to prepare SiO₂-R NPs. First, the small (80 nm) and large (600 nm) SiO₂ NPs were functionalized with (3-aminopropyl)-triethoxysilane (APTES) and (3-Glycidyloxypropyl)trimethoxysilane (GPS) to form amino- and epoxy- functionalized particles, respectively. Subsequently, the amino-functionalized SiO₂ NPs (SiO₂-NH₂) were covalently bonded to the epoxy-functionalized SiO₂ NPs (SiO₂-GPS) by the ring-opening of the epoxy group under nitrogen atmosphere, resulting in the formation of SiO₂-R NPs with a diameter of approximately 750 nm. Figure 5.1b shows a scanning electron microscope (SEM) image of SiO₂-R NPs prepared by the attaching method. From the SEM image in Figure 5.1b it is readily observed that the smaller particles attached tend to form large clusters on the larger SiO₂ NPs. Despite multiple attempts we did not obtain full surface coverage by using this approach. In addition, the multiple reaction steps, the relatively long reaction time, and the required dry atmosphere directed us towards using the etching method to produce surface roughened SiO₂ NPs.

Figure 5.1 (a) Scheme of the SiO₂-R NP preparation process via the attaching method. (b) SEM image of SiO₂-R NPs with a particle diameter of ~ 750 nm.

For the etching method, NaBH₄ was used to adjust the pH of the SiO₂ dispersion to

eventually yield rough particle surfaces. The reaction scheme is depicted in Figure 5.2a. During the surface roughening reaction, the high basicity of the dissolved NaBH_4 results in the dissociation of Si-O bonds from the surface of nearly smooth Stöber SiO_2 ($\text{SiO}_2\text{-S}$) NPs and subsequently in the formation of soluble mono- and polysilicate species. Eventually the dissolved silicate species in the solution become supersaturated, which leads to the redeposition of small SiO_2 NPs on the surface of the remaining silica NPs (Figure 5.2a, step 1).^{51–53}

SEM images of $\text{SiO}_2\text{-S}$ NPs and $\text{SiO}_2\text{-R}$ NPs with a diameter of approximately 155 nm are shown in Figure 5.2b and c, respectively. The diameter of the $\text{SiO}_2\text{-R}$ is defined as the diameter of a circle just large enough to enclose the $\text{SiO}_2\text{-R}$ NPs outer surface. Particles with diameters between 80 nm and 200 nm were prepared (see Figure S5.1). Hereinafter, the numbers preceeding the name SiO_2 refer to the apparent particle diameter. For instance, 155 $\text{SiO}_2\text{-S}$ refers to a nanoparticle with an average diameter of 155 nm.

From Figure 5.2c it is obvious that small silica domains (with diameters of ~ 20 to 30 nm) are present at the surface of the NPs after treatment with NaBH_4 , which is in agreement with the etching and subsequent deposition of silicate species at the silica particle surface during the reaction.⁵²

Following the successful synthesis of $\text{SiO}_2\text{-R}$ NPs with diameters of ~ 200 nm, ~ 155 nm, ~ 120 nm and ~ 80 nm, PDMS shells were grafted to each type, yielding the corresponding hybrid ($\text{SiO}_2\text{-RP}$) NPs (Figure 5.2a). In brief, $\text{SiO}_2\text{-R}$ NPs were derivatized with APTES, resulting in the formation of amine functionalized NPs ($\text{SiO}_2\text{-R-NH}_2$) (step 2). The NPs were functionalized by PDMS employing the “grafting to” approach of monoglycidyl ether terminated PDMS (step 3). We note here that prolonged sonication or even melt blending did not destroy the surface roughness of the (hybrid) $\text{SiO}_2\text{-R}$ NPs i.e. the NPs are stable enough for utilization as nucleating particles in nanocellular foaming.

Figure 5.2d shows the Fourier transform infrared (FTIR) absorbance spectra of SiO_2 , $\text{SiO}_2\text{-R}$, $\text{SiO}_2\text{-R-NH}_2$, $\text{SiO}_2\text{-RP}$ and nearly smooth PDMS grafted ($\text{SiO}_2\text{-SP}$) NPs with a (silica core) diameter of ~ 155 nm. The remaining ethoxy groups after the Stöber reaction of tetraethyl orthosilicate (TEOS) are clearly observed in the FTIR spectra of the 155 $\text{SiO}_2\text{-S}$ particles, i.e. the CH_2/CH_3 bending absorbance band at 1452 cm^{-1} and the CH_2/CH_3 absorbance band at 2980 cm^{-1} .⁵⁴ After NaBH_4 etching to yield surface roughened NPs these absorbance bands disappear, which indicates quantitative hydrolysis of the remaining ethoxy groups of the 155 $\text{SiO}_2\text{-R}$ NPs.⁵² The reappearance of

bands at 2980 cm^{-1} , 1450 cm^{-1} and 1380 cm^{-1} in the FTIR spectrum of $155\text{SiO}_2\text{-R-NH}_2$ are assigned to CH_2 groups of the propyl spacer of surface tethered APTES. The presence of absorption bands ascribed to CH_3 stretching at 2967 cm^{-1} and to C-H bending at 1263 cm^{-1} in the FTIR spectrum of $155\text{SiO}_2\text{-RP}$ NPs confirm the successful grafting of PDMS.⁵⁵ The same absorbances are observed in the FTIR spectrum of $\text{SiO}_2\text{-SP}$ NPs; their synthesis is described in the experimental section.

Figure 5.2 (a) A schematic of the $\text{SiO}_2\text{-RP}$ NPs preparation process. In (b) and (c) SEM images of $\text{SiO}_2\text{-S}$ and $\text{SiO}_2\text{-R}$ NPs with a silica particle diameter of $\sim 155\text{ nm}$ are shown, respectively. (d) Single reflection ATR-FTIR absorbance spectra of $155\text{SiO}_2\text{-S}$, $155\text{SiO}_2\text{-R}$, $155\text{SiO}_2\text{-R-NH}_2$, $155\text{SiO}_2\text{-RP}$ and $155\text{SiO}_2\text{-SP}$ NPs. The black arrows in the FTIR spectra indicate characteristic FTIR absorbance values of the (modified) NPs. (e) Non-isothermal TGA thermograms of the $155\text{SiO}_2\text{-S-NH}_2$, $155\text{SiO}_2\text{-R-NH}_2$, $155\text{SiO}_2\text{-SP}$ and $155\text{SiO}_2\text{-RP}$ NPs.

To determine the amount of PDMS grafted to the NPs, thermogravimetric analysis (TGA) was employed. Figure 5.2e shows the weight loss versus temperature curves for

non-isothermal TGA measurements of SiO₂S-S and SiO₂-R, amino-functionalized and PDMS grafted NPs with silica (core) diameters of approximately 155 nm. The results clearly show that the amount of PDMS covalently bound to the SiO₂ NPs with a rough surface is significantly higher, i.e. ~ 10.3 wt%, compared to that of spherical NPs, i.e. ~ 3.0 wt%. This nearly 3.4 fold increase in PDMS grafted weight is ascribed to the increased specific surface area for the SiO₂-R NPs as shown in Figure S5.1. For the NPs with a diameter of 155 nm the surface area increased from $33 \text{ m}^2 \text{ g}^{-1}$ to $116 \text{ m}^2 \text{ g}^{-1}$ for the spherical and SiO₂-R NPs, respectively (see Figure S5.1). The nearly 3.6 fold increase in surface area is in good agreement with the 3.4 times higher grafted amount of PDMS. For the SiO₂-R NPs with diameters of 200 nm and 120 nm the increase in PDMS grafting wt% were in good agreement with the corresponding increase in surface area as well.

Figure 5.3 TEM images of (a) 155SiO₂-S, (b) 155SiO₂-SP, (c) 155SiO₂-R and (d) 155SiO₂-RP NPs.

Based on the grafted PDMS mass obtained by TGA measurements, the molar mass of the grafted PDMS chains (i.e. $1,000 \text{ g mol}^{-1}$) and the Brunauer-Emmett-Teller (BET) surface area of the NPs the PDMS grafting densities were calculated to be ~ 0.6 chains nm^{-2} for the 155SiO₂-SP and 155-SiO₂-RP NPs. This number is lower compared to the earlier reported value of 0.9 for SiO₂-SP NPs with diameters of 12 nm to 120 nm, respectively.⁵⁶ This difference is ascribed to the known overestimation of the surface area of SiO₂ NPs determined by BET measurements^{57–59} compared to the simple arithmetic estimation of the nanoparticle surface area used, based on the particle diameters. When

using this simple arithmetic method, grafting density values close to $0.9 \text{ chains nm}^{-2}$ were obtained. This is in good agreement with values for $\text{SiO}_2\text{-SP}$ NPs reported in our previous work.⁶⁰ Based on these results we note that BET analysis is used here only to qualitatively show the significant differences in surface area of the particles before and after roughening their surface.

Finally, transmission electron microscope (TEM) was used to confirm the core-shell structure of the PDMS grafted NPs. Figure 5.3a-d shows TEM images of 155 nm bare and PDMS grafted spherical and $\text{SiO}_2\text{-R}$ NPs. From these TEM images it is clear that there is a thin PDMS shell around the 155 $\text{SiO}_2\text{-SP}$ (Figure 5.3b) and 155 $\text{SiO}_2\text{-RP}$ (Figure 5.3d) NPs. The thickness of the PDMS shell on the NPs was estimated to be around $6.0 \pm 1.5 \text{ nm}$, which agrees well with previous results reported for $\text{SiO}_2\text{-SP}$ NPs with silica core diameters from 12 nm to 120 nm.⁶⁰

Following successful synthesis and characterization of the NPs we employed them as nucleating agents in CO_2 assisted batch foaming of PMMA as presented and discussed in the next sections.

5.2.2 Nanocomposite Foaming and Multinucleation

Prior to foaming, $\text{SiO}_2\text{-R}$ and $\text{SiO}_2\text{-RP}$ NPs were melt blended in a PMMA matrix and pressed to films with thickness values of around $200 \mu\text{m}$. $\text{SiO}_2\text{-S}$ and $\text{SiO}_2\text{-SP}$ NPs were incorporated in PMMA matrix via the same procedure as control group. For comparison of the nucleation efficiency, NPs with the same volume number density (i.e. $1.07 \times 10^{13} \text{ particles cm}^{-3}$) were used for each nanocomposite film were used. Thus assuming a good particle dispersion in the PMMA films and that each particle can nucleate the same amount of foam cells, all nanocomposite films had the same volume number density of potential nucleation sites prior to foaming. The particles were well dispersed in PMMA prior to foaming as was observed from SEM images of cross sectioned PMMA nanocomposite films (See Figure S5.3).

The CO_2 saturation pressure used for foaming was 55 bar and following quick depressurization (i.e. within 2 seconds), foams were prepared at a foaming temperature of 40°C for 1 second. This relatively short foaming time was chosen since we were primarily interested in the nucleation efficiency of the prepared particles and not in the well developed foam morphology at the end stages of foaming (i.e. after several tens of seconds to minutes). Figure 5.4a-d show SEM images of cross sectioned PMMA foams nucleated by 155 $\text{SiO}_2\text{-S}$, 155 $\text{SiO}_2\text{-SP}$, 155 $\text{SiO}_2\text{-R}$ and 155 $\text{SiO}_2\text{-RP}$ NPs. It is clear that for the 1 second foaming time the PMMA foams have thick cell walls and struts.

Furthermore, the 155SiO₂-S, 155SiO₂-SP and 155SiO₂-R NPs are present at the polymer foam cell wall surface. The 155SiO₂-S NPs are more embedded in the PMMA cell wall compared to the 155SiO₂-SP, which can be attributed to the low surface energy and high CO₂-philicity of the decorated PDMS shell compared with the bare particles, resulting in variations in the strength of the interfacial interactions between the NPs and the polymer gas mixture.⁶⁰ This is in good agreement with the reported results for the nucleation behavior of pristine SiO₂ and corresponding PDMS grafted core shell NPs with (core) diameters up to 120 nm.^{28,60}

Interestingly, when examining the 155SiO₂-RP NPs embedded in the PMMA foams we observed that most of these particles are surrounded by a few primary polymer foam cells (see Figure 5.4d). Of particular interest is that the cell walls in between these primary foam cells are much thinner compared to the non nucleated/expanded PMMA matrix surrounding them and that the size of the cells around the 155SiO₂-RP particles is fairly uniform. This points towards simultaneous multiple heterogeneous nucleation events per added particle. In addition, the thin wall between some foam cells appears to be ruptured, or partly disappeared. This indicates that cell coalescence occurs during the initial stages of nucleation. An explanation for this behavior is provided later.

The presence of multiple nucleation events per 155SiO₂-RP particle is promising for developing nanocellular foams with increased cell densities. To exploit this option, it is of pivotal importance to obtain a deeper understanding of cell nucleation as a function of the surface roughening feature sizes. Therefore, we have prepared SiO₂-R and SiO₂-RP NPs with a diameter of ~ 80 nm, ~ 120 nm and ~ 200 nm to explore this idea. Figure S5.2 shows SEM images of 80SiO₂-R, 120SiO₂-R and 200SiO₂-R NPs. It is clear that the feature sizes of the roughened surfaces are different for the particles with different diameters, i.e. 80SiO₂-R has only a few small protrusions at its surface, while 200SiO₂-R reveals numerous larger protruding features (Figure S5.2). It turned out that for the etching method used the initial SiO₂ NP size has an impact on the particle roughness.⁵²

The SEM images of the cross sectioned PMMA foams nucleated by 80SiO₂-RP (Figure 5.4e) and 200SiO₂-RP (Figure 5.4f) NPs reveal distinct differences in the foam morphology, as well. For instance, 200SiO₂-RP clearly shows the presence of multiple cells around single nucleating particles, however, no multiple cell nucleation events are observed around single 80SiO₂-RP NPs.

Figure 5.4 SEM images of cross sectioned PMMA foams nucleated by (a) 155SiO₂-S, (b) 155SiO₂-SP, (c) 155SiO₂-R, (d) 155SiO₂-RP, (e) 80SiO₂-RP and (f) 200SiO₂-RP NPs. The white arrows in (d) and (f) point towards the particles showing multiple cell nucleation events per particle. The insets show higher magnification images of nucleating NPs in cross sectioned PMMA foam cells. The saturation pressure, foaming temperature and foaming time were 55 bar, 40 °C and 1 second, respectively.

Below we present quantitatively how the nucleation efficiency of SiO₂-RP NPs depends on the particles surface roughness for a PMMA foamed in 1 second. Figure 5.5 shows the cell size (4a), cell density (4b) and nucleation efficiency (4c) values for foams

nucleated by SiO₂-S, SiO₂-SP, SiO₂-R, and SiO₂-RP NPs as a function of the silica particle diameter.

Figure 5.5 (a) Foam cell size, (b) cell density and (c) cell nucleation efficiency for PMMA foams nucleated by SiO₂-S, SiO₂-SP, SiO₂-R and SiO₂-RP with diameters of ~ 80 nm, ~120 nm, ~ 155 nm and ~ 200 nm, respectively. The saturation pressure, foaming temperature and foaming time were 55 bar, 40 °C and 1 second, respectively. The inserts in Figure 5.5c show SEM images of cross sectioned PMMA foam cells showing the presence of multiple cells around single 155SiO₂-RP and 200SiO₂-RP NPs.

As can be clearly seen from Figure 5.5a, the average cell size nucleated with SiO₂-R and SiO₂-RP NPs are smaller compared to SiO₂-S and SiO₂-SP NPs with the same diameter, respectively. In addition, upon increasing the particule diameter from 80 to 200 nm, the average cell size decreases and the cell size distribution becomes narrower. SEM images of cross sectioned PMMA foams nucleated by 80SiO₂-RP particles did not reveal any multiple cell nucleation events per particle (see Figure 5.4e), while for 120SiO₂-RP this was observed for some particles (Figure S5.4). The decrease of multiple nucleation events is ascribed to a lower surface roughness of the 80-SiO₂-RP and 120SiO₂-RP NPs, resulting in a reduced number of effective nanocavities. However, for PMMA foams nucleated by 155SiO₂-RP and 200SiO₂-RP particles multiple cell nucleation events were

observed, which resulted in a higher CO₂ consumption during cell growth compared to the foams without multiple cell nucleation events occurring. This explains the reduction in cell size to 160 ± 50 nm and 110 ± 60 nm for foams with 155SiO₂-RP and 200SiO₂-RP particles, respectively.

The occurrence of multiple cell nucleation events for SiO₂-RP NPs with various roughnesses has, as expected, a significant effect on the cell density and nucleation efficiency values (Figure 5.5b and c). The use of 200SiO₂-RP NPs results in, similar to the 155SiO₂-RP NPs, a significant boost in cell density and cell nucleation efficiency compared to the other particle types. In fact, for the 200SiO₂-RP NPs the nucleation efficiency was ~ 6.2 , which is the highest nucleation efficiency reported so far.

In addition, 120SiO₂-R and 120SiO₂-RP particles have a higher nucleation efficiency compared to 120SiO₂-S and 120SiO₂-SP, respectively, as well (see Figure 5.5c). This is again qualitatively explained by the presence of the nanocavities. However, 80SiO₂-RP show a comparable nucleation efficiency with 80SiO₂-SP, which is ascribed to presence of mainly convex surface domains at its particle surface. Compared to concave surface roughness, convex structures have a higher cell nucleation free energy.^{41,42}

From Figure 5.5 it is obvious that for the particle sizes evaluated the SiO₂-R NPs have nucleation efficiencies comparable to SiO₂-SP NPs, while the SiO₂-S particles are the least effective nucleating agents. Overall it is shown that NPs designed with a concave surface roughness are more efficient when used as nucleation agents compared to the nearly spherical ones and that a combination of roughness with a CO₂-philic low surface energy PDMS shell has a very large synergetic effect on PMMA foam cell nucleation.

5.2.3 Multiple Foam Cells Nucleation Mechanism

The synergetic effect of a PDMS shell with the presence of cavities on the nucleation efficiency of SiO₂-RP NPs was much higher than expected. In fact, we reason that for the higher number of cells to grow, more CO₂ as a blowing agent must be available. Thus the CO₂ absorption of PMMA films containing SiO₂-S, SiO₂-SP, SiO₂-R and SiO₂-RP particles with diameters of ~ 80 nm, ~ 120 nm, ~ 155 nm and ~ 200 nm were determined in order to further elucidate the cell nucleation efficiency as a function of the particle type and size. The results are shown in Figure 5.6a. As is obvious, PMMA films containing SiO₂-S and SiO₂-SP have no significant differences in CO₂ absorption regardless of the particle diameter as compared to PMMA without NPs. The same is observed for 80SiO₂-R and 80SiO₂-RP NPs. Hence for these particles the overall CO₂ concentration is not altered while locally in the PMMA films the CO₂ concentration may vary due to the

presence of the PDMS shell. Upon increasing the surface roughness of the particles, e.g. for the 120SiO₂-R, 155SiO₂-R and 200SiO₂-R NPs, the amount of CO₂ absorbed is expected to significantly increase. The presence of a PDMS shell increases the amount absorbed even more for these NPs. For instance, for 200SiO₂-R and 200SiO₂-RP the increase in CO₂ absorbed was ~ 4.7 wt% and ~ 8.8 wt%, respectively, compared to the PMMA containing no particles (~ 18.2 wt%).

This increase in CO₂ absorption for the rough particles is ascribed to capillary condensation of CO₂ in the nanocavities.^{62–64} The even larger increase in CO₂ absorption for the rough particles with a PDMS shell with diameters of ~ 120 nm, ~ 155 nm and ~ 200 nm compared to their bare counterparts is ascribed to the presence of CO₂-philic molecules attached to the nanocavity surfaces, which is known to potentially enhance the absorption of CO₂.^{65–67}

The higher physical blowing agent concentration close to the particle surface is favorable for increasing the nucleation rate and combined with the presence of a low surface energy PDMS shell in the nanocavities the foam cell nucleation efficiency of these particles is significantly enhanced. Figure 5.6b shows a schematic representation of the proposed mechanism leading to multiple cell nucleation events for PDMS grafted SiO₂-R. Upon saturation of PMMA films containing SiO₂-RP NPs, CO₂ capillary condensation in the cavities results in the presence of significantly increased amounts of CO₂ in close proximity of the nucleating particle surface. The nanocavities are energetically favorable nucleating sites and together with the increased amount of available CO₂, result in more than 1 nucleating event per particle (step A), subsequent cell growth (step B), and cell coalescence (step C). This is further experimentally confirmed by the development of the foam cell morphology as a function of the foaming time for PMMA foams nucleated by 155SiO₂-RP NPs, as shown in Figure 5.6c-f. Upon increasing of foaming time, the cell walls in between these primary foam cells nucleated from the same single 155SiO₂-RP appears to be ruptured or partly disappeared, leading to the cells coalescence. In addition, the cell size and cell nucleation efficiency for PMMA foams, obtained with 155SiO₂-S, 155SiO₂-SP, 155SiO₂-R and 155SiO₂-RP NPs, were also determined as a function of the foaming time (see Figure S5.5).

Figure 5.6 (a) CO₂ absorption for PMMA films containing SiO₂-S, SiO₂-SP, SiO₂-R and SiO₂-RP particles with diameters between 80 nm to 200 nm. The saturation pressure and time were 55 bar and 4h, respectively. The dashed line shows the CO₂ absorption of PMMA containing no NPs. (b) Schematic representation of the nucleation of multiple cells from PDMS grafted SiO₂-R NPs. SEM images of cross sectioned PMMA foams nucleated by 155SiO₂-RP NPs for (c) 10 seconds, (d) 5 second, (e) 1 seconds and (f) 0.3 seconds. In the insets, the foam cell wall around a single nanoparticle is shown. The saturation pressure and foaming temperature were 55 bar and 40 °C, respectively.

Overall, we presented that by incorporating PDMS decorated SiO₂-R NPs in PMMA matrix, multiple cell nucleation events per nanoparticle can be achieved. The designer NPs we developed and prepared in this Thesis exhibit significantly higher cell nucleation efficiency in PMMA nanocellular foaming compared to their bare and nearly spherical counterparts. We have also exploited 155SiO₂-RP NPs in the CO₂ assisted batch foaming of polystyrene and the corresponding SEM images revealed the occurrence of multiple cell nucleation events as well (see Figure S5.6). Hence, these hybrid core shell NPs are very promising as highly efficient cell nucleation agents in polymer nanocellular foaming in general.

To fully exploit the high nucleation efficiency of SiO₂-RP particles it is of pivotal importance to find foaming strategies and foam matrices that allow both the introduction

of a high number of cell nuclei and also ensure early cell stabilization during the foaming process to prevent cell coalescence. For instance, without optimization of any of the foaming parameters and or composition of the PMMA nanocomposite matrix we have obtained a high cell density of $\sim 6.6 \times 10^{13}$ cells cm^{-3} , which is already very close to the order of magnitude of interest for superior thermal isolation (i.e. 10^{14} cells cm^{-3}). Future work must be directed to developing new strategies for sufficiently increasing the surface roughness of NPs with a particle diameter < 100 nm. This is essential since at the same weight percentage of particle loading a higher number of effective nucleation agents is available when smaller particles are used.

5.3 Conclusion

In summary, SiO_2 -R NPs were synthesized via attaching and etching approaches. Particles synthesized via the attaching method showed unevenly distributed smaller particles on the larger core particles. The fact that the attaching method can only achieve partial coverage and the long reaction time required, directed us towards exploring the etching method to prepare SiO_2 -R NPs. The etching method resulted in the uniform formation of small (20-30 nm) silica domains covering the surface of SiO_2 -R NPs. The SiO_2 -R NPs synthesized via the etching method were successfully exploited as efficient nucleation agents in CO_2 -blown PMMA nanocellular foaming. Compared to nearly spherical SiO_2 NPs, SiO_2 -R NPs exhibit a higher nucleation efficiency after being incorporated in the PMMA matrix due to the lower critical nucleation energy. Multiple nucleating events per particle were observed for SiO_2 -RP NPs with core diameters of 155 nm and 200 nm, respectively. The highest nucleation efficiency obtained was 6.2 for 200 SiO_2 -RP NPs. The significantly higher nucleation efficiency (well above unity) of the core-shell surface roughed silica NPs is attributed to the synergetic effect of the thin PDMS shell combined with the presence of nanocavities on the NPs' surface as well as the higher CO_2 absorption. This results in an increased physical blowing agent concentration available for nucleation close to the energetically favorable nanocavities as nucleating sites. Hence, PDMS decorated, core-shell surface roughed silica NPs are very promising to be used as an interesting class of highly efficient nucleation agents. To increase our understanding of multiple cell nucleation events by PDMS decorated core-shell surface roughed silica NPs, future work should be directed to the quantification of the relationship between nucleation energy barrier and surface cavity structure dimensions, as well optimization of foaming conditions to stabilize the nucleated multiple cells during the early stages of foaming.

5.4 Materials and Methods

Materials. PMMA was obtained from Arkema (VM100, i.e. a PMMA-co-EA polymer, $\rho = 1.18 \text{ g cm}^{-3}$) (La Garenne-Colombes, France). Absolute ethanol for analysis was purchased from Merck (Darmstadt, Germany). Absolute tetrahydrofuran (THF), 2-propanol 99.8% and chloroform 99.9% were acquired from Biosolve (Valkenswaard, the Netherlands). Monoglycidyl ether terminated poly(dimethylsiloxane) (PDMS-G) ($M_w = 1000 \text{ g mol}^{-1}$), ammonium hydroxide solution 28–30%, (3-aminopropyl)triethoxysilane $\geq 98\%$ (APTES), Sodium borohydride purum p.a., $\geq 96\%$ (gas-volumetric) (NaBH_4), polyvinylpyrrolidone with a molar mass of $40,000 \text{ g mol}^{-1}$ (PVP40), (3-Glycidyloxypropyl)trimethoxysilane $\geq 98\%$ (GPS), and tetraethyl orthosilicate (TEOS) $\geq 99.0\%$ were purchased from Sigma-Aldrich (St. Louis, MO, USA). Milli-Q water was produced by a Millipore Synergy System (Billerica, MA, USA). Unless otherwise mentioned, all other chemicals were used as received.

Stöber Silica Nanoparticle Synthesis. Nearly smooth Stöber silica nanoparticles (SiO_2 -S NPs) with a diameter of $\sim 80 \text{ nm}$, $\sim 120 \text{ nm}$, $\sim 155 \text{ nm}$, $\sim 180 \text{ nm}$ $\sim 200 \text{ nm}$, $\sim 310 \text{ nm}$ and 600 nm were prepared by the Stöber method. To prepare SiO_2 -S NPs with a diameter of $\sim 155 \text{ nm}$, 100 ml ethanol was mixed with 8 ml Milli-Q water and 10 ml TEOS in the presence of 5 ml ammonium hydroxide while stirring at 500 rpm at 50°C . After 4.5 hours the SiO_2 -S NP dispersion obtained was centrifuged at 10,000 rpm for 30 min. Subsequently, the collected SiO_2 -S NPs were redispersed in ethanol and centrifuged again. This washing step was repeated 2 more times followed by vacuum drying the collected SiO_2 -S NPs at room temperature for 12 hours. To prepare SiO_2 -S NPs with a diameter of $\sim 80 \text{ nm}$, 168 ml ethanol was mixed with 28 ml Milli-Q water and 30 ml TEOS in the presence of 2 ml ammonium hydroxide while stirring for 1.5 hours at 500 rpm at room temperature. To synthesize the $\sim 120 \text{ nm}$ particles 100 ml ethanol was mixed with 8 ml Milli-Q water and 5 ml TEOS in a round bottom flask stirring at 500 rpm and subsequently 5 ml of ammonium hydroxide was added and reacted for 3 hours at 50°C . To synthesize the $\sim 180 \text{ nm}$ particles 100 ml of ethanol was mixed with 8 ml Milli-Q water and 10 ml TEOS in the presence of 5.3 ml ammonium hydroxide in a 250 ml round bottom flask while stirring at 500 rpm. The reaction was conducted for 4.5 hours at 50°C . To synthesize the $\sim 200 \text{ nm}$ particles 100 ml of ethanol was mixed with 8 ml Milli-Q water and 10 ml TEOS in the presence of 5.6 ml ammonium hydroxide in a 250 ml round bottom flask while stirring at 500 rpm. The reaction was conducted for 4.5 hours at 50°C . To synthesize the $\sim 310 \text{ nm}$ particles 100 ml ethanol was mixed with 8 ml Milli-Q water and 10 ml TEOS in a round bottom flask stirring at 500 rpm and subsequently 7.0

ml of ammonium hydroxide was added and reacted for 4.5 hours at 50 °C. To synthesize the ~600 nm particles 75 ml 2-propanol was mixed with 25 ml methanol and 10 ml TEOS in a round bottom flask stirring at 270 rpm and subsequently 21 ml of ammonium hydroxide was added and reacted for 24 h at room temperature. The collecting, washing and drying steps of NPs were the same as described for NPs of ~155 nm.

Silica Nanoparticle Hydrolysis. To introduce silanol groups on the surface of the prepared SiO₂-S NPs, these were redispersed in Milli-Q water by sonication (BRANSON 2510, Canada) for 1 hour. Subsequently, hydrochloric acid was added to the dispersion while stirring at 500 rpm until the pH of the solution reached a value of approximately 1. After 4 hours the dispersion was centrifuged at 10,000 rpm for 30 min. The collected NPs were redispersed in Milli-Q water and centrifuged again. This washing step was repeated 2 more times followed by drying the silanol functional NPs (SiO₂-OH) under vacuum at room temperature for 12 hours.

Amino-Functionalization of Silica Nanoparticles. 1.5 g SiO₂-OH NPs were redispersed in 50 ml ethanol followed by the addition of 7.5 ml APTES. The dispersion was left to stir at 500 rpm at room temperature for 17 hours. The APTES functionalized NPs (SiO₂-NH₂) were collected by centrifugation at 10,000 rpm for 30 min and redispersed in ethanol and centrifuged again. This washing step was repeated 2 more times followed by drying the collected SiO₂-NH₂ NPs under vacuum at room temperature for 12 hours.

Epoxy-Functionalization of Silica Nanoparticles. 1.5 g of SiO₂-S (600 nm) were re-dispersed in 40 mL dry toluene, followed by addition of 0.2 g GPS in 5 mL dry toluene in dropwise under vigorous stirring. The suspension was stirred at 50 °C under N₂ atmosphere for 24 h. The GPS grafted SiO₂ NPs (SiO₂-GPS) were collected by centrifugation and washed with toluene twice, then vacuum dried at 50 °C for 12 h.

Grafting to of PDMS-G to Silica Nanoparticles. 1.0 g of SiO₂-NH₂ NPs were redispersed in 20.5 ml THF and 15 g PDMS-G while stirring at 500 rpm for 1 hour followed by sonication for 1 hour. Subsequently, THF was removed by rotary evaporation and the resulting silica nanoparticle dispersion in PDMS-G was immersed in an oil bath thermostated at 80 °C for 17 h. Following cooling to room temperature the reaction mixture was washed with THF and centrifuged at 10,000 rpm for 30 min. This washing step was repeated 2 more times, followed by vacuum drying the PDMS-G grafted silica NPs (SiO₂-SP) at room temperature for 12 hours.

Synthesis and Modification of Surface Roughness Engineered Silica

Nanoparticles via the Attaching Method. 0.3 g SiO₂-NH₂ (80 nm) were suspended in 20 mL ethanol. Next, 0.6 g of SiO₂-GPS (600 nm) were suspended in 15 ml ethanol, which were then added dropwise to the SiO₂-NH₂ suspension. The suspension was refluxed at 70 °C for 24 h under N₂ flux. The SiO₂-R were collected by centrifugation and washed with ethanol twice, followed by vacuum drying at 50 °C for 16 h.

Synthesis and Modification of Surface Roughness Engineered Silica Nanoparticles via the Etching Method. To synthesize NPs with enhanced surface roughness of ~ 80 nm, 0.3 g SiO₂-S NPs of ~ 80 nm and 0.25 g PVP were redispersed in 10 ml Milli-Q water by sonication for 30 min. Subsequently, 0.6 g NaBH₄ was added to the dispersion while stirring at 500 rpm at room temperature for another 30 min. The resulting mixture was reacted at 50 °C for 1 hour and 15 min. Stöber silica NPs with diameters of ~ 155 nm, ~ 180 nm and ~ 310 nm were used to synthesize rough surface NPs of ~ 120 nm, ~ 155 nm and ~ 200 nm, respectively, and the reaction were conducted for 3 hours and 20 min, 3.5 hours, and 6 hours, respectively. The other steps for synthesis of these surface rough NPs (with diameters from 120 to 220 nm) were the same as described for the synthesis of rough surface NPs of ~ 80 nm. Subsequently, The obtained NPs featuring rough surfaces were collected by centrifugation at 10,000 rpm for 30 min and redispersed in Milli-Q water and centrifuged again. This washing step was repeated 2 more times followed by drying the collected NPs in vacuum at room temperature for 12 hours. The process of amino-functionalization and grafting to of PDMS-G to the rough surface NPs were the same as described for the Stöber silica NPs.

Nanocomposite Preparation. Nanocomposites were prepared by dispersing the same amount of (functional) silica NPs ($1.07 \times 10^{13} \text{ cm}^{-3}$) in PMMA with a mini extruder (DSM Xplore, the Netherlands). In a typical procedure a dry blend of NPs and PMMA was fed to the extruder followed by internal mixing for 3 minutes. The barrel temperature was set to 155 °C and the screw speed was 100 rpm. Subsequently the PMMA nanocomposite was collected and left to cool to room temperature.

Film Preparation. A hot press (Fontijne, the Netherlands) was used to press ~ 0.2 mm thick nanocomposite films in a mold (4 × 3 cm). The press temperature, applied load and press time were 180 °C, 250 kN and 10 minutes, respectively.

Batch Foaming of Nanocomposite Films. The nanocomposite PMMA films were saturated with CO₂ (55 bar) in an autoclave for 4 hours at room temperature followed by rapid depressurization. Subsequently, the PMMA nanocomposite films were immersed in a water bath thermostated at 40 °C for different foaming time (0.3 second, 1 second, 5 second, 10 second and 30 second) after which the samples were quenched in an ice bath

for 30 minutes. The samples were left to dry in air for at least 12 hours prior to further analysis.

Fourier Transform Infrared Spectroscopy. FTIR spectra were collected with a Bruker ALPHA single attenuated total reflection (ATR) FTIR Spectrometer equipped with an ATR single reflection crystal (Bruker Optic GmbH, Ettlingen, Germany). The spectra were collected in the range of $400 - 4000\text{ cm}^{-1}$ (spectral resolution of 4 cm^{-1} , 128 scans). Background spectra were recorded against air.

Thermogravimetric Analysis. The weight loss of the (modified) particles as a function of temperature was measured with a TGA400 (PerkinElmer, Inc., Waltham, MA, USA). A sample weighing $\sim 3 - 6\text{ mg}$ was loaded into the platinum pan and the temperature was set to $50\text{ }^{\circ}\text{C}$ to stabilize. Subsequently the sample was heated to $900\text{ }^{\circ}\text{C}$ at a heating rate of $20\text{ }^{\circ}\text{C min}^{-1}$. The applied air flow was 20 ml min^{-1} .

Transmission Electron Microscopy. TEM was performed by a FEI/Philips CM300 system (Eindhoven, the Netherlands). Diluted particle dispersions in THF were deposited on the carbon side of a carbon/copper grid (HC200-Cu) (EMS, Germany) prior to imaging. Images were obtained in the bright field mode with a 300 kV acceleration voltage.

Scanning Electron Microscopy. For SEM a high-resolution scanning electron microscope (JEOL Field Emission JSM-6330F, JEOL Benelux, Nieuw-Vennep, the Netherlands) was employed using an acceleration voltage of 5 keV . Prior to analysis the nanocomposite foams were freeze fractured following cooling in liquid nitrogen for 5 minutes.

Surface Area Measurements of Nanoparticles. The specific surface area of the NPs was measured by determining nitrogen adsorption isotherm obtained at $300\text{ }^{\circ}\text{C}$ using an ASAP 2010 Sorptometer (Micromeritics). Around 100 mg nanoparticle powder was used for each measurement.

CO₂ Absorption Measurement. To measure the absorption of CO₂ PMMA nanocomposite films containing the same amount of the respective NPs were saturated in CO₂ at 55 bar for 4 hours. The weight of the PMMA (nanocomposite) films before and after CO₂ saturation were measured.

Calculation of PDMS Grafting Density. The grafting density (D) of PDMS decorated NPs surface was determined according to equation 1.

$$D = \frac{K*(m/M)}{S} \quad \text{eq.1}$$

$K = 6.02 * 10^{23} \text{ mol}^{-1}$ which is Avogadro's number, m is the weight of PDMS grafted per gram NPs (determined from TGA). $M = 1,000 \text{ g}\cdot\text{mol}^{-1}$, which is the molar mass of the used PDMS. S is the surface area per gram NPs, which was determined by BET.

Calculation of Cell Density and Nucleation Efficiency. The cell size and cell density were obtained by analyzing the obtained SEM cross sectional images. Cell density (N_v) of the foams was calculated according to Kumar's theoretical approximation.⁶⁸ No direct measurements of cell dimensions over the micrograph are required in this method, only the micrograph area (A) and the total number of cells (n) contained therein are measured. Together with the magnification factor of the micrograph (M), N_v can be calculated according to equation 2.

$$N_v = \left[\frac{(nM^2)}{A} \right]^{3/2} \quad \text{eq.2}$$

By combining N_v with the volume expansion ratio (B) of nanocomposite films after foaming, the cell numbers per cm^3 of unfoamed materials (N) can be calculated according to equation 3.

$$N = N_v * B \quad \text{eq.3}$$

The mentioned cell density in the main text are all refer to N . In addition, the nucleation efficiency (f) of NPs during foaming can be calculated as:

$$f = N/C \quad \text{eq.4}$$

Where C is the number of NPs per cm^3 (i.e., 1.07×10^{13}) used for foaming.

Figure S5.7 shows how we calculated the amount of cells in the occasion of multiple cell nucleating events occurring around a particle.

5.5 Supporting Information

Figure S5.1 The specific surface area determined by BET measurements of SiO₂-S and SiO₂-R NPs with a diameter of ~80 nm, ~120 nm, ~155 nm and ~200 nm.

BET measurements were used to determine the surface area of the prepared silica NPs. The results are shown in Figure S5.1. It is obvious that the surface area of NPs was significantly increased after NaBH₄ treatment. For the NPs with a diameter of 155 nm the surface area increased from 32.4 m² g⁻¹ (155SiO₂-S) to 116.0 m² g⁻¹ (155SiO₂-R). Nearly 3.6 fold increase in surface area is in good agreement with the 3.4 times higher grafted amount of PDMS to these particles.

Figure S5.2 SEM images showing SiO₂-R NPs with a diameter of (a) 80 nm, (b) ~120 nm, and (c) ~200 nm.

Figure S5.2 shows the SEM images of the SiO₂-R NPs with diameters of ~80 nm, ~

120 nm and ~ 200 nm. Figure S5.3 shows cross sectional SEM images of the 80 nm series of particles melt blended in PMMA as a representative case to demonstrate the particle dispersion in the composite. From Figure S5.3 it is clear that a good particle dispersion was obtained by melt blending.

Figure S5.3 Cross sectional SEM images showing the dispersion of (a) 80SiO₂-S, (b) 80SiO₂-SP, (c) 80SiO₂-R and (d) 80SiO₂-RP NPs in PMMA.

Figure S5.4 SEM images of cross sectioned PMMA foams nucleated by 120SiO₂-RP NPs. The saturation pressure, foaming temperature and foaming time were 55 bar, 40 °C and 1 second, respectively. The white arrows point towards the particles showing multiple cell nucleation events per particle.

Figure S5.4 shows the SEM images of cross sectioned PMMA foams nucleated by 120SiO₂-RP NPs. The multiple cells nucleation events were observed for some of the particles.

Figure S5.5 (a) Foam cell size and (b) cell nucleation efficiency as a function of foaming time for PMMA foams nucleated by 155SiO₂-S, 155SiO₂-SP, 155SiO₂-R and 155SiO₂-RP NPs. The used saturation pressure and foaming temperature were 55 bar and 40 °C, respectively.

The cell size and cell nucleation efficiency for PMMA foams nucleated by 155SiO₂-

S, 155SiO₂-SP, 155SiO₂-R and 155SiO₂-RP NPs were determined as a function of the foaming time. The results are shown in Figure S5.5. It is obvious that regardless of the type of NP used cell size of the corresponding PMMA foams increases as a function of foaming time up to 10 seconds after which it reaches a plateau value with a size value that depends on the nucleating particle type used.

The cell nucleation efficiency of PMMA foams containing 155SiO₂-SP NPs is higher compared to those containing 155SiO₂-S NPs for the same foaming time (as shown in Figure S5.5b), which is ascribed to the high CO₂-philicity and low surface energy of the thin PDMS shell of the 155SiO₂-SP NPs.⁵⁶ Interestingly, the SiO₂-R NPs, i.e. 155SiO₂-R NPs, show a higher cell nucleation efficiency compared to that of 155SiO₂-S NPs, as well. This is ascribed to the presence of cavities on the SiO₂-R NP surfaces, resulting in energetically favorable cell nucleation.⁴⁰ The nucleation efficiency of 155SiO₂-RP decreases upon increasing the foaming time. This is due to the observed cell coalescence occurring during the early stages of foaming (see Figure 5.5c-f). Notably, the nucleation efficiency of 155SiO₂-RP NPs is well above 1 within the first 10 seconds of foaming, which is ascribed to the multiple cell nucleation events occurring per nucleating 155SiO₂-RP NPs. The excellent nucleation performance of 155SiO₂-RP NPs is ascribed to the energetically favorable cell nucleation from the particles surface cavities combined with the presence of a CO₂ philic PDMS layer around the 155SiO₂-RP NPs.^{40–42}

Figure S5.6 SEM images of cross sectioned polystyrene foams nucleated by 150SiO₂-RP NPs. The saturation pressure, foaming temperature and foaming time were 55 bar, 100 °C and 1 second, respectively. The white arrows point towards the particles showing multiple cell nucleation events per particle.

Figure S5.7 SEM image showing multiple nucleating events at individual 200SiO₂-RP NPs. The white arrows point at the cells we included in the calculation of the cell density. We counted cells only when the cell walls were clearly visible.

5.6 References

- (1) Costeux, S. CO₂-Blown Nanocellular Foams. *Journal of Applied Polymer Science* **2014**, *131* (23), 10.1002/app.41293.
- (2) Mills, N. J. Handbook of Polymeric Foams and Foam Technology. *Polymer* **1993**, *34* (10), 2237.
- (3) Forest, C.; Chaumont, P.; Cassagnau, P.; Swoboda, B.; Sonntag, P. Polymer Nano-Foams for Insulating Applications Prepared from CO₂ Foaming. *Progress in Polymer Science* **2015**, *41* (C), 122–145.
- (4) Liu, S.; Duvigneau, J.; Vancso, G. J. Nanocellular Polymer Foams as Promising High Performance Thermal Insulation Materials. *European Polymer Journal* **2015**, *65*, 33–45.
- (5) Notario, B.; Pinto, J.; Rodriguez-Perez, M. A. Nanoporous Polymeric Materials: A New Class of Materials with Enhanced Properties. *Progress in Materials Science* **2016**, *78–79*, 93–139.
- (6) Lee, L. J.; Zeng, C.; Cao, X.; Han, X.; Shen, J.; Xu, G. Polymer Nanocomposite Foams. *Composites Science and Technology* **2005**, *65* (15-16 SPEC. ISS.), 2344–2363.
- (7) Notario, B.; Pinto, J.; Solorzano, E.; de Saja, J. A.; Dumon, M.; Rodríguez-Pérez, M. A. Experimental Validation of the Knudsen Effect in Nanocellular Polymeric Foams. *Polymer* **2015**, *56*, 57–67.
- (8) Pinto, J.; Notario, B.; Verdejo, R.; Dumon, M.; Costeux, S.; Rodriguez-Perez, M. A. Molecular Confinement of Solid and Gaseous Phases of Self-Standing Bulk Nanoporous Polymers Inducing Enhanced and Unexpected Physical Properties.

- Polymer* **2017**, *113*, 27–33.
- (9) Notario, B.; Pinto, J.; Rodríguez-Pérez, M. A. Towards a New Generation of Polymeric Foams: PMMA Nanocellular Foams with Enhanced Physical Properties. *Polymer* **2015**, *63*, 116–126.
 - (10) Lee, S. T.; Ramesh, N. S. Polymeric Foams: Mechanisms and Materials; 2004.
 - (11) Li, L.; Shen, X.; Hong, S. W.; Hayward, R. C.; Russell, T. P. Fabrication of Co-Continuous Nanostructured and Porous Polymer Membranes: Spinodal Decomposition of Homopolymer and Random Copolymer Blends. *Angewandte Chemie - International Edition* **2012**, *51* (17), 4089–4094.
 - (12) Zhang, X.; Chang, D.; Liu, J.; Luo, Y. Conducting Polymer Aerogels from Supercritical CO₂ Drying PEDOT-PSS Hydrogels. *Journal of Materials Chemistry* **2010**, *20* (24), 5080–5085.
 - (13) Hedrick, J. L.; Miller, R. D.; Hawker, C. J.; Carter, K. R.; Volksen, W.; Yoon, D. Y.; Trollsås, M. Templating Nanoporosity in Thin-Film Dielectric Insulators. *Advanced Materials* **1998**, *10* (13), 1049–1053.
 - (14) Park, S. H.; Xia, Y. Macroporous Membranes with Highly Ordered and Three-Dimensionally Interconnected Spherical Pores. *Advanced Materials* **1998**, *10* (13), 1045–1048.
 - (15) du Fresne Von Hohenesche, C.; Schmidt, D. F.; Schädler, V. Nanoporous Melamine - Formaldehyde Gels by Microemulsion Templating. *Chemistry of Materials* **2008**, *20* (19), 6124–6129.
 - (16) Bledzki, A. K.; Faruk, O. Effects of the Chemical Foaming Agents, Injection Parameters, and Melt-Flow Index on the Microstructure and Mechanical Properties of Microcellular Injection-Molded Wood-Fiber/Polypropylene Composites. *Journal of Applied Polymer Science* **2005**, *97* (3), 1090–1096.
 - (17) Zeng, C.; Han, X.; Lee, L. J.; Koelling, K. W.; Tomasko, D. L. Polymer-Clay Nanocomposite Foams Prepared Using Carbon Dioxide. *Advanced Materials* **2003**, *15* (20), 1743–1747.
 - (18) Park, C. B.; Behraves, A. H.; Venter, R. D. Low Density Microcellular Foam Processing in Extrusion Using CO₂. *Polymer Engineering and Science* **1998**, *38* (11), 1812–1823.
 - (19) Tomasko, D. L.; Li, H.; Liu, D.; Han, X.; Wingert, M. J.; Lee, L. J.; Koelling, K. W. A Review of CO₂ Applications in the Processing of Polymers. *Industrial and Engineering Chemistry Research* **2003**, *42* (25), 6431–6456.
 - (20) Costeux, S.; Zhu, L. Low Density Thermoplastic Nanofoams Nucleated by Nanoparticles. *Polymer* **2013**, *54* (11), 2785–2795.
 - (21) Costeux, S.; Bunker, S. P.; Jeon, H. K. Homogeneous Nanocellular Foams from Styrenic-Acrylic Polymer Blends. *Journal of Materials Research* **2013**, *28* (17), 2351–2365.
 - (22) Liao, Z. E.; Yeh, S. K.; Chu, C. C.; Tseng, T. W. Critical Parameters of Generating PMMA Nanocellular Foam. *Proceedings of the Annual Technical Conference* **2016**, 1773–1778.
 - (23) Tammara, D.; Astarita, A.; di Maio, E.; Iannace, S. Polystyrene Foaming at High Pressure Drop Rates. *Industrial and Engineering Chemistry Research* **2016**, *55* (19), 5696–5701.
 - (24) Pinto, J.; Dumon, M.; Pedros, M.; Reglero, J.; Rodriguez-Perez, M. A.

- Nanocellular CO₂ Foaming of PMMA Assisted by Block Copolymer Nanostructuration. *Chemical Engineering Journal* **2014**, *243*, 428–435.
- (25) Li, L.; Nemoto, T.; Sugiyama, K.; Yokoyama, H. CO₂ Foaming in Thin Films of Block Copolymer Containing Fluorinated Blocks. *Macromolecules* **2006**, *39* (14), 4746–4755.
- (26) Spitael, P.; Macosko, C. W.; McClurg, R. B. Block Copolymer Micelles for Nucleation of Microcellular Thermoplastic Foams. *Macromolecules* **2004**, *37* (18), 6874–6882.
- (27) Yokoyama, H.; Sugiyama, K. Nanocellular Structures in Block Copolymers with CO₂-Philic Blocks Using CO₂ as a Blowing Agent: Crossover from Micro- to Nanocellular Structures with Depressurization Temperature. *Macromolecules* **2005**, *38* (25), 10516–10522.
- (28) Liu, S.; Zoetebier, B.; Hulsman, L.; Zhang, Y.; Duvigneau, J.; Vancso, G. J. Nanocellular Polymer Foams Nucleated by Core-Shell Nanoparticles. *Polymer* **2016**, *104*, 22–30.
- (29) Ji, G.; Zhai, W.; Lin, D.; Ren, Q.; Zheng, W.; Jung, D. W. Microcellular Foaming of Poly(Lactic Acid)/Silica Nanocomposites in Compressed CO₂: Critical Influence of Crystallite Size on Cell Morphology and Foam Expansion. *Industrial and Engineering Chemistry Research* **2013**, *52* (19), 6390–6398.
- (30) Zhai, W.; Yu, J.; Wu, L.; Ma, W.; He, J. Heterogeneous Nucleation Uniformizing Cell Size Distribution in Microcellular Nanocomposites Foams. *Polymer* **2006**, *47* (21), 7580–7589.
- (31) Yuan, H.; Xiong, Y.; Luo, G.; Shen, Q.; Zhang, L. The Influence of in Situ Synthesized Nanoparticles on Microstructure and Compression Properties of Polymer Foams during Supercritical Carbon Dioxide Foaming. *Journal of Applied Polymer Science* **2017**, *134* (14).
- (32) Rende, D.; Schadler, L. S.; Ozisik, R. Controlling Foam Morphology of Poly(Methyl Methacrylate) via Surface Chemistry and Concentration of Silica Nanoparticles and Supercritical Carbon Dioxide Process Parameters. *Journal of Chemistry* **2013**, *2013*, 864926.
- (33) Liberman, A.; Mendez, N.; Trogler, W. C.; Kummel, A. C. Synthesis and Surface Functionalization of Silica Nanoparticles for Nanomedicine. *Surface Science Reports* **2014**, *69* (2–3), 132–158.
- (34) Bagwe, R. P.; Hilliard, L. R.; Tan, W. Surface Modification of Silica Nanoparticles to Reduce Aggregation and Nonspecific Binding. *Langmuir* **2006**, *22* (9), 4357–4362.
- (35) Yang, J.; Sang, Y.; Chen, F.; Fei, Z.; Zhong, M. Synthesis of Silica Particles Grafted with Poly(Ionic Liquid) and Their Nucleation Effect on Microcellular Foaming of Polystyrene Using Supercritical Carbon Dioxide. *Journal of Supercritical Fluids* **2012**, *62*, 197–203.
- (36) Goren, K.; Chen, L.; Schadler, L. S.; Ozisik, R. Influence of Nanoparticle Surface Chemistry and Size on Supercritical Carbon Dioxide Processed Nanocomposite Foam Morphology. *Journal of Supercritical Fluids* **2010**, *51*(3), 420–427.
- (37) Siripurapu, S.; DeSimone, J. M.; Khan, S. A.; Spontak, R. J. Low-Temperature, Surface-Mediated Foaming of Polymer Films. *Advanced Materials* **2004**, *16* (12), 989–994.

- (38) Miller, M. B.; Luebke, D. R.; Enick, R. M. CO₂-Philic Oligomers as Novel Solvents for CO₂ Absorption. *Energy and Fuels* **2010**, *24* (11), 6214–6219.
- (39) Wang, H.; Li, W. Selective Ultrasonic Foaming of Polymer for Biomedical Applications. *Journal of Manufacturing Science and Engineering, Transactions of the ASME* **2008**, *130* (2), 0210041–0210049.
- (40) Liu, Q.; Zhu, Y.; Yang, G.; Yang, Q. Nucleation Thermodynamics inside Micro/Nanocavity. *Journal of Materials Science and Technology* **2008**, *24* (2), 183–186.
- (41) Qian, M.; Ma, J. The Characteristics of Heterogeneous Nucleation on Concave Surfaces and Implications for Directed Nucleation or Surface Activity by Surface Nanopatterning. *Journal of Crystal Growth* **2012**, *355* (1), 73–77.
- (42) Maksimov, A. O.; Kaverin, A. M.; Baidakov, V. G. Heterogeneous Vapor Bubble Nucleation on a Rough Surface. *Langmuir* **2013**, *29* (12), 3924–3934.
- (43) Tsai, H. J.; Lee, Y. L. Facile Method to Fabricate Raspberry-like Particulate Films for Superhydrophobic Surfaces. *Langmuir* **2007**, *23* (25), 12687–12692.
- (44) Cano, M.; de la Cueva-Méndez, G. Self-Assembly of a Superparamagnetic Raspberry-like Silica/Iron Oxide Nanocomposite Using Epoxy–Amine Coupling Chemistry. *Chemical Communications* **2015**, *51* (17), 3620–3622.
- (45) Ming, W.; Wu, D.; van Benthem, R.; de With, G. Superhydrophobic Films from Raspberry-like Particles. *Nano Letters* **2005**, *5* (11), 2298–2301.
- (46) Pureskiy, N.; Ionov, L. Synthesis of Robust Raspberry-like Particles Using Polymer Brushes. *Langmuir* **2011**, *27* (6), 3006–3011.
- (47) Wang, J.; Yang, X. Raspberry-like Polymer/Silica Core-Corona Composite by Self-Assemble Heterocoagulation Based on a Hydrogen-Bonding Interaction. *Colloid and Polymer Science* **2008**, *286* (3), 283–291.
- (48) Mammen, L.; Deng, X.; Untch, M.; Vijayshankar, D.; Papadopoulos, P.; Berger, R.; Riccardi, E.; Leroy, F.; Vollmer, D. Effect of Nanoroughness on Highly Hydrophobic and Superhydrophobic Coatings. *Langmuir* **2012**, *28* (42), 15005–15014.
- (49) Yuhong, Z.; Qichao, Z.; Xingwang, S.; Qingqiong, T.; Min, C.; Limin, W. Preparation of Raspberry-like Polymer/Silica Nanocomposite Microspheres via Emulsifier-Free Polymerization in Water/Acetone Media. *Journal of Colloid and Interface Science* **2009**, *336* (2), 544–550.
- (50) Du, X.; Liu, X.; Chen, H.; He, J. Facile Fabrication of Raspberry-like Composite Nanoparticles and Their Application as Building Blocks for Constructing Superhydrophilic Coatings. *Journal of Physical Chemistry C* **2009**, *113* (21), 9063–9070.
- (51) Zhang, T.; Zhang, Q.; Ge, J.; Goebel, J.; Sun, M.; Yan, Y.; Liu, Y. S.; Chang, C.; Guo, J.; Yin, Y. A Self-Templated Route to Hollow Silica Microspheres. *Journal of Physical Chemistry C* **2009**, *113* (8), 3168–3175.
- (52) Du, X.; He, J. A Self-Templated Etching Route to Surface-Rough Silica Nanoparticles for Superhydrophobic Coatings. *ACS Applied Materials and Interfaces* **2011**, *3* (4), 1269–1276.
- (53) Zhang, T.; Ge, J.; Hu, Y.; Zhang, Q.; Aloni, S.; Yin, Y. Formation of Hollow Silica Colloids through a Spontaneous Dissolution-Regrowth Process. *Angewandte Chemie - International Edition* **2008**, *47* (31), 5806–5811.

-
- (54) Musić, S.; Filipović-Vinceković, N.; Sekovanić, L. Precipitation of Amorphous SiO₂ Particles and Their Properties. *Brazilian Journal of Chemical Engineering* **2011**, 28 (1), 89–94.
- (55) Kim, H.; Kim, H. G.; Kim, S.; Kim, S. S. PDMS-Silica Composite Membranes with Silane Coupling for Propylene Separation. *Journal of Membrane Science* **2009**, 344 (1–2), 211–218.
- (56) Liu, S.; Eijkelenkamp, R.; Duvigneau, J.; Vancso, G. J. Silica-Assisted Nucleation of Polymer Foam Cells with Nanoscopic Dimensions: Impact of Particle Size, Line Tension, and Surface Functionality. *ACS Applied Materials and Interfaces* **2017**, 9 (43), 37929–37940.
- (57) Thommes, M. Physical Adsorption Characterization of Nanoporous Materials. *Chemie-Ingenieur-Technik* **2010**, 82 (7), 1059–1073.
- (58) Thommes, M.; Cychosz, K. A. Physical Adsorption Characterization of Nanoporous Materials: Progress and Challenges. *Adsorption* **2014**, 20 (2–3), 233–250.
- (59) Rouquerol, J.; Rouquerol, F.; Llewellyn, P.; Maurin, G.; Sing, K. S. W. (2013). *Adsorption by Powders and Porous Solids: Principles, Methodology and Applications: Second Edition*. Academic Press.
- (60) Liu, S.; Pandey, A.; Duvigneau, J.; Vancso, J.; Snoeijer, J. H. Size-Dependent Submerging of Nanoparticles in Polymer Melts: Effect of Line Tension. *Macromolecules* **2018**, 51 (7), 2411–2417.
- (61) Liu, S. (2017). Designer Nanoparticles as Efficient Nucleation Agents in Polymer Foaming. University of Twente. <https://doi.org/10.3990/1.9789036544023>
- (62) Jones, W. M.; Isaac, P. J.; Phillips, D. The Adsorption of Carbon Dioxide and Nitrogen at High Pressures by Porous Plugs of Lampblack. *Transactions of the Faraday Society* **1959**, 55 (0), 1953–1958.
- (63) Ally, J.; Molla, S.; Mostowfi, F. Condensation in Nanoporous Packed Beds. *Langmuir* **2016**, 32 (18), 4494–4499.
- (64) Ullah, R.; Atilhan, M.; Diab, A.; Deniz, E.; Aparicio, S.; Yavuz, C. T. Synthesis, Characterization and Evaluation of Porous Polybenzimidazole Materials for CO₂ Adsorption at High Pressures. *Adsorption* **2016**, 22 (2), 247–260.
- (65) Fujiki, J.; Yamada, H.; Yogo, K. Enhanced Adsorption of Carbon Dioxide on Surface-Modified Mesoporous Silica-Supported Tetraethylenepentamine: Role of Surface Chemical Structure. *Microporous and Mesoporous Materials* **2015**, 215, 76–83.
- (66) Fujiki, J.; Yogo, K. The Increased CO₂ Adsorption Performance of Chitosan-Derived Activated Carbons with Nitrogen-Doping. *Chemical Communications* **2016**, 52 (1), 186–189.
- (67) Sanz-Pérez, E. S.; Arencibia, A.; Sanz, R.; Calleja, G. An Investigation of the Textural Properties of Mesoporous Silica-Based Adsorbents for Predicting CO₂ Adsorption Capacity. *RSC Advances* **2015**, 5 (125), 103147–103154.
- (68) Kumar, V.; Suh, N. P. A Process for Making Microcellular Thermoplastic Parts. *Polymer Engineering & Science* **1990**, 30 (20), 1323–1329.

Chapter 6

Fluorescent Polyethylene by In-Situ Facile Synthesis of Carbon Quantum Dots Facilitated by Silica Nanoparticle Agglomerates

We describe an in-situ facile synthetic approach to prepare carbon quantum dot (CQD) fluorescent markers (FMs) for polyethylene in the presence of agglomerated silica nanoparticles (SiO₂ NPs), under mild reaction conditions. First SiO₂ NPs, prepared by

the Stöber method, were dispersed in toluene. This dispersion was added to a polyethylene (PE) solution in toluene. After heating (either in air or under Ar) a fluorescent mixture was obtained. After drying, PE films were obtained by compression molding, which showed strong blue fluorescence, attributed to CQDs. SiO₂ NPs loading values varied between 0.5 and 4 wt %. Subsequent to isolation, the fluorescent CQDs were characterized by TEM, UV-VIS and fluorescence spectroscopy. TEM imaging unveiled a lattice spacing value of 0.21 nm of the isolated fluorescent particles that is typical for (100) graphite plane lattice spacing in CQDs. UV spectroscopy and fluorescence measurements show characteristic absorption and excitation spectra for aromatic core and oxidized surface defects typically observed for CQDs. The emission maximum for PE/CQD samples increased from 394 nm to 408 nm when the reaction temperature was decreased from 110 °C to 90 °C, which is attributed to increasing oxygen content in the reaction mixture upon decreasing the reaction temperature. When the reaction was performed under Ar, the PE/CQD samples emitted in the ultraviolet region (286 nm). Finally, we demonstrated that PE samples marked with CQDs can be easily visually identified upon irradiating with 367 nm light. Thus the marked PE can be used e.g. as a labelling ingredient in master batches for component identification, and in recycling.

6.1 Introduction

To decrease the environmental impact of plastic waste and consumption of fossil resources employed in the production of plastics, recycling plastic waste is an essential practice. However, plastic sorting efficiency and component identification remain a technological challenge.¹⁻³ To increase the recycling rate for plastic waste, one needs to improve the sorting accuracy and speed. To this end, adding fluorescent markers (FMs) to enable high-efficiency sorting is one of the most promising approaches.

Currently, there are three main approaches to plastic waste management. These are landfilling, incineration, and chemical/mechanical recycling.³ In general, plastic waste streams are treated with other municipal waste streams for landfilling and incineration. More than 80% of the waste plastic is disposed in the landfill.³ Due to plastics' usually high resistance to degradation, it can take more than 50 years for a piece of plastic to degrade after being buried.^{4,5} Degradation of landfilled plastic waste can damage the environment by, e.g., releasing large amounts of greenhouse gasses (CO₂), accelerating global warming, and forming microplastics/nanoplastics that may eventually accumulate in humans.^{6,7} Besides these environmental concerns, landfilling is getting increasingly expensive in highly-populated areas, like in Western Europe and in Southern China.⁸ Incineration is also a standard method for plastic waste management.³ Its most significant advantages are that upon incineration, the waste volume is reduced and that simultaneously, the heat of combustion can be used for electricity generation. In 2015, approximately 12% of the global plastic waste was incinerated.⁹ However, the toxic gases released by incineration pose a significant health and environmental concern, especially when the incineration plants are operated in densely populated areas.¹⁰ Furthermore, the incineration of plastic waste is accompanied by a relatively high CO₂ emission. Incineration of 1 kg plastic waste can release up to 4.6 kg of CO₂, which for 1 kg municipal solid waste (MSW) is only 1.2 kg.¹¹ Typically, MSW contains approximately 10-12% of plastic. Thus sorting plastic waste from MSW before incineration will substantially decrease greenhouse gas emissions.¹⁰

Compared to landfilling and incineration, recycling is an eco-friendlier way to deal with plastic waste.¹¹⁻¹³ Recycling plastic reduces the above-mentioned environmental issues and decreases the required amount of fossil fuel to produce new plastic by reducing the demand for virgin materials. It is widely accepted that recycling plastics is an essential step towards creating a circular economy.¹⁴ There are two main approaches for recycling plastics, i.e. by using chemical or mechanical methods.² Depending on the composition of the plastics to recycle, each method has its strengths and weaknesses.¹

The sorting of plastic waste typically consists of three steps.¹ First, Fourier transform near-infrared (FTNR) spectroscopy and a color recognition camera are used to pre-sort various plastic types from waste streams. The second step consists of milling the plastic waste into small pieces and removing the non-plastic residuals. The final step is to further sort the milled plastics by type. Various techniques are in place for sorting plastic waste streams, like sink/float separation,¹⁵ electrostatic separation,¹⁶ air elutriation,¹⁷ froth flotation,¹⁸ and selective degradation.¹⁹ Each of the above-mentioned techniques has its strengths and weaknesses; for more details, the interested reader is directed to references 20,21.

The use of FMs, as an accurate and cost-effective approach to identify and sort specific polymers from plastic waste streams, has received considerable attention in recent years.^{21–25} FMs can be incorporated in polymer matrices via masterbatches, e.g., by extrusion or injection molding. They can even be applied as a thin fluorescent coating onto the finished plastic products or intermediates.^{26,27} For instance, Massardier et al. reported the incorporation of 0.1 wt% of lanthanide complex particles into a polypropylene (PP) matrix under a high shear rate ($N = 800$ rpm) to prepare a fluorescent polypropylene that is detectable with UV-ray fluorescence spectrometry within 10 milliseconds.²³ Langhals et al. reported using organic dyes, i.e. perylene ester, perylene carboxylic bisimide, and terylene carboxylic bisimide FMs to identify polymers by measuring the time constant of autofluorescence decay values.²⁵ They also demonstrated that the polymer type (styrene-polyacrylonitrile copolymer, polyoxymethylene, or polyamide) alters the fluorescence lifetime values of the incorporated markers. This observation opened the path towards using the difference in the time constant values of the autofluorescence decay in sorting of different types of plastics. Recently, Woidasky et al. reported adding oxide crystals, doped with rare earth elements, as up-conversion inorganic FMs to the polymer matrix for marking and identification.²⁸ By utilizing the up-conversion fluorescence of the FMs, the authors were able to generate photoluminescence (PL) in the visible light range upon near IR (NIR) excitation and, as such, eliminate the influence of background emission from plastics and additives.

Despite promises, there are numerous open challenges when considering the use of fluorescent particles/dyes at industrially relevant scales. For instance, fluorescent particles/dyes usually suffer from high cost, toxicity, and poor photostability.^{29–32} These drawbacks currently limit their use as FM labeled plastics on a large scale. Thus, if progress is to be made in this area, additional efforts are needed. Keeping this in mind, we decided to tackle the problem of loading polyethylene (PE) by carbon quantum dots (hereinafter CQDs) and explored facile reaction routes to obtain fluorescent labelled PE.

CQDs are considered as a viable alternative for fluorescent dyes and inorganic QDs because of their low toxicity, low cost, good solubility, and high photostability.³³ A variety of techniques have been deployed to synthesize CQDs. These methods can be classified into two categories, i.e. top-down and bottom-up approaches.^{34–36}

The 'top-down' method usually involves chemical, electrochemical and physical approaches to break down large carbon-based materials, i.e. carbon soot, carbon nanotubes, graphite, etc.^{37,38} The 'bottom-up' approach typically utilizes solvothermal/hydrothermal carbonization, laser ablation, electrochemical oxidation, microwave irradiation, or pyrolysis to grow CQDs from organic molecules.³⁹ Many organic compounds have been reported to be used to synthesize CQDs via the bottom-up method, for instance, polybasic acid, glucose, sucrose, glycol, glycerol, chitosan.^{40–44} Among the techniques used to synthesize CQDs, solvothermal/hydrothermal carbonization is considered one of the simplest, most direct, and most efficient pathways.⁴³ However, the complicated chemical reactions, time-consuming purification, and harsh synthesis conditions pose serious challenges for large-scale applications.^{36,45}

Figure 6.1 Schematic of CQD formation through thermal PE degradation inside the cavities/pores of silica nanoparticle aggregates. The method does not require extensive particle purification; upon removing the solvent, the particles are readily used as FMs in PE.

In this Chapter we introduce a facile 'bottom-up' route that uses silica nanoparticles (SiO₂ NPs) as enablers to fabricate fluorescent CQDs from polyethylene (PE). The reaction scheme is captured in Figure 6.1. One of the most beneficial features of this route is that upon removing the solvent, the CQD, silica, and PE mixture is present in a concentrated FM blend, which can be used as a masterbatch to add to (virgin) PE. Hence extensive and costly CQD collection and purification are not required. This opens new avenues to the widespread applicability of CQDs as FM for plastic waste recycling, which we will demonstrate in the last part of this Chapter.

6.2 Results and Discussion

6.2.1 SiO₂ Synthesis and Characterization

First, we employed a modified Stöber procedure to synthesize SiO₂ NPs.⁴⁶ Figure 6.2a and Figure 6.2b show a scanning electron microscope (SEM) image and the size distribution of the SiO₂ NPs, respectively. The nearly spherical SiO₂ NPs have an average particle size of 114 ± 11 nm and most of the particles have a diameter between 100 and 130 nm. Figure 6.2c shows a Fourier-transform infrared (FTIR) absorbance spectrum of the SiO₂ NPs. In the FTIR spectrum, the SiO₂ signature absorption bands ascribed to the asymmetric vibration of Si-O, the asymmetric vibration of Si-OH, and the symmetric vibration of Si-O are clearly observed at 1063 cm^{-1} , 940 cm^{-1} , and 803 cm^{-1} , respectively. The broad absorption band with a maximum at 3431 cm^{-1} and the small peak located at 1635 cm^{-1} are ascribed to O-H stretching absorbances by Si-OH bonds and to physically absorbed water.⁴⁷ The small absorption bands located at 2980 cm^{-1} and 1452 cm^{-1} indicate the presence of CH₂/CH₃, which is attributed to residual ethoxy moieties.⁴⁷

Figure 6.2 a) SEM image and b) size distribution of SiO₂ NPs used in this work. c) Single reflection ATR-FTIR absorbance spectrum of the as-prepared SiO₂ NPs.

6.2.2 PE/SiO₂ Composites and Fluorescence Microscopy

In Figure 6.3, fluorescent microscope images (λ_{ex} 360-370 nm and $\lambda_{\text{em}} > 460$ nm) of 2.5-PE/SiO₂ thin films obtained by employing varying reaction times up to 72 h are shown. From this figure, it is clear that upon increasing the reaction time, the observed fluorescent emission intensity increases (see also later). Additionally, for separate PE/toluene and SiO₂/toluene samples heated for 24 hours in air at $110\text{ }^{\circ}\text{C}$, no fluorescence was observed. Thus, we conclude that the combination of SiO₂ NPs and PE together is required for the reaction that results in fluorescent material. In the following sections, we will first confirm that CQDs are formed and explain the role of the SiO₂ NPs in the reaction. In the last part of this work, we show that modest shifts in the emission wavelengths are obtained upon changing the reaction conditions (from air to Ar).

Figure 6.3 Fluorescent microscopy images of 2.5-PE/SiO₂ thin films prepared as a function of the reaction time up to 72 hours in air.

6.2.3 The Origin of the Observed Fluorescent: CQD Isolation and Characterization

During preparation, as mentioned, liquid nitrogen quenching of the toluene solution containing 2.5-PE/SiO₂ and CQDs was used to suppress PE crystallization and leave the particles (SiO₂ NPs and CQDs) in the toluene phase. Following the removal of the residual PE and subsequently the SiO₂ NPs by filtration, the residual toluene fraction was dried to isolate the fluorophores. Subsequently, small quantities of a yellowish paste were formed at the bottom of the container. This paste was used to prepare samples for transmission electron microscope (TEM) analysis. Figure 6.4a shows an TEM image of the residual paste, revealing crystalline nanoparticles (dark, circular objects). The arrows in Figure 6.4a point at single fluorophores. From zoomed-in images (such as shown in the top right inset) and following a Fast Fourier Transform (FFT) analysis of the TEM intensities (bottom right inset), a lattice spacing of 2.1 Å for the nanoparticles was determined. This value agrees well with the (100) plane graphite lattice spacing typically observed for CQDs.^{48–51} While we expected clear TEM images of the CQDs, the particle edges appear slightly blurred. We attribute this to the presence of residual polymer that the isolation process did not remove, combined with curvature effects. The residual polymer promoted particle agglomeration during TEM sample preparation. The average diameter for the CQDs was 2.3 ± 0.5 nm, which agrees with the particle height measured by atomic force microscope (AFM) (2.2 ± 0.7 nm, see Figure 6.4c)

Figure 6.4 a) TEM image, b) single reflection ATR-FTIR absorbance spectrum and c) AFM image. d) Normalized UV-Vis absorption (blue), excitation ($\lambda_{\text{em}}=386$ nm) (red), and emission spectra ($\lambda_{\text{em}}=286$ nm (orange) and 340 nm (green)) of the isolated CQDs and the polymeric residue suspended in toluene.

The residual polymer and the fact that the samples for TEM imaging were retrieved as a yellowish paste indicate the presence of degraded polymer that remained in the toluene during liquid nitrogen quenching and was not removed by filtration and drying. Figure 6.4b shows an FTIR spectrum of the yellowish paste obtained. The spectrum has all the representative peaks of PE with additional peaks located at 1712 cm^{-1} and 1736 cm^{-1} corresponding to absorbances of C=O from carboxylic acids and aldehyde, respectively.⁵² Those peaks typically indicate thermooxidative degradation of PE.⁵³ There is also a noticeable small peak located at 1660 cm^{-1} , indicating that C=C bonds were also formed.⁵⁴ We note, that as described in the literature, oxidation of PE is required for the formation of CQDs.⁴⁵ The sharp peak (289 nm) and the small shoulder (330–340 nm) from the Ultraviolet–Visible (UV-Vis) spectrum of the CQD suspension (Figure 6.4d) are ascribed to the $\pi\text{-}\pi^*$ transition of aromatic ring structures (C=C) and the $\text{n-}\pi^*$ transition of oxidized groups (C=O), respectively.^{55,56} The presence of C=C ($\pi\text{-}\pi^*$ transition) and C=O ($\text{n-}\pi^*$ transition) absorbance in the UV-Vis spectrum are in agreement with the structures observed in the FTIR spectrum, shown in Figure 6.4b. The normalized excitation spectrum exhibits a peak and shoulder combination that is similar to the UV-Vis spectrum. The excitation at 286 nm and 330–340 nm correspond to the CQD core (aromatic ring structure) and surface defects (C=O containing groups).⁵⁷ The emission bands located at 337 nm and 383 nm are ascribed to the surface defects of CQDs. It is worth noting that when excited at 286 nm, the emission spectrum shows a small shoulder around 320 nm. This small shoulder is attributed to the photon emitted

directly from the CQD cores without being trapped by surface defects.⁵⁸

The absence of fluorescent and degradation products of PE heated without dispersed SiO₂ NPs confirms that the SiO₂ NPs play a role in forming the fluorescent CQDs. Therefore, to better understand the mechanism behind CQDs' formation during thermal treatment, one must first understand the role that the SiO₂ NPs play in the reaction, which we elucidate in the following section.

6.2.4 Role of SiO₂ NPs in CQD Formation in Heated PE/SiO₂ Solutions

Dynamic light scattering (DLS) was used to investigate the dispersion of the SiO₂ NPs in toluene. Additionally, the morphology of SiO₂ was observed by SEM in the PE matrix at room temperature. For DLS, the hydrodynamic radius of SiO₂ NPs in water was also determined. Figure 6.5a and Figure 6.5b show the hydrodynamic particle size of SiO₂ NPs suspended in water and in toluene, respectively.

Figure 6.5 The hydrodynamic particle size of SiO₂ NPs dispersed in a) water and b) toluene.

The range of hydrodynamic particle diameter values of the SiO₂ NPs in water is around 110 ± 3 nm, which agrees with the determined dry particle size by SEM (Figure 6.6b). This confirms that after drying, the SiO₂ NPs did not irreversibly aggregate. The hydrodynamic particle diameter values of the SiO₂ NPs in toluene, however, varied in the range of 750 ± 45 nm, which is nearly seven times larger than the primary particle size, pointing at severe particle agglomeration in toluene. Figure 6.6 shows SEM images of the cross-sections of 1-, 2.5- and 4-PE/SiO₂ films prepared after only 10 minutes of reaction time from the respective SiO₂ PE solutions. Figure 6.6 shows that almost all SiO₂ NPs are present as part of large agglomerates (with sizes exceeding 1 μ m) in 1- and 2.5-PE/SiO₂ films, while in 4-PE/SiO₂ thin film, the observed SiO₂ NPs formed a large number of smaller agglomerates with a diameter in the sub-micrometer range. Based on these results, we conclude that the SiO₂ NPs agglomerated during the thermal treatment process. Like in mesoporous SiO₂ particles (aerogels), the silica agglomerates in the PE/toluene mixture have an open porous structure. According to the literature, these pores

may act as nanometric size reactors that prolong the lifetime of radicals produced from the thermal degradation of polyolefins.⁵⁹ These long-lived radicals confined in the pores have more chance to react with other PE molecules, accelerating the thermal degradation of PE. The confinement effect on the kinetics of enzymatic reactions has been shown earlier by us and presumably can be extended to the radical activities of degraded PE.⁶⁰ Typically, the thermal degradation rate for PE is low at 110 °C.⁶¹ When these nanometric-sized reactors are present, we increased the PE degradation reaction rate at lower temperatures and prepared CQDs from the degradation products within few hours.

Figure 6.6 SEM images of cross-sectioned a) 1-PE/SiO₂, b) 2.5-PE/SiO₂, and c) 4-PE/SiO₂ thin films after 10 minutes of thermal treatment. The red circles indicate SiO₂ NP agglomerates.

Heat is a known physical factor that triggers the formation of macroradicals when accompanied by oxygen⁶²:

RH represents the monomer units of PE (CH₂). Typically, the free radicals in solution at elevated temperature have a very short half-life time, in the range of 10⁻⁹ to 10⁻⁶ s. However, the pores/cavities accessible from the surface of SiO₂ NP agglomerates can act as nanometer-sized reaction vessels that prolong the half-life of free radicals and therefore accelerate the degradation of PE.⁵⁹ Consequently, the HO₂^{*} radicals formed in the nanocavities remain active for a longer time and have a higher chance of reacting with RH units to produce more R^{*} radicals. Subsequently, the free radicals R^{*} react with adjacent RH units to form vinyl groups resulting in chain-scission and the formation of C=C bonds:

This mechanism is supported by the appearance of the observed C=C absorbance band at 1660 cm⁻¹ in the FTIR spectrum (Figure 6.4b), indicating the presence of vinyl groups in CQDs and in the polymer residue.⁶³ During CQD formation, the initially

degraded polymer forms C=C/C-C frameworks inside the porous agglomerated SiO₂ NPs during the thermal degradation/oxidation, thereby acting as skeletons/nucleus. As degradation progresses, these nuclei grow to nanometer-sized CQDs.⁶⁴

Free radicals R^{*} can also undergo oxidation with oxygen to form peroxide radicals (RO₂^{*}), followed by reacting with neighboring monomer units to form hydroperoxides (ROOH)⁶²:

The presence of carboxylic acid (ROOH) and aldehyde (ROH) moieties formed by the thermal oxidation are also supported by the observed sharp peaks (C=O) located at 1712 and 1736 cm⁻¹ in the FTIR spectrum (Figure 6.3), respectively. The formation of C=O can occur either on the CQDs resulting in the presence of impurities and surface defects in the CQDs, or on the polymer chains resulting in the formation of carbonyl groups. As it was not among the objectives of the scope of this study, we cannot confirm whether the CQDs do or do not have these defects. This requires more extensive purification and characterization of the CQDs.

6.2.5 Effect of SiO₂ NPs Concentration of Fluorescent Intensity of PE/SiO₂ Thin Films

To further investigate the influence of SiO₂ NPs on the fluorescent properties, PE/SiO₂ composites with particle concentrations of 1, 2.5, and 4 wt% were prepared with up to 24 hours of thermal treatment at 110 °C in air. The as-prepared composites were proceeded into thin films and measured with a fluorescent microscope. Figure 6.7 shows the grey values of the fluorescence of 1-, 2.5-, and 4-PE/SiO₂ against reaction time. We note that the PE/SiO₂/toluene mixture needed the first 10 minutes to homogenize due to its high viscosity. As a consequence, 10 minutes is the first experimentally available reaction time for taking aliquots for further study. Furthermore, we note, that the differences in baseline grey value intensities of the PE films with different SiO₂ NP loading (resulting from the differences in particle loading) lead to changes in the refraction of the excitation/emission light beams.

Interestingly, there is no significant change in the measured fluorescent intensity during the first few hours of the reaction for 1- and 2.5-PE/SiO₂. However, the fluorescent intensity gradually increases for the 4-PE/SiO₂ film right after the start of the reaction. In fact, for 1-PE/SiO₂ films, even after 24 hours of thermal treatment, there is no noticeable

change in the fluorescence intensity. However, the fluorescent intensity increased significantly for 2.5-PE/SiO₂ films after 8 hours of thermal treatment.

Figure 6.7 Grey value intensity of as-prepared 1-PE/SiO₂, 2.5-PE/SiO₂, and 4-PE/SiO₂ films as a function of the reaction time. The reaction was performed at 110 °C in air.

This remarkable difference is explained by the relatively high concentration of SiO₂ agglomerates present in 4-PE/SiO₂ (Figure 6.6c). The increased amount of smaller SiO₂ agglomerates results in an increased specific contact area between the SiO₂ NPs and PE chains. Consequently, the relative number of accessible nanocavities to accelerate the CQD formation increases. For 1- and 2.5-PE/SiO₂, the relatively low particle surface area available for promoting the CQD formation results in a reduced rate of CQD formation. The observed dependence of CQD formation on the concentration and size of SiO₂ agglomerates confirms that the SiO₂ agglomerates play a crucial role in forming CQDs at relatively low temperatures and that their exploitation as an enabling platform in the facile synthesis of CQD based FM is of interest for further exploration. For spectral engineering, we eventually need to be able to tune the emission wavelengths of the CQDs by varying the size of the emitters. The following sections show the first attempts to control the emission wavelengths of the CQDs and a proof of concept showing their potential as FMs in polymers to aid in sorting.

6.2.6 Fluorescent Spectra of PE/SiO₂ Thin Films and the Influence of the Reaction Temperature

In a first attempt to show the potential utilization of the CQDs as FMs, we examined their emission spectra as a function of particle concentration and reaction time upon excitation with 360 nm and 380 nm light, respectively. Figure 6.8a and 6.8b show the fluorescent emission spectra of 2.5- and 4-PE/SiO₂ thin films with an excitation wavelength of 360 nm and 380 nm, respectively.

Figure 6.8 Fluorescent emission spectra of a) 2.5-PE/SiO₂ and b) 4-PE/SiO₂ thin films prepared in air with 20 hours (dashed lines) and 24 hours (solid lines) reaction times upon excitation with 340 nm, 360 nm, and 380 nm wavelengths. c) Fluorescent emission spectra of thin films of 4-PE/SiO₂ upon excitation with 340 nm light, fabricated at reaction temperatures of 90 °C, 100 °C, and 110 °C for 24 hours in air.

The observed fluorescent emission maxima for the PE/SiO₂ samples fall into the blue emission range (380 nm to 500 nm), which is typically the result of the radiative recombination of e-h pairs in the sp² cluster and surface defects of CQDs.⁶⁵ A clear redshift of a few nm in the fluorescent emission is observed in the fluorescent spectra by increasing the excitation wavelength from 340 to 380 nm. Although the exact mechanism for CQDs fluorescent emission is still under debate, it is generally agreed that the CQDs' size and surface status significantly influence the fluorescent properties of CQDs.⁶⁶ We consider that the excitation-dependent fluorescence behavior of our thin films is a combination of CQDs size dispersity, impurities, and surface defects.⁶⁷ Furthermore, a modest redshift was also observed in the fluorescent emission spectrum when the reaction time increased from 20 to 24 h. The observed redshift can be tentatively explained by the longer time available for the CQDs to grow, resulting in larger CQDs that typically have a redshift in their emission spectrum.⁴³

Figure 6.8c shows normalized fluorescent emission spectra of 4-PE/SiO₂ samples fabricated at different temperatures. One can observe in Figure 6.8c that upon increasing the reaction temperature from 90 °C to 110 °C for the 4-PE/SiO₂ mixture, the emission peak shifts from 408 nm to 394 nm upon excitation with 340 nm light. It is known that upon increasing the reaction temperature, the oxygen solubility decreases.⁶⁸ Therefore, it is reasonable to assume that upon increasing the reaction temperature from 90 °C to 110 °C, fewer oxygen molecules were present in the reaction mixture, which reduced the chance for free radicals to be involved in oxidation reactions and the formation of C=O

species. This could decrease the number of surface traps and impurities (C=O) present in the formed CQDs leading to less energy loss for the fluorescent emission, resulting in higher emission energy for the CQDs prepared at higher temperatures.⁶⁹

Figure 6.9 Fluorescent excitation and emission spectra of 4-PE/SiO₂ thin films prepared with 24 h reaction time in air (solid line) and Ar (dashed line) atmosphere.

To further elucidate the role oxygen during the CQD synthesis, the reaction was performed in Ar atmosphere for 4-PE/SiO₂ mixtures at 110 °C. The corresponding fluorescent excitation and emission spectra of the 4-PE/SiO₂ samples are shown in Figure 6.9. The maximum excitations for 4-PE/SiO₂ synthesized in air and Ar are located at 240 nm and 260 nm, respectively. These excitation peaks are ascribed to the photon absorption of C=C (aromatic structure) in the CQD core.⁷⁰ The corresponding emission centers are located at 350 nm and 285 nm.⁵⁷ The blueshift in emission wavelength upon substituting air with Ar is ascribed to the reduced presence of surface defects (surface oxidation) of the CQDs when prepared without the presence of oxygen. This means that the photons are directly emitted from the aromatic ring structure (C=C) upon excitation and that without the presence of surface defects to trap these photons, they can maintain a higher energy level, therefore, emitting at a shorter wavelength.⁵⁸

Overall, these results demonstrate that with minor modifications to the reaction conditions, changes in the CQD emissions are accessible, rendering our system a valuable designer platform for the controlled synthesis of PE-based FMs at mild reaction conditions.

6.2.7 Solution Blending CQDs and PE/SiO₂ Composites with Pure PE

We used solution blending to prepare CQD containing PE films to demonstrate the applicability of the CQD as fluorescent markers in virgin polymers. As-prepared CQD 4-PE/SiO₂ (114 hours reaction at 110 °C in air) and isolated CQDs (extracted from 4-PE/SiO₂ after 24 hours reaction in air) were used as tracer batches to prepare PE films

with a tracer loading of 10 wt% (meaning the actual CQD concentration is unknown). Following compression molding, film samples were cut to easily recognizable shapes, i.e. circles and triangles, respectively. In addition, pristine PE films were prepared and cut to rectangular shapes for comparison. Five pieces were placed together from each PE film type, and photos were taken in daylight (Figure 6.10a) and upon excitation with 360 nm light (Figure 6.10b).

Figure 6.10 Photos of pure PE (rectangle), PE/CQD (triangle), and CQD 4-PE/SiO₂ (circular) films in a) daylight and b) upon excitation with 367 nm light.

In Figure 6.10a (photo taken in daylight), all pieces are visible and their shape is clearly identifiable. Upon excitation with 367 nm light, only the CQD-loaded pieces are visible by their emission in the blue range. The color difference (not intensity) between triangular (darker blue) and circular (lighter blue) pieces under 367 nm excitation is due to differences in thermal treatment time, resulting in the presence of larger CQDs in the circular PE films, as discussed earlier. The observed modest redshift is in agreement with this observation.⁴³ Also, from this simple visual experiment, we learn that the embedded SiO₂ NPs do not affect the PE samples' detectability. Overall, we conclude that the simple preparation method at mild reaction conditions of CQD FMs in SiO₂/PE mixtures described here is a promising approach for fluorescence marking. Further in-depth exploration to enhance the CQD traceability is needed and is underway to explain details of the fluorescence. In addition, upon expanding the variations and control of emission wavelengths, our simple preparation method without requiring extensive purification methods opens a broad range of novel applications, *e.g.*, counter faking, sorting, tracing, etc.

6.3 Conclusion

PE, containing CQDs markers with tunable fluorescence was prepared by a facile thermal approach operated at mild conditions. For the reaction employed, solvent-

induced SiO₂ NP aggregation provided surface-exposed nanocavities that were assumed to function as nanoreactors, enabling CQDs to form at relatively low reaction temperatures. TEM imaging of isolated CQD particles, UV spectroscopy, and fluorescent measurements confirmed the successful preparation of CQDs. The emission maximum for PE/CQD samples was tunable between 394 nm to 408 nm by decreasing the reaction temperature from 110 °C to 90 °C. PE/CQD samples prepared in the absence of oxygen only emitted in the ultraviolet region (286 nm). Finally, we successfully exploited CQDs with a different emission maximum as FMs in PE compression molded films. Upon irradiating with 367 nm light, the different PE samples were readily visually identified.

6.4 Materials and Methods

Materials. Tetraethyl orthosilicate (TEOS) $\geq 99.0\%$, toluene 99.5%, and 2-propanol 99.5% were purchased from Aldrich (Milwaukee, WI, USA). Ammonium hydroxide solution 28-30%, triethylamine (TEA) 99.5%, and PE (medium density, MQ 200) were purchased from Sigma-Aldrich (St. Louis, MO, USA). Ethanol (EtOH) absolute for analysis was purchased from Merck (Darmstadt, Germany). Milli-Q water was produced by a Millipore Synergy system (Billerica, MA, USA). Unless otherwise mentioned, all chemicals were used as received.

Stöber Synthesis of Silica Nanoparticles. SiO₂ NPs with a diameter of ~ 110 nm were prepared by the Stöber method.⁴⁶ In a typical reaction, 168 ml EtOH was mixed with 28 ml Milli-Q water and 30 ml TEOS in the presence of 2 ml ammonium hydroxide in a round-bottom flask by stirring for 1.5 hours at 500 rpm at room temperature. Subsequently, the SiO₂ NP dispersion was centrifuged at 10,000 rpm for 30 min. Then, the collected SiO₂ NPs were redispersed in 2-propanol and centrifuged again. This washing step was repeated twice, followed by vacuum drying of the purified and collected SiO₂ NPs at room temperature for 12 hours.

Silica Nanoparticle Characterization. A high-resolution scanning electron microscope (JEOL Field Emission JSM-7610F Plus, JEOL Benelux, Nieuw-Vennep, the Netherlands) was used to study the morphology of the SiO₂ NPs particles. The electron acceleration voltage was typically between 3 to 5 keV. Fourier Transform Infrared (FTIR) spectra were collected by a Bruker ALPHA single attenuated total reflection (ATR) FTIR spectrometer equipped with an ATR single reflection crystal (Bruker Optic GmbH, Ettlingen, Germany). The spectra were collected in the range of 400-4000 cm⁻¹ (spectral resolution of 4 cm⁻¹, 1280 scans). Background spectra were recorded against air. The as-prepared SiO₂ NPs were dispersed in water and toluene at a concentration of 2.5 wt% via

intense sonication over 30 min. The hydrodynamic radius values of the particles in water and toluene were measured by Dynamic Light Scattering (DLS) (Malvern Zetasizer Nano-ZS, Malvern Instruments, Malvern, UK).

Synthesis of Fluorescent Polyethylene Silica Nanocomposites in Air. We used two pathways to obtain FM containing PE, i.e., in air and under Ar atmosphere. First, we describe the preparative steps in air. We started with 0.4 g 110 nm SiO₂ NPs, which were suspended in 10 ml toluene in a round-bottom flask and exposed to 30 min intense sonication, followed by heating the suspension formed under vigorous stirring to 110 °C by immersing the flask in a thermostated oil bath. Simultaneously, 9.6 g PE was dissolved in 30 ml toluene employing vigorous stirring in a round-bottom flask, which was immersed in a thermostated oil bath at 90 °C. Subsequently, the PE/toluene mixture was transferred to a reflux setup, followed by adding the SiO₂ NPs to the toluene suspension. After adding the SiO₂ NPs suspension, the reaction mixture was refluxed at 110 °C for 24 hours. Finally, the excess toluene was removed by drying the reaction mixture under a gentle nitrogen flow for 5 hours. The PE/SiO₂ was dried to constant weight by vacuum drying at 40 °C for 24 hours. This resulted in a PE/SiO₂ composite with a SiO₂ NP loading of 4 wt%. This composite is abbreviated as 4-PE/SiO₂. The same procedure was followed to produce 1.0 wt% and 2.5 wt% PE/SiO₂ (1-PE/SiO₂ and 2.5-PE/SiO₂) in which 0.1 and 0.25 g SiO₂ NPs and 9.9 and 9.75 g PE, were used, respectively. The amount of toluene used was not changed. Additionally, 4-PE/SiO₂ composites were prepared at 90 °C and 100 °C, as well. (Unless otherwise mentioned, we refer to PE/SiO₂ prepared at 110 °C in the main text.) The pure PE sample was prepared by refluxing in toluene at 110 °C for 24 hours and dried using same procedure mentioned before as the control group.

Fluorescent Polyethylene Silica Nanocomposite Synthesis Under Argon. In order to test the influence of air on the reaction and on the reaction products, for comparison, synthesis was also performed in Ar atmosphere. For this process 0.04 g 110 nm SiO₂ NPs and 0.96 g PE were dried in a vacuum oven at 40 °C for 48 h, then the mixture was transferred into a 50 ml Schlenk tube with a magnetic stirring bar under a nitrogen environment (in a glove box). 4 ml anhydrous toluene was added to the Schlenk tube. The Schlenk tube was sealed with a Teflon cap before it was removed from the glovebox. Next, the Schlenk tube was connected to a Schlenk line and flushed with Ar for 10 mins. Subsequently, the Schlenk tube was heated under vigorous stirring by a thermostated oil bath at 90 °C. After the PE was fully dissolved in the toluene, the Schlenk tube was disconnected from the Schlenk line and removed from the oil bath, followed by 15 min sonication in 90 °C water. After sonication, the Schlenk tube was reconnected to the Schlenk line under Ar and immersed into a thermostated oil bath at 110 °C. The reaction

was allowed to proceed under Ar with vigorous stirring for 24 hours. Next, the reaction mixture was extracted from the Schlenk tube and cooled in an ice bath, followed by drying under a gentle nitrogen flow for 5 hours to remove the excess toluene. Finally, the PE/SiO₂ mixture was dried to constant weight by vacuum drying at 40 °C for 24 hours.

Film Preparation. A hot press (Fontijne, the Netherlands) was used to press 200 µm thick PE/SiO₂ films in a stainless-steel mold (4 x 3 cm). The processing temperature, applied load, and press time were 110 °C, 200 kN, and 5 minutes, respectively.

Thin Film Characterization. An inverted Olympus IX71 fluorescence microscope equipped with an IX2-RFAC reflector turret filter cube (Olympus, Germany) and a PerkinElmer LS 55 fluorescence spectrometer (PerkinElmer, Waltham, MA, USA) were used to study the optical properties of the PE/SiO₂ films. The filter cubes' excitation and emission cut-offs were 360-370 nm and 460 nm, respectively. The emission spectra were recorded by a fluorescence spectrometer with an excitation wavelength of 340, 360, and 380 nm, respectively. In addition, Scanning Electron Microscopy (SEM) was performed by a JEOL Field Emission JSM-7610F Plus instrument (JEOL Benelux, Nieuw-Venep, the Netherlands) to study the cross-section of the PE/SiO₂ thin films. Before analysis, the thin films were freeze-fractured after cooling in liquid nitrogen for 15 min.

Carbon Quantum Dot Extraction. 1 gram of 4-PE/SiO₂ was dissolved in 10 ml toluene thermostated at 90 °C in an oil bath. Following the complete dissolution of the 4-PE/SiO₂, the mixture was quenched into liquid nitrogen and left to cool down to below ambient for 15 mins to avoid PE crystallization. Subsequently, the excess liquid nitrogen was removed, and the sample was left on the bench to heat up slowly to room temperature. Next, the supernatant was filtered with a 200 nm pore size glass filter (Merck Millipore, USA) to remove the suspended agglomerated SiO₂ NPs, followed by collecting the CQDs by solvent removal of the filtrate via evaporation under a gentle nitrogen flow, which left a yellowish paste as residue for analysis.

Carbon Quantum Dot Characterization. Transmission Electron Microscopy (TEM) was performed by a FEI/Philips CM300 system (FEI, Eindhoven, the Netherlands). Diluted CQD dispersions in toluene were deposited on the carbon side of a carbon/copper grid (HC200-Cu) (EMS, Germany) before imaging. Images were obtained in the bright field mode at a 300 kV acceleration voltage. Ultraviolet/Visible (UV-Vis) spectroscopy was performed by a LAMBDA 850 UV-Vis spectrometer (PerkinElmer, Waltham, MA, USA). The CQDs were dispersed in toluene via 10 mins intense sonication. The CQD suspension was measured against pure toluene. The excitation and emission spectra were recorded by a PerkinElmer LS 55 fluorescence

spectrometer (PerkinElmer, Waltham, MA, USA) with an emission wavelength of 384 and excitation wavelengths of 286 and 340 nm.

Solution Blending. 20 mg of CQDs (extracted) was solution blended with 180 mg PE in 5 ml toluene under vigorous stirring in a round-bottom flask, while thermostated in an oil bath at 80 °C. After 30 min, the excess toluene was removed by drying the reaction mixture under a gentle nitrogen flow for 5 hours. The PE/SiO₂ composite was dried to constant weight by vacuum drying at 40 °C for 24 hours. The same procedure was used to blend 20 mg of 114 h thermal treated PE/SiO₂ (non-extracted) with 180 mg of PE. The as-prepared nanocomposites were pressed to films (see section **Film Preparation**) and cut to different shapes before being observed under daylight and a 360 nm light source to identify the respective PE samples.

6.5 Supporting Information

Figure S6.1 TEM image of as-prepared isolated CQDs embedded in PE polymeric residue after liquid nitrogen quenching and filtration.

Figure S6.2 Emission spectra of isolated CQDs suspended in toluene after 0 min (solid line), 10 min (dash-dot line) and 30 min (dash line) sonication with 340 nm (red) and 360 nm (green) excitation.

6.6 References

- (1) Ruj, B.; Pandey, V.; Jash, P.; Srivastava, V. K. Sorting of Plastic Waste for Effective Recycling. *Int. Journal of Applied Sciences and Engineering Research* **2015**, 4 (4), 564–571.
- (2) Ragaert, K.; Delva, L.; van Geem, K. Mechanical and Chemical Recycling of Solid Plastic Waste. *Waste Management* **2017**, 69, 24–58.
- (3) Singh, N.; Hui, D.; Singh, R.; Ahuja, I. P. S.; Feo, L.; Fraternali, F. Recycling of Plastic Solid Waste: A State of Art Review and Future Applications. *Composites Part B: Engineering* **2017**, 115, 409–422.
- (4) Pol, V. G.; Thiagarajan, P. Remediating Plastic Waste into Carbon Nanotubes. *Journal of Environmental Monitoring* **2010**, 12 (2), 455–459.
- (5) Müller, R. J.; Kleeberg, I.; Deckwer, W. D. Biodegradation of Polyesters Containing Aromatic Constituents. *Journal of Biotechnology* **2001**, 86 (2), 87–95.
- (6) Manfredi, S.; Tonini, D.; Christensen, T. H.; Scharff, H. Landfilling of Waste: Accounting of Greenhouse Gases and Global Warming Contributions. *Waste Management and Research* **2009**, 27 (8), 825–836.
- (7) Rhodes, C. J. Plastic Pollution and Potential Solutions. *Science progress* **2018**, 101 (3), 207–260.
- (8) Tall, S. (2000). Recycling of Mixed Plastic Waste – Is Separation Worthwhile?, Royal Institute of Technology. <https://www.diva-portal.org/smash/get/diva2:8665/FULLTEXT01.pdf>
- (9) Geyer, R.; Jambeck, J. R.; Law, K. L. Production, Use, and Fate of All Plastics Ever Made. *Science Advances* **2017**, 3 (7), 10.1126/sciadv.1700782.
- (10) Verma, R.; Vinoda, K. S.; Papireddy, M.; Gowda, A. N. S. Toxic Pollutants from Plastic Waste- A Review. *Procedia Environmental Sciences* **2016**, 35, 701–708.
- (11) Johnke, B. Emissions From Waste Incineration. *Intergovernmental Panel on Climate Change* **1998**, 455–468.
- (12) Hopewell, J.; Dvorak, R.; Kosior, E. Plastics Recycling: Challenges and Opportunities. *Philosophical Transactions of the Royal Society B: Biological Sciences* **2009**, 364 (1526), 2115–2126.
- (13) Ross, S.; Evans, D. The Environmental Effect of Reusing and Recycling a Plastic-Based Packaging System. *Journal of Cleaner Production* **2003**, 11 (5), 561–571.
- (14) Taranic, I.; Behrens, A.; Corrado, T. Understanding the Circular Economy in Europe from Resource Efficiency to Sharing Platforms: The CEPS Framework. *CEPS Special Reports* **2016**, 143, 29.
- (15) Wang, C. qing; Wang, H.; Fu, J. gang; Liu, Y. nian. Flotation Separation of Waste Plastics for Recycling-A Review. *Waste Management* **2015**, 41, 28–38.
- (16) Reinsch, E.; Frey, A.; Albrecht, V.; Simon, F.; Peuker, U. Continuous Electric Sorting in the Recycling Process of Plastics. *Chemie Ingenieur Technik* **2014**, 86, 784–796.
- (17) Chanda, M.; Roy, S. K. *Plastics Technology Handbook*; CRC Press, 2006.
- (18) Censori, M.; La Marca, F.; Carvalho, M. T. Separation of Plastics: The Importance of Kinetics Knowledge in the Evaluation of Froth Flotation. *Waste Management* **2016**, 54, 39–43.
- (19) Thiounn, T.; Smith, R. C. Advances and Approaches for Chemical Recycling of

- Plastic Waste. *Journal of Polymer Science* **2020**, *58* (10), 1347–1364.
- (20) Al-Salem, S. M.; Lettieri, P.; Baeyens, J. Recycling and Recovery Routes of Plastic Solid Waste (PSW): A Review. *Waste Management* **2009**, *29* (10), 2625–2643.
- (21) Brunner, S.; Fomin, P.; Kargel, C. Automated Sorting of Polymer Flakes: Fluorescence Labeling and Development of a Measurement System Prototype. *Waste Management* **2015**, *38* (1), 49–60.
- (22) Maris, E.; Aoussat, A.; Naffrechoux, E.; Froelich, D. Polymer Tracer Detection Systems with UV Fluorescence Spectrometry to Improve Product Recyclability. *Minerals Engineering* **2012**, *29*, 77–88.
- (23) Massardier, V.; Louizi, M.; Maris, E.; Froelich, D. High Shear Dispersion of Tracers in Polyolefins for Improving Their Detection. *Polimeros* **2015**, *25* (5), 466–476.
- (24) Ahmad, S. R. A New Technology for Automatic Identification and Sorting of Plastics for Recycling. *Environmental Technology* **2004**, *25* (10), 1143–1149.
- (25) Langhals, H.; Zgela, D.; Schlücker, T. High Performance Recycling of Polymers by Means of Their Fluorescence Lifetimes*. *Green and Sustainable Chemistry* **2014**, *04* (03), 144–150.
- (26) Gao, G.; Turshatov, A.; Howard, I. A.; Busko, D.; Joseph, R.; Hudry, D.; Richards, B. S. Up-Conversion Fluorescent Labels for Plastic Recycling: A Review. *Advanced Sustainable Systems* **2017**, *1* (5), 160003.
- (27) Arenas-Vivo, A.; Beltrán, F. R.; Alcázar, V.; de la Orden, M. U.; Martínez Urreaga, J. Fluorescence Labeling of High Density Polyethylene for Identification and Separation of Selected Containers in Plastics Waste Streams. Comparison of Thermal and Photochemical Stability of Different Fluorescent Tracers. *Materials Today Communications* **2017**, *12* (July), 125–132.
- (28) Woidasky, J.; Sander, I.; Schau, A.; Moesslein, J.; Wendler, P.; Wacker, D.; Gao, G.; Kirchenbauer, D.; Kumar, V.; Busko, D.; Howard, I. A.; Richards, B. S.; Turshatov, A.; Wiethoff, S.; Lang-Koetz, C. Inorganic Fluorescent Marker Materials for Identification of Post-Consumer Plastic Packaging. *Resources, Conservation and Recycling* **2020**, *161*, 104976.
- (29) Field, M. S.; Wilhelm, R. G.; Quinlan, J. F.; Aley, T. J. An Assessment of the Potential Adverse Properties of Fluorescent Tracer Dyes Used for Groundwater Tracing. *Environmental Monitoring and Assessment* **1995**, *38* (1), 75–96.
- (30) Tchounwou, P. B.; Yedjou, C. G.; Patlolla, A. K.; Sutton, D. J. Heavy Metal Toxicity and the Environment. *Exs* **2012**, *101*, 133–164.
- (31) Ali, H.; Khan, E.; Ilahi, I. Environmental Chemistry and Ecotoxicology of Hazardous Heavy Metals: Environmental Persistence, Toxicity, and Bioaccumulation. *Journal of Chemistry* **2019**, *2019*, 6730305.
- (32) Choyke, P. L.; Alford, R.; Simpson, H. M.; Duberman, J.; Craig Hill, G.; Ogawa, M.; Regino, C.; Kobayashi, H. Toxicity of Organic Fluorophores Used in Molecular Imaging: Literature Review. *Molecular Imaging* **2009**, *8* (6), 341–354.
- (33) Molaei, M. J. Principles, Mechanisms, and Application of Carbon Quantum Dots in Sensors: A Review. *Analytical Methods* **2020**, *12* (10), 1266–1287.
- (34) Zhang, Z.; Zhang, J.; Chen, N.; Qu, L. Graphene Quantum Dots: An Emerging Material for Energy-Related Applications and Beyond. *Energy and*

- Environmental Science* **2012**, 5 (10), 8869–8890.
- (35) Shen, J.; Zhu, Y.; Yang, X.; Li, C. Graphene Quantum Dots: Emergent Nanolights for Bioimaging, Sensors, Catalysis and Photovoltaic Devices. *Chemical Communications* **2012**, 48 (31), 3686–3699.
- (36) Zheng, X. T.; Ananthanarayanan, A.; Luo, K. Q.; Chen, P. Glowing Graphene Quantum Dots and Carbon Dots: Properties, Syntheses, and Biological Applications. *Small* **2015**, 11 (14), 1620–1636.
- (37) Zhou, J.; Booker, C.; Li, R.; Zhou, X.; Sham, T. K.; Sun, X.; Ding, Z. An Electrochemical Avenue to Blue Luminescent Nanocrystals from Multiwalled Carbon Nanotubes (MWCNTs). *Journal of the American Chemical Society* **2007**, 129 (4), 744–745.
- (38) Sun, Y. P.; Zhou, B.; Lin, Y.; Wang, W.; Fernando, K. A. S.; Pathak, P.; Mezziani, M. J.; Harruff, B. A.; Wang, X.; Wang, H.; Luo, P. G.; Yang, H.; Kose, M. E.; Chen, B.; Veca, L. M.; Xie, S. Y. Quantum-Sized Carbon Dots for Bright and Colorful Photoluminescence. *Journal of the American Chemical Society* **2006**, 128 (24), 7756–7757.
- (39) Huang, H.; Xu, Y.; Tang, C. J.; Chen, J. R.; Wang, A. J.; Feng, J. J. Facile and Green Synthesis of Photoluminescent Carbon Nanoparticles for Cellular Imaging. *New Journal of Chemistry* **2014**, 38 (2), 784–789.
- (40) Sharma, A.; Das, J. Small Molecules Derived Carbon Dots: Synthesis and Applications in Sensing, Catalysis, Imaging, and Biomedicine. *Journal of Nanobiotechnology* **2019**, 17 (1), 92.
- (41) Hu, Y.; Gao, Z.; Yang, J.; Chen, H.; Han, L. Environmentally Benign Conversion of Waste Polyethylene Terephthalate to Fluorescent Carbon Dots for “on-off-on” Sensing of Ferric and Pyrophosphate Ions. *Journal of Colloid and Interface Science* **2019**, 538, 481–488.
- (42) Hu, Y.; Yang, J.; Tian, J.; Jia, L.; Yu, J. S. Green and Size-Controllable Synthesis of Photoluminescent Carbon Nanoparticles from Waste Plastic Bags. *RSC Advances* **2014**, 4 (88), 47169–47176.
- (43) Wang, Y.; Hu, A. Carbon Quantum Dots: Synthesis, Properties and Applications. *Journal of Materials Chemistry C* **2014**, 2 (34), 6921–6939.
- (44) Wang, X.; Feng, Y.; Dong, P.; Huang, J. A Mini Review on Carbon Quantum Dots: Preparation, Properties, and Electrocatalytic Application. *Frontiers in Chemistry* **2019**, 7, 671.
- (45) Huang, C.; Dong, H.; Su, Y.; Wu, Y.; Narron, R.; Yong, Q. Synthesis of Carbon Quantum Dot Nanoparticles Derived from Byproducts in Bio-Refinery Process for Cell Imaging and in Vivo Bioimaging. *Nanomaterials* **2019**, 9 (3), 387.
- (46) Stöber, W.; Fink, A.; Bohn, E. Controlled Growth of Monodisperse Silica Spheres in the Micron Size Range. *Journal of Colloid And Interface Science* **1968**, 26 (1), 62–69.
- (47) Beganskiene, A.; Sirutkaitis, V.; Kurtinaitiene, M.; Juskenas, R.; Kareiva, A. FTIR, TEM and NMR Investigations of Stöber Silica Nanoparticles. *Materials Science* **2004**, 10 (4), 287–290.
- (48) Dager, A.; Uchida, T.; Maekawa, T.; Tachibana, M. Synthesis and Characterization of Mono-Disperse Carbon Quantum Dots from Fennel Seeds: Photoluminescence Analysis Using Machine Learning. *Scientific Reports* **2019**, 9

- (1), 1–12.
- (49) Yang, H.; Liu, Y.; Guo, Z.; Lei, B.; Zhuang, J.; Zhang, X.; Liu, Z.; Hu, C. Hydrophobic Carbon Dots with Blue Dispersed Emission and Red Aggregation-Induced Emission. *Nature Communications* **2019**, *10* (1), 1–11.
- (50) Lu, S.; Xiao, G.; Sui, L.; Feng, T.; Yong, X.; Zhu, S.; Li, B.; Liu, Z.; Zou, B.; Jin, M.; Tse, J. S.; Yan, H.; Yang, B. Piezochromic Carbon Dots with Two-Photon Fluorescence. *Angewandte Chemie* **2017**, *129* (22), 6283–6287.
- (51) Wang, T. Y.; Chen, C. Y.; Wang, C. M.; Tan, Y. Z.; Liao, W. S. Multicolor Functional Carbon Dots via One-Step Refluxing Synthesis. *ACS Sensors* **2017**, *2* (3), 354–363.
- (52) Hamid, S. H. *Handbook of Polymer Degradation*; CRC Press, 2000.
- (53) Gardette, M.; Perthue, A.; Gardette, J. L.; Janecska, T.; Földes, E.; Pukánszky, B.; Therias, S. Photo- and Thermal-Oxidation of Polyethylene: Comparison of Mechanisms and Influence of Unsaturation Content. *Polymer Degradation and Stability* **2013**, *98* (11), 2383–2390.
- (54) Vogel, C.; Morita, S.; Sato, H.; Noda, I.; Ozaki, Y.; Siesler, H. W. Thermal Degradation of Poly(3-Hydroxybutyrate) and Poly(3-Hydroxybutyrate- Co-3-Hydroxyhexanoate) in Nitrogen and Oxygen Studied by Thermogravimetric-Fourier Transform Infrared Spectroscopy. *Applied Spectroscopy* **2007**, *61* (7), 755–764.
- (55) Sun, X.; Lei, Y. Fluorescent Carbon Dots and Their Sensing Applications. *TrAC - Trends in Analytical Chemistry* **2017**, *89*, 163–180.
- (56) Ahn, J.; Song, Y.; Kwon, J. E.; Lee, S. H.; Park, K. S.; Kim, S.; Woo, J.; Kim, H. Food Waste-Driven N-Doped Carbon Dots: Applications for Fe³⁺ Sensing and Cell Imaging. *Materials Science and Engineering C* **2019**, *102*, 106–112.
- (57) Dhenadhayalan, N.; Lin, K. C.; Suresh, R.; Ramamurthy, P. Unravelling the Multiple Emissive States in Citric-Acid-Derived Carbon Dots. *Journal of Physical Chemistry C* **2016**, *120* (2), 1252–1261.
- (58) Arumugam, S. S.; Xuing, J.; Viswadevarayalu, A.; Rong, Y.; Sabarinathan, D.; Ali, S.; Agyekum, A. A.; Li, H.; Chen, Q. Facile Preparation of Fluorescent Carbon Quantum Dots from Denatured Sour Milk and Its Multifunctional Applications in the Fluorometric Determination of Gold Ions, in Vitro Bioimaging and Fluorescent Polymer Film. *Journal of Photochemistry and Photobiology A: Chemistry* **2020**, *401*, 112788.
- (59) Sakata, Y.; Uddin, M. A.; Muto, A. Degradation of Polyethylene and Polypropylene into Fuel Oil by Using Solid Acid and Non-Acid Catalysts. *Journal of Analytical and Applied Pyrolysis* **1999**, *51* (1), 135–155.
- (60) Chen, Q.; Schönherr, H.; Vancso, G. J. Block-Copolymer Vesicles as Nanoreactors for Enzymatic Reactions. *Small* **2009**, *5* (12), 1436–1445.
- (61) Yang, R.; Liu, Y.; Yu, J.; Wang, K. Thermal Oxidation Products and Kinetics of Polyethylene Composites. *Polymer Degradation and Stability* **2006**, *91* (8), 1651–1657.
- (62) Shibryaeva, L. Thermal Oxidation of Polypropylene and Modified Polypropylene - Structure Effects. *Polypropylene* **2012**, 63–86.
- (63) Iring, M.; Földes, E.; Barabás, K.; Kelen, T.; Tüdös, F.; Ódor, L. Thermal Oxidation of Linear Low Density Polyethylene. *Polymer Degradation and*

- Stability* **1986**, 14 (4), 319–332.
- (64) He, M.; Zhang, J.; Wang, H.; Kong, Y.; Xiao, Y.; Xu, W. Material and Optical Properties of Fluorescent Carbon Quantum Dots Fabricated from Lemon Juice via Hydrothermal Reaction. *Nanoscale Research Letters* **2018**, 13 (1), 175.
- (65) Zhu, C.; Yang, S.; Wang, G.; Mo, R.; He, P.; Sun, J.; Di, Z.; Kang, Z.; Yuan, N.; Ding, J.; Ding, G.; Xie, X. A New Mild, Clean and Highly Efficient Method for the Preparation of Graphene Quantum Dots without by-Products. *Journal of Materials Chemistry B* **2015**, 3 (34), 6871–6876.
- (66) Zhu, S.; Song, Y.; Zhao, X.; Shao, J.; Zhang, J.; Yang, B. The Photoluminescence Mechanism in Carbon Dots (Graphene Quantum Dots, Carbon Nanodots, and Polymer Dots): Current State and Future Perspective. *Nano Research* **2015**, 8 (2), 355–381.
- (67) Cayuela, A.; Soriano, M. L.; Carrillo-Carrión, C.; Valcárcel, M. Semiconductor and Carbon-Based Fluorescent Nanodots: The Need for Consistency. *Chemical Communications* **2016**, 52 (7), 1311–1326.
- (68) Li, A.; Tang, S.; Tan, P.; Liu, C.; Liang, B. Measurement and Prediction of Oxygen Solubility in Toluene at Temperatures from 298.45 K to 393.15 K and Pressures up to 1.0 MPa. *Journal of Chemical and Engineering Data* **2007**, 52 (6), 2339–2344.
- (69) Zhang, R.; Adsetts, J. R.; Nie, Y.; Sun, X.; Ding, Z. Electrochemiluminescence of Nitrogen- and Sulfur-Doped Graphene Quantum Dots. *Carbon* **2018**, 129, 45–53.
- (70) Sharma, A.; Gadly, T.; Neogy, S.; Ghosh, S. K.; Kumbhakar, M. Molecular Origin and Self-Assembly of Fluorescent Carbon Nanodots in Polar Solvents. *Journal of Physical Chemistry Letters* **2017**, 8 (5), 1044–1052.

Chapter **7**

Outlook

7.1 Introduction

As part of the rapid developments in nanotechnology, silicon-containing nanoparticles (Si-containing NPs) have become an exciting class of materials holding great promise to serve as enablers in emerging application areas.¹⁻³ In this Thesis, we have presented and discussed our efforts to extend the utilization of Si-containing nanoparticles as active ink components for the printing of flexible electronics; as highly effective nucleation agents in polymer foaming; and as nanometric reactors for carbon quantum dot synthesis at relatively mild reaction conditions. However, to move Si-containing nanoparticles from laboratory research to real-life applications, work remains to be done. This Chapter will briefly introduce and discuss some directions for future research towards the large-scale implementation of silicon nanoparticle-based (SiNP-based) inks for printable electronics. In addition, we present preliminary results for the utilization of the SiNPs used in this Thesis as a promising dual probe in magnetic resonance and fluorescent biomedical imaging.

7.2 Long-Term Stability and Printability of SiNP-Based Inks

In Chapter 4, we demonstrated that grafting polymers from SiNP surfaces effectively enhanced the colloidal stability of SiNP inks. With the core-shell hybrid silicon nanoparticles, we successfully prolonged the shelf life of SiNP-based inks and reduced nozzle clogging during inkjet printing. Finally, we demonstrated that the polymer shell is probably responsible for the poor I-V (current-voltage) characteristics of a printed diode. To circumvent this issue, future research must be directed to identify polymer coatings that can stabilize SiNPs-based inks and enhance their printability without leaving too much carbon residue after processing (i.e. annealing) that can negatively affect the electrical properties of printed devices.

Figure 7.1 Schematic drawing of a self-immolative polymer that undergoes head-to-tail depolymerization upon applying an external stimulus.⁴

Using self-immolating polymers (SIPs) to modify SiNPs could be a promising approach to reduce carbon contamination in printed devices. SIPs can readily depolymerize from end-to-end into small molecules with a relatively low boiling point (~ 300 °C) upon applying an external stimulus (See Figure 7.1).⁵ Therefore, we believe that the grafted SIPs can be depolymerized after printing by applying a stimulus and the residue can subsequently be vaporized during the sintering process, which effectively reduces carbon contamination in the printed devices while still possessing a prolonged shelf life and enhanced printability for the SiNP-based electronic inks. There are multiple potentially interesting polymers for this purpose, e.g., poly(benzyl carbamates)⁵, poly(carbamates)⁶, poly(benzyl ether)s⁷, poly(phthalaldehyde)⁸ and poly(α -methyl styrene)⁹. For example, Hernandez et al. recently reported the fabrication of transient electronics using a metastable 2-(4-methoxystyryl)-4,6-bis(trichloromethyl)-1,3,5-triazine/poly(phthalaldehyde) (MBTT/cPPA) substrate.⁸ When triggered by UV-irradiation, the MBTT releases HCl, which depolymerizes the cPPA and destroys electronic devices on the substrate without the need of solvents. When the polymer chains are removed, their surface-immobilized anchoring layers can potentially affect printed devices' performance. Therefore the next section provides a suggestion to consider as alternative polymer shell coupling strategy.

7.3 Strategies for Polymer Immobilization on SiNP Surfaces

In Chapter 4, we have demonstrated the use of surface-initiated atom transfer radical polymerization (SI-ATRP) to synthesize core-shell silicon nanoparticles with a shell of poly(methyl methacrylate) (PMMA) and poly(ethylene glycol) methacrylate (PEGMA) brushes. However, the complex reaction steps and harsh reaction conditions limit the capability of these materials for large-scale production. Moreover, the chemicals (e.g., (3-aminopropyl)-triethoxysilane (APTES) and α -bromoisobutyryl bromide (BiBB)) used to attach the surface-active ATRP initiators increase the risk of contaminating the printed electrical devices and potentially negatively affect their performance. Therefore, it is essential to select new surface derivation strategies to prepare polymer SiNP hybrids.

Figure 7.2 Schematic drawing of SiNP surface derivatization strategies to introduce a) ATRP initiator moieties for subsequent SI-ATRP and b) functional groups (R) by hydrosilylation. The R groups are used to attach polymer chains.

Hydrosilylation is a common approach used in organosilicon synthesis.¹⁰ The recent developments in catalyst-free hydrosilylation make this technique more accessible for the large-scale modification of silicon nanoparticles.^{11–13} Compared to SI-ATRP, the hydrosilylation approach normally introduces less carbon content to the particle surface (see Figure 7.2). Therefore, this method is considered of interest to modify SiNP surfaces before anchoring polymers. However, at the moment, the reaction efficiency for catalyst-free hydrosilylation is relatively low compared to Pt-catalyzed hydrosilylation. Increasing the reaction rate is an essential step to enable large-scale utilization of catalyst-free hydrosilylation for SiNP modification.

7.4 SiNPs as Dual Probe for Magnetic Resonance and Fluorescent Imaging

Besides the application areas mentioned in this Thesis, Si-containing NPs have also been thoroughly studied in biomedicine (see Chapter 2). Their outstanding properties made SiNPs a promising candidate as magnetic resonance imaging (MRI) contrast agents. Through dynamic nuclear polarization (DNP), a process that temporarily creates a non-equilibrium nuclear spin to enhance MR signal by several orders of magnitudes,¹⁴ hyperpolarized ^{29}Si MRI allows obtaining positive-contrast background-free imaging since the human body only contains a small amount of silicon. SiNPs also possess a relatively long spin-lattice relaxation time (T_1 , range of few minutes to hours at room temperature).^{15–17}

In addition to their promising MRI contrast characteristics, SiNPs are also well known for their photoluminescence (PL). Compared to other toxic heavy metal nanoparticles like CdS and CdSe, SiNPs are ideal for in-vivo fluorescence imaging.¹⁸ Ruckenstein and coworkers¹⁹ were one of the first that reported biological imaging with SiNPs. They demonstrated in-vitro imaging of Chinese hamster ovary cells using polyacrylic acid-terminated SiNPs. To date, numerous efforts have been reported that utilize SiNPs for in-vitro and in-vivo fluorescence imaging.^{20–22}

Inspired by the exciting SiNPs material characteristics mentioned above, we made some first attempts to utilize the obtained SiNPs (boron doped, 10^{18} atoms cm^{-3}) as a dual probe for hyperpolarized ^{29}Si MRI and fluorescent imaging.

Excitation Dependent Photoluminescence. The SiNPs used in Chapter 3 and Chapter 4 were suspended in ethylene glycol at a concentration of 120 ppm, and then emission spectra of the suspension were measured with a photoluminescent spectrometer. Figure 7.3 presents the emission spectrum of the SiNPs for excitation wavelengths between 440 nm to 540 nm. All spectra were recorded under identical conditions. Thus, the measured intensities are directly comparable. From Figure 7.3, it is clear that the SiNPs show a strong excitation-wavelength-dependent fluorescence emission. Upon increasing the excitation wavelength (λ_{ex}) from 440 to 540 nm, the emission peaks gradually shift from 590 to 700 nm. The highest emission intensity is observed at $\lambda_{\text{em}} = 620$ nm with $\lambda_{\text{ex}} = 460$ nm. The intensity of the emission peaks decreases upon increasing λ_{ex} from 460 nm to 540 nm.

Figure 7.3 Excitation-dependent PL emission of SiNPs. The excitation wavelength increased from 440 nm to 540 nm.

The exact mechanism for silicon nanoparticle fluorescence is still under debate. However, it is widely agreed that the fluorescence emission is originated from the recombination of excited electron-hole pairs in the quantum-dimensional nanocrystalline core. Those nanocrystalline cores behave as direct bandgap materials during excitation. The excitation-dependent fluorescence is likely due to the size dispersity of the crystal domains embedded in the primary particles.²³ Since the bandgap of the silicon nanoparticles is directly related to the size of the nanocrystalline cores, only the crystalline core with the corresponding diameter (bandgap) will contribute to the luminescence emission.^{23,24} The maximum emission intensity ($\lambda_{em} = 620$ nm) corresponds to a nanocrystalline core with a diameter of 3.74 nm.²³

²⁹Si Magnetic Resonance Imaging. Long T_1 time is critical for targetable DNP MRI agents. In this part, we focused on measuring the T_1 time of our SiNPs using DNP. Prior to DNP, the electron paramagnetic resonance (EPR) of the SiNPs was measured to confirm the presence of free electrons that can be directly hyperpolarized. The EPR spectrum at 4.2 K (Figure 7.4a) shows one resonance peak with a g-value of 2.0055, corresponding to paramagnetic point defects at the interface of crystalline Si and SiO₂.²⁵ Therefore, the free electrons in the SiNPs are primarily located in the surface defects between the crystalline Si and SiO₂ phase. The DNP profiles from frequency modulated (FM) microwave irradiation and continuous wave (CW) irradiation at 4.2 K are shown in Figure 7.4b. It can be observed that the FM irradiation shows considerably higher DNP enhancement compared to CW irradiation. The observed intensity difference between FM and CW irradiation for SiNPs is because FM irradiation can prevent dephasing and relaxation effects during hyperpolarization.²⁶ The DNP build-up curve of SiNPs is shown in Figure 7.4c. DNP build-up curves were recorded with a series of pulse-acquire

experiments with a repetition time of 60s and a low ~ 15 degree flip angle. The DNP build-up time for SiNP is 937 ± 33 s, which is considerably shorter than the value reported for SiNPs in the literature.²⁷ The magnetization decay of polarized SiNPs was measured at 4K (Figure 7.4d). The T_1 extrapolated from the magnetization decay for SiNPs at 4 K is approximately 570 s. As a next step, we note that the SiNPs' T_1 at physiological conditions must be determined before we can conclude that these particles are useful as a probe in dual imaging.

Figure 7.4 a) EPR spectrum of SiNPs. The g -value is 2.0055. b) DNP profiles of SiNPs with (FM microwave irradiation (red) and CW irradiation (green) at 4.2 K. c) DNP build-up curves of SiNPs at 4.2 K using FM irradiation. d) The magnetization decay of the SiNPs at 4.2 K after 4 hours of hyperpolarization.

Overall, these preliminary results show that the SiNPs are magnetic and visually responsive, rendering them a promising candidate to serve as a dual probe for hyperpolarized ^{29}Si MRI and fluorescent biomedical imaging. Future work should focus on i) SiNPs surface modification with organic molecules/polymers to improve the solubility and stability in biofluids, ii) extrapolate the relation between size, T_1 , and an optimal MRI signal at room temperature, and iii) perform laboratory as well as in-vivo tests to evaluate the combined hyperpolarized ^{29}Si MRI and fluorescent imaging capabilities.

7.5 References

- (1) Chang, H.; Sun, S. Q. Silicon Nanoparticles: Preparation, Properties, and Applications. *Chinese Physics B* **2014**, *23* (8), 1–14.
- (2) Jeelani, P. G.; Mulay, P.; Venkat, R.; Ramalingam, C. Multifaceted Application of Silica Nanoparticles. A Review. *Silicon* **2020**, *12* (6), 1337–1354.
- (3) Nayfeh, M. H.; Mitas, L. (2008) Silicon Nanoparticles. New Photonic and Electronic Material at the Transition Between Solid and Molecule. In V. Kumar (Ed.). *Nanosilicon* (pp 1-78). Elsevier.
- (4) Peterson, G. I.; Larsen, M. B.; Boydston, A. J. Controlled Depolymerization: Stimuli-Responsive Self-Immolative Polymers. *Macromolecules* **2012**, *45* (18), 7317–7328.
- (5) Sagi, A.; Weinstein, R.; Karton, N.; Shabat, D. Self-Immolative Polymers. *Journal of the American Chemical Society* **2008**, *130* (16), 5434–5435.
- (6) Robbins, J. S.; Schmid, K. M.; Phillips, S. T. Effects of Electronics, Aromaticity, and Solvent Polarity on the Rate of Azaquinone-Methide-Mediated Depolymerization of Aromatic Carbamate Oligomers. *Journal of Organic Chemistry* **2013**, *78* (7), 3159–3169.
- (7) Olah, M. G.; Robbins, J. S.; Baker, M. S.; Phillips, S. T. End-Capped Poly(Benzyl Ethers): Acid and Base Stable Polymers That Depolymerize Rapidly from Head-to-Tail in Response to Specific Applied Signals. *Macromolecules* **2013**, *46* (15), 5924–5928.
- (8) Lopez Hernandez, H.; Kang, S. K.; Lee, O. P.; Hwang, S. W.; Kaitz, J. A.; Inci, B.; Park, C. W.; Chung, S.; Sottos, N. R.; Moore, J. S.; Rogers, J. A.; White, S. R. Triggered Transience of Metastable Poly(Phthalaldehyde) for Transient Electronics. *Advanced Materials* **2014**, *26* (45), 7637–7642.
- (9) Malhotra, S. L.; Baillet, C.; Minh, L.; Blanchard, L. P. Thermal Decomposition of Poly- α -Methylstyrene. *Journal of Macromolecular Science: Part A - Chemistry* **1978**, *12* (1), 129–147.
- (10) Hofmann, R. J.; Vlatkovic, M.; Wiesbrock, F. Fifty Years of Hydrosilylation in Polymer Science: A Review of Current Trends of Low-Cost Transition-Metal and Metal-Free Catalysts, Non-Thermally Triggered Hydrosilylation Reactions, and Industrial Applications. *Polymers* **2017**, *9* (10), 534.
- (11) Lie, L. H.; Duerdin, M.; Tuite, E. M.; Houlton, A.; Horrocks, B. R. Preparation and Characterisation of Luminescent Alkylated-Silicon Quantum Dots. *Journal of Electroanalytical Chemistry* **2002**, *538*, 183–190.
- (12) Rogozhina, E. v.; Eckhoff, D. A.; Gratton, E.; Braun, P. v. Carboxyl Functionalization of Ultrasmall Luminescent Silicon Nanoparticles through Thermal Hydrosilylation. *Journal of Materials Chemistry* **2006**, *16* (15), 1421–1430.
- (13) Yu, Y.; Hessel, C. M.; Bogart, T. D.; Panthani, M. G.; Rasch, M. R.; Korgel, B. A. Room Temperature Hydrosilylation of Silicon Nanocrystals with Bifunctional Terminal Alkenes. *Langmuir* **2013**, *29* (5), 1533–1540.
- (14) Seo, H.; Choi, I.; Whiting, N.; Hu, J.; Luu, Q. S.; Pudakalakatti, S.; McCowan, C.; Kim, Y.; Zacharias, N.; Lee, S.; Bhattacharya, P.; Lee, Y. Hyperpolarized Porous Silicon Nanoparticles: Potential Theragnostic Material for ^{29}Si Magnetic

- Resonance Imaging. *ChemPhysChem* **2018**, *19* (17), 2143–2147.
- (15) Atkins, T. M.; Cassidy, M. C.; Lee, M.; Ganguly, S.; Marcus, C. M.; Kauzlarich, S. M. Synthesis of Long T_1 Silicon Nanoparticles for Hyperpolarized ^{29}Si Magnetic Resonance Imaging. *ACS Nano* **2013**, *7* (2), 1609–1617.
 - (16) Lilburn, D. M. L.; Pavlovskaya, G. E.; Meersmann, T. Perspectives of Hyperpolarized Noble Gas MRI beyond ^3He . *Journal of Magnetic Resonance* **2013**, *229*, 173–186.
 - (17) Keshari, K. R.; Wilson, D. M. Chemistry and Biochemistry of ^{13}C Hyperpolarized Magnetic Resonance Using Dynamic Nuclear Polarization. *Chem Soc Rev.* **2014**, *43* (5), 1627–1659.
 - (18) Peng, F.; Su, Y.; Zhong, Y.; Fan, C.; Lee, S. T.; He, Y. Silicon Nanomaterials Platform for Bioimaging, Biosensing, and Cancer Therapy. *Accounts of Chemical Research* **2014**, *47* (2), 612–623.
 - (19) Li, Z. F.; Ruckenstein, E. Water-Soluble Poly(Acrylic Acid) Grafted Luminescent Silicon Nanoparticles and Their Use as Fluorescent Biological Staining Labels. *Nano Letters* **2004**, *4* (8), 1463–1467.
 - (20) Shiohara, A.; Hanada, S.; Prabakar, S.; Fujioka, K.; Lim, T. H.; Yamamoto, K.; Northcote, P. T.; Tilley, R. D. Chemical Reactions on Surface Molecules Attached to Silicon Quantum Dots. *Journal of the American Chemical Society* **2010**, *132* (1), 248–253.
 - (21) Zhou, Y.; Zhang, Y.; Zhong, Y.; Fu, R.; Wu, S.; Wang, Q.; Wang, H.; Su, Y.; Zhang, H.; He, Y. The in Vivo Targeted Molecular Imaging of Fluorescent Silicon Nanoparticles in *Caenorhabditis Elegans*. *Nano Research* **2018**, *11* (5), 2336–2346.
 - (22) Cao, Z.; Peng, F.; Hu, Z.; Chu, B.; Zhong, Y.; Su, Y.; He, S.; He, Y. In Vitro Cellular Behaviors and Toxicity Assays of Small-Sized Fluorescent Silicon Nanoparticles. *Nanoscale* **2017**, *9* (22), 7602–7611.
 - (23) Kim, T. Y.; Park, N. M.; Kim, K. H.; Sung, G. Y.; Ok, Y. W.; Seong, T. Y.; Choi, C. J. Quantum Confinement Effect of Silicon Nanocrystals in Situ Grown in Silicon Nitride Films. *Applied Physics Letters* **2004**, *85* (22), 5355–5357.
 - (24) Meier, C.; Gondorf, A.; Lüttjohann, S.; Lorke, A.; Wiggers, H. Silicon Nanoparticles: Absorption, Emission, and the Nature of the Electronic Bandgap. *Journal of Applied Physics* **2007**, *101* (10), 103112.
 - (25) Stesmans, A.; Jivanescu, M.; Godefroo, S.; Zacharias, M. Paramagnetic Point Defects at $\text{SiO}_2/\text{Nanocrystalline Si}$ Interfaces. *Applied Physics Letters* **2008**, *93* (2), 023123.
 - (26) Blazina, D.; Duckett, S. B.; Halstead, T. K.; Kozak, C. M.; Taylor, R. J. K.; Anwar, M. S.; Jones, J. A.; Carteret, H. A. Generation and Interrogation of a Pure Nuclear Spin State by Parahydrogen-Enhanced NMR Spectroscopy: A Defined Initial State for Quantum Computation. *Magnetic Resonance in Chemistry* **2005**, *43* (3), 200–208.
 - (27) Kwiatkowski, G.; Jähnig, F.; Steinhauser, J.; Wespi, P.; Ernst, M.; Kozerke, S. Nanometer Size Silicon Particles for Hyperpolarized MRI. *Scientific Reports* **2017**, *7* (1), 7946.

Summary

Due to the swift progress in nanotechnology new and exciting opportunities have become within reach for nanoparticles. Great progress has been made in utilizing silicon-containing nanoparticles in various applications, e.g., in drug delivery, bio-sensing, energy (solar cell) utilization, and energy storage. The work presented in this Thesis aims at exploiting the frontier of silicon-containing nanoparticles from the application perspective. Both silicon (Si NPs) and silica (SiO₂ NPs) nanoparticles have formed target systems.

In **Chapter 2**, a literature review, introducing the general aspects and synthetic strategies of silicon-based nanoparticles are provided. In addition, a detailed overview of the utilization of silicon-based nanoparticles in emerging application areas, including printing of electronic devices, biomedical imaging, nanocellular foaming, and catalysis, are also reviewed. The limitations and challenges hampering the successful integration of silicon-based nanoparticles into real-life applications are presented and discussed, as well.

As the first step of formulating Si NPs-based printable electronic inks, in **Chapter 3**, the long-term colloidal stability of SiNPs with complex geometry and broad size distribution are studied in detail, combining theoretical and experimental approaches. The colloidal stability of SiNPs in different alcohols and glycols is evaluated by applying Stokes' law. In addition, the long-term colloidal stability of SiNP dispersions is investigated with experimental approaches, i.e. analytical centrifugation and batch sedimentation. Furthermore, the limitations of using theories and analytical centrifugation to predict the long-term colloidal stability of SiNPs with complex geometries and broad size distributions are elucidated. Eventually, based on the results presented and discussed in this Chapter, we conclude that surface modification of the SiNPs is needed to obtain SiNP inks with the required dispersion stability.

In **Chapter 4**, core-shell SiNP/polymer hybrids are prepared to enhance the printability of SiNP-based inks introduced in Chapter 3. The SiNP/polymer hybrid-based inks are tested with inkjet printing and spin coating. Moreover, the influence of the grafted polymer on the electrical properties of the printed electronic devices' is also thoroughly investigated. Using core-shell SiNP/polymer hybrids is shown to constitute an effective approach to reduce nozzle clogging during inkjet printing. Furthermore, the

polymer shell prevents undesirable chemical reactions between particle and solvent from occurring, which broadens the range of solvents suitable for ink formulation. However, the grafted polymer shell around the SiNPs has a negative impact on the performance of the printed electronic devices fabricated with these NPs. This points out the urgency to search for alternative polymers and immobilization strategies to reduce the influence of polymer grafts on the functionality of printed devices, while maintaining enhanced colloidal stability and improved printability of the SiNP-based inks.

Besides SiNPs, SiO₂ are a fascinating class of silicon-containing nanoparticles, and they are investigated in two applications at the frontiers of nanoparticle science in this Thesis, as well. Surface roughness engineered SiO₂ (SiO₂-R) NPs with poly(dimethylsiloxane) (PDMS) shells are presented in **Chapter 5** as nucleating agents in the CO₂ batch foaming of poly(methyl methacrylate) (PMMA) nanocellular foams. We showed that the nanocavities (concave surfaces) on SiO₂-R NPs can act as heterogeneous nucleation centers. We concluded that the concave surface effectively reduces the free energy for foam cell nucleation. The PDMS decorated SiO₂-R NPs can nucleate multiple foam cells from a single particle. Due to capillary condensation inside the nanocavities, SiO₂-R NPs can absorb more CO₂ during saturation than their nearly smooth counterparts. Moreover, the PDMS shell boosts the CO₂ uptake, resulting in multiple nucleation sites on a single particle. This results in a nucleation efficiency of 6.2 for 200 nm PDMS coated SiO₂-Rs, which is 40 times higher than their nearly smooth counterparts.

In **Chapter 6**, SiO₂ NP aggregates are used as enablers to fabricate carbon quantum dot (CQD) fluorescent markers containing polyethylene (PE). The SiO₂ NP aggregates are obtained by suspending monodispersed SiO₂ NPs in toluene. The pores on the aggregates act as nanometric reactors and facilitate CQD formation when PE chains enter while the solution is heated. Strong blue fluorescence is observed from the resulting PE/CQD composites. Upon decreasing the reaction temperature from 110 °C to 90 °C, the maximum emission wavelength shifts from 394 nm to 408 nm for PE/CQD composites. This shift in emission wavelength is attributed to the increased oxygen content in the reaction mixture upon decreasing the reaction temperature. The CQDs can be extracted from PE/CQD composites via a simple freeze-melt process. The extracted CQDs have an average diameter of 2.3 ± 0.5 nm, as is obtained by TEM image analysis. Finally, we demonstrate that PE/CQD composites and extracted CQDs marked PE samples could be visually separated from pure unmarked PE upon irradiation with 367 nm light.

In **Chapter 7**, we suggest future research directions for SiNP-based inks. We exploit the possible use of self-immolating polymers and catalyst-free hydrosilylation as the next essential step to reduce the impact of polymer coating on the performance of printed electronic devices. Moreover, we present preliminary results on utilizing multi-crystalline SiNPs as a dual imaging agent for magnetic resonance imaging and fluorescent imaging.

Samenvatting

Vanwege de snelle vooruitgang in de nanotechnologie zijn er allerlei nieuwe en interessante mogelijkheden binnen handbereik gekomen voor nanodeeltjes. Er is veel vooruitgang geboekt om silicium-houdende nanodeeltjes in verscheidene toepassingen, zoals medicijnen, biosensoren, energie opwekking (zonnecellen), en energie opslag, te gebruiken. Het in dit proefschrift uiteengezette werk richt zich er op om vanuit een toepassingsperspectief het uiterste uit silicium-houdende nanodeeltjes te halen. Zowel silicium (SiNPs) als silica (SiO₂ NPs) nanodeeltjes zijn hiervoor gebruikt.

In **Hoofdstuk 2**, een literatuur overzicht, worden algemene aspecten en synthese strategieën voor op silicium gebaseerde nanodeeltjes gegeven. Hiernaast wordt een gedetailleerd overzicht voor het gebruik van op silicium gebaseerde nanodeeltjes, waaronder het printen van elektronica, biomedisch imaging, nanocellulair schuimen, en katalyse, gegeven. De beperkingen alsook de uitdagingen die de succesvolle toepassing van op silicium gebaseerde nanodeeltjes in de weg staan, worden ook uiteengezet en besproken.

In **Hoofdstuk 3** wordt als eerste stap voor de op SiNPs gebaseerde printbare, elektronische inkt-formulering, de colloïdale stabiliteit van SiNPs met complexe geometrie en brede distributie van de deeltjesgrootte, in detail bestudeerd, waarbij theoretische en experimentele benaderingen worden gecombineerd. De colloïdale stabiliteit van SiNPs in verschillende alcoholen en glycolen wordt hier geëvalueerd door middel van de Wet van Stokes. Daarnaast wordt de colloïdale stabiliteit van SiNP suspensies op de lange termijn onderzocht met behulp van experimentele benaderingen, d.w.z., analytisch centrifugeren en batch sedimentatie. Ook worden de beperkingen van het gebruik van theorieën alsook analytisch centrifugeren om de colloïdale stabiliteit van SiNPs met complexe geometrie en brede distributie van de deeltjesgrootte op de lange termijn te bepalen, verder uitgediept. Uiteindelijk, gebaseerd op de resultaten die gepresenteerd en uitgelegd zijn in dit Hoofdstuk, concluderen we dat oppervlakte aanpassingen van SiNPs nodig is om een SiNP inkt te kunnen maken met de vereiste dispersie stabiliteit.

In **Hoofdstuk 4** worden core-shell SiNP/polymer hybride deeltjes gemaakt om de printbaarheid van op SiNP gebaseerde inkt, zoals geïntroduceerd in Hoofdstuk 3. De SiNP/polymer hybride inkten zijn getest door middel van inkjet printen en spin coating.

Hiernaast wordt ook de invloed van de geënte polymeer op de elektrische eigenschappen van de geprinte elektronische apparaten uitvoerig bestudeerd. Van het gebruik van core-shell SiNP/polymer hybride deeltjes wordt aangetoond dat het een effectieve manier is om verstopping van printmoppen tijdens het printen te voorkomen. Verder voorkomt de polymeer schil dat ongewenste chemische reacties tussen de deeltjes en de oplosmiddelen plaatsvindt. Echter, de geënte polymeer schil rondom de SiNPs heeft een negatieve impact op de prestatie van de met deze nanodeeltjes gemaakte, geprinte elektronische apparaten. Dit benadrukt de noodzaak om in volgende stappen te zoeken naar alternatieve polymeren en immobilisatie strategieën om de invloed van geënte polymeren op de functionaliteit van geprinte apparaten met behoud van de verbeterde colloïdale stabiliteit en verbeterde printbaarheid van de op SiNPs gebaseerde inkten te verminderen.

Naast SiNPs zijn ook SiO₂ deeltjes een interessante groep van silicium houdende nanodeeltjes. Deze groep wordt ook in dit proefschrift onderzocht door middel van twee toepassingen op de grenzen van het nanodeeltjes-vakgebied. Het gebruik van SiO₂ deeltjes met ruwe oppervlaktes (SiO₂-R) met polydimethylsiloxaan (PDMS) schillen als cel nucleatiekernen wordt gedemonstreerd in **Hoofdstuk 5** door middel van het CO₂ batch schuim proces van polymethyl methacrylate (PMMA) nanocellulaire schuimen. We laten zien dat de nanoholtes (met concaaf oppervlak) op de SiO₂-R NPs kunnen dienen als heterogene nucleatie kernen. We concluderen dat het concave oppervlak de vrije energie, benodigd voor schuim cel nucleatie, verlaagd. De, in PDMS gehulde, SiO₂-R NPs kunnen meer CO₂ absorberen tijdens de verzadigingsstap dan de gladde tegenhangers. Ook verbeteren de PDMS schillen de CO₂ opname waardoor meerdere nucleaties kunnen plaatsvinden op één enkel deeltje. Dit leidt tot een nucleatie efficiëntie van 6.2 voor met PDMS gehulde SiO₂-R NPs, wat maar liefst 40 keer hoger is dan voor de gladde tegenhangers.

In **Hoofdstuk 6** worden SiO₂ NP aggregaten gebruikt als platform om fluorescente, polyethyleen bevattende carbon quantum dot (CQD) markers te maken. De SiO₂ NP aggregaten zijn verkregen door middel van de suspensie van monodisperse SiO₂ NPs in toluen. De poriën op de aggregaten dienen als nanoreactoren en faciliteren CQD formatie wanneer de polyethyleen ketens zich hierin bevinden terwijl de oplossing wordt verhit. Intense blauwe fluorescentie wordt geobserveerd in de PE/CQD composieten. Wanneer de reactie temperatuur van 110 °C naar 90 °C verlaagd wordt, verschuift de emissie golflengte van 394 nm naar 408 nm voor de PE/CQD composieten. Deze verschuiving in emissie golflengte wordt toegedicht aan het verhoogde zuurstof gehalte in het reactie mengsel wanneer de temperatuur verlaagd wordt. De CQDs kunnen uit het PE/CQD composiet gehaald worden door middel van een simpel vreis-smelt proces. De

geëxtraheerde CQDs hebben een gemiddelde diameter van 2.3 ± 0.5 nm, zoals gemeten met TEM analyse. Concluderend, we hebben van PE/CQD composieten en met geëxtraheerde CQDs gemarkeerde PE monsters laten zien dat ze op visuele basis onderscheiden kunnen worden van schone, ongemarkeerde PE onder bestraling met licht van 367 nm golflengte.

In **Hoofdstuk 7** stellen we voor op SiNPs gebaseerde inkt, een aantal potentiële onderzoeksrichtingen voor. We verkennen het potentieel gebruik van zelf-verbrandende polymeren en katalysatorvrije hydrosilylatie als de volgende essentiële stap om de invloed van polymeer coatings op de prestatie van geprinte elektronische apparaten. Hiernaast presenteren we ook de voorlopige resultaten voor het gebruik van multi-kristallijne SiNPs als een tweezijdig imaging agent voor magnetic resonance imaging (MRI) en fluorescentie imaging.

Acknowledgements

Before finishing the Thesis, I want to dedicate this section to express my deepest gratitude to all those who have supported me along these years.

First and foremost, I would love to express my deepest gratitude and sincere appreciation to my promoter, Prof. Julius Vancso. Dear Julius, it is a great pleasure and honor to be your student and to be part of the SPC (MTP). You are a serious, rigorous, and enthusiastic scientist in teaching and scientific research. Your broad knowledge and precise perspectives towards science and technology have benefited me a lot. Your patient guidance and encouragement provided me the great motivation and enjoyments that kept me going.

My gratitude and appreciation also transfer to my supervisor/assistant promotor, Dr. Joost Duvinneau. Dear Joost, thank you for your supervision and help during all these years. Your professional and sharp insights towards scientific research and writing have inspired me a lot. Every discussion and meeting with you end with constructive suggestions and encouragements, which highly motivated me in fulfilling my research activities. I am very grateful for the plentiful efforts and time that you have spent on guiding me. You are not only a great supervisor, but also a great friend for me. I enjoyed every scientific discussion and daily conversation with you.

I would also like to thank my daily supervisor Dr. Olivier Nguon. Dear Olivier, thank you for your guidance in the first two years of my Ph.D. Starting a Ph.D is always hard and sometimes confusing. I am lucky to have you there to guide me through the first two years. Your sharp insights and rigorous attitude towards scientific research are an inspiration to me.

Dearest Julius, Joost, and Olivier, without the guidance and support from you, the work described in this Thesis would not be accomplished. Words are powerless to express my gratitude and thanks to all of you. I sincerely wish you and your families all the best in the coming future.

I would also like to thank all the other collaborators in the Thesis: Prof. Niels Benson, Fabian Langer, Laura Kühnel, Juha Niittynen, Joost Valetton, Dr. Dominique Thies-Weesie, Paul H.H. Bomans. Thanks, Prof. Niels Benson, Fabian Langer, Laura Kühnel for your help and valuable discussion in inkjet printing and diode processing of silicon

nanoparticle inks. Thanks, Juha Niittynen and Joost Valeton for the help and valuable discussion in inkjet printing of silicon nanoparticles. Thanks, Dr. Dominique Thies-Weesie for the help and valuable discussion of analytical centrifugation of silicon nanoparticle inks. Thanks Paul H.H. Bomans for conducting the high-resolution transmission electron microscopy measurements.

I would also like to thank my defense committee members, Prof. Leon Lefferts, Prof. Anke Blume, Prof Niels Benson, Prof. Mikael Hedenqvist, Dr. Olivier Nguon, for your time to read my thesis and give me constructive suggestions.

The next person I would like to express my sincere gratitude to is Clemens Padberg. Dear Clemens, you are one of the most amazing persons in the SPC (MTP) group. You can fix almost every instrument failure in our group (and others) and are always willing to help with anything. This makes everyone chase after you for help every day, certainly, including me. But no matter how busy you are, you are always glad and timely to help me.

Grateful thanks to our secretaries, Romon, Marion, Nicole, and Izabel, for your help. You are always there when I need help, whether dealing with various tedious TGS processes or providing support for paperwork.

Next, I would like to give my special thanks to my best Chinese friends from MTP, Kaihuan, Yan, Shanqiu, Yunchong, Huan, and Jinmeng. Thank you for your assistance in my earlier life and research work. I wish you and your loved ones all the best.

I also wish to thank all the present and former SPC (MTP) members. Thanks a lot for the help from you guys, and I really enjoyed the time we have spent together. It is of great pleasure to have the chance to work with you.

Finally, I would like to express my most enormous thanks to my family members who always support me, my parents (殷建立, 刘静), my wife (石湘雯). I am very grateful for the endless love and support from them. Without all your suggestions and support, I would not be at the point where I am now. Sincerely wish all of you a healthy and happy life. I love you all.

殷思达
Sida Yin
Enschede, 2021

List of Publications

➤ Journal articles:

1. Liu, S.; **Yin, S.**; Duvigneau, J.; Vancso, G. J. Bubble Seeding Nanocavities: Multiple Polymer Foam Cell Nucleation by Polydimethylsiloxane-Grafted Designer Silica Nanoparticles. *ACS Nano* 2020, *14* (2), 1623–1634.
2. **Yin, S.**; Duvigneau, J.; Vancso, G. J. Fluorescent polyethylene by in-situ facile synthesis of carbon quantum dots facilitated by silica nanoparticle agglomerates, *Accepted*

➤ Manuscripts:

1. **Yin, S.**; Nguon, O. J.; Duvigneau, J.; Vancso, G. J. Dispersion stability of nonspherical silicon nanoparticles: impact of solvent selection and storage time, *submitted*.
2. **Yin, S.**; Duvigneau, J.; Vancso, G. J. Emerging applications of silicon-containing nanoparticles, *in preparation*.

Curriculum Vitae

Sida Yin was born on Aug. 04th, 1990 in Hebei China. After finishing his B.Sc. in 2014, he continued his master studies in chemical engineering at University of Twente in the same year. This research project was conducted in the group of Prof. dr. Julius Vancso and focused on the CO₂ assisted nanocellular polymer foaming with silica nanoparticles as efficient nucleation agents. After graduation in 2016, he continued as a Ph.D. student under the supervision of Prof. dr. Julius Vancso and Dr. Joost Duvigneau in the group of Materials Science and Technology of Polymers (MTP) (later Sustainable Polymer Chemistry group) at the University of Twente. His Ph.D. project focused on utilizing the application potential of Si-containing NPs (SiNPs and SiO₂ NPs) to ensure continuous progress in the field. The result of his research are described in this Thesis.

Silicon

piitä

मिळीवरु

silício

ຊີລິໂຄນ

硅

siliciu

sîlîkon

lesilicon

nesilicon

silizioa

uḥlḥghnLḥ

نوكيليسلا

ซิลิคอน

ሲሊከን

silīcijs

kremniý

Pii

pakachitsulo

silicio

Silizium

silikon

ସିଲିକନ୍ |

silicium

räni

סיליציום

sileacain

silicio

సిలికాన్

silisium

kisel

kremík

кремний

सिलिकन

πυρίτιο