Analysis of Extreme Ultraviolet Induced Surface Defect Processes

An Gao

Ph.D. committee

Chairman:

Prof.dr.ir. J.W.M. Hilgenkamp

University of Twente, TNW

Secretary:

Prof.dr.ir. J.W.M. Hilgenkamp

University of Twente, TNW

Promoter:

Prof.dr. F. Bijkerk

University of Twente, TNW

Co-Promoter:

Dr. C.J. Lee

University of Twente, TNW

Members:

Prof.dr. A.P. Mosk

University of Twente, TNW

Prof.dr. J. Schmitz

University of Twente, TNW

Prof.dr. W. van der Zande

Radboud University Nijmegen

Prof.dr. M.W. Beijersbergen

University of Leiden

Prof.dr. J. Herek

University of Twente, TNW

Cover: An optical instrument built in this PhD project, which can serve Photoluminescence and Raman measurement. Photography by Dr. Lennino Cacace

Analysis of Extreme Ultraviolet Induced Surface Defect Processes

Ph.D Thesis, University of Twente, Enschede – Illustrated.

With references – With summary in English and Dutch

ISBN: 978-90-365-3985-2

Printed by Ridderprint BV, the Netherlands

ANALYSIS OF EXTREME ULTRAVIOLET INDUCED SURFACE DEFECT PROCESSES

PROEFSCHRIFT

ter verkrijging van de
graad van doctor aan de Universiteit Twente,
op gezag van de rector magnificus,
prof. dr. H. Brinksma,
volgens besluit van het College voor Promoties
in het openbaar te verdedigen op
donderdag 22 oktober 2015 om 12:45 uur

door

An Gao

geboren op 25 Nov 1984
te Shandong, China

Dit proefschrift is goedgekeurd door de promotor

Prof.dr. F. Bijkerk

en assistent promotor

Dr. C.J. Lee

This thesis is based on the following publications:

Chapter 4:

A. Gao, P. J. Rizo, L. Scaccabarrozi, C.J. Lee, V. Banine, F. Bijkerk, "Photoluminescence-based detection of particle contamination on Extreme Ultra-Violet reticles" *Review of Scientific Instruments* **86**, 063109 (2015)

Chapter 5:

A. Gao, P.J. Rizo, E. Zoethout, L. Scaccabarozzi, C.J. Lee, V. Banine, F. Bijkerk, "Extreme ultraviolet induced defects on few-layer graphene", *Journal of Applied. Physics* **114**, 044313 (2013)

Chapter 6:

A. Gao, E. Zoethout, J.M. Sturm, C.J. Lee, F. Bijkerk, "Defect formation in single layer graphene under extreme ultraviolet irradiation", *Applied Surface Science*, **317** . 745 - 751 (2014)

Chapter 7:

A. Gao, C.J. Lee, F. Bijkerk, "Graphene defect formation by extreme ultraviolet generated photoelectrons", *Journal of Applied Physics*. **116**, 054312 (2014)

This work is part of the research programme 'Controlling photon and plasma induced processes at EUV optical surfaces (CP3E)' of the 'Stichting voor Fundamenteel Onderzoek der Materie (FOM)', which is financially supported by the 'Nederlandse Organisatie voor Wetenschappelijk Onderzoek (NWO)'. The CP3E programme is co-financed by Carl Zeiss SMT and ASML. We also acknowledge financial support from Agentschap NL (EXEPT project).

Table of Contents

Chapter 1	Introduction	1
1.1	Photolithography	1
1.2	EUV reticles and reticle defects	4
1.3	Particle contamination on reticles in EUVL.....	7
1.4	Inspection of particle contamination	9
1.5	EUV Pellicle: prevention of particle contamination.....	13
1.6	Outline of this thesis	15
1.7	References	16
Chapter 2	Photoluminescence	20
2.1	Introduction	20
2.2	Color centers.....	26
2.3	Photoluminescence from particles in EUVL	28
2.4	References	29
Chapter 3	Graphene.....	31
3.1	Introduction	31
3.2	Graphene synthesis.....	32
3.3	Defects in graphene	36
3.4	Graphene characterization: Raman spectroscopy.....	38
3.5	Reference	44
Chapter 4	Photoluminescence-based detection of particle contamination on EUV reticles	48
4.1	Introduction	48
4.2	Theory.....	51
4.3	Experimental setup	53
4.4	Experiment procedure	55
4.5	Results and Discussion	56

4.6	Conclusion	66
4.7	References.....	67
Chapter 5	EUV induced defects in few-layer graphene	70
5.1	Introduction.....	70
5.2	Experimental	71
5.3	Results and discussion	72
5.3.1	Raman analysis	72
5.3.2	XPS analysis	76
5.4	Conclusions.....	78
5.5	References.....	79
Chapter 6	Defects formation in single layer graphene under extreme ultraviolet irradiation	82
6.1	Introduction.....	82
6.2	Experiments	84
6.3	Results and discussion	85
6.3.1	Photo-induced plasma of the residual water	85
6.3.2	Photo-induced plasma of the adsorbed water.....	88
6.3.3	Exposing graphene with hydrocarbon contamination...	94
6.4	Conclusion	97
6.5	Reference	98
Chapter 7	Graphene defect formation by Extreme UV generated photoelectrons	101
7.1	Introduction.....	102
7.2	Experiments	103
7.3	Results and Discussion.....	104
7.4	Conclusion	112
7.5	Reference	113
Chapter 8	Valorization.....	116

8.1	Inspection of EUV reticles	116
8.2	Pellicle for the EUV reticle	119
8.3	Conclusion.....	124
8.4	References	124
Chapter 9	Summary.....	126
	Acknowledgement.....	132
	Curriculum Vitae	134

Chapter 1 Introduction

1.1 Photolithography

Defect free imaging is of paramount importance for many optical systems. Photolithography, for instance, is a key process in semiconductor manufacturing, and a technology which requires ultimate imaging control. It transfers chip patterns from a photomask or reticle* to silicon wafers coated with a photo-sensitive lacquer, or resist. A simplified version of an optical lithography system, i.e. designed for the visible or near UV wavelength range, is shown in **Figure 1-1**. Light from a light source is collimated by a condenser lens; then the light passes through the reticle, where the light is partially blocked by an absorber pattern on the reticle, while the transmitted pattern is projected on the wafer by the projection optics.

The smallest feature that can be patterned is often described as the critical dimension (CD) in semiconductor processing. Making the critical dimension smaller is the primary concern of the semiconductor industry, for two main reasons: 1) the number of devices per unit area can increase. Therefore, more devices (integrated circuits) will be produced per wafer, reducing the cost of a single device; 2) a smaller CD improves the performance of the device by allowing, for instance, a faster clock speed (frequency), and/or lower power consumption. The CD is given by Rayleigh's equation:¹

---

* In the early days of lithography, the layout on the mask was identical to that on the wafer. However, in current lithography systems (wafer scanners), the pattern on the mask covers only part of wafer, and full wafer coverage is achieved by repetitive projection of this pattern on the wafer. These types of masks are usually called reticles.

Figure 1-1 A schematic view of an optical photolithography system.

$$C = k_1 \frac{\lambda}{N_A} \quad 1-1$$

where C is the critical dimension, k_1 is an empirical coefficient related to the implementation details of the imaging system, λ is the wavelength of the light used, and N_A is the numerical aperture (NA) of the projection lens. According to **Eq. 1.1**, the minimum feature size can be reduced by decreasing the wavelength of the light and k_1 . Phase-shift masks, off-axis illumination, and double patterning are used to reduce k_1 . One may notice that increasing NA will also reduce the CD. However, this will raise another concern in the design of the lithography optics: the depth of focus (DOF) diminishes. The DOF is a measure of the tolerance of displacement of the reticle or the wafer perpendicular to the surface. The DOF constrains the thickness of the photoresist and the topography of the wafer, and is given as:¹

$$f = k_2 \frac{\lambda}{N_A^2} \quad 1-2$$

Where f is the depth of focus, k_2 is also an empirically determined coefficient. If an optical system is designed to have a larger NA to reduce the critical dimension, at the same time, the DOF will be reduced at an even faster rate, since it has a quadratic dependence on the NA. Note that k_1 and k_2 both depend on a large number of practical factors, such as process parameters, resist, the type of reticle, and the type of illumination. Typically, they are both in the range of 0.5 to 1.0.²

Eq. 1.1 and **1.2** also provide the basis for understanding how defects on the optics, such as mirrors, lenses, and reticles, can influence their imaging performance. For example, a particle on a reticle can be imaged (or printed) within the depth of focus on the wafer. The creation of reticle defects and their imaging are discussed in detail in **Sec. 1.2**.

As mentioned above, the critical dimension is dependent on the wavelength of the light source used in the lithography system. In the early days, gas discharge mercury lamps (sometimes with noble gases, such as xenon) were used. The light produced by such lamps was filtered to select particular wavelengths: 436 nm, 405 nm, and 365 nm. However, as the shrinkage of the integrated circuit feature size continued, shorter wavelengths were required for lithography. To decrease the wavelength, excimer lasers, such as KrF at 248 nm and ArF laser at 193 nm, were developed. Currently, the most advanced lithography systems use immersion techniques with a water film between the lens and the resist, allowing an effectively larger value of NA. This technique is capable of printing features down to 14 nm with a complex combination of techniques, such as double-patterning or quadruple-patterning, i.e., a single layer is patterned by using multiple exposure/etch processes.³ However, these more complicated patterning procedures make the contribution of photolithography to the overall cost of integrated circuit fabrication larger.⁴

The next generation lithography, extreme ultraviolet lithography (EUVL), operates at a wavelength of 13.5 nm. The large decrease in wavelength will allow features smaller than 22 nm to be printed using simpler patterning techniques. A sketch of an EUV lithography system is shown in **Figure 1-2**. In such a system, 13.5 nm EUV light is

generated by ionizing droplets of tin with a powerful laser (e.g., CO₂ laser). Due to the high absorption of EUV light by all materials, reflective optics, including the reticle, are used instead of transmissive optics. To achieve high reflectance, multilayer mirrors, composed of molybdenum and silicon layered stacks, using the principle of Bragg reflection, are applied in EUVL systems.^{5, 6} Since the maximum reflectance of such Mo/Si multilayer mirrors is about 70% at 13.5 nm, the number of mirrors in the EUVL system is limited to maximize the light intensity at the wafer. Furthermore, the optical path has to be kept in vacuum conditions to prevent absorption by gases, such as nitrogen or oxygen.⁷ The first EUV lithography systems are currently in operation, and successfully printed IC devices have been reported.⁸

Figure 1-2 Schematic diagram of an EUVL system.

1.2 EUV reticles and reticle defects

In current lithography systems, patterns on the reticle are transferred onto the wafer through the projection optics with a demagnification factor of, typically, 4. Due to the demagnification, this relaxes the constraints on the precision of reticle patterns, e.g., a feature size of 88 nm on the reticle can be used to print 22 nm size features on the wafer. However, the demagnification factor cannot be increased substantially, because larger demagnification requires either a larger

reticle substrate size, or a reduced printing field size (therefore, more reticles are required per chip design). As the critical dimension of the chip devices shrinks, so does the feature size on the reticle, making reticle fabrication more challenging. The fabrication of EUV reticles contains two main processes: EUV reticle blank fabrication, and reticle patterning with an absorber. A fabrication process is indicated in **Figure 1-3**. EUV reticles require a flat and ultra-low thermal expansion material (ULE) as a substrate. On top of the substrate, a multilayer (ML: e.g., Si/Mo) is deposited. The multilayer is protected from oxidation by a capping layer. A backside, conductive coating is applied to allow the reticle to be electrostatically clamped in the EUVL tool. After defect inspection and repair, the reticle blank fabrication is complete. Reticle patterning starts with the deposition of a buffer layer and an absorber layer. The buffer layer protects the ML during absorber etching and/or repair. The absorber patterning is created using e-beam writing and dry etching. The whole reticle is then inspected and repaired if any defects are present. As a last step, the buffer layer is removed from the exposed parts of the ML, and a final inspection and cleaning procedure is applied.

Figure 1-3 EUV reticle fabrication process. Figure is based on reference.⁹

Figure 1-4 Different types of defects in EUV reticles.

EUV reticles are sensitive to defects, both on the surface, as well as in the deposited structures. Reticle defects become printed defects on the wafer, leading to a reduced number of working chips. Defects can be introduced during reticle fabrication, reticle handling, and exposure in EUVL. Mainly, there are five types of defects in EUV reticles: bumps (particles) and pits on the substrate, particles in the ML, defects in absorber patterns, and particles deposited on the reticle during handling or exposure, as shown in **Figure 1-4**. Bumps, particles, or pits at the substrate level, can propagate to the ML through the deposition process. These defects distort the flatness of the ML, leading to a perturbation of the reflected wavefront, i.e. a spatially dependent phase deviation, which degrades the sharpness of the projected image. It is required that there are no particles with a size larger than 50 nm (spherical equivalent).⁷ During ML deposition, particles can be accidentally introduced. Depending on their location, particles near the top of the ML will directly absorb EUV light (amplitude defect), while particles near the bottom of the ML will cause deformation of the ML, resulting in wavefront distortion. Other amplitude or phase defects in the ML are voids, and swelling or compaction of the ML. In principle, for the 22 nm process node, no particles with a size larger than 25 nm (spherical equivalent) should be present in the ML. This requirement is relaxed to 0.003 defect/cm² for the stage of high volume manufacturing.⁷ In the absorber, defects can take the form of missing absorber, or undesired extra absorber, as shown in **Figure 1-4**. Those

defects could be repaired by an advanced focus ion beam (FIB) deposition and milling technique.⁷ The last type of defect is particle contamination on the EUV reticle, which can be introduced during reticle storage, handling, and exposure. In this thesis we will investigate mitigation strategies for particle contamination introduced during exposure in EUVL systems.

1.3 Particle contamination on reticles in EUVL

EUV lithography systems require a clean environment, especially on the reticle, to ensure that the reticle pattern is printed with high fidelity. Although EUVL operates under vacuum conditions ($\sim 10^{-2}$ mbar H_2), contamination with small particles is unavoidable. For example, particles can come from the plasma light source, wearing of mechanical parts, dust introduced during system assembly, manufacture debris, and photoresist. These particles can be picked up by gas flows and transported to other places, e.g., EUV reticles or ML mirrors. Although the EUV reticle is placed facing down to prevent particles depositing on its surface, particles carried by the gas flow can hit the EUV reticle surface, and stick to the surface via van der Waals forces or, if charged, by electrostatic forces. The minimum particle size which will cause defects on the wafer can be calculated from:^{10, 11}

$$s = \frac{1}{2} \cdot \frac{C * M}{E} \quad 1-3$$

where s is the particle size, C is the critical dimension as described in **Eq. 1-1**, M is the demagnification factor of the imaging system ($=4$), E is the mask (reticle) error factor, which indicates the influence of the errors on reticles to the printed patterns on wafers. E is defined as the derivative of the CD at the wafer to that at the reticle (corrected with the corresponding demagnification ratio). It depends on feature size, pattern type (line or contact), exposure parameters, illumination conditions, etc.¹² Typical values are usually calculated and fall within the range: 1.5-3.5.^{10, 11} Thus, for example, the minimum particle size

that will cause defects on the wafer for the 22 nm process node can be calculated by **Eq. 1-3** to be approximately 25 nm.

The three key aspects of a particle contamination control strategy are prevention, detection, and cleaning. The current strategy to mitigate particle contamination in an EUV system is to design, build, and maintain a clean system.¹³ However, the number of particles that are allowed to be present on the reticle during exposure is rapidly reducing to improve system productivity, therefore, new developments are required. As EUV lithography comes closer to volume manufacturing, it becomes increasingly important to control particle contamination, and, particularly, maintain a particle-free reticle in the lithography system.

In current, immersion-based lithography systems, DUV (deep ultraviolet) pellicles are used to protect reticles from particle contamination (**Figure 1-5**).¹⁴ A pellicle is placed beyond the depth of focus (**Eq. 1.2**) — typically, a distance of a few millimeters away from the reticle. Although particles with size larger than 5 μm will not be imaged sharply², they will, instead, reduce the light intensity at the wafer due to shadowing, and create strong diffraction fringes, which will distort the image at wafer.¹¹ However, these relatively large particles can be quickly and reliably detected by optical inspection techniques based on light scattering. For EUVL systems, in contrast, although being investigated, there were no pellicles available when this PhD project started.^{13, 15} Therefore, particles are able to deposit onto the reticle, where they will be imaged sharply on the wafer since they are in the object plane (**Figure 1-5**).

Figure 1-5 Particle contamination of (a) DUV reticle and (b) EUV reticle. The dashed lines indicate a EUV pellicle was not ready when this PhD project started.

Reticle handling and storage techniques have been introduced to reduce particle contamination to acceptable levels.¹⁶ However, during exposure, particle contamination is still a significant problem. Inside the lithography system, although the reticle is in a vacuum environment, particles are still able to deposit onto the reticle due to the lack of a protective pellicle. Therefore, an inspection, cleaning and protection strategy is required to control particle contamination on the reticle. Here, in this thesis, inspection and protection will be discussed.

1.4 Inspection of particle contamination

Currently, there are three main reticle inspection techniques: light scattering techniques (dark field or bright field imaging) using 193 nm light sources, electron beam based inspection, and at wavelength (13.5 nm) actinic inspection. These tools, either commercially available or under development, still need to improve their sensitivity, throughput, and/or cost to be integrated as *in situ* inspection in EUVL. The primary requirements for *in situ* inspection of EUV reticles are detection of 25 nm or larger particles for the 22 nm node within 1 hr with an inspection area of 132 x 132 mm². Commercial tools, e.g. the Surfscan from KLA tencor, or the UVision from Applied Materials, are used to inspect reticles before they are patterned. These tools are based on laser scatterometry. As illustrated in **Figure 1-6**, light

illuminates the surface from a certain angle. The surface will reflect the light specularly, while particles will scatter the light over a range of angles, determined by the shape and composition of the particle. Commercial tools, based on light scattering techniques, such as dark field imaging, are capable of very fast and high resolution measurements, e.g., the KLA SP3 can scan a standard 300 mm wafer in a few minutes with a sensitivity of 26 nm. However, laser scatterometry cannot be used to find particles on the patterned surfaces of the EUV reticle, since the scattering due to particles cannot be distinguished from the scattering due to the pattern. For patterned surfaces, a different method is used. The surface is imaged at very high resolution (i.e., sub-100 nm pixels using 193 nm deep UV light) and the image is compared to the image of a nominally identical location elsewhere on the wafer/reticle (die-to-die analysis) or to a calculated (or reference) image (die-to-database). In this way, it is possible to detect and distinguish defects due to a particle on the reticle. This method is very effective but typically very slow (it takes a few hours for inspection of a whole reticle) compared to laser scatterometry.¹¹

The main challenge for fast, *in situ* EUV reticle inspection is the detection of particles on a patterned surface with the same efficiency and speed of laser scatterometry. The difficulty lies in the fact that a particle on a reticle, from the scattering point of view, will look exactly like a pattern feature. However, if the pattern is periodic (i.e., memory banks), scattering from these periodic patterns is predictable (diffraction patterns), while the scattering from a particle with an unknown shape is not predictable. Simple periodic structures, as shown in **Figure 1-6**, will produce diffraction orders that have equal angular spacing (purple dashed lines). The diffracted light from the pattern is collimated by a lens. The light from the periodic structures will be reimaged at the focal plane of the lens. By placing beam stops at the locations of the dots (called a Fourier filter), these diffraction orders are blocked. The particle diffracts light over a continuum of angles, so much of the spatial information from the particle is transmitted by the filter. Therefore, the scattered light from the reticle patterns can be filtered out, leaving only the scattered light from the particle. This can be easily realized by an extension of current laser scatterometry. **Figure 1-6** shows a schematic

of this technique. It has been shown that particles as small as 50 nm can be detected in patterned areas, even in case of particles located on top of a feature.¹¹ However, such an approach fails in presence of non-periodic patterns (i.e., periphery of memory chips).

Figure 1-6 Schematic diagram of an inspection technique, based on laser scatterometry. (a) Inspection of particles on a reticle blank; (b) Inspection of particles on a reticle with periodic structures. The optics are designed to collect certain diffraction orders from periodic structures and later filter them out, leaving only the light scattered from the particle.

Other inspection techniques like electron beam based inspection are still under development. A normal SEM cannot provide sufficient throughput to inspect 25 nm particles on a full EUV reticle (~100 mm x 100 mm). A novel electron beam inspection system was developed by Toshiba and Ebara Corporation to achieve the requirements for high sensitivity, high throughput, and relatively low cost. In their system, as shown in **Figure 1-7**, they combine projection electron beam microscopy, a time delayed and integrated (TDI) sensor to acquire images while scanning the reticle, and a parallel image processing unit to do real-time inspection. A more detailed description can be found in ref.¹⁷ The large field of view, compared to a normal SEM, allows high throughput scanning of reticles.¹⁷⁻¹⁹ In 2011, they have demonstrated that 30 nm polystyrene latex sphere (PSL) particles on 88 nm Line/Space patterns can be detected. Later on in 2012, they demonstrated the detection of 20 nm PSL particles on a full size reticle

Chapter 1

blank within 1 hr at 100% capture rate.¹⁹ Progress has been focused on reticle pattern (absorber) inspection, and inspection of particle contamination on patterned reticle is still under research and development. However, the sensitivity of this technique depends on the secondary electron emission from the contaminant particles. Therefore, detection of other type of particles, e.g., metals, and metal oxides, needs to be investigated. Besides, due to its size and system complexity, it is not possible to integrate this technique inside the EUVL system for *in situ* inspection. Although transfer of the reticle from the EUVL system to the e-beam inspection system can be arranged via vacuum, there is still a risk of adding particles to the reticle during handling after a reticle has been inspected. Another concern is that, compared with visible light inspection, carbon contamination is induced by electron beam irradiation, which will reduce EUV reflectivity.^{20, 21}

Figure 1-7 Schematic view of the EBEYE (EBEYE = name of the tool) inspection system. Figure is based on reference¹⁹.

Actinic inspection is yet another promising technique for EUV reticle inspection. This technique detects the reflected EUV light or the photoelectron/photon emission from the contaminant particles induced by the EUV irradiation. Until today, there is still debate on whether “actinic only” defects exist on EUV reticles, i.e., defects that only

appear under illumination of EUV light. The advantage of this technique is that it is able to detect defects buried inside multilayers or absorbers, and bumps or pits in a reticle, as shown in **Figure 1-4**. These defects are very difficult or even not possible to detect by optical scattering techniques or e-beam based inspection, while defects buried in the multilayer will deteriorate the reflection of EUV, thus, the defect can be detected. In 2010, when this PhD project started, actinic inspection was the subject of intense research activity. For example, an EUV Schwarzschild microscope developed at the University of Hyogo in Japan, synchrotron-based high-magnification EUV zoneplate imaging in Lawrence Berkeley National Lab in the US, and EUV AIMS™ at Carl Zeiss in Germany.²² However, these activities mainly focus on reticle blank inspection and aerial image microscopy (a technique used to predict a mask or reticle's imaging performance in a lithography system without printing into photoresist). Carl Zeiss has demonstrated that their latest AIMS™ EUV system is able to inspect EUV reticles for the 16 nm process node and announced that they expect to deliver their first system to a customer in 2015.²³ For particle and pattern inspection on EUV reticles, little study has been conducted. Furthermore, one of the remaining bottle necks is developing an EUV light source with sufficient brightness (Radiance: more than $1000 \text{ W}/(\text{sr}\cdot\text{mm}^2)$).²⁴ Similarly to SEM inspection it is difficult to integrate this technique with an EUVL system. Therefore, this inspection method might add particles because of handling the reticles outside of the EUVL system. Finally, the cost of such an inspection method is high.

1.5 EUV Pellicle: prevention of particle contamination

The EUV reticle can be protected from particle contamination by placing it behind a pellicle. The pellicle should be resistant to EUV induced chemical reactions, highly transparent to EUV, and mechanically robust. An EUV pellicle has to meet practical requirements: light transmission above 90%, sufficient robustness to

Figure 1-8 EUV (13.5 nm) transmission of a Si membrane as function of thickness. The dashed line indicates the minimum transmission requirement for an EUV pellicle. The transmission value is calculated using the online tool from CXRO.²⁵

withstand an acceleration of 100 m/s^2 , a pumping speed of 3.5 mbar/s , and a heat load of 2.5 W/cm^2 (single pass, equivalent of 250 W/cm^2 source power). Current DUV pellicles, based on organic membranes, are not suitable for EUVL, due to their high absorption of EUV light. Si was chosen as EUV pellicle material due to its low absorption of EUV and existing manufacturing techniques. However, in order to meet the transmission requirement, an EUV pellicle based on Si needs to be thin. **Figure 1-8** shows the theoretical EUV transmission of a Si based pellicle depending on thickness. This figure indicates that to achieve 90% transmission, the Si membrane has to be thinner than 60 nm. Such an extremely thin membrane will lack the mechanical strength and thermal conductivity required for a pellicle. Several investigations have reported that this type of pellicle suffers from imaging performance degradation, manufacturing issues, and rupturing due to repeated rapid thermal expansion and contraction.¹⁵ Recent advances in poly-silicon based thin membrane technology led to renewed research activities on EUV pellicles. ASML has demonstrated a full-size ($106 \times 139 \text{ mm}^2$) poly-silicon pellicle with an EUV transmission of 84% (thickness: 57 nm including two capping layers). However, the EUV transmission ($>90\%$), thermal shock resistivity, and mechanical strength require further improvement before the poly-silicon pellicle meets the

requirements for industrial application. Therefore, alternative material for the pellicle such as graphene is investigated in this study.

1.6 Outline of this thesis

Particle contamination mitigation on reticles is of critical importance for high volume manufacturing with EUVL. In this thesis we have explored two strategies, inspection and protection of EUV reticles, to achieve particle mitigation.

We propose a comparison-free and *in situ* inspection method, using the intrinsic photoluminescence from contaminant particles to detect their presence on the reticle. An advantage of this inspection method is that it is possible to identify the type of contaminant particles from their photoluminescence spectrum, thus allowing an appropriate cleaning mechanism to be chosen. Furthermore, photoluminescence based inspection can detect particles on patterned areas of an EUV reticle. Our inspection system also has the potential to be integrated to the lithography system so that it avoids the loading-unloading cycle (thereby avoiding additional particle contamination due to additional handling) of the EUV reticle. In Chapter 2, we discuss the fundamentals of photoluminescence and the principle of photoluminescence.

To determine the feasibility of photoluminescence-based inspection as a detection method for particle contamination on EUV reticles, we have conducted experiments and present the results in Chapter 4. We have analyzed the photoluminescence spectrum from different particles found in EUV lithographic systems and determined the minimum detectable particle size. We have shown that our apparatus has the potential to be integrated into EUV lithography systems, allowing *in situ* inspection.

In the second part of this thesis, we have investigated graphene as a candidate material for an EUV pellicle to protect reticles from particle contamination.²⁶⁻³³ A single layer of graphene has a theoretical transmission of 99.8% at 13.5 nm.²⁵ It was reported as one of the

strongest materials, with a Young's modulus of 1 TPa, and a tensile strength of 130 GPa.³² The thermal conductivity of graphene was reported to be approximately 5×10^3 W/m K.³⁴ The high thermal conductivity and ultra-low interfacial thermal resistance between graphene and metals could be an important advantage in thermal management.³⁵ Despite the promising properties of graphene, its chemical inertness under EUV exposure conditions is not yet fully understood. It is of critical importance to understand the chemical stability of graphene during EUV exposure, particularly for reticle lifetime considerations. In Chapter 3, a general introduction to graphene is given. Raman spectroscopy, a common technique for characterizing graphene is discussed as well. In chapter 5, 6, and 7, an investigation of the chemical stability of graphene under EUV irradiation is presented. Preliminary experimental results on multi-layer graphene under EUV irradiation are presented in Chapter 5. These results show that defects can be created in graphene during EUV irradiation. A series of controlled experiments on single layer graphene that determine the sources of defect formation in graphene during EUV irradiation: EUV photons, EUV induced plasma, and EUV induced photoelectrons, are presented in Chapter 6 and Chapter 7.

Valorization aspects of this work are discussed in Chapter 8, followed by conclusions in Chapter 9.

1.7 References

1. D. Attwood, *"Soft x-rays and extreme ultraviolet radiation: principles and applications"*. (Cambridge University Press, 1999).
2. C. G. Soon, *"Optical resolution enhancement techniques and applications in optical lithography"*, (PhD Thesis, 2007).
3. B. Wu and A. Kumar, *"Extreme ultraviolet lithography: a review"*, Journal of Vacuum Science & Technology B **25** (6), 1743-1761 (2007).
4. P. Zimmerman, *"Double patterning lithography: double the trouble or double the fun?"*, SPIE Newsroom **20** (2009).
5. E. Spiller, *"Soft X-ray optics"*. (SPIE Optical Engineering Press Bellingham, WA, 1994).

6. E. Louis, A. Yakshin, T. Tsarfati and F. Bijkerk, "*Nanometer interface and materials control for multilayer EUV-optical applications*", Progress in Surface Science **86** (11), 255-294 (2011).
7. V. Bakshi, "*EUV lithography*". (SPIE Press Bellingham, 2009).
8. I. Mori, O. Suga, H. Tanaka, I. Nishiyama, T. Terasawa, H. Shigemura, T. Taguchi, T. Tanaka and T. Itani, "*Selete's EUV program: progress and challenges*", SPIE Advanced Lithography, (2008).
9. H.-K. Cho and J. Ahn, "*EUV mask and mask metrology*", EUV lithography **178**, 325 (2009).
10. L. Scaccabarozzi, N. A. Lammers, R. Moors and V. Banine, "*Particle cleaning of EUV reticles*", Journal of Adhesion Science and Technology **23** (12), 1603-1622 (2009).
11. L. Scaccabarozzi, N. A. Lammers, R. Moors and V. Banine, "*Cleaning and inspection of EUV reticles: specifications and prospects*", 11th international symposium on particles on surfaces, (2008).
12. H.-Y. Kang, S.-H. Kim, C.-H. Lee and H.-K. Oh, "*Mask error enhancement factor variation with pattern density*", Photomask Technology, (2005).
13. C. Zoldesi, K. Bal, B. Blum, G. Bock, D. Brouns, F. Dhalluin, N. Dziomkina, J. D. A. Espinoza, J. de Hoogh and S. Houweling, "*Progress on EUV pellicle development*", SPIE Advanced Lithography, (2014).
14. Y. A. Shroff, M. Goldstein, B. Rice, S. H. Lee, K. Ravi and D. Tanzil, "*EUV pellicle development for mask defect control*", SPIE 31st International Symposium on Advanced Lithography, (2006).
15. L. Scaccabarozzi, D. Smith, P. R. Diago, E. Casimiri, N. Dziomkina and H. Meijer, "*Investigation of EUV pellicle feasibility*", SPIE Advanced Lithography, (2013).
16. M. Amemiya, K. Ota, T. Taguchi, T. Kamono, Y. Usui, T. Takikawa and O. Suga, "*Particle-free mask handling techniques and a dual-pod carrier*", SPIE Advanced Lithography, (2008).
17. S. Yamaguchi, M. Naka, T. Hirano, M. Itoh, M. Kadowaki, T. Koike, Y. Yamazaki, K. Terao, M. Hatakeyama and K. Watanabe, "*Performance of EBeyeM for EUV mask inspection*", SPIE Photomask Technology, (2011).
18. T. Hirano, S. Yamaguchi, M. Naka, M. Itoh, M. Kadowaki, T. Koike, Y. Yamazaki, K. Terao, M. Hatakeyama and H. Sobukawa, "*Development of EB inspection system EBeyeM for EUV mask*", SPIE Photomask Technology, (2010).
19. M. Naka, S. Yamaguchi, M. Kadowaki, T. Koike, T. Hirano, M. Itoh, Y. Yamazaki, K. Terao, M. Hatakeyama and K. Watanabe, "*Capability of model EBeye M for EUV mask production*", SPIE Photomask Technology, (2012).

Chapter 1

---

20. R. L. Stewart, "*Insulating films formed under electron and ion bombardment*", *Physical Review* **45** (7), 488 (1934).
21. J. Chen, E. Louis, H. Wormeester, R. Harmsen, R. van de Kruijs, C. J. Lee, W. van Schaik and F. Bijkerk, "*Carbon-induced extreme ultraviolet reflectance loss characterized using visible-light ellipsometry*", *Measurement Science and Technology* **22** (10), 105705 (2011).
22. K. Goldberg and I. Mochi, "*Wavelength-specific reflections: A decade of extreme ultraviolet actinic mask inspection research*", *Journal of Vacuum Science & Technology B* **28** (6), C6E1-C6E10 (2010).
23. M. R. Weiss, D. Hellweg, J. H. Peters, S. Perlitz, A. Garetto and M. Goldstein, "*Actinic review of EUV masks: first results from the AIMS EUV system integration*", *SPIE Advanced Lithography*, (2014).
24. P. Choi, S. V. Zakharov, R. Aliaga-Rossel, A. Bakouboula, J. Bastide, O. Benali, P. Bove, M. Cau, G. Duffy and W. Kezzar, "*High brightness EUV light sources for actinic metrology*", *SPIE Advanced Lithography*, (2010).
25. http://henke.lbl.gov/optical_constants/filter2.html.
26. A. K. Geim and K. S. Novoselov, "*The rise of graphene*", *Nature materials* **6** (3), 183-191 (2007).
27. A. K. Geim, "*Graphene: status and prospects*", *Science* **324** (5934), 1530-1534 (2009).
28. K. S. Novoselov, D. Jiang, F. Schedin, T. J. Booth, V. V. Khotkevich, S. V. Morozov and A. K. Geim, "*Two-dimensional atomic crystals*", *Proceedings of the National Academy of Sciences of the United States of America* **102** (30), 10451 (2005).
29. Y. Zhang, Y.-W. Tan, H. L. Stormer and P. Kim, "*Experimental observation of the quantum Hall effect and Berry's phase in graphene*", *Nature* **438** (7065), 201-204 (2005).
30. M. Y. Han, B. Özyilmaz, Y. Zhang and P. Kim, "*Energy band-gap engineering of graphene nanoribbons*", *Physical Review Letters* **98** (20), 206805 (2007).
31. K. I. Bolotin, K. J. Sikes, Z. Jiang, M. Klima, G. Fudenberg, J. Hone, P. Kim and H. L. Stormer, "*Ultrahigh electron mobility in suspended graphene*", *Solid State Communications* **146** (9), 351-355 (2008).
32. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", *Science* **321** (5887), 385-388 (2008).
33. J. S. Bunch, A. M. Van Der Zande, S. S. Verbridge, I. W. Frank, D. M. Tanenbaum, J. M. Parpia, H. G. Craighead and P. L. McEuen, "*Electromechanical resonators from graphene sheets*", *Science* **315** (5811), 490-493 (2007).

34. A. A. Balandin, S. Ghosh, W. Bao, I. Calizo, D. Teweldebrhan, F. Miao and C. N. Lau, "*Superior thermal conductivity of single-layer graphene*", Nano Letters **8** (3), 902-907 (2008).
35. Q. Liang, X. Yao, W. Wang, Y. Liu and C. P. Wong, "*A three-dimensional vertically aligned functionalized multilayer graphene architecture: an approach for graphene-based thermal interfacial materials*", ACS nano **5** (3), 2392-2401 (2011).

Chapter 2 Photoluminescence

2.1 Introduction

Photoluminescence is a light emission process from any substance when electronically excited after the absorption of light. Depending on the nature of the excited states and the emission pathway, it is formally divided into two categories: fluorescence and phosphorescence.

The fluorescence phenomenon was first observed from a quinine solution in sunlight by Sir John Frederick William Herschel in 1845.¹ Later on, in 1852, Sir George G. Stokes observed that fluorescence typically occurs at longer wavelength compared with the excitation light.² The difference between the absorption wavelength and emission wavelength is, therefore, named the Stokes shift. In his experiments, Stokes used ultraviolet light, filtered from sunlight by a blue window glass. This glass filter selectively transmitted light under 400 nm, which was absorbed by the quinine solution. The incident light was removed by a yellow glass of wine (filter). The emission from a quinine solution is near 450 nm, therefore, it is easily observed by the human eye. Quinine was used to develop spectrofluorometers to monitor antimalarial drugs around 1950s.³ This resulted in a subsequent program at the National Institutes of Health to develop the first practical spectrofluorometer.³ Fluorescence is also used for high sensitivity detection. In 1877, fluorescein was used to demonstrate that the River Danube and Rhine were connected by underground streams. Fluorescein was first put into River Danube, after six hours, its characteristic green fluorescence appeared in a small river that led to River Rhine.⁴ Today, fluorescein is still an important emergency marker for locating people at

sea. Another important application of fluorescence is the fluorescence microscope invented in 1910s by German scientists Otto Heimstadt and Heinrich Lehmann.⁵ The fluorescence microscope is widely used in cell biology to increase the contrast of bacteria, as well as animal, and plant tissues.

The fluorescence process includes sub-processes: light absorption, relaxation, and light emission, as illustrated by the Jablonski diagram in **Figure 2-1**.⁶ The electronic energy state of a molecule determines the distribution of electrons and the molecular geometry. Several different electronic states can exist, illustrated in **Figure 2-1** as S_0 (ground state), S_1 (first excited state), and S_2 (second excited state). Each of the electronic energy states is further subdivided into a number of vibrational and rotational energy levels. The ground state is usually a singlet state, where the electrons are spin-paired with anti-parallel spin orientation, thus, the total spin angular momentum is zero. At room temperature, molecules usually exist at the electronic ground state, and thus, the light excitation process originates from the ground state.

When electrons undergo a transition from one energy state to another, they have to fulfill both conservation of energy and momentum. Since photons carry an intrinsic angular momentum corresponding to $s=\pm 1$, the change of electron momentum must compensate for the angular momentum carried by the photon. Therefore, some transitions are allowed, whereas other transitions are forbidden. A selection rule determines which transitions are allowed. They are defined to identify the transitions that conserve the angular momentum when a photon is absorbed or emitted.

In quantum mechanics, the energy levels of a molecule can only be certain quantized values. Therefore, absorption of light to promote an electron from the ground state to an excited state occurs in discrete amounts of energy (photon energy). Absorption of photons can happen at any photon energy, but the probability of absorbing a photon is strongly maximized when the energy of the photon matches the energy difference between energetic states. In this thesis we will only discuss

Photoluminescence

fluorescence processes associated with electronic transitions within the ultraviolet to visible light wavelength range.

In **Figure 2-1**, there are two absorption transitions: the left-hand purple vertical arrow indicates a transition from the ground state to the third vibrational state of the S_2 (second excited state manifold); the right-hand purple vertical arrow describes another transition where the electrons are promoted from the ground state to the third vibrational state of the S_1 manifold.

Figure 2-1 Jablonski energy level diagram. The thicker horizontal black lines represent electronic energy levels, while the thinner lines denote the various vibrational energy states. Transitions between the states are illustrated as straight or wavy arrows, depending on whether the transition is associated with absorption or emission of a photon (straight arrow) or results from a molecular internal conversion, vibrational relaxation, or intersystem crossing (wavy arrows). Figure is based on reference.⁷

After the electron is promoted to a certain excited state, several processes will occur. The electron may return to lower vibrational energy levels within the manifold by vibrational relaxation. If vibrational energy levels strongly overlap with electronic energy levels (S_1 and S_2 manifold in **Figure 2-1**), a possibility exists that the excited electron can make a transition from a vibration level in one electronic state to another vibration level in a lower electronic state (pink arrow). This process is called internal conversion. The

electrons may also return to the ground state by emitting a photon. This process is known as fluorescence. The electrons can also return to a higher vibrational level of the ground state, from which it will return to a rotational or vibrational state that returns the atom to thermal equilibrium state with the bath.

The excited electron can also return to the excited triplet state (a state which contains electrons with parallel spin orientation, thus, the total spin is 1 instead of 0 in a singlet state) via an intersystem crossing. These electrons in the triplet state will be further relaxed to the ground state by emitting a photon (phosphorescence). Meanwhile, non-radiative decay of the excited electron can also occur from the triplet state. Transitions from the triplet excited state to the singlet ground state are “forbidden” in classical physics. However, in quantum mechanics, these transitions will still rarely occur, which leads to a long lifetime of the phosphorescence. One of the main differences between fluorescence and phosphorescence is that the electron relaxes from different excited energy states. In fluorescence, the excited state is a singlet state, where the electrons are paired so that the net spin is zero. Therefore, the transition to the ground state is spin allowed, and the emission rate is typically 10^8 s^{-1} . In contrast, phosphorescence is emission of light from a triplet excited state, where the electrons are unpaired so that the spin orientation is parallel and the net spin is 1. Therefore, transitions from the triplet state to the ground state are forbidden, which means the transition cannot proceed through the most efficient way (dipole moment). However, there is still a certain possibility that transitions occur, but at a relatively low rate, which is typically at 10^3 - 10 s^{-1} .

Other relaxation pathways exist to compete with the fluorescence or phosphorescence emission processes. The electrons in excited states can be relaxed through non-radiative pathways, i.e., dissipate the energy as heat, quenching, or by transferring energy to a nearby molecule via a collision.

Figure 2-2 shows the absorption and emission spectra for several different electronic transitions. The blue curve is the absorption spectrum, and the dashed dark blue arrows indicate the electronic

Photoluminescence

transitions from ground state to different vibrational energy levels of the excited state. In solids, the absorption spectrum is typically broadened due to factors like the closely spaced vibrational energy levels, defects, and the presence of isotopes, which allows a range of photon energies to match the electron transition. An excitation spectrum is generally obtained by scanning a range of wavelengths while recording the emission intensity at certain single wavelength. Likewise, exciting a fluorophore at a single wavelength while measuring the emission intensity over a range of wavelengths will result in an emission spectrum. The various transitions have different probabilities.

Figure 2-2 A schematic of absorption and emission spectra. Figure is based on reference.⁷

According to the Franck-Condon Principle, as shown in **Figure 2-3**, an electronic transition between two states will be more likely to occur if the wave functions of these two energy states have a more significant spatial overlap.^{8, 9} One may notice that the absorption and emission spectra shown in **Figure 2-2** are mirror images with respect to each other. The reason is that the probability of an electronic transition between ground state and a particular vibrational energy level (0 to 1 in **Figure 2-3**) is similar to the probability of the reciprocal transition.

Figure 2-3 Franck-Condon principle energy diagram. Different level vibrational state is shown with $v = 0, 1, 2, 3$. The yellow area indicates the vibrational energy distribution probability. The figure shows that the favoring transition is between $v = 0$ and $v = 1$. Figure is based on reference.⁷

Figure 2-4 Absorption and emission spectra which do not obey the mirror image rule due to vibrational relaxation. Figure is based on reference.⁷

Photoluminescence

In many cases, electrons are promoted to the higher excited electronic states due to absorption of high energy photons. These electrons will quickly return to the lowest vibrational energy level of the excited states by vibrational relaxation. Therefore, due to this rapid relaxation process, the emission spectrum is generally independent of the excitation wavelength. As a result, the emission spectrum is only a mirror image of the ground state to the lowest excited state transitions, but not the entire absorption spectrum, as shown in **Figure 2-4**.

The quantum yield and lifetime in photoluminescence are very important characteristics. The quantum yield is defined as the ratio between the number of photons emitted and the number absorbed. The emission rate, Γ , and the non-radiative decay rate, κ , will both depopulate the excited state. The fraction that relax through emission, and hence the quantum yield is given by:

$$Q = \frac{\Gamma}{\Gamma + K} \quad 2-1$$

Due to the existence of the non-radiative relaxation process, the quantum yield is less than one.

The lifetime of the excited state is defined as the period of time, τ , over which the state population reduces from N to N/e (Euler's number). This indicates that few molecules will emit their photons at precisely $t = \tau$. For a single exponential relaxation, 63% of the molecules relax before $t = \tau$ and 37% relax at $t > \tau$. The lifetime is given by:

$$\tau = \frac{1}{\Gamma + K} \quad 2-2$$

2.2 Color centers

Figure 2-5 Schematic diagram of the ionic configuration of different types of color centers. Upper row from left to right: F center, F_2 center, and F_2^+ center. Lower row from left to right: $F_A(II)$ center, $F_B(II)$ center, $F_A(II)^+$ center.

The word color center is originally from German *Farbzentrum*, therefore, it is also called an F-center. A color center is a type of crystallographic defect, in which an anion vacancy in a crystal is filled by one or more electrons. Such centers occur naturally in many crystal and glass materials, as can be seen in the study of alkali-halide crystals. Color centers in alkali-halide crystals have been intensively investigated because the crystals can be used as the gain material for laser systems.¹⁰⁻¹² **Figure 2-5** shows different color centers in a potassium chloride crystal. The basic color center, F-center, is shown on the upper left corner. Two F-centers next to each other will form an F_2 center, and if such a color center is singly ionized, e.g., losing one electron, it becomes an F_2^+ center, while if an F_2 center captures another electron, it forms an F_2^- center. Replacing a K^+ ion with foreign metal atom (like a Li atom in **Figure 2-5**) will enhance the stability of the F_2^+ center. On the lower row of **Figure 2-5**, three different types of colors are shown. An $F_A(II)$ center is formed when one of the nearest K^+ ions is replaced by a Li^+ ion. Similarly, if two of the nearest K^+ ions are replaced by Li^+ ions, such centers becomes a $F_B(II)$ center. If one of the K^+ ions is replaced by a Li^+ ion in an F_2^+ center, it transforms to an $(F_2^+)_A$ center. It should be noted that more of these F centers can aggregate to form F_3 , F_4 centers...etc, and such centers can be further positively or negatively

charged. One of most important applications of color centers is to develop color center based laser systems.^{11, 12}

The optical properties such as light absorption-emission of color centers strongly depend on the type and characteristic parameters of the crystalline lattice in which they are produced. For example, when Al_2O_3 is irradiated with γ rays or electrons, there are color centers generated with different absorption bands. Two absorption lines at 680 nm and 840 nm were reported with an absorption cross section of 5.7×10^{-18} and $1.3 \times 10^{-17} \text{ cm}^2$, respectively.¹³ These two absorption lines result in a broad band emission spectrum with peaks at 830 nm (FWHM = 1870 cm^{-1}) and 990 nm (FWHM = 1340 cm^{-1}).¹² Emission from Mg-doped Al_2O_3 was observed as well. The absorption at 440 nm leads to a wide spectrum from 500 to 590 nm with a peak at around 520 nm.^{11, 12} Particles in EUV system have been exposed to various conditions such as EUV radiation, and EUV induced hydrogen and water plasma. Their photoluminescence properties will be discussed in the following.

2.3 Photoluminescence from particles in EUVL

The majority of contaminant particles on EUV reticles are stainless steel, aluminum, and organics (hydrocarbons). The different compounds have different potential sources of photoluminescence. Hydrocarbons are usually effective emitters under UV irradiation due to their complex electronic structures. Photoluminescence from metal particles is expected to be due to color centers in the oxidized outer shell, which are introduced during oxidation in the presence of the residual water in the EUV lithography system. The stainless steel particles in this study mainly contain Fe, Cr and Ni. Cr naturally forms a passivation layer of oxide, which prevents surface corrosion. Among the ionization states of Cr, Cr^{3+} has a well-known sharp emission line at 694 nm in a metal matrix composite.¹⁴ NiO has also been reported to have emission lines at 312 nm and 400 nm under UV excitation.¹⁵ For Al particles, it is also

expected that the majority of the photoluminescence will originate from their oxide shell. Wide band emission in the visible range has been reported in various studies of Al_2O_3 thin films.¹⁶⁻²⁰ However, these color centers in an oxide layer are not well understood, for example, the excitation spectrum and quantum yield is difficult to predict due to the complex structure and composition of those particles. These issues will be discussed in this thesis (Chapter 4).

2.4 References

1. J. F. W. Herschel, "*Ἀμφοφῶτα No. I. On a Case of Superficial Colour Presented by a Homogeneous Liquid Internally Colourless*", Philosophical Transactions of the Royal Society of London, 143-145 (1845).
2. G. G. Stokes, "*On the change of refrangibility of light*", Philosophical Transactions of the Royal Society of London, 463-562 (1852).
3. S. Udenfriend, "*Development of the spectrophotofluorometer and its commercialization*", Protein Science **4** (3), 542-551 (1995).
4. I. Berlman, "*Handbook of fluorescence spectra of aromatic molecules*", 2nd ed. (Elsevier, 2012).
5. F. W. Rost, "*Fluorescence microscopy*". (Cambridge University Press, 1992).
6. J. R. Lakowicz, "*Principles of fluorescence spectroscopy*", 3rd ed. (Springer Science & Business Media, 2013).
7. <http://www.olympusconfocal.com/theory/fluoroexciteemit.html>.
8. J. Franck and E. Dymond, "*Elementary processes of photochemical reactions*", Transactions of the Faraday Society **21** (February), 536-542 (1926).
9. E. Condon, "*A theory of intensity distribution in band systems*", Physical Review **28** (6), 1182 (1926).
10. W. Gellermann, "*Color center lasers*", Journal of Physics and Chemistry of Solids **52** (1), 249-297 (1991).
11. T. T. Basiev, S. B. Mirov and V. V. Osiko, "*Room-temperature color center lasers*", IEEE journal of quantum electronics **24**, 1052-1069 (1988).
12. V. V. Ter-Mikirtychev and T. Tsuboi, "*Stable room-temperature tunable color center lasers and passive Q-switchers*", Progress in quantum electronics **20** (3), 219-268 (1996).

13. E. Martynovich, A. Tokarev and V. Grigorov, "*Al₂O₃ color center lasing in near infrared at 300 K*", Optics communications **53** (4), 254-256 (1985).
14. T. H. Maiman, R. Hoskins, I. d'Haenens, C. Asawa and V. Evtuhov, "*Stimulated optical emission in fluorescent solids. II. Spectroscopy and stimulated emission in ruby*", Physical Review **123** (4), 1151 (1961).
15. Y. Wang, C. Ma, X. Sun and H. Li, "*Preparation and photoluminescence properties of organic–inorganic nanocomposite with a mesolamellar nickel oxide*", Microporous and Mesoporous Materials **71** (1), 99-102 (2004).
16. D. Liu, S. Clark and J. Robertson, "*Oxygen vacancy levels and electron transport in Al₂O₃*", Applied physics letters. **96** (3), 032905 (2010).
17. J. Carrasco Rodríguez, J. R. Gomes and F. Illas i Riera, "*Theoretical study of bulk and surface oxygen and aluminium vacancies in α -Al₂O₃*", Physical Review B **69** (6), 064116 (2004).
18. L. Brock, K. Mishra, M. Raukas, W. P. Lapatovich and G. C. Wei, "*Color centers in magnesium doped polycrystalline alumina*", MRS Proceedings, (2001).
19. T. Perevalov, O. Tereshenko, V. Gritsenko, V. Pustovarov, A. Yelisseyev, C. Park, J. H. Han and C. Lee, "*Oxygen deficiency defects in amorphous Al₂O₃*", Journal of Applied Physics **108** (1), 013501 (2010).
20. B. D. Evans and M. Stapelbroek, "*Optical properties of the F⁺ center in crystalline Al₂O₃*", Physical Review B **18** (12), 7089 (1978).

Chapter 3 Graphene

3.1 Introduction

Graphene is a two-dimensional hexagonal packed sheet of carbon atoms. The unit cell of graphene contains two carbon atoms and the graphene lattice can be viewed as formed by two sub-lattices, as shown in **Figure 3-1**. Graphene is the basic building block for forming different forms of graphitic materials, such as stacking into graphite, rolling into carbon nanotubes or wrapping into fullerenes. Graphene has attracted a lot of attention from different research fields due to its unique physical and chemical properties, such as quantum electronic transport, a tunable band gap, extremely high mobility, high elasticity, and electromechanical modulation.¹⁻⁸ Besides these remarkable properties, graphene has thermal and mechanical properties that make it a very promising material for a pellicle and other membrane-based applications. Graphene can act as a diffusion barrier by providing physical separation between an underlying substrate and reactant gases. Indeed, studies show that graphene is highly impermeable to gases.⁹ Furthermore, single-layer graphene is also highly transparent, which makes it a promising protection layer for optical devices, such as mirrors, lenses and screens.¹⁰ Additionally, graphene can be grown on large scales by chemical vapor deposition (CVD) and can be transferred to various kinds of substrate, making the range of potential applications very wide.¹¹

Figure 3-1 Graphene sp^2 network. The blue and red atoms indicate the two sub-lattices in the unit cell (black lines). Figure is based on reference.¹²

3.2 Graphene synthesis

Graphene can be synthesized by several techniques, including mechanical exfoliation, chemical vapor deposition, and epitaxial growth. In the following, we will summarize these three synthesis methods, and discuss their advantage and disadvantages. Other synthesis methods such as chemical exfoliation and unzipping nanotubes are discussed in the review article by Liu *et al.*¹³

Graphene flakes were first prepared by mechanical exfoliation from graphite by Novoselov *et al.* in 2004.³ A fresh piece of Scotch tape is pressed firmly with the adhesive-side down to the shiny side of a piece of highly ordered pyrolytic graphite (HOPG). The tape is then gently peeled away with thick, shiny layers of graphite stuck to it. The part of the tape with layers from the HOPG is refolded upon a clean adhesive section of the same piece of tape; the two layers are then pressed firmly together for several seconds. Subsequently, the tape is gently unfolded so that two mirrored graphite areas on the tape remain. This process is repeated several times with the original area removed from the HOPG on the tape until a large portion is no longer shiny. When this stage has

been achieved, the tape is firmly pressed on a substrate, e.g., SiO₂. Finally, a microscope is used to identify the graphene flakes by color contrast. Due to the high quality (in terms of structural integrity) of the graphene flakes, this well-known “Scotch tape” method is widely used to prepare graphene flakes in scientific research to study the fundamental properties of graphene. However, this method fails to produce graphene with a controlled flake size, thickness and azimuthal orientation. Furthermore, the scotch tape method only produces graphene flakes with a size of several microns. Applications that use graphene’s extraordinary electric transport properties require structurally coherent graphene on a large scale (wafer scale), or large arrays of graphene flakes positioned with a unique azimuthal orientation on a substrate.

Figure 3-2 Schematic of graphene grown by CVD process.

Large area graphene can be grown by chemical vapor deposition (CVD) from carbon containing gases on transition metal surfaces.^{14, 15} Graphene has already been reported to grow on a variety of transition metals, e.g., Ni, Cu, Pt, Ru, Ir, Co, Fe, and Pd.¹² The formation of graphene on such metal surfaces is realized by surface catalytic decomposition of a carbon precursor and/or by surface segregation of carbon dissolved in the bulk of the metal. Either of these two processes can be the dominant process, or they can coexist, depending on the solubility of carbon in the transition metal. A typical setup for growing graphene by CVD is illustrated in **Figure 3-2**. The metal substrate is heated up to approximately 1000 °C in a hot furnace. Then it is exposed to a flow of gas: CH₄+H₂. Finally, the substrate is cooled down to room temperature in a H₂ environment. For a Ni substrate, as shown in **Figure 3-3**,

methane decomposes at the surface, creating a carbon concentration gradient between the surface and the bulk. As a result, carbon atoms start to diffuse into Ni, forming a carbon solid solution in Ni. As the substrate cools, the dissolved carbon precipitates out and segregates to the surface, producing graphene layers. The quality and the thickness of graphene can be tuned by changing the reaction parameters, such as cooling rate, pre and post annealing processes, concentration of carbon precursor, reaction time, and reaction temperature. For example, pre annealing the Ni substrate in an H_2 atmosphere removes sulfur and phosphorus impurities, which cause local variations in carbon solubility, thereby producing more uniformly thick graphene layers.¹⁶ Besides the formation process, the substrate morphology is also critical for the formation of graphene layers grown by CVD. An atomically smooth surface of a single crystal Ni is more likely to produce uniform and thin graphene layers, while on a polycrystalline Ni surface, thicker layers of graphene will form because of the extra nucleation sites provided by the grain boundaries.¹⁷

Figure 3-3 Schematic of graphene CVD growth process (a) on a Ni surface and (b) on a Cu surface. Figure is based on reference.¹⁷

The solubility of carbon in copper is about one thousand times less than that in Ni at $1000^\circ C$.^{18, 19} Therefore, the growth of graphene on copper proceeds via direct decomposition of carbon precursors, as shown in **Figure 3-3**. The growth of a continuous graphene layer will cover the copper surface, which eventually stops the decomposition process, resulting in single layer graphene. There are multiple nucleation sites on the copper surface, and graphene generally starts to grow spontaneously at many of these sites. These graphene domains may have different lattice orientations, depending on the underlying Cu grains. As growth

continues, the separate graphene domains merge into a continuous polycrystalline graphene film. These orientation mismatches result in defects and are undesirable for practical applications. In industrial applications, such as graphene-based electronic, photonic, and mechanical devices, uniform wafer-scale single crystal graphene films are required. The difficulty for obtaining such films lies in the multiple nucleation sites, with each site producing a graphene domain with a different crystal orientation, resulting in mismatch or defects where domains meet during the growth process.

Currently there are two strategies to grow large area single-crystal graphene over a solid substrate surface. The first approach involves growing a single grain to as large size as possible from a single nucleation site. Hao *et al.*, reported that oxygen at the copper surface substantially decreases the nucleation site density by passivation of the copper surface.²⁰ Control of the surface oxygen coverage enables growth of centimeter-sized single-crystal graphene domains from a single nucleation site. However, this approach still needs improvement with respect to throughput and reproducibility for synthesis of wafer-scale single crystal graphene. The second method is to align all the different graphene domains so that as their size increases, they will merge into a single crystal graphene layer without grain boundary defects. Lee *et al.* demonstrated wafer scale single layer single domain graphene growth on a hydrogen-terminated germanium buffer layer.²¹ The anisotropic twofold symmetry of the germanium(110) surface favors unidirectional alignment of the graphene nucleation sites, which merge to form a uniform single graphene crystal with a predefined orientation. With this method, single crystal graphene with a 2 inch wafer size has been achieved.

One of the advantages of CVD grown graphene is that it can be transferred to different kinds of substrate. The transfer process is shown in **Figure 3-4**. A layer of PMMA or PDMS is first deposited on top of the graphene film. Then the metal substrate is etched away by wet chemical etching, e.g. etching Cu in an iron chloride solution. As a result, a floating graphene thin film together with the polymer layer is left in the chemical bath. These are then transferred to the target

substrate, and the polymer layer is removed by dissolving it in acetone solution followed by annealing. The transfer process can introduce unwanted wrinkles and cracks in the graphene film.

Graphene layers can also be obtained by epitaxial growth on an insulating SiC surface. Graphene is formed via sublimation of silicon and graphitization of the remaining carbon atoms by annealing at high temperature (above 1000 °C).²² The top layers of the SiC crystals undergo thermal decomposition under such annealing conditions. Silicon atoms sublime, and the carbon atoms remaining on the surface rearrange and bond to form epitaxial graphene layers. Several factors influence the formation of graphene on SiC surface, e.g., the annealing temperature, the annealing gas environment, and growth on the Si-face or C-face. One advantage of such a growth method is that the graphene can be used immediately after synthesis, because it is grown on a large bandgap semiconductor surface of a material that is already compatible with semiconductor industry processes. Challenges still remain for applications of graphene on a SiC substrate, such as controlling the number of graphene layers for large scale production, and controlling the growth pattern on different SiC faces.¹²

Figure 3-4 Transferring graphene to a target substrate. Figure is based on reference.¹⁴

3.3 Defects in graphene

The control of defects in graphene is one of the key requirements for industrial applications. The electronic properties of graphene are greatly affected by the presence of defects because they can act as scattering centers for electrons, reducing sheet conductivity.²³ Defects associated with dangling bonds can enhance the chemical reactivity of graphene.²⁴ Likewise, the presence of defects reduces the thermal conductivity of graphene.²⁶

Figure 3-5 Point defects in graphene. From top to down: Stone-Wales defect (The dash lines and two grey atoms indicate their original position before the defect formed), vacancy defect, adatom defect (the red circle stands for an adatom on top of graphene). Figure is based on reference.²⁷

In graphene, there exist point defects, which typically are vacancies or interstitial atoms, one dimensional defects, such as dislocation line

defects, and two dimensional defects, like grain boundaries or stacking faults. **Figure 3-5** shows three types of point defects in graphene: Stone-Wales defects, vacancy defects, and adatom defects. The Stone-Wales defect is a pure reconstruction of a graphene crystal lattice. Four hexagons are transformed into two pentagons and two heptagons by rotating one of the C-C bonds by 90° as shown in **Figure 3-5 (top)**. Vacancy defects are defects with missing atoms in the lattice, as shown in **Figure 3-5 (middle)**. A single C atom is missing, forming a five-atom and a nine-atom carbon ring. Both Stone-Wales defects and vacancy defects can be introduced by electron irradiation.²⁷ A minimum amount of energy must be transferred to a carbon atom to drive it from its lattice position without it immediately recombining and healing the defect. The threshold energy for displacing carbon atoms from the graphene lattice is about 18-20 eV, which requires a very high electron energy of 90-100 keV due to the large mass difference between a carbon atom and an electron.²⁸ Stone-Wales defects require less energy than the vacancy defect because it only involves a carbon bond transformation and no carbon atom is knocked out of the lattice. Foreign atoms can be physisorbed on the graphene surface by van der Waals force, or chemisorbed by covalent bonding with carbon atoms. Sometimes, such foreign atoms are pinned by structural defects which normally serve as reactive sites due to locally increased reactivity of the π -electron system.²⁹

3.4 Graphene characterization: Raman spectroscopy

Raman spectroscopy is one of the most popular techniques to characterize graphene. It provides a fast and non-destructive way to probe the structural and electronic information in graphene in both scientific research and industrial mass production. Raman spectroscopy has been widely used to study disorder, chemical modification, electrical mobility, thermal conductivity, and electron-phonon and electron-electron interaction in graphene.³⁰ This is due to the fact that Raman scattering probes graphene lattice phonons, which are excited by

electronic transitions (see below). The position, width, and intensities of Raman peaks reveal information on defects, edges, doping, and strain in graphene.

When light interacts with matter, it can be absorbed or scattered. As discussed in Chapter 2, the process of absorption requires that the incident photon energy corresponds to the energy gap between the ground state of the molecule and the excited state. In contrast, scattering can occur without matching the energy difference. There are two types of light scattering: Rayleigh scattering, an elastic scattering process where the energy of the photons is unchanged by scattering; Raman scattering, an inelastic scattering process where the scattering involves movement of nuclei, thus, the photon energy changes during scattering. These two processes are indicated in **Figure 3-6**. In a Raman scattering process, a molecule is excited to a so called virtual state by absorption of photons. The molecule then returns to a rotational or vibrational state different from the energetic state of the molecule before absorbing the incident photon. The resulting energy difference is termed a Stokes shift or anti-Stokes shift, depending on the original and final state of the molecule. At room temperature, most of the molecules are in the ground state.

Figure 3-6 Light scattering processes: Rayleigh scattering, non-resonant (stokes and anti-stokes) Raman scattering, and resonant (stokes and anti-stokes) Raman scattering.

The emitted photon has a lower energy than the incident photon after Raman scattering, resulting in a Stokes shift. Due to thermal activation, some molecules may be excited to a vibrational state before scattering, leading to the possibility of an emitted photon with a higher energy than

the incident photon. In this case, the energy difference is called anti-Stokes shift. For vibrational modes with an energy that is too high to be thermally excited, the anti-Stokes shift still exists because the Stokes shift Raman process (which is dominant) excites a small population of molecules to all Raman-active vibrational states. This vibrationally excited population then becomes a population for anti-Stokes Raman scattering. Raman scattering is a relatively rare event, and typically the cross section is about 10^{-25} to 10^{-30} cm^2 , which is about 10^6 times smaller than the cross section for fluorescence processes discussed in Chapter 2.³¹ If a Raman scattering process is associated with a real electronic transition (as shown **Figure 3-6** on the right side), a scattering enhancement up to 10^6 can be observed. Both Stokes and anti-Stokes process exist for resonant Raman scattering.

The Raman scattering can be further understood by examining the energy and momentum conservation in the process. In a Raman process, a photon with energy $E_i = E_{\text{laser}}$ and momentum $\mathbf{k}_i = \mathbf{k}_{\text{laser}}$ is incident on the molecule and is scattered. In this process, both energy and momentum are conserved. Therefore, the scattered photon has an energy E_s and momentum $\mathbf{k}_s$.

$$E_s = E_i \pm E_q \quad k_s = k_i \pm q \quad 3-1$$

where E_q and q are the energy and momentum change during the scattering event (usually by phonons). In a one-phonon scattering process (also called first-order Raman scattering), the momentum transfer is usually neglected, i.e., $q = k_s - k_i \approx 0$. The momenta associated with the one-phonon scattering process are on the order of $k_i = 2\pi/\lambda_{\text{laser}}$, where usually the λ_{laser} is in visible range (390-700 nm). Thus, k_i is a relatively small value compared with the dimensions of the first Brillouin zone, which is limited to $2\pi/a$ with a the unit cell vector ($a = 0.246$ nm for graphene). This explains why a one-phonon Raman scattering event in graphene can only occur with phonons at $q \approx 0$, that is phonons near the Γ point. For phonons with $q \neq 0$, multiple scattering (also known as high order Raman scattering, e.g., Raman scattering involving two scattering events is called second-order Raman scattering) is required for the Raman process. For example, a

photoexcited electron at $\mathbf{k}$ can be scattered to $\mathbf{k}+\mathbf{q}$ by a phonon, and then can be scattered back to its original state $\mathbf{k}$ by a second phonon scattering with wave vector $-\mathbf{q}$, which allows the electron to recombine with the corresponding hole. This two-phonon scattering can be observed in any solid but the probability is typically very small. However, as we shall see in the following text, under the resonant conditions in graphene, $q \neq 0$ phonons contribute significantly to the observed Raman spectrum.

When light interacts with single layer graphene, electrons are excited from the valence band to the conduction band, as shown in **Figure 3-8** bottom left. Because single layer graphene has zero bandgap, all radiation frequencies match the energy difference between the valence and conduction band for a certain $\mathbf{k}$. Hence, real electronic transitions occur during the Raman process in graphene. A typical Raman spectrum of graphene is shown in **Figure 3-7**. There are three prominent peaks in the spectrum: the D band at around 1350 cm^{-1} , the G band at around 1580 cm^{-1} , and the 2D band at around 2700 cm^{-1} .

Figure 3-7 A Raman spectrum of defected single layer graphene. The weak peak at around 2450 cm^{-1} is under debate³⁰. Another peak at around 2950 cm^{-1} is the combination of inter-valley and intra-valley transition of D band.

The G band is due to the E_{2g} vibrational mode at the Γ -point, and is a one-phonon scattering event, as shown in **Figure 3-8 (left)**. The G band originates from the stretching of the sp^2 C-C bond in graphitic materials and exists in all sp^2 carbon systems. The D band corresponds to the breathing mode of six-atom rings (**Figure 3-8 (right)**) and requires a defect to activate the process. The presence of a defect breaks the translational symmetry of the crystal, and, thus, provides additional scattering to allow conservation of momentum. Phonons with $\mathbf{q} \neq \mathbf{0}$ are allowed in this process. The D band can be explained by a double resonance process (electron-photon and electron-phonon scattering) shown in **Figure 3-8 (right)**. An electron with wavevector $\mathbf{k}$ around the $\mathbf{K}$ point moves to an excited state by absorbing a photon of energy E_p , creating an electron-hole pair. The electron is scattered by a defect with wavevector $\mathbf{q}$ to a point near the $\mathbf{K}'$ point, with wavevector $\mathbf{k}+\mathbf{q}$. The electron is then scattered back to a $\mathbf{k}$ state, and emits a phonon ($-\mathbf{q}$), where the electron recombines with a hole at a $\mathbf{k}$ state. The 2D band can be explained similarly to the D band by a double resonance process. In this case, momentum conservation is fulfilled by scattering with two phonons, with vectors $+\mathbf{q}$ and $-\mathbf{q}$. Since it involves two phonons, it generates a Raman signal with a doubled frequency. Note that the weak peak at around 2450 cm^{-1} is under debate.³⁰ Another peak at around 2950 cm^{-1} is the combination of an inter-valley (D band) and an intra-valley (D' band, similar to the D band, but the electron transition occurs within the same Dirac cone) transition.

Figure 3-8 Top: E_{2g} (left) and A_{2g} (right) vibrational mode. Bottom: Raman scattering process of G band (left) and double resonant process of D band (right).

The D peak intensity of a Raman spectrum provides a qualitative assessment of the number of defects in a graphene sample. However, quantitative assessment is more difficult. Early studies combined STM and Raman spectroscopy to correlate the defect density using the ratio of the D and G peak intensities $I(D)/I(G)$. Lucchese *et al.* reported a correlation between the defect density and $I(D)/I(G)$ by using Ar^+ ion bombardment on graphene.³² They analyzed the STM image for a range of ion doses to count the number of defects, from which they extracted the average distance between defects L_D . Quantifying the development of defects in graphene was achieved by plotting $I(D)/I(G)$ as a function of the average distance between defects L_D . They found that $I(D)/I(G)$ increases with decreasing L_D (from low defect density to high defect density). This trend reverses once L_D falls below a critical value (~ 3.5 nm). This behavior suggests the existence of two mechanisms contributing to defect formation in graphene. A single Ar^+

ion impact on graphene will cause modification in two regions, as shown in **Figure 3-9** (the light and dark green circles). The inner light green region (denoted as structural disordered area) indicates the defect region, where the Ar^+ ion impacted, and, thus, where the crystal lattice is damaged. In the outer dark green region (denoted as activated area), the crystal structure is preserved. However, due to proximity to a defected region, phonons and electrons from this region can still scatter off the defect, thus, contributing to the intensity of the D peak. Both regions contribute to the D peak intensity. Therefore, the D peak evolves as follows: in the low defect density regime, the D peak intensity grows as the defect density increases (increase of the structural and activated area). As the defect density continues to increase, the activated areas start to overlap. The D peak intensity then reaches its maximum value. Further increase of the defect density results in a decrease of the D peak intensity due to the vanishing of six-atom ring breathing mode.

Figure 3-9 Definition of activated area (outer dark green) and structural disordered area (inner light green).

3.5 Reference

1. A. K. Geim and K. S. Novoselov, "*The rise of graphene*", Nature materials **6** (3), 183-191 (2007).

2. A. K. Geim, "*Graphene: status and prospects*", Science **324** (5934), 1530-1534 (2009).
3. K. S. Novoselov, D. Jiang, F. Schedin, T. J. Booth, V. V. Khotkevich, S. V. Morozov and A. K. Geim, "*Two-dimensional atomic crystals*", Proceedings of the National Academy of Sciences of the United States of America **102** (30), 10451 (2005).
4. Y. Zhang, Y.-W. Tan, H. L. Stormer and P. Kim, "*Experimental observation of the quantum Hall effect and Berry's phase in graphene*", Nature **438** (7065), 201-204 (2005).
5. M. Y. Han, B. Özyilmaz, Y. Zhang and P. Kim, "*Energy band-gap engineering of graphene nanoribbons*", Physical Review Letters **98** (20), 206805 (2007).
6. K. I. Bolotin, K. J. Sikes, Z. Jiang, M. Klima, G. Fudenberg, J. Hone, P. Kim and H. L. Stormer, "*Ultrahigh electron mobility in suspended graphene*", Solid State Communications **146** (9), 351-355 (2008).
7. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", Science **321** (5887), 385-388 (2008).
8. J. S. Bunch, A. M. Van der Zande, S. S. Verbridge, I. W. Frank, D. M. Tanenbaum, J. M. Parpia, H. G. Craighead and P. L. McEuen, "*Electromechanical resonators from graphene sheets*", Science **315** (5811), 490-493 (2007).
9. J. S. Bunch, S. S. Verbridge, J. S. Alden, A. M. van der Zande, J. M. Parpia, H. G. Craighead and P. L. McEuen, "*Impermeable atomic membranes from graphene sheets*", Nano Letters **8** (8), 2458-2462 (2008).
10. R. Nair, P. Blake, A. Grigorenko, K. Novoselov, T. Booth, T. Stauber, N. Peres and A. Geim, "*Fine structure constant defines visual transparency of graphene*", Science **320** (5881), 1308-1308 (2008).
11. A. Reina, X. Jia, J. Ho, D. Nezich, H. Son, V. Bulovic, M. S. Dresselhaus and J. Kong, "*Large area, few-layer graphene films on arbitrary substrates by chemical vapor deposition*", Nano Letters **9** (1), 30-35 (2008).
12. P. Avouris and C. Dimitrakopoulos, "*Graphene: synthesis and applications*", Materials Today **15** (3), 86-97 (2012).
13. W.-W. Liu, S.-P. Chai, A. R. Mohamed and U. Hashim, "*Synthesis and characterization of graphene and carbon nanotubes: A review on the past and recent developments*", Journal of Industrial and Engineering Chemistry **20** (4), 1171-1185 (2014).
14. K. S. Kim, Y. Zhao, H. Jang, S. Y. Lee, J. M. Kim, K. S. Kim, J.-H. Ahn, P. Kim, J.-Y. Choi and B. H. Hong, "*Large-scale pattern growth of graphene films for stretchable transparent electrodes*", Nature **457** (7230), 706-710 (2009).

15. C. Mattevi, H. Kim and M. Chhowalla, "*A review of chemical vapour deposition of graphene on copper*", Journal of Materials Chemistry **21** (10), 3324-3334 (2011).
16. Q. Yu, J. Lian, S. Siriponglert, H. Li, Y. P. Chen and S.-S. Pei, "*Graphene segregated on Ni surfaces and transferred to insulators*", Applied Physics Letters **93** (11), 113103 (2008).
17. Y. Zhang, L. Gomez, F. N. Ishikawa, A. Madaria, K. Ryu, C. Wang, A. Badmaev and C. Zhou, "*Comparison of graphene growth on single-crystalline and polycrystalline Ni by chemical vapor deposition*", The Journal of Physical Chemistry Letters **1** (20), 3101-3107 (2010).
18. S. Chen, W. Cai, R. D. Piner, J. W. Suk, Y. Wu, Y. Ren, J. Kang and R. S. Ruoff, "*Synthesis and characterization of large-area graphene and graphite films on commercial Cu-Ni alloy foils*", Nano Letters **11** (9), 3519-3525 (2011).
19. W. Cai, R. D. Piner, Y. Zhu, X. Li, Z. Tan, H. C. Floresca, C. Yang, L. Lu, M. J. Kim and R. S. Ruoff, "*Synthesis of isotopically-labeled graphite films by cold-wall chemical vapor deposition and electronic properties of graphene obtained from such films*", Nano Research **2** (11), 851-856 (2009).
20. Y. Hao, M. Bharathi, L. Wang, Y. Liu, H. Chen, S. Nie, X. Wang, H. Chou, C. Tan and B. Fallahazad, "*The role of surface oxygen in the growth of large single-crystal graphene on copper*", Science **342** (6159), 720-723 (2013).
21. J.-H. Lee, E. K. Lee, W.-J. Joo, Y. Jang, B.-S. Kim, J. Y. Lim, S.-H. Choi, S. J. Ahn, J. R. Ahn and M.-H. Park, "*Wafer-scale growth of single-crystal monolayer graphene on reusable hydrogen-terminated germanium*", Science **344** (6181), 286-289 (2014).
22. J. Hass, R. Feng, T. Li, X. Li, Z. Zong, W. de Heer, P. First, E. Conrad, C. Jeffrey and C. Berger, "*Highly ordered graphene for two dimensional electronics*", Applied Physics Letters **89** (14), 143106 (2006).
23. D. Boukhvalov, M. Katsnelson and A. Lichtenstein, "*Hydrogen on graphene: Electronic structure, total energy, structural distortions and magnetism from first-principles calculations*", Physical Review B **77** (3), 035427 (2008).
24. A. Cortijo and M. A. Vozmediano, "*Effects of topological defects and local curvature on the electronic properties of planar graphene*", Nuclear Physics B **763** (3), 293-308 (2007).
25. G. Rutter, J. Crain, N. Guisinger, T. Li, P. First and J. Stroscio, "*Scattering and interference in epitaxial graphene*", Science **317** (5835), 219-222 (2007).
26. F. Hao, D. Fang and Z. Xu, "*Mechanical and thermal transport properties of graphene with defects*", Applied Physics Letters **99** (4), 041901 (2011).

27. F. Banhart, J. Kotakoski and A. V. Krasheninnikov, "*Structural defects in graphene*", ACS nano **5** (1), 26-41 (2010).
28. F. Banhart, "*Irradiation effects in carbon nanostructures*", Reports on Progress in Physics **62** (8), 1181 (1999).
29. O. Cretu, A. V. Krasheninnikov, J. A. Rodríguez-Manzo, L. Sun, R. M. Nieminen and F. Banhart, "*Migration and localization of metal atoms on strained graphene*", Physical Review Letters **105** (19), 196102 (2010).
30. A. C. Ferrari and D. M. Basko, "*Raman spectroscopy as a versatile tool for studying the properties of graphene*", Nature nanotechnology **8** (4), 235-246 (2013).
31. K. Kneipp and H. Kneipp, "*Single molecule Raman scattering*", applied spectroscopy **60** (12), 322A (2006).
32. M. M. Lucchese, F. Stavale, E. M. Ferreira, C. Vilani, M. Moutinho, R. B. Capaz, C. Achete and A. Jorio, "*Quantifying ion-induced defects and Raman relaxation length in graphene*", Carbon **48** (5), 1592-1597 (2010).

Chapter 4

Photoluminescence-based detection of particle contamination on EUV reticles

Here, we propose a comparison-free inspection technique to detect particle contamination on the reticle of extreme ultraviolet (EUV) lithography systems, based on the photoluminescence spectral characteristics of the contaminant particles and their elemental composition. We have analyzed the spectra from different particles found on reticles in EUV lithographic systems and have determined the minimum detectable particle size: 25 nm for organic particles and 100 nm for Al particles. Stainless steel coatings (50 nm thick and $50 \times 50 \mu\text{m}^2$ in area) exhibit detectable photoluminescence, and the estimated minimum detectable particle is 2 μm .

4.1 Introduction

Optical lithography is one of the key technologies in semiconductor fabrication. Currently, the most advanced lithography systems use immersion techniques, based on 193 nm light. This technique is capable of printing features as small as 22 nm with a complex combination of techniques, such as double-patterning. Thus, the contribution of photolithography to the overall cost of integrated circuit fabrication is increasing.¹ Extreme ultraviolet lithography (EUVL), operating at a

wavelength of 13.5 nm, is required to continue reducing feature sizes.² The dramatic decrease in wavelength will allow features smaller than 22 nm to be printed, using simpler patterning techniques.

EUV lithography systems require a clean environment, especially on the reticle, to ensure that the reticle pattern is printed with high fidelity. Although EUVL operates under vacuum conditions, contamination with small particles is unavoidable.³ For example, particles can come from tin droplets, mechanical parts, and the photoresist. Particles can cause fatal defects on the final printed wafer, leading to a reduced yield of working chip devices. In current immersion-based lithography systems, DUV (deep ultraviolet) pellicles are used to protect reticles from particle contamination. Although new pellicle materials are being investigated, currently there are no pellicles available for EUVL systems.⁴ Therefore, particles can be deposited onto the reticle, where they will be imaged on the wafer since they are in the object plane. Particles with a size comparable to the feature size on the wafer, e.g., 25 nm particles for the 20 nm chip process node, will result in defects on the exposed wafers. Particle contamination can be introduced to the reticle, either during handling outside of the lithography system, or during exposure inside the system. The former has been largely mitigated by an advanced protection system, e.g., the dual-pod carriersystem.⁵ For the latter, reticle protection (pellicle), and/or, inspection, and cleaning are required.

Currently, the primary requirement for *in situ* inspection at the 22 nm process node is to detect 25 nm particles on a full size reticle ($132 \times 132 \text{ mm}^2$) within 1h. The main difficulty with current inspection techniques, based on light scattering, is that the particle scatters light into a similar band of spatial frequencies as the features on the reticle, e.g., a particle would look like a contact hole when examining the scattering pattern. Hence, in an arbitrary reticle pattern, there is no way to detect the presence of a particle from the scattering pattern without comparison to a reference. Currently, inspection is done *ex situ* by imaging the surface at very high resolution (i.e., sub-100 nm pixels using 193 nm UV light) and comparing the image to a nominally identical location elsewhere on the wafer/reticle (die-to-die analysis) or to a calculated (or reference) image (die-to-database). However, it takes

a few hours to inspect a whole reticle using this method, thereby, increasing the overall cost of semiconductor fabrication. Other inspection techniques, including E-beam inspection and actinic inspection, are under development.^{6, 7} Although they have shown detection of 30 nm or even smaller particles on patterned reticles, those techniques suffered from throughput and cost. Besides, due to their large volume, it is not yet possible to integrate them as an inspection module inside an EUVL system; thus, there is an additional risk that particles contaminate the reticle during the loading-unloading process of the lithography system.

Figure 4-1 (a) Principle of the photoluminescence process; (b) schematic view of the working principle for inspection based on the photoluminescence.

Here, we propose a comparison-free and potentially *in situ* inspection method, using the intrinsic photoluminescence from contaminant particles to detect their presence on the reticle. The photoluminescent signal from the particle has a different wavelength from the excitation wavelength (laser), and the reticle will have little or no photoluminescence signal. Thus, the scattered light from the reticle can be filtered out, leaving only the photoluminescence signal from particles captured by the detector, as illustrated in **Figure 4-1**. Since only the light signal from particles is captured, no comparison is needed, which is an advantage over the techniques based on light scattering. This method also allows a fast scan with low resolution, followed by a high resolution scan, if required. The scan time of a whole reticle is determined by the resolution and the photoluminescence signal intensity from the contaminant particles. An additional advantage of this

inspection method is that it is possible to identify the type of contaminant particles from their photoluminescence spectrum, thus allowing an appropriate cleaning mechanism to be chosen. In this paper, our primary experiments focus on determining the photoluminescent yield of typical particles found on reticles.

4.2 Theory

The majority of contaminant particles on EUV reticles are stainless steel, aluminum, and organics (hydrocarbons), however, the contribution from each category varies substantially between reticles. And, although they are defined as stainless steel or aluminum particles, particles often contain a small fraction of other elements, e.g., Al particles may contain Mg and/or O. The different compounds have different potential sources of photoluminescence. Hydrocarbons are usually effective emitters under UV irradiation due to their complex electronic structures. Here, we do not distinguish between different organic molecules, and simply refer to them as organic particles. Photoluminescence from metal particles is expected to be due to an oxidized outer shell, which occurs due to the presence of water in the residual gases of the EUV lithography system. The stainless steel particles in this study mainly contain Fe, Cr and Ni. Cr naturally forms a passivation layer of oxide, which prevents surface erosion. Among the ionization states of Cr, Cr^{3+} has well known sharp emission line at 694 nm in a metal matrix composite.⁸ NiO has also been reported to have emission lines at 312 nm and 400 nm under UV excitation.⁹ For Al particles, it is also expected that the majority of the photoluminescence will originate from their oxide shell. Wide band emission in visible range has been reported in various studies of Al_2O_3 thin films.¹⁰⁻¹⁴ Color centers in the oxide layer are the main source of photoluminescence.

It is noted that small differences in composition of particles can lead to different photoluminescence yield. For example, some Al particles were found to contain a small amount of Mg. In addition, the photoluminescence spectrum from metallic particles depends on the oxidation process and, often, the presence of defects. As a result,

Chapter 4

differences between seemingly identical particles can lead to a different photoluminescence spectrum.

The quantum yield is one of the most important parameters of an emission center. The quantum yield is defined as the emitted photons relative to the number of absorbed photons. In this study, in order to include the excitation efficiency, we define the yield, Q , as the emitted photons relative to the number of incident photons. The number of photons that result in detector counts can be estimated:

$$C_{det} = \Phi_{inc} (\pi R^2) \alpha \eta_{emi} \eta_{col} T \eta_{det} \quad 4-1$$

where C_{det} is the count rate (count/s) at detector, Φ_{inc} is the incident photon flux (photon/s/m²), πR^2 is the particle area (with effective radius R), α is the photon absorption rate by the particle, η_{emi} is the emission efficiency of the particle, η_{col} is the collection efficiency, T is the transmission of system, η_{det} quantum efficiency of detector (count/photon). Note that **Eq. 4-1** contains the assumption that the incident photons are absorbed within a certain depth, e.g. the thickness of oxide shell. Q can be, thus, derived by:

$$Q = \frac{\Phi_{emi}}{\Phi_{in}} = \frac{C_{det}}{\Phi_{inc} \pi R^2 \eta_{col} T \eta_{det}} = \alpha \eta_{emi} \quad 4-2$$

where Φ_{in} is the number of photons incident on the particle, which can be derived by multiply the incident photon flux (Φ_{inc}) by the effective area of the particle (πR^2). The Φ_{emi} is the number of photons emitted by the particle, which can be obtained by the count rate at detector (C_{det}) divided by the system transmission (T), collection efficiency (η_{col}), and detector quantum efficiency (η_{det}).

Figure 4-2 Schematic view of the setup.

The number of photons or Q required for the particle to be detected depends on the photoluminescence intensity of the reticle (absorber, Ru capping layer, and Si/Mo multilayer). In this study, this is experimentally determined. The signal to noise ratio, i.e., photons emitted by the particles to the photons emitted by the reticle, is required to be larger than one to allow the particle to be detected. Here, we take a signal to noise ratio of 10 to eliminate almost all false positives during the inspection. A detailed calculation will be presented in **Sec. 4.5**.

4.3 Experimental setup

A schematic drawing of the experimental setup used for investigation of photoluminescence-based detection of particles is shown in **Figure 4-2**. There are three main building blocks: the laser systems (listed in **Table 4-1**), sample stage, and collection system. By using three lasers, a wide spectral excitation range, from the ultraviolet to the near IR is covered, which allows the optimal excitation wavelength to be found. The laser beam is focused using a custom made tunable beam shaping system. The beam shaping system focuses the laser beam into a rectangle with length of 4 mm, and a width ranging from 100 μm to 1000 μm .

In the sample stage block, there is a sample holder that can handle standard 300 mm wafers, as well as smaller samples. The sample holder is placed on an x - y - z translation stage (AeroTech ES15800-1, AVSI125) with an absolute positional accuracy of 1 μm . To ensure that the

Chapter 4

sensitivity of the photoluminescence-based detection is accurately characterized, the stage positioning is correlated with a particle map, obtained from a phase contrast image (KLA Surfscan SP2). In this way, it is also possible to precisely locate target particles.

Table 4-1 *Laser specifications*

Type	Wavelength (Range)	Max. Avg. Power
Continuous wave	532 nm*	5 W
Continuous wave	266 nm*	200 mW
ns pulsed	355 nm	10 W
fs pulsed	680-1080 nm#	4 W
fs pulsed	340-540 nm#	1 W
fs pulsed	230-360 nm#	400 mW

* 266 nm is the second harmonic of 532 nm.

230-360 nm and 340-540 nm are the third and second harmonic of 680-1080 nm.

The collection block contains an objective with an NA = 0.13, a CCD camera (AVT Stingray F-080B) to obtain dark field images, and a spectrograph with two 300 lines/mm gratings, blazed for 350 and 500 nm, respectively (SOLAR Laser Systems, M266i), coupled to a high sensitivity EMCCD camera (Andor Technology, DU971P UVB, pixel size=10 μ m) to capture photoemission from the particle. The excitation wavelength was filtered out using two sets of filters (Semrock), which are detailed in **Table 4-2**. The collection efficiency was calibrated using an HG-1 Mercury Argon Calibration Light Source and a Deuterium-Halogen Light Source (AvaLight-D(H)-S). **Figure 4-3** shows the collection efficiency curve from 200 to 1000 nm, including the collection optics with NA=0.13, the loss through the lenses, mirrors, the transmission of the gratings in monochromator, and the quantum efficiency of EMCCD detector. The most effective collection range lies between 400 and 750 nm with the highest collection efficiency located at approximately 520 nm.

Figure 4-3 System transmission.

Table 4-2 Longpass filter specification

Filter type	Cutoff wavelength (nm)	Transmission	Filter type	Cutoff wavelength (nm)	Transmission
LP02-266RU-25	266	>90%	FF02-409/LP-25	409	>93%
LP03-325RE-25	325	>93%	LP02-442RE-25	442	>93%
LP02-355RE-25	355	>93%	LP02-488RE-25	488	>93%
LP02-364RU-25	364	>93%	LP03-532RE-25	532	>93%

4.4 Experiment procedure

Particles were collected from the reticle in a real EUV lithography exposure process, and then were transferred to a 300 mm wafer. The wafer was then scanned to identify the size and location of the particles by KLA Surfscan SP2. Certain particles were then analyzed using

SEM-EDX to obtain their chemical composition. A map with the information of particle size, location and chemical composition was generated. The wafer containing the particles was then loaded into the photoluminescence setup. Dark Field imaging was used to find chosen particles, using location data from the particle map. Finally photoluminescence spectral measurements were obtained from the particle on the wafer.

4.5 Results and Discussion

In **Figure 4-4**, an Al particle is shown. It mainly contains O and Al with a very small amount of Mg. A weak photoluminescence spectrum (**Figure 4-4b**) was obtained by using 266 nm excitation with an intensity of 76 W/cm². The bright horizontal streak in the center of the hyperspectral image in **Figure 4-4b** is the photoluminescence signal from the Al particle during excitation. The strong emission lines from 550 nm that have no positional dependence are due to Raman scattering (from the second order of the diffraction grating) from the Si substrate, and the strong photoluminescence emission beyond 575 nm is also from Si substrate. We can see that the spectrum has a relatively low intensity, and very broad spectral bandwidth (FWHM=150 nm) with a peak at around 450 nm. To obtain optimum excitation, the photoluminescence excitation spectrum for Al particles was studied. In **Figure 4-5**, we show a typical photoluminescence excitation spectrum, which has a peak at 420 nm. All other photoluminescence spectra for Al were taken using a laser excitation wavelength of 420 nm. All particle sizes in the following text refer to their diameter.

Figure 4-4 detection of an Al particle. (a) SEM image the Al particle. (b) hyper-spectral image of the photoluminescence signal from the Al particle. (c) The spectrum of the Al particle.

Figure 4-5 The yield, Q , of an Al particle as a function of excitation wavelength.

Figure 4-6 Photoluminescence spectra for two types of "Al" particles with 420 nm excitation wavelength and excitation intensity of 44 W/cm^2 .

As mentioned above, the Al particles may have different additives, which lead to different photoluminescence characteristics. In **Figure 4-6**, we show two "Al" particles, particle 1 (diameter: $1.6 \mu\text{m}$) contains Al, Mg, O, and C, while particle 2 (diameter: 490 nm) contains Al, O, and C (The majority element of these particles is Al, with the additives being only a very small fraction). However, these two particles show distinctive photoluminescence spectra: one spectrum peaks at around 500 nm, while the other peaks at 630 nm. This is expected

because different dopants result in different color centers with different emission spectra. The difference will result in variations in Q , which will be discussed in the next section of this paper.

An organic particle is shown in the SEM image in **Figure 4-7**. It only contains C and O elements. **Figure 4-7b** is the hyperspectral image taken at an excitation wavelength of 420 nm with an intensity of 44 W/cm². The bright horizontal streak in the center of the hyperspectral image is the photoluminescence signal from the organic particle during excitation. The two strong emission lines that have no positional dependence are due to Raman scattering from the Si substrate. The broad photoluminescence spectrum, shown in **Figure 4-7c**, has a peak around 550 nm. All detected organic particles have similar spectra.

The photoluminescence signal from the same organic particle was also examined under 266 nm (11 W/cm²) excitation. However, no signal was detected in this case. Furthermore, subsequent photoluminescent measurements at 420 nm (44 W/cm²) revealed that the particle was no longer photoluminescent, indicating that the shorter wavelength excitation resulted in bleaching (see **Figure 4-8**). To confirm this, a similar organic particle was exposed in a sequence of excitation wavelengths: 420 nm, 420 nm, 266 nm, finally and 420 nm. We found that there was a clear photoluminescence spectrum from the first and second exposure (420 nm excitation), but no signal in the following measurements with 266 and 420 nm excitation. The dark field images showed that the particles were not removed after exposure. These results indicate that organic particles are likely to be bleached by UV excitation.¹⁵ No bleaching was observed for Al particles subjected to similar exposures.

Figure 4-7 Detection of an organic particle. (a) SEM image the organic particle. (b) hyper-spectral image of the organic photoluminescence signal. (c) The spectrum of the organic particle.

Figure 4-8 Organic particle bleaching due to exposure to 266 nm excitation. (a) and (b) organic particle was exposed in a sequence to 420 nm, 266 nm and 420 nm excitation; (c) and (d) similar organic particle was exposed in a sequence to 420 nm, 420 nm, 266 nm and 420 nm.

Different sizes (from 100 nm to $\sim \mu\text{m}$) of stainless steel particles were also investigated. No photoluminescence signal was observed. However, photoluminescence was observed on both a 50 nm thin stainless steel layer and 50 μm by 50 μm square pillar (Lab-grade, 50 nm thick). In **Figure 4-9**, we show the photoluminescence signal of such stainless steel sample. Under excitation of 355 nm, the stainless steel exhibits a strong photoluminescence signal (similar spectra were observed for 420 nm and 266 nm excitation). Meanwhile, an array of 500 nm x 500 nm pillars (225 pillars, 50 nm high, fabricated at the same time and on the same sample substrate) showed no photoluminescence signal,

which indicates that the photoluminescence from a small stainless steel particle is probably too weak to be detected by our setup. By comparing the surface areas of the pillar array and the pillar, the photoluminescence emission intensity from the 500 nm pillars was estimated to be 1 photon per second. If we extend the estimation to 25 nm particles, we expect 1 photon per 25 hours.

Figure 4-9 Photoluminescence signal of stainless steel layer (area: $50\ \mu\text{m} \times 50\ \mu\text{m}$ and thickness: $50\ \text{nm}$) with excitation at $355\ \text{nm}$, power density: $142\ \text{W}/\text{cm}^2$. (a) hyperspectral image; (b) spectrum of the stainless steel.

The Q for all the inspected particles is summarized in the **Figure 4-10**. The Q for different sizes of particles is calculated according to **Eq. 4-2**, based on the conditions that the incident laser intensity is $200\ \text{W}/\text{cm}^2$ (estimated damage threshold of the reticle) at $420\ \text{nm}$, the photon counts for the system noise (including the photoluminescence signal from the reticle itself) is 20 photons/s. Considering the signal to noise ratio of 10, we can eliminate almost all the false positives during the inspection. Therefore, the signal from the particle reaching the detector needs to be 200 photons/s. The collection efficiency, and the average system transmission is taken as 0.004243 (based on $\text{NA}=0.13$), and 30%, based on the measurements used to produce **Figure 4-3**.

Figure 4-10 Yield Q distribution for the inspected particles. All the particles were inspected using 420 nm excitation except that part of the detected Al particles were inspected with 266 nm excitation.

Figure 4-10 clearly shows that the Q for the organic particles, at least over the limited size range available, scales roughly with the inverse square of particle size, while for the Al particles Q is very scattered. Note that all the organic particles that were targeted were also detected, while only about one third of the Al particles were detected. Based on the experimental data of the quantum yield-particle size relationship, we can estimate that it is possible to detect 25 nm organic particles (estimation is performed by putting the average measured Q value into the “minimum Q value required for detection” curve/formula and calculating the size). For the Al particles that emitted detectable photoluminescence, Q varied over 2 orders of magnitude. One possible explanation for the undetected Al particles is that the compositions for detected and undetected particle are slightly different, although they are all defined as Al particles. Different additives, such as C, Mg, Fe, appear in the Al particles, i.e. corresponding to different Al alloys. This might lead to different types of color centers and, therefore, different yields.

Chapter 4

The probability of detecting Al particles of 25 nm or smaller can be estimated by considering the color center density of the observed Al particles. The minimum number of color centers required to ensure that a particle is detected can be estimated from **Figure 4-10** and literature values for color center properties. Although emission cross sections for color centers varies over a wide range, aluminum and Mg-doped aluminum oxide color centers are rather well studied. For these aluminum oxides, the emission cross section is known to be in the range 10^{-17} - 10^{-18} cm².¹⁶ The average excitation photon flux is $Np \approx 4.24 \times 10^{20}$ cm⁻²/s. Therefore, assuming that all absorbed excitation photons result in emitted photons,^{16, 17} the photon flux per color center ranges from 400 to 4000 photons per second. Using the instrument transfer function above, we estimate that a single color center generates 0.5 to 5 detected photons per second. Therefore, the detected particles must have at least 40 color centers, given the current experimental setup (requires 200 photons/s). Examining the particle sizes and their Q , we note that the edge at which a particle may or may not exhibit photoluminescence is at a size of ~800 nm, and no particles smaller than 350 nm were detected. Assuming an oxide layer thickness of ~5 nm, the observed color center density can be estimated between 4×10^{15} /cm³ and 2×10^{16} /cm³, assuming a total of 40 color centers in the particle. A particle with size of 25 nm will have 0.12 to 0.024 color centers, therefore, statistically less than one out of 10 Al particles will contain one color center. If we only require a signal to noise ratio slightly larger than 1, slightly more than 2 color centers per particle are required, which corresponds to a particle size of 60 nm. Fundamentally, if the setup is improved so that it can detect a single color center, i.e., remove most of the background noise signal, the minimum particle size that is detectable is ~40 nm, based on our color center density estimation. However, the particle's metal core can strongly quench optical emission for polarizations that are parallel to the metal surface. It is, therefore, only possible for approximately half the color centers to emit efficiently in the direction of the collection optics (i.e., the minimum detectable size is ~80 nm). Returning to **Figure 4-10**, smaller particles are undetectable because they have too few color centers. For larger particles, however, compositional differences lead to a wide range of color center densities, which enable some particles to be detected, while

others remain undetectable. Using only the average value for Q and the minimum Q required for detection, it is estimated that the minimum detectable particle size for Al particles is found to be about 100 nm, which compares very well to the value derived from color center density estimates.

An in depth analysis of Q for stainless steel is not presented here. However, based on the data in **Figure 4-9**, a Q of 1.6×10^{-9} is obtained, which will lead to a minimum detectable size of 2 μm . This value, however, is an over estimate, since the array of pillars has a combined size of 7.5 μm .

The method presented here has the potential to be integrated into an EUVL system for *in situ* inspection. In order to reduce the total inspection time for a full EUV reticle, a 2D image of the photoluminescent particle was made—that is the integrated photoluminescence is recorded, instead of a hyperspectral image (a hyperspectral image can still be taken to determine the type of the particle by switching the detector). As an example of a heavily polluted reticle, **Figure 4-11** shows the dark-field image (image of the scattering of the incident light) of the reticle and contaminant particles, and the photoluminescence image of the reticle and particles. **Figure 4-11b** shows that light scattering from the reticle is entirely removed by a long pass filter, leaving only the photoluminescence spectrum from the particles. Comparing the images in the unpatterned area (red circles), it shows that photoluminescent imaging does not detect all particles. Importantly, however, some particles within the patterned area are clearly visible (yellow circle). As can be seen from **Figure 4-11b**, there is little-to-no photoluminescence signal from the reticle pattern, showing that the basic principle holds (see **Figure 4-12**).

Figure 4-11 Demonstration of the inspection concept with a real EUV reticle. Left picture: dark-field image of the reticle; right: fluorescence image of the reticle.

4.6 Conclusion

An inspection setup for EUV reticles, based on element specific photoluminescence of contaminant particles, has been designed, built, and characterized. Critical contaminant particles from the reticle of an EUVL system, like organic (hydrocarbon), Al, and stainless steel particles have been inspected. Organic particles with a size of 100 nm, i.e. the smallest available in this study, have been detected, while it is estimated that particles down to 25 nm are detectable. The smallest of the Al particles detected was 350 nm, while it is estimated that 100 nm particles can still be detected. Note that not all the Al particles larger than 350 nm can be detected. Stainless steel particles (100 nm to $\sim \mu\text{m}$) were not detected, but stainless steel coatings did exhibit detectable photoluminescence. And based on experimental data, we estimate that particles larger than $2 \mu\text{m}$ can be detected. To ensure the reliable functioning of such a particle inspection tool, the fundamentals of photoluminescence from contaminant metal nanoparticles should be

studied in more detail. For example, the particles on the EUV reticle will experience a short extreme UV exposure, in which the ionizing radiation is likely to induce color centers, increasing the possibility of the smaller particles to be detected.¹⁶ Finally, we note that, although the inspection method proposed here is for inspecting EUV reticles, it can be applied for detecting particle contamination on nano-imprint structures or templates.

Figure 4-12 The photoluminescence spectra comparison of a particle and reticle.

4.7 References

1. P. Zimmerman, "Double patterning lithography: double the trouble or double the fun?", SPIE Newsroom **20** (2009).
2. C. Wagner and N. Harned, "EUV lithography: Lithography gets extreme", Nature Photonics **4** (1), 24-26 (2010).
3. T. E. Madey, N. S. Faradzhev, B. V. Yakshinskiy and N. Edwards, "Surface phenomena related to mirror degradation in extreme ultraviolet (EUV) lithography", Applied Surface Science **253** (4), 1691-1708 (2006).

4. H. Meiling, N. Buzing, K. Cummings, N. Harned, B. Hultermans, R. de Jonge, B. Kessels, P. Kürz, S. Lok and M. Lowisch, "*EUVL system: Moving towards production*", SPIE Advanced Lithography, (2009).
5. M. Amemiya, K. Ota, T. Taguchi, T. Kamono, Y. Usui, T. Takikawa and O. Suga, "*Particle-free mask handling techniques and a dual-pod carrier*", SPIE Advanced Lithography, (2008).
6. M. Naka, S. Yamaguchi, M. Kadowaki, T. Koike, T. Hirano, M. Itoh, Y. Yamazaki, K. Terao, M. Hatakeyama and K. Watanabe, "*Capability of model EBEYE M for EUV mask production*", SPIE Photomask Technology, (2012).
7. K. Goldberg and I. Mochi, "*Wavelength-specific reflections: A decade of extreme ultraviolet actinic mask inspection research*", Journal of Vacuum Science & Technology B **28** (6), C6E1-C6E10 (2010).
8. T. H. Maiman, R. Hoskins, I. d'Haenens, C. Asawa and V. Evtuhov, "*Stimulated optical emission in fluorescent solids. II. Spectroscopy and stimulated emission in ruby*", Physical Review **123** (4), 1151 (1961).
9. Y. Wang, C. Ma, X. Sun and H. Li, "*Preparation and photoluminescence properties of organic-inorganic nanocomposite with a mesolamellar nickel oxide*", Microporous and Mesoporous Materials **71** (1), 99-102 (2004).
10. D. Liu, S. Clark and J. Robertson, "*Oxygen vacancy levels and electron transport in Al_2O_3* ", Applied physics letters. **96** (3), 032905 (2010).
11. L. Brock, K. Mishra, M. Raukas, W. P. Lapatovich and G. C. Wei, "*Color centers in magnesium doped polycrystalline alumina*", MRS Proceedings, (2001).
12. T. Perevalov, O. Tereshenko, V. Gritsenko, V. Pustovarov, A. Yelisseyev, C. Park, J. H. Han and C. Lee, "*Oxygen deficiency defects in amorphous Al_2O_3* ", Journal of Applied Physics **108** (1), 013501 (2010).
13. J. Carrasco Rodríguez, J. R. Gomes and F. Illas i Riera, "*Theoretical study of bulk and surface oxygen and aluminium vacancies in α - Al_2O_3* ", Physical Review B **69** (6), 064116 (2004).
14. B. D. Evans and M. Stapelbroek, "*Optical properties of the F^+ center in crystalline Al_2O_3* ", Physical Review B **18** (12), 7089 (1978).
15. M. V. Encinas, M. A. Rubio and E. Lissi, "*Quenching and photobleaching of excited polycyclic aromatic hydrocarbons by carbon tetrachloride and chloroform in micellar systems*", Photochemistry and Photobiology **37** (2), 125-130 (1983).
16. V. V. Ter-Mikirtychev and T. Tsuboi, "*Stable room-temperature tunable color center lasers and passive Q-switchers*", Progress in quantum electronics **20** (3), 219-268 (1996).

17. M. S. Akselrod, A. E. Akselrod, S. S. Orlov, S. Sanyal and T. H. Underwood, "*Fluorescent aluminum oxide crystals for volumetric optical data storage and imaging applications*", Journal of Fluorescence **13** (6), 503-511 (2003).

Chapter 5

EUV induced defects in few-layer graphene

We use Raman spectroscopy to show that exposing few-layer graphene to extreme ultraviolet (EUV, 13.5 nm) radiation, i.e. relatively low photon energy, results in an increasing density of defects. Furthermore, exposure to EUV radiation in a H₂ background increases the graphene dosage sensitivity, due to reactions caused by the EUV induced hydrogen plasma. X-ray photoelectron spectroscopy (XPS) results show that the sp² bonded carbon fraction decreases while the sp³ bonded carbon and oxide fraction increases with exposure dose. Our experimental results confirm that even in reducing environment oxidation is still one of the main sources of inducing defects.

5.1 Introduction

Graphene is a single planar sheet of sp² bonded carbon atoms which are closely packed in a honeycomb-like crystal structure. It is the basis of many carbon-based materials, e.g., stacked into graphite, rolled into carbon nanotubes or wrapped into buckyballs.¹⁻³ Graphene has unique physical properties, such as ballistic electronic transport, a tunable band gap, extremely high mobility, high elasticity, and electromechanical modulation.³⁻⁸ This makes graphene a promising material for many applications, including graphene transistors, electronic circuits, and solar cells, as well as other applications in biology and chemistry.³⁻⁸ However, one of the key requirements for such applications is the

control of defects, such as vacancies, dislocations or adatoms. The electronic properties of graphene are greatly affected by the presence of defects because they can act as scattering centers for electrons, reducing sheet conductivity.⁹ Defects associated with dangling bonds can enhance the chemical reactivity of graphene.^{10, 11} Likewise, the presence of defects reduces the thermal conductivity of graphene.¹²

The unique properties make graphene an attractive candidate for applications in radiation-rich environment. However the presence of defect may affect its performance. Therefore, it is critical to understand the radiation-induced damage in graphene. Zhou *et al*¹³, reported that soft x-rays can easily break the sp^2 bond structure and form defects in graphene that is weakly bound to the substrate. Hicks *et al*¹⁴ also studied multilayer graphene, grown on SiC, before and after 10 keV x-ray irradiation in air. They concluded that defects were generated due to surface etching by reactive oxygen species created by x-rays. In this paper, we focus on defect generation in graphene, induced by exposure to 13.5 nm (EUV) radiation under a variety of background conditions. We compare the rate at which defects are induced by EUV in a vacuum condition, and the rate at which defects are induced by exposure to EUV in a background of molecular hydrogen. We show that, defects are introduced in both cases, though at different rates. Surprisingly, our data also show that, even in a reducing environment, oxidation is still one of the main sources of EUV induced defects. The experimental results are important for illustrating the damage-creating mechanisms upon photon interaction as well as designing graphene-based components for EUV lithography systems.

5.2 Experimental

Graphene samples in this report were produced by the Graphene Supermarket. A few layers of graphene were grown on 25 x 25 mm² Ni/Si substrate with chemical vapor deposition method. The number of layers of graphene varies from 1 to 7, with an average of 4 over the sample. Three groups of experiments were performed: (1) a pristine sample served as a reference (refer to S_{ref}) and was not exposed; (2) a

sample was exposed to EUV irradiation (S_{EUV}) without molecular hydrogen in the background gas; (3) a sample was exposed to EUV irradiation in a 5×10^{-2} mbar H_2 background (S_{EUV+H_2}). The other experimental settings are summarized in **Table 5-1**. Graphene samples were irradiated by an EUV source (Philips EUV Alpha Source 2) with a repetition rate of 1 kHz and an average dose of 0.1 mJ/cm^2 per pulse. Raman spectra were collected with a home-built system. In this system, a 532 nm diode-pumped solid state laser is used to excite the samples with an illumination spot of $3.5 \times 0.1 \text{ mm}^2$ and a power density of 200 W/cm^2 . The collection efficiency of the detector system was calibrated using the HG-1 Mercury Argon Calibration Light Source and AvaLight-D(H)-S Deuterium-Halogen Light Source. 2D Raman intensity maps were acquired by collecting Raman signal over the central $2 \times 0.1 \text{ mm}^2$ area. The transverse distance between two data points was set to $500 \mu\text{m}$, and along the longitudinal direction, the data points were collected continuously. X-ray photoelectron spectroscopy (XPS) was measured by monochromatic Al-Kalpha, Thermo Fisher Theta probe with a footprint of 1mm diameter.

Table 5-1 Experimental settings summary. Two parameters vary among different experiments: Exposure time to EUV radiation and/or H_2 , hydrogen pressure.

Sample	S_{ref}	S_{EUV}	$S_{\text{EUV}+H_2}$
Exposure time [hr]	NA	8	8
H_2 pressure [mbar]	NA	0	5×10^{-2}
Chamber pressure[mbar]	NA	1×10^{-8}	1×10^{-8}

5.3 Results and discussion

5.3.1 Raman analysis

A typical Raman spectrum of graphene has three prominent features, i.e., D, G, and 2D peaks, located at 1350 cm^{-1} , 1580 cm^{-1} , and 2700 cm^{-1} , respectively. The G peak is a first order Raman scattering process,

corresponding to an in plane stretching of sp^2 bonds. The D band is due to the breathing modes of six-atom rings, and requires a defect for activation. The 2D peak is the second order of the D peak. Since the 2D originates from a process where momentum conservation is satisfied by two phonons with opposite wavevectors, defects are not required for their activation, and the 2D peak is, thus, always present.^{15, 16} **Figure 5-1** shows the Raman spectra of the three samples. There is a small D peak in the spectrum of pristine sample, which is caused by natural defects such as edges, grain boundaries, or vacancies in graphene produced by CVD.^{17, 18} The spectrum for the sample that was exposed to EUV irradiation shows slightly higher D peak intensities compared to the pristine sample. The energetic photons from EUV irradiation might be expected to break sp^2 carbon bonds, leading to defects in graphene as well. The spectrum for the sample exposed to EUV in a hydrogen background has the highest D peak intensity. Besides the direct impact from EUV photons, hydrogen is photo-ionized by the EUV radiation, resulting in atomic and molecular hydrogen ions, atomic hydrogen, and electrons.^{19, 20} Energetic electrons are known to break carbon bonds forming defects in graphene.^{21, 22} Furthermore, graphene hydrogenation occurs due to presence of a hydrogen plasma.²³ These combined effects lead to a higher defect density on the sample exposed to EUV in a hydrogen background. There is also a G peak shift from 1583 cm^{-1} for pristine sample to 1598 cm^{-1} for both S_{EUV} and S_{EUV+H_2} , indicating the formation of sp^2 clusters or chains.^{24, 25} Furthermore, there is another possible source for defects generation: secondary electrons from the Ni substrate, produced during EUV radiation. These electrons can be expected to have an energy less than 50 eV with a peak distribution between 2 and 5 eV.²⁶ These low energy electrons are not expected to create vacancy type defects. However, low energy electrons (7 eV) have been reported to dissociate adsorbed water and initiate oxide formation on metal surfaces.²⁷ This will be discussed in Chapter 7.

Figure 5-1 Comparison of the Raman spectra and the spectrum for the sample exposed to EUV in a hydrogen background has the highest D peak intensity. The spectra for the samples exposed to EUV irradiation show slightly lower D peak intensity. The pristine sample has the lowest D peak intensity. Note that the spectra are separated by an offset of 1×10^6 counts/s.

Besides the single spectrum comparison, 2D scans for the two samples S_{EUV} and S_{EUV+H2} were made to map the ratio of the D and G integrated intensities (shown in **Figure 5-2**). In **Figure 5-2**, the two samples S_{EUV} and S_{EUV+H2} were partially covered with a metal mask. The spatial intensity distribution of EUV light is indicated in **Figure 5-2(a)** and **(d)**. **Figure 5-2(c)** shows that S_{EUV+H2} has a higher D/G value, within exposed area, than that for S_{EUV} . It is also noted that for D/G ratio maps of the samples S_{EUV} and S_{EUV+H2} , there is a clear distinction between the exposed and unexposed areas. The D/G ratio map in **Figure 5-2(a)** clearly coincides with the EUV intensity profile shown in **Figure 5-2(b)**. The D/G ratio is also plotted as a function of EUV dose for both S_{EUV} and S_{EUV+H2} samples in **Figure 5-3(a)** and **(b)**. The D/G ratio first grows as the EUV intensity increases, then saturates. It appears that for S_{EUV} the D/G ratio does not saturate as the EUV dose increases. Note that the $I(D)/I(G)$ of S_{EUV} value is lower than the ratio of S_{EUV+H2} , indicating that it may saturate at higher values.

Figure 5-2 $I(D)/I(G)$ ratio mapping. (b) and (c) are $I(D)/I(G)$ ratio maps for S_{EUV} and S_{EUV+H2} . (a) and (d) are the EUV intensity profiles for S_{EUV} and S_{EUV+H2} , respectively. The white circle indicates the mask boundary.

Figure 5-3 $I(D)/I(G)$ ratio versus EUV. (a) The sample was exposed to EUV irradiation without molecular hydrogen in the background gas; (b) the sample was exposed to EUV irradiation in a 5×10^{-2} mbar H_2 background. Both exposure time was 10hrs.

5.3.2 XPS analysis

Quantitative information on the relative concentrations of different C bond types in the sample was obtained by analyzing the C1s peak of the XPS spectrum.^{28, 29} The curve fitting results for the C1s spectrum of

S_{EUV+H2} are shown in **Figure 5-4(a)**. There are four components in the C1s spectrum: the first peak at binding energy 283.4 eV, which is attributed to carbide formation with the underlying Ni layer, the second peak, at binding energy 284.4 eV, corresponds to the sp^2 bonds in graphitic like carbon, the third peak, at binding energy 285.3 eV, corresponds to carbon bonds with sp^3 hybridization, and the fourth peak, at binding energy 286.8 eV, is assigned to hydroxyl group. The appearance of sp^3 carbon and C-OH both indicate the generation of defects in graphene. Oxidation occurs when graphene reacts with the residual water during exposure. At the same time, oxidation will generate at least one sp^3 bond as well. The sp^3 bonds can also be introduced by hydrogen plasma generated under EUV irradiation.

Figure 5-4 (a) XPS analysis: curve fitting results for S_{EUV} ; (b) Element concentration versus EUV power for S_{EUV+H2} and S_{EUV} ; (c) and (d) Bond concentration change with respect to the pristine sample versus EUV power for S_{EUV} and S_{EUV+H2} .

In **Figure 5-4(b)**, for both the S_{EUV+H2} and S_{EUV} sample, we can see that C element (the sp^2 bonded carbon) concentration drops by 5%–9% and

O element concentration increases by 5%–8% compared with that in pristine sample. The concentration change of different bonds versus EUV power with respect to the pristine sample are plotted in Figs. 4(c) and 4(d). In the case of S_{EUV} , the sp^2 concentration decreases less in the higher power range than in the lower power ranges. It appears that under EUV irradiation, besides breaking sp^2 bonds and forming sp^3 and C-OH bonds, there is also a transformation from C-OH phase to sp^2 phase, since the C-OH concentration change drops to almost zero. This transformation can be induced by local heating due to EUV irradiation.³⁰ However, this transformation does not indicate that the converted sp^2 bonds are forming an ordered ring structure like in the undistorted graphene network, since, in the Raman spectrum, $I(D)/I(G)$ (Figure 5-4(a)) increases in higher EUV power range. In contrast, for S_{EUV+H_2} , the transformation to sp^2 is neglectable. Because hydrogenation can be the dominant effect, the converted sp^2 bonds will be hydrogenated in the end. Besides forming C-OH (oxidation), forming C-H bond (hydrogenation) will generate C-C (sp^3) bonds as well. The sp^3 concentration increases slowly at low intensities (lower than 0.5 W/cm^2) and saturates at higher powers, which coincide with the $I(D)/I(G)$ ratio map in Figure 5-4(b). However, comparing S_{EUV+H_2} with S_{EUV} , even with the same amount of sp^2 , sp^3 , and C-OH, they show different $I(D)/I(G)$ values, indicating that there is no unique quantitative relationship between $I(D)/I(G)$ ratio and sp^3 or C-OH content. The contribution from C-H or C-OH solely to $I(D)/I(G)$ has yet to be investigated. Nevertheless, the XPS data clearly show that the defects were generated by EUV photons, including hydrogenation, and oxidation even in a reducing environment (H_2).

5.4 Conclusions

The Raman results reported here show that there are defects induced in graphene after EUV irradiation, which is reflected by an increase of the D peak intensity. The defects are caused by breaking sp^2 bonds by EUV photons, oxidation due to the formation of OH groups, and hydrogenation due to hydrogen plasma generated during EUV irradiation. The XPS results confirm that, after EUV irradiation, the

concentration of sp^2 bonds in graphene decreases while the concentration of sp^3 bonds and C-OH bonds increases, clearly indicating defects generated in graphene. EUV irradiation introduces defects both through oxidation with the residual water background, and more effectively by hydrogenation due to the presence of hydrogen plasma.

5.5 References:

1. A. K. Geim and K. S. Novoselov, "*The rise of graphene*", Nature materials **6** (3), 183-191 (2007).
2. A. K. Geim, "*Graphene: status and prospects*", Science **324** (5934), 1530-1534 (2009).
3. K. Novoselov, D. Jiang, F. Schedin, T. Booth, V. Khotkevich, S. Morozov and A. Geim, "*Two-dimensional atomic crystals*", Proceedings of the National Academy of Sciences of the United States of America **102** (30), 10451-10453 (2005).
4. Y. Zhang, Y.-W. Tan, H. L. Stormer and P. Kim, "*Experimental observation of the quantum Hall effect and Berry's phase in graphene*", Nature **438** (7065), 201-204 (2005).
5. M. Y. Han, B. Özyilmaz, Y. Zhang and P. Kim, "*Energy band-gap engineering of graphene nanoribbons*", Physical Review Letters **98** (20), 206805 (2007).
6. K. I. Bolotin, K. Sikes, Z. Jiang, M. Klima, G. Fudenberg, J. Hone, P. Kim and H. Stormer, "*Ultrahigh electron mobility in suspended graphene*", Solid State Communications **146** (9), 351-355 (2008).
7. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", Science **321** (5887), 385-388 (2008).
8. J. S. Bunch, A. M. Van der Zande, S. S. Verbridge, I. W. Frank, D. M. Tanenbaum, J. M. Parpia, H. G. Craighead and P. L. McEuen, "*Electromechanical resonators from graphene sheets*", Science **315** (5811), 490-493 (2007).
9. D. W. Boukhvalov and M. I. Katsnelson, "*Chemical functionalization of graphene with defects*", Nano Letters **8** (12), 4373-4379 (2008).
10. A. Cortijo and M. A. Vozmediano, "*Effects of topological defects and local curvature on the electronic properties of planar graphene*", Nuclear Physics B **763** (3), 293-308 (2007).

11. G. Rutter, J. Crain, N. Guisinger, T. Li, P. First and J. Stroscio, "*Scattering and interference in epitaxial graphene*", *Science* **317** (5835), 219-222 (2007).
12. F. Hao, D. Fang and Z. Xu, "*Mechanical and thermal transport properties of graphene with defects*", *Applied Physics Letters* **99** (4), 041901 (2011).
13. S. Y. Zhou, C. O. Girit, A. Scholl, C. J. Jozwiak, D. A. Siegel, P. Yu, J. T. Robinson, F. Wang, A. Zettl and A. Lanzara, "*Instability of two-dimensional graphene: Breaking sp^2 bonds with soft x rays*", *Physical Review B* **80** (12), 121409 (2009).
14. J. Hicks, R. Arora, E. Kenyon, P. S. Chakraborty, H. Tinkey, J. Hankinson, C. Berger, W. A. de Heer, E. H. Conrad and J. D. Cressler, "*X-ray radiation effects in multilayer epitaxial graphene*", *Applied Physics Letters* **99** (23), 232102-232102 (2011).
15. A. C. Ferrari, "*Raman spectroscopy of graphene and graphite: Disorder, electron-phonon coupling, doping and nonadiabatic effects*", *Solid State Communications* **143** (1), 47-57 (2007).
16. A. C. Ferrari, J. C. Meyer, V. Scardaci, C. Casiraghi, M. Lazzeri, F. Mauri, S. Piscanec, D. Jiang, K. S. Novoselov and S. Roth, "*Raman spectrum of graphene and graphene layers*", *Physical Review Letters* **97**, 187401 (2006).
17. M. H. Gass, U. Bangert, A. L. Bleloch, P. Wang, R. R. Nair and A. K. Geim, "*Free-standing graphene at atomic resolution*", *Nature nanotechnology* **3** (11), 676-681 (2008).
18. A. Eckmann, A. Felten, A. Mishchenko, L. Britnell, R. Krupke, K. S. Novoselov and C. Casiraghi, "*Probing the nature of defects in graphene by Raman spectroscopy*", *Nano Letters* **12** (8), 3925-3930 (2012).
19. Y. M. Chung, E. M. Lee, T. Masuoka and J. A. R. Samson, "*Dissociative photoionization of H from 18 to 124 eV*", *The Journal of Chemical Physics* **99**, 885 (1993).
20. H. Kossmann, O. Schwarzkopf, B. Kmmerling and V. Schmidt, "*Unexpected behaviour of double photoionization in H_2* ", *Physical Review Letters* **63** (19), 2040-2043 (1989).
21. D. Teweldebrhan and A. A. Balandin, "*Modification of graphene properties due to electron-beam irradiation*", *Applied Physics Letters* **94** (1), 013101-013101 (2009).
22. M. Z. Iqbal, A. Kumar Singh, M. W. Iqbal, S. Seo and J. Eom, "*Effect of e-beam irradiation on graphene layer grown by chemical vapor deposition*", *Journal of Applied Physics* **111** (8), 084307-084307 (2012).
23. D. C. Elias, R. R. Nair, T. M. G. Mohiuddin, S. V. Morozov, P. Blake, M. P. Halsall, A. C. Ferrari, D. W. Boukhvalov, M. I. Katsnelson and A. K. Geim, "*Control of graphene's properties by reversible*

hydrogenation: evidence for graphane", Science **323** (5914), 610-613 (2009).

24. A. C. Ferrari and J. Robertson, "*Interpretation of Raman spectra of disordered and amorphous carbon*", Physical Review B **61** (20), 14095 (2000).

25. K. N. Kudin, B. Ozbas, H. C. Schniepp, R. K. Prud'Homme, I. A. Aksay and R. Car, "*Raman spectra of graphite oxide and functionalized graphene sheets*", Nano Letters **8** (1), 36-41 (2008).

26. J. J. Scholtz, D. Dijkkamp and R. W. A. Schmitz, "*Secondary electron emission properties*", Philips journal of research **50** (3), 375-389 (1996).

27. H. D. Ebinger and J. T. Yates, "*Electron-impact-induced oxidation of Al (111) in water vapor: Relation to the Cabrera-Mott mechanism*", Physical Review B **57** (3), 1976 (1998).

28. S. Kaciulis, "*Spectroscopy of carbon: from diamond to nitride films*", Surface and Interface Analysis **44**, 1155-1161 (2011).

29. P. Patsalas, M. Handrea, S. Logothetidis, M. Gioti, S. Kennou and W. Kautek, "*A complementary study of bonding and electronic structure of amorphous carbon films by electron spectroscopy and optical techniques*", Diamond and Related Materials **10** (3), 960-964 (2001).

30. A. Bagri, C. Mattevi, M. Acik, Y. J. Chabal, M. Chhowalla and V. B. Shenoy, "*Structural evolution during the reduction of chemically derived graphene oxide*", Nature Chemistry **2** (7), 581-587 (2010).

Chapter 6

Defects formation in single layer graphene under extreme ultraviolet irradiation

We study extreme ultraviolet (EUV) radiation induced defects in single-layer graphene. Two mechanisms for inducing defects in graphene were separately investigated: photon induced chemical reactions between graphene and background residual gases, and disrupting the network of sp^2 bonds, due to photon and/or photoelectrons induced bond cleaving. Raman spectroscopy shows that D peak intensities grow after EUV irradiation with increasing water partial pressure in the exposure chamber. Temperature-programmed desorption (TPD) experiments prove that EUV radiation results in water dissociation on the graphene surface. The oxidation of graphene, caused by water dissociation, is triggered by photon and/or photoelectron induced dissociation of water. Our studies show that the EUV photons cleave the sp^2 bonds, forming sp^3 bonds, leading to defects in graphene.

6.1 Introduction

Graphene, a two-dimensional hexagonal packed sheet of carbon atoms, has attracted a lot of attention from different research fields due to its unique physical and chemical properties.¹⁻⁸ Graphene can act as a diffusion barrier by providing physical separation between an

underlying substrate and reactant gases. Indeed, studies show that graphene is highly impermeable to gases.⁹ Furthermore, single-layer graphene is also highly transparent to light, which makes it a promising protection layer for optical devices, such as mirrors, lenses and screens.¹⁰ Additionally, graphene can be grown on large scales by chemical vapor deposition (CVD) and can be transferred to arbitrary substrate, making the range of potential applications very wide.¹¹

Graphene devices may be used in harsh environments e.g., space applications, soft x-ray systems and extreme ultraviolet (EUV) lithography systems. Since the light source of current EUV lithography systems operates at a wavelength of 13.5 nm, the optical system is in vacuum, but with a significant partial pressure of water. The physical and chemical stability of graphene in such an environment is of critical importance if it is to be used as a part of an optical component. Early experimental work showed that defects were generated in multilayer graphene after EUV exposure. And, even in a reducing environment, a small partial pressure of oxidizing agents (water) may cause oxidation.¹² The damage to graphene observed in our previous study was attributed to two possible effects: photo-induced chemistry between graphene and background residual gases, and breaking sp^2 bonds, due to EUV photon and/or photoelectron induced bond cleaving.

In this work, we investigate both of these possible EUV-induced damage mechanisms on CVD grown single layer graphene. In previous chapter, the oxidative damage to graphene was tentatively attributed to the presence of a reactive low density water plasma produced by EUV irradiation in the vicinity of graphene surface. But in ref¹², the amount of water (which was the main source of oxidative damage to graphene) adsorbed to the graphene surface was not controlled, nor was it possible to perform experiments without a substantial plasma-surface interaction. In this work, the influence of the EUV-induced water plasma is controlled in two different ways. In the first set of experiments, the partial pressure of water in the vacuum chamber was set by introducing water vapor into the interaction chamber. In the second set of experiments, water layers were deliberately deposited on a cold graphene surface (83 K). In the first set of experiments, the graphene is exposed to an EUV-induced plasma, which contains different

concentrations of water plasma. In the second set of experiments, the solid water layer can be ionized into much denser plasma under EUV irradiation. In addition, since this water layer is physisorbed onto the graphene surface, the reaction probability is much higher compared with that in the first set of experiments. By comparing the nature and density of defects induced in these two experiments, it is possible to determine the relative contribution of the EUV-induced plasma to the damage observed in graphene after exposure.

Finally, in a third set of experiments, naturally accumulated hydrocarbon contamination (~ 0.7 nm) on a graphene surface was used as a barrier layer between the residual water and graphene surface. In this way, it was possible to study the damage to graphene, while minimizing the reaction rate between graphene and water plasma.

In our experiments, the graphene was characterized using Raman spectroscopy, X-Ray photoelectron spectroscopy (XPS), and scanning electron microscopy (SEM), before and after exposure. The ratio of the D and G Raman spectral features is used as a measure of how well-ordered the graphene crystalline structure is, while XPS is used to determine the amount of oxidation. SEM was used to qualitatively compare the graphene layer completeness. The adsorbed water was examined using temperature-programmed desorption (TPD) spectroscopy to understand the water layer morphology, water-water, and water-graphene interactions.

6.2 Experiments

For the first and second sets of experiments, single layer graphene samples, obtained from Graphene Supermarket Inc., were grown on copper substrates by CVD and transferred to SiO_2/Si substrates. The substrate size was 10 mm x 10 mm with a 285 nm thick layer of SiO_2 . For the third set of experiments, single layer graphene samples on Cu substrates were purchased from Graphenea, which were stored in ambient condition for several months, leading to a layer of hydrocarbons about 0.7 nm thick on top of the graphene layer. For the

first and third sets of experiments, the graphene samples were exposed to EUV from a Xe plasma discharge source (Philips EUV Alpha Source 2) with a repetition rate of 500 Hz. The light source is filtered by a Si/Mo/Zr thin membrane filter to produce 13.5 nm (92 eV) light, with deep UV light less than 3%.^{13, 14} The EUV beam profile has a Gaussian distribution with FWHM= 3 mm. The EUV intensity at the sample surface was estimated to be 5 W/cm² with a dose of 10 mJ/cm² per pulse. The base pressure of the exposure chamber was 2x10⁻⁹ mbar (water partial pressure less than 2x10⁻⁹ mbar). For the second set of experiments, the graphene samples were exposed with EUV intensity of 0.05 W/cm², and the base pressure of the exposure chamber was 1x10⁻⁹ mbar.

All exposed samples were characterized using Raman spectroscopy, XPS, and SEM after exposure. Raman spectra were collected with a home-built system, based on a 532 nm solid state laser system and a Solar M266 spectrometer with a resolution of 1 cm⁻¹. The illumination intensity was set at 200 W/cm². The collection optics and pixel size of the detector result in a spatial resolution of 100x100 um². The collection efficiency of the detector system was calibrated using the HG-1 Mercury Argon Calibration Light Source and AvaLight-D(H)-S Deuterium-Halogen Light Source. XPS was measured by using a monochromatic Al-K α , Thermo Fisher Theta probe with a beam footprint of 1 mm diameter.

6.3 Results and discussion

6.3.1 Photo-induced plasma of the residual water

Four graphene samples (single layer graphene on SiO₂/Si substrate) were exposed to EUV for 30 min with various water partial pressures. One of the graphene samples was exposed without adding water into the chamber (water partial pressure less than 10⁻⁹ mbar), while another three samples were exposed with water partial pressures of 1x10⁻⁷ mbar, 1x10⁻

6 mbar, and 1×10^{-5} mbar, respectively. These four samples were kept at 289 K by backside cooling during the exposure. After exposure, all the samples were examined by Raman spectroscopy and XPS. A typical Raman spectrum of graphene has three prominent features i.e., D, G and 2D peaks, located at approximately 1350 cm^{-1} , 1580 cm^{-1} , and 2680 cm^{-1} . The G peak is a first order Raman scattering process, corresponding to an in plane stretching of sp^2 bonds. The D band is due to the breathing modes of six-atom rings, and requires a defect for activation. The ratio of $I(D)/I(G)$ is commonly used to quantify the defect density.¹⁵ **Figure 6-1(a)** shows the Raman spectra of the reference graphene sample (unexposed) and the exposed graphene samples. It clearly shows that the D peak height grows after exposure for all samples, indicating defect generation. Furthermore, the dependence of the $I(D)/I(G)$ ratio on water partial pressure is clearly indicated in **Figure 6-1(b)**.

Figure 6-1 (a) The Raman spectra of the graphene samples on SiO_2/Si substrate exposed to EUV under different water partial pressure. (b) The $I(D)/I(G)$ ratio as function of the water partial pressure. The x axis is in log scale.

Figure 6-2 (color online) (a) The curve fitting results of the XPS spectrum for the graphene samples on SiO₂/Si substrate exposed to EUV with water partial pressure of 1×10^{-5} mbar. The solid curve indicates the C1s peak while the four dot-dash curves are fitted curves. (b) The total carbon thickness of the exposed samples with various water partial pressures. Note that the unexposed sample has slightly hydrocarbon contamination on the s surface due to transport and storage in atmospheric conditions. The thickness is calculated based on the angle resolved XPS measurements assuming the carbon density of 2.1 g/cm^3 . The x axis is in log scale.

The Raman spectra, however, do not clearly show the source of the increased defect density. **Figure 6-2** shows the curve fit for the XPS spectrum of the C1s peak of the exposed sample. The four components of the C1s spectrum, corresponding to sp² bonds in graphitic like carbon (284.3 eV), sp³ hybridization (285.2 eV), hydroxyl (C-O) groups (286.1 eV), and carboxyl (C=O) groups (288 eV), are plotted separately for the exposed sample. The appearance of sp³, C-O, and C=O bonds can be attributed to photo-induced bond cleaving and photo-induced oxidation of graphene, due to presence of water. However, **Figure 6-2(b)** also shows that the total carbon thickness of the exposed samples increases, due to the well-known effect of hydrocarbon deposition during EUV exposure.¹⁶ The contribution of the deposited hydrocarbons to the XPS spectra makes a single interpretation of the data impossible, since the sp³, C-O, and C=O contributions can also come from the hydrocarbon contamination. Note that the EUV transmission will decrease by less than 1% due to 0.3 nm carbon contamination¹⁷, thus, the difference of EUV dose on graphene samples

is negligible, and cannot explain the differences between Raman spectra for the five samples.

6.3.2 Photo-induced plasma of the adsorbed water

In order to prevent hydrocarbon contamination, a layer of water was deliberately deposited on the graphene surface by dosing the surface with water while it was held at a temperature of 83 K. Directly before water dosing, the graphene sample was heated to 600 K to remove surface contamination, after which a calibrated surface coverage of water was adsorbed onto the sample. The water dose is expressed in Langmuir, with $1 \text{ L} = 1.33 \times 10^{-6} \text{ mbar}$.

Temperature-programmed desorption (TPD) spectroscopy was performed to investigate how water adsorbs on to the graphene surface. The graphene sample was heated at a rate of 0.5 K/s and water desorption was detected by a quadrupole mass spectrometer. To ensure that the signal is dominated by sample surface desorption, the entrance to the mass spectrometer consists of a cone that faces the sample surface. The cone has an entrance aperture of 4 mm, located approximately 2 mm from the graphene surface. The temperature was measured with a thermocouple pressed onto the sample with a molybdenum clamp. Since this clamp has a relatively good thermal contact with the cold finger of the manipulator, the measured temperature will underestimate the actual sample temperature.

In our experimental procedure, the graphene sample was dosed with water, and TPD spectroscopy was performed prior to EUV exposure. The sample was then re-dosed with water and exposed to EUV. A second TPD spectrum was obtained from the exposed water-graphene sample. Finally, the sample was dosed with water a third time and a third TPD was performed on the exposed graphene. This procedure was repeated three times on the same sample after EUV exposure of 10 min, 30 min, and 180 min respectively. The EUV intensity in this exposure

was estimated to be $100 \mu\text{J}/\text{cm}^2$, about 100 times lower than used in the first set of experiments.

Figure 6-3 Temperature-programmed desorption spectra for H_2O desorption on the graphene surface (a) TPD spectra for various H_2O doses; (b) TPD spectra of the graphene sample under different EUV exposure time with water dosing time of 1 L. The “after exposure” dash-line curve stands for the TPD spectrum collected after all three cumulative exposures have been completed. The total exposure time is 220 min. The heating rate is 0.5 K/s. The curves are manually offset to have the same background.

The TPD results are shown in **Figure 6-3(a)**. The spectra at low water dosages and high water dosages are markedly different, indicating that the structure of the adsorbed water is different, or evolves differently as function of both temperature and initial dose. As graphene (with certain hydrocarbon contamination) has a hydrophobic surface, water films tend to dewet upon heating. At low coverage, the water molecules form two-dimensional (2D) clusters. Water molecules at edges of these clusters have low coordination to other water molecules, such that their desorption energy is low, resulting in the desorption peak around 130 K.¹⁸⁻²⁰

However, as the coverage increases, water molecules can form 3D clusters of crystalline-ice like structure, resulting in a second peak at 134 K. The position (temperature) of this peak increases with coverage, while the leading edge remains similar. This is characteristic for zero-order desorption of water molecules from ice.^{19, 20} The rearrangement of the water suppresses the peak at 130 K for water doses above 3 L. At a

water dose of 5 L the 130 K peak disappears, which indicates that all water molecules form multilayers or 3D ice clusters. The TPD data from **Figure 6-3(a)** also indicates that water does not dissociate on adsorption to the graphene surface, thus, any water dissociation and resulting changes to the graphene are driven by EUV-induced processes as discussed in the following.

In **Figure 6-3**, the TPD spectra of water on graphene before and after exposure are shown for a water dose of 1 L. It is shown in **Figure 6-3(b)** that the spectra of the graphene sample after exposure exhibits lower peak intensities than that of before exposure. This indicates that the amount of water on the surface decreases due to EUV-induced desorption of water. Note that, aside from the decrease in the total amount of water on the graphene surface, a second TPD peak appears at higher temperature after 30 min of exposure. This second peak is likely due to the water layer rearranging itself during EUV exposure.

EUV photons with an energy of 92 eV can also cause water dissociation by direct photon excitation or by an indirect process involving secondary electrons emitted from the substrate. Many studies have shown that the indirect process, induced by secondary electrons, dominates over the direct photon excitation in the surface photochemistry.^{16, 21, 22} Therefore, direct EUV-dissociation can be neglected and the water molecules can be dissociated according to the following reactions:¹⁶

Upon dissociation, the reactive species can either desorb from the surface or react (mainly reactive oxygen species) with the graphene.

Figure 6-4(a) shows the Raman spectra of the graphene sample before and after EUV exposure with adsorbed water layer. Comparing these two spectra in **Figure 6-4(a)**, there is a clear D peak intensity increase at around 1350 cm⁻¹, which is attributed to the presence of defects in graphene. Previous work has shown that defects in graphene can be induced by EUV radiation¹², however, the shift of the G peak from

1585 cm^{-1} to 1595 cm^{-1} and of the 2D peak 2681 cm^{-1} to 2691 cm^{-1} , are usually interpreted as evidence of oxide doping.²³

Figure 6-4(b) shows the Raman spectra of samples exposed with and without water adsorbed on to the graphene surface. The two spectra differ in both the $I(D)/I(G)$ ratio and the spectrum fluorescence background. Clearly, the $I(D)/I(G)$ ratio of the sample exposed with water is much higher than that of the sample exposed without water, indicating more defects were generated in the former sample. The water layer adsorbed to the graphene surface will result in a very dense water plasma, and such a plasma should have a faster reaction rate than that of water plasma generated in the background residual gas. The large fluorescence signal in the sample exposed without water is attributed to hydrocarbon contamination.

Figure 6-4 (a) Raman spectra of the graphene sample before (pristine) and after EUV radiation with water adsorbed onto the sample (exposed). (b) Raman spectra of the samples exposed with or without water adsorbed onto graphene surface.

Figure 6-5 shows the curve fit for the C1s peak of the sample exposed to EUV with adsorbed water. The components of the C1s spectrum: sp^2 , sp^3 , C-O, and C=O, are plotted. The atomic concentration of each component and full width half maximum of the spectral components for the pristine sample, and samples exposed to EUV with and without adsorbed water are summarized in **Table 6-1**. The broadening of the sp^2 peak from 0.88 eV to 0.98 eV is usually evidence of a transition from a highly ordered graphite-like carbon to a less ordered carbon state, supporting the conclusion from the Raman results that the exposed

graphene has more defects. The changes in C-O and C=O concentrations are not significant, considering that the uncertainty in the atomic concentration is $\pm 2.5\%$. The C-O and C=O bonds are most likely to be due to residual poly (methyl meth acrylate), used during the transfer process, and clearly observed on all samples using SEM (see **Figure 6-6**).

Figure 6-5 (color online) The XPS spectra of the graphene sample exposed to EUV with adsorbed water onto graphene. The solid curve indicates the C1s peak while the four dot-dash curves are fitted curves.

From the SEM images in **Figure 6-6**, it is apparent that there is less PMMA on the graphene after exposure. Cracks and holes are also observed in the SEM images for the exposed samples, indicating an oxidative etching effect. We can see that the exposed graphene samples show more cracks and holes than the pristine sample. And these holes and cracks are predominantly along graphene grain boundaries, a phenomenon also observed for thermal oxidation of graphene.^{24, 25} The formation of C-O or C=O groups as a result of oxidation is due to fully dissociated water (e.g., atomic oxygen), or partially dissociated water (e.g., OH groups). The small holes in the pristine sample may come from the transfer process.

Table 6-1 Atomic concentration of C1s component, the total carbon thickness, and FWHM of the pristine sample, and samples exposed to EUV with and without adsorbed water. The total thickness is calculated based on the angle resolved XPS measurements assuming the carbon density of 2.1 g/cm^3 .

	C sp ² (at.%)	C sp ³ (at.%)	C-O (at.%)	C=O (at.%)	sp ² FWHM (eV)	Total thickness (nm)
Pristine (unexposed)	20.4	4.4	2.4	1.0	0.88	0.34
Exposed with adsorbed H ₂ O	19.3	2.7	2.4	1.1	0.98	0.30
Exposed without adsorbed H ₂ O	31.5	6.4	6.4	3.7	1.03	0.74

It is also noted that the total thickness of carbon in the exposed sample decreases, due to both the etching of graphene and the removal of PMMA. This can be seen in the XPS data in **Table 6-1**, where the concentration of the sp² and sp³ components decrease, while both the C-O and C=O contributions remain almost unchanged. Cleaved sp² bonds can either form sp³ bonds, or through oxidation form both sp³ bonds and C-O or C=O bonds. The combination of decreasing carbon, but increasing oxidation is indicative that the PMMA is preferentially removed. However, the unchanged sp³ and oxygen content (despite the disruption to the graphene and the overall removal of carbon) indicates that two competing processes are present. The removal of PMMA is compensated for by the oxidation of the graphene.

Figure 6-6 SEM images of the pristine sample, and the sample exposed to EUV with adsorbed water showing PMMA residue, cracks and holes. The PMMA appears as the darker patches in both images.

Defects in single layer graphene

Until now, we have shown that from Raman results, $I(D)/I(G)$ ratio grows as the water partial pressure increases, indicating more defects are forming in graphene. Together with the XPS data, it suggests that oxidation, triggered by the EUV radiation in the presence of water, results in the graphene being etched, forming cracks and holes, which is similar to the effect observed during thermal oxidation of graphene. In the case of EUV exposure, the oxidation process originates from the dissociation of water by EUV. However, to determine the relative contributions of EUV-induced oxidation and EUV-induced bond cleaving, the EUV-induced plasma must be separated from the graphene surface.

Figure 6-7 Raman spectrum after fluorescence background subtraction (a) and XPS results (b) for the reference sample of monolayer graphene on Cu substrate with naturally accumulated hydrocarbon contamination. The solid curve indicates the C1s peak while the four dot-dash curves are fitted curves.

6.3.3 Exposing graphene with hydrocarbon contamination

Samples of single layer graphene on Cu substrate with a hydrocarbon contamination layer were prepared. The hydrocarbon layer is used as barrier layer between the residual water and graphene surface. In this way, it was possible to study the damage to graphene, while minimizing the reaction rate between graphene and water plasma. Four graphene samples were exposed to EUV for 30 min with background gas conditions that should be either reducing or oxidizing. One of the graphene samples was exposed without modifying the background

gas (10^{-9} mbar, mostly water), a second sample was exposed in a water partial pressure of 1×10^{-5} mbar, a third was exposed in a hydrogen partial pressure of 1×10^{-5} mbar, and the last was exposed in an oxygen partial pressure of 1×10^{-5} mbar. All samples were kept at 289 K by backside cooling during the exposure.

Figure 6-7 shows the Raman spectrum and XPS results for an unexposed sample. From the Raman spectra, we can see that the single layer graphene is still visible after fluorescence background subtraction, despite the presence of hydrocarbon contamination. The XPS results clearly show that, in addition to the sp^2 contribution, there is a significant amount of sp^3 , C-O, and C=O, which is attributed to the presence of hydrocarbon. Assuming a density of 2.1 g/cm^3 , the hydrocarbon contamination layer was found to be about 0.7 nm thick from XPS measurement (see **Table 6-1**). This hydrocarbon layer acts as a barrier layer between the graphene and the background residual gases in the exposure chamber. In this way, reactions between the EUV-induced plasma and the graphene can be excluded. The dissociation of hydrocarbon to reactive H species by EUV irradiation is possible. However, an estimate of the rate indicates that, at maximum, the hydrogenation of graphene proceeds at a rate that is at least 6 times lower than the damage directly imparted by absorbed EUV radiation.

Figure 6-8 (a) Raman spectra for the reference and exposed graphene samples on Cu substrate with naturally accumulated hydrocarbon contamination. (b) XPS results for the graphene sample exposed to oxygen. The solid curve indicates the C1s peak while the four dot-dash curves are fitted curves.

Defects in single layer graphene

Figure 6-8(a) shows the Raman spectra of the reference (unexposed) and exposed graphene samples with naturally accumulated hydrocarbon contamination. It is noted that all the exposed samples show a clear D peak with approximately the same intensity. The G peak, however, is broadened due to a more disordered carbon network after exposure. Analysis is complicated by the fact that all samples, except the one exposed to oxygen, show an increase in hydrocarbon carbon (see **Table 6-2**), which contributes to, not only the broadening, but also the increased intensity of the G peak. In **Table 6-2**, it is also apparent that the sp^2 atomic concentration is greatly reduced after exposure, from 53.3 at.% to ~34.0 at.%, indicating that sp^2 bonds are being broken and sp^3 bonds are being formed. The C-O and C=O peaks are obviously more pronounced in the exposed samples shown in the XPS results in **Figure 6-8(b)** due to EUV induced oxidation of the covering hydrocarbon carbon layer.

Table 6-2 Atomic concentration and total carbon thickness of the reference and exposed graphene samples with naturally accumulated hydrocarbon contamination. The error margin of the data is ± 1 at. %.

	Reference	Exposed to background gas	Exposed to H ₂ O	Exposed to H ₂	Exposed to O ₂
C sp^2 (at.%)	53.3	34.0	36.3	36.2	35.7
C sp^3 (at.%)	10.0	13.0	10.6	11.0	10.1
C-O (at.%)	1.9	5.0	5.4	7.0	5.1
C=O (at.%)	2.0	11.2	8.6	6.7	6.4
O 1s (at.%)	13.0	22.8	23.2	22.8	23.9
Cu2p3 (at.%)	19.8	14.0	15.9	16.3	18.9
Total thickness (nm)	0.98	1.24	1.10	1.06	0.92

These results show that direct contact of the EUV-induced plasma and the graphene is not a necessary requirement for damage to graphene. The $I(D)/I(G)$ ratio (~ 0.2) found in **Figure 6-8** is much lower compared with the $I(D)/I(G)$ ratio (~ 1.9) found in **Figure 6-1** for the sample exposed to EUV with partial water pressure of 1×10^{-5} mbar, indicating that the hydrocarbon carbon layer is an effective barrier layer. In addition, in **Figure 6-8**, the $I(D)$ intensities are almost the same for all exposed samples, indicating that the process is largely independent of the background gases. Considering these facts, the induced defects are predominantly due to photon and/or photoelectron induced bond cleaving, rather than the EUV-induced plasma. The photoelectrons from the Cu substrate may play an important role in defect generation in graphene, since the Cu substrate has a relatively high photoelectron yield.²⁶ These photoelectrons may directly attribute to breaking the carbon sp^2 bonds and subsequent oxidation process.

It is important to note that the damage to graphene caused by plasma depends very strongly on the concentration and composition of the background gases, while, on the other hand, the damage to graphene caused by photon and photoelectron is only dependent on the photon flux. It is, therefore, impossible to determine the relative dominance of these two mechanisms, without specifying the background conditions, photon flux and even the type of substrate (photoelectron yield). Judging from the data in **Figure 6-8**, the contribution to $I(D)/I(G)$ from photon and photoelectrons is about 0.2. Considering the experimental results shown with **Figure 6-1** (where the $I(D)/I(G)$ is about 1.9), we can conclude that, in those experiments, EUV-induced plasma is the main source for the defect generation. This finding is reinforced by the fact that the photoelectron yield for the SiO_2 substrate is 0.001²⁷, much less than that from the Cu substrate, which is 0.1.²⁶

6.4 Conclusion

We have studied the damage mechanism of CVD grown single layer graphene under EUV irradiation. We found that the residual water in the vacuum chamber, EUV photons, and/or photoelectrons, all contribute to

defect generation in graphene during EUV exposure. The experimental data demonstrate that, under EUV radiation in the presence of water, defects were generated through oxidation, resulting in the graphene being etched, forming cracks and holes, which is similar to thermal oxidation of graphene. The oxidation process originates from the dissociation of water by EUV, and the fact that the EUV photons directly break the sp^2 bonds forming sp^3 bonds, which leads to defects in graphene. The photoelectrons emitted from the substrate can either cause oxidation via dissociating water molecules on the graphene surface, or directly break sp^2 bonds, both of which will induce defects in graphene. Our results help understand lifetime considerations for graphene devices in the presence of hard radiation. Furthermore, the EUV-induced oxidation of graphene provides a possible route to resist-free patterning of graphene.

6.5 Reference:

1. A. K. Geim and K. S. Novoselov, "*The rise of graphene*", Nature materials **6** (3), 183-191 (2007).
2. A. K. Geim, "*Graphene: status and prospects*", Science **324** (5934), 1530-1534 (2009).
3. K. Novoselov, D. Jiang, F. Schedin, T. Booth, V. Khotkevich, S. Morozov and A. Geim, "*Two-dimensional atomic crystals*", Proceedings of the National Academy of Sciences of the United States of America **102** (30), 10451-10453 (2005).
4. Y. Zhang, Y.-W. Tan, H. L. Stormer and P. Kim, "*Experimental observation of the quantum Hall effect and Berry's phase in graphene*", Nature **438** (7065), 201-204 (2005).
5. M. Y. Han, B. Özyilmaz, Y. Zhang and P. Kim, "*Energy band-gap engineering of graphene nanoribbons*", Physical Review Letters **98** (20), 206805 (2007).
6. K. I. Bolotin, K. Sikes, Z. Jiang, M. Klima, G. Fudenberg, J. Hone, P. Kim and H. Stormer, "*Ultrahigh electron mobility in suspended graphene*", Solid State Communications **146** (9), 351-355 (2008).
7. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", Science **321** (5887), 385-388 (2008).
8. J. S. Bunch, A. M. Van der Zande, S. S. Verbridge, I. W. Frank, D. M. Tanenbaum, J. M. Parpia, H. G. Craighead and P. L. McEuen,

"Electromechanical resonators from graphene sheets", Science **315** (5811), 490-493 (2007).

9. J. S. Bunch, S. S. Verbridge, J. S. Alden, A. M. van der Zande, J. M. Parpia, H. G. Craighead and P. L. McEuen, *"Impermeable atomic membranes from graphene sheets"*, Nano Letters **8** (8), 2458-2462 (2008).

10. R. Nair, P. Blake, A. Grigorenko, K. Novoselov, T. Booth, T. Stauber, N. Peres and A. Geim, *"Fine structure constant defines visual transparency of graphene"*, Science **320** (5881), 1308-1308 (2008).

11. A. Reina, X. Jia, J. Ho, D. Nezich, H. Son, V. Bulovic, M. S. Dresselhaus and J. Kong, *"Large area, few-layer graphene films on arbitrary substrates by chemical vapor deposition"*, Nano Letters **9** (1), 30-35 (2008).

12. A. Gao, P. J. Rizo, E. Zoethout, L. Scaccabarozzi, C. J. Lee, V. Banine and F. Bijkerk, *"Extreme ultraviolet induced defects on few-layer graphene"*, Journal of Applied Physics **114** (4), 044313-044313 (2013).

13. L. Sjmaenok, *"Nanoscale Multilayer Membranes as Optical Elements for EUVL"*, International Workshop on EUV and Soft X-Ray Sources, (2012).

14. V. Banine, *"Spectral Purity Filter Development for EUV HVM"*, EUVL Symposium, (2008).

15. A. C. Ferrari and D. M. Basko, *"Raman spectroscopy as a versatile tool for studying the properties of graphene"*, Nature nanotechnology **8** (4), 235-246 (2013).

16. T. E. Madey, N. S. Faradzhev, B. V. Yakshinskiy and N. Edwards, *"Surface phenomena related to mirror degradation in extreme ultraviolet (EUV) lithography"*, Applied Surface Science **253** (4), 1691-1708 (2006).

17. D. L. Windt, *"IMD—Software for modeling the optical properties of multilayer films"*, Computers in Physics **12**, 360 (1998).

18. R. Souda, *"Nanoconfinement Effects of Water on Hydrophilic and Hydrophobic Substrates at Cryogenic Temperatures"*, The Journal of Physical Chemistry C **116** (39), 20895-20901 (2012).

19. A. S. Bolina, A. J. Wolff and W. A. Brown, *"Reflection absorption infrared spectroscopy and temperature-programmed desorption studies of the adsorption and desorption of amorphous and crystalline water on a graphite surface"*, The Journal of Physical Chemistry B **109** (35), 16836-16845 (2005).

20. D. Chakarov and B. Kasemo, *"Photoinduced crystallization of amorphous ice films on graphite"*, Physical Review Letters **81**, 5181-5184 (1998).

21. K. Andersson, A. Nikitin, L. G. M. Pettersson, A. Nilsson and H. Ogasawara, "*Water dissociation on Ru (001): an activated process*", Physical Review Letters **93** (19), 196101 (2004).
22. X. L. Zhou, X. Y. Zhu and J. M. White, "*Photochemistry at adsorbate/metal interfaces*", Surface science reports **13** (3), 73-220 (1991).
23. N. Mitoma, R. Nouchi and K. Tanigaki, "*Photo-oxidation of Graphene in the Presence of Water*", The Journal of Physical Chemistry C **117** (3), 1453-1456 (2013).
24. L. Liu, S. Ryu, M. R. Tomasik, E. Stolyarova, N. Jung, M. S. Hybertsen, M. L. Steigerwald, L. E. Brus and G. W. Flynn, "*Graphene oxidation: thickness-dependent etching and strong chemical doping*", Nano Letters **8** (7), 1965-1970 (2008).
25. S. P. Surwade, Z. Li and H. Liu, "*Thermal Oxidation and Unwrinkling of Chemical Vapor Deposition-Grown Graphene*", The Journal of Physical Chemistry C **116** (38), 20600-20606 (2012).
26. V. Baglin, I. Collins and O. Gröbner, "*Photoelectron yield and photon reflectivity from candidate LHC vacuum chamber materials with implications to the vacuum chamber design*", CERN-LHC-Project-Report-206, (1998).
27. unpublished data

Chapter 7

Graphene defect formation by Extreme UV generated photoelectrons

We have studied the effect of photo-electrons on defect formation in graphene during EUV irradiation. Assuming the major role of these low energy electrons, we have mimicked the process by using low energy primary electrons. Graphene is irradiated by an electron beam with energy lower than 100 eV. After e-beam irradiation, it is found that the D peak, $I(D)$, appears in the Raman spectrum, indicating defect formation in graphene. The evolution of $I(D)/I(G)$ follows the amorphization trajectory with increasing irradiation dose, indicating that graphene goes through a transformation from microcrystalline to nanocrystalline and then further to amorphous carbon. Further, irradiation of graphene with increased water partial pressure does not significantly change the Raman spectra, which suggests that, in the extremely low energy range, e-beam induced chemical reactions between residual water and graphene is not the dominant mechanism driving defect formation in graphene. Single layer graphene, partially suspended over holes was irradiated with extreme ultraviolet (EUV, 92 eV) radiation. By comparing with the Raman results from e-beam irradiation, it is concluded that the photo-induced secondary electrons, especially those from the valence band, contribute to defect formation in graphene during irradiation.

7.1 Introduction

Graphene, a two-dimensional hexagonal packed sheet of carbon atoms, has attracted a lot of attention from different research fields due to its unique physical and chemical properties.¹⁻⁸ However, defects in graphene may substantially influence the performance of graphene-based devices and materials. Irradiation of graphene with energetic particles, such as electrons, ions or photons, is known to generate defects in graphene.⁹⁻¹⁶ In the case of electron irradiation, defect formation in graphene has been extensively studied using transmission electron microscopy (TEM).¹⁴ In these studies, the same electron beam is used both to irradiate and image graphene, therefore, formation of defects is monitored *in situ* at atomic resolution. The electron beam energy in TEM is typically higher than the carbon atom displacement threshold in the graphene structure (80-100 keV)¹⁷, leading to vacancy type defects.¹⁴ Electron irradiation of graphene with electron energies lower than the displacement threshold has also been reported. Iqbal and Teweldebrhan reported separately that defects appeared in graphene after irradiation with a 20 keV electron beam.^{11, 12} Furthermore, based on the evolution of D and G peak in Raman spectroscopy, they suggested that graphene went through a transition from crystalline to nanocrystalline and, finally, to amorphous carbon. Irradiation of graphene with energetic photons has also been studied, since graphene-based devices may be used in the presence of ionizing radiation.^{9, 10} Zhou reported that soft x-rays can easily break the sp^2 bond structure and form defects in graphene that is weakly bound to a substrate.¹⁰ In their study, exfoliated bi-layer graphene, partially suspended over a trench with a depth of a few micrometers, was also exposed to X-ray radiation. Their analysis showed very similar D peak intensities for the Raman spectra of both the suspended and unsuspended regions. Therefore, it was concluded that defect formation was intrinsic to the graphene and not relevant to the substrate or any gases trapped in the trench.

The above mentioned studies on the effects of irradiation on graphene are typically done with graphene on a substrate. The observed defect generation in graphene is usually attributed to the primary irradiation,

and the role of photo electrons, emitted from the substrate in response to the primary irradiation, has not been discussed in detail. However, in surface photochemistry, secondary electrons are considered to be the dominant factor responsible for surface processes.^{18, 19} In the study of Zhou and coworkers¹⁰ it was not possible to discuss the effect of the secondary electrons on defect generation in graphene in a quantitative way. This is because the secondary electron yield of the SiO₂ substrate is unknown.

In this letter, we study graphene defect generation due to direct exposure to electrons with energies that are typical for photoelectrons. Furthermore, by increasing the partial pressure of water in the chamber, we show that defects do not arise from electron-induced surface chemistry. By comparing the rate at which defects are generated by direct, low energy electrons and EUV generated electrons, we show that the photo-induced secondary electrons, especially those from the valence band, contribute to defect formation in graphene during irradiation.

7.2 Experiments

Single layer graphene samples were obtained from Graphene Master and Graphene Supermarket. In both cases, the graphene was grown by chemical vapor deposition on copper and transferred to a SiO₂/Si substrate with a 285 nm thick layer of SiO₂. The samples from Graphene Master were placed on a 5 mm square substrate that had a two dimensional array of holes etched into it. The diameter of the holes varied from 2 μ m to 5 μ m and had a depth of 300 nm, so that the transferred graphene was partially suspended. The samples from Graphene Supermarket were transferred to a 10 mm square, unstructured substrate for low energy electron beam studies.

EUV exposures were performed using radiation from a Xe plasma discharge source (Philips EUV Alpha Source 2) with a repetition rate of 1000 Hz. The light source is filtered by a Si/Mo/Zr thin membrane filter to produce 13.5 nm (92 eV) light.^{20, 21} The EUV beam profile has a

Gaussian distribution with full width half maximum of 3 mm. The peak EUV intensity at the sample surface was estimated to be 5 W/cm^2 with a dose of 5 mJ/cm^2 per pulse. The base pressure of the EUV exposure chamber was 1×10^{-8} mbar, which increases to 5×10^{-7} mbar during irradiation due to a small amount of Xe/Ar/N₂ gas mixture from the source chamber leaking into the exposure chamber.

E-beam irradiation was performed with an ELG-2/ EGPS-1022 electron gun (Kimball physics). The electron energy was varied from 3.7 eV to 80 eV, while the electron dose was controlled by varying the irradiation time and emission current. The distance between the electron gun and the grounded sample was approximately 25 mm. E-beam exposures were performed at a chamber base pressure of 5×10^{-9} mbar, which increased only when additional background gases were deliberately added.

Raman spectra were collected with both a commercial Raman microspectrometer system (Renishaw) with an excitation wavelength of 514 nm, a spot size of $1 \text{ }\mu\text{m}$ and an excitation power of 2.5 mW. A home-built Raman spectrometer, based on a 532 nm excitation wavelength, an illumination intensity of 200 W/cm^2 , and a spectrometer (Shamrock Solar M266) with a resolution of 1 cm^{-1} , was used to collect wide-area Raman maps. The collection optics and pixel size of the detector result in a spatial resolution of $100 \times 100 \text{ }\mu\text{m}^2$ and a field of view of $100 \text{ }\mu\text{m}$ by $1000 \text{ }\mu\text{m}$.

7.3 Results and Discussion

Figure 7-1(a) shows the optical image of single layer graphene partially suspended on the SiO₂/Si substrate. The Raman spectra for the graphene suspended and supported regions before EUV irradiation are shown in **Figure 7-1(b)**. The $I(2D)/I(G)$ is about 4, and the full width of the 2D peak is about 30 cm^{-1} , confirming that the graphene is single layer. After EUV irradiation, the Raman spectra for the graphene suspended and supported regions are plotted in **Figure 7-1(c)**. It is clearly shown that in both regions, a D peak, and a fluorescence background appear. The

latter is due to EUV induced carbon contamination.²² The two spectra have approximately the same $I(D)$ but differ in the fluorescence background from 1800 cm^{-1} and higher wavenumbers. For the graphene on a substrate, there is fluorescence from hydrocarbon adsorbed on both sides of graphene. However, for the suspended sample, there is an additional signal from hydrocarbon at the bottom surface of the hole as well as signal from around the edges of the diffraction-limited spot (a ring that appears to have originated from the diffraction-limited spot at the graphene surface from the point of view of the microscope image plane). This can lead to an enhancement of the fluorescence background of about 2.4 times. The same $I(D)$ indicates that the defect density is the same in both suspended and supported regions.

The experimental results here give rise to an interesting conclusion: either the secondary electrons emitted from the substrate do not generate any defects in graphene, or the secondary electrons emitted from both regions (graphene on SiO_2 graphene suspended over Si) result in the same defect density in graphene, despite having vastly different secondary electron yields. It is likely that the secondary electrons, which typically have an energy spectrum with a maximum near the work function of the material (<10 eV) from which they are emitted, do not have sufficient energy to generate defects in graphene.

The photoelectron energy spectrum from Si with native oxide starts at around 2 eV and is sharply peaked at around 2.5 eV, with a full width half maximum of 0.86 eV. At higher energies, the photoelectron yield decays exponentially. Electrons with energies above 20 eV are rarely emitted with an exception at 80-85 eV, corresponding to emission directly from the valence band. The flux of electrons within the energy range of 80-85 eV is approximately 3% of the total dose. To test if secondary electrons can damage graphene, graphene samples were irradiated using the low energy electron gun. **Figure 7-2** shows the Raman spectra of graphene on an unstructured SiO_2/Si after irradiation of electrons with different energies. In **Figure 7-2(a)**, where the electron dose is about $1 \times 10^{17} \text{ cm}^{-2}$, the Raman spectra of the irradiated graphene samples are almost identical to the unirradiated samples, with no clear D peak. This indicates that no detectable defects were generated in graphene during e-beam irradiation. However, as the electron dose

Chapter 7

increases to $1 \times 10^{18} \text{ cm}^{-2}$, and beyond, as shown in **Figure 7-2(b)**, all the irradiated samples show a relatively small but clear D peak in their Raman spectra, confirming defect formation in graphene during irradiation.

Figure 7-1 (a) top, optical image of graphene partially suspended on the holes on SiO₂/Si substrate. The darker purple area indicates where the graphene is. The scale bar in the image is 20 μm. (b) middle, the Raman spectra for the graphene suspended and supported regions before EUV irradiation. (c) bottom, right, Raman spectra for the graphene suspended on a 4 μm hole and supported regions after irradiation. All the Raman spectra have been normalized.

Figure 7-2 Raman spectra of graphene on SiO₂/Si (no holes, all graphene supported on SiO₂) irradiated with different e-beam energies. The electron dose (a) $1 \times 10^{17} \text{ cm}^{-2}$, and (b) $1 \times 10^{18} \text{ cm}^{-2}$ (except for 3.7 eV and 5 eV, which is $1 \times 10^{19} \text{ cm}^{-2}$).

Figure 7-3 (a) Raman spectra for graphene samples on SiO_2/Si (no holes, all graphene supported on SiO_2) irradiated under different dosages of electrons with energy of 80 eV. (b) $I(D)/I(G)$ ratio versus the electrons dose. (c) $I(D)/I(G)$ ratio versus the electron energy times electron dose.

Graphene samples irradiated by electrons with an energy of 80 eV were also examined. The secondary electron energy spectrum of Si has a small peak at 80 eV, due to photo-emission from the valence band. As a

result, the secondary electron flux at 80 eV is much greater than the flux at energies between 80 and 20 eV and should be investigated. The Raman spectra of the irradiated samples are shown in Figure 7-3(a). From the Raman spectra, it can be seen that a D peak appears, even at very low dose, indicating 80 eV electrons generate defects in graphene more efficiently. The $I(D)/I(G)$ ratio as a function of the electron dose is plotted in **Figure 7-3(b)**. The $I(D)/I(G)$ ratio first increases to a maximum and then falls with increasing electron dose. This behavior follows the amorphization trajectory in irradiated carbon material proposed by Ferrari.²³ Electrons first cause local defects in graphene, reducing the long-range order. Thus (micro) crystalline graphene transforms to nanocrystalline graphene. As the defects accumulate, the nanocrystalline graphene becomes more disordered, until it must be considered to be amorphous sp^2 carbon. Note that the $I(D)/I(G)$ ratio as a function of dose for 5 eV electrons is also plotted in **Figure 7-3(b)** and appears to be following the same trajectory, though requiring a larger dose. It should also be noted, however, that the damage is not simply a function of the energy deposited in the sample, as can be seen in **Figure 7-3(c)**.

The presence of residual water vapor in the vacuum chamber is known to result in graphene oxidation when exposed to 100 keV electron irradiation.^{14, 24} It is, therefore, possible, that the observed increase in defects is due to electron-induced chemistry. To test this, graphene was irradiated with 20 eV and 40 eV electrons at two different background water partial pressures. Under normal operating conditions, the main residual gas in the chamber is water, at a maximum pressure of 5×10^{-9} mbar (in reality it is less, since this is the total chamber pressure). The background water pressure was increased by leaking water into the chamber until the pressure was 2.2×10^{-8} mbar. Note that higher pressures cannot be used because the electron gun only works at pressures below 1×10^{-7} mbar. **Figure 7-4** shows the Raman spectra of the graphene samples irradiated by 20 eV and 40 eV electrons at two different chamber pressures. The spectra are almost identical, meaning that, in the extremely low energy range of electron irradiation, the electron flux does not initiate chemical reactions between residual water and graphene at a measurable rate. Therefore, oxidation is not the

dominant mechanism for defect formation in graphene. Yuzvinsky et al also reported that electron beam induced damage to carbon nanotube was closely related with the water partial pressure.²⁴ In their experiments, no damage was observed for experiments with water partial pressure below 2×10^{-6} Torr with electron energy of 1 keV. Furthermore, in **Figure 7-2(b)** it is shown that irradiation with 3.7 eV electrons is sufficient to initiate defects in graphene, which is lower than the bond energy of O-H bonds in water (about 4.8 eV) and the ionization energy of water (about 12.6 eV).²⁵

Figure 7-4 Raman spectra for graphene on SiO₂/Si irradiated by 20 and 40 eV in different vacuum conditions.

As mentioned in the introduction, vacancy type defects in graphene, require an electron energy of 80-100 keV. It is also reported that the Stone-Wales type of defect requires an electron energy of approximately 25 keV.¹⁷ Since the energy of electrons in this study is far below these values, neither vacancy nor Stone- Wales type of defects are expected here. Krauss *et al* reported disassembly of a graphene single crystal into a nanocrystalline network induced by 488 nm (2.54 eV) laser irradiation.²⁶ They concluded that the disassembly process is due to two-photon induced breaking of sp² carbon-carbon bonds. The bond enthalpy for carbon-carbon single bond and double bonds is 3.6 eV and 6.14 eV separately.²⁵ The carbon single bond energy is about the same

as the lowest electron beam energy in our experiments. We conclude, therefore, that defects are due to breaking sp^2 and, thus, forming sp^3 bonds. As a result, smaller sub-crystal structures form (nanocrystalline graphene).

Now it is possible to explain the results in **Figure 7-1**. The secondary electron yield under EUV (92 eV) irradiation from a Si surface with native oxide is about 0.017 electrons/photon.²⁷ Although there is no published data on the secondary electron yield from SiO_2 , it was estimated to be 0.001.²⁸ The secondary electron energy spectrum from Si starts at around 2 eV and is sharply peaked at around 2.5 eV, with a full width half maximum of 0.86 eV. At higher energies, the secondary electron yield decays exponentially. Electrons with energies above 20 eV are rarely emitted with an exception at 80-85 eV, corresponding to emission directly from the valence band. The flux of electrons within the energy range of 80-85 eV is approximately 3% of the total dose. For 30 min exposure with an EUV intensity of 5 W/cm², the total dose of secondary electrons ejected from the silicon surface is about 1×10^{19} cm⁻², and from SiO_2 surface is 6×10^{17} cm⁻² (assuming the yield is 0.001). According to the data in **Figure 7-2** and **Figure 7-3**, the graphene sitting directly on the SiO_2 substrate is exposed to an electron dose which is unlikely to lead to a detectable D peak with an exception of the valence band electrons with energy at around 80 eV, which will contribute an $I(D)/I(G)$ of 0.15 (see supplementary material). On the other hand, the high secondary electron yield of the Si surface should result in an increase in defects (corresponding to an increase of $I(D)/I(G) \approx 1.2$ relative to the unsuspended graphene. Yet, this is not observed.

A possible explanation is that the flux of secondary electrons to the graphene is reduced by the experimental conditions. It has been shown that graphene, suspended over trenches and holes, is able to trap gas at atmospheric pressure.²⁹ The graphene membrane was transferred onto the SiO_2 substrate under atmospheric conditions, therefore, it is possible that the pressure in the hole is approximately 1 bar. Under these conditions, the secondary electrons are likely to scatter given the fact that its mean free path is comparable with the height of the hole. From the Raman spectra in **Figure 7-1**, we also observed that the fluorescence

background, due to amorphous carbon deposition (on graphene and/or Si), was substantially stronger in the suspended regions. This indicates that an amorphous carbon layer may be shielding the graphene from the secondary electron flux.

It is also interesting to compare our observations to those from electron and EUV irradiation of other surfaces, such as ruthenium.¹⁸ In the case of metals, the dominant form of degradation is due to oxidation (provided residual hydrocarbons are under control). Published data show that the low energy secondary electrons are primarily responsible for the dissociation of water, leading to the surface and subsurface oxidizing.¹⁸ This is in stark contrast to our results, which indicate that the secondary electrons do not promote oxidation, and that the graphene damage is limited to direct processes, such as sp^2 bond breaking.

7.4 Conclusion

We have studied the effect of secondary electrons from a substrate on defect formation in graphene during EUV irradiation. Experiments show that extremely low (80 eV) energy electrons will lead to defect formation in graphene if it is irradiated with sufficient dose. The electrons excited directly from the valence band are more efficient in defect formation than the secondary electrons. The process of the damage to graphene follows the amorphization trajectory with increasing irradiation dose, indicating that graphene goes through a transformation to nanocrystalline and then further to amorphous carbon. Furthermore, irradiation of graphene with different water partial pressures show similar Raman spectra, which suggests that, in the extremely low energy range, e-beam induced chemical reactions between residual water and graphene is not the dominant effect in defect formation in graphene. These results indicate a different degradation process compared to the EUV induced oxidation of metallic surfaces, namely photo-induced electrons break sp^2 bonds and, thus, lead to graphene degradation during EUV radiation. These findings are of relevance for protective top layers on EUV reflecting mirrors in applications, such as EUV photolithography.

7.5 Reference

1. A. K. Geim and K. S. Novoselov, "*The rise of graphene*", Nature materials **6** (3), 183-191 (2007).
2. A. K. Geim, "*Graphene: status and prospects*", Science **324** (5934), 1530-1534 (2009).
3. K. Novoselov, D. Jiang, F. Schedin, T. Booth, V. Khotkevich, S. Morozov and A. Geim, "*Two-dimensional atomic crystals*", Proceedings of the National Academy of Sciences of the United States of America **102** (30), 10451-10453 (2005).
4. Y. Zhang, Y.-W. Tan, H. L. Stormer and P. Kim, "*Experimental observation of the quantum Hall effect and Berry's phase in graphene*", Nature **438** (7065), 201-204 (2005).
5. M. Y. Han, B. Özyilmaz, Y. Zhang and P. Kim, "*Energy band-gap engineering of graphene nanoribbons*", Physical Review Letters **98** (20), 206805 (2007).
6. K. I. Bolotin, K. Sikes, Z. Jiang, M. Klima, G. Fudenberg, J. Hone, P. Kim and H. Stormer, "*Ultrahigh electron mobility in suspended graphene*", Solid State Communications **146** (9), 351-355 (2008).
7. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", Science **321** (5887), 385-388 (2008).
8. J. S. Bunch, A. M. Van der Zande, S. S. Verbridge, I. W. Frank, D. M. Tanenbaum, J. M. Parpia, H. G. Craighead and P. L. McEuen, "*Electromechanical resonators from graphene sheets*", Science **315** (5811), 490-493 (2007).
9. A. Gao, P. J. Rizo, E. Zoethout, L. Scaccabarozzi, C. J. Lee, V. Banine and F. Bijkerk, "*Extreme ultraviolet induced defects on few-layer graphene*", Journal of Applied Physics **114** (4), 044313-044313 (2013).
10. S. Y. Zhou, C. O. Girit, A. Scholl, C. J. Jozwiak, D. A. Siegel, P. Yu, J. T. Robinson, F. Wang, A. Zettl and A. Lanzara, "*Instability of two-dimensional graphene: Breaking sp^2 bonds with soft x rays*", Physical Review B **80** (12), 121409 (2009).
11. D. Teweldebrhan and A. A. Balandin, "*Modification of graphene properties due to electron-beam irradiation*", Applied Physics Letters **94** (1), 013101-013101 (2009).
12. M. Z. Iqbal, A. Kumar Singh, M. W. Iqbal, S. Seo and J. Eom, "*Effect of e-beam irradiation on graphene layer grown by chemical vapor deposition*", Journal of Applied Physics **111** (8), 084307-084307 (2012).

13. M. Xu, D. Fujita and N. Hanagata, "*Monitoring electron-beam irradiation effects on graphenes by temporal Auger electron spectroscopy*", *Nanotechnology* **21** (26), 265705 (2010).
14. J. C. Meyer, F. Eder, S. Kurasch, V. Skakalova, J. Kotakoski, H. J. Park, S. Roth, A. Chuvilin, S. Eychen, G. Benner, A. Krashennnikov and U. Kaiser, "*Accurate measurement of electron beam induced displacement cross sections for single-layer graphene*", *Physical Review Letters* **108** (19), 196102 (2012).
15. L. Tao, C. Qiu, F. Yu, H. Yang, M. Chen, G. Wang and L. Sun, "*Modification on Single-Layer Graphene Induced by Low-Energy Electron-Beam Irradiation*", *The Journal of Physical Chemistry C* **117** (19), 10079-10085 (2013).
16. M. M. Lucchese, F. Stavale, E. H. Ferreira, C. Vilani, M. V. O. Moutinho, R. B. Capaz, C. A. Achete and A. Jorio, "*Quantifying ion-induced defects and Raman relaxation length in graphene*", *Carbon* **48** (5), 1592-1597 (2010).
17. F. Banhart, J. Kotakoski and A. V. Krashennnikov, "*Structural defects in graphene*", *ACS nano* **5** (1), 26-41 (2010).
18. T. E. Madey, N. S. Faradzhev, B. V. Yakshinskiy and N. Edwards, "*Surface phenomena related to mirror degradation in extreme ultraviolet (EUV) lithography*", *Applied Surface Science* **253** (4), 1691-1708 (2006).
19. X. L. Zhou, X. Y. Zhu and J. M. White, "*Photochemistry at adsorbate/metal interfaces*", *Surface science reports* **13** (3), 73-220 (1991).
20. L. Sjmaenok, "*Nanoscale Multilayer Membranes as Optical Elements for EUVL*", *International Workshop on EUV and Soft X-Ray Sources*, (2012).
21. V. Banine, "*Spectral Purity Filter Development for EUV HVM*", *EUVL Symposium*, (2008).
22. D. L. Windt, "*IMD—Software for modeling the optical properties of multilayer films*", *Computers in Physics* **12**, 360 (1998).
23. A. C. Ferrari and J. Robertson, "*Interpretation of Raman spectra of disordered and amorphous carbon*", *Physical Review B* **61** (20), 14095 (2000).
24. T. D. Yuzvinsky, A. M. Fennimore, W. Mickelson, C. Esquivias and A. Zettl, "*Precision cutting of nanotubes with a low-energy electron beam*", *Applied Physics Letters* **86** (5), 053109 (2005).
25. <http://webbook.nist.gov/>.
26. B. Krauss, T. Lohmann, D. H. Chae, M. Haluska, K. von Klitzing and J. H. Smet, "*Laser-induced disassembly of a graphene single crystal into a nanocrystalline network*", *Physical Review B* **79** (16), 165428 (2009).

27. Personal communication with Dr. Boris Yakshinskiy, Rutgers University
28. unpublished data
29. A. L. Kitt, Z. Qi, S. Remi, H. S. Park, A. K. Swan and B. B. Goldberg, "*How graphene slides: measurement and theory of strain-dependent frictional forces between graphene and SiO₂*", Nano Letters **13** (6), 2605-2610 (2013).

Chapter 8 Valorization

In this thesis, we have explored a novel EUV reticle inspection method, and a material candidate for an EUV pellicle, both of which could be applied in EUVL systems. In section 8.1, we will discuss how the photoluminescence-based inspection method described in Chapter 4 can be used as an *in situ* inspection technique in EUVL. In section 8.2, based on the experimental results from graphene exposed to EUV irradiation discussed in Chapter 5-7, we will present the recommended future work towards making an adequate EUV pellicle based on graphene.

8.1 Inspection of EUV reticles

In Chapter 4, we proposed an inspection method based on the photoluminescence characteristics of contaminant particles on EUV reticles. A feasibility study was conducted in the research department of ASML. The requirements for inspection of EUV reticles are proposed by ASML, together with one of its customers (**Table 8-1**). We particularly focused on the investigation to identify the minimum particle size which can be detected with our method. An inspection setup was designed and built to investigate the photoluminescence characteristics of contaminant particles. This inspection method can be potentially applied as Reticle Inspection Module (RIM) in EUVL systems. A concept of implementation of such an inspection module is illustrated in **Figure 8-1**.

Figure 8-1 Schematic view of the proposed Reticle Inspection Module in an EUVL system. Filters are included in the collection optics.

This inspection module is based on our inspection setup with the major change of using only one CCD camera to capture the photoluminescence signal from the contaminant particles. Based on our experimental results, the excitation laser is chosen to be 420 nm with a maximum power of 200 W/cm². A configuration with an EMCCD (Electron Multiplying Charge Coupled Device) camera is also possible, but is not required. An example of the working principle of such an inspection module is shown in Chapter 4.

Table 8-1 Requirements for particle inspection on EUV reticles.

Item	Requirements
Minimum detectable particle size on reticle	25 nm for 22 nm node
Total inspection time	< 60 min
Probability of detecting min. particle	>0.99
# false positives per reticle	1/10
Reflectivity loss of reticle	< 1% within lifetime

We have analyzed the critical contaminant particles from a real exposed EUV reticle, composed of organics (hydrocarbons), Al, and stainless steel. It is estimated that 25 nm organic particles and 100 nm Al particles could be detected. However, not all the particles categorized as Al particle could be detected. For stainless steel particles,

photoluminescence has been detected with coating $50\text{ }\mu\text{m} \times 50\text{ }\mu\text{m}$, 50 nm thick. Based on the photoluminescence yield, the estimated minimum detectable size is about $2\text{ }\mu\text{m}$. An increase of emission intensity for both Al and steel particles is required to meet the inspection requirements. For Al particles, within the size range of interest, the color center doping density may play a critical role for its photoluminescence signal. Electron or γ radiation could introduce color centers in Al_2O_3 , but this needs further investigation. For stainless steel particles, further studies are required to either introduce emission centers within the particle or to label the particles with fluorescent dyes.

Figure 8-2 Proposed Reticle Inspection Module, based on a combination of diffractive filtering and photoluminescence.

In Chapter 1, we described a method based on light scattering for inspection of particles on reticles with periodic structures. We can combine this inspection method with the photoluminescence method. A proposal has been shown in **Figure 8-2**. A dichroic mirror is used to split the reflected (diffracted) light and the photoluminescence emission. Two extra spectral filters are used to further suppress the residual reflection and photoemission, respectively. Two separate images, from scattered light and photoluminescence signals, are recorded simultaneously. Although combining these two techniques in a single setup enables our inspection module to detect particles with smaller

sizes on periodically patterned reticles, this still needs further improvement to detect 25 nm particles on reticles with arbitrary patterns.

8.2 Pellicle for the EUV reticle

Pellicles are widely used to prevent particles from depositing on the reticle in visible and deep UV lithography. However, a pellicle has to fulfill several critical requirements, listed in **Table 8-2**, which makes the development of a pellicle for EUV reticles very challenging. The requirements put limits on the mechanical, chemical, and thermal properties of the pellicle materials.

Table 8-2 *Proposed requirements for an EUV pellicle.*

	Item	Requirements
Material requirements	EUV transmission	90% for single pass
	Size	110 x142 mm ²
	EUV power at reticle	5 W/cm ² (250 W source)
	Lifetime	315 hrs
	Max. acceleration	100 m/s ²
Imaging requirements	EUV transmission spatial non-uniformity	<0.2% at reticle
	EUV transmission angular non-uniformity	< 300 mrad of local pellicle angle
Pellicle + frame requirements	Stand-off distance	<2.5mm (including tolerances and sagging)
	Max. pressure changing rate	3.5 mbar/s (peak during pump-down)

In this study, we focused on the lifetime of graphene based pellicles. Our experimental results show that defects appear in graphene after exposure to EUV. The influence of defects on the physical and chemical properties that make graphene promising for use as an EUV pellicle is still under investigation. Water plasma induced by EUV leads to holes and cracks in graphene membranes, which may cause potential EUV transmission non-uniformity, or, even worse, result in particles flying

through the pellicle. This indicates that graphene pellicles may require protection or sacrificial layers.

Figure 8-3 (a) schematic of a nano-indentation measurement. (b) a force-deflection curve of such measurement.

The mechanical properties of graphene membranes under EUV irradiation is not understood yet. The mechanical properties of free-standing graphene films can be probed by nano-indentation with an AFM, as illustrated in **Figure 8-3(a)**. The test is performed by pressing the AFM tip against the center of a graphene membrane while recording the applied force and deflection of the membrane. The force-deflection data are then processed to determine the elastic properties of the graphene membrane (**Figure 8-3(b)**). The force-deflection data is fit using **Eq. 8-1** as described in Ref.¹

$$F = \sigma^{2D} (\pi a) \frac{\delta}{a} + E^{2D} (q^3 a) \left(\frac{\delta}{a} \right)^3 \quad 8-1$$

where F is the applied force, δ is the membrane deflection, σ^{2D} is the pretension in the film, $q = 1.02$ is a constant, E^{2D} is the elastic modulus, and a is the radius of the membrane. Some preliminary experiments show that the 2D effective elastic modulus of pristine graphene membranes is about 83 ± 11 N/m, which is lower than the intrinsic elastic modulus of graphene (340 N/m). However, the elastic modulus increases to 212 ± 18 N/m after the graphene membranes were exposed to EUV irradiation, although Raman spectroscopy indicates defects generated in graphene. This could be caused by the hydrocarbon deposition on graphene membranes after EUV exposure.

Several other issues should be addressed here. The influence of defects on graphene's other properties, such as thermal and mechanical strength, should be understood. And, to eliminate cracks or holes and minimize the defect density in graphene within the pellicle lifetime, a protection layer could be applied on both sides of the graphene membrane, thereby excluding reactions between water and graphene. However, the thermal, chemical and optical properties of this new sandwiched structure should also be investigated. The number of graphene layers which can be used for pellicle applications is also still under investigation. Generally, graphene with more than 10 layers is considered to be graphite (for which the properties are well known), and each layer of graphene will absorb 0.2% of EUV light per pass. Another topic which is under investigation is the growth of graphene layers with a size of 110 x 140 mm². Single crystal graphene is preferred to meet the EUV transmission non-uniformity requirements and preserve other physical properties, e.g., mechanical strength, thermal conductivity, etc. Polycrystalline graphene can meet the EUV transmission non-uniformity requirements, however, the grain size has to be on the order of sub microns. At the same time, the thermal conductivity may decrease because of scattering at grain boundaries. A new PhD project has been granted for continuing with investigation on these topics.

Figure 8-4 Schematic view of graphene-Si based pellicle. There are 9 layers of Si, each 5 nm thick. In between, a monolayer of graphene is deposited. The pellicle is capped by SiNx on both sides. Note that the exact number of layers, the Si layer thickness, and the capping material can still be optimized for EUV transmission.

In the end, we propose a new concept for an EUV pellicle, based on graphene-Si composites. This pellicle consists of alternating poly-silicon layers and monolayer graphene with SiN_x capping layers, as shown in **Figure 8-4**.

Single layer graphene is known as one of strongest materials with a tensile strength of 130 GPa and a Young's modulus of 1 TPa.¹ Owing to its two dimensional geometry and high mechanical strength, graphene has the potential to be a strength enhancer in composites. Youbin Kim *et al.*, reported that a nano-layered composite consisting of alternating layers of metal (Cu or Ni) and monolayer graphene showed a increased mechanical strength.² The graphene layers here are used to block dislocation propagation across the metal-graphene interface. In a similar manner for our pellicle design, graphene is used to strengthen the poly-silicon membranes, preventing cracking. Besides, the high thermal conductivity and ultra-low interfacial thermal resistance between graphene and metals could be an important advantage in thermal management.³ The embedded graphene layers in pellicles can be used to dissipate heat to increase the maximum thermal load of the pellicle. Manufacture of such a pellicle is technically challenging. Here we propose two ways of fabricating such a pellicle, which are indicated in **Figure 8-5** and **Figure 8-6**, respectively. Both are capable of producing full size pellicles (142 x 118 mm²), and have advantages and disadvantages.

Figure 8-5 The "PMMA transfer" method for producing a multilayer graphene/Si pellicle.

Figure 8-6 The "direct growth" method.

The “PMMA transfer” method, as shown in **Figure 8-5**, uses mature technologies: graphene grown by chemical vapor deposition on a Cu substrate, followed by transferring to a Si substrate. These techniques are commercially well established.⁴⁻⁶ However, transferring process using PMMA will introduce undesired particles, wrinkles, or even cracks.⁶ In contrast, the “direct growth” method grows graphene directly on Si within the same sample preparation chamber, and no PMMA transferring process is needed, thus, eliminating particles, wrinkles or cracks in graphene. The main challenge of this method is to grow high quality single layer graphene on a Si substrate. Only few studies were reported on graphene growth on Si, in which the quality of the graphene

with respect to the defect density and grain size needs to be improved to fulfill the requirements for pellicle applications.^{7, 8} This type of graphene-based pellicle will be investigated in the future.

8.3 Conclusion

Valorization aspects in Extreme UV photolithography are generally of a complex, interdisciplinary nature. They require research of an exploratory nature at the boundary of technology. To mitigate particle contamination on the reticle in EUVL systems, we have explored two strategies: photoluminescence-based inspection and a graphene-based pellicle. The photoluminescence-based inspection method can detect organic particles all down to 25 nm, Al particles 100nm, and stainless steel particle 2 μm . Therefore, it requires further improvement to be applied as a Reticle Inspection Module (RIM) in EUVL systems. We have noticed that although this technique is aimed at inspection of EUV reticles, it can also be applied to detect particle contamination on nano-imprint templates, where the contaminant particles are mainly organics. Research related to EUV pellicles showed that defects appear in graphene after exposure to EUV irradiation. Nevertheless, it may still be possible to make a graphene-based pellicle by combining graphene with other protection layers or by using graphene as strengthening layers in a composite.

8.4 References:

1. C. Lee, X. Wei, J. W. Kysar and J. Hone, "*Measurement of the elastic properties and intrinsic strength of monolayer graphene*", Science **321** (5887), 385-388 (2008).
2. Y. Kim, J. Lee, M. S. Yeom, J. W. Shin, H. Kim, Y. Cui, J. W. Kysar, J. Hone, Y. Jung and S. Jeon, "*Strengthening effect of single-atomic-layer graphene in metal-graphene nanolayered composites*", Nature Communications **4** (2013).
3. Q. Liang, X. Yao, W. Wang, Y. Liu and C. P. Wong, "*A three-dimensional vertically aligned functionalized multilayer graphene*"

architecture: an approach for graphene-based thermal interfacial materials", ACS nano **5** (3), 2392-2401 (2011).

4. S. Chen, W. Cai, R. D. Piner, J. W. Suk, Y. Wu, Y. Ren, J. Kang and R. S. Ruoff, "*Synthesis and characterization of large-area graphene and graphite films on commercial Cu–Ni alloy foils*", Nano Letters **11** (9), 3519-3525 (2011).

5. J.-H. Lee, E. K. Lee, W.-J. Joo, Y. Jang, B.-S. Kim, J. Y. Lim, S.-H. Choi, S. J. Ahn, J. R. Ahn and M.-H. Park, "*Wafer-scale growth of single-crystal monolayer graphene on reusable hydrogen-terminated germanium*", Science **344** (6181), 286-289 (2014).

6. A. Reina, X. Jia, J. Ho, D. Nezich, H. Son, V. Bulovic, M. S. Dresselhaus and J. Kong, "*Large area, few-layer graphene films on arbitrary substrates by chemical vapor deposition*", Nano Letters **9** (1), 30-35 (2008).

7. D. Wei and X. Xu, "*Laser direct growth of graphene on silicon substrate*", Applied Physics Letters **100** (2), 023110 (2012).

8. M. Suemitsu and H. Fukidome, "*Epitaxial graphene on silicon substrates*", Journal of Physics D: Applied Physics **43** (37), 374012 (2010).

Chapter 9 Summary

Extreme UV photolithography is scheduled to be the next generation lithography method which is used in semiconductor manufacturing. To ensure that the original chip pattern is printed with high fidelity, EUV lithography masks, or ‘reticles’, require a clean environment. Small particles, e.g. from the EUV light source, dust or mechanical wear parts, are present in the system and need to be prevented, detected, and cleaned. The acceptable number and size of particles on the reticle during exposure is decreasing while the size demand is typically 25 nm (spherical equivalent diameter) and less. This demanding situation requires the development of new technologies. Two of the most perspective are explored in this thesis: *in situ* reticle inspection, and protecting the reticle from particles using a membrane, or ‘pellicle’.

In this study, we propose a comparison-free inspection technique to detect particle contamination on the reticle of EUV lithography systems, based on the photoluminescence spectral characteristics of the contaminant particles. Our primary experiments focus on determining the photoluminescent yield of typical particles found on reticles. An inspection setup for EUV reticles has been designed, built, and characterized. The photoluminescent spectrum from critical contaminant particles, obtained from exposed EUV reticles, namely organic (hydrocarbon), Al, and stainless steel particles, has been characterized. Based on experimental results, where the photoluminescent spectrum from organic particles with a size of 100 nm was obtained, it was estimated that down to 25 nm particles are detectable. For Al particles, the smallest particle detected was 350 nm. It was found, however, that not all the Al particles were photoluminescent. Based on the average photoluminescence yield, the minimum detectable Al particle size was estimated 100 nm. The

photoluminescence spectrum from stainless steel particles was only detected from stainless steel coatings. The estimated minimum detected particle size was approximately 2 μm . Finally, we note that the inspection method proposed here can be applied not only for inspecting EUV reticles, but also for detecting particle contamination on nano-imprint structures or templates.

Pellicles, a second subject explored in this thesis, are widely used in lithography to shield reticles from particles. Conventional pellicles are not suitable for EUV lithography due to their high absorption. Several investigations of Si-based pellicles were reported, but they suffer from imaging performance degradation, and unmanageable heat loads. Recently, there has been renewed interest in EUV pellicles because advances in 2D materials, such as graphene, have provided materials with more suitable mechanical and thermal properties. The chemical stability of graphene during EUV exposure is not yet fully understood, while one of the aspects which is of importance for lifetime considerations. Multi-layer and single layer graphene on different substrates (Ni, Cu, SiO_2), as well as suspended single-layer graphene, were investigated in this thesis. Results show that defects are created during EUV irradiation. The experimental data demonstrate that, under EUV radiation in the presence of residual water, oxidation occurs, resulting in the graphene being etched, and forming cracks and holes, due to dissociation of water by EUV. In addition, the defect density was found to be proportional to the water partial pressure in the exposure chamber.

By introducing a physical barrier (consisting of naturally accumulated hydrocarbons) between the graphene and the residual gas, it was found that EUV photons still generate defects in graphene. To understand if the defects are photon-generated, or electron-generated, an electron gun was used to mimic the photoelectrons flux (3.7 eV-80 eV) generated by the photons. Depending on the flux and electron energy, an increase in defects was observed, compared to unexposed graphene. However, this defect density was not dependent on the water partial pressure. It was concluded that low energy electrons (photoelectrons) can directly break sp^2 bonds in graphene, which will induce defects.

Based on our experimental data, we have shown that EUV photons, EUV induced photoelectrons can all generate defects in graphene. And we conclude that at the relatively high water partial pressure (10^{-5} mbar) in the exposure chamber, water vapor dissociated by EUV, is the main source of defects. The results shown here are of critical importance for the lifetime of graphene-based pellicles. Considering our exposure conditions, it is estimated that under the conditions in a real EUVL system with an EUV intensity of 250 W/cm^2 , and required lifetime of 315 hrs, a significant increase in defect density can be expected, leading to possible degradation of the performance required for a pellicle, e.g., transmission uniformity, thermal conductivity and mechanical strength.

On the above two topics on EUVL defect sensitivity, current key mechanisms were identified and explored in this thesis, with onsets to further materials development.

Samenvatting

Extreem Ultraviolet fotolithografie wordt alom gezien als de nieuwe methode voor het fabriceren van halfgeleiderstructuren. Om er zeker van te zijn dat het originele chippatroon met een hoge reproduceerbaarheid kan worden geprint, moeten de maskers voor EUV-lithografie (ook aangeduid als ‘reticles’) zich in een zeer schone omgeving bevinden. In de lithografiemachine kunnen kleine deeltjes aanwezig zijn, afkomstig van bijvoorbeeld de EUV lichtbron of van aan slijtage onderhevige mechanische onderdelen. Het ontstaan van deze deeltjes dient zoveel mogelijk te worden vermeden, en resterende deeltjes moeten worden gedetecteerd en geëlimineerd. Het toelaatbare aantal alsmede de grootte van de deeltjes op het reticle tijdens de belichting wordt voortdurend lager. Typisch ligt die grens bij 25 nm. Deze veeleisende specificaties maken het noodzakelijk om naar nieuwe technieken te kijken. Twee van de meest veelbelovende oplossingen worden in dit proefschrift nader bestudeerd: *in situ* detectie van deeltjes op het reticle en het gebruik van een beschermend membraan, ook wel ‘pellicle’ genoemd, dat voor het reticle wordt geplaatst.

Allereerst is gekeken naar een vergelijkingsvrije inspectietechniek om deeltjes op een EUV-reticle te detecteren. Deze techniek is gebaseerd op het karakteristieke fotoluminescentiespectrum van de contaminatiedeeltjes. Onze eerste experimenten hebben zich vooral gericht op het bepalen van de mate van fotoluminescentie van deeltjes die typisch op reticles worden gevonden. Om deze inspectiemethode van EUV reticles mogelijk te maken is een experimentele opstelling ontworpen, geïnstalleerd en gekarakteriseerd.

Het fotoluminescentiespectrum van kritieke contaminatiedeeltjes, nl. organische (koolwaterstoffen), aluminium en roestvrijstaal (RVS) deeltjes, is gekarakteriseerd. Op basis van deze experimentele resultaten,

Summary

---

waarbij het fotoluminescentiespectrum van organische deeltjes met een afmeting van 100 nm met succes is bepaald, zouden deeltjes groter dan 25 nm detecteerbaar moeten zijn. De kleinste aluminiumdeeltjes die gedetecteerd konden worden, waren 350 nm. Hierbij moet echter opgemerkt worden dat niet alle aluminiumdeeltjes fotoluminescent waren. Op basis van de gemiddelde fotoluminescentie-opbrengst is de detectielimiet voor aluminiumdeeltjes vastgesteld op ongeveer 100 nm. Het fotoluminescentiespectrum van RVS-deeltjes is alleen gedetecteerd op RVS coatings. De geschatte detectielimiet van deze deeltjes is 2 micrometer.

De hierboven genoemde inspectiemethode is niet beperkt tot het inspecteren van EUV-reticles maar leent zich ook voor het detecteren van contaminatiedeeltjes op nano-imprint-structuren of patronen.

Het tweede onderwerp dat in dit proefschrift wordt beschreven zijn masker-membranen, ook pellicles genoemd. Bij fotolithografie worden deze gebruikt om het reticle-oppervlak te beschermen tegen contaminatie. Voor EUV-lithografie kunnen conventionele pellicles niet worden gebruikt vanwege hun hoge mate van absorptie van het EUV-licht. Verschillende op silicium gebaseerde pellicles worden in de literatuur genoemd, maar deze veroorzaken veelal degradatie van de afbeelding en zijn vaak onvoldoende bestand tegen de thermische belasting. De laatste jaren echter is er opnieuw interesse gekomen in het ontwikkelen van EUV pellicles door de vooruitgang in het fabriceren van 2D-materialen zoals grafeen. Grafeen heeft namelijk uitstekende thermische en mechanische eigenschappen voor de omgeving waarin een EUV-pellicle wordt geplaatst. Over de chemische stabiliteit van grafeen onder EUV-straling is echter nog weinig bekend, hoewel dit voor de levensduur een belangrijk punt is. In dit proefschrift zijn daarom multi- en enkellaags grafeen op verschillende substraten (Ni, Cu en SiO₂) en vrijstaand opgespannen enkellaags grafeen onderzocht. De resultaten laten zien dat EUV-straling defecten aan het grafeen kan veroorzaken. Uit de experimenten volgt dat water (wat altijd in kleine hoeveelheden als restgas aanwezig is) dissocieert onder invloed van EUV-straling en het grafeen oxideert. Dit kan vervolgens leiden tot het ontstaan van scheuren en gaten of het wegetsen van grafeen. De

defectdichtheid is hierbij afhankelijk van de partiële druk van waterdamp in de vacuümkamer waarin het grafeen is blootgesteld aan EUV-straling.

Zelfs wanneer een barrière, bestaande uit natuurlijk geaccumuleerde koolwaterstoffen, tussen het grafeen en het achtergrondgas aanwezig is, bleek het mogelijk voor EUV-fotonen om defecten in het grafeen te veroorzaken. Om te begrijpen of deze defecten veroorzaakt worden door fotonen of elektronen is een elektronenkanon gebruikt om het effect van een foto-elektronenflux (3.7-80 eV) na te bootsen. Afhankelijk van de flux en de elektronenergie is er een toename in het aantal defecten geobserveerd in vergelijking met grafeensamples die niet zijn blootgesteld. In dit geval was de dichtheid van de defecten onafhankelijk van de partiële druk van waterdamp. Hieruit kan geconcludeerd worden dat elektronen met lage energie (foto-elektronen) direct de sp^2 -bindingen in grafeen kunnen verbreken, hetgeen resulteert in defecten.

Gebaseerd op deze experimentele gegevens hebben we laten zien dat zowel EUV-fotonen als EUV-geïnduceerde foto-elektronen defecten in grafeen kunnen veroorzaken. Ook kunnen we concluderen dat een relatief hoge partiële druk van waterdamp in de vacuümkamer (10^{-5} mbar) hiervoor een belangrijke oorzaak is: het EUV-licht kan water dissociëren, wat vervolgens het grafeen kan oxideren. Deze resultaten zijn van groot belang voor de levensduur van een op grafeen gebaseerd pellicle. Afgaande op de intensiteit van de EUV-bron in ons systeem, kan voor een realistisch EUVL systeem met een gespecificeerde EUV-intensiteit van 250 W/cm^2 en een levensduur van 315 uur voor het pellicle een significante defectdichtheid verwacht worden. Deze defecten kunnen leiden tot bijvoorbeeld verlaagde thermische geleiding, mechanische sterkte of uniformiteit in de transmissie van het EUV-licht.

In dit proefschrift zijn de twee bovengenoemde aspecten van deeltjescontaminatie in EUVL onderzocht. Dit heeft inzicht in de belangrijkste mechanismen opgeleverd en geeft daarnaast een startpunt voor de ontwikkeling van nieuwe materialen.

Acknowledgement

First and foremost, I would like to thank my promoter prof. Fred Bijkerk for providing me the opportunity to carry out the PhD research. He has taught me how an excellent experimental physicist should behave. I really appreciate his contributions of time, ideas, and funding to make my PhD life productive and stimulating.

I have been fortunate to have Chris Lee as my daily supervisor. Thanks to his great supervision, I could overcome and avoid the difficult times during my PhD. I was a conservative person, and it is Chris who lets me understand the importance and necessity of risk in scientific research. I really enjoyed all the discussions we have for the projects. He always explains explicitly in an easy understanding way, regardless that it is simply physics or complex quantum mechanics. To me, he is an excellent example of successful scientist, who I admire greatly.

I would also like to express my gratitude to my supervisors from ASML: Vadim Banine, Luigi Scaccabarozzi, and Pedro Rizo Diago. Thanks to your guidance, I could easily and quickly pick up the research topics at the beginning to the project. And also thank you for helping me comfortably and actively involved in the activities of ASML research department, without feeling ignored as the first and lonely person to work in ASML from our institute. I want to say thank you to Luigi Scaccabarozzi especially, not only for the help in scientific research but also for helping me overcome the difficult times in my personal life. I would also thank other colleagues in ASML, Andrey Yakunin for bringing me on board to ASML first as an intern, Edgar Osorio for useful discussions and support with experiments, Maarten van Kampen for the discussions and clearance of publications. Last but not least, I truly thank our Lab Masters Goran Milinkovic, Luc Stevens, and John de Kuster for all the support of lab administration, experiments, sample preparation, programming, building setups...etc.

Acknowledgement

My PhD fellow colleagues Rogier van de Bos, Malgorzata Pachecka, Feng Liu, and Baibhav Mund are a group of young, enthusiastic, and supportive people. I really enjoy working atmosphere both in the lab and office. I will not forget the jokes we made with each other, the places we have been to together, and the activities we have participated. At DIFFER and University of Twente, I want to thank Marko Sturm for AFM, XPS measurements and correcting papers and thesis; Erwin Zoethout for useful and inspiring discussions of the graphene experimental results. My thanks also go to our secretaries Melanie van der Vlis, Jolanda van Achthoven, and Jacqueline Emmerich for all the administration work.

My special thanks go to Shouen Zhou in TU Delft for preparing graphene samples, Jan-Willem Webber, Rene Vervuurt for Raman characterization.

Life is not only about physics, thanks to my friends Yin Sun, Ying Hua, Jiaqi Shen, Zhengjie Lu, Qixiao Yu, Shangxia Song, Xiao Ma, Feng Liu, Fei Liu, my stay at Eindhoven is enjoyable. I would also thank our basketball group for letting me have the chance to continue playing basketball.

At last, my family is always supportive and encouraging to me during my PhD. I would thank my parents who raised me with love and supported me in all my pursuits. I would also thank my girlfriend Ruiju Gao who supports and encourages me during the thesis writing and job hunting.

My four years' PhD life consists of joy, excitement, satisfactory as well as depression and disappointment. I have been fortunate to have all of you around. Without you I could not complete my PhD. Thank you all!

An Gao
ASML, Veldhoven
August 2014

Curriculum Vitae

An Gao was born on Nov. 25, 1984 in Qingdao, Shandong, China. From 2004 to 2008, he studied Microelectronics at Fudan University. After graduation, he went to the Netherlands and pursued his master degree in Nanotechnology at University of Twente. At the end of his master study, he carried out an internship at ASML Research with focusing on lifetime study of spectral purity filter. In October 2010, he started his PhD research at Nanolayer Surfaces and Interfaces department of FOM Institute for Plasma Physics Rijnhuizen. During his PhD period, he worked closely to the ASML research department, and most of the research was carried out in the ASML Research Lab. The PhD research was supervised by Prof. F. Bijkerk and Dr. C.J. Lee, and a selection of the results are presented in this thesis.